



HAL
open science

Modulated magnetic structure in ^{57}Fe doped orthorhombic YbMnO_3 : a Mössbauer study

Mathieu Duttine, Alain Wattiaux, Félix Balima, Claudia Decorse, Hicham Moutaabbid, Dominic H. Ryan, Pierre Bonville

► **To cite this version:**

Mathieu Duttine, Alain Wattiaux, Félix Balima, Claudia Decorse, Hicham Moutaabbid, et al.. Modulated magnetic structure in ^{57}Fe doped orthorhombic YbMnO_3 : a Mössbauer study. *AIP Advances*, 2019, 9 (3), pp.035008. 10.1063/1.5077005 . hal-01866145

HAL Id: hal-01866145

<https://hal.science/hal-01866145v1>

Submitted on 29 Nov 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Modulated magnetic structure in ^{57}Fe doped orthorhombic YbMnO_3 : a Mössbauer study

MATHIEU DUTTINE, ALAIN WATTIAUX, FELIX BALIMA
CNRS, Université de Bordeaux, ICMCB, UPR 9048
33600 Pessac, France

CLAUDIA DECORSE
ICMMO, Université Paris-Sud, Université Paris-Saclay
91405 Orsay, France

HICHAM MOUTAABBID
IMPMC, Sorbonne Universités - UPMC, CNRS, IRD, MNHN
75005 Paris, France

PIERRE BONVILLE*
SPEC, CEA, CNRS, Université Paris-Saclay, CEA-Saclay
91191 Gif-sur-Yvette, France

November 8, 2021

Abstract

In the orthorhombic manganites $o\text{-RMnO}_3$, where R is a heavy rare earth (R = Gd-Yb), the Mn^{3+} sublattice is known to undergo two magnetic transitions. The low temperature phase has an anti-ferromagnetic structure (collinear or elliptical), which has been well characterized by neutron diffraction in most of these compounds. The intermediate phase, occurring in a narrow temperature range (a few K), is documented for R = Gd-Ho as a collinear modulated structure, incommensurate with the lattice spacings. We report here on a ^{57}Fe Mössbauer study of 2% ^{57}Fe doped $o\text{-YbMnO}_3$, where the spin only Fe^{3+} ion plays the role of a magnetic probe. From the analysis of the shape of the magnetic hyperfine Mössbauer spectra, we show that the magnetic structure of the intermediate phase in $o\text{-YbMnO}_3$ ($38.0\text{ K} < T < 41.5\text{ K}$) is also modulated and incommensurate.

*Contact author: pierre.bonville@cea.fr

Keywords: Modulated magnetic structures, Orthorhombic manganites, Mössbauer spectroscopy

1 Introduction

The physics of the orthorhombic (or perovskite) rare earth manganites o-RMnO_3 , where R is a rare earth ion, is governed by the interplay of various interactions: the largest is the Jahn-Teller effect on the $3d^4 \text{Mn}^{3+}$ ion, which can lead to orbital ordering; the interionic exchange interaction, which leads to magnetic ordering; and the magneto-electric coupling which couples ferroelectric order and magnetic order in certain given circumstances (for a review, see Ref.[1]). Due to the present interest in multiferroic phenomena, i.e. acting on magnetic moments *via* an electric field (or vice-versa) [2], the precise determination of the lattice and magnetic properties of these interesting materials, and of their interplay, is of prime importance.

The magnetic phase diagram of the orthorhombic rare-earth manganates has been thoroughly established in Ref.[3] by means of specific heat measurements. For the naturally occurring perovskite phases (R = La-Gd), a single magnetic transition, due to ordering of the Mn moments, is observed. Its critical temperature T_{N1} decreases with the rare earth radius. For Eu and Gd however, a second transition occurs at $T_{N2} > T_{N1}$. The same happens for all the heavier rare earth manganates, for which the orthorhombic phase is metastable. It is obtained through high pressure annealing of the naturally occurring hexagonal phase. Regarding the ground magnetic structure of o-RMnO_3 , neutron diffraction studies determined it to be of antiferromagnetic (AF) collinear A-type for R=La-Gd [4, 5], of transverse spiral type for R = Tb and Dy [6, 7] and of AF collinear E-type for R = Ho [8]. In TbMnO_3 and DyMnO_3 , the spiral magnetic order is accompanied by a ferroelectric order and a large magneto-electric effect [2, 4]. In HoMnO_3 , the E-type order also bears ferroelectricity [9]. The structure of the intermediate phase ($T_{N1} < T < T_{N2}$) is documented only for R = Gd-Ho, where it was shown to be incommensurate sine-wave modulated [8]. The Néel temperature T_{N1} characterizes therefore a lock-in transition below which the magnetic structure becomes commensurate with the lattice spacing.

For the last rare earths of the series, the ground magnetic structure has been determined only for R = Yb [10]: it is of AF E-type, but the structure of the intermediate phase has not yet been elucidated. By analogy with what occurs for R = Gd-Ho, it is expected to be incommensurate modulated. A Mössbauer spectroscopy study of ^{57}Fe doped o-YbMnO_3 , with the isotopes ^{57}Fe and ^{170}Yb , was performed in Ref.[11], but could not reach a definitive conclusion about the structure of the intermediate phase.

We have performed a ^{57}Fe Mössbauer investigation of this material, doped at a 2% level with ^{57}Fe , and by analyzing the shapes of the spec-

tra in the intermediate phase, we show they are compatible with a collinear incommensurate modulated type. Recently, we have shown the feasibility of this method by analyzing the incommensurate magnetic phases in FeVO_4 by Mössbauer spectroscopy [12] (see also Ref.[13]).

2 Sample preparation and magnetic measurements

2.1 Sample preparation and characterisation

The hexagonal polymorph $\text{h-YbMn}_{0.98}\text{Fe}_{0.02}\text{O}_3$ was prepared as polycrystalline powder by solid state reaction. Oxides Yb_2O_3 , MnO_2 and Fe_2O_3 of at least 99.99% purity were used as precursors. The iron oxide was enriched in the ^{57}Fe isotope up to 95.5%.




Figure 1: Full-pattern matching (Le Bail) analysis of XRD patterns ($\text{Cu-K}\alpha_1\text{K}\alpha_2$) in 2% ^{57}Fe -doped h-YbMnO_3 (a) and o-YbMnO_3 (b). Black dots: experimental data, red line: calculated pattern, blue line: arithmetic difference between observed and calculated data, green marks: Bragg positions.

Stoichiometric quantities of the starting materials were thoroughly mixed and ground together, then pressed into pellets and heated up to 950°C ,

in air, for 12h. After an intermediate grinding, the mixture was pressed again into pellets and further heated at 1100°C for 48h in air, which completed the synthesis. According to the powder x-ray diffraction pattern (see Fig.1 **a**), the h-YbMnO₃ sample was single phase, with $a=b=6.068(1)$ Å and $c=11.364(1)$ Å.

The orthorhombic phase of YbMnO₃ was prepared by heating the hexagonal phase h-YbMnO₃ under high pressure. The powder was packed into a platinum capsule surrounded by pyrophyllite (a good pressure transmitter and thermal insulator) and heated at 1100° (ramp rate 40°/min) during 40 min under an applied pressure of 5 GPa. The XRD pattern is entirely compatible with the orthorhombic Pnma space group (see Fig.1 **b**), with lattice parameters (with the Pnma setting) : $a = 0.57988$ nm, $b = 0.73094$ nm and $c = 0.52197$ nm, in good agreement with published values [10, 11]. The Bragg peaks are narrow, showing negligible nonstoichiometry.

2.2 Magnetic susceptibility

The polycrystal magnetic susceptibility was measured with a field of 20 G in the temperature range 5 - 70 K. It shows a monotonic decrease as temperature rises, with a tiny accident around 40 K (see Fig.2).




Figure 2: Thermal variation of the magnetic susceptibility $\chi(T)$ in o-YbMnO₃ doped with 2% ⁵⁷Fe, in a field of 20 G. The inset shows the derivative of $\chi(T)$.

The structure of the accident is better revealed by the derivative $d\chi/dT$ shown in the inset of Fig.2. As temperature is decreased, one observes a jump at 41.5 K, which is therefore identified as T_{N2} , the transition temperature to the intermediate phase, and a maximum at 38 K, which is identified as T_{N1} , the transition temperature to the collinear E-type AF phase. Thus, in our o-YbMnO₃ sample, the intermediate magnetic phase occurs in the

range $38.0\text{ K} < T < 41.5\text{ K}$. These boundaries match rather well the T_N value of 43 K reported in Ref.[10] and the two values $T_{N1} \simeq 36\text{ K}$ and $T_{N2} \simeq 40\text{ K}$ inferred from Ref.[3], showing that the intermediate phase transition temperatures vary slightly from sample to sample.

3 Mössbauer measurements

The Mössbauer spectra were recorded with a linear velocity electromagnetic drive on which is mounted a commercial $^{57}\text{Co}^*:\text{Rh}$ γ -ray source. A standard liquid He cryostat with temperature regulation was used.

3.1 The Electric Field Gradient tensor

o-YbMnO_3 crystallizes into the orthorhombic space group Pnma , where the Mn 4b-site has triclinic C_i point symmetry. Fe substitutes for Mn in the doped material, and since Fe^{3+} and Mn^{3+} have approximately the same radius (0.645 \AA), one can reasonably assume that the Fe site is not appreciably distorted with respect to the Mn site. On this basis, the authors of Ref.[11] have performed a Point Charge Model calculation using the o-YbMnO_3 crystal parameters in order to obtain the Electric Field Gradient (EFG) tensor V_{ij} (principal axes and diagonal values) at the Fe/Mn site. This tensor is needed in order to evaluate the quadrupole hyperfine interaction which characterizes the Mössbauer spectrum in the paramagnetic phase. It has zero trace and it is usually determined by two quantities: V_{ZZ} , where OZ is the principal axis and $\eta = \left| \frac{V_{YY} - V_{XX}}{V_{ZZ}} \right|$.

The splitting ΔE_Q of the spectral doublet observed in the paramagnetic phase, due to the electric quadrupolar hyperfine interaction with the $I=3/2$ excited nuclear state of ^{57}Fe , with quadrupole moment $Q=0.21$ barn, is given by:

$$\Delta E_Q = \frac{eQV_{ZZ}}{2} \sqrt{1 + \frac{\eta^2}{3}}. \quad (1)$$

The experimental value $\Delta E_Q \simeq 1.54\text{ mm/s}$, obtained above 43 K in Ref.[11] as well as in the present work (not shown), is in rather good agreement ($\Delta E_Q \simeq 1.59\text{ mm/s}$) with the Point Charge calculation of Ref.[11], which also yields $\eta=0.175$. Furthermore, the ordered Mn^{3+} magnetic moment lies along the orthorhombic \mathbf{a} axis in the low temperature E-type collinear AF phase [10]. The impurity Fe moment and the hyperfine field, proportional to the moment for Fe^{3+} , are expected to lie along \mathbf{a} as well. The Point Charge calculation of Ref.[11] has determined the values of the polar and azimuthal angles of the hyperfine field (the \mathbf{a} axis) in the Electric Field Gradient frame: $\theta \simeq 37.8^\circ$ and $\varphi \simeq 270^\circ$.




Figure 3: ^{57}Fe Mössbauer spectra in $o\text{-YbMnO}_3\text{:Fe}$ at selected temperatures. The fits, shown by a solid red line, are as explained in the text.

3.2 Mössbauer spectra in the magnetic phases

Selected spectra are represented in Fig.3, in the ground collinear E-type phase at 4.2 K, and for three temperatures inside the intermediate phase: 38.1, 39.1 and 40.3 K. They are in good agreement with those in Ref.[11].

The spectra show no significant variation in the ground E-type phase, between 4.2 K and 36 K, revealing the presence of a single magnetic hyperfine field, in agreement with the magnetic structure determination of a collinear single moment AF structure [10], with moments directed along the \mathbf{a} axis. A good fit is obtained using the quadrupolar parameters and the polar and azimuthal angles of the hyperfine field determined in Ref.[11]. The hyperfine field at 4.2 K is 44.3 T, a value lying at the lower end of the typical range

for Fe^{3+} in insulators (50 ± 5 T).




Figure 4: In the presence of a sine-wave modulated collinear magnetic structure: **a** Distribution of hyperfine fields at the Fe site, with a maximum value of 38 T; **b** Simulated ^{57}Fe Mössbauer spectrum in the presence of this distribution.

Above 38 K, in the intermediate phase, the spectra show a drastic change: the lines broaden and the resonant absorption strongly increases in the center of the spectrum, i.e. near zero velocity. At 40.3 K, the spectrum is an almost featureless asymmetric doublet. These characteristics point to the presence of a distribution of hyperfine fields with a rather strong weight near zero and low values. Generally speaking, in a magnetically ordered phase, this very specific feature is generated in a Mössbauer spectrum solely by an incommensurate collinear magnetic structure, like that observed in FeVO_4 in the intermediate magnetic phase, for $15.7\text{K} < T < 23\text{K}$ [12]. Other types of incommensurate orderings (for instance elliptical) do not yield an enhanced weight near zero hyperfine field.

The distribution corresponding to a collinear incommensurate sine-wave modulation of hyperfine fields is shown in Fig.4 **a**, for a maximum hyper-

fine field of 38 T, and the associated simulated spectrum, with the same quadrupolar parameters and orientation of the hyperfine field as determined for o-YbMnO₃:Fe, in Fig.4 **b**. Comparison of the simulated spectrum in Fig.4 **b** and of the experimental spectra in the intermediate phase of o-YbMnO₃:Fe at 38.1 K and 39.1 K shows a clear similarity: not only, as mentioned above, the presence of a large spectral weight at the center of the spectrum, but also the left-hand central line being broader than the right-hand one. There is however an important difference: the outer and intermediate lines in the simulation of Fig.4 **b** have an asymmetric shape, whereas those in the spectra are rather symmetrically broadened. Such a broadening could be caused by hyperfine field fluctuations, but the two other spectral features mentioned above clearly cannot, thus excluding relaxation effects as a cause for the observed peculiar spectral shapes.

The simulated spectrum in Fig.4 **b** actually corresponds to the case of a modulated magnetic structure in a pure material, where there is only one sort of magnetic ion, like in FeVO₄. In o-YbMnO₃:Fe, we observe the spectrum of Fe impurities whose presence in the matrix must entail a small perturbation of the magnetic structure of the matrix Mn ions. Furthermore, we assume that the Mn magnetic structure is locally reflected in the magnitude of the Fe impurity magnetic moment, hence of the hyperfine field at the Fe site. This assumption means that a low level substitution of the $3d^4$ Mn³⁺ ion by a $3d^5$ Fe³⁺ ion does not essentially perturb the superexchange interaction, but it is reasonable to consider that it can somehow blur the modulation of the Fe moments all over the sample.

For these reasons, we have fitted the spectra in the intermediate phase using the four following assumptions:

- i) the quadrupole interaction tensor is fixed to its value at 4.2 K.
- ii) the magnetic structure is collinear incommensurate, yielding a modulated variation for the Fe moment, and the Mn/Fe moment direction, hence that of the hyperfine field, is along the **a** axis, i.e. it is the same as in the collinear E-type ground structure.
- iii) the modulation is described by a Fourier expansion up to the 3 first (odd) harmonics, as a function of the abscissa x along the propagation vector **k**:

$$H_{hf}(kx) = \sum_{p=0}^2 h_{2p+1} \sin[(2p+1)kx], \quad (2)$$

in order to account for possible deviations from the pure sine-wave.

- iv) a small random deviation from the modulated value exists at each site, which accounts for potential defects of the incommensurate structure reflected at the impurity site. This deviation has the form: $\delta H_{hf} = x \Delta H_{hf}$, where x is chosen at random in the interval $[0;1]$ and ΔH_{hf} is a parameter which must be fitted to the lineshape. The mean value of the deviation is therefore $\sigma = \frac{1}{2} \Delta H_{hf}$.




Figure 5: Fitted hyperfine field (or moment) modulations in the intermediate phase of o-YbMnO₃:Fe at 38.1 K, 39.1 K and 40.3 K showing the random deviations from the nominal modulation with their mean value σ .

The spectra in the intermediate phase have been successfully fitted this way, as witness the red solid lines in Fig.3. The corresponding hyperfine field (or moment) modulations as shown in Fig.5. At 38.1 K, just above $T_{N1} = 38.0$ K, the modulation is somewhat squared, and 3 harmonics are needed to reproduce the spectral shape: $h_1 = 38.0$ T, $h_3 = 4.32$ T and $h_5 = 0.80$ T. At 39.1 K, in the middle of the intermediate phase, the modulation is close to pure sine wave with $h_1 = 31.2$ T. At these two temperatures, the mean value of the deviation from the modulation amounts to $\simeq 6\%$ of the maximum hyperfine field. At 40.3 K, just below $T_{N2} = 41.5$ K, the first harmonics has decreased to $\simeq 11$ T and the mean value of the deviation is rather large: $\sigma \simeq 6.2$ T, so that the magnetic hyperfine structure has almost disappeared, leaving an asymmetric doublet with a broad base.

4 Conclusion

Using ⁵⁷Fe Mössbauer spectroscopy, we have shown that the lineshapes in the intermediate magnetic phase ($38.0 \text{ K} < T < 41.5 \text{ K}$) of orthorhombic

YbMnO₃ (doped with 2% ⁵⁷Fe) are compatible with a collinear incommensurate magnetic structure. The Fe hyperfine field, and hence the Mn spontaneous moment, has the same direction as in the ground E-type AF phase, i.e. the crystal **a** axis. The modulation is mainly sine-wave, but we could detect some “squaring” just above the lock-in transition. Since this type of magnetic structure has been found for the intermediate phase in orthorhombic RMnO₃ with R = Gd-Ho [4, 5, 6, 7, 8], we think our Mössbauer spectra demonstrate its presence also in orthorhombic YbMnO₃. Since Mössbauer spectroscopy is a local microscopic technique, it cannot determine the wave vector of the modulation, and this should be done by neutron diffraction.

Acknowledgments

We thank the “Service Synthèses Hautes Pressions” of the ICMCB (Bordeaux) for the preparation of the orthorhombic YbMnO₃ sample.

References

- [1] Shuai Dong and Jun-Ming Liu 2012 *Modern Physics Letters B* **26** 1230004
- [2] Kimura T, Goto T, Shintani H, Ishizaka K, Arima T and Tokura Y 2003 *Nature (London)* **426** 55
- [3] Tachibana M, Shimoyama T, Kawaji H, Atake T and Takayama-Muromachi E 2007 *Phys. Rev. B* **75** 144425
- [4] Goto T, Kimura T, Lawes G, Ramirez A P and Tokura Y 2004 *Phys. Rev. Lett.* **92** 257201
- [5] Kimura T, Ishibara S, Shintani H, Arima T, Takahashi K T, Ishizaka K and Tokura Y 2003 *Phys. Rev. B* **68** 060403(R).
- [6] Kenzelmann M, Harris A B, Jonas S, Broholm C, Schefer J, Kim S B, Zhang C L, Cheong S W, Vajk O P and Lynn J W 2005 *Phys. Rev. Lett.* **95** 087206
- [7] Arima T, Tokunaga A, Goto T, Kimura H, Noda Y and Tokura Y 2006 *Phys. Rev. Lett.* **96** 097202
- [8] Muñoz A, Casáis M T, Alonso J A, Martínez-Lope M J, Martínez J L and Fernández-Díaz M T 2001 *Inorg. Chem.* **40** 1020
- [9] Lorenz B, Wang Y Q and Chu C W 2007 *Phys. Rev. B* **76** 104405

- [10] Huang Y H, Fjellvåg H, Karppinen M, Hauback B C, Yamauchi H and Goodenough J B 2006 *Chem. Mater.* **18** 2130, and Erratum 2007 *Chem. Mater.* **19** 2139
- [11] Stewart G A, Salama H A, Voyer C J, Ryan D H, Scott D and StC. O'Neill H 2015 *Hyperfine Interact.* **230** 195
- [12] Colson D, Forget A and Bonville P 2015 *J. Magn. Magn. Mat.* **378** 529
- [13] Sobolev A V, Presnyakov I A, Rusakov V S, Gapochka A M, Glazkova Ya S, Matsnev M E and Pankratov D A 2017 *J. Exp. Th. Physics* **124** 943