

Computational micromechanics: a variational derivation of FFT-based schemes

Pierre Suquet, Jean-Claude Michel

▶ To cite this version:

Pierre Suquet, Jean-Claude Michel. Computational micromechanics: a variational derivation of FFTbased schemes. International workshop in honor of Dominique Jeulin, Jun 2018, Oléron, France. hal-01901253

HAL Id: hal-01901253 https://hal.science/hal-01901253

Submitted on 22 Oct 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Computational micromechanics: a variational derivation of FFT-based schemes

J.C. Michel and P. Suquet

Laboratoire de Mécanique et d'Acoustique Aix Marseille Univ, CNRS, Centrale Marseille, LMA, Marseille, France

It is a well-established result in the theory of linear composites that the local fields in such materials satisfy an integral equation which can be written symbolically as (Kröner, 1972; Willis, 1981; Milton, 2002; Jeulin, 2005)

$$\left(\boldsymbol{I} + \boldsymbol{\Gamma}^0 \boldsymbol{\delta} \boldsymbol{L}\right) \boldsymbol{\varepsilon} = \boldsymbol{E},\tag{1}$$

where $\boldsymbol{\varepsilon}$ is the local field under investigation, \boldsymbol{E} is its average, Γ^0 is the Green's operator associated with a homogeneous reference medium \boldsymbol{L}^0 and $\boldsymbol{\delta} \boldsymbol{L} = \boldsymbol{L} - \boldsymbol{L}^0$ is the deviation of the actual material properties of the composite from the homogeneous reference medium. As recognized by Kröner, this integral equation has the same form as the Lippmann-Schwinger (LS) equation in scattering theory.

The resolution of (1) requires the inverse of $\mathbf{I} + \Gamma^0 \boldsymbol{\delta} \mathbf{L}$. One of the earlier method to perform this inversion iteratively is based on a fixed point method:

$$\boldsymbol{\varepsilon}^{(k+1)} = -\boldsymbol{\Gamma}^{0}\boldsymbol{\delta}\boldsymbol{L}\boldsymbol{\varepsilon}^{(k)} + \boldsymbol{E}, \ i.e. \ \boldsymbol{\varepsilon}^{(k)} = \sum_{j=0}^{k} \left(-\boldsymbol{\Gamma}^{0}\boldsymbol{\delta}\boldsymbol{L}\right)^{j} \boldsymbol{E}.$$
 (2)

This scheme with one of the phases as reference medium has been used by Brown (1955) to study the first few terms of the series and Moulinec and Suquet (1994) used an optimized reference medium, together with the discrete Fourier transform to turn the formal expansion (2) into an iterative computational scheme. Although the simple fixed point technique is quite efficient for composites with moderate contrast, it is sensitive to the choice of the reference medium and its convergence can be slow for materials with high contrast. Accelerated iterative methods have been proposed, and some of them have been used by D. Jeulin and his coworkers (Escoda et al., 2011). According to Mishra et al. (2016) conjugate gradient methods (see in particular Zeman et al., 2010; Gélébart and Mondon-Cancel, 2013) are among the most efficient existing techniques. However, as noted by these authors, the operator $\mathbf{I} + \Gamma^0 \delta \mathbf{L}$ is not a self-adjoint operator (the corresponding matrix for the discrete problem is not symmetric) since the operators Γ^0 and $\delta \mathbf{L}$ do not commute. So the use of biconjugate gradient methods is in principle required to solve (1).

The starting point of this study is the following question: *can the Lippmann- Schwinger operator be made self-adjoint by some magic?* The answer is "yes" (Schneider, 2017), the proof is elementary and relies on a simple change of scalar product (similar, but different from that used in Jeulin, 2005 p189).

The variational property of the LS equation opens new avenues for computational schemes. Its extension to constituents governed by one non-quadratic potential is straightforward. The extension to materials governed by two potentials relies on incremental variational principles (Mialon, 1986; Ortiz and Stainier, 1999; Bourdin et al., 2008; Michel and Suquet, 2016). Assume that the constitutive laws for each constituents can be written as:

$$\boldsymbol{\sigma} = \frac{\partial w}{\partial \boldsymbol{\varepsilon}}(\boldsymbol{\varepsilon}, \boldsymbol{\alpha}), \quad \frac{\partial w}{\partial \boldsymbol{\alpha}}(\boldsymbol{\varepsilon}, \boldsymbol{\alpha}) + \frac{\partial \varphi}{\partial \dot{\boldsymbol{\alpha}}}(\dot{\boldsymbol{\alpha}}) = 0, \tag{3}$$

where α denote a set of internal variables. Then, after time-discretization with an implicit scheme (backward Euler), the fields (strain and internal variables) solution of the local problem (expressing equilibrium of the stress field, compatibility of the strain field with appropriate boundary) at time t_{n+1} has the variational property :

$$(\boldsymbol{\varepsilon}_{n+1}, \boldsymbol{\alpha}_{n+1}) = \underset{\langle \boldsymbol{\varepsilon} \rangle = \bar{\boldsymbol{\varepsilon}}}{\operatorname{Argmin}} \operatorname{Argmin}_{\boldsymbol{\alpha}} \langle w(\boldsymbol{\varepsilon}, \boldsymbol{\alpha}) + \Delta t \varphi \left(\frac{\boldsymbol{\alpha} - \boldsymbol{\alpha}_n}{\Delta t} \right) \rangle.$$
(4)

This variational property is used to derive computational schemes for the class of composites described by (3) which are significantly faster than the usual schemes.

References

- Bourdin, B., Francfort, G. A., Marigo, J. J., 2008. The variational approach to fracture. Springer.
- Brown, W., 1955. Solid mixture permittivities. J. Chem. Phys. 23, 1514–1517, doi: 10.1063/1.1742339.
- Escoda, J., Willot, F., Jeulin, D., Sanahuja, J., Toulemonde, C., 2011. Estimation of local stresses and elastic properties of a mortar sample by FFT computation of fields on a 3D image. Cement and Concrete Research **41**, 542–556.
- Gélébart, L., Mondon-Cancel, R., 2013. Non linear extension of FFT-based methods accelerated by conjugate gradients to evaluate the mechanical behavior of composite materials. Computational Materials Science **77**, 430 439.
- Jeulin, D., 2005. Random structures in physics. In: Bilodeau M., Meyer F., S. M. (Ed.), Space, Structure and Randomness. Vol. 183 of Lecture Notes in Statistics. Springer-Verlag, pp. 183–222.
- Kröner, E., 1972. Statistical Continuum Mechanics. Vol. 92 of CISM Lecture Notes. Springer-Verlag, Wien.
- Mialon, P., 1986. Eléments d'analyse et de résolution numérique des relations de l'élastoplasticité. Tech. rep., EDF. Bulletin de la Direction des Etudes et recherches. Série C. Mathématiques, Informatique.

- Michel, J., Suquet, P., 2016. A model-reduction approach in micromechanics of materials preserving the variational structure of constitutive relations. J. Mech. Phys. Solids 90, 254–285, http://dx.doi.org/10.1016/j.jmps.2016.02.005.
- Milton, G., 2002. The Theory of Composites. Cambridge University Press, Cambridge.
- Mishra, N., Vondřejc, J., Zeman, J., 2016. A comparative study on low-memory iterative solvers for FFT-based homogenization of periodic media. Journal of Computational Physics 321, 151–168.
- Moulinec, H., Suquet, P., 1994. A fast numerical method for computing the linear and nonlinear properties of composites. C. R. Acad. Sc. Paris II **318**, 1417–1423.
- Ortiz, M., Stainier, L., 1999. The variational formulation of viscoplastic constitutive updates. Comput. Methods Appl. Mech. Engrg **171**, 419–444.
- Schneider, M., 2017. An FFT-based fast gradient method for elastic and inelastic unit cell homogenization problems. Comput. Methods Appl. Mech. Engrg. 315, 846–866, doi.org/10.1016/j.cma.2016.11.004.
- Willis, J., 1981. Variational and related methods for the overall properties of composites. In: Yih, C. (Ed.), Advances in Applied Mechanics 21. Academic Press, New-York, pp. 1–78.
- Zeman, J., Vondřejc, J., Novák, J., Marek, I., 2010. Accelerating a FFT-based solver for numerical homogenization of periodic media by conjugate gradients. Journal of Computational Physics 229 (21), 8065–8071.