



**HAL**  
open science

## Tannins extraction: A key point for their valorization and cleaner production

Pedro Luis de Hoyos-Martinez, Juliette Merle, Jalel Labidi, Fatima Charrier-El Bouhtoury

### ► To cite this version:

Pedro Luis de Hoyos-Martinez, Juliette Merle, Jalel Labidi, Fatima Charrier-El Bouhtoury. Tannins extraction: A key point for their valorization and cleaner production. *Journal of Cleaner Production*, 2019, 206, pp.1138-1155. 10.1016/j.jclepro.2018.09.243 . hal-01925978

**HAL Id: hal-01925978**

**<https://hal.science/hal-01925978v1>**

Submitted on 27 Nov 2018

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

## **Tannins extraction: a key point for their valorization and cleaner production**

**Pedro L. de Hoyos-Martínez<sup>1,2</sup>, Juliette Merle<sup>2</sup>, Jalel Labidi<sup>1</sup>, Fatima Charrier – El Bouhtoury<sup>2\*</sup>**

<sup>1</sup> *Chemical and environmental engineering department, University of the Basque Country, Plaza Europa, 1, 20018, Donostia-San Sebastián, Spain.*

<sup>2</sup> *CNRS/UPPA PAU & PAYS ADOUR/ E25 UPPA, Institute of Analytical Sciences and Physico-Chemistry for Environment and Materials (IPREM), IUT des Pays de l'Adour, 371 Rue de Ruisseau, 40004 Mont de Marsan, France*

### **\*Corresponding author:**

Fatima Charrier - El Bouhtoury: [fatima.charrier@univ-pau.fr](mailto:fatima.charrier@univ-pau.fr)

### **Abstract:**

Tannins are phenolic compounds with considerable abundance in nature. They have attracted significant attention lately owing to their huge variety of potential applications. Accordingly, the tannin-related activity in terms of research has undergone a great boost, especially as green feedstock for materials in several fields. Nevertheless, the extraction process remains as the main bottleneck for their valorization, due to their heterogeneous nature. In the present review, a comprehensive study of the main types of tannins extraction techniques was carried out based on the works from the last 20 years. The literature review was carried through analysis of an initial sample of works followed by snowballing process, obtaining the main extraction parameters of each method. Thereby, the different tannins extraction methods were assessed and their major strengths and weaknesses elucidated. Moreover, a direct comparison between the different techniques was done, leading to the main perspectives for the efficient and clean tannins extraction and production.

**Keywords:** tannin, polyphenols, novel extraction techniques, green production

**Abbreviations:** GA-gallic acid, HHDP-hexahydroxyphenic acid, EA-ellagic acid, SLE-Solid-liquid extraction, HWE-hot water extraction, SFE-supercritical fluid extraction, PWE-pressurized water extraction, MAE-microwave assisted extraction, UAE-ultrasound assisted extraction.

### **Highlights:**

- The great potential of tannins is hindered by their extraction process
- A literature review was carried out assessing the main tannins extraction methods
- Novel extraction techniques represented a greener option for tannins production
- Combination of novel techniques is an interesting option for industrial scale up

## 1 1. INTRODUCTION

2 Tannins are the most abundant components extracted from biomass, after cellulose,  
3 hemicelluloses and lignin (Arbenz and Avérous, 2016). Besides, they represent the second most  
4 extensive source of phenolic compounds after lignins (Laurichesse and Avérous, 2014).

5 Among the vegetal kingdom, tannins are extensively well distributed in both terrestrial and  
6 aquatic environments (Barbehenn and Peter Constabel, 2011). Terrestrial tannins, can be found  
7 in tropical, arid and semi-arid areas but also in other regions, like Atlantic or Mediterranean ones  
8 (Balogun et al., 1998; Jackson et al., 1996). They are present in high concentrations in several  
9 species such as *Schinopsis balansae* (quebracho wood), *Acacia mearnsii* (black mimosa bark),  
10 *Pinus radiata* and *Pinus nigra* (pine species), *Quercus spp* (oak bark.) and *Castanea sativa*  
11 (chestnut wood). They are also found in considerable amounts in various seeds (cocoa, guarana,  
12 kola, areca) and leaves (hamamelis, green tea) (Bele et al., 2010; Lochab et al., 2014). They are  
13 visibly present too in everyday life products like tea or wine (Mattivi et al., 2009). On the other  
14 hand, in aquatic environments tannins occur in smaller extent and prominently in non-vascular  
15 plants such as algae (Kirke et al., 2017).

16 Tannins major features are derived from their phenolic nature. For instance, their antioxidant  
17 capacity is linked to the phenolic rings present in their structure, which can act as electron  
18 scavenger to trap ions and radicals. Owing to this antioxidant nature, tannins are widely utilized  
19 in different areas such as the pharmaceutical, medical or food industry (Chen et al., 2016; Ismail  
20 et al., 2016; Park et al., 2014). Tannins phenolic character makes them a potential source of  
21 products in the chemical industry as well, as substituent in phenolic resins for several applications  
22 (Chupin et al., 2015; Jahanshahi et al., 2012; Ramires and Frollini, 2012).

23 This abundance in nature and variety of applications have encouraged a growing tendency in the  
24 tannins-related research in the last 20 years (figure 1).

25 Accordingly, they are considered an attractive family of compounds in terms of potential  
26 applications and environmental friendliness. However, one important aspect of tannins is their  
27 heterogeneous nature which makes impossible to settle a universal method for their extraction  
28 (Hagerman, 1988). The yield, purity and composition of the extracts rely normally on several  
29 parameters such as the vegetal source, technique employed, extraction time, temperature etc.  
30 (Bacelo et al., 2016). Thereby the extraction of tannins from vegetable residues is a process, which  
31 constitutes a crucial keypoint for their reuse, valorization and their sustainable production (Bacelo  
32 et al., 2017).

33 In the literature there have already been efforts towards the analysis of the phenolic compounds  
34 extraction from plants by different methods (Khoddami et al., 2013; Xu et al., 2017). However,  
35 plants polyphenols include a vast range of compound such as flavonoids, phenolic acids, tannins,  
36 stilbenes and lignans. For this reason, these works usually lack of specificity concerning the  
37 results given. This review was focus only on the extraction of tannins and therefore the results

1 were provided in terms of specific tannin amounts or tannin equivalents. Moreover, the discussion  
2 and evaluation of the different methods presented is exclusively oriented to the tannins cleaner  
3 production.

4 This study aims to describe the evolution of the existing methods for tannin extraction through a  
5 comprehensive critical literature review. A detailed comparison between the different techniques  
6 was carried out. The main strengths and weaknesses of each methodology are presented,  
7 providing a better understanding in the matter and the future lines for the tannins cleaner and more  
8 efficient manufacture.

9 The work structure is divided in several parts. After the introduction, section 2 is presented  
10 covering a brief state of the art on the field of tannins related to the tannin extraction. Then section  
11 3, describes the methodology employed for carrying out this research. Section 4 displays the main  
12 results related to tannins extraction by the different methods, an in-depth comparison between  
13 them and a full discussion of the major advantages and disadvantages of each one. The study is  
14 concluded with the main outcomes and future perspectives.

## 15 **2. BACKGROUND**

### 16 **2.1. Tannin definition**

17 The “tannin” definition has its origin in the primary function of this group of compounds i.e.  
18 tanning. The tanning process has been important along history since it allowed the protection of  
19 animal skins turning them into leather by means of plant extracts. The first species reported for  
20 tanning leather was oak, which was actually designated with the name “tann” among the Celts  
21 (Arapitsas, 2012; Frutos et al., 2004).

22 One of the first tannins definitions was given by A. Seguin in 1796, who described them as  
23 substances in vegetable extracts used for converting animal skins into stable leather (Bele et al.,  
24 2010). Nevertheless, it was not until the early 1960s that a more accurate definition of tannin was  
25 introduced by Swain and Bate-Smith in 1962. They defined tannins as “*naturally occurring water*  
26 *soluble polyphenolic compounds having a molecular weight between 500 and 3000, capable of*  
27 *precipitating alkaloids as well as gelatin and other proteins from aqueous solutions*”(Bate-Smith  
28 and Swain, 1962). This definition is the one most frequently found and cited within the literature

### 29 **2.2. Tannin classification**

30 The categorization of tannins based on their structural aspects and chemical characteristics is the  
31 most extended, since it offers a proper framework for further study. Traditionally, tannins were  
32 divided into two major classes namely condensed and hydrolysable tannins. However, currently  
33 two other types are also considered i.e. complex tannins and phlorotannins.

34 Chemically, condensed tannins are defined as polymeric flavonoids (Hagerman, 2002). However,  
35 they can appear as oligomers as well, when they are composed of two to ten monomeric units

1 (Haslam, 2007). In the form of polymeric flavonoids they have limited to no solubility in water,  
2 whereas in oligomeric form they are water soluble (Bennick, 2002). Within the flavonoids group,  
3 condensed tannins are considered as flavanols, since they are composed of flavan-3-ol moieties  
4 (figure 2) (Dai and Mumper, 2010).

5 The flavan-3-ols units can display different structures depending on the type of *A* and *B* rings  
6 present. *A* ring can appear as a phloroglucinol or resorcinol moieties (McGraw, 1989), whereas *B*  
7 ring can be arranged as a catechol or pyrogallol units. These combinations lead to the formation  
8 of several monomers of condensed tannins (table 1).

9 The compounds showed in table 1 are the precursors of various types of condensed tannins. In  
10 this sense, the condensed tannins whose structure is exclusively composed of (epi)catechins are  
11 designated as procyanidins. These are the most abundant type present in plants (Hümmer and  
12 Schreier, 2008). On the other part, those tannins mainly formed by (epi)fisetinidol,  
13 (epi)robinetinidol and (epi)gallocatechin units, are labelled as profisetinidin, prorobinetidin and  
14 prodelphinidin respectively.

15 Hydrolysable tannins are heteropolymers composed of polyphenolic acids and their derivatives,  
16 esterified to a polyol (Frutos et al., 2004). This polyol, generally a carbohydrate, forms a central  
17 core to which several polyphenolic acid units are attached via ester bonds (figure 3).

18 Gallic acid (GA) is the most basic block attached to the core of the monomeric units (Hernes and  
19 Hedges, 2004). Gallic acid moieties can yield other derivatives such as hexahydroxydiphenic acid  
20 units (HHDP), via oxidative coupling of two or more molecules (Hartzfeld et al., 2002). In turn,  
21 the HHDP units can spontaneously lactonize to ellagic acid (EA) moieties upon hydrolysis  
22 (Landete, 2011). In figure 4, the transformation between the different polyphenolic acids, which  
23 can be present in hydrolysable tannins structure are showed.

24 The distinctive property of hydrolysable tannins is their ability of being fractionated  
25 hydrolytically into their basic components. This is due to their ester bonds, which are susceptible  
26 to break via hydrolysis under acidic and basic conditions. Thereby, they are usually classified  
27 into two main subcategories i.e. gallotannins and ellagitannins.

28 *Gallotannins*: they represent the simplest kind of hydrolysable tannins and consist of  
29 galloyl or digalloyl units linked to a polyol core and therefore they have the ability to yield  
30 gallic acid from the hydrolysis reaction.

31 *Ellagitannins*: this kind of tannins are characterized by having one to several HHDP units  
32 attached to a polyol core. Upon hydrolysis, ellagitannins are able to produce HHDP free  
33 units, which spontaneously turn into the dilactone (ellagic acid).

34 Another type of tannins out of the traditional tannin classification is complex tannins. This kind  
35 is characterized by the present of monomeric units of hydrolysable and condensed tannins (Hatano  
36 et al., 1991). They are composed of a gallotannin or ellagitannin moiety and a flavan-3-ol building

1 block connected through a carbon-carbon linkage. This type represents a minority group within  
2 the tannins family. A typical example of this kind of compounds is acutissim A (figure 5).  
3 The other type of tannins discovered in the recent years is phlorotannins. This group is  
4 prominently found in brown algae and is composed of phloroglucinol units (1,3,5-  
5 trihydroxybenzene). The research carried out lately on this group of tannins, has led to the  
6 structural elucidation of more than 150 compounds with a large range of molar masses between  
7 126-625000 g·mol<sup>-1</sup> (Glombitza and Pauli, 2003; Lopes et al., 2012; Sathya et al., 2017).  
8 Structurally phlorotannins form dehydro-oligomers and polymers of phloroglucinol moieties  
9 linked via aryl-aryl (C-C) and diaryl ether bonds (C-O) (Koivikko et al., 2008).  
10 Considering the previous information, it is clear tannins can display a variety of structures  
11 resulting in diverse chemical compositions. This aspect, which discussed in the next point, is of  
12 considerable importance, since it can have a direct impact over the extraction efficiency.

### 13 **2.3. Tannins abundance and occurrence in nature**

14 In nature, tannin content depends on several aspects such as the plant part and species considered.  
15 Within the same species, the tannin content is reported to vary between the different parts with  
16 special abundance in barks, leaves, seeds, roots and rhizomes (Bele et al., 2010). In addition, their  
17 content can also vary with seasonal and environmental factors e.g. water availability, temperature,  
18 light intensity and soil quality (Frutos et al., 2004). These points have a relevant importance, since  
19 they can influence the results of the different extraction methods. In the literature, there are several  
20 works assessing the effect of different species and plant parts on the tannin extraction results  
21 (Geoffroy et al., 2017; Tabaraki et al., 2013). In this sense, it was reported by Cheng et al. (2012)  
22 that the variety of the grape employed significantly influenced the amount of tannins quantified  
23 in the extracts (Cheng et al., 2012). They found that the extracts of the variety *Pinot Noir* presented  
24 higher amount of tannins (gallic acid equivalents) than *Pinot Meunier*. This was attributed to the  
25 different viticultural practices and environmental conditions. Moreover, the amount of tannins  
26 was higher in the seeds compared to skin and pomace. In another work, tannins from different  
27 spices were extracted via microwave and ultrasound and significant differences regarded. Again,  
28 the variety of spice was confirmed to have a major role. Thus, the extraction for *Crocus sativus*  
29 resulted in a tannin amount thirty times higher than that of *Coriandrum sativum* (Gallo et al.,  
30 2010). Besides, the spices were reported to provide higher tannin amounts in the extracts by means  
31 of microwave assisted extraction than ultrasound.

32 Regarding tannin chemical composition, species have a direct influence as well. It has been  
33 reported that different plants species display diverse physico-chemical properties, derived from  
34 the distinct types of tannins present (Mangan, 1988). In the previous section, it was discussed that  
35 the different type of tannins can lead to various chemical compositions, based on their structure.  
36 Thus depending on the species, diverse types of tannins could be extracted and therefore the  
37 tannin composition of the extracts would be different. A research carried out by Bianchi et al.

1 (2015), proved that the tannin composition of the extracts from different wood barks species  
2 extracted under the same conditions showed several divergences (Bianchi et al., 2015). Thereby,  
3 a predominant amount of prodefininidins was determined in Silver fir, whereas a higher amount of  
4 procyanidins was found for European Larch. They reported too, that the tannins composition of  
5 these species substantially differ from those of tropical species such as Mimosa and Quebracho.  
6 This divergences were also displayed on another work on tannin extraction from the seeds of  
7 different varieties of grapes (Mattivi et al., 2009). The results showed significant variations  
8 between the major tannin monomers present in the different grape species.

### 9 **3. METHODS AND RESEARCH DESIGN**

10 In this section, the different steps followed for carrying out the bibliographic review are showed,  
11 including the search, selection and analysis of articles and limitations.

12 In the preparation of this review, two bibliographic databases were selected: Scopus and Web of  
13 science (all databases). Scopus is reported to cover more than 21500 journals from social, life,  
14 health and physical sciences (Elsevier, 2016) whereas Web of science includes over 12000  
15 different journals from science, arts and humanities (Thomson Reuters, 2013). For this reason,  
16 these two directories were chosen since they are said to comprise the major part of the articles  
17 related to the topic of tannins cleaner production. The selection of the published works was refine  
18 by selecting different subjects of interest. A previous search based on the topics of tannin  
19 definition, classification and distribution in nature was carried out to provide some background  
20 on the field (section 2). Then, the main search linked to the major topic of this work i.e. extraction  
21 of tannins was performed. First, general information was seeked about each technique to introduce  
22 the main principles of the extraction methods. Afterwards, the results from each method (main  
23 extraction parameters) were searched, aiming the comparison between the different techniques  
24 and the assessment of their major strengths and weaknesses (section 4).

#### 25 **3.1. Choice of search terms and selection of articles**

26 Regarding the major topic, a general bibliographic search was firstly made by using the search  
27 string [tannin AND extraction]. This search produced approximately 4500 hits, from which the  
28 main methods of tannin extraction and production were obtained. The selection of the different  
29 methods was based on the search of keywords in the articles titles and abstracts (e.g. *ultrasound*  
30 *assisted extraction*, *solvent extraction*, *pressurized water extraction*). Then, a narrower search  
31 (based on these terms) was done focusing specifically on each extraction technique and giving a  
32 considerable smaller number of hits. The parameters employed for this search are presented in  
33 table 2. All the hits given in this table, were scanned by their titles, abstracts and keywords. Then  
34 the most relevant articles were imported to the Mendeley© reference management system. From  
35 this sample, the articles were sorted into eight different categories:

- 1 1) Conventional tannins extraction with organic solvents
- 2 2) Tannins extraction with hot water
- 3 3) Tannins extraction with ionic liquids
- 4 4) Tannins extraction with supercritical fluids
- 5 5) Tannins extraction with pressurized hot water or subcritical water
- 6 6) Tannins extraction assisted by microwave
- 7 7) Tannins extraction assisted by ultrasound
- 8 8) Comparison of tannins extraction with several extraction methods

9 The articles that did not belong to any category or that were duplicated in a previous category  
10 were removed. To this sample of selected and categorized articles, a semi structured snowballing  
11 approach followed (Wohlin and Claes, 2014). Thus, it was possible to add to our sample works  
12 that were not found in the previous search and categorization (figure 6).

### 13 **3.2. Method of analysis and limitations of research**

14 The final sample of articles was analysed by thoroughly examine their content (specially the  
15 results and discussion section). Thus, bibliometric information about the main extraction  
16 parameters was gathered and summarized for each article. These parameters include the plant  
17 species extracted, conditions of extraction (temperature, pressure and times), solvents involved,  
18 extraction yields and tannin content of the extract. The data collected was analysed to discuss the  
19 main results and tendencies and to compare the divergences between the extraction methods.

20 Regarding the limitations of the review, it was decided to focus mainly on peer-reviewed articles  
21 written in English. The period of time selected was comprising the last 20 years of research on  
22 the field (between 1997-2018).

## 23 **4. RESULTS AND DISCUSSION**

24 Within this section, the main parameters of the tannin extraction methods are presented and  
25 examined. A comprehensive comparison between the different techniques is intended as well.

### 26 **4.1. Extraction parameters for each extraction process**

27 Here the conditions used and the yields obtained for each extraction procedure are presented  
28 according to the sample of papers selected from the literature. The aim is the identification of the  
29 strengths and weaknesses of each method and the influence of the different parameters over the  
30 process.

#### 31 **4.1.1. Solid-liquid extraction (SLE)**

32 This section is devoted to the extraction of tannins exclusively based on the contact between a  
33 solvent and a solid matter, without any further assisting mechanism. During this kind of  
34 extraction, the solvent penetrates into the cell wall of the feedstock containing the tannins. Then,  
35 they are dissolved and taken out in the form of extracts (Mailoa et al., 2013). This is the simplest



1 and most traditional method employed for tannins extraction. Within this part, several types of  
2 solvents are studied namely organic solvents, aqueous solutions, water and ionic liquids.

3 Concerning the use of organic solvents and their aqueous solutions, the extraction is commonly  
4 carried out by means of a soxhlet apparatus whose experimental extraction procedure has been  
5 described in several works (Jensen, 2007; Luque de Castro and Priego-Capote, 2010). However,  
6 other techniques are also employed and reported in the literature such as infusion or maceration.

7 The extraction with water can be carried out under reflux or through simple maceration in flasks  
8 or vessels. At the industrial scale it is generally performed on wood barks by percolation or open  
9 diffusion (Ciesla, 1998; Myers, 1998).

10 The extraction with ionic liquids is an alternative based on the substitution of the traditional  
11 solvents with these new liquids, which are known for having unusual combination of properties  
12 such as negligible vapour pressure, high thermal stability and dissolution of a broad range of  
13 compounds present in plants (Olivier-Bourbigou et al., 2010).

14 In table 3 is presented a sample of works from the literature devoted to solid-liquid extraction  
15 with the previously commented solvents. In regards to these results, it is seen that a considerable  
16 percentage of recovery of extracts is achieved by this method. The content of tannins in the  
17 extracts is reported to be high as well and can reach even to yields of 96% (grams of reactive  
18 tannins per gram of extract) (Vázquez et al., 2001). However, the results presented are influenced  
19 by several parameters. Within these parameters, the nature of the solvent employed for the  
20 extraction is regarded to be of significant importance. It is reported that the extraction yields  
21 increase with the solvent polarity (Markom et al., 2007). Accordingly, high extraction yields are  
22 generally obtained using water or methanol as solvent whereas poor extraction efficiencies are  
23 achieved with hexane (Widyawati et al., 2014). The employment of water is normally preferred,  
24 especially at the industrial scale owing to environmental reasons. Nevertheless, the solution of  
25 tannins in water generally leads to acidic pHs (Vieira et al., 2011). Under these conditions, the  
26 formation of insoluble precipitates due to tannin self-condensation reactions is promoted, limiting  
27 the extraction efficiency (Sealy-Fisher and Pizzi, 1992). The addition of certain amounts of  
28 NaOH% is proposed as an alternative to overcome this problem, since it is capable of improving  
29 the extraction yields (Chupin et al., 2013). Similarly, the use of salts like sodium carbonate  
30 ( $\text{Na}_2\text{CO}_3$ ) and sodium bisulfite ( $\text{NaHSO}_3$ ) is able to increment the extraction efficiency and to  
31 lower the high viscosity of the extracts derived from the tannin self-condensation reactions  
32 (Panamgama, 2007). In both cases, the increment of extraction yields is related to the alteration  
33 of the pH. Alkaline pH values are reported to increase the percentage of extracts, owing to the  
34 partial break of pyran rings in phlobaphenes (tannin-derived compounds). It has been presented  
35 in a recent work, that even the change of pH from neutral to slightly alkaline values can lead to  
36 higher extraction yields (Lochab et al., 2014). Moreover, a relationship between the base  
37 concentrations and the extraction yields is observed. The use of higher percentages of these

1 components is proved to reach higher extraction yields compared to lower concentrations (Antwi-  
2 Boasiako and Animapauh, 2012; Inoue et al., 1998). Nevertheless, the increment of the  
3 concentrations can provide a lower tannin content in the extracts due to the raise of undesirable  
4 non-tannin components (Ping et al., 2011). For this reason, the indiscriminate increase of the  
5 alkaline compounds and salts concentrations is not desirable. Different works were found  
6 underlining the importance of employing moderate amount of these compounds (Aires et al.,  
7 2016; Vieira et al., 2011).

8 Regarding the tannin content in the extracts, methanol and ethanol provide the best results (do  
9 Prado et al., 2014; Widyawati et al., 2014). For instance, it is stated in a work about  
10 anthocyanidins extraction from *Phyllanthus niruri*, that methanol and ethanol are more suitable for  
11 performing the extraction compared to water (Kaur and Kaur, 2016). This is due to the fact that  
12 these organic solvents have more similar characteristics to anthocyanidins.

13 The use of aqueous solutions of organic solvents has proved its efficiency as well, providing both  
14 considerable extraction yields and levels of tannins in the extracts (Vijayalaxmi et al., 2015;  
15 Widyawati et al., 2014). Besides, they present the advantage of being able to regulate the polarity  
16 of the solvent by adjusting the ratio of both components.

17 Compared to already mentioned solvents, ionic liquids represent a novel type still under  
18 development for tannins extraction. Despite this fact, they have already proved to achieve  
19 comparable or even better results than water (Chowdhury et al., 2010). Among this type of  
20 solvents, the imidazolium-based ionic liquids are said to be preferred and their concentrations  
21 have a direct influence on the results. It is reported that the increase of this parameter provides  
22 higher tannins extracted until certain point where not further improvement is regarded (Z. Liu et  
23 al., 2016; Lu et al., 2012). For this reason, the concentration of the ionic liquid is normally  
24 optimized. Another relevant factor in the tannins extraction with these solvents, is the alkyl chain  
25 length of the cation linked to the ionic liquid. It is presented that the increase of the alkyl chain  
26 length decrease the surface tension and increment the hydrophobic nature and viscosity (Ćurko et  
27 al., 2017). Thus, the ionic liquid can have a stronger interaction with the tannins extracting higher  
28 amounts. Above butyl chains, this effect is reported to be the opposite. Consequently, the alkyl  
29 chain length of the cations is also further optimized within the different studies.

30 Apart from the solvents nature, other parameters are regarded to have a major influence over the  
31 results namely temperature of extraction, time of extraction and solid to liquid ratio.

32 Concerning the time of extraction, it is seen that the increment of this parameter provides a higher  
33 content of tannins extracted as presented in some of the works from literature (Baldosano et al.,  
34 2015; Chowdhury et al., 2010). This is due to the longer times the solute and the solvent are in  
35 contact, which favours the mass transfer between both components. Nevertheless, the increase of  
36 the extraction times beyond certain values is not desirable. It was discussed by Tan et al. (2013)  
37 that the amount of tannins extracted above 4.5h was dramatically decreasing towards a minimum

1 (Tan et al., 2013). This was explained by the fact that an equilibrium was reached between the  
2 tannins concentration in the plant matrix and the solvent (Fick's law of diffusion), resulting in the  
3 slowdown of the extraction. Besides, at longer times the possibility of tannins degradation owing  
4 to the extraction conditions is enhanced.

5 The temperature of extraction is observed to increase the extraction yields as displayed in the  
6 results from table 3 (Kemppainen et al., 2014; Vázquez et al., 2001). This enhancement is due to  
7 the increase of the mass transfer coefficient at higher temperatures (Huang et al., 2016). Moreover  
8 the increment of the temperature results in the improvement of the solute solubility and diffusion  
9 coefficient and also decreases of solvent viscosity, which promotes the extraction (Al-Farsi and  
10 Lee, 2008). This parameter is normally regulated and optimized, since high temperatures can also  
11 lead to lower amount of tannins in the extracts as showed by Ramos et al. (2013) (Ramos et al.,  
12 2013). This was attributed to the denaturation of these compounds owing to the harsh conditions  
13 employed. The use of too high temperatures can also result in solvent evaporation. For this reason,  
14 in this kind of extraction the temperature is normally set up at the solvent boiling point.

15 Regarding ratio solid-liquid, it is showed that the decrease of this parameter provides higher  
16 extraction yields, since higher amounts of solvent are employed (Politi et al., 2011). Nevertheless,  
17 at low solid-liquid ratios, the differences between the extraction efficiencies are normally  
18 minimized and therefore this parameter is generally optimized at certain value.

19 To conclude, it can be remarked that the main general advantages of this method are its simplicity,  
20 efficiency and low cost. In the case of the extraction with hot water, it should be highlighted as  
21 well the fact that it can be successfully transferred to the industry, especially the extraction from  
22 wood barks (Amaral-Labat et al., 2013; Kemppainen et al., 2014). On the other hand, the major  
23 drawbacks of this method are the long times needed for the extraction, which can range from  
24 several hours to even several days, and the great amount of solvent normally employed. These  
25 disadvantages could be minimized by the use of ionic liquids, which display special properties  
26 favorable to the extraction (Hernández-Fernández et al., 2015). Nevertheless, the high prices of  
27 this novel solvents and the difficulty to recover the solute from the ionic liquid are still hindering  
28 their utilization.

#### 29 **4.1.2. Supercritical fluid extraction (SFE)**

30 In this part, the extraction of tannins by using supercritical fluids is presented. The principle of  
31 this method is based on the concept of critical point, which is defined as the highest temperature  
32 and pressure at which a pure substance can exist in a vapour-liquid equilibrium (Ajila et al., 2011).  
33 Above this point a fluid shares properties between a gas and a liquid, such as the typical weight  
34 of liquids with the penetration power of gases (Azmir et al., 2013). The works found in the  
35 literature related to this technique are presented in table 4. In regards to the presented results,  
36 various common characteristics are identified. The most widely employed solvent among all the  
37 works is carbon dioxide (CO<sub>2</sub>). This is due to its desirable properties such as non toxicity, non-

1 flammability, non-corrosive nature, availability and low critical temperature and pressure (31°C  
2 and 7.28 MPa) (Palmer and Ting, 1995; Talmaciu et al., 2016). The range of pressures and  
3 temperatures used within the different works for this fluid is between 10-65.5MPa for the former  
4 parameter and between 40-88°C for the later.

5 Concerning the extraction yields and tannins extracted, the parameter with the greatest influence  
6 is the utilization of a co-solvent. Thus, poor extraction yields are achieved using supercritical CO<sub>2</sub>  
7 alone whereas considerable enhancements are reported after the addition of a co-solvent  
8 (Cavalcanti et al., 2012; Conde et al., 2013). This is due to the non-polar nature of CO<sub>2</sub> as solvent  
9 and the polar nature of most of tannin compounds. The addition of co-solvents of polar nature  
10 such as ethanol, methanol or aqueous mixtures help ameliorating the solvating power of CO<sub>2</sub>  
11 towards tannins and improves the extraction yields. The pressure employed also presents a major  
12 role in the extraction efficiency and amount of tannins extracted. It is observed that the increment  
13 of the pressure promotes the extraction of tannins (do Prado et al., 2014). The reason for that is  
14 that at higher pressures the fluid density is increased, decreasing the distance between the  
15 molecules and therefore improving the interactions fluid-matrix (Maran et al., 2015).

16 Regarding the temperature of extraction, low values are said to be preferred. This parameter do  
17 not show though a crucial influence over the process, since most of the works do not report big  
18 differences in terms of extraction yields and amount of tannins extracted. However, it has been  
19 presented that higher temperatures can lead to lower amounts of tannins in the extracts  
20 (Luengthanaphol et al., 2004).

21 The main advantages concerning this extraction method are the utilization of mild temperatures  
22 and a nontoxic solvent (CO<sub>2</sub>) which can be easily removed and can avoid further oxidation  
23 reactions by creating an oxygen free environment. On the other side, one of the main drawbacks  
24 are the high investment costs, due to the high pressures needed for the extraction process (Perrut†,  
25 2000). The other main problem concerning CO<sub>2</sub> is its non polar nature, which reduces the  
26 extraction power towards tannins (low solubility of polar compounds). Consequently, the addition  
27 of co-solvents such as methanol, ethanol, acetone or water, becomes an essential requirement

#### 28 **4.1.3. Pressurized water extraction (PWE)**

29 This extraction method is based on the use of water as solvent at high pressures and temperatures,  
30 generally at subcritical conditions i.e. between its atmospheric boiling point (100°C, 0.1 MPa)  
31 and its critical point (374°C, 22.1 MPa). Within this range water is maintained in the liquid state  
32 but properties such as the polarity, viscosity, surface tension and disassociation constant are  
33 considerably lowered compared to water at ambient conditions (Liang and Fan, 2013). The  
34 reduction of these parameters enhances the mass transfer of the tannins from the feedstock matrix  
35 (Vergara-Salinas et al., 2013). Besides, under these conditions the ability to extract different types  
36 of compounds from this family is improved (Rangsiwong et al., 2009). The main difference with  
37 traditional solid-liquid extraction using hot water, is that pressurized water extraction utilizes

1 temperatures above the boiling point and pressures above the atmospheric to maintain water in  
2 liquid state.

3 The results related to this extraction method are presented in table 5. It is observed in most of the  
4 works, that the extraction was carried out at subcritical conditions (0.1-22 MPa, 100-374°C).  
5 Nevertheless, in some works pressures above the critical point are reported as well, to improve  
6 the results. A significant characteristic of this method is the reduction of the extraction times  
7 needed (5-60 minutes). Despite the short extraction times, high extraction yields are reported even  
8 up to  $\approx 70\%$  (Erşan et al., 2018). Furthermore, by adjusting the pressure and temperature of the  
9 solvent, its polarity can be modulated and a wide variety of tannins in significant amounts can be  
10 extracted depending on the source. For this reason, both variables present a significant influence  
11 in the extraction process.

12 The temperature plays a major role and its increment leads to higher extraction yields (Sousa et  
13 al., 2016). This effect is attributed to the fact that at higher temperatures the solvent is more easily  
14 diffused into the plant matrix. Moreover at higher temperatures the solute vapour pressure is  
15 incremented and it is easier for the solute to free itself from the matrix (Markom et al., 2010a).  
16 However, the employment of too severe temperatures was proved to have a negative effect,  
17 particularly on the tannin content of the extracts (García-Marino et al., 2006; Rangsiwong et al.,  
18 2009). This is associated to the possible degradation and denaturation of the different  
19 polyphenolic compounds at harsh temperatures (Vergara-Salinas et al., 2013).

20 Concerning the pressure, the influence on the water properties is little as far as it stays as a liquid  
21 (Plaza and Turner, 2015). For this reason, its effect on the results of extraction is normally lower.  
22 Despite this fact, the increase of this parameter can result in slightly higher extraction yields and  
23 tannin content in the extracts until certain pressure values (Aliakbariana et al., 2012). Above these  
24 pressure values the solvent solubility is not further improve and accordingly the extraction yields  
25 remain or even slightly decrease as well as the amount of tannin extracted (Markom et al., 2010a).  
26 The main advantages of this method are the reduced handling time and solvent consumption and  
27 the no utilisation of toxic organic solvents. Another advantage is the possibility to extract  
28 selectively tannins of different polarities by the modification of the temperature, pressure or co-  
29 solvent. On the other hand, the major disadvantages are related to the high temperatures and  
30 pressures used (reduction of the extraction selectivity and possible degradation of the analytes)  
31 and the expensive equipment required (solvent transporting pump, a pressure vessel and system  
32 controller, and a collection device for the extract needed).

#### 33 **4.1.4. Microwave assisted extraction (MAE)**

34 This method is based on the combination of the traditional solvents employed for tannins  
35 extraction and the fast heating in the microwave field. In some cases, the extraction process is  
36 ameliorated because both the solvent and the sample can be rapidly heated by direct interaction  
37 with electromagnetic radiation (depending on their dielectric characteristics). Another possibility

1 is the heating of one of the components by interaction with the other, previously heated by the  
2 microwave irradiation. The effect of heating on the solvent increases its solubility, whereas on  
3 the material it improves porosity allowing an easier penetration of the solvent (Routray and Orsat,  
4 2012). Thereby, in either case the extraction of tannins from the cell wall of the feedstock is eased.  
5 Within this section, a sample of papers focused on the tannins extraction assisted by microwave  
6 is displayed (table 6). From the previous results, it is remarked the short times needed for  
7 extraction (1-20 minutes), which achieved a significant level of tannin extraction. Regarding the  
8 solvent employed, the volume used for the extraction has a direct impact on the amount of tannins  
9 extracted. Normally a larger amount of solvent is supposed to achieve a higher quantity of tannins  
10 extracted, according to the principle of equilibrium between solvents and materials. In a work by  
11 Wang et al., 2010 (Wang et al., 2010), it was found that the increase of the solvent volume led to  
12 the enhancement of the tannins extracted until certain point (ratio 1:30) and then decreased. This  
13 was attributed to the relatively large amount of solvent employed, which resulted in a dilution of  
14 the amount of the tannins in the extracts (Guo et al., 2001; Xiao et al., 2008). The nature of the  
15 solvent also plays a major role on the extraction as was already mentioned in section 4.1.1  
16 Accordingly, the increase of the polarity of the solvent leads to higher amounts of tannins  
17 extracted (Pan et al., 2010). The effect of the microwave power was discussed in several works  
18 as well (Naima et al., 2015; Švarc-Gajić et al., 2013). It is proved that the increase of the power  
19 leads to higher amounts of tannins extracted. This is due to the enhancement of the solvent  
20 penetration into the matrix and the faster energy transfer to the solvent and material. However,  
21 above high values of microwave irradiation, the amount of tannins extracted is observed to  
22 decrease. Normally, this fact is due to the thermal degradation of the tannins, which results in a  
23 lower content of these compounds in the extracts (Dahmoune et al., 2015). It has been showed as  
24 well that too high microwave power can provide excess of energy to the solvent and material.  
25 This superfluous energy can generate abnormal molecular interaction, which affect the extraction  
26 yields of tannins (Jin et al., 2010). Consequently, this parameter is normally optimized in the  
27 majority of the works to achieve the highest amount of tannins recovered.  
28 The main advantages of this method are the employment of considerably short extraction times,  
29 and lower amount of solvents compared to traditional solid-liquid extraction. Another advantage  
30 is the agitation provided by the microwave irradiation, which can ameliorate the mass transfer  
31 phenomenon (Jain et al., 2013). The main disadvantages are the great costs of the equipment  
32 needed (specially at larger scale) and the possibility of thermal degradation of the feedstocks and  
33 tannins, especially those with high number of hydroxyl groups (Xu et al., 2017).

#### 34 **4.1.5. Ultrasound assisted extraction (UAE)**

35 The extraction of tannins by this technique is based on the formation, growth and collapse of  
36 micro bubbles inside a liquid phase submitted to ultrasonic cavitation (Chemat et al., 2011). The  
37 bubbles are induced by sound waves, with frequencies above 20 kHz, which cause mechanical

1 vibrations into the plant matrix. These mechanical vibrations, can rupture cell wall tissues  
2 ameliorating the penetration of the solvent into the matrix and achieving higher amounts of  
3 tannins extracted (Ali et al., 2018).

4 In this section, a sample of works related to the extraction of tannins assisted by ultrasound, is  
5 discussed (table 7). Within the works presented, the influence of several parameters on tannin  
6 extraction efficiency is observed. Again, the solvent employed has a prominent effect and  
7 therefore the use of more polar solvents leads to the improvement of the extraction yields.  
8 Nonetheless, it was reported that ethanol and methanol presented a higher selectivity to the  
9 polyphenolic compounds, providing higher amounts of tannins in the extracts (Dhanani et al.,  
10 2013; Tabaraki et al., 2013). Regarding the extraction times, not high values are needed to achieve  
11 good extraction yields (below 1hour). The increment of this parameter can lead to higher  
12 extraction yields and amount of tannin in the extract (Ivanovic et al., 2014). However, when the  
13 extraction time is incremented above relatively high values, the extraction efficiency tends to  
14 decrease. A first work by Dalzell and Kerven, (1998) showed that sonication after 30 minutes  
15 decreased the tannins extraction efficiency from *Leucaena* spp. This result was attributed to the  
16 possible degradation of the proanthocyanidins due to the increased temperature of the water bath,  
17 provided by the prolonged sonication time (Dalzell and Kerven, 1998). In another work, the  
18 decrease of the tannins extracted at high extraction times was associated to the prolonged interval  
19 of sonication and the possible degradation of the tannins as well but also to the lower  
20 concentration gradient of the solvent (Annegowda et al., 2012). A similar tendency is observed  
21 for the sonication power. Hence, the increase of this parameter provides higher amounts of tannins  
22 extracted until certain point and then began to decrease (Agarwal et al., 2018; Chavan and  
23 Singhal, 2013). This is due to the chemical decomposition of tannins extracted. Taking the  
24 previous phenomena into consideration, a further optimization of the conditions was carried out  
25 in most of the works presented.

26 The major advantages of this technique are the short extraction times employed and the fact that  
27 it is a simple and inexpensive extraction method (Khoddami et al., 2013). On the contrary, the  
28 main drawbacks are the lack of uniformity in the intensity of ultrasounds (maximum peak  
29 observed in the vicinity of radiating surface and decreasing with the distance to the source) and  
30 the reduction of the power with the time (Routray and Orsat, 2012).

#### 31 **4.2. Comparison of extraction methods**

32 In this section, a sample of works devoted to the analysis and assessment of various extraction  
33 methods for tannins extraction is presented. A comprehensive and direct comparison between the  
34 different techniques is provided as well (table 8). In the majority of the studies, the most  
35 traditional tannin extraction method namely solid-liquid extraction, was contrasted with other  
36 modern techniques.

1 Considerable differences are regarded between SLE and SFE, especially when no co-solvent was  
2 used (Reátegui et al., 2014). SLE can achieve a higher amount of tannins extracted owing to the  
3 more polar nature of the solvent and the longer times employed. It is regarded though, that the  
4 addition of a more polar co-solvent or the use of simultaneous sonication highly ameliorates the  
5 results of SFE. Thereby, the amounts of tannins extracted are comparable to those of SLE but  
6 employing lower times. Concerning PWE, it is reported that the amount of tannins extracted  
7 compared to that of traditional method SLE is enhanced owing to the increased solvating power  
8 of water under subcritical conditions (Rangsiwong et al., 2009). Moreover, the extraction times  
9 are considerably lowered.

10 Other recent techniques such as MAE and UAE have been also compared to SLE within the  
11 literature (Aspé and Fernández, 2011; Belwal et al., 2017; Ghadage et al., 2017). Superior  
12 performance is displayed by MAE and UAE in terms of higher extraction yields and amount of  
13 tannins recovered. This is due to the acting mechanisms of both methods, which ameliorates the  
14 penetration power of the solvent and extraction efficiency of the tannins from the plant matrix.  
15 Furthermore, the extraction times can be dramatically decreased by more than a 95% in some of  
16 the cases and the amount of solvent used lowered. The use of ionic liquids also provides a great  
17 improvement in the extraction of tannins compared to the performance of conventional organic  
18 solvents in SLE (Ribeiro et al., 2013)

19 Within the presented results, a comparison between the modern tannin extraction techniques is  
20 observed as well. For example, it was presented that the SFE was able to obtained similar  
21 extraction yields to that of UAE. Nevertheless, it was reported to recovered substantially lower  
22 amounts of tannins (Pereira et al., 2017, 2016).

23 In regards to the results presented in table 8, MAE, UAE and PWE are the techniques with the  
24 best future perspectives for tannin extraction. Some works were found providing a further  
25 comparison between them and the conventional extraction methods (Veličković et al., 2017). In  
26 terms of extraction yields, PWE was able to achieve the highest values, followed by MAE and  
27 UAE. Nonetheless, concerning the amount of tannins extracted no considerable differences were  
28 observed. The main advantage of PWE compared to MAE and UAE, was the use water as solvent  
29 instead of organic compounds. MAE was able to provide the shortest extraction times (as seen in  
30 several works) compared to UAE and PWE (1-5 min for MAE in contrast to 15-30 min for UAE  
31 and PWE). Additionally, MAE and UAE can generally perform the extraction at lower pressure  
32 compared to PWE, which requires the use of subcritical conditions.

33 The combination of several of these modern techniques is also reported to provide synergistic  
34 effects and improved results (Lu et al., 2012). For example, the utilization of simultaneous  
35 microwave and ultrasound assisted extraction (UMAE) is proved to provide better results than  
36 these methods alone. Moreover, the substitution of the conventional organic solvents by ionic



1 liquid, shows highly ameliorated results and leads to a promising environmentally friendly option  
2 for tannins extraction.

### 3 **4.2.1 Technical and costs comparison**

4 The major economic and operational considerations in the different extraction methods are  
5 generally derived from the amount and nature of solvent employed, the extraction conditions, the  
6 recovery of the tannin extracts from the solvent and the equipment required for the process.  
7 Regarding these costs and technical characteristics, several differences can be observed.

8 The industrial production of tannins at the moment, is generally performed using traditional solid-  
9 liquid extraction. In this regard, water as solvent is preferred in contrast to the organic solvents,  
10 owing to the lower emissions of VOC and costs (Lochab et al., 2014). However, there is current  
11 a tendency towards the switch of traditional tannin extraction methods by other more  
12 environmentally friendly. This is due to the long extraction times and the high amount of solvent  
13 required, which has to be evaporated afterwards, resulting in elevated energy costs  
14 (Selvamuthukumar and Shi, 2017).

15 Consequently, in the majority of the works presented in this study it is showed that the modern  
16 extraction techniques are more favourable for future implementation in the industry.

17 The implementation in larger scale of PWE for tannin extraction was assessed based on a study  
18 of the main economic factors by Veggi et al. (2011) (Veggi et al., 2011). Here, it was found that  
19 although the addition of a co-solvent can lead to an increment of the manufacturing costs  
20 (distillation step for the solvent), in the end the global manufacturing costs were lower owing to  
21 the improvement in the recovery of tannins. In addition to that, they reported for the process  
22 (design to run 7920h/year) manufacturing costs of 983\$/Kg for the global yields. In contrast to  
23 that technique, Ravber et al (2015) carried out another research with a preliminary economic  
24 evaluation of the PWE for tannins extraction from larch wood (Ravber et al., 2015). After  
25 optimization of the process ( $V_{\text{extractor}}=350\text{L}$  and  $T=300^{\circ}\text{C}$ , process run 8016h/year), they presented  
26 operating costs of 223\$/Kg, achieving an extraction yield of 21.60%. This can provide a more  
27 environmentally friendly and cheaper option compared to conventional solid-liquid extraction.

28 Regarding MAE, moderate global capital costs and good performance at atmospheric conditions  
29 are reported as well as lower energy demands compared to traditional extraction method  
30 (Bouaoudia-Madi et al., 2017). In addition to that, MAE can be highly improved by the use of  
31 ionic liquids as solvent. Liu et al. (2016) pointed out the considerable lower energy requirements  
32 compared to conventional SLE (0.13 kWh MAE in contrast to 1.54kWh SLE) (Z. Liu et al., 2016).  
33 The employment of MAE has been also promoted in other the works from the literature. For  
34 instance, Belwal et al. (2017) presented the need of scaling up the MAE process from the  
35 laboratory scale to the industry to harness the potential of tannins (Belwal et al., 2017). In  
36 comparison to MAE, UAE has been presented as an alternative as well. In fact, Diouf et al. (2009)  
37 found that the energy requirements for UAE were slightly lower than MAE for the same amount

1 of material extracted (0.94kWh and 1.51kWh respectively) (Diouf et al., 2009). The UAE is also  
2 reported to save time, energy and costs compared to conventional SLE. Nevertheless, parameters  
3 should be optimized as excessive sonication can increase energy and operational costs (Agarwal  
4 et al., 2018).

## 5 **5. Conclusions**

6 After performing the literature review it was clear the interest on the topic of tannins extraction,  
7 taking into account the significant number of works found. Besides, a clear evolution was  
8 observed from the traditional extraction method towards the most novel methodologies. The  
9 modern tannin extraction methods show a similar or even better performance compared to the  
10 most traditional one, in terms of extraction yields and amount of tannins extracted. They also  
11 display several advantages concerning the environmental impact such as the reduction of the  
12 extraction times and amount of solvent needed, leading to a lower energy consumption. Despite  
13 these facts, the truth is that the current industrial tannin production still remains old-fashioned,  
14 since it is majorly carried out by solid-liquid extraction using large amounts of water. It has been  
15 clearly stated from the works presented here, that lately several efforts are being made towards  
16 modern ways of extract tannins. Nevertheless, they usually remain in the laboratory scale. For  
17 this reason, an inflection point has to be reached in the short-term to switch from this old-  
18 fashioned industrial tannin production system to a state-of-the-art one. With this aim, works  
19 should be carried in the following years specially focus on the scale up and the economic analysis  
20 of the process of tannins extraction.

21 Finally, it should be added as well that this change in the tannins extraction methods, not only can  
22 lead to a cleaner and more effective production but also can promote and spread tannins utilization  
23 in several fields of the industry. This is of major importance since they represent a renewable  
24 feedstock with numerous applications.

25

## REFERENCES:

- Agarwal, C., Máthé, K., Hofmann, T., Csóka, L., 2018. Ultrasound-Assisted Extraction of Cannabinoids from Cannabis Sativa L. Optimized by Response Surface Methodology. *J. Food Sci.* 83, 700–710. <https://doi.org/10.1111/1750-3841.14075>
- Aires, A., Carvalho, R., Saavedra, M.J., 2016. Valorization of solid wastes from chestnut industry processing: Extraction and optimization of polyphenols, tannins and ellagitannins and its potential for adhesives, cosmetic and pharmaceutical industry. *Waste Manag.* 48, 457–464. <https://doi.org/10.1016/J.WASMAN.2015.11.019>
- Ajila, C.M., Brar, S.K., Verma, M., Tyagi, R.D., Godbout, S., Valéro, J.R., 2011. Extraction and Analysis of Polyphenols: Recent trends. *Crit. Rev. Biotechnol.* 31, 227–249. <https://doi.org/10.3109/07388551.2010.513677>
- Al-Farsi, M.A., Lee, C.Y., 2008. Optimization of phenolics and dietary fibre extraction from date seeds. *Food Chem.* 108, 977–985. <https://doi.org/10.1016/J.FOODCHEM.2007.12.009>
- Alexandre, E.M.C., Araújo, P., Duarte, M.F., de Freitas, V., Pintado, M., Saraiva, J.A., 2017. High-pressure assisted extraction of bioactive compounds from industrial fermented fig by-product. *J. Food Sci. Technol.* 54, 2519–2531. <https://doi.org/10.1007/s13197-017-2697-2>
- Ali, A., Lim, X.Y., Chong, C.H., Mah, S.H., Chua, B.L., 2018. Optimization of ultrasound-assisted extraction of natural antioxidants from Piper betle using response surface methodology. *LWT* 89, 681–688. <https://doi.org/10.1016/J.LWT.2017.11.033>
- Aliakbariana, B., Fathib, A., Perego, P., Dehghanib, F., 2012. Extraction of antioxidants from winery wastes using subcritical water. *J. Supercrit. Fluids* 65, 18–24. <https://doi.org/10.1016/J.SUPFLU.2012.02.022>
- Amaral-Labat, G., Grishechko, L.I., Fierro, V., Kuznetsov, B.N., Pizzi, A., Celzard, A., 2013. Tannin-based xerogels with distinctive porous structures. *Biomass and Bioenergy* 56, 437–445. <https://doi.org/10.1016/J.BIOMBIOE.2013.06.001>
- Annegowda, H. V., Bhat, R., Min-Tze, L., Karim, A.A., Mansor, S.M., 2012. Influence of sonication treatments and extraction solvents on the phenolics and antioxidants in star fruits. *J. Food Sci. Technol.* 49, 510–4. <https://doi.org/10.1007/s13197-011-0435-8>
- Antwi-Boasiako, C., Animapauh, S.O., 2012. Tannin extraction from the barks of three tropical hardwoods for the production of adhesives. *J. Appl. Sci. Res.* 8, 2959–2965.
- Arapitsas, P., 2012. Hydrolyzable tannin analysis in food. *Food Chem.* 135, 1708–1717. <https://doi.org/10.1016/J.FOODCHEM.2012.05.096>
- Arbenz, A., Avérous, L., 2016. Tannins: A Resource to Elaborate Aromatic and Biobased Polymers, in: *Biodegradable and Biobased Polymers for Environmental and Biomedical Applications*. John Wiley & Sons, Inc., Hoboken, NJ, USA, pp. 97–148. <https://doi.org/10.1002/9781119117360.ch4>
- Ashraf-Khorassani, M., Taylor, L.T., 2004. Sequential Fractionation of Grape Seeds into Oils, Polyphenols,

- and Procyanidins via a Single System Employing CO<sub>2</sub>-Based Fluids. *J. Agric. Food Chem.* 52, 2440–2444. <https://doi.org/10.1021/JF030510N>
- Aspé, E., Fernández, K., 2011. The effect of different extraction techniques on extraction yield, total phenolic, and anti-radical capacity of extracts from *Pinus radiata* Bark. *Ind. Crops Prod.* 34, 838–844. <https://doi.org/10.1016/J.INDCROP.2011.02.002>
- Azmir, J., Zaidul, I.S.M., Rahman, M.M., Sharif, K.M., Mohamed, A., Sahena, F., Jahurul, M.H.A., Ghafoor, K., Norulaini, N.A.N., Omar, A.K.M., 2013. Techniques for extraction of bioactive compounds from plant materials: A review. *J. Food Eng.* 117, 426–436. <https://doi.org/10.1016/J.JFOODENG.2013.01.014>
- Bacelo, H.A.M., Botelho, C.M.S., Santos, S.C.R., 2017. Production of tannin-based adsorbents and their use for arsenic uptake from water, in: Vilarinho, C., Castro, F., Lopes, M. de L. (Eds.), *WASTES – Solutions, Treatments and Opportunities II: Selected Papers from the 4th Edition of the International Conference on Wastes: Solutions, Treatments and Opportunities*. CRC Press (Taylor & Francis), London, pp. 113–118.
- Bacelo, H.A.M., Santos, S.C.R., Botelho, C.M.S., 2016. Tannin-based biosorbents for environmental applications – A review. *Chem. Eng. J.* 303, 575–587. <https://doi.org/10.1016/J.CEJ.2016.06.044>
- Baldosano, H.Y., Beatriz, M., Castillo, M.G., Danica, C., Elloran, H., Bacani, F.T., 2015. Effect of Particle Size, Solvent and Extraction Time on Tannin Extract from *Spondias purpurea* Bark Through Soxhlet Extraction. *Proc. DLSU Res. Congr.* 3, 1–6.
- Balogun, R., Jones, R., Holmes, J.H., 1998. Digestibility of some tropical browse species varying in tannin content. *Anim. Feed Sci. Technol.* 76, 77–88. [https://doi.org/10.1016/S0377-8401\(98\)00210-7](https://doi.org/10.1016/S0377-8401(98)00210-7)
- Barbehenn, R. V., Peter Constabel, C., 2011. Tannins in plant–herbivore interactions. *Phytochemistry* 72, 1551–1565. <https://doi.org/10.1016/J.PHYTOCHEM.2011.01.040>
- Bate-Smith, E.C., Swain, T., 1962. Flavonoid compound, in: Mason, H.S., Florkin, A.M. (Eds.), *Comparative Biochemistry*. Academic Press, New York, pp. 755–809.
- Bele, A.A., Jadhav, V.M., Kadam, V.J., 2010. Potential of Tannins: A Review. *Asian J. Plant Sci.* 9, 209–214. <https://doi.org/10.3923/ajps.2010.209.214>
- Belwal, T., Giri, L., Bhatt, I.D., Rawal, R.S., Pande, V., 2017. An improved method for extraction of nutraceutically important polyphenolics from *Berberis jaeschkeana* C.K. Schneid. fruits. *Food Chem.* 230, 657–666. <https://doi.org/10.1016/J.FOODCHEM.2017.03.086>
- Bennick, A., 2002. Interaction of plant polyphenols with salivary proteins. *Crit. Rev. Oral Biol. Med.* 13, 184–96.
- Berardini, N., Carle, R., Schieber, A., 2004. Characterization of gallotannins and benzophenone derivatives from mango (*Mangifera indica* L. cv. “Tommy Atkins”) peels, pulp and kernels by high-performance liquid chromatography/electrospray ionization mass spectrometry. *Rapid Commun. Mass Spectrom.*

- 18, 2208–2216. <https://doi.org/10.1002/rcm.1611>
- Bianchi, S., Krosalakova, I., Janzon, R., Mayer, I., Saake, B., Pichelin, F., 2015. Characterization of condensed tannins and carbohydrates in hot water bark extracts of European softwood species. *Phytochemistry* 120, 53–61. <https://doi.org/10.1016/J.PHYTOCHEM.2015.10.006>
- Bouaoudia-Madi, N., Boulekbache-Makhlouf, L., Kadri, N., Dahmoune, F., Remini, H., Dairi, S., Oukhmanou-Bensidhoum, S., Madani, K., 2017. Phytochemical analysis of *Myrtus communis* plant: Conventional versus microwave assisted-extraction procedures. *J. Complement. Integr. Med.* 14. <https://doi.org/10.1515/jcim-2016-0098>
- Çam, M., Hıışıl, Y., 2010. Pressurised water extraction of polyphenols from pomegranate peels. *Food Chem.* 123, 878–885. <https://doi.org/10.1016/J.FOODCHEM.2010.05.011>
- Carrera, C., Ruiz-Rodríguez, A., Palma, M., Barroso, C.G., 2012. Ultrasound assisted extraction of phenolic compounds from grapes. *Anal. Chim. Acta* 732, 100–104. <https://doi.org/10.1016/J.ACA.2011.11.032>
- Cavalcanti, R.N., Navarro-Díaz, H.J., Santos, D.T., Rostagno, M.A., Meireles, M.A.A., 2012. Supercritical Carbon Dioxide Extraction of Polyphenols from Pomegranate (*Punica granatum* L.) Leaves: Chemical Composition, Economic Evaluation and Chemometric Approach. *J. Food Res.* 1, 282. <https://doi.org/10.5539/jfr.v1n3p282>
- Chavan, Y., Singhal, R.S., 2013. Ultrasound-assisted extraction (UAE) of bioactives from arecanut (*Areca catechu* L.) and optimization study using response surface methodology. *Innov. Food Sci. Emerg. Technol.* 17, 106–113. <https://doi.org/10.1016/J.IFSET.2012.10.001>
- Chemat, F., Zill-e-Huma, Khan, M.K., 2011. Applications of ultrasound in food technology: Processing, preservation and extraction. *Ultrason. Sonochem.* 18, 813–835. <https://doi.org/10.1016/J.ULTSONCH.2010.11.023>
- Chen, K., Escott, C., Loira, I., del Fresno, J., Morata, A., Tesfaye, W., Calderon, F., Benito, S., Suárez-Lepe, J., 2016. The Effects of Pre-Fermentative Addition of Oenological Tannins on Wine Components and Sensorial Qualities of Red Wine. *Molecules* 21, 1445. <https://doi.org/10.3390/molecules21111445>
- Cheng, V.J., Bekhit, A.E.-D.A., McConnell, M., Mros, S., Zhao, J., 2012. Effect of extraction solvent, waste fraction and grape variety on the antimicrobial and antioxidant activities of extracts from wine residue from cool climate. *Food Chem.* 134, 474–482. <https://doi.org/10.1016/J.FOODCHEM.2012.02.103>
- Chowdhury, S.A., Vijayaraghavan, R., MacFarlane, D.R., 2010. Distillable ionic liquid extraction of tannins from plant materials. *Green Chem.* 12, 1023. <https://doi.org/10.1039/b923248f>
- Chupin, L., Charrier, B., Pizzi, A., Perdomo, A., Charrier-El Bouhtoury, F., 2015. Study of thermal durability properties of tannin–lignosulfonate adhesives. *J. Therm. Anal. Calorim.* 119, 1577–1585. <https://doi.org/10.1007/s10973-014-4331-0>

- Chupin, L., Motillon, C., Charrier-El Bouhtoury, F., Pizzi, A., Charrier, B., 2013. Characterisation of maritime pine (*Pinus pinaster*) bark tannins extracted under different conditions by spectroscopic methods, FTIR and HPLC. *Ind. Crops Prod.* 49, 897–903. <https://doi.org/10.1016/J.INDCROP.2013.06.045>
- Ciesla, W.M., 1998. Bark and Roots, in: *Non-Wood Forest Products from Conifers*. Food and Agriculture Organization of the United Nations, pp. 36–48.
- Conde, E., Hemming, J., Smeds, A., Reinoso, B.D., Moure, A., Willför, S., Domínguez, H., Parajó, J.C., 2013. Extraction of low-molar-mass phenolics and lipophilic compounds from *Pinus pinaster* wood with compressed CO<sub>2</sub>. *J. Supercrit. Fluids* 81, 193–199. <https://doi.org/10.1016/J.SUPFLU.2013.04.018>
- Ćurko, N., Tomašević, M., Cvjetko Bubalo, M., Gracin, L., Radojčić Redovniković, I., Kovačević Ganić, K., 2017. Extraction of Proanthocyanidins and Anthocyanins from Grape Skin by Using Ionic Liquids. *Food Technol. Biotechnol.* 55, 429–437. <https://doi.org/10.17113/ftb.55.03.17.5200>
- Da Porto, C., Porretto, E., Decorti, D., 2013. Comparison of ultrasound-assisted extraction with conventional extraction methods of oil and polyphenols from grape (*Vitis vinifera* L.) seeds. *Ultrason. Sonochem.* 20, 1076–1080. <https://doi.org/10.1016/J.ULTSONCH.2012.12.002>
- Dahmoune, F., Nayak, B., Moussi, K., Remini, H., Madani, K., 2015. Optimization of microwave-assisted extraction of polyphenols from *Myrtus communis* L. leaves. *Food Chem.* 166, 585–595. <https://doi.org/10.1016/J.FOODCHEM.2014.06.066>
- Dahmoune, F., Spigno, G., Moussi, K., Remini, H., Cherbal, A., Madani, K., 2014. *Pistacia lentiscus* leaves as a source of phenolic compounds: Microwave-assisted extraction optimized and compared with ultrasound-assisted and conventional solvent extraction. *Ind. Crops Prod.* 61, 31–40. <https://doi.org/10.1016/J.INDCROP.2014.06.035>
- Dai, J., Mumper, R.J., 2010. Plant Phenolics: Extraction, Analysis and Their Antioxidant and Anticancer Properties. *Molecules* 15, 7313–7352. <https://doi.org/10.3390/molecules15107313>
- Dalzell, S.A., Kerven, G.L., 1998. A rapid method for the measurement of *Leucaena* spp proanthocyanidins by the proanthocyanidin (butanol/HCl) assay. *J. Sci. Food Agric.* 78, 405–416. [https://doi.org/10.1002/\(SICI\)1097-0010\(199811\)78:3<405::AID-JSFA133>3.0.CO;2-G](https://doi.org/10.1002/(SICI)1097-0010(199811)78:3<405::AID-JSFA133>3.0.CO;2-G)
- Deng, Y., Zhao, Y., Padilla-Zakour, O., Yang, G., 2015. Polyphenols, antioxidant and antimicrobial activities of leaf and bark extracts of *Solidago canadensis* L. *Ind. Crops Prod.* 74, 803–809. <https://doi.org/10.1016/J.INDCROP.2015.06.014>
- Dhanani, T., Shah, S., Gajbhiye, N.A., Kumar, S., 2013. Effect of extraction methods on yield, phytochemical constituents and antioxidant activity of *Withania somnifera*. *Arab. J. Chem.* 10, S1193–S1199. <https://doi.org/10.1016/J.ARABJC.2013.02.015>
- Diouf, P.N., Stevanovic, T., Boutin, Y., 2009. The effect of extraction process on polyphenol content, triterpene composition and bioactivity of yellow birch (*Betula alleghaniensis* Britton) extracts. *Ind. Crops Prod.* 30, 297–303. <https://doi.org/10.1016/J.INDCROP.2009.05.008>

- do Prado, A.C.P., da Silva, H.S., da Silveira, S.M., Barreto, P.L.M., Vieira, C.R.W., Maraschin, M., Ferreira, S.R.S., Block, J.M., 2014. Effect of the extraction process on the phenolic compounds profile and the antioxidant and antimicrobial activity of extracts of pecan nut [*Carya illinoensis* (Wangenh) C. Koch] shell. *Ind. Crops Prod.* 52, 552–561. <https://doi.org/10.1016/J.INDCROP.2013.11.031>
- Elsevier, 2016. Scopus Factsheet.
- Erşan, S., Güçlü Üstündağ, Ö., Carle, R., Schweiggert, R.M., 2018. Subcritical water extraction of phenolic and antioxidant constituents from pistachio (*Pistacia vera* L.) hulls. *Food Chem.* 253, 46–54. <https://doi.org/10.1016/J.FOODCHEM.2018.01.116>
- Fernandes, L., Casal, S.I.P., Pereira, J.A., Ramalhosa, E., Saraiva, J.A., 2017. Optimization of high pressure bioactive compounds extraction from pansies (*Viola × wittrockiana*) by response surface methodology. *High Press. Res.* 37, 415–429. <https://doi.org/10.1080/08957959.2017.1347925>
- Frutos, P., Hervás, G., Giráldez, F.J., Mantecón, A.R., 2004. Review. Tannins and ruminant nutrition. *Spanish J. Agric. Res.* 2, 191. <https://doi.org/10.5424/sjar/2004022-73>
- Gallo, M., Ferracane, R., Graziani, G., Ritieni, A., Fogliano, V., 2010. Microwave Assisted Extraction of Phenolic Compounds from Four Different Spices. *Molecules* 15, 6365–6374. <https://doi.org/10.3390/molecules15096365>
- García-Marino, M., Rivas-Gonzalo, J.C., Ibáñez, E., García-Moreno, C., 2006. Recovery of catechins and proanthocyanidins from winery by-products using subcritical water extraction. *Anal. Chim. Acta* 563, 44–50. <https://doi.org/10.1016/J.ACA.2005.10.054>
- Geoffroy, T.R., Fortin, Y., Stevanovic, T., 2017. Hot-Water Extraction Optimization of Sugar Maple (*Acer saccharum* Marsh.) and Red Maple (*Acer rubrum* L.) Bark Applying Principal Component Analysis. *J. Wood Chem. Technol.* 37, 261–272. <https://doi.org/10.1080/02773813.2017.1279631>
- Ghadage, D.M., Kshirsagar, P.R., Pai, S.R., Chavan, J.J., 2017. Extraction efficiency, phytochemical profiles and antioxidative properties of different parts of Saptarangi (*Salacia chinensis* L.) – An important underutilized plant. *Biochem. Biophys. Reports* 12, 79–90. <https://doi.org/10.1016/J.BBREP.2017.08.012>
- Glombitza, K.-W., Pauli, K., 2003. Fucols and Phlorethols from the Brown Alga *Scytothamnus australis* Hook. et Harv. (Chnoosporaceae). *Bot. Mar.* 46, 315–320. <https://doi.org/10.1515/BOT.2003.028>
- Goli, A.H., Barzegar, M., Sahari, M.A., 2005. Antioxidant activity and total phenolic compounds of pistachio (*Pistacia vera*) hull extracts. *Food Chem.* 92, 521–525. <https://doi.org/10.1016/J.FOODCHEM.2004.08.020>
- Guo, Z., Jin, Q., Fan, G., Duan, Y., Qin, C., Wen, M., 2001. Microwave-assisted extraction of effective constituents from a Chinese herbal medicine *Radix puerariae*. *Anal. Chim. Acta* 436, 41–47. [https://doi.org/10.1016/S0003-2670\(01\)00900-X](https://doi.org/10.1016/S0003-2670(01)00900-X)
- Hagerman, A.E., 2002. Tannin chemistry. Oxford.

- Hagerman, A.E., 1988. Extraction of tannin from fresh and preserved leaves. *J. Chem. Ecol.* 14, 453–461. <https://doi.org/10.1007/BF01013897>
- Hartzfeld, P.W., Forkner, R., Hunter, M.D., Hagerman, A.E., 2002. Determination of Hydrolyzable Tannins (Gallotannins and Ellagitannins) after Reaction with Potassium Iodate. <https://doi.org/10.1021/JF0111155>
- Haslam, E., 2007. Vegetable tannins – Lessons of a phytochemical lifetime. *Phytochemistry* 68, 2713–2721. <https://doi.org/10.1016/J.PHYTOCHEM.2007.09.009>
- Hatano, T., Shida, S., Han, L., Okuda, T., 1991. Tannins of theaceous plants. III. Camelliatannins A and B, two new complex tannins from *Camellia japonica* L. *Chem. Pharm. Bull. (Tokyo)*. 39, 876–880. <https://doi.org/10.1248/cpb.39.876>
- Hernández-Fernández, F.J., Bayo, J., Pérez de los Ríos, A., Vicente, M.A., Bernal, F.J., Quesada-Medina, J., 2015. Discovering less toxic ionic liquids by using the Microtox® toxicity test. *Ecotoxicol. Environ. Saf.* 116, 29–33. <https://doi.org/10.1016/J.ECOENV.2015.02.034>
- Hernes, P.J., Hedges, J.I., 2004. Tannin signatures of barks, needles, leaves, cones, and wood at the molecular level. *Geochim. Cosmochim. Acta* 68, 1293–1307. <https://doi.org/10.1016/J.GCA.2003.09.015>
- Hong, N., Yaylayan, V.A., Vijaya Raghavan, G.S., Paré, J.R.J., Bélanger, J.M.R., 2001. Microwave-assisted Extraction of Phenolic Compounds from Grape Seed. *Nat. Prod. Lett.* 15, 197–204. <https://doi.org/10.1080/10575630108041280>
- Huang, Z., Ye, C., Li, L., Zhang, X., Qiu, T., Huang, Z., Ye, C., Li, L., Zhang, X., Qiu, T., 2016. Measurement and correlation of the mass transfer coefficient for a liquid-liquid system with high density difference. *Brazilian J. Chem. Eng.* 33, 897–906. <https://doi.org/10.1590/0104-6632.20160334s20150488>
- Huma, Z.-E., Jayasena, V., Nasar-Abbas, S.M., Imran, M., Khan, M.K., 2018. Process optimization of polyphenol extraction from carob (*Ceratonia siliqua*) kibbles using microwave-assisted technique. *J. Food Process. Preserv.* 42, e13450. <https://doi.org/10.1111/jfpp.13450>
- Hümmer, W., Schreier, P., 2008. Analysis of proanthocyanidins. *Mol. Nutr. Food Res.* 52, 1381–1398. <https://doi.org/10.1002/mnfr.200700463>
- Inoue, S., Asaga, M., Ogi, T., Yazaki, Y., 1998. Extraction of Polyflavanoids from Radiata Pine Bark Using Hot Compressed Water at Temperatures Higher than 100 °C. *Holzforschung* 52, 139–145. <https://doi.org/10.1515/hfsg.1998.52.2.139>
- Ismail, T., Calcabrini, C., Diaz, A.R., Fimognari, C., Turrini, E., Catanzaro, E., Akhtar, S., Sestili, P., 2016. Ellagitannins in Cancer Chemoprevention and Therapy. *Toxins (Basel)*. 8. <https://doi.org/10.3390/TOXINS8050151>
- Ivanovic, J., Tadic, V., Dimitrijevic, S., Stamenic, M., Petrovic, S., Zizovic, I., 2014. Antioxidant properties of the anthocyanin-containing ultrasonic extract from blackberry cultivar “Čačanska Bestrna.” *Ind.*



- Crops Prod. 53, 274–281. <https://doi.org/10.1016/J.INDCROP.2013.12.048>
- Jackson, F.S., McNabb, W.C., Barry, T.N., Foo, Y.L., Peters, J.S., 1996. The Condensed Tannin Content of a Range of Subtropical and Temperate Forages and the Reactivity of Condensed Tannin with Ribulose- 1,5-bis-phosphate Carboxylase (Rubisco) Protein. *J. Sci. Food Agric.* 72, 483–492. [https://doi.org/10.1002/\(SICI\)1097-0010\(199612\)72:4<483::AID-JSFA684>3.0.CO;2-G](https://doi.org/10.1002/(SICI)1097-0010(199612)72:4<483::AID-JSFA684>3.0.CO;2-G)
- Jahanshaei, S., Tabarsa, T., Asghari, J., 2012. Eco-friendly tannin-phenol formaldehyde resin for producing wood composites. *Pigment Resin Technol.* 41, 296–301. <https://doi.org/10.1108/03699421211264857>
- Jain, R., Bhagchandani, T., Yadav, N., 2013. An efficient and simple methodology coupling microwave assisted extraction to GC-MS for the identification of components in root bark of *Guazuma tomentosa*. *Int. J. Pharma Bio Sci.* 4, 520–533.
- Jensen, W.B., 2007. The Origin of the Soxhlet Extractor. *J. Chem. Educ.* 84, 1913. <https://doi.org/10.1021/ed084p1913>
- Jin, Z.-X., Wang, B.-Q., Chen, Z.-J., 2010. Microwave-assisted extraction of tannins from Chinese herb *Agrimonia pilosa* Ledeb. *J. Med. Plants Res.* 4, 2229–2234. <https://doi.org/10.5897/JMPR10.378>
- Kaur, B., Kaur, N., 2016. Metabolic fingerprinting of different populations of *Phyllanthus niruri* L. from Punjab using electrospray ionization mass spectrometry (ESI–MS). *Med. Chem. Res.* 25, 2798–2821. <https://doi.org/10.1007/s00044-016-1674-z>
- Kemppainen, K., Siika-aho, M., Pattathil, S., Giovando, S., Kruus, K., 2014. Spruce bark as an industrial source of condensed tannins and non-cellulosic sugars. *Ind. Crops Prod.* 52, 158–168. <https://doi.org/10.1016/J.INDCROP.2013.10.009>
- Khoddami, A., Wilkes, M.A., Roberts, T.H., 2013. Techniques for Analysis of Plant Phenolic Compounds. *Molecules* 18, 2328–2375. <https://doi.org/10.3390/molecules18022328>
- Kirke, D.A., Smyth, T.J., Rai, D.K., Kenny, O., Stengel, D.B., 2017. The chemical and antioxidant stability of isolated low molecular weight phlorotannins. *Food Chem.* 221, 1104–1112. <https://doi.org/10.1016/J.FOODCHEM.2016.11.050>
- Koivikko, R., Eränen, J.K., Lopenen, J., Jormalainen, V., 2008. Variation of Phlorotannins Among Three Populations of *Fucus vesiculosus* as Revealed by HPLC and Colorimetric Quantification. *J. Chem. Ecol.* 34, 57–64. <https://doi.org/10.1007/s10886-007-9410-2>
- Landete, J.M., 2011. Ellagitannins, ellagic acid and their derived metabolites: A review about source, metabolism, functions and health. *Food Res. Int.* 44, 1150–1160. <https://doi.org/10.1016/J.FOODRES.2011.04.027>
- Laurichesse, S., Avérous, L., 2014. Chemical modification of lignins: Towards biobased polymers. *Prog. Polym. Sci.* 39, 1266–1290. <https://doi.org/10.1016/J.PROGPOLYMSCI.2013.11.004>
- Li, Y., Skouroumounis, G.K., Elsey, G.M., Taylor, D.K., 2011. Microwave-assistance provides very rapid and efficient extraction of grape seed polyphenols. *Food Chem.* 129, 570–576.

- <https://doi.org/10.1016/J.FOODCHEM.2011.04.068>
- Liang, X., Fan, Q., 2013. Application of Sub-Critical Water Extraction in Pharmaceutical Industry. *J. Mater. Sci. Chem. Eng.* 1, 1–6. <https://doi.org/10.4236/msce.2013.15001>
- Liu, C., Hu, J., Zhang, H., Xiao, R., 2016. Thermal conversion of lignin to phenols: Relevance between chemical structure and pyrolysis behaviors. *Fuel* 182, 864–870. <https://doi.org/10.1016/J.FUEL.2016.05.104>
- Liu, Z., Chen, Z., Han, F., Kang, X., Gu, H., Yang, L., 2016. Microwave-assisted method for simultaneous hydrolysis and extraction in obtaining ellagic acid, gallic acid and essential oil from Eucalyptus globulus leaves using Brønsted acidic ionic liquid [HO3S(CH2)4mim]HSO4. *Ind. Crops Prod.* 81, 152–161. <https://doi.org/10.1016/J.INDCROP.2015.11.074>
- Lochab, B., Shukla, S., Varma, I.K., 2014. Naturally occurring phenolic sources: monomers and polymers. *RSC Adv.* 4, 21712–21752. <https://doi.org/10.1039/C4RA00181H>
- Lopes, G., Sousa, C., Silva, L.R., Pinto, E., Andrade, P.B., Bernardo, J., Mouga, T., Valentão, P., 2012. Can phlorotannins purified extracts constitute a novel pharmacological alternative for microbial infections with associated inflammatory conditions? *PLoS One* 7, e31145. <https://doi.org/10.1371/journal.pone.0031145>
- Lu, C., Wang, H., Lv, W., Ma, C., Lou, Z., Xie, J., Liu, B., 2012. Ionic liquid-based ultrasonic/microwave-assisted extraction combined with UPLC–MS–MS for the determination of tannins in *Galla chinensis*. *Nat. Prod. Res.* 26, 1842–1847. <https://doi.org/10.1080/14786419.2011.607454>
- Luengthanaphol, S., Mongkholkhajornsilp, D., Douglas, S., Douglas, P.L., Pongsopa, L., Pongamphai, S., 2004. Extraction of antioxidants from sweet Thai tamarind seed coat—preliminary experiments. *J. Food Eng.* 63, 247–252. <https://doi.org/10.1016/J.JFOODENG.2003.07.006>
- Luque de Castro, M.D., Priego-Capote, F., 2010. Soxhlet extraction: Past and present panacea. *J. Chromatogr. A* 1217, 2383–2389. <https://doi.org/10.1016/J.CHROMA.2009.11.027>
- Mailoa, M.N., Mahendradatta, M., Laga, A., Djide, N., 2013. Tannin extract of guava leaves (*Psidium guajava* L) variation with concentration organic solvents. *Int. J. Sci. Technol. Res.* 2, 106–110. <https://doi.org/10.1023/A:1026206511084>
- Mangan, J.L., 1988. Nutritional Effects of Tannins in Animal Feeds. *Nutr. Res. Rev.* 1, 209. <https://doi.org/10.1079/NRR19880015>
- Maran, J.P., Manikandan, S., Priya, B., Gurumoorthi, P., 2015. Box-Behnken design based multi-response analysis and optimization of supercritical carbon dioxide extraction of bioactive flavonoid compounds from tea (*Camellia sinensis* L.) leaves. *J. Food Sci. Technol.* 52, 92–104. <https://doi.org/10.1007/s13197-013-0985-z>
- Markom, M., Hasan, M., Daud, W.R.W., 2010a. Pressurized Water Extraction of Hydrolysable Tannins from *Phyllanthus niruri* Linn. *Sep. Sci. Technol.* 45, 548–553. <https://doi.org/10.1080/01496390903485005>

- Markom, M., Hasan, M., Daud, W.R.W., Anuar, N., Hassan, O., Singh, H., 2010b. Chemical Profiling and Quantification of Tannins in *Phyllanthus niruri* Linn. Fractionated by SFE Method. *Sep. Sci. Technol.* 46, 71–78. <https://doi.org/10.1080/01496395.2010.498005>
- Markom, M., Hasan, M., Daud, W.R.W., Singh, H., Jahim, J.M., 2007. Extraction of hydrolysable tannins from *Phyllanthus niruri* Linn.: Effects of solvents and extraction methods. *Sep. Purif. Technol.* 52, 487–496. <https://doi.org/10.1016/J.SEPPUR.2006.06.003>
- Mašković, P.Z., Veličković, V., Đurović, S., Zeković, Z., Radojković, M., Cvetanović, A., Švarc-Gajić, J., Mitić, M., Vujić, J., 2018. Biological activity and chemical profile of *Lavatera thuringiaca* L. extracts obtained by different extraction approaches. *Phytomedicine* 38, 118–124. <https://doi.org/10.1016/J.PHYMED.2017.11.010>
- Mattivi, F., Vrhovsek, U., Masuero, D., Trainotti, D., 2009. Differences in the amount and structure of extractable skin and seed tannins amongst red grape varieties. *Aust. J. Grape Wine Res.* 15, 27–35. <https://doi.org/10.1111/j.1755-0238.2008.00027.x>
- McGraw, G.W., 1989. Reactions at the A-ring of Proanthocyanidins, in: *Chemistry and Significance of Condensed Tannins*. Springer US, Boston, MA, pp. 227–248. [https://doi.org/10.1007/978-1-4684-7511-1\\_14](https://doi.org/10.1007/978-1-4684-7511-1_14)
- Murugan, R., Parimelazhagan, T., 2014. Comparative evaluation of different extraction methods for antioxidant and anti-inflammatory properties from *Osbeckia parvifolia* Arn. – An in vitro approach. *J. King Saud Univ. - Sci.* 26, 267–275. <https://doi.org/10.1016/J.JKSUS.2013.09.006>
- Myers, M.L., 1998. Agriculture and Natural Resources Based Industries, in: *Encyclopaedia of Occupational Health and Safety*. International Labour Organization.
- Naima, R., Oumam, M., Hannache, H., Sesbou, A., Charrier, B., Pizzi, A., Charrier – El Bouhtoury, F., 2015. Comparison of the impact of different extraction methods on polyphenols yields and tannins extracted from Moroccan *Acacia mollissima* barks. *Ind. Crops Prod.* 70, 245–252. <https://doi.org/10.1016/J.INDCROP.2015.03.016>
- Olivier-Bourbigou, H., Magna, L., Morvan, D., 2010. Ionic liquids and catalysis: Recent progress from knowledge to applications. *Appl. Catal. A Gen.* 373, 1–56. <https://doi.org/10.1016/J.APCATA.2009.10.008>
- Palmer, M.V., Ting, S.S.T., 1995. Applications for supercritical fluid technology in food processing. *Food Chem.* 52, 345–352. [https://doi.org/10.1016/0308-8146\(95\)93280-5](https://doi.org/10.1016/0308-8146(95)93280-5)
- Pan, Y., He, C., Wang, H., Ji, X., Wang, K., Liu, P., 2010. Antioxidant activity of microwave-assisted extract of *Buddleia officinalis* and its major active component. *Food Chem.* 121, 497–502. <https://doi.org/10.1016/J.FOODCHEM.2009.12.072>
- Panamgama, L.A., 2007. Polyphenolic extracts of *Pinus radiata* bark and networking mechanisms of additive-accelerated polycondensates. *J. Appl. Polym. Sci.* 103, 2487–2493. <https://doi.org/10.1002/app.24466>

- Pansera, M.R., Iob, G.A., Atti-Santos, A.C., Rossato, M., Atti-Serafini, L., Cassel, E., 2004. Extraction of tannin by *Acacia mearnsii* with supercritical fluids. *Brazilian Arch. Biol. Technol.* 47, 995–998. <https://doi.org/10.1590/S1516-89132004000600019>
- Park, M., Cho, H., Jung, H., Lee, H., Hwang, K.T., 2014. Antioxidant and Anti-Inflammatory Activities of Tannin Fraction of the Extract from Black Raspberry Seeds Compared to Grape Seeds. *J. Food Biochem.* 38, 259–270. <https://doi.org/10.1111/jfbc.12044>
- Pereira, P., Cebola, M.-J., Oliveira, M.C., Bernardo-Gil, M.G., 2016. Supercritical fluid extraction vs conventional extraction of myrtle leaves and berries: Comparison of antioxidant activity and identification of bioactive compounds. *J. Supercrit. Fluids* 113, 1–9. <https://doi.org/10.1016/J.SUPFLU.2015.09.006>
- Pereira, P., Cebola, M.-J., Oliveira, M.C., Bernardo Gil, M.G., 2017. Antioxidant capacity and identification of bioactive compounds of *Myrtus communis* L. extract obtained by ultrasound-assisted extraction. *J. Food Sci. Technol.* 54, 4362–4369. <https://doi.org/10.1007/s13197-017-2907-y>
- Perrut†, M., 2000. Supercritical Fluid Applications: Industrial Developments and Economic Issues. <https://doi.org/10.1021/IE000211C>
- Ping, L., Brosse, N., Chrusciel, L., Navarrete, P., Pizzi, A., 2011. Extraction of condensed tannins from grape pomace for use as wood adhesives. *Ind. Crops Prod.* 33, 253–257. <https://doi.org/10.1016/J.INDCROP.2010.10.007>
- Plaza, M., Amigo-Benavent, M., del Castillo, M.D., Ibáñez, E., Herrero, M., 2010. Facts about the formation of new antioxidants in natural samples after subcritical water extraction. *Food Res. Int.* 43, 2341–2348. <https://doi.org/10.1016/J.FOODRES.2010.07.036>
- Plaza, M., Turner, C., 2015. Pressurized hot water extraction of bioactives. *TrAC Trends Anal. Chem.* 71, 39–54. <https://doi.org/10.1016/J.TRAC.2015.02.022>
- Politi, F.A.S., de Mello, J.C.P., Migliato, K.F., Nepomuceno, A.L.A., Moreira, R.R.D., Pietro, R.C.L.R., 2011. Antimicrobial, cytotoxic and antioxidant activities and determination of the total tannin content of bark extracts *Endopleura uchi*. *Int. J. Mol. Sci.* 12, 2757–68. <https://doi.org/10.3390/ijms12042757>
- Poveda, J.M., Loarce, L., Alarcón, M., Díaz-Maroto, M.C., Alañón, M.E., 2018. Revalorization of winery by-products as source of natural preservatives obtained by means of green extraction techniques. *Ind. Crops Prod.* 112, 617–625. <https://doi.org/10.1016/J.INDCROP.2017.12.063>
- Ramires, E.C., Frollini, E., 2012. Tannin–phenolic resins: Synthesis, characterization, and application as matrix in biobased composites reinforced with sisal fibers. *Compos. Part B Eng.* 43, 2851–2860. <https://doi.org/10.1016/J.COMPOSITESB.2012.04.049>
- Ramos, V., Bocalandro, C., Riquelme, S., Sanhueza, V., Aspé, E., Roeckel, M., Fernández, K., 2013. Effect of the bench scale extraction conditions on *Pinus radiata* bark extract yield, antioxidant properties and composition. *Maderas. Cienc. y Tecnol.* 15, 0–0. <https://doi.org/10.4067/S0718-221X2013005000003>

- Rangsrivong, P., Rangkadilok, N., Satayavivad, J., Goto, M., Shotipruk, A., 2009. Subcritical water extraction of polyphenolic compounds from *Terminalia chebula* Retz. fruits. *Sep. Purif. Technol.* 66, 51–56. <https://doi.org/10.1016/J.SEPPUR.2008.11.023>
- Ravber, M., Knez, Ž., Škerget, M., 2015. Isolation of phenolic compounds from larch wood waste using pressurized hot water: extraction, analysis and economic evaluation. *Cellulose* 22, 3359–3375. <https://doi.org/10.1007/s10570-015-0719-7>
- Reátegui, J.L.P., Machado, A.P. da F., Barbero, G.F., Rezende, C.A., Martínez, J., 2014. Extraction of antioxidant compounds from blackberry (*Rubus* sp.) bagasse using supercritical CO<sub>2</sub> assisted by ultrasound. *J. Supercrit. Fluids* 94, 223–233. <https://doi.org/10.1016/J.SUPFLU.2014.07.019>
- Ribeiro, B.D., Coelho, M.A.Z., Rebelo, L.P.N., Marrucho, I.M., 2013. Ionic Liquids as Additives for Extraction of Saponins and Polyphenols from Mate (*Ilex paraguariensis*) and Tea (*Camellia sinensis*). *Ind. Eng. Chem. Res.* 52, 12146–12153. <https://doi.org/10.1021/ie400529h>
- Routray, W., Orsat, V., 2012. Microwave-Assisted Extraction of Flavonoids: A Review. *Food Bioprocess Technol.* 5, 409–424. <https://doi.org/10.1007/s11947-011-0573-z>
- Saad, H., Charrier-El Bouhtoury, F., Pizzi, A., Rode, K., Charrier, B., Ayed, N., 2012. Characterization of pomegranate peels tannin extractives. *Ind. Crops Prod.* 40, 239–246. <https://doi.org/10.1016/J.INDCROP.2012.02.038>
- Sathya, R., Kanaga, N., Sankar, P., Jeeva, S., 2017. Antioxidant properties of phlorotannins from brown seaweed *Cystoseira trinodis* (Forsskål) C. Agardh. *Arab. J. Chem.* 10, S2608–S2614. <https://doi.org/10.1016/J.ARABJC.2013.09.039>
- Saxena, R., Sharma, R., Nandy, C., Jasuja, N.D., 2014. Qualitative and quantitative estimation of bioactive compounds in *mimosa hamata*. *Int. J. Pharm. Pharm. Sci.* 6.
- Sealy-Fisher, V.J., Pizzi, A., 1992. Increased pine tannins extraction and wood adhesives development by phlobaphenes minimization. *Holz als Roh- und Werkst.* 50, 212–220. <https://doi.org/10.1007/BF02663290>
- Selvamuthukumaran, M., Shi, J., 2017. Recent advances in extraction of antioxidants from plant by-products processing industries. *Food Qual. Saf.* 1, 61–81. <https://doi.org/10.1093/fqsafe/fyx004>
- Sousa, A.D., Maia, A.I.V., Rodrigues, T.H.S., Canuto, K.M., Ribeiro, P.R.V., de Cassia Alves Pereira, R., Vieira, R.F., de Brito, E.S., 2016. Ultrasound-assisted and pressurized liquid extraction of phenolic compounds from *Phyllanthus amarus* and its composition evaluation by UPLC-QTOF. *Ind. Crops Prod.* 79, 91–103. <https://doi.org/10.1016/J.INDCROP.2015.10.045>
- Švarc-Gajić, J., Stojanović, Z., Segura Carretero, A., Arráez Román, D., Borrás, I., Vasiljević, I., 2013. Development of a microwave-assisted extraction for the analysis of phenolic compounds from *Rosmarinus officinalis*. *J. Food Eng.* 119, 525–532. <https://doi.org/10.1016/J.JFOODENG.2013.06.030>
- Tabaraki, R., Safari, A., Yeganeh, F.A., 2013. Ultrasonic-assisted extraction of condensed tannin from

- acron, gland, leaf and gall of oak using response surface methodology. *J. Appl. Chem. Res.* 7, 67–77.
- Talmaciu, A.I., Ravber, M., Volf, I., Knez, Ž., Popa, V.I., 2016. Isolation of bioactive compounds from spruce bark waste using sub- and supercritical fluids. *J. Supercrit. Fluids* 117, 243–251. <https://doi.org/10.1016/J.SUPFLU.2016.07.001>
- Tan, M., Tan, C., Ho, C., 2013. Effects of extraction solvent system, time and temperature on total phenolic content of henna (*Lawsonia inermis*) stems. *Int. Food Res. J.* 20, 3117–3123.
- Thomson Reuters, 2013. Web of Science Factsheet.
- Vázquez, G., González-Alvarez, J., Freire, S., López-Suevos, F., Antorrena, G., 2001. Characteristics of *Pinus pinaster* bark extracts obtained under various extraction conditions. *Holz als Roh- und Werkst.* 59, 451–456. <https://doi.org/10.1007/s00107-001-0246-0>
- Veggi, P.C., Cavalcanti, R.N., Meireles, M.A.A., 2011. Modifier effects on Supercritical Fluid Extraction (SFE) of some Brazilian plants: Antioxidant activity and Economical evaluation. *Procedia Food Sci.* 1, 1717–1724. <https://doi.org/10.1016/J.PROFOO.2011.09.253>
- Veličković, V., Đurović, S., Radojković, M., Cvetanović, A., Švarc-Gajić, J., Vujić, J., Trifunović, S., Mašković, P.Z., 2017. Application of conventional and non-conventional extraction approaches for extraction of *Erica carnea* L.: Chemical profile and biological activity of obtained extracts. *J. Supercrit. Fluids* 128, 331–337. <https://doi.org/10.1016/J.SUPFLU.2017.03.023>
- Vergara-Salinas, J.R., Bulnes, P., Zúñiga, M.C., Pérez-Jiménez, J., Torres, J.L., Mateos-Martín, M.L., Agosin, E., Pérez-Correa, J.R., 2013. Effect of Pressurized Hot Water Extraction on Antioxidants from Grape Pomace before and after Enological Fermentation. *J. Agric. Food Chem.* 61, 6929–6936. <https://doi.org/10.1021/jf4010143>
- Vieira, M.C., Lelis, R.C.C., Couto Da Silva, B., De, G., Oliveira, L., De Pesquisa, A., 2011. Tannin Extraction from the Bark of *Pinus oocarpa* var. *oocarpa* with Sodium Carbonate and Sodium Bisulfite. *Floresta e Ambient.* 18, 1–81. <https://doi.org/10.4322/loram.2011.017>
- Vijayalaxmi, S., Jayalakshmi, S.K., Sreeramulu, K., 2015. Polyphenols from different agricultural residues: extraction, identification and their antioxidant properties. *J. Food Sci. Technol.* 52, 2761–2769. <https://doi.org/10.1007/s13197-014-1295-9>
- Wang, Y.-L., Xi, G.-S., Zheng, Y.-C., Miao, F.-S., 2010. Microwave-assisted extraction of flavonoids from Chinese herb *Radix puerariae* (Ge Gen). *J. Med. Plants Res.* 4, 304–308. <https://doi.org/10.5897/JMPR09.426>
- Widyawati, P.S., Dwi, T., Budianta, W., Kusuma, F.A., Wijaya, E.L., 2014. Difference of Solvent Polarity To Phytochemical Content and Antioxidant Activity of *Pluchea indicia* Less Leaves Extracts. *Int. J. Pharmacogn. Phytochem. Res.* 6, 850–855.
- Wohlin, C., Claes, 2014. Guidelines for snowballing in systematic literature studies and a replication in software engineering, in: *Proceedings of the 18th International Conference on Evaluation and Assessment in Software Engineering - EASE '14*. ACM Press, New York, New York, USA, pp. 1–

10. <https://doi.org/10.1145/2601248.2601268>

Xiao, W., Han, L., Shi, B., 2008. Microwave-assisted extraction of flavonoids from Radix Astragali. Sep. Purif. Technol. 62, 614–618. <https://doi.org/10.1016/J.SEPPUR.2008.03.025>

Xu, C.-C., Wang, B., Pu, Y.-Q., Tao, J.-S., Zhang, T., 2017. Advances in extraction and analysis of phenolic compounds from plant materials. Chin. J. Nat. Med. 15, 721–731. [https://doi.org/10.1016/S1875-5364\(17\)30103-6](https://doi.org/10.1016/S1875-5364(17)30103-6)

ACCEPTED MANUSCRIPT

## LIST OF FIGURES:




Figure 1. Number of tannins-related publications per year in the period 1998-2017 indexed in Web-of-Science and Scopus.




Figure 2. Structure of Flavan-3-ol and its nomenclature




Figure 3. Example of a hydrolysable tannin unit and the linkages present (e.g. pentagalloyl glucose structure linked via ester bonds).






Figure 4. Transformation between the main polyphenolic acids and derivatives present in the structure of hydrolysable tannins




Figure 5. Acutissimin A typical complex tannins group.




Figure 6. Literature review process

## LIST OF TABLES:

Table 1. Structures of the most common flavan-3-ol monomers of condensed tannins









A rings B rings	 resorcinol ring	 phloroglucinol ring
 catechol ring	 <b>R1=OH R2=H</b> fisetinidol <b>R1=H R2=OH</b> epifisetinidol	 <b>R1=OH R2=H</b> catechin <b>R1=H R2=OH</b> epicatechin
 pyrogallol ring	 <b>R1=OH R2=H</b> robinetinidol <b>R1=H R2=OH</b> epirobinetinidol	 <b>R1=OH R2=H</b> gallocatechin <b>R1=H R2=OH</b> epigallocatechin

Table 2. Strings and number of results obtained for the individual search of each tannin extraction method

SEARCH STRINGS	NUMBER OF RESULTS	
	SCOPUS	WEB OF SCIENCE
[organic solvent extraction AND tannin]	117	111
[hot water extraction AND tannin]	73	80
[ionic liquid extraction AND tannin]	9	12
[supercritical fluid extraction AND tannin]	31	46
[pressurized water extraction AND tannin]	13	17
[subcritical water extraction AND tannin]	7	11
[microwave assisted extraction AND tannin]	35	48
[ultrasound assisted extraction AND tannin]	36	50

Table 3. Results related to the tannins solid-liquid extraction with different solvents

Species	Plant part	Solvent	Extraction conditions	Extraction Yield (% w/w) <sup>a</sup>	Tannin content (mg/g <sub>DE</sub> ) <sup>b</sup>	References
<i>Pinus radiata</i>	Bark	Water	1:20, 2h	19.60	887.00 <sup>c</sup>	(Inoue et al., 1998)
		Water+ 1% NaOH	100°C	30.50	828.00 <sup>c</sup>	
<i>Pinus pinaster</i>	Bark	Water + 2.5% NaOH	1:10, 0.5h	16.5	965.00 <sup>c</sup>	(Vázquez et al., 2001)
		Water + 5% NaOH	70°C	18.9	875.00 <sup>c</sup>	
		Water + 2.5% NaOH	1:10, 0.5h	23.20	963.00 <sup>c</sup>	
		Water + 5% NaOH	90°C	25.00	812.00 <sup>c</sup>	
<i>Mangifera indica</i>	Peels	Acetone (80%)	1:20, 3h	---	1.4 <sup>d</sup>	(Berardini et al., 2004)
	Pulp			0.2 <sup>d</sup>		
	Kernel			15.5 <sup>d</sup>		
<i>Acacia mearnsii</i>	Bark	Ethanol	1:10, 24h	---	237.00 <sup>e</sup>	(Pansera et al., 2004)
<i>Phyllanthus niruri</i>	Stem and aerial parts	Water	1:30, 3h b.p <sup>g</sup>	26.2	215.90 <sup>f</sup>	(Markom et al., 2007)
		Ethanol (50%)		22.50	149.00 <sup>f</sup>	
		Ethanol (70%)		20.80	91.10 <sup>f</sup>	
<i>Acacia catechu</i>	Whole plant	N,N-dimethylammonium N',N'-dimethylcarbamate (DIMCARB) (15%)	1:5, 25°C 1h	30	---	(Chowdhury et al., 2010)
			1:5, 25°C 2h	60	---	
			1:5, 25°C 16h	85	61.50 <sup>f</sup>	
		Water	1:10, 70°C 16h	64	28.60 <sup>f</sup>	
<i>Pinus radiata</i>	Bark	Acetone (70%)	1:10, 1-6h	12.00	62.10 <sup>h</sup>	(Aspé and Fernández, 2011)
<i>Vitis vinifera</i>	Pomace	Water + 10% NaOH	1:8, 2h 120°C	45.20	550.00 <sup>c</sup>	(Ping et al., 2011)
		Water + 20% NaOH		71.10	490.00 <sup>c</sup>	
		Water + 30% NaOH		88.40	390.00 <sup>c</sup>	
<i>Endopleura uchi</i>	Bark	Water	1:20	9.70	226.60 <sup>d</sup>	(Politi et al., 2011)
			1:10	8.85	260.60 <sup>d</sup>	
			1:5	8.53	120.80 <sup>d</sup>	
<i>Pinus ocarpa</i>	Bark	Water	1:15, 2h b.p.	24.84	655.60 <sup>c</sup>	(Vieira et al., 2011)
		Water + 1% Na <sub>2</sub> CO <sub>3</sub>		30.94	857.20 <sup>c</sup>	
		Water + 5% Na <sub>2</sub> CO <sub>3</sub>		35.74	890.70 <sup>c</sup>	
		Water + 1% NaHSO <sub>3</sub>		19.86	846.40 <sup>c</sup>	
		Water + 5% NaHSO <sub>3</sub>		26.70	722.80 <sup>c</sup>	
<i>T. tetraptera</i>	Bark	Water	1:5, 6h b.p.	14.02	884.49 <sup>c</sup>	(Antwi-Boasiako and Animapauh, 2012)
		Water + 1% NaOH		75.29	374.60 <sup>c</sup>	
<i>Galla chinensis</i>	Whole plant	1-butyl-3-methylimidazole bromide [C4mim]Br 0.5M	1:15, 1min UMAE <sup>d</sup> : Microwave 400W Ultrasound 50W	---	380.00 <sup>d</sup>	(Lu et al., 2012)
		1-butyl-3-methylimidazole bromide [C4mim]Br 1.5M		---	555.00 <sup>d</sup>	

		1-butyl-3-methylimidazole bromide [C4mim]Br 2.5M			601.00 <sup>d</sup>		
		1-butyl-3-methylimidazole bromide [C4mim]Br 4M			605.00 <sup>d</sup>		
<i>Punica granatum</i>	Peels	Methanol	1:20, 6h	---	3.10 <sup>i</sup>	504.80 <sup>e</sup>	(Saad et al., 2012)
<i>Pinus pinaster</i>	Bark	Water + 1% NaOH + 0.25% Na <sub>2</sub> SO <sub>3</sub> + 0.25% NaHSO <sub>3</sub>	1:9, 2h 80°C	22.06	489.70 <sup>c</sup>		(Chupin et al., 2013)
		Water + 5% NaOH + 0.25% Na <sub>2</sub> SO <sub>3</sub> + 0.25% NaHSO <sub>3</sub>		31.30	179.20 <sup>c</sup>		
<i>Pinus radiata</i>	Bark	Acetone (25%)	1:20, 2h 40°C	3.50	350.00 <sup>h</sup>		(Ramos et al., 2013)
		Ethanol (25%)		3.00	310.00 <sup>h</sup>		
		Acetone (25%)	1:20, 2h 120°C	11.00	220.00 <sup>h</sup>		
		Ethanol (25%)		10.10	250.00 <sup>h</sup>		
<i>Carya illinoensis</i>	Shells	Water	1:50, 0.5h 98°C	32.12	36.94 <sup>h</sup>		(do Prado et al., 2014)
		Ethanol	1:50, 1h 25°C	32.09	412.10 <sup>h</sup>		
<i>Osbeckia parvifolia</i>	Whole plant	Hexane	1:5, 24h	3.40	7.31 <sup>d</sup>		(Murugan and Parimelazhagan, 2014)
		Ethyl acetate		4.80	10.88 <sup>d</sup>		
		Methanol		9.20	20.32 <sup>d</sup>		
		Ethanol		1.60	10.67 <sup>d</sup>		
<i>Picea abies</i>	Bark	Water + 2% NaHSO <sub>3</sub> + 0.5% Na <sub>2</sub> CO <sub>3</sub>	1:20, 2h 60°C	16.10	330.00 <sup>j</sup>		(Kemppainen et al., 2014)
			1:20, 2h 90°C	20.90	480.00 <sup>j</sup>		
<i>Mimosa hamata</i>	Whole plant	Methanol (80%)	1:6, 48h	24.20	264.40 <sup>k</sup>		(Saxena et al., 2014)
		Ethanol (95%) <sup>l</sup>		34.74	287.50 <sup>k</sup>		
<i>Pluchea indica</i>	Leaves	Water	3h b.p	40.65	81.30 <sup>h</sup>		(Widyawati et al., 2014)
		Methanol		38.07	911.90 <sup>h</sup>		
		Ethyl acetate		32.97	93.10 <sup>h</sup>		
		Ethanol		31.09	7.80 <sup>h</sup>		
		Hexane		29.46	0.90 <sup>h</sup>		
<i>Spondias purpurea</i>	Bark	Ethanol (95%)	1:30	---	31.80 <sup>e</sup>	(Baldosano et al., 2015)	
					73.75 <sup>e</sup>		
					181.60 <sup>e</sup>		
<i>Saccharum officinarum</i>	Bagasse	Methanol (50%)	1:10, 72h	6.20	381.80 <sup>Ee</sup>		(Vijayalaxmi et al., 2015)
		Ethanol (50%)		4.50	316.50 <sup>e</sup>		

<i>Castanea sativa</i>	Peels	Water	1:4, 4h 85°C	7.03	234.80 <sup>c</sup>	(Aires et al., 2016)
		Water + 1% Na <sub>2</sub> SO <sub>3</sub>		7.74	794.90 <sup>c</sup>	
		Water + 4% Na <sub>2</sub> SO <sub>3</sub>		8.67	373.80 <sup>c</sup>	
		Water + 1% NaOH		11.63	728.70 <sup>c</sup>	
		Water + 4% NaOH		66.59	415.00 <sup>c</sup>	
<i>Eucaliptus globulus</i>	Leaves	1-butyl-3-methylimidazole bromide [C4mim]Br 0.6M	1:30, 0.33h MAE <sup>e</sup> 385W	---	3.40 <sup>f*</sup>	(C. Liu et al., 2016)
		1-butyl-3-methylimidazole bromide [C4mim]Br 1M		---	7.15 <sup>f*</sup>	
		1-butyl-3-methylimidazole bromide [C4mim]Br 1.2M		---	6.90 <sup>f*</sup>	
<i>Phyllanthus niruri</i> (Patiala region)	Whole plant	Ethanol	1:2, 24h	---	2.50 <sup>i</sup>	(Kaur and Kaur, 2016)
		Methanol		---	16.00 <sup>i</sup>	
<i>Vitis vinifera</i>	Skins	1-butyl-3-methylimidazolium bromide [C4mim]Br 0.5M	1:10, 4h 25°C	---	60.10 <sup>j</sup>	(Ćurko et al., 2017)
		1-pentyl-3-methylimidazolium bromide [C5mim]Br 0.5M		---	41.30 <sup>j</sup>	
		1-heptyl-3-methylimidazolium bromide [C7mim]Br 0.5M		---	38.60 <sup>j</sup>	
		1-decyl-3-methylimidazolium bromide [C10mim]Br 0.5M		---	6.60 <sup>j</sup>	

\*Results expressed in mg of tannins per gram of dry matter.

<sup>a</sup>Extraction yield expressed in grams of extracts per grams of material.

<sup>b</sup>DE= dry extract.

<sup>c</sup>Tannin content in extracts expressed in mg of reactive tannins/g dry extract (Stiasny number).

<sup>d</sup>Tannin content in extracts expressed in gallic acid equivalents (GAE).

<sup>e</sup>Tannin content in extracts expressed in tannic acid equivalents (TAE).

<sup>f</sup>Hydrolysable tannin content in the extracts (HTC).

<sup>g</sup>b.p= boiling point.

<sup>h</sup>Content of extracts expressed in catechin equivalents (CE).

<sup>i</sup>Tannin content in extracts expressed in cyaniding equivalents (CYE).

<sup>j</sup>Condensed tannin content in the extracts (CTC).

<sup>k</sup>Tannin content in extracts expressed in quercetin equivalents (QE).

Table 4. Results related to the extraction of tannins via fluid at supercritical conditions

Species	Plant part	Fluid	Co-solvent	T <sup>a</sup> (°C)	P (MPa)	Extraction yield (% w/w) <sup>a</sup>	Tannin content (mg/g <sub>DE</sub> <sup>b</sup> )	References
<i>Tamarindus indica</i>	Seed	CO <sub>2</sub>	Ethanol (10%)	40	30.00	<1	0.06 <sup>c</sup>	(Luengthanaphol et al., 2004)
				55			0.05 <sup>c</sup>	
				88			0.02 <sup>c</sup>	
<i>Acacia mearnsi</i>	Bark		Ethanol Water	60	25.00	---	95.00 <sup>d</sup>	(Pansera et al., 2004)
							135.00 <sup>d</sup>	
<i>Vitis vitifera</i>	Seed		Methanol (30%) Methanol (35%) Methanol (40%)	80	65.50	---	600.00 <sup>e</sup>	(Ashraf- Khorassani and Taylor, 2004)
							720.00 <sup>e</sup>	
							770.00 <sup>e</sup>	
<i>Phyllanthus niruri</i>	Stem and aerial parts		Water Ethanol (50%) Ethanol (70%)	60	20.00	17.78	93.80 <sup>f</sup>	(Markom et al., 2010b)
						19.83	93.60 <sup>f</sup>	
						8.50	92.10 <sup>f</sup>	
<i>Punica granatum</i>	Leaves		---	50	30.00	0.21-0.67	340.00 <sup>g</sup>	(Cavalcanti et al., 2012)
<i>Pinus pinaster</i>	Sapwood and knotwood		---	50	25.00	1.60	19.38 <sup>g</sup>	(Conde et al., 2013)
						4.10	75.61 <sup>g</sup>	
<i>Carya illinoensis</i>	Shells		Ethanol (10%)	50	10.00	0.83	0.48 <sup>h</sup>	(do Prado et al., 2014)
		20.00			8.40	29.00 <sup>h</sup>		
<i>Camellia sinensis</i>	Leaves	Ethanol	50	18.80	---	499.90 <sup>d</sup>	(Maran et al., 2015)	
<i>Picea abies</i>	Bark	Ethanol (70%)	40	10.00	22.5	26.38 <sup>d</sup>	(Talmaciu et al., 2016)	

<sup>a</sup>Extraction yield expressed in grams of extracts per grams of material.

<sup>b</sup>DE= dry extract.

<sup>c</sup>Amount of epicatechin recovered in the extracts.

<sup>d</sup>Tannin content in extracts expressed in tannic acid equivalents (TAE).

<sup>e</sup>Amount of catechin recovered in the extracts.

<sup>f</sup>Total ellagitannin content in the extracts.

<sup>g</sup>Tannin content in extracts expressed in gallic acid equivalents (GAE).

<sup>h</sup>Tannin content in extracts expressed in catechin equivalents (CE).

Table 5. Results related to the extraction of tannins using water at high pressures and temperatures

Species	Plant part	Time (min)	T <sup>a</sup> (°C)	P (MPa)	Extraction yield (% w/w) <sup>a</sup>	Tannin content (mg/g <sub>DE</sub> ) <sup>b</sup>		References
<i>Vitis vinifera</i>	Seeds	30	50	10.34	4.20	615.47 <sup>c</sup>		(García-Marino et al., 2006)
			100		12.40	405.67 <sup>c</sup>		
			150		37.70	505.44 <sup>c</sup>		
<i>Terminalia chebula</i>	Fruits	37.50	120	4	---	15.57 <sup>d*</sup>		(Rangsriwong et al., 2009)
			180			21.43 <sup>d*</sup>		
			220			3.95 <sup>d*</sup>		
<i>Punica granatum</i>	Peels	5	40	10.34	43.30	21.94 <sup>c</sup>	610.39 <sup>e</sup>	(Çam and Hışıl, 2010)
<i>Phyllanthus niruri</i>	Stem and aerial parts	60	100	5	21.50	100.46 <sup>d</sup>		(Markom et al., 2010a)
				10	23.21	102.11 <sup>d</sup>		
				15	24.50	95.92 <sup>d</sup>		
				25	23.35	90.36 <sup>d</sup>		
<i>Rosmarinus officinalis</i>	Leaves	20	200	10.34	15.00	192.84 <sup>f</sup>		(Plaza et al., 2010)
<i>Thymus vulgaris</i>					14.80	188.48 <sup>f</sup>		
<i>Verbena officinalis</i>					8.00	81.14 <sup>f</sup>		
<i>Vitis vinifera</i>	Pomace	30	120	8	---	12.29 <sup>c*</sup>		(Aliakbariana et al., 2012)
				11.50		14.35 <sup>c*</sup>		
				15		11.52 <sup>c*</sup>		
<i>Vitis vinifera</i>	Pomace	5	100	10.34	---	52.90 <sup>c</sup>		(Vergara-Salinas et al., 2013)
			200			18.30 <sup>c</sup>		
<i>Larix europaea</i>	Barks	30	100	2	10.50	381.90 <sup>e</sup>		(Ravber et al., 2015)
<i>Phyllanthus amarus</i>	Aerial parts	15	107.60	11	---	0.54 <sup>f*</sup>		(Sousa et al., 2016)
			150.00			3.15 <sup>f*</sup>		
			192.40			4.14 <sup>f*</sup>		
<i>Viola × wittrockiana</i>	Flowers	15	---	250	---	93.86 <sup>e*</sup>		(Fernandes et al., 2017)
<i>Ficus carica</i>	Industry fermented byproducts	30	---	0.1	5.32	0.46 <sup>c*</sup>		(Alexandre et al., 2017)
				300	6.61	0.53 <sup>c*</sup>		
				600	7.13	0.49 <sup>c*</sup>		
<i>Pistacia vera</i>	Hulls	50	110	6.9	59.10	41.46 <sup>g</sup>		(Erşan et al., 2018)
			150		70.90	45.84 <sup>g</sup>		
			190		65.30	31.24 <sup>g</sup>		

\*Results expressed in mg of tannins per gram of dry matter.

<sup>a</sup>Extraction yield expressed in grams of extracts per grams of material.

<sup>b</sup>DE= dry extract.

<sup>c</sup>Tannin content in extracts expressed in catechin equivalents (CE).

<sup>d</sup>Hydrolysable tannin content in extracts (gallotannins+ellagitannins+coraligin).

<sup>e</sup>Tannin content in extracts expressed in tannic acid equivalents (TAE)

<sup>f</sup>Tannin content in extracts expressed in gallic acid equivalents (GAE)

<sup>g</sup>Gallotannin content in extracts obtained by HPLC

Table 6. Results devoted to the extraction of tannins assisted by microwave

Species	Plant part	Extraction conditions					Extraction Yield (% w/w) <sup>a</sup>	Tannin content (mg/g <sub>DM</sub> <sup>a</sup> )		References
		Solvent	S/L (g/mL)	T (°C)	Time (min)	Power (W)				
<i>Vitis vinifera</i>	Seed	Methanol (90%)	1:15	73	3.33	30	15.12	429.00 <sup>c*</sup>		(Hong et al., 2001)
<i>Radix puerariae</i>	Whole plant	Ethanol (70%)	1:20	---	6.50	255	---	5.75 <sup>d</sup>		(Wang et al., 2010)
			1:30					8.00 <sup>d</sup>		
			1:40					6.25 <sup>d</sup>		
<i>Cinnamomum zeylanicum</i>	Leaves	Ethanol (50%)	1:20	50	18.00	200	---	16.79 <sup>e</sup>		(Gallo et al., 2010)
<i>Crocus sativus</i>	Powder							29.39 <sup>e</sup>		
<i>Coriandrum sativum</i>	Seeds							0.82 <sup>e</sup>		
<i>Cuminum cyminum</i>								11.59 <sup>e</sup>		
<i>Agrimonia pilosa</i>	Stems and roots	Acetone	1:35	30	15.00	300	---	99.95 <sup>e</sup>		(Jin et al., 2010)
						500		128.65 <sup>e</sup>		
						700		107.00 <sup>e</sup>		
<i>Buddleia officinalis</i>	Whole plant	Ethanol (75%)	1:10	78	10	900	---	55.5 <sup>f*</sup>		(Pan et al., 2010)
		Ethanol (95%)						62.00 <sup>f*</sup>		
		Ethanol pure						58.50 <sup>f*</sup>		
<i>Vitis vinifera</i>	Seeds	Ethanol (70%)	1:40	60	2.00	125	16.40	528.05 <sup>e*</sup>		(Li et al., 2011)
<i>Pinus radiata</i>	Bark	Acetone (70%)	1:10	25	3.00	900	10.40	523.69 <sup>f*</sup>		(Aspé and Fernández, 2011)
<i>Rosmarinus officinalis</i>	Leaves	Methanol (70%)	1:5	70	5.00	180	---	3.48 <sup>d</sup>		(Švarc-Gajić et al., 2013)
						320		3.90 <sup>d</sup>		
						800		3.25 <sup>d</sup>		
<i>Pinus pinaster</i>	Bark	Acetone (80%)	1:20	---	3.00	100	13.60	48.98 <sup>f*</sup>		(Chupin et al., 2015)
<i>Myrtus communis</i>	Leaves	Ethanol (42%)	1:32	---	1.04	500	---	32.65 <sup>g</sup>		(Dahmoune et al., 2015)
<i>Acacia mollissima</i>	Bark	Water	1:20	---	5.00	150	---	47.64 <sup>h</sup>	0.09 <sup>c</sup>	(Naima et al., 2015)
		Ethanol						30.29 <sup>h</sup>	0.03 <sup>c</sup>	
<i>Eucalyptus globulus</i>	Leaves	Ethanol (45%)	1:30	---	4.50	340	---	4.11 <sup>f</sup>		(Huma et al., 2018)

\*Results expressed in mg of tannins per gram of dry extract.

<sup>a</sup>Extraction yield expressed in grams of extracts per grams of material.

<sup>b</sup>DM= dry matter.

<sup>c</sup>Tannin content in extracts expressed in tannic acid equivalents (TAE).

<sup>d</sup>Rutin content in the extracts (RC).

<sup>e</sup>Tannin content in extracts expressed in gallic acid equivalents (GAE).

<sup>f</sup>Tannin content in extracts expressed in catechin equivalents (CE).

<sup>g</sup>Amount of condensed tannins precipitated from extracts (CTP).

<sup>h</sup>Tannin content in extracts expressed in cyaniding equivalents (CyE).



Table 7. Results related to the extraction of tannins assisted by ultrasound

Species	Plant part	Extraction conditions					Extraction Yield (% w/w) <sup>a</sup>	Tannin content (mg/g <sub>DM</sub> ) <sup>b</sup>	References
		Solvent	S/L (g/mL)	T (°C)	Time (min)	Power (W)			
<i>Leucaena spp</i>	Leaves	Acetone 70%	1:50	25	15	---	---	86.10 <sup>c</sup>	(Dalzell and Kerven, 1998)
					20			89.80 <sup>c</sup>	
					30			88.10 <sup>c</sup>	
<i>Betula alleghaniensis</i>	Foliage	Ethanol (95%)	---	20	30	750	14.80	43.00 <sup>d*</sup>	(Diouf et al., 2009)
<i>Averrhoa carambola</i>	Fruit	Methanol	1:10	25	15	135	4.80	11.70 <sup>e*</sup>	(Annegowda et al., 2012)
					30		4.70	11.20 <sup>e*</sup>	
					45		4.30	10.90 <sup>e*</sup>	
<i>Vitis vinifera</i>	Full berry	Ethanol (50%)	1:10	10	6	200	---	6.00 <sup>f</sup>	(Carrera et al., 2012)
<i>Vitis vinifera</i>	Seeds	Methanol	1:10	30	15	150	---	61.80 <sup>e</sup>	(Da Porto et al., 2013)
<i>Areca catechu</i>	Nuts	Acetone (80%)	1:10	---	37.50	10	---	44.53 <sup>e</sup>	(Chavan and Singhal, 2013)
						50		101.60 <sup>e</sup>	
						90		37.02 <sup>e</sup>	
<i>Withania somnifera</i>	Roots	Ethanol	1:10	25	20	480	3.17	29.15 <sup>g*</sup>	(Dhanani et al., 2013)
		Ethanol (10%)					9.08	22.12 <sup>g*</sup>	
		Water					10.27	18.18 <sup>g*</sup>	
<i>Quercus brantii</i>	Leaves	Methanol (50%)	1:20	60	45	140	21.10	104.50 <sup>e*</sup>	(Tabaraki et al., 2013)
		Methanol (90%)					25.30	127.00 <sup>e*</sup>	
<i>Pistacia lentiscus</i>	Leaves	Ethanol (40%)	1:50	---	15	130	---	35.94 <sup>f</sup>	(Dahmoune et al., 2014)
<i>Rubus fruticosus</i>	Fruits	Ethanol	1:2.50	25	15	60	5.30	5.09 <sup>h*</sup>	(Ivanovic et al., 2014)
					30		5.90	25.42 <sup>h*</sup>	
<i>Phyllanthus amarus</i>	Aerial parts	Deionized water	---	25	7	301	---	27.23 <sup>g</sup>	(Sousa et al., 2016)
<i>Cannabis sativa</i>	Flowers, leaves and seed husks	Methanol (80%)	1:25	---	15	90	8.75	31.44 <sup>d</sup>	(Agarwal et al., 2018)
						120	11.29	40.39 <sup>d</sup>	
						150	9.68	39.19 <sup>d</sup>	
<i>Piper betle</i>	Leaves	Ethanol (78.74%)	1:21.85	51.60	30	400	13.71	21.5 <sup>i</sup>	(Ali et al., 2018)
<i>Vitis vinifera</i> (Tempranillo)	Pomace	Ethanol (44%)	1:5	50	3	500	---	86.67 <sup>f</sup>	(Poveda et al., 2018)

\*Results expressed in mg of tannins per gram of dry extract.

<sup>a</sup>Extraction yield expressed in grams of extracts per grams of material.

<sup>b</sup>DM= dry matter.

<sup>c</sup>Tannin content in extracts expressed in L leucocephale proanthocyanidin equivalents (LPAE).

<sup>d</sup>Tannin content in extracts expressed in quercetin equivalents (QE).

<sup>e</sup>Tannin content in extracts expressed in catechin equivalents

<sup>f</sup>Total content of condensed tannins in extracts (TCT).

<sup>g</sup>Tannin content in extracts expressed in gallic acid equivalents (GAE).

<sup>h</sup>Total tannin content in extracts (TTC).

<sup>i</sup>Tannin content in extracts expressed in rutin equivalents (RE).

ACCEPTED MANUSCRIPT

Table 8. Results devoted to the assessment and comparison of the different tannins extraction methods

Species	Plant part	Extraction technique	Extraction conditions	Extraction yield (% w/w) <sup>a</sup>	Tannin content (mg/g <sub>DE</sub> ) <sup>b</sup>	Reference
<i>Pistachia Vera</i>	Hulls	SLE	Methanol-1:4 25°C, 6h	---	32.80 <sup>d</sup>	(Goli et al., 2005)
		SFE	SCCO <sub>2</sub> <sup>c</sup> co-solvent- 15%Methanol 45°C-15 min. 35.46MPa		6.55 <sup>d</sup>	
		UAE	Methanol-1:8 45 min.		32.80 <sup>d</sup>	
<i>Terminalia chebula</i>	Fruit	SLE	Ethanol-1:15 78.3°C, 240 min	---	9.92 <sup>e</sup>	(Rangsriwong et al., 2009)
			Water-1:15 100°C, 120 min		15.96 <sup>e</sup>	
		PWE	Water 180°C, 37.5 min 4MPa		21.43 <sup>e</sup>	
<i>Pinus radiata</i>	Bark	SLE	Acetone (70%)-1:10 82°C, 180 min.	12.00	62.10 <sup>f</sup>	(Aspé and Fernández, 2011)
		UAE	Acetone (70%)-1:10 25°C, 6 min. 85W	9.50	47.2 <sup>f</sup>	
		MAE	Acetone (70%)-1:10 25°C, 3 min. 900W	10.40	55.4 <sup>f</sup>	
<i>Galla chinensis</i>	Whole plant	EtOH+UAE+MAE	Ethanol-1:15 Microwave 400W+ Ultrasound 50W 1 min	---	543.50 <sup>g*</sup>	(Lu et al., 2012)
		IL+UAE+MAE	1-butyl-3- methylimidazole bromide [C4mim]Br-1:15 Microwave 400W+ Ultrasound 50W 1 min		630.20 <sup>g*</sup>	
		MAE	Ethanol-1:15 400W 1 min		528.50 <sup>g*</sup>	
		UAE	Ethanol-1:15 50W 1 min		491.20 <sup>g*</sup>	
<i>Camellia sinensis</i>	Leaves and aerial parts	SLE	Ethanol (30%)-1:10 40°C, 2h	---	180 <sup>g</sup>	(Ribeiro et al., 2013)
		ILE	1-ethyl-3- methylimidazolium chloride [C2mim]Cl (50%) 40°C, 2h, 1:10	---	300 <sup>g</sup>	

<i>Rubus sp.</i>	Bagasse	SLE	Ethanol-1:31.60 50°C, 6-8h	14.58	4.25 <sup>g*</sup>	(Reátegui et al., 2014)
		SFE	SCCO <sub>2</sub> <sup>c</sup> no cosolvent, 15MPa 120 min.	6.84	4.07 <sup>g*</sup>	
		SFE+UAE	SCCO <sub>2</sub> <sup>c</sup> no cosolvent, 15 MPa 400W, 57 min.	7.94	3.53 <sup>g*</sup>	
			SCCO <sub>2</sub> <sup>c</sup> cosolvent- 10%Ethanol, 15MPa 200W, 57 min	18.25	12.73 <sup>g*</sup>	
<i>Solidago canadensis</i>	Bark	SLE	Ethanol (50%)-1:20 25°C, 30 min.	---	26.29 <sup>h</sup>	(Deng et al., 2015)
		UAE	Ethanol (50%)-1:20 30 min		30.15 <sup>h</sup>	
<i>Myrtus comunis</i>	Leaves	UAE	Ethanol (96%)-1:5.4 30 min. 320W	10.81	324.34 <sup>g*</sup>	(Pereira et al., 2017, 2016)
		SFE	SCCO <sub>2</sub> <sup>c</sup> co-solvent-Ethanol 45°C, 700 min. 23MPa	10.80	47.28- 94.56 <sup>g*</sup>	
<i>Berberis jaeschkeana</i>	Fruits	SLE	Methanol 80%-1:70 70°C-15 min.	---	21.41 <sup>d</sup>	(Belwal et al., 2017)
		UAE	Methanol 80%-1:70 70°C-15 min.		32.41 <sup>d</sup>	
		MAE	Methanol 80%-1:40 5 min. 670W		24.04 <sup>d</sup>	
<i>Myrtus communis</i>	Leaves	SLE	Ethanol 42%-1:50 120 min.	---	36.01 <sup>f</sup>	(Bouaoudia-Madi et al., 2017)
		MAE	Ethanol 42%-1:30 1 min 500W		34.50 <sup>f</sup>	
<i>Salacia chinensis</i>	Roots	SLE	Methanol-1:10 25°C, 360 min.	---	43.37 <sup>d</sup>	(Ghadage et al., 2017)
		UAE	Methanol-1:10 25°C, 10 min.		41.29 <sup>d</sup>	
		MAE	Methanol-1:10 25°C, 5 min. 180W		43.54 <sup>d</sup>	
<i>Erica carnea</i>	Aerial parts	SLE	Ethanol 96%-1:30 22°C, 7 days (maceration)	15.30	57.19 <sup>g</sup>	(Veličković et al., 2017)
		UAE	Ethanol 96%-1:20 30 min 216W	18.33	60.65 <sup>g</sup>	

		MAE	Ethanol 96%-1:20 30 min 600W	30.65	61.70 <sup>g</sup>	
		PWE	Water-1:20 140°C, 30 min. 4MPa	42.66	62.53 <sup>g</sup>	
<i>Lavatera thuringiaca</i>	Whole plant	SLE	Ethanol 96%-1:30 22°C, 8h	---	65.61 <sup>g*</sup>	(Mašković et al., 2018)
		UAE	Ethanol 96%-1:20 30 min 216W		71.78 <sup>g*</sup>	
		MAE	Ethanol 96%-1:20 30 min 600W		71.15 <sup>g*</sup>	
		PWE	Water-1:20 140°C, 30 min. 4MPa		72.23 <sup>g*</sup>	

\*Results expressed in mg of tannins per gram of dry matter.

<sup>a</sup>Extraction yield expressed in grams of extracts per grams of material.

<sup>b</sup>DE= dry extract.

<sup>c</sup>SCCO<sub>2</sub>= carbon dioxide at supercritical conditions.

<sup>d</sup>Tannin content in extracts expressed in tannic acid equivalents (TAE).

<sup>e</sup>Hydrolysable tannin content in extracts (HTC)

<sup>f</sup>Tannin content in extracts expressed in catechin equivalents (CE).

<sup>g</sup>Tannin content in extracts expressed in gallic acid equivalents (GAE).

<sup>h</sup>Total tannin content in the extracts (TTC).

