

Dynamics of Si surface nanostructures under electromigration

Stefano Curiotto, Ali El-Barraj, Fabien Cheynis, Pierre Muller, Frédéric Leroy

▶ To cite this version:

Stefano Curiotto, Ali El-Barraj, Fabien Cheynis, Pierre Muller, Frédéric Leroy. Dynamics of Si surface nanostructures under electromigration. C'Nano: The Nanoscience Meeting, Dec 2018, Toulon, France. 2019. hal-01955777

HAL Id: hal-01955777 https://hal.science/hal-01955777

Submitted on 14 Dec 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.





Dynamics of Si surface nanostructures under electromigration

Stefano Curiotto, Ali El-Barraj, Fabien Cheynis, Pierre Müller, Frédéric Leroy

Aix Marseille Université, CNRS, CINaM UMR7325, 13288 Marseille, France

Mass transport processes play an important role in nano devices. They determine the morphology and the stability of a working device, and eventually its lifetime. When a direct electric current is applied to a material, it affects the mass transport by adding a bias to the atomic diffusive motion. This effect, called electromigration, can play an important role on the dynamics and the morphological stability of nanostructures at surfaces. In this work we have studied the motion of single-step holes and islands under the effect of an electric field on Si(100), in real time, by Low Energy Electron Microscopy (LEEM). The details of the motion depend on the strong diffusion anisotropy of the Si dimer rows. Studying the velocity and the shape of the nanostructures, we discuss a model to explain and guide the motion of holes and islands.

The manipulation of nanostructures is an important challenge for nanoelectronics and nanofabrication technologies. External fields and thermal gradients are natural candidates to move and control the nanostructure position on a surface. Particularly promising is the use of electric fields to induce mass transport in specific directions, phenomenon known as electromigration (EM).

The elementary process of electromigration of an atom on a surface (adatom) is well known: the electric illumination current biases random diffusion inducing mass transport in specific directions. The motion of many optics adatoms results in the motion of an entire nanostructure.



While it has been neglected in most studies, the crystalline anisotropy of the surface may play an important role on adatom motion and therefore on nanostructure motion. We have used Low Energy Electron Microscopy (LEEM), to observe Si(100) surfaces in-situ and in real time with high temporal and spatial resolution, and in a large temperature range (1000-1500 K).

In order to support the experimental results and obtain more insights in the motion mechanism, we have developed a Kinetic Monte Carlo model based on both anisotropic and electromigration-biased diffusion at surfaces.

optioo	contrast aperture
	objective lens
UHV: P< 5x10 ⁻¹⁰ mbar	
variable T during deposition	sample (~ -20 kV)

Electron energy lower than 20 eV 5 nm lateral resolution High imaging dynamics (0.1 s per image) atomic vertical resolution

Si(100) surface reconstruction



The Si(100) surface structure has dimer rows running perpendicularly on alternating terraces. Diffusion is faster along dimer rows than perpendicularly to them.

Displacement of 2D voids under electromigration (EM)





Voids elongated perpendicularly to the EM force move opposite to the force.

Voids with shape parallel to the force move in the same direction of the force.





Schematics of a 2D void. The dimer rows inside the hole are oriented horizontally, in the same direction of **u**. The force exerted by the electric field is oriented along the blue arrow and forms an angle θ with **u**. The void displaces in a direction forming an angle γ with **u**. J_{ext} and J_{int} are the atomic fluxes at the exterior and at the interior of the void. D are diffusion coefficients parallele and perpendicular to dimer rows; v are hole and island velocities; *a* is an atomic length; c is the concentration of diffusion species

Conclusions

- The motion of nanostructures on Si(100) is possible thanks to the difference of diffusion coefficient parallel or perpendicular to dimer rows.
- The effective activation energy for the motion of 2D islands and voids at Si(100) surfaces is 2.0±0.1 eV, given by the sum of a diffusion energy and a creation energy of the diffusing species

This work was performed in the framework of the ANR grant HOLOLEEM (ANR-15-CE09-0012). We are grateful to B. Ranguelov and M. Michailov for stimulating discussions had in the framework of the PHC Rila project (38663TB)) project. The poster is based on the paper: "2D nanostructure motion on anisotropic surfaces controlled by electromigration", S. Curiotto, P. Müller, A. El-Barraj, F. Cheynis, O. Pierre-Louis, and F. Leroy, Applied Surface Science, vol. 469 (2019) 463-470