



HAL
open science

Analyse thermographique des sources de chaleur accompagnant la fatigue à grand nombre de cycles

André Chrysochoos, Olivier Arnould, Thomas Boulanger, André Galtier

► To cite this version:

André Chrysochoos, Olivier Arnould, Thomas Boulanger, André Galtier. Analyse thermographique des sources de chaleur accompagnant la fatigue à grand nombre de cycles. Journée thématique SFT - Thermographie infrarouge appliquée à l'Automobile, PSA Peugeot-Citroën, Oct 2004, Poissy, France. hal-01961215

HAL Id: hal-01961215

<https://hal.science/hal-01961215>

Submitted on 2 Nov 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Thermographie infrarouge appliquée à l'Automobile

Journée thématique SFT du 13 octobre 2004
PSA PEUGEOT CITROËN - POISSY

***Analyse thermographique des sources
de chaleur accompagnant
la fatigue à grand nombre de cycles***



A. Chrysochoos*, O. Arnould*, T. Boulanger*, A. Galtier**

(*) LMGC, Université Montpellier II


(**) IRSID-ARCELOR, Mézières-les-Metz

Introduction

Evolution of the temperature during a cyclic loading




$$\theta = T - T_0 \text{ (}^\circ\text{C)}$$




[Luong,1998], [Risitano, 2000], ...

Trend of the mean temperature drift



[Luong, 1998] [Risitano, 2000]



Objectives

- Analysis of fatigue mechanisms in terms of heat rather than in terms of temperature
- Separate estimate of dissipative and thermoelastic sources (dissipation \ll thermoelasticity)
- Quantization of fatigue mechanisms (constitutive equations)
- New data and criteria for behaviour characterization and structure design

Thermodynamic aspects

1-Small Perturbation Hypothesis (SPH)

2-Fatigue : quasi-static process

GSM formalism

$$\rho C \dot{T} - \text{div}(k : \text{grad} T) = d_1 + s_{the} + \cancel{s_{ic}} + r_e$$


Thermal aspects

1D diffusion problem

$$s(x, t) \approx \rho C \left(\frac{\partial \theta}{\partial t} + \frac{\theta}{\tau_{th}^{1D}} - \delta_{th} \frac{\partial^2 \theta}{\partial x^2} \right)$$

Image processing (1D)

$$\rho C \left(\frac{\partial \theta}{\partial t} + \frac{\theta}{\tau_{th}} - \delta_{th} \frac{\partial^2 \theta}{\partial x^2} \right) = d_1 + s_{the}$$



In phase with the loading

$$w_{the} = \oint_{Cycle} s_{the} d\tau = 0$$

Slow evolution of mean dissipation

$$\oint_{Cycle} f_L \cdot d_1 d\tau = \bar{d}_1$$

Local least-squares fitting

$N \approx 5, 30$ cycles







$M \approx 3, 15$ pixels

$$\theta(x,t) = \underbrace{p_1(x)t + p_2(x)}_{\text{drift}} + \underbrace{p_3(x)\cos(2\pi f_L t) + p_4(x)\sin(2\pi f_L t)}_{\text{periodic response}}$$

Data processing validation (1D)


$$\Delta s_{\text{the}}(x), d_1(x) = \bar{d}_1$$

$$\Delta s_{\text{the}} \gg \bar{d}_1$$




Distribution of \bar{d}_1 during a loading block

Steel




Mean profiles of $\langle \bar{d}_1 \rangle$ for different loading blocks



Steel

$$\Delta\sigma_1 > \Delta\sigma_2 > \Delta\sigma_3 > \Delta\sigma_4$$

First trial of 2D distribution of dissipation 1D^{1/2} !!




Steel

2D distribution of thermoelastic source

« True » 2D !

A. E. Morabito, UMII
+ Lecce, Italy


Failure ; block # 15



Pre-localization of crack onset

Aluminium


Block 3



[°C/s]


$$\frac{\Delta S_{the}}{\rho C}$$

Block 15



Y Axis / (pixel)

Block 15: failure



Y Axis / (pixel) 11

Concluding comments

- **Image processing** : s_{the} , \vec{d}_1 separately identified ($|s_{the}| \gg \vec{d}_1$)
- **Thermoelastic coupling** \Leftrightarrow state equation
- **Dissipation** \Leftrightarrow evolution equation
- **Fatigue limit** : **???**

heterogeneous fatigue tests
1D, 2D (near future)
(0D : *Int. J. of Fatigue* 2004)

Local analysis : material/structure

DIC + IRT : combined image processing