



**HAL**  
open science

## GaN surface as the source of non-radiative defects in InGaN/GaN quantum wells

C. Haller, J.-F. Carlin, Gwenolé Jacopin, W. Liu, D. Martin, R. Butté, N.  
Grandjean

► **To cite this version:**

C. Haller, J.-F. Carlin, Gwenolé Jacopin, W. Liu, D. Martin, et al.. GaN surface as the source of non-radiative defects in InGaN/GaN quantum wells. Applied Physics Letters, 2018, 113 (11), pp.111106. 10.1063/1.5048010 . hal-01981711

**HAL Id: hal-01981711**

**<https://hal.science/hal-01981711>**

Submitted on 18 Dec 2020

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# GaN surface as the source of non-radiative defects in InGaN/GaN quantum wells

C. Haller,<sup>a)</sup> J.-F. Carlin, G. Jacopin, D. Martin, R. Butté, and N. Grandjean

*Institute of Physics, Ecole Polytechnique Fédérale de Lausanne (EPFL), CH-1015, Lausanne, Switzerland*

(Dated: 10 July 2018)

Blue light-emitting diodes based on III-nitride semiconductors are nowadays widely used for solid-state lighting. They exhibit impressive figures of merit like an internal quantum efficiency close to 100%. This value is intriguing when considering the high dislocation density running throughout the InGaN/GaN quantum well (QW) active region. This striking feature is currently ascribed to carrier localization occurring in the InGaN alloy, which hinders their diffusion toward non-radiative recombination centers. However, it was recently reported that another source of defects, disconnected from dislocations, dramatically decreases the radiative efficiency of InGaN/GaN QWs. Those defects, present at the surface, are usually trapped in an InGaN underlayer (UL), which is grown before the QW active region. To get insight into the trapping mechanism we varied the UL thickness, In content, and materials system (InGaN or InAlN) and studied the photoluminescence decay time at 300 K of a single InGaN/GaN QW. Our data demonstrate that nearly two defects are incorporated for three indium atoms whatever the UL materials. In addition, we show that those defects are created during the high-temperature growth of GaN and that they segregate at the surface even at low-temperature. Eventually, we propose an intrinsic origin for these surface defects.

III-nitride white light-emitting devices (LEDs), which consist of a blue LED covered by a yellow phosphor recently achieved a record luminous efficacy of 300 lm/W.<sup>1</sup> This spectacular performance must be credited to InGaN/GaN quantum wells (QWs), which form the active region of blue LEDs. When S. Nakamura reported the first high-brightness InGaN based LED,<sup>2</sup> the scientific community was astonished since the device grown on sapphire was full of dislocations (density  $> 10^9 \text{cm}^{-2}$ ), which act as non-radiative recombination centers (NRCs).<sup>3</sup> The defect-insensitivity of InGaN/GaN QWs was then ascribed to the intrinsic properties of InGaN alloy: carrier are strongly localized due to large potential fluctuations induced by random alloy disorder<sup>4</sup> hindering their diffusion towards NRCs.<sup>5</sup> Besides dislocations, point defects such as impurities or vacancies are another common source of NRCs in semiconductor optoelectronic devices. In this vein, Armstrong *et al.* pointed out the detrimental impact of deep level defects on the efficiency of blue LEDs.<sup>6</sup> In particular, they showed that the density of NRCs in InGaN/GaN QWs decreases if an InGaN thick layer is deposited before the growth of the active region. In fact such an InGaN underlayer (UL), or InGaN/GaN superlattice, is commonly used in high efficiency commercial blue LEDs grown by metal-organic chemical vapor deposition (MOCVD). Its role is to trap surface defects (SDs) and avoid their further incorporation into the InGaN/GaN active region.<sup>6-8</sup> It was also noticed that this effect holds when InGaN QWs are grown on free-standing GaN substrates, which indicates that dislocations are not at play.<sup>7</sup>

In this study, we show that the defects buried in the InGaN UL are intrinsic to the GaN surface. They form at

high temperature ( $> 900^\circ\text{C}$ ) and segregate at the surface even for low growth temperatures ( $< 800^\circ\text{C}$ ). In turn, they are incorporated in indium containing layers (InGaN or InAlN) where they create NRCs.

Samples were grown by MOCVD either in a vertical Aixtron 3x2" CCS system (reactor 1) or a horizontal Aixtron 200/4 RF-S system (reactor 2). Substrates are *c*-plane sapphire (dislocation density of about  $10^9 \text{cm}^{-2}$ ) or *c*-plane freestanding (FS) GaN (dislocation density  $\sim 10^6 \text{cm}^{-2}$ ). The common structure for all the samples is a GaN buffer, an InGaN (InAlN) UL, a GaN spacer, an InGaN single (S)QW and a GaN cap of 50 nm. The buffer is grown using trimethylgallium (TMGa) and  $\text{H}_2$  as carrier gas at a temperature of  $1000^\circ\text{C}$ . For the growth of the InGaN (InAlN) alloy, the GaN spacer and the GaN cap, the carrier gas is switched to  $\text{N}_2$ . The InGaN UL is grown using trimethylindium (TMIn) and triethylgallium (TEGa) at a temperature of  $770^\circ\text{C}$ . The InAlN UL is grown using TMIn and trimethylaluminum (TMAl) at a temperature of  $750^\circ\text{C}$ . The SQW growth temperature is  $750 - 755^\circ\text{C}$ , the indium composition 12% and the thickness 2.7 nm. Time-resolved photoluminescence (TRPL) was performed using a streak camera operating in synchroscan mode. We used the third harmonic of a mode-locked Ti:sapphire laser emitting at 280 nm as excitation source. The pulse width is 2 ps and the repetition rate is 80.5 MHz. To extend the time window for long PL decay times, we used a pulse picker. For the InGaN QWs, the spectral window corresponds to the QW emission. Time-integrated PL (TIPL) was performed with the same excitation source as TRPL but the signal was integrated over several pulses (with an excitation power density of  $0.26 \text{ W/cm}^2$ ).

As shown in previous reports,<sup>6-8</sup> the role of InGaN UL in an LED structure is to bury SDs and ensure high efficiency InGaN/GaN active region. We first study

<sup>a)</sup>camille.haller@epfl.ch

the capture mechanism of these SDs by the InGaN UL. For that purpose, we grew a series of identical 2.7 nm  $\text{In}_{0.12}\text{Ga}_{0.88}\text{N}/\text{GaN}$  single SQWs (Series A) except for the thickness ( $d$ ) of the  $\text{In}_{0.03}\text{Ga}_{0.97}\text{N}$  UL, which was varied from 0 to 214 nm. PL measurements were performed at room temperature with a low excitation power density ( $0.26 \text{ W}/\text{cm}^2$ ). The PL intensity increases by more than two orders of magnitude between a bare SQW sample (without UL) and the SQW with an UL of 214 nm (Fig. 1(a)). The intensity first increases with the thickness and then saturates. One can also notice a slight red-shift of both the SQW and the UL emission energy for thick ULs, which might be ascribed to strain-dependent In incorporation.<sup>9</sup> Interestingly, the PL intensity of the InGaN UL also gets higher (see SM).

Additionally, we carried out TRPL experiments at 300 K to measure the QW effective lifetime and get insight into non-radiative (NR) processes. In agreement with the PL intensity behavior, the effective lifetime exhibits a huge improvement when the UL thickness increases (Fig. 1(b)). From 170 ps when no UL is inserted, it goes up to 20 ns for the thickest one. Notice that the nonexponential behavior at long delays has already been observed in InGaN/GaN QWs grown on bulk GaN substrates and ascribed to the saturation of slow dynamics NRCs.<sup>10</sup>

The dependence of the InGaN/GaN SQW optical properties with the thickness of the InGaN UL suggests the following mechanism: SDs are incorporated if In atoms are present at the surface and, once buried in InGaN layers, they create NRCs. This accounts well with former results, which showed, for instance, a strong improvement of the optical properties of multiple (M) QW structures compared to SQW.<sup>11–13</sup> Indeed, in this case, the first QWs in the MQW structure play the role of the InGaN UL by trapping SDs.

To account for the evolution of the QW decay time as a function of the InGaN UL thickness, we developed a model where the NR lifetime is a function of the SD concentration in the InGaN/GaN QWs.<sup>14</sup> First, we suppose that SDs segregate at the surface, with a surface concentration given by  $[SD] = \theta_0 R^N$ , where  $\theta_0$  is the initial surface density after the GaN growth at high temperature,  $N$  is the number of monolayers (ML) deposited ( $N = d/e_{\text{ML}}$  with  $e_{\text{ML}}$  the InGaN ML thickness), and  $R$  the segregation coefficient.<sup>15</sup> Previous observations by Akasaka *et al.*<sup>8</sup> indicate that incorporation of SDs in GaN is negligible, i.e.  $R$  is close to 1. In contrast, SDs are incorporated in InGaN layers, i.e.  $R$  decreases. Assuming that SDs are buried upon interaction with In atoms, we can write  $R = R_{\text{GaN}} - xp$  with  $R_{\text{GaN}}$  the segregation of SDs in GaN,  $x$  the In composition of the InGaN layer, and  $p$  the interaction efficiency between In atoms and SDs. Then we express the effective lifetime of the QW as:  $1/\tau_{\text{eff}} = 1/\tau_0 + 1/\tau_{\text{NR,SD}}$ , with  $\tau_0$  the QW lifetime when SDs are all trapped into the InGaN UL, and  $\tau_{\text{NR,SD}}$  the NR lifetime induced by the incorporation of SDs. The latter is given by:  $1/\tau_{\text{NR,SD}} \propto [SD]_{\text{QW}}$ , with  $[SD]_{\text{QW}}$  the concentration of SDs in the QW. Finally, the QW




FIG. 1. (a) PL spectra recorded at 300 K for different InGaN UL thicknesses. (b) Corresponding normalized PL decay traces for a 80 ns time window and, Inset, for a time window of 4 ns.

effective lifetime can be expressed as:

$$\tau_{\text{eff}} = \tau_0 \frac{1}{1 + \tau_0 \alpha (R_{\text{GaN}} - xp)^N} \quad (1)$$

with  $\alpha$ , a constant, which depends on  $\theta_0$  and the electron-hole capture coefficient of the NR defect (see SM). The experimental effective lifetime as a function of the InGaN UL thickness are fitted using Eq. 1 (Fig. 2(a), green line). The value for  $\tau_0$  is 18 ns, which is measured for a 214 nm thick InGaN UL. The composition and the thickness are measured by high resolution x-ray diffraction (HR-XRD) analysis. The best fit is obtained with an interaction efficiency of 0.7 ( $R = 0.9782$ ), which confirms the strong interaction of SDs with indium.

Next, a set of InGaN/GaN SQW samples (Series B) was prepared keeping constant the InGaN UL thickness (55 nm) but varying the In content (up to 16% to ensure pseudomorphic layer). It is worth noticing that we used another reactor (horizontal reactor) and the substrate was sapphire. The InGaN UL was deposited under slightly different growth conditions ( $T_g = 750^\circ\text{C}$  with  $\text{H}_2$  and  $\text{N}_2$  used as carrier gases). The QW effective lifetimes for this sample series are displayed in Fig. 2(b). Eq. (1) still with  $p = 0.7$  reproduces well the QW effective lifetime. Note that  $\tau_0$  is 3.3 ns, which is smaller than the value measured on FS GaN substrate, which might be




FIG. 2. (a) Effective lifetime as a function of UL thickness for three different materials: InGaN UL in green (Series A), GaN UL in blue (Series D) and InAlN UL in orange (Series C). (b) Effective lifetime as a function of InGaN UL composition (Series B). The dots are experimental data and the lines are fits based on Eq. (1) using an interaction efficiency  $p = 0.7$ .

due to a higher dislocation density. A piece of information is that SDs are present whatever the reactor type: vertical design with stainless steel showerhead for reactor 1 or horizontal design with quartz liner (no stainless steel) for reactor 2.

We then checked whether SD trapping is specific to InGaN layers. To this end, we prepared a series of InGaN/GaN SQWs grown on FS-GaN substrate with In<sub>0.15</sub>Al<sub>0.85</sub>N UL (series C). Notice that the In<sub>0.15</sub>Al<sub>0.85</sub>N alloy is under slight tensile strain for this composition.<sup>16</sup> The PL decay time of the InGaN/GaN SQWs dramatically increases with the InAlN UL thickness (Fig 2(a)). Due to the high indium content in the InAlN layer, the thickness needed to reach the saturation of the effective lifetime is only 20 nm. The data in Fig. 2(a) were fitted with Eq. (1) with  $p = 0.7$  ( $R = 0.8942$ ), as for InGaN UL. To further emphasize the critical role of indium, we grew an additional series of InGaN/GaN SQW samples where the UL was replaced by a pure GaN layer grown at 770°C (series D). The PL decay time exhibits a slight increase with GaN thickness (Fig. 2(a)). Fitting the data with Eq. (1) (with  $x = 0$ ) leads to  $R_{\text{GaN}} = 0.99915$ . This high  $R$  value confirms the strong surface segregation of SDs in GaN even at a growth temperature as low as 770°C. Consequently, 2  $\mu\text{m}$  of GaN grown at 770°C would be required to trap all SDs. This highlights the need of indium in the UL, as already pointed out by Akasaka *et al.*<sup>8</sup>

Although the phenomenological model we propose accounts well for the dependence of the QW effective life-

time on the InGaN (InAlN) UL thickness or composition, it does not provide any insights into the nature of those SDs. In the literature, capture coefficients for impurities and complexes range between  $10^{-6}$  and  $10^{-8}$   $\text{cm}^3\text{s}^{-1}$ ,<sup>17-20</sup> corresponding to impurity densities comprised between  $10^{15}$  and  $10^{17}\text{cm}^{-3}$ .

We carried out secondary ion mass spectrometry (SIMS) and searched for Fe, Ca, O, C, Mg, which are supposed to be detrimental to the radiative efficiency of InGaN QWs.<sup>17,21-25</sup> SIMS measurements did not allow us establishing any straightforward relationship between those impurities and the QW effective lifetime. However, one could argue that the SIMS detection limit was too high (around  $10^{16}\text{cm}^{-3}$ ) or that we missed the relevant impurity.

Based on previous results, SDs should have the following properties: (i) once incorporated into InGaN layers they create efficient NRCs, (ii) they strongly interact with indium atoms, and (iii) their concentration should range between  $10^{15}$  and  $10^{17}\text{cm}^{-3}$ . Another intriguing observation is that SDs are present whatever the MOCVD growth reactor type. It is also a common feature that InGaN/GaN SQWs grown without InGaN UL exhibit a poor radiative efficiency.<sup>11-13</sup> We therefore postulate that SDs could not be impurities but rather intrinsic point defects, which form during the growth of GaN at high temperature.

To investigate the dependence of the density of SDs on growth temperature, we prepared a new series (Series E) of InGaN/GaN SQW samples with InGaN UL, but with a GaN spacer deposited at various temperatures  $T_{\text{GaN}}$  (Fig. 3). Increasing the growth temperature  $T_{\text{GaN}}$  from 770°C to 1020°C leads to a rapid collapse of the QW PL intensity (Fig. 3). The effective lifetimes measured at 300 K are displayed in log scale as a function of  $1000/T_{\text{GaN}}$  (Inset, Fig. 3). Using the previous model and assuming that the SD density  $\theta_0$  scales as  $\exp\left(-\frac{E_a}{k_B T_{\text{GaN}}}\right)$ , we extracted an activation energy of 3.6 eV. Interestingly, this value is close to the activation energy reported in the literature for the decomposition of GaN.<sup>26,27</sup>

The dependence of the SD density on growth temperature suggests intrinsic point defects whose creation rate might be enhanced at the GaN near surface region. Indeed, the defect formation energy may be significantly different from the bulk formation energy.<sup>28</sup> In addition, vacancies tend to diffuse towards the surface, as observed in other materials.<sup>29</sup>

We could thus infer that the GaN surface and near surface region provide a reservoir of point defects, which segregate at the surface until they react with indium atoms. Once buried, due to the interaction with indium, they form NRCs.

Let us consider the most likely points defects, which are gallium and nitrogen vacancies. Gallium vacancies ( $V_{\text{Ga}}$ ) in GaN epilayers grown by MOCVD have been discussed back to 1996 and proposed to be responsible for the yellow-band luminescence.<sup>30</sup> In GaN homoepitaxial layers, two energy levels associated to  $V_{\text{Ga}}$  com-




FIG. 3. PL spectra recorded at 300 K for a sample with a spacer grown at different temperatures ( $T_{\text{GaN}}$ ). Inset: InGaN SQW effective lifetime (red points) as a function of  $1000/T_{\text{GaN}}$ . The red line corresponds to the calculated effective lifetimes assuming thermally activated SDs ( $E_a = 3.6$  eV).

plexes have been determined by deep level spectroscopy:  $E_c - 0.56$  eV and  $E_c - 0.23$  eV.<sup>31</sup> These values are far from the energy level  $E_c - 1.62$  eV that was identified to be related to the creation of NRCs by SDs in InGaN/GaN QWs.<sup>6</sup> Recently, theoretical calculations have pointed out that  $V_{\text{Ga}}$  are unlikely in bulk GaN, but instead complexes with oxygen and hydrogen are.<sup>20,32</sup> This would mean that oxygen and hydrogen could be detected by SIMS if their density were high enough, which is not the case in our samples (see SM). In addition, Dreyer *et al.* computed the impact of these  $V_{\text{Ga}}$  complexes on NR recombinations in InGaN layer and found that they play a marginal role below 15% In content.<sup>20</sup> Thus  $V_{\text{Ga}}$  and related complexes are not expected to dramatically impact the efficiency of the present InGaN/GaN QWs, which have an indium content of 12%.

It is commonly admitted that the concentration of nitrogen vacancies ( $V_{\text{N}}$ ) in bulk GaN is very low due to their large formation energy.<sup>28</sup> However, the formation energy of vacancies at semiconductor surface may be significantly smaller.<sup>33</sup> It was also proposed that during the decomposition of GaN, nitrogen atoms dissociate from the surface and form  $\text{N}_2$  molecules, leading to a nitrogen-poor growth front, which could be a source of  $V_{\text{N}}$ .<sup>27,34,35</sup> Therefore, if  $[V_{\text{N}}]$  is low in bulk GaN, this might be no longer the case at the GaN surface. Notice that the predominance of anion vacancies near the surface was already pointed out in common III-V semiconductors.<sup>33</sup>

The present study points out the strong affinity of SDs with indium atoms. A theoretical study predicts that the formation energy of  $V_{\text{N}}$  in the presence of indium is decreased.<sup>36,37</sup> Therefore, the scenario could be the following:  $V_{\text{N}}$  are created near the surface during high temperature growth of GaN. Once formed, they segregate at the surface even for LT growth GaN due to their high formation energy in bulk GaN.<sup>38</sup> In the presence of

indium atoms, the segregation process is quenched:  $V_{\text{N}}$  are incorporated in the bulk due to a decrease of their formation energy in InGaN. This is consistent with the formation of stable  $V_{\text{N}}$  and In complexes as theoretically predicted.<sup>39,40</sup>

In conclusion, we studied the origin of surface defects in GaN, which dramatically reduce the efficiency of InGaN/GaN QWs. We proposed that the rather low stability of GaN at high temperature induces nitrogen vacancies at the surface. Those  $V_{\text{N}}$  strongly segregate, even during low-temperature growth of GaN. In contrast,  $V_{\text{N}}$  are incorporated in indium containing layers (InGaN or InAlN), where they create NRCs. We thus propose that the role of the InGaN UL is to capture preexisting  $V_{\text{N}}$  at the GaN surface. Hence, our results shed new light on the physics and fabrication of high performance III-nitride based optoelectronic devices.

## SUPPLEMENTARY MATERIAL

See supplementary material for complementary information.

## ACKNOWLEDGMENTS

The authors would like to thank W. Liu for his help with TRPL measurements and Dr. G. Callsen for useful discussion. This work was supported by the CTI-KTI project “High power GaN-lasers for white light generation” 17519.1 PFEN-NM.

- <sup>1</sup>S. Nakamura, “Background Story of the Invention of Efficient InGaN Blue-Light-Emitting Diodes (Nobel Lecture),” *Angewandte Chemie International Edition* **54**, 7770–7788 (2015).
- <sup>2</sup>S. Nakamura, M. Senoh, and T. Mukai, “P-GaN/N-InGaN/N-GaN Double-Heterostructure Blue-Light-Emitting Diodes,” *Japanese Journal of Applied Physics* **32**, L8–L11 (1993).
- <sup>3</sup>D. Cherns, S. J. Henley, and F. A. Ponce, “Edge and screw dislocations as nonradiative centers in InGaN/GaN quantum well luminescence,” *Applied Physics Letters* **78**, 2691–2693 (2001).
- <sup>4</sup>S. F. Chichibu, A. Uedono, T. Onuma, B. A. Haskell, A. Chakraborty, T. Koyama, P. T. Fini, S. Keller, S. P. DenBaars, J. S. Speck, U. K. Mishra, S. Nakamura, S. Yamaguchi, S. Kamiyama, H. Amano, I. Akasaki, J. Han, and T. Sota, “Origin of defect-insensitive emission probability in In-containing (Al,In,Ga)N alloy semiconductors,” *Nature Materials* **5**, 810–816 (2006).
- <sup>5</sup>J.-M. Gerard and C. Weisbuch, “Semiconductor structure for optoelectronic components with inclusions,” US Patent , US5075742A (1991).
- <sup>6</sup>A. M. Armstrong, B. N. Bryant, M. H. Crawford, D. D. Koleske, S. R. Lee, and J. J. Wierer, “Defect-reduction mechanism for improving radiative efficiency in InGaN/GaN light-emitting diodes using InGaN underlayers,” *Journal of Applied Physics* **117**, 134501 (2015).
- <sup>7</sup>C. Haller, J.-F. Carlin, G. Jacopin, D. Martin, R. Butté, and N. Grandjean, “Burying non-radiative defects in InGaN underlayer to increase InGaN/GaN quantum well efficiency,” *Applied Physics Letters* **111**, 262101 (2017).
- <sup>8</sup>T. Akasaka, H. Gotoh, T. Saito, and T. Makimoto, “High luminescent efficiency of InGaN multiple quantum wells grown on InGaN underlying layers,” *Applied Physics Letters* **85**, 3089 (2004).

- <sup>9</sup>G. Schmidt, M. Müller, P. Veit, F. Bertram, J. Christen, M. Glauser, J.-F. Carlin, G. Cosendey, R. Butté, and N. Grandjean, “Nano-scale luminescence characterization of individual InGaN/GaN quantum wells stacked in a microcavity using scanning transmission electron microscope cathodoluminescence,” *Applied Physics Letters* **105**, 032101 (2014).
- <sup>10</sup>M. Dworzak, T. Stempel, A. Hoffmann, G. Franssen, S. Grzanka, T. Suski, R. Czernecki, M. Leszczynski, and I. Grzegory, “Luminescence Efficiency of InGaN/GaN Quantum Wells on Bulk GaN Substrate,” *Materials Research Society Symposium Proceeding* **892**, 825 (2006).
- <sup>11</sup>M. S. Minsky, S. B. Fleischer, A. C. Abare, J. E. Bowers, E. L. Hu, S. Keller, and S. P. Denbaars, “Characterization of high-quality InGaN/GaN multiquantum wells with time-resolved photoluminescence,” *Applied Physics Letters* **72**, 1066–1068 (1998).
- <sup>12</sup>C. Prall, C. Kaspari, F. Brunner, K. Haberland, M. Weyers, and D. Rueter, “In-situ photoluminescence measurements during MOVPE growth of GaN and InGaN MQW structures,” *Journal of Crystal Growth* **415**, 1–6 (2015).
- <sup>13</sup>S. F. Chichibu, H. Marchand, M. S. Minsky, S. Keller, P. T. Fini, J. P. Ibbetson, S. B. Fleischer, J. S. Speck, J. E. Bowers, E. Hu, U. K. Mishra, S. P. DenBaars, T. Deguchi, T. Sota, and S. Nakamura, “Emission mechanisms of bulk GaN and InGaN quantum wells prepared by lateral epitaxial overgrowth,” *Applied Physics Letters* **74**, 1460–1462 (1999).
- <sup>14</sup>Y. Kawakami, K. Omae, A. Kaneta, K. Okamoto, T. Izumi, S. Sajou, K. Inoue, Y. Narukawa, T. Mukai, and S. Fujita, “Radiative and Nonradiative Recombination Processes in GaN-Based Semiconductors,” *physica status solidi (a)* **183**, 41–50 (2001).
- <sup>15</sup>K. Muraki, S. Fukatsu, Y. Shiraki, and R. Ito, “Surface segregation of In atoms during molecular beam epitaxy and its influence on the energy levels in InGaAs/GaAs quantum wells,” *Applied Physics Letters* **61**, 557–559 (1992).
- <sup>16</sup>R. Butté, J.-F. Carlin, E. Feltn, M. Gonschorek, S. Nicolay, G. Christmann, D. Simeonov, A. Castiglia, J. Dorsaz, H. J. Buehlmann, S. Christopoulos, G. Baldassarri Höger von Hög, A. J. D. Grundy, M. Mosca, C. Piquier, M. A. Py, F. Demangeot, J. Frandon, P. G. Lagoudakis, J. J. Baumberg, and N. Grandjean, “Current status of AlInN layers lattice-matched to GaN for photonics and electronics,” *Journal of Physics D: Applied Physics* **40**, 6328–6344 (2007).
- <sup>17</sup>D. Wickramaratne, J.-X. Shen, C. E. Dreyer, M. Engel, M. Marsman, G. Kresse, S. Marcinkevičius, A. Alkauskas, and C. G. Van de Walle, “Iron as a source of efficient Shockley-Read-Hall recombination in GaN,” *Applied Physics Letters* **109**, 162107 (2016).
- <sup>18</sup>T. K. Uždavinsys, S. Marcinkevičius, J. H. Leach, K. R. Evans, and D. C. Look, “Photoexcited carrier trapping and recombination at Fe centers in GaN,” *Journal of Applied Physics* **119**, 215706 (2016).
- <sup>19</sup>M. A. Reshchikov, D. O. Demchenko, A. Usikov, H. Helava, and Y. Makarov, “Carbon defects as sources of the green and yellow luminescence bands in undoped GaN,” *Physical Review B* **90**, 235203 (2014).
- <sup>20</sup>C. E. Dreyer, A. Alkauskas, J. L. Lyons, J. S. Speck, and C. G. Van de Walle, “Gallium vacancy complexes as a cause of Shockley-Read-Hall recombination in III-nitride light emitters,” *Applied Physics Letters* **108**, 141101 (2016).
- <sup>21</sup>J.-X. Shen, D. Wickramaratne, C. E. Dreyer, A. Alkauskas, E. Young, J. S. Speck, and C. G. Van de Walle, “Calcium as a nonradiative recombination center in InGaN,” *Applied Physics Express* **10**, 021001 (2017).
- <sup>22</sup>E. C. Young, N. Grandjean, T. E. Mates, and J. S. Speck, “Calcium impurity as a source of non-radiative recombination in (In,Ga)N layers grown by molecular beam epitaxy,” *Applied Physics Letters* **109**, 212103 (2016).
- <sup>23</sup>N. Okada, K. Tadatomo, K. Yamane, H. Mangyo, Y. Kobayashi, H. Ono, K. Ikenaga, Y. Yano, and K. Matsumoto, “Performance of InGaN/GaN light-emitting diodes grown using NH<sub>3</sub> with oxygen-containing impurities,” *Japanese Journal of Applied Physics* **53**, 081001 (2014).
- <sup>24</sup>J. Yang, D. G. Zhao, D. S. Jiang, P. Chen, Z. S. Liu, L. C. Le, X. J. Li, X. G. He, J. P. Liu, S. M. Zhang, H. Wang, J. J. Zhu, and H. Yang, “Investigation on the compensation effect of residual carbon impurities in low temperature grown Mg doped GaN films,” *Journal of Applied Physics* **115**, 163704 (2014).
- <sup>25</sup>S.-H. Han, C.-Y. Cho, S.-J. Lee, T.-Y. Park, T.-H. Kim, S. H. Park, S. Won Kang, J. Won Kim, Y. C. Kim, and S.-J. Park, “Effect of Mg doping in the barrier of InGaN/GaN multiple quantum well on optical power of light-emitting diodes,” *Applied Physics Letters* **96**, 051113 (2010).
- <sup>26</sup>N. Grandjean, J. Massies, F. Semond, S. Y. Karpov, and R. A. Talalaev, “GaN evaporation in molecular-beam epitaxy environment,” *Applied Physics Letters* **74**, 1854–1856 (1999).
- <sup>27</sup>D. D. Koleske, A. E. Wickenden, R. L. Henry, J. C. Culbertson, and M. E. Twigg, “GaN decomposition in H<sub>2</sub> and N<sub>2</sub> at MOVPE temperatures and pressures,” *Journal of Crystal Growth* **223**, 466–483 (2001).
- <sup>28</sup>C. G. Van de Walle and J. Neugebauer, “First-principles calculations for defects and impurities: Applications to III-nitrides,” *Journal of Applied Physics* **95**, 3851–3879 (2004).
- <sup>29</sup>H. Ding, J. Wang, C. Li, J. Nie, and X. Liu, “Study of the surface segregation of carbon vacancies in TiCx,” *Solid State Communications* **152**, 185–188 (2012).
- <sup>30</sup>J. Neugebauer and C. G. Van de Walle, “Gallium vacancies and the yellow luminescence in GaN,” *Applied Physics Letters* **69**, 503–505 (1996).
- <sup>31</sup>Y. Tokuda, Y. Matsuoka, H. Ueda, O. Ishiguro, N. Soejima, and T. Kachi, “DLTS study of n-type GaN grown by MOCVD on GaN substrates,” *Superlattices and Microstructures* **40**, 268–273 (2006).
- <sup>32</sup>J. L. Lyons and C. G. Van de Walle, “Computationally predicted energies and properties of defects in GaN,” *npj Computational Materials* **3**, 12 (2017).
- <sup>33</sup>M. S. Daw and D. L. Smith, “Vacancies near semiconductor surfaces,” *Physical Review B* **20**, 5150 (1979).
- <sup>34</sup>K. Rapcewicz, M. Buongiorno Nardelli, and J. Bernholc, “Theory of surface morphology of wurtzite GaN (0001) surfaces,” *Physical Review B* **56**, R12725–R12728 (1997).
- <sup>35</sup>M. E. Bartram and J. R. Creighton, “GaN CVD Reactions: Hydrogen and Ammonia Decomposition and the Desorption of Gallium,” *MRS Internet Journal of Nitride Semiconductor Research* **4**, 369–374 (1999).
- <sup>36</sup>T. V. Bezyazychnaya, D. M. Kabanau, V. V. Kabanov, Y. V. Lebiadok, A. G. Ryabtsev, G. I. Ryabtsev, V. M. Zelenkovskii, and S. K. Mehta, “Influence of vacancies on indium atom distribution in InGaAs and InGaN compounds,” *Lithuanian Journal of Physics* **55**, 10–16 (2015).
- <sup>37</sup>A. Uedono, T. Watanabe, S. Kimura, Y. Zhang, M. Lozac’h, L. Sang, S. Ishibashi, N. Oshima, R. Suzuki, and M. Sumiya, “Vacancy-type defects in In<sub>x</sub>Ga<sub>1-x</sub>N grown on GaN templates probed using monoenergetic positron beams,” *Journal of Applied Physics* **114**, 184504 (2013).
- <sup>38</sup>S. Limpijumngong and C. Van de Walle, “Diffusivity of native defects in GaN,” *Physical Review B* **69**, 035207 (2004).
- <sup>39</sup>A. Terentjevs, A. Catellani, and G. Cicero, “Nitrogen vacancies at InN (1100) surfaces: A theoretical study,” *Applied Physics Letters* **96**, 171901 (2010).
- <sup>40</sup>P. Kessler, K. Lorenz, S. M. C. Miranda, J. G. Correia, K. Johnston, and R. Vianden, “An In-defect complex as a possible explanation for high luminous efficacy of InGaN and AlInN based devices,” *Hyperfine Interactions* **197**, 187–191 (2010).

