



Inverse method to estimate the size of scatterers in semi-crystalline thermoplastics via laser scattering and spectroscopic analyses

Sinan Boztepe, Rémi Gilblas, Olivier de Almeida, Fabrice Schmidt, Yannick Le Maout

► To cite this version:

Sinan Boztepe, Rémi Gilblas, Olivier de Almeida, Fabrice Schmidt, Yannick Le Maout. Inverse method to estimate the size of scatterers in semi-crystalline thermoplastics via laser scattering and spectroscopic analyses. 26ème congrès de la Société Française de Thermique (SFT), May 2018, Pau, France. <hal-02064311>

HAL Id: hal-02064311

<https://hal.science/hal-02064311v1>

Submitted on 20 Mar 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



HAL Authorization

Inverse method to estimate the size of scatterer in semi-crystalline thermoplastics via laser scattering and spectroscopic analyses

Sinan BOZTEPE¹, Remi GILBLAS¹, Olivier de ALMEIDA¹, Fabrice SCHMIDT¹, Yannick Le MAOULT^{1*}

¹Université de Toulouse ; Mines Albi, ICA (Institut Clément Ader) ; Campus Jarlard, F-81013 Albi cedex 09, France

*(auteur correspondant : sboztepe@mines-albi.fr)

Résumé – It is widely known that microcrystalline structure of semi-crystalline thermoplastics induces an optically heterogeneous medium that eventually causes optical scattering. In case of building a predictive radiation heat transfer model for semi-crystalline polymers the scattering of radiation need to be taken into account [1]. Crystal formation in semi-crystalline polymers typically involves folding of polymer chains where the height of fold chains, which is named as lamellae thickness, is generally much smaller than their radial growth. Such type of radially-growth ordered chains eventually create larger structures, where both the crystalline and non-crystalline regions are named as spherulites [2].

In this study, the laser scattering profiles of polyethylene (PE) film samples were experimentally analyzed. Laser beam scattering tests were performed on PE using CASI® Scatterometer equipped with collimated monochromatic light at 632nm and, the bidirectional scattering distribution function (BSDF) of PE was obtained for the angles between 0° and 350°. In order to analyze the effect of microcrystalline structure on the scattering behavior of PE different film samples were prepared with different morphology but with identical thickness. Apart from it, directional-directional ($T_{\lambda\text{-directional}}$) and directional-hemispherical transmittances ($T_{\lambda\text{-hemispherical}}$) of the identical PE samples were obtained via a FT-IR spectrometer and an integrating sphere [3]. In order to estimate the size of scatterer in PE, an inverse method was developed adopting the well-known optical scattering theories, such as Mie and Rayleigh-Debye-Gans (RDG) theories [3], [4]. Using the scattering theories, the laser scattering profile of PE was predicted considering arbitrarily adopted scatterer sizes and the predicted laser scattering profiles were compared to the experimental analyses. Thanks to this comparative study the equivalent scatterer size in semi-crystalline PE was estimated. The estimated parameter is called as equivalent scatterer size as, it was assumed that the scatterer is spherical while the microcrystalline structure of semi-crystalline polymers is much more complex. The obtained equivalent scatterer size will be used for developing an advanced radiation heat transfer model that takes into account extinction coefficient (β_{λ}), which is function of both absorption and scattering characteristics of PE.

Références

- [1] Boglea AL, Roesner A, Russek UA (2011) Laser Beam Welding of Thermoplastics, In: Poprawe R (ed) Tailored Light 2. Springer Berlin Heidelberg, Berlin, Heidelberg, pp 284-307
- [2] A. J. Peacock, *Handbook of polyethylene: structures, properties, and applications*. New York: Marcel Dekker, 2000.
- [3] R. Apetz and M. P. Bruggen, "Transparent Alumina: A Light-Scattering Model," *J. Am. Ceram. Soc.*, vol. 86, no. 3, pp. 480–486, 2003.
- [4] M. Ilie, J.-C. Kneip, S. Mattei, A. Nichici, C. Roze, and T. Girasole, "Laser beam scattering effects in non-absorbent inhomogenous polymers," *Opt. Lasers Eng.*, vol. 45, no. 3, pp. 405–412, Mar. 2007.