



HAL
open science

Softening upon Adsorption in Microporous Materials: A Counterintuitive Mechanical Response

Félix Mouhat, David Bousquet, Anne Boutin, Lila Bouëssel Du Bourg,
François-Xavier Coudert, Alain Fuchs

► **To cite this version:**

Félix Mouhat, David Bousquet, Anne Boutin, Lila Bouëssel Du Bourg, François-Xavier Coudert, et al.. Softening upon Adsorption in Microporous Materials: A Counterintuitive Mechanical Response. *Journal of Physical Chemistry Letters*, 2015, 6 (21), pp.4265-4269. 10.1021/acs.jpcllett.5b01965 . hal-02115286

HAL Id: hal-02115286

<https://hal.science/hal-02115286v1>

Submitted on 30 Apr 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Softening upon Adsorption in Microporous Materials: a Counter-Intuitive Mechanical Response

Félix Mouhat,[†] David Bousquet,[‡] Anne Boutin,[‡] Lila Bouéssel du Bourg,[†] François-Xavier Coudert,^{†,*} Alain H. Fuchs^{†,*}

[†]PSL Research University, Chimie ParisTech – CNRS, Institut de Recherche de Chimie Paris, 75005 Paris, France

[‡]École Normale Supérieure, PSL Research University, Département de Chimie, Sorbonne Universités – UPMC Univ Paris 06, CNRS, 75005 Paris, France

ABSTRACT: We demonstrate here that microporous materials can exhibit softening upon adsorption of guest molecules, at low to intermediate pore loading, in parallel to the pore shrinking that is well-known in this regime. This novel and counter-intuitive mechanical response was observed through molecular simulations of both model pore systems (such as slit pore) and real metal-organic frameworks. It is contrary to common belief that adsorption of guest molecules necessarily leads to stiffening due to increased density, a fact which we show is the high-loading limit of a more complex behavior, namely a non-monotonic softening-then-stiffening.

Fluid adsorption in nanoporous materials^{1,2,3} such as activated carbons, carbon nanotubes or zeolites has been the subject of numerous studies in the past two decades, owing to its practical importance in such processes as separation, ion exchange, catalysis, biosensing and controlled drug delivery. For a long time these materials were considered as sufficiently stiff so that their intrinsic flexibility needed not be taken into account in the models employed to understand and predict equilibrium adsorption properties.^{4,5,6} Indeed the magnitude of the adsorption-induced strain in zeolites is usually of the order of 10^{-3} to 10^{-4} . It was only when transport properties were considered that flexible materials models were tested^{7,8} in order to ascertain whether or not it could help in better reproducing and explaining the observed experimental trends. Nonetheless, during these years an important amount of data were collected by the Russian adsorption school of Dubinin and coworkers on the adsorption-induced deformation of microporous carbons and zeolites. These studies were nicely summarized in 2006 in a book by Tvardovskiy.⁹

These features were at least partly overlooked until the issue of adsorption-deformation in mesoporous systems such as MCM-41, SBA-15, or controlled pore glasses (CPGs) was addressed through the study of the phase behavior of confined fluids, with a specific focus on the capillary condensation phenomenon.¹⁰ In such mesoporous materials, a continuous swelling is observed upon fluid adsorption, up to capillary condensation, and this can be understood in terms of the so-called Bangham effect,¹¹ which qualitatively relies on interfacial energy change upon internal surface adsorption. Models have been developed to rationalize this effect.^{12,13}

In the case of microporous materials however, the vapor adsorption phenomenon displays a trend different from what happens in mesoporous materials. At low vapor pressure the system undergoes a structural contraction followed by swelling at higher vapor pressure.⁹ This peculiar non-monotonic behavior been observed experimentally and documented dating back to the 1940's,¹⁴ and was recently reported very clearly by Reichenauer and coworkers¹⁵ in a series of detailed *in situ* dilatometry experiments of various gases adsorption in synthetic microporous carbons. This non-monotonic deformation is generic to microporous materials and does not depend on the specifics of host-guest interactions. It contradicts the common intuition that gas adsorption in a confined system increases internal pressures and leads to a continuous volumetric expansion as long as the host framework is flexible (the “sponge” or “balloon picture”).^{16,17}

On the theoretical side, Neimark and coworkers developed a non-local density functional theory,^{18,19} that was able to reproduce this contraction-expansion behavior of adsorption strain in zeolites. Density functional theory and Grand Canonical Monte Carlo simulations were also applied to study adsorption deformation in micropores of activated carbons.²⁰ The concept of *adsorption stress*

enabled to rationalize this phenomenon.^{18,21,22} At low gas loading, contraction of the material is driven by the host-guest dispersion attractive interactions, leading to a negative adsorption stress. At higher loading, once the adsorbed phase becomes denser, short-range repulsive interactions come to play which lead to a reversal of the adsorption stress, and the material expands in order to accommodate additional guest molecules.

This was a first step towards a comprehensive understanding of the adsorption-deformation coupling phenomena in microporous materials. The next issue to be dealt with is the mechanical stability of the microporous frameworks in the presence of adsorbate species.

Pressure-Induced Amorphization (PIA) was observed in several porous clathrasils and zeolites^{23,24,25} as well as in metal-organic frameworks of the ZIF family (Zeolitic Imidazolate Framework).^{26,27} This structural transition was attributed to the framework mechanical instability due to softening of low-energy phonon modes.²⁸ We note in passing that such a mechanism was also proposed for the PIA process in non-porous α -quartz²⁹ and ice I_h.³⁰ More recently, PIA in ZIF-8 and some other porous ZIFs was attributed to the framework mechanical instability due to shear mode softening.^{31,32}

The phenomenon of pressure-induced amorphization is quite sensitive to the presence of molecules inside the pore space. Insertion of guest molecules was shown to either shift amorphization to higher pressure than in the evacuated material,^{23,25,31} or even to suppress (“deactivate”) PIA as in the case of silicalite-1.³³ It was then deduced that the presence of adsorbate molecules enhances the stability of the microporous frameworks. This was later supported by a Monte Carlo simulation of silicalite-1 which showed an increase of the computed bulk modulus upon CO₂ adsorption.³⁴ It should be mentioned however that there are some scarce indications in the literature of opposite behaviors. For instance, Canepa et al.³⁵ studied by *ab initio* simulations the response of MOF-74-Zn when loaded with several molecular gases. They observed that “for almost all adsorbates, the molecular adsorption in the MOF pores induces a substantial increase of the elastic constants – i.e. the MOF loses some of its flexibility”. A close examination of their data (Table III of reference 35), shows that, while the bulk modulus increases with the insertion of gas molecules, the individual C_{12} and C_{14} elastic constants as well as two of the Young’s modulus components decrease when the MOF is loaded with CO₂ or CH₄ (but not H₂O). In many of the cases studied experimentally, the precise value of the gas loading is not well known, and we presume that many of the experiments were performed at high, if not full, loading. Given that the PIA mechanism involves a collapse of the framework structure around the empty pores,³² it seems clear that the mechanical properties can only be en-

hanced when the pore voids are fully filled with adsorbate molecules. This might, however, not be the case at low gas loading. There is thus a great need to better understand the mechanical response of nanoporous materials upon adsorption, and in particular of *soft* framework materials such as flexible and stimuli-responsive MOFs.³⁶

In this work we examine the elastic response of two model microporous frameworks upon gas adsorption, with a special focus on the initial stage of the adsorption process, i.e. at low gas loading, in order to try understanding the effect of the non-monotonic volumetric behavior upon adsorption described above on the simultaneous change in the framework mechanical stability.




Figure 1: Sketch of the two model microporous frameworks. Left: slit-pore; right: lozenge-shaped pore. The red arrows represent the direction of the stress exerted on the solid frameworks, and the unique order parameters of the deformation are represented in green.

We performed Monte Carlo (MC) simulations of a Lennard-Jones fluid adsorption in pores of two different geometries: a slit-pore which mimics a MOF framework such as ELM-11,³⁷ and a lozenge-shaped pore which is a simplified model of the MIL-53 family of “breathing” materials^{38,39,40} (Figure 1). In both cases the walls of the framework were made of regularly spaced Lennard-Jones particles (more details on the unit cell setup and the forcefield parameters are given in the Supporting Information). These are very simple model systems for flexible nanoporous materials. They exhibit only one order parameter describing the framework deformation, namely the width of the slit-pore (h) and the opening angle of the lozenge-shaped pore (α); all other dimensions are kept constant. It enables to perform accurate direct Monte Carlo simulations in the osmotic statistical ensemble ($N_{\text{host}}, \mu_{\text{ads}}, \sigma, T$) where N_{host} is the number of host unit cells, μ_{ads} is the adsorbate chemical potential, T is the temperature, and σ is the mechanical stress (in our case a uniaxial stress) exerted on the system boundaries. It is the appropriate thermodynamic ensemble to treat ad-

sorption in flexible open porous materials,⁴¹ similar to the Grand isostress ensemble used to describe Surface Force Apparatus (SFA) experiments.^{42,43} For each system, simulations of adsorption were performed at increasing values of guest chemical potential μ_{ads} , and from each osmotic simulation the following quantities were extracted: the loading, or average number of adsorbed particles; the deformation of the unit cell, quantified by the average value of h or a , and which is directly related to the strain; and the elastic modulus (or stiffness constant) along the deformation mode, calculated from the fluctuations of the unit cell (in Voigt notation, C_{33} for the slit pore, and C_{66} for the lozenge-shaped pore; see supporting information for details).

We first performed a series of simulations in the case of the slit pore. The width of the empty pore h_0 was fixed to the value of 15 Å, which corresponds to a typical microporous pore. This width should not be too small in order to avoid spurious effects due to layering that is known to take place in this particular geometry in very narrow pores.^{42,43} We allow the pore width to fluctuate in the osmotic MC simulations and the free energy of the empty host is simply written in the elastic regime as:

$$F_{\text{host}}(h) = \frac{1}{2} k (h - h_0)^2 \quad (1)$$

The harmonic constant k is chosen such that the elastic constant of the bare framework C_{33}^0 (the Young's modulus of the host) is equal to 10 GPa, a rather typical value for MOFs or zeolite microporous materials. The same approach is followed for the lozenge-shaped pore, whose free energy also follows linear elasticity (the mathematical expression for the free energy can be found in a preceding paper³⁹).




Figure 2. Changes in the slit-pore width (upper frame) and in the elastic constant C_{33} (lower frame) as a function of the number of adsorbed molecules. The black curves correspond to the direct osmotic simulations, with uncertainties indicated (when not visible, they are smaller than symbol size). The blue curves to Grand Canonical simulations in which the elastic constant is obtained through the second derivative of N_{ads} with respect to h , using the data of a series of simulations ranging from $h = 14$ to 15 Å (details in Sup-

porting Information). Simulations were performed at 298 K.

In Figure 2, we report the evolution of the slit-pore width and the elastic constant C_{33} as a function of the number of adsorbed molecules (pore loading) at 298 K. A slight increase in the pore width at very low N_{ads} values in the osmotic simulations is observed, which is due to an oscillating solvation pressure effect that is still present, although of small amplitude, in such a 15 Å width slit-pore (as well as in additional simulations performed for widths of 18 Å and 21 Å). This is in keeping with the fact that this effect is not present in the grand canonical simulations. A rather similar feature was observed by Schoen and coworkers in their simulations of pores of several guest molecular diameters.⁴⁴ This effect is of small amplitude, and strongly dependent on the relative guest size and pore width h_0 .

After that low-pressure effect, the volumetric behavior is non-monotonic, as expected, and shows a contraction at low to intermediate gas loading followed by an expansion of the pore at high loading. This is the standard contraction–expansion mechanism commonly observed in microporous materials.^{9,16} What is absolutely new and striking is the observation of a non-monotonic change in the elastic constant upon fluid adsorption. Even in such a simple model as the slit pore, the continuous evolution of elastic stiffness upon adsorption loading has never been reported before. In this particular system, we see that the initial contraction of the porous volume is accompanied by a lowering of the Young's modulus along the z axis, i.e. a *softening* of the framework. The subsequent expansion at high loading is, on the contrary, accompanied with a *stiffening* of the framework, as guest molecules fill the micropore. It is worth noting that, on this model whose elastic modulus (10 GPa) is representative of a MOF, the variations in mechanical properties (up to 5 GPa change in C_{33} , i.e. a 50% variation) are quite large, much larger than variations in the pore size itself (0.6 Å in a pore of 15 Å).

To investigate the influence of geometry, we then studied the evolution of elastic constants upon adsorption in the lozenge-shaped pore, from GCMC simulation data at varying pore opening and chemical potential (see Supporting Information). We report in Figure 3 the changes in the order parameter a (lozenge angle) and the elastic constant C_{66} (shear modulus), as a function of the number of adsorbed molecules at 298 K. Again the non-monotonic volumetric contraction-expansion behavior is accompanied by a softening-stiffening process upon fluid adsorption. In this particular pore model, adsorption-induced softening reaches 20% while the transition from softening to stiffening occurs at lower relative loading. The generic features of adsorption-induced softening-

stiffening are, however, strikingly similar to the case of the slit pore.




Figure 3. Changes in the lozenge-shaped pore order parameter a (upper frame) and in the elastic constant C_{66} (lower frame) as a function of the number of adsorbed molecules.

The question arises now as to whether or not this behavior of the elastic response of microporous frameworks disclosed here is generic, i.e. whether we can expect to see an adsorption-induced softening of host-guest systems at partial loading. Obviously more work is needed to be able to fully answer this question; for this, experimental studies at low loading are sorely needed. We have begun however to address this question by closely examining the simulation data from our previous Molecular Dynamics (MD) work on series of MOFs. In the case of cubic material ZIF-8,³¹ no such behavior was observed at low loading in our simulations of methane adsorption. The {ZIF-8 + CH₄} system exhibits a continuous increase in the computed elastic constants upon methane adsorption. However another ZIF material, which we have previously studied in order to predict the high pressure stability of ZIF frameworks,³² was observed softening upon CH₄ adsorption. The Zn(imidazolate)₂ framework of *nog* topology⁴⁵ exhibits the same non-monotonic softening-stiffening behavior as our two model pore systems, upon methane adsorption at 300 K. For this material, we show in Figure 4 the evolution of the softest elastic deformation mode, λ_{\min} , as a function of methane loading. It exhibits a softening by a factor of two at low loading, with the modulus going down from 2 GPa to 1 GPa at 20 molecules per unit cell.




Figure 4. Change in the elastic response of the ZIF *nog*⁴⁵ as a function of the number of methane molecules adsorbed species, obtained from isostress-isothermal MD simulations at 300 K.³² The ordinate is the smallest elastic modulus of the material, i.e. the lowest eigenvalue λ_{\min} of the elastic stiffness tensor. Uncertainty on each value is of the order of 0.1 GPa (see ref. 32).

We conclude from this first systematic study of mechanical properties of microporous materials under adsorption that a non trivial softening of the microporous {guest + host} system can be observed at low loading, paralleling the contraction of the system. This counter-intuitive effect is followed, at higher fluid loading, by the traditionally expected materials stiffening. This phenomenon is rather generic and does not stem from specific interactions, as we have seen it occurring for methane adsorption in pores of various geometries (slit pore, diamond-shaped pore, and *nog* ZIF). However, some microporous frameworks such as ZIF-8 do not show such a behavior for reasons that are not yet clear. It is possible that only some of the components of the framework elastic response experience such a temporary softening in the low loading regime. Work on a larger number of host-guest systems is in progress to clear up this point.

This non-monotonic softening-stiffening evolution of mechanical properties, proposed on the basis of molecular simulations, can explain some results from the earlier literature. In particular, it explains the MOF softening upon adsorption found (but not commented upon) by Canepa et al. in their *ab initio* studies of CO₂ and CH₄ adsorption in MOF-74-Zn.³⁵ It can also help explain the recent counter-intuitive experimental results of Alabarse et al., who showed that the presence of water within the pores of AlPO₄-54 lead to a decrease in mechanical stability, attested by the occurrence of pressure-induced amorphization at lower pressure than in the guest-free AlPO₄-54.⁴⁶ This last example shows the importance of better understanding the influence of guest adsorption on mechanical properties of microporous materials, as it can have a drastic impact not only on the modification of the elastic behavior (thus augmenting, through soften-

ing, the magnitude of adsorption deformation) but also on the stability under pressure, a key property for many industrial applications.

ASSOCIATED CONTENT

Supporting Information. Full description of the pore models, molecular simulation procedures, and calculation of elastic constants. This material is available free of charge via the Internet at <http://pubs.acs.org>.

AUTHOR INFORMATION

Corresponding Author

alain.fuchs@cnr-dir.fr; fx.coudert@chimie-paristech.fr

ACKNOWLEDGMENT

We thank Alex Neimark and Gudrun Reichenauer for fruitful discussions. We acknowledge funding from Agence Nationale de la Recherche (project ANR-2010-BLAN-0822), and computing time on HPC platforms by GENCI (grant x2015087069).

REFERENCES

- ¹ Porous materials in which the pore diameters are < 2 nm are called “microporous”, following IUPAC recommendations.³ Materials which exhibit pore diameters larger than 2 nm are called “mesoporous”. The present study is mostly devoted to understanding the effect of adsorption on compliant microporous materials.
- ² F. Rouquerol, J. Rouquerol, K. Sing, *Adsorption by Powders and Porous Solids*, Academic Press, 1999
- ³ J. Rouquerol, D. Avnir, C. W. Fairbridge, D. H. Everett, J. M. Haynes, N. Pernicone, J. D. F. Ramsay, K. S. W. Sing and K. K. Unger, *Pure Appl. Chem.* 66 (1994) 1739-1758
- ⁴ R.F. Cracknell, K.E. Gubbins and D. Nicholson, *Acc. Chem. Res.* 28 (1995) 281
- ⁵ B. Smit, *Phys. Scripta* 66 (1996) 80
- ⁶ A.H. Fuchs and A.K. Cheetham, *J. Phys. Chem. B*(2001)
- ⁷ S.M. Auerbach, *Int. Rev. Phys. Chem.* 19 (2000) 155
- ⁸ F. Leroy, B. Rousseau and A.H. Fuchs, *Phys. Chem. Chem. Phys.* 6 (2004) 775
- ⁹ A. V. Tvardovskiy, *Sorption Deformation* (2006), Elsevier, Amsterdam
- ¹⁰ G.A. Zickler, S. Jähnert, W. Wagermeier, S.S. Funari, G.H. Findenegg and O. Paris, *Phys. Rev. B.* 73 (2006) 184109
- ¹¹ D.H. Bangham and N. Fakhoury, *Nature* 122 (1928) 681
- ¹² P.I. Ravikovitch and A.V. Neimark, *Langmuir* 22 (2006) 11171
- ¹³ G. Y. Gor and A. V. Neimark, *Langmuir* 26 (2010) 13021
- ¹⁴ R. S. Haines and R. McIntosh, *J. Chem. Phys.*, 1947, 15, 28–38.
- ¹⁵ C. Baltzer, G. Reichenauer and M. Wiener, *Proc. 5th Poromechanics Conference*, Vienna (2013), 701, ASCE
- ¹⁶ F.-X. Coudert, A.H. Fuchs and A.V. Neimark, *Phys. Chem. Chem. Phys.* 16 (2014) 4394
- ¹⁷ J. Joo, H. Kim and S.S. Han, *Phys. Chem. Chem. Phys.* 15 (2013) 18822-18826

- ¹⁸ P.I. Ravikovitch and A.V. Neimark, *Langmuir* 22 (2006) 10864
- ¹⁹ P. Kowalczyk, A. Ciach and A.V. Neimark, 24(2008) 6603
- ²⁰ D. D. Do, D. Nicholson, and H. D. Do, *J. Phys. Chem. C* 112 (2008) 14075
- ²¹ A.V. Neimark, F.-X. Coudert, A. Boutin and A.H. Fuchs, *J. Chem. Phys. Lett.* 1 (2010) 445
- ²² F.-X. Coudert, A. Boutin, A.H. Fuchs and A.V. Neimark, *J. Chem. Phys. Lett.* 4 (2013) 3198
- ²³ J.S. Tse, D.D. Klug, J.A. Ripmeester, S. Degreniers and K. Lagarec, *Nature* 369 (1994) 724-727
- ²⁴ P. Gillet, J.-M. Melezieux, and J.-P. Itie, *Am. Mineral.* 81 (1996) 651-657
- ²⁵ Y. Huang and E.A. Havenga, *Chem. Phys. Lett.* 345 (2001) 65-71
- ²⁶ K.W. Chapman, G.J. Halder and P.J. Chupas, *J. Am. Chem. Soc.* 131 (2009) 17546-17547.
- ²⁷ T.D. Bennett, P. Simoncic, S.A. Moggach, F. Gozzo, P. Macchi, D.A. Keen, J.-C. Tan and A.K. Cheetham, *Chem. Commun.* 47 (2011) 7983-7985
- ²⁸ G.N. Greaves, F. Meneau, O. Majerus, D.G. Jones and J. Taylor, *Science* 308 (2005) 1299-1302
- ²⁹ J.S. Tse and D.D. Klug, *Phys. Rev. Lett.* 67 (1991) 3559-3562
- ³⁰ J.S. Tse, *J. Chem. Phys.* 96 (1992) 5482-5487
- ³¹ A.U. Ortiz, A. Boutin, A.H. Fuchs and F.-X. Coudert, *J. Phys. Chem. Lett.* 4 (2013) 1861
- ³² L. Bouëssel du Bourg, A.U. Ortiz, A. Boutin and F.-X. Coudert, *APL Mater.* 2 (2014) 124110
- ³³ J. Haines, O. Gambon, C. Levelut, M. Santoro, F. Gorelli and G. Garbarino, *J. Am. Chem. Soc.* 132 (2010) 8860-8861
- ³⁴ B. Coasne, J. Haines, C. Levelut, O. Cambon, M. Santoro, F. Gorelli and G. Garbarino, *Phys. Chem. Chem. Phys.* 13 (2011) 20096-20099
- ³⁵ P. Canepa, K. Tan, Y. Du, H. Lu, Y.J. Chabal and T. Thonhauser, *J. Mater. Chem. A* 3 (2015) 986-995
- ³⁶ F.-X. Coudert, *Chem. Mater.*, 2015, 27, 1905–1916
- ³⁷ R. Namaguchi, H. Tanaka, S. Watanabe and M.T. Miyahara, *J. Chem. Phys.* 140 (2014) 044707
- ³⁸ G. Férey and C. Serre, *Chem. Soc. Rev.* 38 (2009) 1380
- ³⁹ D. Bousquet, F.-X. Coudert, A.G.J. Fossati, A.V. Neimark, A.H. Fuchs and A. Boutin, *J. Chem. Phys.* 138 (2013) 174106
- ⁴⁰ D. Bousquet, F.-X. Coudert and A. Boutin, *J. Chem. Phys.*, 2012, 137, 044118
- ⁴¹ F.-X. Coudert, M. Jeffroy, A.H. Fuchs, A. Boutin and C. Mellot-Drazniecks, *J. Am. Chem. Soc.* 130 (2008) 14294
- ⁴² P. Bordarier, B. Rousseau and A.H. Fuchs, *J. Chem. Phys.* 106 (1997) 7295
- ⁴³ P. Bordarier, M. Schoen and A.H. Fuchs, *Phys. Rev. E* 57 (1998) 1621
- ⁴⁴ G. Günther, J. Prass, O. Paris and M. Schoen, *Phys. Rev. Lett.* 101 (2008) 086104
- ⁴⁵ Y.-Q. Tian, Y.-M. Zhao, Z.-X. Chen, G.-N. Zhang, L.-H. Weng, and D.-Y. Zhao, *Chem. - Eur. J.* 13 (2007) 4146
- ⁴⁶ F. G. Alabarse, G. Silly, A. Haidoux, C. Levelut, D. Bourgoigne, A.-M. Flank, P. Lagarde, A. S. Pereira, J.-L. Bantignies, O. Cambon and J. Haines, *J. Phys. Chem. C* 2014, 118, 3651–3663




Table of Contents artwork