



**HAL**  
open science

## Cationic water dispersion of bio-sourced cross-linked polyurethane

Laurence Pessoni, Prakash Sane, Etienne Grau, Henri Cramail

► **To cite this version:**

Laurence Pessoni, Prakash Sane, Etienne Grau, Henri Cramail. Cationic water dispersion of bio-sourced cross-linked polyurethane. *Green materials*, 2019, pp.1-9. 10.1680/jgrma.19.00003. hal-02134731

**HAL Id: hal-02134731**

**<https://hal.science/hal-02134731>**

Submitted on 19 Nov 2019

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Cationic water dispersion of bio-sourced crosslinked polyurethane

Laurence Pessonj,<sup>a,b</sup> Prakash Sane,<sup>a,b</sup> Etienne Grau,<sup>\*a,b</sup> Henri Cramail <sup>\*a,b</sup>

<sup>a</sup>University of Bordeaux, Laboratoire de Chimie des Polymères Organiques, UMR 5629, Bordeaux INP/ ENSCBP, 16 avenue Pey Berland, Pessac Cedex, France

<sup>b</sup>Centre National de la Recherche Scientifique, Laboratoire de Chimie des Polymères Organiques, UMR 5629, Pessac Cedex, France

Corresponding author : egrau@enscbp.fr

## ABSTRACT

A series of crosslinkable waterborne polyurethanes (WPU) from bio-sourced diol were synthesized by the acetone process. WPU raise much interest in coating and adhesives application due to its low volatile organic compounds emission. Crosslinking of the obtained PU film should improve mechanical properties and water and solvent resistance. In this study, *N*-methyldiethanolamine (MDEA), the emulsifier, was used as short hydrophilic diol to obtain a cationic dispersion after quaternization with acetic acid. The crosslinker, *N*-4-vinylbenzyl-diethanolamine (VBDEA) synthesized in this study, also contains a tertiary amine which can improve dispersion in addition to the mechanical properties. Finally, a telechelic diol (Priplast 1900) obtained by polyesterification of dimer fatty acid was used as long hydrophobic diol. Stable PU water dispersions (40 wt%) were obtained by acetone process with various diisocyanates (HMDI, HDI and IPDI) and characterized by DLS. After complete evaporation of water, films were obtained from these dispersions. Then, the films were crosslinked by solar irradiation. The network formation was confirmed

using swelling test in acetone and THF. Films were compared after and before irradiation demonstrated that irradiation improves solvent and water resistance but also mechanical properties of each film.

## INTRODUCTION

Polyurethanes (PU) are employed for many applications such as coating, ink, adhesives, rubbers plastic or textiles.<sup>1-6</sup> Due to the environmental requirements in these days, waterborne polyurethanes (WPU) are more and more developed due to its low volatile organic compounds emission and have much interest in coating and adhesives application.<sup>4</sup> In industry, different synthetic routes were developed to obtain PU dispersions such as the melt, the cetimine-cetazine, the acetone, and the prepolymer emulsification processes.<sup>4-10</sup> The most commonly used are the prepolymer emulsification<sup>11-15</sup> and acetone processes.<sup>16-20</sup> Most of these processes require the incorporation of internal emulsifiers within the PU backbone to disperse it in water.<sup>4,5,7,21,22</sup> These species are usually a diol with an ionic group such as a carboxylate,<sup>8,11-14,16,23-25</sup> a sulfonate<sup>17</sup>, a quaternary ammonium,<sup>26-29</sup> phosphonium<sup>30,31</sup> or non-ionic groups as poly(ethylene oxide).<sup>7</sup> The most used emulsifier is the 2,2-Bis(hydroxymethyl)propionic acid (DMPA). After incorporation of DMPA along the chain of PU, a base group as trimethylamine (TEA) is used to neutralize the carboxylate acid and allow the anionic dispersion. The cationic dispersion is also mainly used. In this case, the most common emulsifier used is *N*-methyldiethanolamine (MDEA). It has a quaternary ammonium which is principally quaternized by acetic acid.

Crosslinking of the PU film obtained after synthesis is mainly used to improve mechanical properties and chemical and water resistance.<sup>18,22,32-41</sup> Usually, UV-cured waterborne technology is used by industrial due to the less environmental impact.<sup>4</sup> In order to obtain a crosslinked film, three components are usually used an oligomer (*e.g.*, acrylated polyurethane), a photoinitiator and a reactive diluent.<sup>4,34,36,42</sup> The reactive diluent is used principally to control the viscosity of the system and to control the UV-curable

speed. Usually, reactive diluents are acrylate or methacrylate.<sup>42</sup> The photoinitiator absorbed UV light to produce free radicals to crosslink the film by the reaction between the prepolymer and reactive diluent.

This study aims to crosslink waterborne polyurethane with only one component to reduce chemical product as the team of Duncan J. Maitland<sup>43</sup> who synthesized a DEA-diol monomer from diethanolamine and allyl chloroformate to crosslink by electron-beam polyurethanes prepared in bulk. This custom DEA-diol was also compared with a commercially available trimethylolpropane allyl ether and the 2-butene-1,4-diol. The custom DEA-diol allows improving thermomechanical properties of shape memory polymer systems. Herein, a styrenic crosslinker, with two hydroxyl function was synthesized and copolymerized with a diol and an emulsifier. The polyurethane synthesized was obtained by the acetone process in one step. The diol used was an amorphous bio-sourced polyester diol. The crosslinker used was the *N*-4-vinylbenzyl-diethanolamine (VBDEA) synthesized according to previous studies.<sup>44,45</sup> MDEA was chosen as emulsifier. MDEA is quaternized with acetic acid in order to obtain a cationic dispersion. The advantage of this kind of dispersion is that the crosslinker can also be quaternized ( $pK_a(\text{MDEA})=8.7$  and  $pK_a(\text{VBDEA})=8.4$ ). Then, different isocyanates and different compositions were tested and compared in order to study the crosslinker effect and to find the better condition to obtain good dispersions and good film mechanical properties. Finally, PU dispersions and films were fully characterized.

## **EXPERIMENTAL**

### **Materials**

Diethanolamine ( $\geq 98.0\%$ ) and 4-vinyl benzyl chloride (90%), anhydrous magnesium sulfate ( $\geq 99.5\%$ ,  $\text{MgSO}_4$ ), *N*-methyldiethanolamine ( $\geq 99\%$ , MDEA) and acid acetic ( $\geq 99.7\%$ ) were purchased from Sigma Aldrich. Triethanolamine ( $\geq 99\%$ , TEA) was obtained from Fisher Scientific. Dibutyltin dilaurate ( $> 95\%$ , DBTDL) and Dicyclohexylmethane 4,4'-Diisocyanate ( $> 90\%$ , mixture of isomers, HMDI) were supplied from TCI. The diol is an amorphous polyester diol ( $M_n = 2000 \text{ g mol}^{-1}$ , Priplast 1900) kindly provided by

CRODA. Acetone (CHROMASOLV<sup>®</sup>, for HPLC, ≥ 99.8 %), Tetrahydrofuran (anhydrous, ≥99.9 %, contains 250 ppm BHT as inhibitor, THF), *N,N*-Dimethylformamide (CHROMASOLV<sup>®</sup> Plus, for HPLC, ≥ 99.9 %, DMF) and Dichloromethane (CHROMASOLV<sup>®</sup> Plus, for HPLC, ≥ 99.9 %, DCM) were purchased from Sigma-Aldrich. All products were used as received.

### Synthesis of *N*-4-vinylbenzyl-diethanolamine (VBDEA)

The experimental procedure described in Figure 1 was adapted from the work of Jin *et al.*<sup>45</sup> In a 250 mL round-bottom flask, diethanolamine (10.0 g, 95.2 mmol) was added in DMF (50 mL). To this solution, TEA (9.62 g, 95.2 mmol) and a stirring bar were added. The resulting solution was stirred at 60 °C for 20 min to get a homogeneous mixture. At the end of this period, 4-vinyl benzyl chloride (14.48 g, 95.2 mmol) was added to the mixture. After 10 h at 60 °C, the reaction mixture was cooled to room temperature, filtered, and most of the DMF was removed under reduced pressure. Then, the filter liquor was washed with water and extracted with DCM. The organic layer was dried with anhydrous MgSO<sub>4</sub> and concentrated under vacuum to give a yellow liquid. <sup>1</sup>H NMR (400 MHz, CDCl<sub>3</sub>, δ ppm): 2.30 (s, 2H, -OH), 2.63-2.66 (t, 4H, -N-CH<sub>2</sub>-CH<sub>2</sub>-OH), 3.54-3.56 (t, 4H, -N-CH<sub>2</sub>-CH<sub>2</sub>-OH), 3.62 (s, 2H, -Φ-CH<sub>2</sub>-N-), 5.14-5.17 (d, 1H, -CH=CH<sub>2</sub>), 5.64-5.68 (d, 1H, -CH=CH<sub>2</sub>), (dd, 1H, -Φ-CH=CH<sub>2</sub>), 7.19-7.21 (d, -CH<sub>2</sub>-C-CH(CH)-), 7.29-7.30 (d, -CH(CH)-C-CH-) (Figure S1 in supplementary data).




Figure 1. Formation of *N*-(4-vinylbenzyl)diethanolamine (C) from the diethanolamine (A) and the 4-vinyl benzyl chloride (B).

### Preparation of WPU dispersions

Diols, Priplast 1900, *N*-methyldiethanolamine and VBDEA were first inserted in 40 mL of acetone into a 250 mL double-neck round bottom flask with a reflux condenser and a mechanical stirrer (150 tr.min<sup>-1</sup>). The mixture is stirred for 10 min at 80 °C. Then, the DBTDL (1 %weight of solid content) in 10 mL of acetone was added to the mixture. After 10 min, the polyaddition starts with the introduction of the isocyanate (1.1 eq of OH) mixed with 30 mL of acetone. After 5 h at 80 °C, the reaction mixture was cooled to room temperature. Then, the prepolymer was neutralized by addition of acetic acid (1.1 eq of MDEA). After 30 min at ambient temperature, water was added droplet by droplet under a strong stirring (500 tr.min<sup>-1</sup>). After 30 min, acetone was evaporated by rotary vacuum evaporation to obtain an aqueous dispersion of PU (WPU) with a solid content of 40 %. All experiments were prepared using the same procedure and based on the mixing plot represented in Figure 2. The compositions of WPU are summarized in Table 1.




Figure 2. Schematic representation of the proportion of diol (a), crosslinker (b) and emulsifier (c) in the different dispersion; numbers represent the name of each sample described in Table 1.

Table 1. Diol composition of WPU. Hard segment correspond to the proportion of VBDEA and MDEA

Sample	Priplast (mmol)	VBDEA (mmol)	MDEA (mmol)	MDEA segment (%mol)	Hard segment (%mol)
1	3.0	-	1.5	33	33
2	3.0	-	3.0	50	50
3	3.0	-	6.0	66	66
4	3.0	1.5	2.25	33	55
5	3.0	3.0	3.0	33	66
6	3.0	6.0	4.5	33	78
7	3.0	1.5	4.5	50	66
8	3.0	3.0	6.0	50	75
9	3.0	6.0	9.0	50	83
10	3.0	1.5	9.0	66	78
11	3.0	3.0	12.0	66	83
12	3.0	6.0	18.0	66	89

### Preparation of WPU films

The PU films were prepared by filling a Teflon mold (50 mm X 70 mm X 4 mm) with the WPU aqueous dispersion. After 48 h under ambient condition, PU films were obtained with thickness around 0.5 mm.

Crosslinked films were obtained by an exposure under a solar simulator (Newport, 146 W) during 5 h. Samples were placed to receive one-sun intensity.

### **Characterization**

NMR experiments were performed at 298 K on a Bruker Avance 400 spectrometer operating at 400 MHz, in CDCl<sub>3</sub>.

Size exclusion chromatography (SEC) was performed in DMF on a GPC 50 from Agilent equipped with a series of three columns from Shodex (KD-G: guard column, 4.6 x 10 mm; two KD-804: 8 x 300 mm). The DMF HPLC grade solvent with 1 g.L<sup>-1</sup> of LiBr was used as eluent at 50°C and a flow rate of 0.8 mL.min<sup>-1</sup>. The elution of the filtered samples was monitored using simultaneous refractive index and UV detection. Number-average molar mass (M<sub>n</sub>) and dispersity ( $\bar{D} = M_w/M_n$ , where M<sub>w</sub> is the mass-average molar mass) of the polymers were calculated from a calibration derived from polystyrene standards. The polymer samples were prepared at 5 g.L<sup>-1</sup> and filtered through 0.45 μm PTFE filters.

Infrared spectra (FTIR-ATR) were obtained on a Bruker-Tensor 27 spectrometer, equipped with a diamond crystal, using the attenuated total reflection mode. The spectra were acquired using 16 scans at a resolution of 4 wavenumbers.

Differential Scanning Calorimetry (DSC) measurements were performed on DSC Q100 (TA Instruments). The sample was heated from -80 °C to 120 °C at a rate of 10 °C.min<sup>-1</sup>. Consecutive cooling and second heating run were also performed at 10 °C.min<sup>-1</sup>. The glass transition temperatures were calculated from the second heating run.

Thermogravimetric analyses (TGA) were performed on TGA-Q500 system from TA instruments at a heating rate of 10 °C.min<sup>-1</sup> under nitrogen atmosphere from room temperature to 600°C.



The tensile strength, Young's modulus, and elongation at the break were measured by using the Traction MTS QTest 25 (0.75±0.25) machine at a crosshead speed of 100 mm.min<sup>-1</sup> with 4 mm width for all samples.

The water and solvent resistance were characterized by the solvent swelling. Films were dipped in deionized water, acetone, and THF at room temperature during one week. Percentage of the soluble part and solvent absorption were calculated by using equation 1 and 2 respectively.

$$S = \frac{w_s}{w_i} \times 100 \quad (1)$$

$$Q = \frac{w_f - w_d}{w_d} \times 100 \quad (1)$$

where S is the soluble part of the sample in acetone or THF,  $w_s$  is the weight of the soluble part after drying,  $w_i$  is the weight of the film before dipped; Q is solvent absorption in % and  $w_f$  is the weight of the film after swelling and  $w_d$  is the weight of the dry film after swelling.

The surface energy and the contact angles of water, diiodomethane and ethylene glycol were measured with a contact angle goniometer with a J1H high speed camera (CCD camera type 8420 assembled) using the sessile-drop method at 25 °C. The software used was Drope Shape Analysis DSA for Windows (TM), DSA version 1.90.1.14 (HS).

TEM were carried on a Hitachi H7650 microscope with an acceleration voltage of 80 kV and images were acquired with an ORIUS SC1000 11 MPx Camera. Samples were prepared by nebulizing dispersions of NPs at concentrations of 1 g L<sup>-1</sup> on Formvar/Carbon 200 mesh copper grids from Agar Scientific and leaving them to dry at room temperature.

## RESULTS AND DISCUSSION

### Elaboration and characterization of PU dispersions

PU emulsions were prepared according to the procedure shown in Figure 3. WPU were obtained from an isocyanate (A: HDI, B: IPDI, C: HMDI or D: MDI), a diol (E: Priplast 1900 an amorphous bio-based polyester diol), an emulsifier (F: MDEA) and a crosslinker (G: VBDEA) following the acetone process. The first step consists of a polymerization in acetone. Then, a step of neutralization with acetic acid is realized. Water is then slowly added on the mixture to obtain a dispersion in water and acetone. Finally, acetone is removed by evaporation under vacuum leading to a PU water dispersion with 40 % of solid content. The absence of isocyanate is controlled by FTIR-ATR. Indeed, after 5 h of polymerization, residual isocyanate (peak at  $2275\text{ cm}^{-1}$ ) are still present as expected since an excess of 1.1 eq. of NCO per OH was used but after addition of water, isocyanate was completely hydrolyzed and undetectable by FTIR analysis (see Figure S2 in supplementary data). Molecular masses were controlled in GPC with DMF as solvent,  $M_n$  obtained after hydrolysis are around  $16000\text{ g mol}^{-1}$  for PU obtained with IPDI,  $18000\text{ g mol}^{-1}$  for PU obtained with MDI and  $27000\text{ g mol}^{-1}$  for PU obtained with HDI and HMDI (see Table S1 in supplementary data).




Figure 3. Scheme illustration on the different steps of the preparation of the aqueous dispersion of PU;

(A) HDI, (B) IPDI, (C) HMDI, (D) MDI, (E) Priplast 1900: amorphous polyester diol, (F) MDEA and (G)

VBDEA.

Dispersions have been obtained in all cases, but they are more or less stable over time. In Table 1 are shown the appearance and the particles size of the PU dispersion after six months at room temperature. All isocyanates, except MDI, lead to stable dispersion. For MDI, a formation of cream is observed within few months. In each case, dispersions were obtained with sample 7 to 12 which contained the highest fraction of emulsifier with particle size in the range of 20-200 nm.

TEM images in Figure 4 and S3 confirm the presence of PU particles. However, the particle sizes are overestimated compared to the DLS analysis, 80 nm vs 120 nm. This may be due to the low T<sub>g</sub> of the PU obtained (around -40°C) leading to a flattening of the spherical particles on the TEM grid.




Figure 4. TEM image and TEM particles size distribution of WPU dispersion realized with HDI (sample 10).

Table 2. Average particle sizes and appearance after six months of WPU obtained with HDI and MDI as isocyanate.

Sample	HMDI			HDI			IPDI			MDI		
	Appearance > 5 month	Particle size (nm) <sup>1</sup>	PDI	Appearance > 5 month	Particle size (nm) <sup>1</sup>	PDI	Appearance > 5 month	Particle size (nm) <sup>1</sup>	PDI	Appearance > 5 month	Particle size (nm) <sup>1</sup>	PDI
1	Precipitate	-	-	Aggregate	-	-	Precipitate	-	-	Precipitate	-	-
2	Precipitate	-	-	Semi-transparent	39	0.581	White	42	0.139	Precipitate	-	-
3	Semi-transparent	28	0.105	Semi-transparent	68	0.401	Transparent	26	0.142	Cream	-	-
4	precipitate	-	-	Aggregate	-	-	Precipitate	-	-	precipitate	-	-
5	precipitate	-	-	Aggregate	-	-	Precipitate	-	-	precipitate	-	-
6	White	179	0.682	White	140	0.325	Precipitate	-	-	Cream	-	-
7	White	60	0.149	Semi-transparent	33	0.536	White	107	0.154	Cream	-	-
8	White	38	0.253	Semi-transparent	30	0.741	White	37	0.198	Cream	-	-
9	Semi-transparent	117	0.895	Semi-transparent	25	0.839	White	96	0.202	Cream	-	-
10	Semi-transparent	40	0.124	Semi-transparent	65	0.283	Semi-transparent	21	0.292	Cream	-	-
11	Semi-transparent	43	0.299	Semi-transparent	22	0.390	Semi-transparent	39	0.332	Cream	-	-
12	White	83	0.301	Semi-transparent	260	0.435	Semi-transparent	44	0.415	Cream	-	-

<sup>1</sup> Diameter of particle size in volume determined by DLS

## Elaboration and study of films properties

Films were realized directly after synthesis, even for unstable dispersion. Therefore, WPU film can be obtained whatever the stability of the dispersion. In this section, thermal and mechanical properties of the films were compared before and after irradiation under a solar simulator.

### *Thermal analysis of WPU films*

An example of a thermogravimetric (TGA) curve is shown in Figure 5 and all compositions are described in supplementary data (Table S2). The decomposition temperature ( $T_d$ ) is taken when the weight loss is 5%. For each sample, the degradation is slow, between  $\sim 200$  °C and  $\sim 500$  °C. Composition in diols and isocyanate nature have no significant influence on the  $T_d$  (210-270°C) and no differences were observed before and after crosslinking.




Figure 5. Example of thermograph of WPU before (green) and after (red) UV (sample 11 with HMDI as diisocyanate); solid line corresponds to the loss of weight and dashed line corresponds to the derivative weight.

In DSC analysis (Table 3 and S3) shows that Tg is mainly impacted by the structure of the isocyanate used: Tg (IPDI)  $\approx$  Tg(HDI) < Tg(HMDI) < Tg(MDI). In all cases, Tg of the PU remains low (from -38°C to -50°C). Again irradiation has no significant effect on the Tg.

Table 3 Tg of WPU films before and after irradiation determined by DSC.

	HDI	MDI	HMDI	IPDI
Before crosslinking	-49.9 $\pm$ 1.0°C	-38.4 $\pm$ 2.3°C	-46.9 $\pm$ 1.7°C	-46.4 $\pm$ 2.9°C
After crosslinking	-50.2 $\pm$ 1.8°C	-37.7 $\pm$ 4.0°C	-45.9 $\pm$ 1.8°C	-46.3 $\pm$ 1.4°C

### ***Solvent resistance of WPU films***

Swelling tests were realized in THF and acetone to confirm the formation of a network after irradiation. The results shown in Figure 6 **Erreur ! Source du renvoi introuvable.** and S5 demonstrated that the films obtained are partially crosslinked. As expected the gel fraction is directly proportional to the amount of crosslinker used. In the best case (sample 6) there is only 6 % of the soluble part of the sample in acetone and 11 % in THF. WPU films obtained with IPDI and HDI exhibit similar behavior than film obtained with HMDI. Even though films are not entirely crosslinked, films obtained with HDI, HMDI, and IPDI conserved its shape upon swelling (see Figure 7). It should be noted that in the case of PUs which do not contain any VBDEA as crosslinker (samples 1-3) or the PU films before crosslinking the total solubilization was observed within one day.




Figure 6. Percentage of soluble part of films (S) obtained from HMDI acetone (left) and THF (right); a: diol, b: crosslinker and c: MDEA.




Figure 7. Photo of film obtained from sample 8 realized with HMDI before swelling (left) and after (right) in acetone

### **Water resistance of WPU films**

#### *Contact angle and surface energy*

In Table 4, the water contact angle and surface energy of each family of PU are represented before irradiation and after irradiation. Diols ratio and crosslinking of the film have no visible effect on these properties. Indeed, in each case, a hydrophilic surface with contact angle between  $56.2 \pm 1.2^\circ$  and  $84.8 \pm 1.1^\circ$ , and surface energy between  $30.9 \pm 0.3 \text{ mN.m}^{-1}$  and  $49.8 \pm 0.7 \text{ mN.m}^{-1}$  is obtained. The film with the highest hydrophilicity and surface energy were obtained with IPDI; the lowest with HDI.

Table 4. Average water contact angle and surface energy of each family of PU before irradiation and after irradiation.



	HMDI		IPDI		MDI		HDI	
	Before UV	After UV	Before UV	After UV	Before UV	After UV	Before UV	After UV
Water Contact Angle	71.4±1.6	72.4±1.7	60.5±1.1	56.2±1.2	82.4±0.8	76.3±1.1	84.8±1.1	81.5±1.2
Surface Energy (mN.m <sup>-1</sup> )	39.3±0.4	38.5±0.2	44.4±0.2	49.8±0.7	34.4±0.3	33.8±0.5	30.9±0.3	32.7±0.4

### Swelling test on water

In **Erreur ! Source du renvoi introuvable.** and S7 are represented water absorption (Q) of WPU. Irradiation of the film allows to dramatically decrease the water absorption except with MDI as diisocyanate where no change was observed. As expected the absorption is directly linked to the crosslinker ratio. As a result, crosslinked WPU films with water absorption below 5% were obtained.




Figure 8. Water absorption of WPU film obtained with HMDI:  $Q = \frac{w_f - w_i}{w_i} \times 100$  (%);  $w_f$  = weight of the film after swelling;  $w_i$  = initial weight of the film; a: polyol, b: crosslinker, c: MDEA and NF: No Film.

### Mechanical properties of WPU films

Finally the mechanical properties of the PU films were determined. Whatever the isocyanate used, tensile strength and modulus are higher after irradiation (Erreur ! Source du renvoi introuvable. 5 and Figure 9, 10, and S6). For example, in the case of PU based on HMDI, the maximum of tensile strength and Young's modulus are respectively 7.7 and 125 MPa while after irradiation its increase to 15 and 247 MPa.




Figure 9. Tensile test of HMDI-based PU films before irradiation (left) and after irradiation (right); samples realized from HMDI as isocyanate (red: film 4, black: film 6, green: film 10 and blue: film 12)

The deformation of each film tends to increase after irradiation if the deformation at break is inferior to approximately 120-130 % before irradiation. However, it will decrease if the initial deformation is over this value. For example, the deformation of the sample 6 obtained with HMDI has an elongation at the break at 23 % before irradiation and 318 % after irradiation. In contrary, the deformation of the sample 12 has an elongation at the break at 302 % before irradiation and 147 % after irradiation.

Table 5. Minimum and maximum value of tensile strength, elongation and modulus of each family of isocyanate with the crosslinker include on the composition; NF = No film

	HMDI		IPDI		MDI		HDI	
	Before UV	After UV	Before UV	After UV	Before UV	After UV	Before UV	After UV
Tensile strength (MPa)	0.2-7.7	3-15	NF-2.1	2-16	NF-2.4	0.3-4.6	0.1-1	0.9-5.4
Elongation (%)	120-784	23-312	NF-322	12-344	NF-196	24-120	16-1718	31-197

Modulus (MPa)	0.1-125	9-247	NF-63	2-251	NF-42	1-103	1-13	6-21
---------------	---------	-------	-------	-------	-------	-------	------	------




Figure 10. Mechanical properties of WPU films realized with HMDI before irradiation to the top and after irradiation to the bottom: in green is represented the tensile strength, in blue the elongation and in orange the modulus; a: diol, b: crosslinker and c: MDEA; NF = No film.

## CONCLUSIONS

To conclude this study waterborne polyurethane (WPU) were synthesized from a bio-sourced diol by cationic dispersion using four isocyanates (HMDI, HDI, IPDI and MDI). These WPUs were obtained by the acetone process. *N*-4-vinylbenzyl-diethanolamine, was synthesized and incorporated in these WPU as internal UV crosslinker. All isocyanate except MDI lead to a stable dispersion with solid content of 40 wt.%. From these dispersions, homogeneous films were obtained by air-drying and their properties compared before and after irradiation under solar simulator. While thermal and surface properties remain

unchanged by the crosslinking, the irradiation lead to an improvement of mechanical properties. Indeed, Tensile strength and Young's modulus increase after irradiation for all composition. To conclude, VBDEA appears to be a versatile crosslinker for WPU applications.

## **ACKNOWLEDGEMENTS**

The authors thank University of Bordeaux, Bordeaux INP, CNRS, Aquitaine Regional Council and FUI for the financial support of this research. They also thank the Equipex Xyloforest ANR-10-EQPX-16 XYLOFOREST for flash chromatography.

## **REFERENCES**

1. Engels, H. W.; Pirkl, H. G.; Albers, R.; Albach, R. W.; Krause, J.; Hoffmann, A.; Casselmann, H.; Dormish, J., *Angewandte Chemie - International Edition* 52, 9422 2013.
2. Avar, G.; Meier-Westhues, U.; Casselmann, H.; Achten, D. In *Polymer Science: A Comprehensive Reference*, 10 Volume Set, 2012.
3. Delebecq, E.; Pascault, J. P.; Boutevin, B.; Ganachaud, F., *Chemical Reviews* 113, 80 2013.
4. Noreen, A.; Zia, K. M.; Zuber, M.; Tabasum, S.; Saif, M. J., *Korean Journal of Chemical Engineering* 33, 388 2016.
5. Zhou, X.; Li, Y.; Fang, C.; Li, S.; Cheng, Y.; Lei, W.; Meng, X., *Journal of Materials Science and Technology* 31, 708 2015.
6. Noble, K. L., *Progress in Organic Coatings* 32, 131 1997.
7. Dieterich, D., *Progress in Organic Coatings* 9, 281 1981.
8. Kim, B. K., *Colloid and Polymer Science* 274, 599 1996.

9. Barni, A.; Levi, M., *Journal of Applied Polymer Science* 88, 716 2003.
10. Madbouly, S. A.; Otaigbe, J. U., *Progress in Polymer Science (Oxford)* 34, 1283 2009.
11. Kim, B. K.; Lee, Y. M., *Colloid & Polymer Science* 270, 956 1992.
12. Visser, S. A.; Cooper, S. L., *Polymer* 33, 3790 1992.
13. Kwak, Y. S.; Kim, E. Y.; Yoo, B. H.; Kim, H. D., *Journal of Applied Polymer Science* 94, 1743 2004.
14. Nanda, A. K.; Wicks, D. A.; Madbouly, S. A.; Otaigbe, J. U., *Journal of Applied Polymer Science* 98, 2514 2005.
15. Athawale, V. D.; Kulkarni, M. A., *Progress in Organic Coatings* 67, 44 2010.
16. Li, Q. A.; Sun, D. C., *Journal of Applied Polymer Science* 105, 2516 2007.
17. Lewandowski, K.; Krepski, L. R.; Mickus, D. E.; Roberts, R. R.; Heilmann, S. M.; Larson, W. K.; Purgett, M. D.; Koecher, S. D.; Johnson, S. A.; McGurran, D. J.; Rueb, C. J.; Pathre, S. V.; Thakur, K. A. M., *Journal of Polymer Science, Part A: Polymer Chemistry* 40, 3037 2002.
18. Reischl, A.; Dieterich, D.; Witt, H.; Google Patents: 1973.
19. Cheng, K. L.; Chen, W. T.; Google Patents: 2001.
20. Chinwanitcharoen, C.; Kanoh, S.; Yamada, T.; Hayashi, S.; Sugano, S., *Journal of Applied Polymer Science* 91, 3455 2004.
21. Raut, K. G.; Bapat, S. P.; Tanavade, S. S., *European Coatings Journal*, 48 1999.
22. Mishra, V. K.; Patel, K. I., *Journal of Dispersion Science and Technology* 36, 351 2015.
23. Chen, Y.; Chen, Y. L., *Journal of Applied Polymer Science* 46, 435 1992.
24. Cakić, S. M.; Špirková, M.; Ristić, I. S.; B-Simendić, J. K.; M-Cincović, M.; Poreba, R., *Materials Chemistry and Physics* 138, 277 2013.
25. Pérez-Limiñana, M. A.; Arán-Aís, F.; Torró-Palau, A. M.; Orgilés-Barceló, A. C.; Martín-Martínez, J. M., *International Journal of Adhesion and Adhesives* 25, 507 2005.
26. Sukhawipat, N.; Saetung, N.; Saetung, A. in *Key Engineering Materials*: 2016, p 19.

27. Daemi, H.; Rad, R. R.; Barikani, M.; Adib, M., *Applied Catalysis A: General* 468, 10 2013.
28. Gurunathan, T.; Rao, C. R. K.; Narayan, R.; Raju, K. V. S. N., *Progress in Organic Coatings* 76, 639 2013.
29. Chan, W. C.; Chen, S. A., *Polymer* 29, 1995 1988.
30. Zhang, M.; Hemp, S. T.; Allen, M. H.; Carmean, R. N.; Moore, R. B.; Long, T. E., *Polymer Chemistry* 5, 3795 2014.
31. Williams, S. R.; Wang, W.; Winey, K. I.; Long, T. E., *Macromolecules* 41, 9072 2008.
32. Fang, Z. H.; Duan, H. Y.; Zhang, Z. H.; Wang, J.; Li, D. Q.; Huang, Y. X.; Shang, J. J.; Liu, Z. Y., *Applied Surface Science* 257, 4765 2011.
33. Wang, X.; Hu, Y.; Song, L.; Xing, W.; Lu, H.; Lv, P.; Jie, G., *Journal of Polymer Research* 18, 721 2011.
34. Xu, J.; Rong, X.; Chi, T.; Wang, M.; Wang, Y.; Yang, D.; Qiu, F., *Journal of Applied Polymer Science* 130, 3142 2013.
35. Zhang, S.; Yu, A.; Song, X.; Liu, X., *Progress in Organic Coatings* 76, 1032 2013.
36. Yu, F.; Cao, L.; Meng, Z.; Lin, N.; Liu, X. Y., *Polymer Chemistry* 7, 3913 2016.
37. Zhang, Y.; Asif, A.; Shi, W., *Progress in Organic Coatings* 71, 295 2011.
38. Bhusari, G. S.; Umare, S. S.; Chandure, A. S., *Journal of Coatings Technology Research* 12, 571 2015.
39. Zhang, S.; Chen, J.; Han, D.; Feng, Y.; Shen, C.; Chang, C.; Song, Z., *Journal of Polymer Research* 22, 2015.
40. Yang, Z.; Wicks, D. A.; Hoyle, C. E.; Pu, H.; Yuan, J.; Wan, D.; Liu, Y., *Polymer* 50, 1717 2009.
41. Blank, W. J.; Tramontano, V. J., *Progress in Organic Coatings* 27, 1 1996.
42. Srivastava, A.; Agarwal, D.; Mistry, S.; Singh, J., *Pigment and Resin Technology* 37, 217 2008.
43. Hearon, K.; Smith, S. E.; Maher, C. A.; Wilson, T. S.; Maitland, D. J., *Radiation Physics and Chemistry* 83, 111 2013.

44. Hoffmann E., N., Takashi, Haibara-gun, Shizuoka-ken (FUJIFILM Co), EP 2 042 309 A2, September 26, 2008.

45. Jin, L. Y.; Hou, R.; Chen, T.; Fang, M.; Mah, S.; Yin, B., *Fibers and Polymers* 8, 143 2007.

## Supplementary data:

### Cationic water dispersion of bio-sourced crosslinked polyurethane

Laurence Pessonj,<sup>a,b</sup> Prakash Sane,<sup>a,b</sup> Etienne Grau,<sup>\*a,b</sup> Henri Cramail<sup>\*a,b</sup>

Characterization of polyurethanes obtained:




FIGURE S1 NMR spectra in CDCl<sub>3</sub> of VBDA in blue, of MDEA in green and VBC in red.



TABLE S1 Molecular weight in number of WPU in g.mol<sup>-1</sup>

	IPDI	HDI	MDI	HMDI
	Mn(Đ)	Mn(Đ)	Mn(Đ)	Mn(Đ)
Priplast	5800	5800	5800	5800
1	35000(1.7)	19700(1.8)	16200(1.2)	20600(1.6)
2	10900(1.7)	20800(1.6)	27000(1.5)	21100(1.5)
3	18300(1.7)	66000(1.3)	9700(1.6)	23900(1.7)
4	14700(1.4)	17600(1.5)	11300(1.8)	23200(1.6)
5	12200(1.5)	18300(1.6)	13500(1.7)	11700(1.5)
6	10100(2.1)	20900(1.6)	18100(1.8)	45700(1.7)
7	13900(1.5)	19100(1.5)	11600(1.9)	22300(1.8)
8	13800(1.5)	23900(1.7)	17400(1.8)	23800(1.9)
9	10300(1.6)	27800(1.7)	21900(1.8)	39200(1.6)
10	20600(1.8)	26300(1.9)	16800(1.7)	23100(1.6)
11	12500(1.8)	20400(2.0)	18900(1.8)	36500(1.8)
12	16300(1.8)	49300(2.6)	20400(1.8)	26100(1.8)
Average	15700	27500	18000	26400




Figure S2 Spectrum of ATR-IR of film "9" realized with HMDI.

TABLE S2 TGA analysis of WPU films before (A) and after (B) irradiation

TGA Sample	IPDI		MDI		HDI		HMDI	
	A	B	A	B	A	B	A	B
1	249	-	252	-	258	-	271	-
2	230	-	240	-	263	-	259	-
3	239	-	226	-	256	-	271	-
4	237	263	228	237	269	258	267	274
5	209	250	267	228	265	253	270	263
6	259	270	243	230	269	249	248	278
7	244	265	233	229	270	250	270	262
8	248	255	244	240	266	243	247	261
9	250	261	223	224	263	232	270	268
10	228	262	235	231	258	243	253	254
11	252	266	215	212	243	235	263	266
12	249	262	207	205	228	228	251	252

TABLE S3 DSC analysis of WPU films before (A) and after (B) irradiation

	cationique							
	IPDI		MDI		HDI		HMDI	
	A	B	A	B	A	B	A	B
1	-45,29	-	-39,42	-	-50,63	-	-47,70	-
2	-45,37	-	-41,14	-	-49,82	-	-47,80	-
3	-48,24	-	-41,17	-	-51,38	-	-46,70	-
4	-47,47	-47,40	-38,65	-40,03	-50,02	-51,02	-45,14	-47,86
5	-44,67	-46,12	-36,56	-32,44	-49,51	-51,28	-47,76	-48,48
6	-44,99	-43,34	-36,04	-33,47	-50,14	-48,21	-44,49	-42,72
7	-44,84	-46,69	-36,61	-42,19	-49,45	-50,31	-45,99	-47,48
8	-40,43	-47,12	-37,06	-31,33	-50,21	-49,81	-44,48	-46,23
9	-49,92	-47,81	-35,51	-39,82	-51,29	-50,10	-47,52	-45,30
10	-51,41	-45,80	-36,62	-37,80	-47,22	-49,72	-49,99	-44,20
11	-44,87	-47,89	-43,11	-42,60	-49,70	-49,68	-49,38	-44,20
12	-49,60	-44,74	-39,53	-39,95	-49,56	-51,82	-46,11	-47,00
MOY	-46,43	-46,32	-38,45	-37,74	-49,91	-50,22	-46,92	-45,94

### Characterization of dispersions:

Others dispersion tests:

For all the water dispersion obtained, 1.1 equivalent of acetic acid to MDEA was added. For example, the sample 4 with HMDI did not lead a good dispersion. But, VBDEA can be also quaternized. Therefore, dispersion could be improved with the addition of more acetic acid in order to have 1.1 equivalents of crosslinker plus emulsifier (sample 4', TABLE S4 and Figure S4). In this condition dispersion obtained was stable. Particle size obtained is 71 nm with a PDI at 0.209. However, VBDEA alone (sample 13 with HMDI) did not lead to good dispersion in the same proportion than MDEA (sample 3 with HMDI).

TABLE S4 Dispersion tests

	Priplast mmol	VBDEA mmol	MDEA mmol	Acetic acid mmol	Dispersion
Sample 4	3	1.5	2.25	2.47 <sup>1</sup>	No
Sample 4'	3	1.5	2.25	4.13 <sup>2</sup>	Yes
Sample 3	3	0	6	6.6 <sup>1</sup>	Yes
Sample 13	3	6	0	6.6 <sup>3</sup>	No

<sup>1</sup> 1.1 Equivalent compare to MDEA

<sup>2</sup> 1.1 Equivalent compare to MDEA and VBDEA

<sup>3</sup> 1.1 Equivalent compare to VBDEA

TEM images:




FIGURE S3 TEM images and TEM particles size distribution of WPU dispersion realized with HMDI (sample 7) and HDI (sample 9).




FIGURE S4 Picture of dispersion obtained with HMDI as isocyanate of the sample 4 with 1.1 equivalent of acetic acid compare to MDEA (left) and 1.1 equivalent of acetic acid compare to MDEA plus crosslinker (right)

Characterization of films:






FIGURE S5 Percentage of soluble part of films obtained from HDI, IPDI and MDI in acetone and in THF; a: polyol, b: crosslinker and c: MDEA.






FIGURE S6 Mechanical properties of WPU films realized with IPDI, MDI and HDI before irradiation to the top and after irradiation to the bottom: in green is represented the tensile strength, in blue the elongation and in orange the modulus; “a” is the polyol, “b” is the crosslinker and “c” is the emulsifier; NF = No film.




FIGURE S7 Water absorption of WPU films obtained with HDI, IPDI and MDI before UV (right) and after UV (left):  $Q = \frac{w_f - w_i}{w_i} \times 100$  (%);  $w_f$  = mass of the film after swelling;  $w_i$  = initial mass of the film; NF = No film, a: polyol, b: crosslinker and c: MDEA.