

Crystallographic orientation maps obtained from ion and back scattered electron channeling contrast

Cyril Langlois, Clément Lafond, Thierry Douillard, Sébastien Dubail, Sophie

Cazottes

► To cite this version:

Cyril Langlois, Clément Lafond, Thierry Douillard, Sébastien Dubail, Sophie Cazottes. Crystallographic orientation maps obtained from ion and back scattered electron channeling contrast. 19th International Microscopy Congress, Sep 2018, Sydney, Australia. hal-02138699

HAL Id: hal-02138699 https://hal.science/hal-02138699

Submitted on 24 May 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Crystallographic orientation maps obtained from ion and back scattered electron channeling contrast

LANGLOIS, C.¹, LAFOND, C.¹, DOUILLARD, T.¹, DUBAIL, S.² and CAZOTTES, S.¹ ¹MATEIS Laboratory, INSA, University of Lyon – CNRS (France), ²Axon Square Ltd. (France)

INTRODUCTION

For several years now, new directions have been explored to obtain orientation maps by other means than the classical Electron Back Scattered Diffraction (EBSD) setup, or to modify it aiming at improved information. Particularly, the channeling contrast may be used to obtain orientation maps, which is the approach presented here, called CHanneling ORientation Determination (CHORD) [1,2]. The main idea relies on the acquisition of an electron or ion image series when rotating a pre-inclined polycrystalline sample with respect to the beam. Along such image series, each (X,Y) pixel of the region of interest undergoes an intensity variation due to the channeling effect, that can be plotted as a function of the rotation angle. Such intensity profiles can be theoretically predicted for a given orientation of a crystal, as described in the following. The orientation is retrieved by a search in a database of theoretical profiles obtained by simulating intensity profiles for a large set of orientations. The principal issue is to model quantitatively for ions and electrons the channeling effect observed in such image series.

Mateis CNIS

CHANNELING CONTRAST

The channeling of the incident beam by crystallographic planes is responsible for the arev level difference between differently oriented grains in a polycrystalline material.


- if the ion beam is parallel to low index planes, the secondary electron are generated far under the surface. A low intensity is then detected.
- with an electron beam, the MMMintensity received by the detector is monitored by back scattered diffraction including dynamical effects

More details on the channeling effect available in ref [3]






ACQUISITION



POST-TREATMENTS

From raw image series


- → Alignment
- → Crop on the region of interest
- → Denoising (eventually)






- · construction of a database of theoretical intensity profiles THEN
- pick up an intensity profile at (X,Y) position
- explore the database to find the closest theoretical one
- assign the corresponding theoretical orientation to the (X,Y)position





ION CHANNELING MODELIZATION

Ballistic description ; numerical approach based on the relationship between the « shadow » of the structure and the detected intensity



For Euler orientation ($\phi_1 \, \Phi \, \phi_2)$ and each rotation angle, the intensity in the profile is the sum of grey levels in the projection.

REFERENCES

Langlois C. *et al.*, Ultramicroscopy 157 (2015), p. 65
Lafond C. *et al.*, Ultramicroscopy, 186 (2018), p. 146
Newbury D. E.*et al.*, Advanced Scanning Electron Microscopy and X-Ray Microanalysis, Springer (1986)
Singh S. & De Graef M., Microscopy and Microanalysis, 23 (2017), p. 1


Gra

250 300 Grain 2 deg


An experimental intensity profile is obtained for each (X,Y) position.

ELECTRON CHANNELING MODELIZATION

Based on similarities with Electron Channeling Pattern acquisition (ECP) ; diffraction including dynamical effects using M. De Graef EMsoft codes [4].




Gathering the intensity along the ECP 10° circle...



Crystallographic orientation maps obtained from ion and back scattered electron channeling contrast

LANGLOIS, C.¹, LAFOND, C.¹, DOUILLARD, T.¹, DUBAIL, S.² and CAZOTTES, S.¹ ¹MATEIS Laboratory, INSA , University of Lyon – CNRS (France), ²Axon Square Ltd. (France)


ECHORD: EXAMPLES




eCHORD map (raw)

Disorientation map eCHORD / EBSD

ICHORD: EXAMPLES



(noise corrected)




iCHORD [001] IPF map

EBSD [010] IPF map (noise corrected)


COBALT SUPERALLOY SAMPLE

eCHORD map (raw) Disorientation map eCHORD / EBSD



iCHORD [010] IPF map

ANGULAR RESOLUTION OF ICHORD MAPS - EXAMPLE ON INCONEL SAMPLE



- More on phase discrimination capability → oral presentation from C. Lafond on Monday 14:45, Meeting Room C4.1
- For a focus on acquisition and image treatments, → oral presentation from C. Langlois on Tuesday 16:00, Meeting Room C4.11

