



HAL
open science

Electro-polymerization of pyrrole on graphite electrode: enhancement of electron transfer in bioanode of microbial fuel cell

Mekhaissia Ouis, Mostéfa Kameche, Christophe Innocent, Mustapha Charef,
Hakima Kebaili

► **To cite this version:**

Mekhaissia Ouis, Mostéfa Kameche, Christophe Innocent, Mustapha Charef, Hakima Kebaili. Electro-polymerization of pyrrole on graphite electrode: enhancement of electron transfer in bioanode of microbial fuel cell. *Polymer Bulletin*, 2018, 75 (2), pp.669-684. 10.1007/s00289-017-2048-5. hal-02322483

HAL Id: hal-02322483

<https://hal.science/hal-02322483>

Submitted on 15 Jan 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Polymer Bulletin

Electro-polymerization of pyrrole on graphite electrode: Enhancement of electron transfer in bio-anode of Microbial Fuel Cell --Manuscript Draft--

Manuscript Number:	
Full Title:	Electro-polymerization of pyrrole on graphite electrode: Enhancement of electron transfer in bio-anode of Microbial Fuel Cell
Article Type:	Original Article
Section/Category:	Polymer Characterization
Funding Information:	
Abstract:	<p>The enhancement of the power output of a Microbial Fuel Cell (MFC) relies on two important issues: the immobilisation of the catalyst microbial film on the bio-anode where oxidation occurs and the electron transfer between them. In the present work, a graphite rod was used as anode and modified by electro-polymerisation using the conducting polymer (pyrrole). It was resulted an improvement of the electronic conduction and therefore an increase of the power density of the cell (i.e. from 7 to 25 mW/m²). The electroactive biofilm was produced from compost leachate garden, deposited naturally on the anode without prior polarisation. The efficiency of this modification was investigated to determine the supply of pyrrole in term of electricity generation. The results show enormous power density supply of the MFC using bio-anode modified with pyrrole.</p> <p>Besides, since the energy produced by a MFC is too small, it would be interesting to recover the maximum of it by selecting the appropriate materials which fulfil the two criteria: better electron transfer and longer bacteria life.</p>
Corresponding Author:	mostefa kameche, PhD Universite des Sciences et de la Technologie d'Oran Mohamed Boudiaf oran, oran ALGERIA
Corresponding Author Secondary Information:	
Corresponding Author's Institution:	Universite des Sciences et de la Technologie d'Oran Mohamed Boudiaf
Corresponding Author's Secondary Institution:	
First Author:	mostefa kameche, PhD
First Author Secondary Information:	
Order of Authors:	mostefa kameche, PhD mekhaissia ouis, master christophe innocent, PhD mustapha abdeldjebbar charef, PhD hakima kebaili, magister
Order of Authors Secondary Information:	
Author Comments:	Cover letter October, 24th 2016 To Editor of Polymer Bulletin Dear Professor, You find enclosed a research paper entitled "Electro-polymerization of pyrrole on graphite electrode: Enhancement of electron transfer in bio-anode of Microbial Fuel Cell" to be submitted to Polymer Bulletin. The work described in this paper concerns

	<p>the electro-polymerization of pyrrole on carbon graphite to be used as a bio-anode in a Microbial Fuel Cell.</p> <p>Yours Sincerely, M. KAMECHE (Corresponding author)</p>
<p>Suggested Reviewers:</p>	<p>sophie tingry, PhD Researcher, Universite de Montpellier Sophie.tingry@univ-montp2.fr because she is involved in the research topic:elaboration of bio-anodes for fuel cells</p> <p>christopher picket, PhD Teacher and researcher, INTO University of East Anglia c.pickett@uea.ac.uk because he is involved in the research topic:electropolymer materials</p> <p>james Rusling, PhD Teacher and researcher, University of Connecticut james.rusling@uconn.edu because he is involved in the research topic:Characterizing Materials with Cyclic Voltammetry</p> <p>hongqiang Ren, PhD Teacher and researcher, Nanjing University of Technology hqren@nju.edu.cn because he is involved in the research topic:microbial fuel cells</p>

[Click here to view linked References](#)

**Electro-polymerization of pyrrole on graphite electrode:
Enhancement of electron transfer in bio-anode of Microbial Fuel Cell**

Mekhaissia OUIS ¹, Mostefa KAMECHE ^{1*}, Christophe INNOCENT ²,

Mustapha CHAREF ¹, Hakima KEBAILI ¹

¹Laboratoire de Physico-Chimie des Matériaux, Catalyse et Environnement, Université des Sciences et de la Technologie d'Oran-Mohammed Boudiaf, M'Nouar BP, 1505, Oran, Algérie

²Institut Européen des Membranes, UMR 5635, Université Montpellier II, CC 047, Place Eugène Bataillon, 34095 Montpellier cedex 5, France

Abstract

The enhancement of the power output of a Microbial Fuel Cell (MFC) relies on two important issues: the immobilisation of the catalyst microbial film on the bio-anode where oxidation occurs and the electron transfer between them. In the present work, a graphite rod was used as anode and modified by electro-polymerisation using the conducting polymer (pyrrole). It was resulted an improvement of the electronic conduction and therefore an increase of the power density of the cell (i.e. from 7 to 25 mW/m²). The electroactive biofilm was produced from compost leachate garden, deposited naturally on the anode without prior polarisation. The efficiency of this modification was investigated to determine the supply of pyrrole in term of electricity generation. The results show enormous power density supply of the MFC using bio-anode modified with pyrrole.

Besides, since the energy produced by a MFC is too small, it would be interesting to recover the maximum of it by selecting the appropriate materials which fulfil the two criteria: better electron transfer and longer bacteria life.


Key Words: Microbial Fuel Cell; Leachate garden soil; Bio-anode; Conducting polymer.

*Corresponding author; mail to:kameche@hotmail.com or mostefa.kameche@yahoo.fr

1. Introduction

Fuel cells are alternative energy sources that convert directly the stored chemical energy into renewable electrical energy. The conversion takes place via an electrochemical process and not combustion; a process not polluting and three times efficient than fuel burning.

Owing to environmental preservation, new but weak bacterial energy sources were investigated to degrade organic matter and therefore to reduce pollution [1]. Microbial Fuel Cells (MFCs) are good candidates for this purpose. They are electrochemical devices which generate electricity from oxidation and reduction processes taking place in micro-organisms [2]. In a MFC, the anodic chamber is usually separated from the cathodic chamber by a proton exchange membrane. In the presence of the electroactive biofilm adhered on the anode, the fuel (organic matter) oxidizes, by releasing electrons and protons [1, 3]. The basic operating principle of an MFC can be explained using the classical dual-chamber MFC. Under biocatalysis, organic carbons are oxidized by the biofilm covering the anode in the anodic chamber under anaerobic condition. Reaction (1) shows the half-reaction using acetate as an example organic carbon. The oxidation occurs inside the cytoplasm of the sessile cells (i.e. biofilm cells). The electrons released by oxidation are transferred by the sessile cells in the anodic biofilm to the anode surface. These electrons flow through an external circuit to reach the cathode in the cathodic chamber where they are used for reduction of oxygen. To maintain electro-neutrality, protons migrate from the anodic chamber to the cathodic chamber to participate in reaction (2) [4].



The materials such as Carbon Graphite (CG) and Carbon Felt (CF) are usually suitable as anodes in MFCs, due to their chemical stability and high electric conductivity [5].

Characteristics of bio-anode are also considered to be significant as it directly affects the bacterial interaction, electron transfer, and substrate oxidation [6, 7].

Anode for MFC, as the bacteria carrier, can influence not only the bacteria adhesion but also the electrons transfer process from the microorganisms to the anode. So an excellent anode should prompt the electrons transfer process described above and suitable for microbial growth. Various strategies have been developed to improve MFC anode, such as metal and nonmetal materials modified [8,9].

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

Conductive polymer materials, which have both strong conductivity and the properties of polymers, are widely used in electronics and biosensors [10]. Recently, they have earned more attention to improve MFC performance by modifying its anode.

In this study, pyrrole was used to modify electrode material, owing to its stable redox reaction and its outstanding electrical conductivity [11]. However, conductive polymers, due to the special characteristics, are likely to affect the bacteria attachment on anode and the process of electrons transfer from bacteria to anode, which can change the biofilm and further affect the MFC power generation. Even the power density can also affect microbial diversity of anode biofilm, in return [12].

Pyrrole was electro-polymerized on the CG, to enhance the electron transfer between the bio-film and the anode. The influence of modification of bioanode has been investigated by performance of the MFC measurement.

2. Experimental Sections

2.1. *Materials*

Garden compost was purchased from Neuhaus (France). The reagents hydrochloric acid, potassium chloride and sodium acetate were of analytical grade. The Nafion 115 membrane from DuPont de Nemours (USA) was used as a separator in the MFC. The materials used for the electrodes were: CG or CF as bio-anode and the alloy titan-platinum or stainless steel sheets as cathode. The multi-meters Fluck 175, pH meter Hanna and conductimeter Hanna were also used. Solutions were prepared using reverse osmosis demineralized water. The TOC instrument for to measure the degradation organic carbon. The potentiostat-galvanostat Voltalab PGZ301 was also used for the modification of the bio-anode and its electrochemical characterization using chrono-amperometry and voltammetry techniques.

2.2. *Methods*

2.2.1. *Preparation of compost leachate*

The microbial flora was extracted by lixiviation, from the mixture of 500g of the Neuhaus garden soil and 1 L of aqueous potassium chloride solution 60 mM. The mixture was placed in an Erlenmeyer and stirred with a magnetic agitator during 72 hours. Then, it was filtered using a paper filter to yield the leachate compost having an ionic conductivity of 4 mS/cm at pH 6.5.

2.2.2. *Elaboration of bio-anode*

1 A CG bar having the dimensions (0.5 x 0.5 x 5.0 cm) was immersed into the compost leachate
2 where it was stored. Then, it was removed from the conditioning solution and dipped again
3 into a new leachate solution, to be used as a bio-anode inside the MFC.
4
5
6
7

2.2.3. *Modifications of bio-anode*

8
9
10 In order to improve its electronic conduction, the CG anode was modified by electro-
11 polymerisation of Pyrrole (Sigma Aldrich) known as a high conducting polymer. According
12 to the literature the electrical conductivity of Polypyrrole (PPy) ranges between 2.0 - 2.5
13 S.cm⁻¹ in LiBF₄ aqueous solution [13] and that of graphite carbon is about 10⁻² S.cm⁻¹ [14]. In
14 effect, the aqueous solution of lithium tetrafluoroborate (Aldrich) was used as a support
15 electrolyte, in the conventional three-electrode electrolysis cell. It consists of the graphite
16 working electrode, Ag/AgCl reference electrode and platinum counter-electrode. PPy films
17 were electro-generated and electro-deposited at room temperature by cyclic voltammetry in
18 the potential range (0-0.9 V). Cyclic voltamograms (Fig.1) shows the formation of dimers
19 (pyrrole oxidation) from 0 to 400 mV. More than 400 mV the synthesis of PPy is started (the
20 combination of dimers).
21
22

23
24
25 The polymerization of pyrrole is well described elsewhere [15,16].The electrochemical
26 synthesis mechanism is due to the partly conjugated PPy.
27
28
29
30
31
32
33
34
35
36
37

38 Fig.1

39 *SEM images*

40
41
42 The magnified SEM images (Fig2) allow for clear perception of the fine structure details.
43 They show the electrode surface before and after modification with PPy. In effect, in the
44 absence of the polymer, it can be observed thin wafers of carbon graphite, separated by empty
45 spaces. In contrast, in the in presence of PPy, the wafers are tightly joined to each other by
46 reducing spaces between them. Moreover, the roughness of the modified electrode becomes
47 higher unlike to smooth electrode without PPy. This modification may provide a better
48 adhesion of the biofilm onto the electrode and therefore a better electron transfer. Besides, on
49 a fundamental scale, the displacement of the electron is relatively higher, because the band
50 gap in carbon is reduced by PPy allowing mean free path of the electron inside the material.
51 For all these reasons, the electron density produced by the MFC increases. As it is illustrated
52
53
54
55
56
57
58
59
60
61
62
63
64
65

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65

by the diagram given by Fig., the the electrical conductivity of PPy is highly greater than that of graphite carbon

Fig.2

2.2.4. *Electroactive biofilm growth*

The electroactive biofilm growth was carried out naturally without applying chronoamperometry as did previous researchers in the field [16, 17]. In Fig.3a, the solution of the compost leachate was dark brown in the beginning. After 20 days of mature, the leachate became almost transparent and a great deal of bio-film aggregated around the anode (Fig.3b). However, small amounts of aggregates flatted on the solution surface. During 10 days, Champavert *et al.* found an electromotive force almost equal to ours [17].

Fig.3a

Fig.3b

2.3. *Microbial Fuell Cell design*

As illustrated by Fig.4, the MFC consists of two half-cells made glass, connected to each other by the Nafion[®] membrane (cationic exchange perfluorinated membrane). The CG bio-anode and the platinized titanium sheet (1 x 5 cm) are placed inside the anolyte and the catholyte respectively. The anolyte contains the leachate solution; whereas the catholyte contains hydrochloric acid solution 0.1 M. the solutions were stirred with magnetic bars. The top end of the anolyte was tightly sealed with paraffin film to avoid penetration of oxygen. The circuit of the cell was closed with an external resistance of 1 000 Ω . The cell voltage of the cell was measured with a multimeter placed in parallel. Owing to the fact of very values, the current density was deduced using Ohm's law. After 20 hours of functioning, both the level of the solution and the current density fell, as a result of the decrease of the contact surface of interface solution/bio-anode. So, the amount of leachate removed, was substituted

by the same amount of sodium acetate 20 mM. After 5 hours, as a result of acclimation, a significant increase of the current was observed (approximately twice higher than that obtained with just pure leachate) and continued to increase provided the fuel was added. Moreover, from the higher current obtained, the power density was determined in terms of current density by varying the external resistance from 100 to 50 000 Ω. Generally, the value of the current stabilized within 3 minutes. However, the required time needed to reach the initial value, depended upon the value of the resistance. In effect, the smaller the value of the resistance, the higher the cell discharge.

Fig.4

2.4. Total Organic Carbon Analysis

The Total Organic Carbon (TOC) is the amount of carbon found in an organic compound. In our case, the amount of carbon contained in sodium acetate was measured with a TOC analyzer received recently by our laboratory. As it is illustrated by Fig.5, during the course of experiment, the quantity of carbon present initially in the solution was drastically reduced, showing the degradation of the fuel (acetate anion) by the bio-film. This yielded an amount of CO₂ which will be consumed by the bacteria. This finding is coherent with the oxidation reaction of acetate (Eq.1). In the cases of sodium acetate, for leachate and mixture (MFC before operating), it is clear that the content of carbon was relatively high. But, when the MFCs started working, the amount of carbon was reduced equally by 25%, whatever the type of the bioanode (unmodified or modified). This finding makes in evidence the degradation of the organic matter by biofilm, transforming the carbon into hydrocarbonate (HCO₃⁻).




Fig.5

1
2
3
4 **3. Results and Discussion**
5
6

7 **3.1. Evolution of ElectroMotive Force (EMF)**
8

9 This work presents the novel bioanode electrode modified with PPy for use in the microbial
10 fuel cell described above, with the aim to obtain the highest electrical energy. The generated
11 EMFs of MFCs using both unmodified and modified bioanodes were represented in (Fig.6).
12 During the course of the experiment, the EMF decreases a little bit and remains almost
13 constant, for 24 h. However, their values are completely different (two times higher) right
14 down from the beginning until the end of the experiment. Besides, the cell's EMF using the
15 CG bioanode, compares well with that of Godwin et al. [16], although they have used more
16 operating conditions (i.e. polarization and immobilized mediator).
17
18
19
20
21
22
23
24
25

26 Fig.6
27
28
29
30

31 **3.2. Electrochemical characteristics of MFC**
32
33

34 After closing the anode compartment (anaerobic condition), the power density was stable in
35 both MFCs. The characteristic curves of polarization and power were used to evaluate the
36 electrical performance of the cell. The polarization was obtained using different values of the
37 resistance ranging between 10 and 50 000 Ω . As shown in Fig.7, the polarization curve
38 presents three regions: voltage drop of activation (low current), Ohmic drop in electrolyte
39 (linear part) and voltage drop due to limiting phenomenon (high current).The power curve
40 yields the maximum corresponding to the highest energy that can be delivered by the MFC.
41
42
43
44
45
46
47
48
49
50

51 These results obtained with similar compost-leachate, also indicate that MFCs even
52 inoculated from the same source, can have different behaviors depending on the nature of the
53 electrode. The polarization curves of Fig.7, i.e. the power density versus current density of the
54 two MFCs (with and without modification), show a relatively large difference. Such
55 observation can explain, the discrepancies reported in the literature about the effect of the
56 polymer. It has often been observed that power density increased as the electrode was
57
58
59
60
61
62
63
64
65

1 modified with conducting polymer. In effect, in the tests using PPy-methylene blue and
2 PANI, the power densities of a similar MFC were respectively 7 mW/m² [16], and 27.3
3 mW/m² [18].
4

5 In our case, it can be clearly seen that PPy had an influence on the performance of the MFC.
6 The lowest power density i.e. 7 mW/m² was observed in unmodified MFC, whereas the
7 highest power density 25 mW/m² appeared in PPy modified MFC (corresponding to cell
8 voltage of 200 mV and current density of 150 mA/m²). These results are summarized in Table
9 1. The MFC using modified anode with PPy, had a relatively good performance for its
10 maximum power. Thus, the PPy enhanced the power output of MFC by three times
11 comparing with unmodified MFC. This relatively large difference is certainly due the
12 enhancement of electron transfer using PPy as a conducting polymer.
13
14
15
16
17
18
19
20
21
22
23

24 Fig.8

25
26
27
28 Table 1
29
30

31 **3.3. Electrochemical characteristics of bioanode**

32 Bioanodes were characterized by cyclic voltammetry after the growth the biofilm. Indeed Fig (9)
33 shows oxidation peaks at 0, 45 V. However, the peaks lying from 0-0,45 V, have small amplitudes
34 which are perhaps adsorption of the electroactive species in the lixiviat solution. But Fig (10) shows
35 voltamogram of the modified bioanode revealing larger current responses compared to the bioanode
36 CG. The increase in the electron transfer is certainly attributed to the conductive proprieties of PPy.
37
38
39
40
41
42
43
44
45
46

47 Fig.9

48
49
50
51 Fig.10
52
53
54
55
56
57
58
59
60
61
62
63
64
65

4. Conclusions

- 1- PPy regarded as conductive polymer, was used to modify the bioanode of MFC which yielded maximum power density supply (i.e. 25 mW/m²).
- 2- The bacterial species of leachate garden compost adhered well on anode and were not poisoned and influenced by the presence of PPy since the MFC gave an open circuit EMF of about 600 mV during 20 days. In effect, PPy provided a more stable biofilm on the anode and more allowance for the power the MFC.
- 3- Without using chronoamperometry for adhering biofilm on CG, a relatively high and stable value of EMF was obtained naturally by us.

Acknowledgements

The authors acknowledge financial support from the cooperation program between Algeria and France 'Tassili 14 MDU912'.

References

- [1] B. E. Logan *et al.*, Electricity-producing bacterial communities in microbial fuel cells, *Trends Microbiol*, Vol.14, N°12, (2006), pp.512-518.
- [2] J. M. Godwin *et al.*, Microbial fuel cell with a polypyrrole/poly (methylene blue) composite electrode, *Reports in Electrochemistry*, N°2, (2012), pp.3-11.
- [3] Z. He *et al.*, Application of bacterial biocathodes in microbial fuel cells. *Ectroanalysisle* , N° 19-20 ,(2006).
- [4] M.Zhou *et al.*, Microbial fuel cells and microbial electrolysis cells for the production of bioelectricity and biomaterials, *Environmental technology*, Vol.34, N° 13-14, (2013), pp. 1915-1928.
- [5] X. B. Gong *et al.*, A novel stainless steel mesh/cobalt oxide hybrid electrode for efficient catalysis of oxygen reduction,biosensors in a microbial fuel cell, *Biosensors and Bioelectronics* , Vol.55, (2014),pp237-241.
- [6] L. Jhansi *et al.* Improvement of power generation of microbial fuel cell by integrating tungsten oxide electrocatalyst with pure or mixed culture biocatalysts, *Electrochimica Acta*,Vol.199,(2016),pp154-163.
- [7] X. Xie *et al.* Design and fabrication of bioelectrodes for microbial bioelectrochemical systems, *Energy Environ. Sci*, Vol.8 (2015),pp 3418-3441.
- [8] S.Cheng *et al.* Increased performance of single-chamber microbial fuel cells using an improved cathode structure, *Electrochemistry Communications*, Vol 8(2006),pp 489-494.

- 1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
61
62
63
64
65
- [9] Y. Liu *et al*, The direct electron transfer of glucose oxidase and glucose biosensor based on carbon nanotubes/chitosan matrix, *Biosensors and Bioelectronics*, Vol.21 (2005).
- [10] S. Lee *et al* Electrochemical properties of polyaniline/carboxydextran (PANI/carDEX) composite films for biofuel cells in neutral aqueous solutions. *Biotechnology Letters* ,Vol 31,pp851-855.
- [11] H.Karami,*et al* . Investigation of pulse-electropolymerization of conductive polypyrrole nanostructures *Int. J. Electrochem. Sci.* Vol, 8 (2013),pp 8905 - 8921.
- [12] K.P.Katuri *et al*, Microbial fuel cells meet with external resistance. *Bioresour Technol.* Vol.102(3),(2011),pp2758-2766.
- [13] Polypyrrole a conducting polymer ; its synthesis,properties and application, *Russian Chemical Reviews*, Vol.66(5), (1997), pp443-457.
- [14] E.O.vilar *et al*, study of the electrical conductivity of graphite felt employed as a porous electrode ,*braz. J. Chem. Eng.* Vol. 15 n° 3 (1998)
- [15]W.Takashima. *et al*. cyclic voltammetric and electrochemomechanical characteristics of freestanding polypyrrole films in diluted media, *Thin Solid Fims*, Vol.438-439 (2003),pp339-345.
- [16] C.Li *et al*. Effect of conductive polymers coated anode on the performance of microbial fuelcells (MFCs) and its biodiversity analysis *Biosensors and Bioelectronics* ,Vol.26(2011), pp 4169–4176 .
- [17] J.Champavert *et al*. Microbial fuel cell based on Ni-tetra sulfonated phthalocyanine cathode and graphene modified bioanode ,*Journal of Electroanalytical Chemistry*, Vol .757 (2015) ,pp270–276.
- [18] B.Cercado. Testing various food-industry wastes for electricity production in microbial fuel cell, *Bioresour Technol.* Vol.101(8),(2010),pp2748-54.

Table 1: Power densities obtained with different MFCs

MFC	Bio-anode	Cathode	Separator	Power density (mW/m²)
Fuel Cell without bio-film	Carbon graphite (modified with PPy)	Platinum sheet	Nafion	~ 0
MFC1-a	Carbon graphite	Platinum sheet	Nafion	6.5
MFC-b	Carbon graphite (modified with PPy)	Platinum sheet	Nafion	25
MFC-c [Ref.2012]	Stainless steel rod modified with PPy-MB)	Carbon graphite (modified with pyrrole)	Nafion	7

Captions to Figures:

Fig.1: Cyclic voltammograms during the electropolymerization of pyrrole . vs Ag/AgCl

Fig.2. SEM images of different anodes (A)- (B) Carbone graphite, (C)-(D) modified Carbone graphite

Fig.3a: Microbial Fuel Cell before the formation of bio-film

Fig.3b: Microbial Fuel Cell after the natural formation of bio-film

Fig.4. Schematic representation of MFC

Fig.5: Amount of carbon consumed in both MFCs

Fig.6: Evolution of open circuit MFC using different electrodes

Fig.7: Current-Voltage and power curves of MFC using CG anode (without polarization).

Fig.8: Power densities of MFCs

Fig.9: Cyclic voltammetry performed with bioanode CG after operating MFC

Fig.10: Cyclic voltammetry performed with PPy-modified bioanode after operating MFC.




Fig.1




Fig.2



Fig.3a



Fig.3b




Fig.4




Fig.5




Fig.6




Fig.7




Fig.8




Fig.9





Fig.10



[Click here to access/download](#)

Supplementary Material

Polymer Bulletin-Highlights-OUIS-KAMECHE.docx

