



HAL
open science

Al-B-C ternary compounds: synthesis, structure, composition and thermal stability

B. Gardiola, Y Meynckens, R. Chiriac, F. Toche, J. Andrieux, O. Dezellus

► **To cite this version:**

B. Gardiola, Y Meynckens, R. Chiriac, F. Toche, J. Andrieux, et al.. Al-B-C ternary compounds: synthesis, structure, composition and thermal stability. CALPHAD, Jun 2017, Saint-Malo, France. hal-02322697

HAL Id: hal-02322697

<https://hal.science/hal-02322697v1>

Submitted on 21 Oct 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.


L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

The Al-B-C system

- ▶ 5 stoichiometric ternary phases
- ▶ Structures are known [Mey98]
- ▶ High temperature phase equilibria are mostly **unknown**
- ▶ **No** complete thermodynamic assessment [Wen93]

Synthesis of phases

- ▶ Growth in Al melt between 1273 and 1800 K
- ▶ Selection of compositions in dedicated triangles
- ▶ Extraction by selective acid etching
- ▶ Characterization of crystals : DRX, Raman, EDX, DTA, DSC-Cp



N.B. : each starting composition used is given with a star and the S.C. label (color code)



Isothermal section at 900 K according to [Gry04]

References

- [Mey98] Meyer F.D., Thesis, Univ. Freiburg, Germany, 1998
 [Wen93] Wen, H., Thesis, Univ. Stuttgart, Germany, 1993
 [Gry04] A. Grytsiv and P. Rogl, G. Effenberg (ed.)
 MSI Eureka in SpringerMaterials (2004)
 [Gon93] J. Gonzalez-Reyes, Thesis INSA-Lyon, France (1993)



τ_5 - Al_3BC

- ▶ 340h at 1173 K - Al_2O_3 crucible
- ▶ TGA-DSC - 10 K.min⁻¹: decomposition at 1465 ± 10 K
- (reported as in between 1273-1800 K [Gon93])





τ_3 - $Al_3B_{48}C_2$

- ▶ 1173 K - 360h - Al_2O_3 crucible
- ▶ Al - τ_3 - τ_5 at equilibrium, only τ_3 after HCl etching
- ▶ Heat capacity measured from 0 to 573 K by sapphire method



τ_4 - Al_3BC_3

- ▶ Arc melting + 1973 K - 30 min in Graphite
- ▶ Same composition in equilibrium with Al_4C_3 and with τ_1 : stoichiometric compound
- ▶ XRD and Raman spectroscopy on single crystal : structure is confirmed [Mey98]



Under progress and Future Work

- ▶ DFT calculations of ΔH_{298K}
- ▶ Heat capacity measurement on τ_4
- ▶ Synthesis and characterization of τ_1 and τ_2
- ▶ Decomposition of phases by DTA (high temperature)
- ▶ Thermodynamic optimization of the Al-B-C system