



HAL
open science

Improved Cu- and Zn-based catalysts for CO₂ hydrogenation to methanol

Djaouida Allam, Simona Bennici, Lionel Limousy, Smain Hocine

► **To cite this version:**

Djaouida Allam, Simona Bennici, Lionel Limousy, Smain Hocine. Improved Cu- and Zn-based catalysts for CO₂ hydrogenation to methanol. *Comptes Rendus. Chimie*, 2019, 22 (2-3), pp.227-237. 10.1016/j.crci.2019.01.002 . hal-02327385

HAL Id: hal-02327385

<https://hal.science/hal-02327385>

Submitted on 22 Oct 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial 4.0 International License

Improved Cu,Zn-based catalysts for CO₂ hydrogenation to methanol

Catalyseurs améliorés à base de Cu et Zn pour l'hydrogénation de CO₂ en méthanol

DjaouidaAllam¹, Simona Bennici^{2,3,*}, Lionel Limousy^{2,3}, and Smain Hocine¹

¹Laboratoire de Chimie Appliquée et de Génie Chimique Université M. Mammeri de Tizi-Ouzou BP .17 R.P 15000 Tizi-Ouzou, Algeria.

²Université de Haute-alsace, CNRS, IS2M UMR 7361, F-68100 Mulhouse, France

³Université de Strasbourg, France

Résumé

Dans cette étude, des catalyseurs binaires et ternaires (CuO-CeO₂, ZnO-CeO₂, CuO-ZnO-CeO₂ et CuO-ZnO-Al₂O₃) ont été utilisés pour l'hydrogénation CO₂ en méthanol à pression atmosphérique. L'influence de la dispersion des métaux, de la formation de spinelles et des propriétés de surface sur les performances catalytiques ont été étudiées.

Les catalyseurs, préparés par la méthode polyol en utilisant du polyéthylène glycol en tant que solvant, présentent des propriétés améliorées en termes de dispersion des oxydes métalliques, de morphologie (forme de type éponge pour les catalyseurs contenant CeO₂) et de variétés d'espèces métalliques et d'oxydes métalliques à la surface. De plus, les catalyseurs CuO-ZnO-CeO₂ et Cu-ZnO-Al₂O₃ présentent une activité et une sélectivité supérieures à celles de catalyseurs préparés par des procédés plus conventionnels, pour la synthèse du méthanol par hydrogénation de CO₂.

Abstract

In this work the influence of the metal dispersion, the spinel formation, and the surface properties of binary and ternary catalysts (CuO-CeO₂, ZnO-CeO₂, CuO-ZnO-CeO₂ and CuO-ZnO-Al₂O₃) was evaluated. The catalysts, prepared by polyol method using polyethylene glycol as a solvent, have been tested in the CO₂ hydrogenation to methanol performed at atmospheric pressure.

The catalysts prepared by polyol method presented improved properties in terms of metal oxide dispersion, morphology (i.e. sponge like shape for the CeO₂-containing catalysts), and a large variety of metal and metal oxide species on the surface. Moreover, the CuO-ZnO-CeO₂ and CuO-ZnO-Al₂O₃ catalysts exhibited a higher activity and selectivity in the methanol synthesis by CO₂ hydrogenation than those displayed by catalysts prepared by more conventional methods.

Keywords: CO₂ valorization; polyol synthesis; methanol synthesis; oxide catalysts

1. Introduction

The concentration of carbon dioxide (a greenhouse gas) inexorably increases in the atmosphere. Various methods are currently examined to decrease the CO₂ concentration or to convert it into valuable chemical products. The utilization of CO₂ as a feedstock for the synthesis of high added value chemicals is a promising alternative for CO₂ abatement [1,2]. The simplest way to utilize carbon dioxide is the hydrogenation into valuable compounds, such as methanol (MeOH) and DME (dimethyl ether) [3-8]. Such conversion is often performed on copper-based catalysts. Industrial methanol synthesis is performed by catalytic hydrogenation of syngas (H₂/CO/CO₂) over Cu/ZnO/Al₂O₃-type catalyst. Unfortunately, the industrial Cu/ZnO/Al₂O₃ catalyst are not active nor selective in CO₂ hydrogenation. Previous

published research works demonstrated that the use of industrial catalysts brings to very low hydrogenation conversions of CO₂ to methanol [9].

This issue can be overcome by developing suitable catalysts, which can effectively convert carbon dioxide to methanol [10-13]. Even if copper based materials are promising catalysts for the hydrogenation of CO₂ [14-19], further investigations are required for developing new catalytic materials able to give high conversion of CO₂ and improved selectivity to MeOH.

In order to improve the catalytic performance for methanol synthesis from H₂/CO₂ feeding gas, CuO/ZnO catalysts have been widely modified by adding various activators or other metals (Zr, Si, La, Ti, Cr, Ga, Ce, Fe, Nb, Pd...) [20-25]. The effect of the support was also extensively studied. The type of support affects both CO₂ conversion and methanol selectivity, and, in general, basic oxides such as La₂O₃, Sm₂O₃, Nb₂O₅, In₂O₃ and ThO₂ [26-27], used as supports, favor the methanol formation. The preparation methods have also a considerable influence on the catalytic performance [28-30]. Several methods such as co-precipitation [31-35], impregnation [36-38], and sol-gel [38-39] have been developed to prepare copper-based oxide catalysts. Moreover, the co-precipitation synthesis was improved by addition of reducing agents, such as chitosane [14], and NaBH₄ [15]. Surfactant-assisted co-precipitation [16], solvent-free routine combustion [40], and micro-fluidic co-precipitation [41] are novel synthesis methods that allow obtaining a good repeatability of the synthesis, and an improved homogeneity of the phases present in the catalyst. Other methods, such as impregnation and sol-gel, can also produce catalysts with large specific surface areas and high CuO dispersion [42]. Polyol synthesis represents a good alternative to the classical synthesis methods. In particular, it presents many advantages, such as the possibility to precisely modulate the stoichiometric ratio, the homogeneous mixing of the various components, the low cost and the short reaction time. Therefore, polyol synthesis reveals to be an attractive technique for the synthesis of nano-oxide powders.

CuO/ZnO/Al₂O₃-type catalysts obtained by polyol synthesis have been successfully applied in the Reverse Water Gas Shift Reaction RWGS [43], in the alcohol-assisted low temperature methanol synthesis from syngas [44], and in methanol reforming [45].

The polyol method [46-47] permits to synthesize nano-sized metallic powders with uniform size distribution and shape [46-48]. In recent years, the polyol method has been studied by many researchers [49-52]. These investigations showed that the crystallites' size and shape [46] can be controlled by varying the reduction temperature, the pH, and the nucleation-protective agent concentration [49-53]. Up to now, and at our knowledge, no attempts to prepare Cu/ZnO catalyst for methanol production using the polyol method have been done. In a typical polyol synthesis, polyols (ethylene glycol, diethylene glycol, glycerol, and tetraethylene glycol) act at the same time as the reaction medium and as the reducing agent. The metal precursor is reduced through a redox reaction between the metal precursors and the polyolic species. Therefore, the reaction temperature is an important parameter, because the oxidation potential of polyol chemicals decreases with the increasing of the reaction temperature [49, 54-55]. Nucleation-protective chemicals such as polyvinylpyrrolidone (PVP) are occasionally employed to prevent sintering and agglomeration of metal particles [54-55]. The various published researches indicate that the choice of the preparation conditions strongly affects the activity of catalysts prepared by polyol method.

In the present work, the so-called "polyol method" has been used to obtain improved catalytic materials for the hydrogenation reaction of CO₂ to methanol. The influence of the metal dispersion, spinel formation and surface properties of binary and ternary catalysts (CuO-CeO₂, -ZnO-CeO₂, CuO-ZnO-CeO₂ and CuO-ZnO-Al₂O₃), prepared by polyol method using polyethylene glycol as solvent, is evaluated in the CO₂ hydrogenation to methanol at atmospheric pressure, used as test reaction.

2. Experimental

2.1. Preparation of binary and ternary polyol catalysts

Two binary catalysts (labeled ZnO-CeO₂, and CuO-CeO₂, with molar ratio of Zn/Ce and Cu/Ce equal to 1) and two ternary catalysts (labeled CuO-ZnO-CeO₂, and CuO-ZnO-Al₂O₃, with Cu/Zn/Ce and Cu/Zn/Al molar ratios of 1/1/2) were prepared by polyol method. The reaction temperature and the choice of the solvent were selected referring to the available investigations reported in the literature [44, 45]. These experimental conditions seem to favor the formation of nanocrystallites. Differently from the synthesis reported in these already published works, nitrate-base precursors were used in the present research instead of Me-acetates. In fact, nitrates do not participate to secondary reactions like those operated by acetates that can react to form methyl acetate and ethyl acetate. Firstly, copper nitrate Cu(NO₃)₂·2.5H₂O (Sigma-Aldrich 98%), and/or zinc nitrate Zn(NO₃)₂·6H₂O (Sigma-Aldrich 99%) were dissolved in polyethylene glycol (C₂H₆O₂)_n (Sigma-Aldrich 99%, d=1.13g/ml). The solution at pH=2 was then heated up, step by step, and kept under stirring for 1 hour at 70°C, 2h at 120°C, and 2h at 180°C. Cerium and/or aluminum nitrates (Ce(NO₃)₃·6H₂O and/or Al(NO₃)₃·9H₂O from (Sigma-Aldrich 99%) were then added to the initial solution under vigorously stirring for 4 hours at the same temperature (180°C). The formation of a precipitate was observed. The suspension was cooled down at 100°C, and NH₄OH was added dropwise to reach a pH of 7. The resulting suspensions were kept under vigorous stirring at 100°C for 24 h. Finally, the formed gel was dried at 180°C for 72 h, and then calcined in air at 450°C for 5h.

2.2. Characterization techniques

Thermogravimetric analyses (TGA) were performed with a TGA/DSC 1 LF 1100 STARS system from METTER TOLEDO. The samples were heated-up at 5°C/min under air flow (100 mL/min) from room temperature to 500°C.

The XRD patterns were acquired with a PANalytical MPD X'Pert Pro diffractometer operating with Cu K α radiation, $\lambda = 0.15406$ nm at 40 mA and 45 kV with a scan rate of 2° min⁻¹. The data were collected in the 5-60° 2 θ range. The diffraction patterns were analyzed using the Joint Committee on Powder Diffraction Standard (JCPDS). CuO, ZnO, and CeO₂ crystallite size were calculated by means of the Scherrer equation:

$$d = \frac{0.89 \lambda}{\beta \cos \theta} * \frac{180}{\pi} \quad (1)$$

where d is the diameter of the crystallite, λ the X-ray wave length, and β is the width at half height (FWHM) of the peak.

N₂-adsorption isotherms of the samples were acquired at -196°C in a Micromeritics ASAP2420 apparatus. 0.25 g of catalyst was pretreated at 300°C during 10 h under vacuum (~50 m Torr). The specific surface area was calculated applying the multi-Pont BET method [56], while the pore size distribution was obtained by applying the BJH method [57] to the desorption branch of the isotherm.

Scanning electron microscopy coupled to energy dispersive X-ray spectroscopy (SEM-EDX) was performed on a PHILIPS XL 30 instrument (electrons acceleration voltage of 15 kV).

X-ray photoelectron spectroscopy (XPS) measurements were performed on a Kratos Axis Ultra DLD spectrometer equipped with a monochromatic micro focused Al K α (1486.6 eV and Mg K α =1253.6 eV) X-ray exciting source. The pass energy of the analyzer was set at 40 eV. The adventitious C1s peak (284.6 eV) was used as internal reference with an accuracy of ± 0.3 eV. XPS was used to evaluate the oxidation state of copper, zinc and cerium species. O 1s, Cu 2p, Zn 2p, Ce 3d and Al 2p species were quantified by analysis of the survey XPS

spectra. The binding energy of C 1s, O 1s, Cu 2p, Zn 2p Ce 3d, and Al 2p were analyzed in order to identify the associated surface species and the relative atomic concentration.

2.3 Catalytic tests

The catalytic hydrogenation of carbon dioxide to methanol was evaluated in a fixed-bed continuous flow reactor. During each test, 0.3 g of catalyst was pretreated with hydrogen at 300°C for 3 hours. After the reduction step, the catalyst was exposed to a H₂/CO₂ (1/9 volume ratio) flow at different reaction temperatures (190-240°C). The feeding mixture and the reaction products were analyzed online with a gas chromatograph (Shimadzu GC-2014) equipped with FID and TCD detectors. CO₂ conversion (X) and products' selectivity were calculated as follows, using the quantitative correction factor kf, and peaks area (S) for the different species:

$$X_{CO_2}(\%) = \frac{S_{CO_2 in} - S_{CO_2 out}}{S_{CO_2 in}} \times 100 \times kf_{CO_2} \quad (2)$$

$$CH_3OH \text{ selectivity } (\%) = \frac{S_{CH_3OH out}}{X_{CO_2}} \times 100 \times kf_{CH_3OH} \quad (3)$$

$$CH_4 \text{ selectivity } (\%) = \frac{S_{CH_4 out}}{X_{CO_2}} \times 100 \times kf_{CH_4} \quad (4)$$

3. Results and discussions

3.1. Characterization of catalysts

3.1.1. Thermal behavior

The catalysts thermal behavior, before and after calcinations, is shown in Fig.1. The samples mass continuously decreased with the temperature. For the catalysts before calcination, the TGA curves showed three main events connected to the residual precursors decomposition (Fig.1a) (indeed, the most part of the precursors has been eliminated by the thermal treatment during the synthesis).

A first mass variation in the 0.5- 2.5% range was observed up to 250 °C, and was attributed to the loss of water (physi- and chemi-sorbed) as well as to the decomposition of residual nitrates from the precursors. The second and highest mass loss (0.5-3%), between 250 and 350°C, was probably related to the elimination of polyethylene glycol. The third step, at temperature higher than 350°C, corresponded to the lowest mass loss (0.5%), and was attributed to the decomposition of hydroxyl groups, leading to metal oxide formation. After calcinations (Fig. 1b), the catalyst showed a low mass loss (below 2%), attributed to the release of physisorbed water (under 150 °C), and the decomposition of carbonates formed by reaction with atmospheric CO₂. The presence of carbonates was observed also by XPS (as described in section 3.1.3).

3.1.2. Structure and morphology of the catalysts

The X-ray diffractograms of the calcined bimetallic and trimetallic catalysts are displayed in Fig.2. For the three calcined catalysts, CuO-CeO₂, ZnO-CeO₂, and CuO-ZnO-CeO₂, only the diffraction peaks relative to the CuO, ZnO, and CeO₂ phases could be clearly identified. The diffraction peaks centered at 28.6, 33.1, 47.5, 56.3, 59.1 and 69.0° 2θ, corresponding respectively to the (111), (200), (220), (311), (222) and (400) diffraction planes of cubic CeO₂ [58-59], were observed for the ZnO-CeO₂, CuO-CeO₂, and CuO-ZnO-CeO₂ catalysts. For the ZnO-CeO₂ and CuO-ZnO-CeO₂ samples, diffractions at 31.7, 34.5, 36.2, 62.9 and 69.0° 2θ indicated the presence of hexagonal ZnO [31,58,60-61] and corresponded respectively to the (100), (002), (101), (103) and (201) planes. The cubic CuO phase [31,58,60], present in the CuO-CeO₂ and CuO-ZnO-CeO₂ samples, was characterized by broad diffraction lines at 35.5 and 38.7° 2θ corresponding to the (-111) and (111) planes. Broad diffraction lines at 2θ = 35.5 38.7, 61.5 and 68.1° indicated the presence of CuO and corresponds respectively to the (-111), (111), (-202), (-113) and (-220) planes. In addition to CuO, CuAl₂O₄ and ZnAl₂O₄ spinel could be identified in the CuO-ZnO-Al₂O₃ sample. The

diffraction peak of CuAl_2O_4 and ZnAl_2O_4 were superposed and placed at 31.2, 36.8, 55.6, 59.3, and $65.2^\circ 2\theta$. No diffraction peaks relative to ZnO could be identified in CuO-ZnO- Al_2O_3 ; all zinc was present as spinel, $\text{CuZnAl}_2\text{O}_4$.

The metal oxide crystallite dimensions were evaluated applying the Scherrer equation to the main diffraction peak of each phase, and the results are reported in Table 1. ZnO crystallites size of 20-30 nm was calculated in the binary ZnO- CeO_2 catalyst. CuO crystallites, in the 10-20 nm dimension range, were detected for the CuO- CeO_2 catalyst (Table 2). The CuO (6 nm) and ZnO (12 nm) crystallites were much smaller for the ternary CuO-ZnO- CeO_2 sample, indicating that the presence of zinc and copper oxides together ameliorate the oxides distribution and dispersion during the synthesis procedure.

The nitrogen adsorption-desorption isotherms of the various polyol samples (acquired at -196°C) are shown in Fig.3a. The catalysts isotherm shows a continuous increase of adsorbed nitrogen over the whole P/P_0 range, with a relatively steep increase at $P/P_0 \geq 0.85$. For the all catalysts, the N_2 adsorption isotherms (Fig.3b) were of type (II) [62] with no plateau at high P/P_0 values, which is usually observed for materials with macropores or interparticular mesoporosity [63]. H4-type hysteresis was observed for the CuO-ZnO- Al_2O_3 sample, and H3-type for the ZnO- CeO_2 , CuO- CeO_2 , and CuO-ZnO- CeO_2 samples [64]. These types of hysteresis are typical of lamellar compounds or slit-shaped pores [65].

All materials presented relatively low porous volumes (Table 1, 3th column), as expected for this kind of preparation that produces bulk oxides. Fig. 3b represents the pore size distribution of the catalysts. All catalysts presented a certain mesoporosity centered in the 17-23 nm range. The presence of macropores (up to 150 nm) was observed for the three samples containing CeO_2 , while even larger pores were present in the CuO-ZnO- Al_2O_3 sample.

The presence of copper oxide seems to improve the specific surface area of the catalysts (in the 30-38 $\text{m}^2\cdot\text{g}^{-1}$ range), as reported in Table 1. The catalyst with the lower surface area (18

$\text{m}^2 \cdot \text{g}^{-1}$) was ZnO-CeO₂. This behavior is probably connected to the improved pore volume that can be obtained in the presence of the copper precursor, that end up into a higher internal surface area. Indeed, ZnO-CeO₂ presented the lowest pore volume, and the hysteresis between the adsorption and desorption isotherms was almost absent.

Table 1: morphological and structural properties of the catalysts

Sample	S_{BET} ($\text{m}^2 \cdot \text{g}^{-1}$)	V_{pore}^b ($\text{cm}^3 \cdot \text{g}^{-1}$)	D_{pore} (nm)	Crystallite size with XRD analysis (nm) ^b			
				CuO	ZnO	CeO ₂	Cu,ZnAl ₂ O ₄
CuO-CeO ₂	32	0.07	17	10-20	-	5	-
ZnO-CeO ₂	18	0.03	20	-	20-30	5	-
CuO-ZnO-CeO ₂	38	0.12	22	6	12	5	NA
CuO-ZnO-Al ₂ O ₃	30	0.04	23	20-30	-	-	30-40

^a Determined from desorption branch of N₂ adsorption isotherm by BJH model

^b Crystallite size calculated by Scherrer equation

The morphology of the different calcined CuO-CeO₂, ZnO-CeO₂, CuO-ZnO-CeO₂, CuO-ZnO-Al₂O₃ samples was investigated by scanning electron microscopy, and the acquired images are presented in Fig.4. The catalysts containing CeO₂ showed a sponge-like morphology, as reported in Fig.4 for the CuO-CeO₂ (a-c), ZnO-CeO₂ (d-f), and CuO-ZnO-CeO₂ (g-i) samples. The three ceria-containing samples were characterized by the presence of round-shaped cavities and pores of various dimensions, well distributed in the sample catalyst structure. CuO-ZnO-Al₂O₃ presented a different morphology (Fig.4 j-l), with well-developed and thin plate-shaped bonded sheets in the 1 to 5 μm dimension interval. The presence of macropores was confirmed by these images and linked to the formation of gas bubbles during the preparation step, due to the decomposition of the metal oxide precursors.

EDX analysis showed a very homogeneous distribution of the different oxides in all samples.

3.1.3. Chemical composition and surface properties

Photoelectron spectroscopy was used to evaluate the oxidation state of copper, zinc and cerium species in the CuO-ZnO-CeO₂ and CuO-ZnO-Al₂O₃ calcined catalysts, as well as to evaluate their surface chemical composition (Tables 2). All elements (Cu, Zn, Ce, Al, and O) were present at the samples' surface (Table 2). The survey XPS acquisition permitted to quantify the various atoms (O 1s, Cu 2p, Zn 2p, Ce 3d and Al 2p) for the two trimetallic catalysts. Clear differences in the surface elements were observed for the two samples. Zn concentration was particularly low on the surface of the CuO-ZnO-CeO₂ sample (0.53 %). At the contrary a big amount of carbon was detected on its surface (24.31 %). Because the most part of carbon on the surface of CuO-ZnO-CeO₂ could be assigned to residual contamination or hydrocarbon chains, as described later in this section, these results can suggest that the carbon pollution presented a higher affinity for Zn, thus selectively covered at the extreme surface. Less dramatic differences were identified in the CuO-ZnO-Al₂O₃ sample that showed similar concentrations of copper and zinc on the surface.

No N1s XPS peak (generally placed around 400.3 eV), related to nitrate (NO₃⁻) species (salt precursors) has been identified for the CuO-ZnO-Al₂O₃ and CuO-ZnO-CeO₂ catalysts, as an indication of the complete decomposition of nitrated after calcination.

The binding energy of C 1s, O 1s, Cu 2p, Zn 2p Ce 3d, and Al 2p of the two trimetallic catalysts are listed in Table 2, as well as the associated surface species and their atomic concentration.

The Cu 2p spectrum of both CuO-ZnO-CeO₂ and CuO-ZnO-Al₂O₃ (Fig.5) catalysts presented the characteristic spin-orbit split Cu 2p_{1/2} and Cu 2p_{3/2} peaks, with their shake-up satellites of Cu²⁺ [66]. Binding energies, in the 932.0-932.8 and 933.2-934.6 eV range, are characteristic of Cu⁺ and Cu²⁺, respectively [67-68]. These two contributions could be identified in the CuO-ZnO-CeO₂ sample (upper spectrum in Fig.5). The large and strong peak centered at 932.7 eV was then attributed to Cu²⁺ and/or Cu⁺ species, while the small and broad peak

centered at 934.9 eV was assigned to Cu^{2+} species [69]. For the $\text{CuO-ZnO-Al}_2\text{O}_3$ sample (Fig.5), the $\text{Cu } 2p_{3/2}$ peak presented two contributions characteristic of Cu^{2+} species; the first one was observed at 933.61 eV and related to copper oxide, while a second contribution, at a higher binding energy (935.66 eV), was assigned to Cu^{2+} in the CuAl_2O_4 -like environment (the presence of the spinel structure, CuAl_2O_4 , was also observed by XRD analysis). Indeed, the shift to higher binding energy is indicative of a charge transfer from Cu^{2+} towards $\text{Al}_2\text{O}_4^{2-}$ [70-71]. The intensity ratio of the satellite peak to the related main peak ($I_{\text{sat}}/I_{\text{pp}}$) was of 0.17, for the CuO-ZnO-CeO_2 catalyst, and of 0.44 for $\text{CuO-ZnO-Al}_2\text{O}_3$. The lower $I_{\text{sat}}/I_{\text{pp}}$ value is characteristic of well dispersed copper oxide species in an octahedral coordination environment, while the higher value is symptomatic of a coordination change, most probably due to the formation of the spinel [72]. In addition, the contribution at around 529 eV of the O 1s spectra can also be assigned to the presence of Cu^{2+} and Cu^+ (see Table 2).

Table 2: Surface elements' presence as determined by XPS analysis

Orbital	CuO-ZnO-CeO ₂			CuO-ZnO-Al ₂ O ₃		
	B.E. (eV)	Species	At (%)	B.E. (eV)	Species	At (%)
C 1s	284.98	C-C	16.54	285.01	C-C	2.46
	286.53	C-OR	0.60	286.56	C-OR	0.28
	287.98	C=O	2.55	288.01	C=O	0.40
	289.48	O=C-O	4.62	289.47	O=C-O	0.89
O 1s	529.49	Cu-O	6.97	529.80	Cu-O	9.02
	529.43	Ce ⁴⁺ /Cu-O	29.07	531.71	Al-O	33.22
	530.90	Ce ³⁺ /Zn-O	4.17	530.80	Zn-O	8.51
	531.90	(CO ₃) ²⁻	7.04	531.40	(CO ₃) ²⁻	2.64
Cu 2p	932.75	Cu ²⁺ /Cu ⁺	5.87	933.61	Cu ²⁺	4.31
	934.91	Cu ²⁺ /Cu ⁺	0.97	935.66	Cu ²⁺	1.42
	940.92	Cu ²⁺ /Cu ⁺	0.99	940.87	Cu ²⁺	1.68
	943.54	Cu ²⁺ /Cu ⁺	0.78	943.43	Cu ²⁺	1.65
Zn 2p	1021.56	ZnO	0.53	1021.87	ZnO	7.71
Ce 3d	881.00 (V ⁰)	Ce ³⁺	0.92	-	-	-
	899.39 (U ⁰)					
	882.44 (V)	Ce ⁴⁺	4.42	-	-	-
	900.76 (U)					
	884.95 (V ^I)	Ce ³⁺	3.80	-	-	-
	903.20 (U ^I)					
	888.70 (V ^{II})	Ce ⁴⁺	5.33	-	-	-
	907.36 (U ^{II})					
898.16 (V ^{III})	Ce ⁴⁺	4.82	-	-	-	

916.34 (U ^{III})						
Al 2p	-	-	-	74.47	Al ³⁺	24.86

The Zn 2p_{3/2} XPS spectra for the two trimetallic catalysts was characterized by one defined peak around 1021-1022eV that could be assigned to Zn²⁺ species. The presence of ZnO have been also confirmed by the O 1s band centered at 530.8 eV [73-74]. The XPS signal of CuO-ZnO-CeO₂ was much less intense than that of CuO-ZnO-Al₂O₃, indicating the higher ZnO concentration on the CuO-ZnO-Al₂O₃ surface (8.68 %_{atom} for CuO-ZnO-Al₂O₃ and 0.53 %_{atom} for CuO-ZnO-CeO₂ catalysts).

The presence of carbon was detected on the surface of both samples. The C 1s spectra is reported in Fig.6, for the CuO-ZnO-CeO₂ and CuO-ZnO-Al₂O₃ catalysts. In both cases the spectra were composed of two contributions; the first, centered at 289.5 eV was assigned to carbonate species, while the more intense band, at around 285 eV, to residual contamination or hydrocarbon chains, probably deriving from the polyethylene glycol used during the catalyst synthesis. Indeed, cerium oxide and reduced cerium are known to react with CO₂ (present in the atmosphere, for example), and give rise to carbonate species on the surface [75]. The carbonate band was much less intense for the CuO-ZnO-Al₂O₃ catalyst, and the corresponding atomic percentage was about 1.3% instead of 7.2 % for the CuO-ZnO-CeO₂ catalyst. The presence of carbonates was also confirmed by the O 1s XPS band centered at high binding energy (531.9 eV and 531.4 eV, respectively for CuO-ZnO-CeO₂ (Fig. 7a) and CuO-ZnO-Al₂O₃ (Fig. 7b).

The XPS spectrum of Ce 3d for the CuO-ZnO-CeO₂ sample is depicted in Fig.8 and presents a complex behavior. The split of the band into numerous peak is due to the hybridization between the final state Ce 4f orbitals and the O 2p oxygen orbital [76]. In Fig.8 the peaks are identified by V and U labels, indicating respectively the spin orbit coupling 3d^{3/2} and 3d^{5/2} [77], by applying the convention introduced by Burroughs et al. [78] in 1976.

Ce3d spectrum can be decomposed in 5 doublets, (U''', V'''), (U'', V''), (U', V'), (U°, V°), and (U,V), corresponding to the emissions from the spin-orbit split $3d^{3/2}$ and $3d^{5/2}$ core levels [77-79]. The five doublets were assigned to different final states of tetravalent (Ce^{4+}) or trivalent (Ce^{3+}) in Ce compounds (see Table 3); U''' (916.6 eV) and V''' (898.2 eV) were due to a Ce $3d^9 4f^0 O_2 p^6$ final state, U'' (907.4 eV) and V'' (888.8 eV) to a Ce $3d^9 4f^1 O_2 p^5$ final state, U' (903.2 eV) and V' (884.9 eV) to a Ce $3d^9 4f^1 O_2 p^6$ final state, U° (899.3 eV) and V° (881.0 eV) to a Ce $3d^9 4f^2 O_2 p^5$ final state, and U (900.8 eV) and V (882.4 eV) to a Ce $3d^9 4f^2 O_2 p^4$ final state. Especially the well-defined U''' peak at 916.6 eV was characteristic of the presence of Ce^{4+} [77].

3.2. Catalytic tests

In order to verify the catalytic performances of the binary and ternary polyol catalysts in relation to the chemical composition, oxide structure and surface properties, CO_2 hydrogenation to methanol was used as test reaction. The tests were carried-out at atmospheric pressure by feeding the tubular reactor with a $H_2/CO_2 = 1/9$ mixture. Methanol and methane were the main carbon containing products, while only traces of carbon monoxide were detected.

The activity of the four catalysts was compared at 240 °C (Fig.9). The binary catalysts, CuO-CeO₂ and ZnO-CeO₂, did not show any catalytic activity (CO_2 conversion below 2%). The ternary CuO-ZnO-CeO₂ and Cu-ZnO-Al₂O₃ catalysts showed similar conversion curves as a function of time, with stabilization of their activity after 4h reaction. The CuO-ZnO-CeO₂ catalyst showed the best result with a maximum conversion of about 20%, while Cu-ZnO-Al₂O₃ reached a conversion not exceeding 14%. The enhanced activity of the ternary catalysts is attributed to the synergistic effect between CuO and ZnO, as already known from the literature [80-82]. The higher activity of the CuO-ZnO-CeO₂ catalyst can be attributed to both the basicity of CeO₂ [83], which favors the adsorption of CO_2 (that is an acid molecule), and

the enhanced reducibility of the system, leading to the increase of the number of active sites after the reducing pretreatment operated in-situ, before the reaction tests. Moreover, in the Cu-ZnO-Al₂O₃ catalyst, copper and zinc oxides were not fully available due to the formation of the CuAl₂O₄ and ZnAl₂O₄ spinels, as shown by XRD. Indeed, zinc and copper trapped into the spinel cannot enter in intimate contact and their synergistic catalytic effect [81-83] cannot be deployed.

On the most active catalyst (CuO-ZnO-CeO₂), further tests, at different reaction temperature, were performed. The CO₂ conversion as a function of time is plotted in Fig.10a for the tests performed in the 190-240 °C temperature range. At the beginning the curves presented an activation step, characterized by a steep section of the conversion curve; after 1 h reaction, the change of slope indicated that the stationary state is going to be reached up (maximum CO₂ conversion). A slightly different behavior was observed for the test performed at 240 °C in which the approach to the maximum conversion was slower and characterized by a change in slope. By increasing the temperature, the selectivity to CH₄ increased, while the methanol selectivity decreased simultaneously (Fig. 10b). Methanol selectivity was favored at low temperature; MeOH is indeed unstable at high temperature and is transformed into CH₄ and H₂O (in presence of hydrogen) through the following successive reactions:



This transformation explains also the change in slope of the CO₂ conversion curve in Fig. 10a; at first the slope of the 240 °C curve followed that of the curves at lower temperature, while when the transformation to CH₄ started, the slope decreased and the rate for reaching the stationary state slowed-down.

4. Conclusions

The catalysts prepared by the polyol method, and reported in the present research, presented improved properties in terms of metal oxide dispersion, and morphology (i.e. sponge like shape for the CeO₂-containing catalysts), and a variety of the metal and metal oxide species on the surface. Moreover, the CuO-ZnO-CeO₂ and Cu-ZnO-Al₂O₃ catalysts exhibited a higher activity and selectivity in the methanol synthesis by CO₂ hydrogenation than those displayed by catalysts prepared by more conventional methods, as summarized in Table 3. The results obtained for the catalysts prepared in the present work are also reported for comparison.

Table 3: catalytic performances in the hydrogenation of CO₂, obtained on the catalysts prepared

Type of catalyst	Preparation method	T (°C)	P (MPa)	R (H ₂ /CO ₂)	CO ₂ conversion (%)	CH ₃ OH Selectivity (%)	Ref.
CuO-ZnO-Al ₂ O ₃	Polyol method	240	0.1	9.0	14	86	this work
CuO-ZnO-CeO ₂	Polyol method	240	0.1	9.0	20	90	
CuO/ZnO/Al ₂ O ₃	Solvent free routine	240	3.0	3.0	16	64	[40]
CuO/ZnO/ZrO ₂	Surfactant co-precipitation method	240	3.0	3.0	12	33	[16]
CuO-ZnO-ZrO ₂ (M)	Co-precipitation microfluidic	240	5.0	3.0	9	47	[41]
CuO-ZnO-ZrO ₂ (pH)	Co-precipitation at controlled pH				14	50	
CZZ0					17	67	
CZZ3	Precipitation/reduction method (NaBH ₄)	230	5.0	3.0	15	62	[15]
CZZ5					15	67	
Cu/ZnO	Co-precipitation	240	3.0	3.0	17	78	[84]
10Cu-/CeO ₂					4	66	
0.5Pd-10Cu/CeO ₂	Coprecipitation + impregnation	230	3.0	3.0	6	49	[85]
2Pd-10Cu/CeO ₂					15	29	
CuO-ZnO-TiO ₂ -ZrO ₂	Co-precipitation (oxalate)	240	3.0	3.0	17	44	[61]
Cu/ZnO	Impregnation	240	0.1	9.0	5	12	[42]
Cu-Zn/SiO ₂	Impregnation	250	2.0	3.0	2	66	[1]
5%CuZn/rGo					14	3	
10%CuZn/rGo	Incipient wetness impregnation	250	1.5	3.0	26	5	[19]
20%CuZn/rGo					19	9	
CuO/ZnO/Al ₂ O ₃ (Cp)	With Internal cooling water	240	3.0	3.0	52	69	[86]
CuO/ZnO/Al ₂ O ₃ (Cp)	Without Internal cooling water						
Cu/ZrO ₂ +CaO	Wetness impregnation	250	0.1	3.0	3	1	[87]

The most part of the catalysts listed in Table 3 presented CO₂ conversion lower than 20 % and selectivity to methanol lower than 65%, even when the reaction was performed at relatively high pressure (1.5-5.0 MPa), a more favorable condition than that used in the present research. It is worth to notice that on catalysts prepared by impregnation [42], the reaction performed at atmospheric pressure, and with a H₂/CO₂ ratio of 9, allowed to obtain only 12% conversion and 70% selectivity to methanol at 240°C, confirming that polyol method is promising for the preparation of active catalysts for CO₂ hydrogenation (20% CO₂ conversion and 90% selectivity to MeOH).

Acknowledgements

All physico-chemical characterizations were performed by the technical platforms of IS2M. The authors are very grateful to S. Hajjar, L. Josien, L. Michelin, H. Nouali for their contribution.

References

- [1] N. Yang, R. Wang, Sustainable technologies for the reclamation of greenhouse gas CO₂, *J. Cleaner. Produc.* 103 (2015) 784-792.
- [2] I. Melian-Cabrera, M.L. Granados, J.L.G. Fierro, Pd-modified Cu–Zn catalysts for methanol synthesis from CO₂/H₂ mixtures: catalytic structures and performance, *J. Catal.* 210 (2002) 285-294.
- [3] M. Matzen, Y. Demirel, Methanol and dimethyl ether from renewable hydrogen and carbon dioxide: Alternative fuels production and life-cycle assessment, *J. Cleaner Produc.* 139 (2016) 1068-1077.
- [4] M.J. Bos, D.W.F. Brilman, A novel condensation reactor for efficient CO₂ to methanol conversion for storage of renewable electric energy, *Chem. Eng. J.* 278 (2015) 527-532.
- [5] W. Wang, S. Wang, X. Ma, J. Gong, Recent advances in catalytic hydrogenation of carbon dioxide, *Chem. Soc. Rev.* 40 (2011) 3703-3727.
- [6] T. Witoon, T. Permsirivanich, N. Kanjanasontorn, C. Akkaraphataworn, A. Seubsai, K. Faungnawakij, C. Warakulwit, M. Chareonpanich, J. Limtrakul, Direct synthesis of dimethyl ether from CO₂ hydrogenation over Cu-ZnO-ZrO₂/SO₄²⁻ ZrO₂ hybrid catalyst: effects of sulfur-to-zirconia ratios, *Catal. Sci. Technol.* 5 (2015) 2347-2357.

- [7] G. A. Olah, A. Goepfert, G. S. Prakash, Chemical recycling of carbon dioxide to methanol and dimethyl ether: from greenhouse gas to renewable, environmentally carbon neutral fuels and synthetic hydrocarbons, *J. Org. Chem.* 74 (2008) 487-498.
- [8] K.C. Waugh, Methanol synthesis, *Catal.Lett.* 142 (2012) 1153-1166.
- [9] J.B. Hansen, P.E Højlund Nielsen, Methanol synthesis, *Handbook of heterogeneous catalysis* (2008).
- [10] H. Arakawa, J.L. Dubois, K. Sayama, Selective conversion of CO₂ to methanol by catalytic hydrogenation over promoted copper catalyst, *Energy. Convers. Mgmt.* 33 (1992) 521-528.
- [11] M. Saito, T. Fujitani, I. Takahara, T. Watanabe, M. Takeuchi, Y. Kanai, K. Moriya, T. Kakumoto, Development of Cu/ZnO-based high performance catalysts for methanol synthesis by CO₂ hydrogenation, *Energy. Convers. Mgmt.* 36 (1995) 577-580.
- [12] K-W. Jun, W-J. Shen, K-W. Lee, T. Inui, H. Hara, T. Takeguchi, J.B. Kim, Concurrent Production of Methanol and Dimethyl Ether from Carbon Dioxide Hydrogenation: Investigation of Reaction Conditions, *Kor. Chem. Soc.* 20 (1999) 993-998.
- [13] K.Ushikoshi, K. Mori, T. Watanabe, M. Takeuchi, M. Saito, A 50 kg/day class test plant for methanol synthesis from CO₂ and H₂, *Stud. Surf. Sci. Catal.* 114 (1998) 357-362.
- [14] T. Witoon, T. Permsirivanich., W. Donphai, A. Jaree, M. Chareonpanich. CO₂ hydrogenation to methanol over Cu/ZnO nano catalysts prepared via a chitosan-assisted co-precipitation method, *Fuel. Process. Technol.* 116 (2013) 72-78.
- [15] X. Dong, F. Li, N. Zhao, F. Xiao, J. Wang, Y. Tan, CO₂ hydrogenation to methanol over Cu/ZnO/ZrO₂ catalysts prepared by precipitation-reduction, method. *Appl. Catal., B.* 191 (2016) 8-17.
- [16] L. Li, D. MAO, J. YU, X. Guo, Highly selective hydrogenation of CO₂ to methanol over CuO-ZnO-ZrO₂ catalysts prepared by a surfactant-assisted co-precipitation method, *J. Power. Sources.* 279 (2015) 394-404.
- [17] X. Guo, D. Mao, G. Lu, S. Wang, G. Wu, CO₂ hydrogenation to methanol over Cu/ZnO/ZrO₂ catalysts prepared via a route of solid-state reaction, *Catal. Commun.* 12 (2011) 1095-1098.
- [18] A. Ateka, I. Sierra, J. Ereña, J. Bilbao, A.T. Aguayo, Performance of CuO-ZnO-ZrO₂ and CuO-ZnO-MnO as metallic functions and SAPO-18 as acid function of the catalyst for the synthesis of DME co-feeding CO₂, *Fuel. Process. Technol.* 152 (2016) 34-45.
- [19] V. Deerattrakul, P. Dittanet, M. Sawangphruk, P. Kongkachuichay, CO₂ hydrogenation to methanol using Cu-Zn catalyst supported on reduced graphene oxide nanosheets, *J. CO₂. Util.* 16 (2016) 104-113.

- [20] L.X. Zhang, Y.C. Zhang, S.Y. Chen, Effect of promoter TiO₂ on the performance of CuO-ZnO-Al₂O₃ catalyst for CO₂ catalytic hydrogenation to methanol, *J. Fuel Chem. and Tech.* 39 (2011) 912-917.
- [21] C. Huang, S. Chen, X. Fei, D. Liu, Y. Zhang, Catalytic hydrogenation of CO₂ to methanol: study of synergistic effect on adsorption properties of CO₂ and H₂ in CuO/ZnO/ZrO₂ system, *J. Catalysts*, 5(2015) 1846-1861.
- [22] B.J. Liaw and Y.Z. Chen, Liquid-phase synthesis of methanol from CO₂/H₂ over ultrafine CuB catalysts, *J. App. Catal. A.* 206 (2001) 245-256.
- [23] P.S.S. Prasad, J.W. Bae, K.W. Jun, K.W. Lee, Fischer-Tropsch Synthesis by Carbon Dioxide Hydrogenation on Fe-Based Catalysts, *J. Cat. Surv. Asia.* 12(2008)170-183.
- [24] T. Inoue, T. Iizuka, K. Tanabe, Support Effect of Zinc Oxide Catalyst on Synthesis of Methanol from CO₂ and H₂, *Bull. Chem. Soc. Jpn.* 60 (1987) 2663-2664.
- [25] I. Melian-Cabrera, M. Lopez Granados, P. Terreros, J. L. G. Fierro, CO₂ hydrogenation over Pd-modified methanol synthesis catalysts, *Catal. Today.* 45 (1998) 251-256.
- [26] B. Denise, R. P. A. Sneed, [Oxide-supported copper catalysts prepared from copper formate: Differences in behavior in methanol synthesis from CO/H₂ and CO₂/H₂ mixtures](#), *Appl. Catal.* 28 (1985) 235-239.
- [27] E. Ramarosan, R. Kieffer, A. Kiennemenn, Reaction of CO-H₂ and CO₂-H₂ on copper-zinc catalysts promoted by metal oxides of groups III and IV, *Appl. Catal.* 4 (1982) 281-286.
- [28] F. Arena, K. Barbera, G. Italiano, G. Bonura, L. Spadaro, F. Frusteri, [Synthesis, characterization and activity pattern of Cu-ZnO/ZrO₂ catalysts in the hydrogenation of carbon dioxide to methanol](#), *J. Catal.* 249 (2007) 185-194.
- [29] X.M. Liu, G.Q. Lu, Z.F. Yan, J. Beltramini, Recent Advances in Catalysts for Methanol Synthesis via Hydrogenation of CO and CO₂, *Ind. Eng. Chem. Res.* 42 (2003) 6518-6530.
- [30] Z.S. Hong, Y. Cao, J.F. Deng, K.N. Fan, CO₂ Hydrogenation to Methanol Over Cu/ZnO/Al₂O₃ Catalysts Prepared by a Novel Gel-Network-Co-precipitation Method, *Catal. Lett.* 82 (2002) 37-44.
- [31] C.L. Chiang, K.S. Lin, H.W. Chuang, Direct synthesis of formic acid via CO₂ hydrogenation over Cu/ZnO/Al₂O₃ catalyst, *J. Cleaner. Produc.* 172 (2018) 1957-1977.
- [32] Y. Nitta, T. Fujimatsu, Y. Okamoto, T. Imanaka, Effect of starting salt on catalytic behaviour of Cu-ZrO₂ catalysts in methanol synthesis from carbon dioxide, *Catal. Lett.* 17 (1993) 157-165.
- [33] J. Słoczynski, R. Grabowski, A. Kozłowska, P. Olszewski, J. Stoch, J. Skrzypek, M. Lachowska, Catalytic activity of the M/(3ZnO·ZrO₂) system (M = Cu, Ag, Au) in the hydrogenation of CO₂ to methanol, *Appl. Catal. A: Gen.* 278 (2004) 11-23.

- [34] J. Słoczynski, R. Grabowski, A. Kozłowska, P. Olszewski, M. Lachowska, J. Skrzypek, J. Stoch, Effect of Mg and Mn oxide additions on structural and adsorptive properties of Cu/ZnO/ZrO₂ catalysts for the methanol synthesis from CO₂, *Appl. Catal. A: Gen.* 249 (2003) 129-138.
- [35] R. Raudaskoski, M.V. Niemelä, R.L. Keiski, The effect of ageing time on co-precipitated Cu/ZnO/ZrO₂ catalysts used in methanol synthesis from CO₂ and H₂, *Top. Catal.* 45 (2007) 57-60.
- [36] Y. Choi, K. Futagami, T. Fujitani, J. Nakamura, The role of ZnO in Cu/ZnO methanol synthesis catalysts-morphology effect or active site model, *Appl. Catal. A: Gen.* 208 (2001) 163-167.
- [37] G. X. Qi, J. H. Fei, X. M. Zheng, Z. Y. Hou, Effect of Titanium on Methanol Synthesis from CO₂ Hydrogenation over Cu/ γ -Al₂O₃, *Chin. Chem. Lett.* 12 (2001) 537-540.
- [38] R.A. Köppel, C. Stöcker, A. Baiker, Copper-and silver-zirconia aerogels: preparation, structural properties and catalytic behavior in methanol synthesis from carbon dioxide, *J. Catal.* 179 (1998) 515-527.
- [39] C.L. Carnes, K.J. Klabunde, The catalytic methanol synthesis over nanoparticle metal oxide catalysts, *J. Mol. Catal. A: Chem.* 194 (2003) 227-236.
- [40] H. Lei, Z. Hou, J. Xie, Hydrogenation of CO₂ to CH₃OH over CuO/ZnO/Al₂O₃ catalysts prepared via a solvent-free routine, *Fuel* 164 (2016) 191-198.
- [41] L. Angelo, M. Girleanu, O. Ersen, C. Serra, K. Parkhomenko, A.C. Roger. Catalyst synthesis by continuous co-precipitation under micro-fluidic conditions: Application to the preparation of catalysts for methanol synthesis from CO₂/H₂. *Catal. Today*, 270 (2016) 59-67.
- [42] J. Díez-Ramírez, F. Dorado, A.R. de la Osa, J.L. Valverde, P. Sánchez, Hydrogenation of CO₂ to methanol at atmospheric pressure over Cu/ZnO catalysts: influence of the calcination, reduction, and metal loading, *Ind. Eng. Chem. Res.* 56 (2017) 1979-1987.
- [43] M. Lortie, R. Isaifan, Y. Liu, S. Mommers, Synthesis of CuNi/C and CuNi/Al₂O₃ Catalysts for the Reverse Water Gas Shift Reaction, *Int. J. Chem. Eng.* (2015)
- [44] Y. Jeong, J. Y. Kang, I. Kim, H. Jeong, J. K. Park, J. H. Park, J. C. Jung, Preparation of Cu/ZnO catalyst using a polyol method for alcohol-assisted low temperature methanol synthesis from syngas, *Korean. J. Chem. Eng.* 33 (2016) 114-119.
- [45] H. S. Wu, S. C. Chung, Kinetics of hydrogen production of methanol reformation using Cu/ZnO/Al₂O₃ catalyst, *J. Comb. Chem.* 9 (2007) 990-997.
- [46] B.K. Park, S. Jeong, D. Kim, J. Moon, S. Lim, J.S. Kim, Synthesis and size control of monodisperse copper nanoparticles by polyol method, *J. Colloid. Interface. Sci.* 311 (2007) 417-424.

- [47] T.G. Altınçekiç, I. Boz, Influence of synthesis conditions on particle morphology of nanosized Cu/ZnO powder by polyol method, *Bull. Mater. Sci.* 31 (2008) 619-624.
- [48] L. F. Bobadilla, C. Garcia, J.J. Delgado, O. Sanz, F. Romero-Sarria, M.A. Centeno, J.A. Odriozola, Influence of PVP in magnetic properties of NiSn nanoparticles prepared by polyol method, *J. Magn. Mater.* 324 (2012) 4011-4018.
- [49] C. Y. Lu, H. H. Tseng, M. Y. Wey, L. Y. Liu, K.H. Chuang. Effects of the ratio of Cu/Co and metal precursors on the catalytic activity over Cu-Co/Al₂O₃ prepared using the polyol process, *MATER. SCI. ENG. B.* 157 (2009) 105-112.
- [50] K. H. Chuang, K. Shih, C.Y. Lu, M.Y. Wey, Copper catalysts prepared via microwave-heated polyol process for preferential oxidation of CO in H₂-rich streams, *Int. J. Hydrog. Energy.* 38 (2013) 100-108
- [51] K.C Song, S.M. Lee, T.S. Park, B.S. Lee, Preparation of colloidal silver nanoparticles by chemical reduction method, *Korean J. Chem. Eng.* 26 (2009) 153-155.
- [52] J.H. Byeon, Y.W. Kim, A novel polyol method to synthesize colloidal silver nanoparticles by ultrasonic irradiation, *Ultrason. Sonochem* 19 (2012) 209-215.
- [53] Y. Jeong, J.Y. Kang, I. Kim, H. Jeong, J.K. Park, J.H. Park, J. C. Jung, Preparation of Cu/ZnO catalyst using a polyol method for alcohol-assisted low temperature methanol synthesis from syngas, *Korean. J. Chem. Eng.*, 33 (2016) 114-119.
- [54] İ. Boz, T.G. Altınçekiç Liquid phase hydroxylation of benzene to phenol over Cu/ZnO catalysts, *React. Kinet. Mech.cat.* 102 (2011) 195-205.
- [55] E. Bayrakdar, T.G. Altınçekiç, M.A.F. Öksüzömer, Effects of PVP on the preparation of nanosized Al₂O₃ supported Ni catalysts by polyol method for catalytic partial oxidation of methane, *Fuel. Process. Technol.* 110 (2013) 167-175.
- [56] S. Brunauer, S. P. H. Emmett, E. Teller, Absorption of gases in multi molecular layers, *J. Am. Chem. Soc.* 60 (1938) 309-319.
- [57] E.P. Barrett, L.G. Joyner, P.P. Halenda, The determination of pore volume and area distributions in porous substances. I. Computations from nitrogen isotherms, *J. Am. Chem. Soc.* 73 (1951) 373-380.
- [58] S.B. Bagherzadeh, M. Haghghi, and N. Rahemi, Novel oxalate gel co-precipitation synthesis of ZrO₂-CeO₂-promoted CuO-ZnO-Al₂O₃ nanocatalyst for fuel cell-grade hydrogen production from methanol: Influence of ceria-zirconia loading, *Energy. Convers. Manage.* 134(2017)88-102.
- [59] B. Ouyang, W. Tan, B. Liu, Morphology effect of nanostructure ceria on the Cu/CeO₂ catalysts for synthesis of methanol from CO₂ hydrogenation, *Catal. Commun.* 95(2017) 36-39.

- [60] H. Ajamein, M. Haghghi, On the microwave enhanced combustion synthesis of CuO–ZnO–Al₂O₃ nanocatalyst used in methanol steam reforming for fuel cell grade hydrogen production: effect of microwave irradiation and fuel ratio, *Energy. Convers. Manage.* 118 (2016) 231-242.
- [61] J. Xiao, D. Mao, X. Guo, J. Yu, Effect of TiO₂, ZrO₂, and TiO₂-ZrO₂ on the performance of CuO-ZnO catalyst for CO₂ hydrogenation to methanol, *Appl. Surf. Sci.* 338 (2015) 146-153.
- [62] T. Witoon, N. Kachaban, W. Donphai, P. Kidkhunthod, K. Faungnawakij, M. Chareonpanich, J. Limtrakul. Tuning of catalytic CO₂ hydrogenation by changing composition of CuO-ZnO-ZrO₂ catalysts, *Energy. Convers. Manage.* 118 (2016) 21-31.
- [63] J. Aguado, M.C. Castro, Influence of the thermal treatment upon the textural properties of sol-gel mesoporous γ -alumina synthesized with cationic surfactants, *Micropor. Mesopor. Mat.* 128 (2010) 48-55.
- [64] V. Deerattrakul, P. Dittanet, M. Sawangphruk, P. Kongkachuichay, CO₂ hydrogenation to methanol using Cu-Zn catalyst supported on reduced graphene oxide nanosheets, *J. CO₂ UTIL.* 16 (2016) 104-113
- [65] F. Prinetto, G. Ghiotti, P. Graffin, D. Tichit, Synthesis and characterization of sol-gel Mg/Al and Ni/Al layered double hydroxides and comparison with co-precipitated samples, *Micropor. Mesopor. Mat.* 39 (2000) 229-247.
- [66] Y. Zhu, X. Kong, D.B. Cao, J. Cui, Y. Zhu, Y.W. Li. The rise of calcination temperature enhances the performance of Cu catalysts: contributions of support, *ACS. Catal.* 4 (2014) 3675-3681.
- [67] J. Liu, C. H. Han, X. Yang, G. Gao, Q. Shi, M. Tong, C. Li, Methyl formate synthesis from methanol on titania supported copper catalyst under UV irradiation at ambient condition: Performance and mechanism, *J. Catal.* 33 (2016) 162-170
- [68] X. Dong, F. Li, N. Zhao, Y. Tan, J. Wang, F. Xiao, CO₂ hydrogenation to methanol over Cu/Zn/Al/Zr catalysts prepared by liquid reduction, *Chinese. J. Catal.* 38 (2017) 717-725.
- [69] B. Zhang, Y. L. Zhu, G. Q. Ding, H. Y. Zheng, Y. W. Li, Modification of the supported Cu/SiO₂ catalyst by alkaline earth metals in the selective conversion of 1, 4-butanediol to γ -butyrolactone, *Appl. Catal. A.* 443 (2012) 191–201.
- [70] S. Murcia-Mascarós, R. M. Navarro, L. Gomez-Sainero. Oxidative methanol reforming reactions on CuZnAl catalysts derived from hydrotalcite-like precursors, *J. Catal.* 198 (2001) 338-347.
- [71] K. Sun, K.W. Lu, F. Qiu, S. Liu, X. Xu, Direct synthesis of DME over bifunctional catalyst: surface properties and catalytic performance, *Appl. Catal. A.* 252 (2003) 243-249.

- [72] R.M. Friedman, J.J. Freeman, F.W. Lytle, Characterization of CuAl₂O₃ catalysts, *J. Catal.*, 55 (1978) 10-28.
- [73] M. C. Biesinger, L.W. Lau, A.R. Gerson, R.S.C. Smart, Resolving surface chemical states in XPS analysis of first row transition metals, oxides and hydroxides: Sc, Ti, V, Cu and Zn, *Appl. Surf. Sci.* 257 (2010) 887-898.
- [74] Y. K. Gao, F. Traeger, O. Shekhah, H. Idriss, C. Wöll, Probing the interaction of the amino acid alanine with the surface of ZnO (101), *J. Colloid. Interface. Sci.* 338 (2009) 16-21.
- [75] C. Yang, F. Bebensee, J. Chen, X. Yu, A. Nefedov, C. Woll, Carbon dioxide adsorption on CeO₂(110): an XPS and NEXAFS study, *Chem. Phys. Chem.* 18 (2017) 1874-1880
- [76] L. Óvári, S. K. Calderon, Y. Lykhach, J. Libuda, A. Erdöhelyi, C. Papp, H. P. Steinrück, Near ambient pressure XPS investigation of the interaction of ethanol with Co/CeO₂ (1 1 1), *J. Cat.* 307 (2013) 132-139.
- [77] A. Pfau, K.D. Schierbaum, The electronic structure of stoichiometric and reduced CeO₂ surfaces: an XPS, UPS and HREELS study, *Surf. Sci.* 321 (1994) 71-81.
- [78] P. Burroughs, A. Hamnett, A.F. Orchard, G. Thorton, Satellite structure in the X-ray photoelectron spectra of some binary and mixed oxides of lanthanum and cerium, *J. Chem. Soc. Dalton Trans.* 17 (1976) 1686-1698.
- [79] C.J. Nelin, P.S. Bagus, E.S. Ilton, S.A. Chambers, H. Kühlenbeck, H.J. Freund, Relationships between complex core level spectra and materials properties, *Int. J. Quantum. Chem.* 110 (2010) 2752-2764.
- [80] J. C. Frost, Junction effect interactions in methanol synthesis catalysts, *Nature.* 334 (1988) 577-580.
- [81] R. Burch, R. J. Chappell, S. E. Golunski, Synergy between copper and zinc oxide during methanol synthesis. Transfer of activating species, *J. Chem. Soc. Faraday Trans. 1 Phys. Chem. Condens. Phases.* 85(1989) 3569-3578.
- [82] R. Burch, R. J. Chappell, S. E. Golunski, Synergy at a distance in the synthesis of methanol over copper catalysts, *Catal. Lett.* 12 (1988) 439-443.
- [83] X. Li, Z.J. Zhao, L. Zeng, J. Zhao, H. Tian, S. Chen, K. Li, S. Sang, J. Gong, On the role of Ce in CO₂ adsorption and activation over lanthanum species, *Chem. Sci.* 9 (2018) 3426-3437.
- [84] H. Lei, R. Nie, G. Wu, Z. Hou, Hydrogenation of CO₂ to CH₃OH over Cu/ZnO catalysts with different ZnO morphology, *Fuel*, 154 (2015) 161-166.
- [85] E.J. Choi, Y. H. Lee, D.W. Lee, D. J. Moon, K.Y. Lee, Hydrogenation of CO₂ to methanol over Pd-Cu/CeO₂ catalysts, *Mol. Catal.* 434 (2017) 146-153.

[86] W. Wu, K. Xie, D. Sun, X. Li, F. Fang, CuO/ZnO/Al₂O₃ Catalyst Prepared by Mechanical-Force-Driven Solid-State Ion Exchange and Its Excellent Catalytic Activity under Internal Cooling Condition, *Ind. Eng. Chem. Res.* 56 (2017) 8216-8223.

[87] S. Soisuwan, W. Wisaijorn, C. Nimmul, O. Maunghimpan, P. Praserthdam, The Combination of Calcium Oxide and Cu/ZrO₂ Catalyst and their Selective Products for CO₂ Hydrogenation, *Eng. J.* 20 (2016) 39-48.

No interest conflicts affect the authors of this manuscript.

FIGURES




Fig.1. TGA profiles of catalyst: (a) before calcination, (b) after calcination at 500 °C

Courbes ATG des catalyseurs : a) avant calcination b) après calcination à 500 °C




Fig.2. XRD patterns of calcined catalysts: (a) CuO-CeO_2 , (b) ZnO-CeO_2 , (c) CuO-ZnO-CeO_2 , and (d) $\text{CuO-ZnO-Al}_2\text{O}_3$.

DRX des catalyseurs calcinés/ (a) CuO-CeO_2 , (b) ZnO-CeO_2 , (c) CuO-ZnO-CeO_2 , et (d) $\text{CuO-ZnO-Al}_2\text{O}_3$.




Fig.3. (a) N_2 -adsorption-desorption isotherms and (b) Pore size distribution, of all samples

(a) Isothermes d'adsorption et désorption d'azote et (b) distribution poreuse des échantillons




Fig.4. SEM images at different magnification of all catalysts (a-c) CuO-CeO_2 , (d-f) ZnO-CeO_2 (g-i) CuO-ZnO-CeO_2 and (j-l) $\text{CuO-ZnO-Al}_2\text{O}_3$

Images MEB des catalyseurs (a-c) CuO-CeO_2 , (d-f) ZnO-CeO_2 (g-i) CuO-ZnO-CeO_2 et (j-l) $\text{CuO-ZnO-Al}_2\text{O}_3$




Fig.5. Cu 2p XPS spectra of CuO-ZnO-CeO₂ and CuO-ZnO-Al₂O₃ samples

Spectres XPS Cu 2p des échantillons CuO-ZnO-CeO₂ et CuO-ZnO-Al₂O₃




Fig.6. C 1s XPS spectra of CuO-ZnO-CeO₂ and CuO-ZnO-Al₂O₃ samples

Spectres XPS C 1s des échantillons CuO-ZnO-CeO₂ et CuO-ZnO-Al₂O₃





Fig.7. O 1s XPS spectra of (a) CuO-ZnO-CeO₂ and (b) CuO-ZnO-Al₂O₃ samples

Spectres XPS O 1s des échantillons (a) CuO-ZnO-CeO₂ et (b) CuO-ZnO-Al₂O₃




Fig.8. Ce 3d XPS spectra of the CuO-ZnO-CeO₂ sample

Spectres XPS Ce 3d de l'échantillon CuO-ZnO-CeO₂




Fig.9. CO_2 conversion as function of the time of reaction. Reaction conditions: $CO_2/H_2 = 1/9$, $T=240^\circ C$, $flow=1L.h^{-1}$ and $P = 1 atm$.

Conversion de CO_2 en fonction du temps de réaction. Conditions de réaction : $CO_2/H_2 = 1/9$, $T=240^\circ C$, $débit=1L.h^{-1}$ et $P = 1 atm$.




Fig.10. a) CO₂ conversion as function of the time and temperature of reaction b)-MeOH and CH₄ selectivity as function of the temperature of reaction, over the CuO-ZnO-CeO₂ catalyst: flow=1L.h⁻¹ and P = 1 atm

a) Conversion de CO₂ en fonction du temps et de la température de réaction b) Sélectivités envers méthanol et méthane en fonction de la température de réaction pour le catalyseur CuO-ZnO-CeO₂: débit=1L.h⁻¹ et P = 1 atm