Elsevier Editorial System(tm) for Nanomedicine: Nanotechnology, Biology, and Medicine Manuscript Draft

Manuscript Number:

Title: Gold Nanoclusters as a new contrast agent for image-guided surgery of Head and Neck tumors

Article Type: Original Article

Keywords: gold nanoclusters; image-guided surgery; Head and Neck carcinoma; nanomedicine

Corresponding Author: Dr. Lucie Sancey, Ph.D.

Corresponding Author's Institution: IAB U1209 UMR5309 UGA

First Author: Cindy Colombé, M.D.

Order of Authors: Cindy Colombé, M.D.; Xavier Le Guével, Ph.D.; Maria Isabel Montañez; Maxime Henry; Clothilde Comby-Zerbino; Rodolphe Antoine, Ph.D.; Ihab Atallah, M.D., Ph.D; Benoit Busser, Pharm.D, Ph.D; Jean-Luc Coll, Ph.D.; Christian A Righini, M.D., Ph.D.; Lucie Sancey, Ph.D.

Abstract: With the objective to evaluate the potential of ultra-small gold (Au) nanoclusters (NCs) for optical image-guided surgery, we synthesized and characterized AuNCs shelled by zwitterionic or pegylated ligands. The toxicity of the different AuNCs was evaluated on the Head and Neck Squamous Cell Carcinoma (HNSCC) CAL-33 and SQ20B cell lines in vitro. The safer AuNCs were administrated intravenously to mice for the determination of the pharmacokinetic properties. Biodistributions were performed on orthotopic CAL-33 HNSCC-bearing mice. Finally, the AuNCs were used for image-guided surgery, allowing the increase of the survival time vs. control animals, and the number of animals without any local recurrence.

Cover Letter Click here to download Cover Letter: cover.pdf





CENTRE DE RECHERCHE UGA - INSERM U 1209 - CNRS UMR 5309

Institute for Advanced Biosciences

SANCEY Lucie, PhD Team Cancer Target & Experimental Therapeutics Institute for Advanced Biosciences Site Santé 38000 Grenoble Cedex

La Tronche, 2019, January 7th

Dear Editor,

The following manuscript is being submitted for consideration in *Nanomedicine: Nanotechnology, Biology and Medicine,* "Gold Nanoclusters as a new contrast agent for image-guided surgery of Head and Neck tumors".

The manuscript describes the synthesis and characterization of ultra-small gold nanoparticles, the *in vitro* evaluation of their toxicity, their *in vivo* distribution in mice-bearing orthotopic Head and Neck carcinoma, and finally their used for image-guided surgery. The AuNCs help the surgeon to remove the tumor lesions, increasing of the survival time of the animals *vs.* control animals, and the number of animals without any local recurrence.

The data in this manuscript are original, and is/was not under consideration for publication elsewhere. All authors have read and approved this manuscript, its contents, and its submission to *Nanomedicine: Nanotechnology, Biology and Medicine*.

Thanks you for considering this manuscript. Lucie Sancey, PhD

Site Santé Allée des Alpes 38700 La Tronche

Tél. : 33 (0)4 76 54 94 49 Fax : 33 (0)4 76 54 94 54 iab.univ-grenoble-alpes.fr

Gold Nanoclusters as a new contrast agent for image-guided surgery of Head and Neck tumors

Cindy Colombé ¹⁻², Xavier Le Guével ¹, Maria Isabel Montañez ³, Maxime Henry ¹, Clothilde Comby-Zerbino ⁴, Rodolphe Antoine ⁴, Ihab Atallah ², Benoit Busser ¹⁻², Jean-Luc Coll ¹, Christian Adrien Righini ¹⁻², Lucie Sancey ¹

Potential reviewers:

1- Pr. Marc Schneider (University of Saarland, Germany): Marc.Schneider@mx.uni-saarland.de Expertise: interaction nanomaterials with biological barriers, optical imaging

 $\label{eq:likelihood} \end{tabular} \end{t$

Expertise: nanobiophotonic, sensing, bioimaging

3-Helder Santos (university of Helsinki, Finland): helder.santos@helsinki.fi

Expertise: Drug delivery system, nano materials for therapy and diagnostic

4- Li Shang (Northwestern Polytechnical University, China): li.shang@nwpu.edu.cn

Expertise: synthesis of metal nanoclusters and their in vitro study by optical and spectroscopic techniques

5- Stéphane Roux (Université de Bourgogne Franche-Comté, France): stephane.roux@univ-fcomte.fr Expertise: Synthesis and characterization of Gold nanoparticles for medical applications

Gold Nanoclusters as a new contrast agent for image-guided surgery of Head and Neck tumors

Cindy Colombé ¹⁻², Xavier Le Guével ¹, Maria Isabel Montañez ³, Maxime Henry ¹, Clothilde Comby-Zerbino ⁴, Rodolphe Antoine ⁴, Ihab Atallah ², Benoit Busser ¹⁻², Jean-Luc Coll ¹, Christian Adrien Righini ¹⁻², Lucie Sancey ¹

Graphical abstract

Gold nanoclusters (AuNCs) were designed and evaluated for image-guided surgery. The core of the NCs was shelled by zwitterionic (*i.e.* ZwEt₂) or pegylated ligands (*i.e.* PegCOOH). Selected AuNCs were administrated to mice-bearing orthotopic Head and Neck carcinoma for image-guided surgery. They contribute to the identification of small tumor residues that were removed by surgery. Histological analysis confirmed the presence of tumor cells within the removed residues.



Gold Nanoclusters as a new contrast agent for image-guided surgery of Head and Neck tumors

Cindy Colombé¹⁻², Xavier Le Guével¹, Maria Isabel Montañez³, Maxime Henry¹, Clothilde Comby-Zerbino⁴, Rodolphe Antoine⁴, Ihab Atallah², Benoit Busser¹⁻², Jean-Luc Coll¹, Christian Adrien Righini¹⁻², Lucie Sancey¹

1- Cancer Targets & Experimental Therapeutics, Institute for Advanced Biosciences (IAB), University of Grenoble Alpes- INSERM U1209 – CNRS UMR 5309- 38000 Grenoble, France

2- Grenoble Alpes University Hospital, 38000 Grenoble, France

3- Research Laboratory and Allergy Service, IBIMA, Regional University Malaga Hospital, UMA, 29009 Malaga, Spain and Andalusian Center for Nanomedicine and Biotechnology - BIONAND, 29590 Málaga, Spain

4- Institut lumière matière, UMR5306, Université Claude Bernard Lyon1-CNRS, Université de Lyon 69622 Villeurbanne cedex, France

Financial support

We acknowledge the Rhône-Alpes Auvergne region for the financial support CLARA-Oncostarter (CVPPRCAN000162) and ARC (RAC17012CCA).

Word count for the abstract: 102 Complete manuscript word count (to include body text and figure legends): 4992 Number of references: 38 Number of figures/tables: 8

Abstract

With the objective to evaluate the potential of ultra-small gold (Au) nanoclusters (NCs) for optical image-guided surgery, we synthesized and characterized AuNCs shelled by zwitterionic or pegylated ligands. The toxicity of the different AuNCs was evaluated on the Head and Neck Squamous Cell Carcinoma (HNSCC) CAL-33 and SQ20B cell lines *in vitro*. The safer AuNCs were administrated intravenously to mice for the determination of the pharmacokinetic properties. Biodistributions were performed on orthotopic CAL-33 HNSCC-bearing mice. Finally, the AuNCs were used for image-guided surgery, allowing the increase of the survival time *vs.* control animals, and the number of animals without any local recurrence.

Background

Head and Neck cancers are frequently observed at the late stage when the 5-years survival does not exceed 25%. At late stages, the surgery of Head and Neck Squamous Cell Carcinoma (HNSCC) remains often fairly complex due to the numerous local structures that should be sustained such as small muscles, nerves and tendons. The preservation of these healthy structures is fundamental in the perspective of restorative surgery (1). In addition, the total removal of tumor should be ensuring by the presence of healthy surrounding tissues around the lesion. This step is critical for the post-surgery treatment, which varied as function of the margin' size, *i.e.* the quantity of healthy tissue removed in addition to the pathologic area. In this context, nanotechnology might bring a strong support to overcome these issues, especially in the field image-guided surgery (2, 3). When the surgery is assisted by real-time imaging, the tumor resection might be improved with the removal of small residues in particular and sufficient margin, the healthy tissues might be spared, and the time of surgery might be reduced (4-6). NIR image-guided surgery has already been validated in small animal studies (5, 7) and is currently under investigation in clinical trials. In particular, antibody directed against Epidermal Growth Factor Receptor, *i.e.* cetuximab-IRDye800CW, is under evaluation in a clinical trial for the intraoperative assessment of tumor margins during surgical treatment of HNSCC (8). In addition, the indocyanine green (ICG) is used to identify the sentinel lymph nodes, which is associated with locoregional recurrence in the most aggressive HNSCC (9). Recently, Warram's group illustrated surgery assisted by real-time imaging. They demonstrated the valuable adjunct of imaging to the oncologic surgeon, both before, during, and after the surgery, facilitating the detection of occult lesions in particular (10). For all these reasons, image-guided surgery can be of benefit for patients in terms of post-treatment procedures, overall survival, side effects, and quality of life.

Gold nanoclusters (AuNCs) are ultra-small particles (<5 nm) that emerged as promising renal clearable nanocompounds for cancer diagnostic and therapy (11-13). Thanks to their photoluminescence properties in the NIR/SWIR region (14, 15), a spectral window favorable for *in vivo* monitoring, these probes could be tracked in real-time imaging, in various organs (16). AuNC size between 10 to 25 gold atoms was recently shown by Zheng's team to strongly affect the pharmacokinetic and the tumor accumulation in mice (17). The physico-chemical properties of the ligands protecting the metal core are another key parameters that highly influence the pharmacokinetics and the biodistribution of AuNCs in animals. For instance, short PEG chains stabilizing AuNCs have enabled to enhance the half-life from 5 to 45 min compared to AuNCs protected by glutathione (18). In another study, we previously observed an increase of the blood circulation for AuNCs stabilized by a bidentate zwitterion ligand compared to the well-known NCs $Au_{25}SG_{18}$ from 1.5 to 6.5 min. This led to a stronger accumulation in glioblastoma mice models by passive uptake with a high tumor retention over 24 h (16).

With the objective to evaluate the potential of AuNCs for image-guided surgery of orthotopic HNSCC-bearing mice, we synthesized AuNCs with different ligands, and performed their *in vitro* and *in vivo* biological investigations. First, the toxicity and the cell uptake properties of the different formulations were evaluated on 2 HNSCC cell lines, *i.e.* CAL-33 and the SQ20B cells. Then, the most favorable formulations, *i.e.* safer and well-uptaken by the cells, were administrated intravenously to mice-bearing tumors for the determination of the biodistribution and the pharmacokinetics properties of the selected NCs. Finally, two AuNCs were used for image-guided surgery, and animals were followed-up until tumor recurrence. The image-assisted removed residues were also analyzed for tumor invasion by histology.

Methods

Materials: Chemical reagents were purchased from Sigma-Aldrich (France) and deionized water was used during the synthesis.

Gold Nanoclusters: AuNCs stabilized by bidentate thiolated organic molecules were synthesized following protocols reported earlier (19). In particular, we chose a zwitterionic ligand LA-ZwEt₂ ($C_{18}H_{36}N_2O_4S_3$; 440.68 g.mol⁻¹) and a short pegylated ligand with a negatively charged terminal group LA-PegCOOH ($C_{38}H_{74}N_2O_{16}S_2$; $n_{PEG}=12$; 879.13 g.mol⁻¹) synthesized in the lab (20, 21). Both type of AuNC were prepared with low and high ligand density by increasing the amount of the bidentate thiolated organic molecules during the synthesis. For the zwitterionic ligand, it corresponded to the molar ratio Au:ZwEt₂:NaBH₄= 1:2:2 and 1:5:2. For the PEG ligand, it corresponded to the molar ratio Au:PEG:NaBH₄= 1:3:2 and 1:5:2. In a typical synthesis for AuPegCOOH 1:3, 26.4 mg of PegCOOH was dissolved in 15 mL water at pH 10 (80 μ L NaOH (2M)) under vigorous stirring and 200 μ L of HAuCl₄ (50 mM) was added. After 10 min, 200 μ L NaBH₄ (100mM) was added dropwise and the solution was kept under mild stirring for 15 hours. Freshly prepared AuPegCOOH was filtered 3 times (Amicon filters 3 kDa) to remove the excess of free ligand and diluted in PBS at the required concentration. Each stock solution was filtered (0.22 μ m) before use.

The well-described AuNC made of 25 gold atoms stabilized by the peptide glutathione $Au_{25}SG_{18}$ was synthesized in two steps as described by Pradeep and coworkers (22), and diluted in PBS at the required concentration. Later in this manuscript, the AuNCs are cited by the name of their ligands.

NC characterization: Absorbance measurements on diluted samples were recorded on an Evolution 201 (ThermoScientific) UV-vis spectrophotometer between 300 and 950 nm. Fluorescence spectra were recorded on a Perkin Elmer LS45 fluorescence spectrometer. Hydrodynamic diameters of the AuNCs were determined by dynamic light scattering (DLS), and their surface charges by zeta potential measurements, both analyses using Malvern Instrument. For mass spectrometry measurements, a commercial quadrupole time-of-flight mass spectrometer (micro-qTOF, Bruker-Daltonics, Bremen, Germany, mass resolution 10,000) was used as previously reported (23, 24) (see also supplementary information).

Cell lines: This study was conducted using two human head and neck squamous carcinoma cell lines. The CAL-33 (Leibniz Institute, Braunschweig, Germany) cell line derived from a tongue carcinoma and was used for *in vitro* experiments, and for orthotopic models. The second cell line used was the larynx carcinoma SQ20B cell line (Institute for Advanced Biosciences, Grenoble, France). The cells were maintained in a monolayer culture in DMEM (Dulbecco's Modified Eagle's medium) supplemented with 10% of heat-inactivated FBS (Fetal Bovine Serum) (v/v) in a humidified incubator (Sanyo, Japan) at 37°C in an atmosphere containing 5% CO₂. The sub-culturing was performed twice a week.

Viability assay: Cell viability assays were used to evaluate the cytotoxicity of AuNC *in vitro*. CAL-33 and SQ20B cells were seeded in a 96-well plate at a density of 10^5 cells per well and cultured overnight. Then cells were incubated with 50 or 100 µL of AuNC/mL of medium for 24 h before medium renewal for the next 48 h incubation. We used staurosporine as negative control that induces massive cell death, and no AuNC as positive control for viability. After washing with PBS, the cell viability was determined using the Presto-Blue viability kit (*i.e.* 72 hours after NCs exposure). According to the manufacturer's instructions, the fluorescence was recorded on a microplate reader after 4 hours of incubation, selecting the fluorescence excitation/emission couple 560 nm/590 nm, avoiding any cross-absorption from the gold atoms.

FACS analysis: 5.10^5 cells (CAL-33 and SQ20B) were plated in a six-well plate with DMEM with 10% FBS. After 24 h, different AuNC were added at 50 µL/mL for 4 h at 37°C and 4°C, 8 h and 24 h at 37°C. At the end of incubation, the cells were prepared for flow cytometry analysis. The NCs'

uptake was measured with LSRII (Becton Dickinson, Le Pont de Claix, France) and photon emission was selected using long-pass filters, and recorded at 730/45 and 780/60-nm. Data were analyzed with the BD FACSDiva 6.3.1 software. One should note that the fluorescence emission of the NCs, in the NIR region prevents the internalization study using conventional microscopy.

Mice and pharmacokinetic study: Animal experiments were conducted in accordance with protocols approved by the Ethical Committee of Grenoble, and the French Minister in agreement with the European directive 2010/63/UE. The pharmacokinetic (PK) study was conducted on 12 SWISS mice divided into 4 groups (n=3/group). The solutions of 200 μ L AuNC were administrated IV at 2.5 mg/mL. The PK of the Au₂₅SG₁₈ was performed previously by our group in similar condition, and was not performed again for ethical reasons (15). Approximately 20 μ L of blood were collected in heparined vials from the tail vein at the indicated times after injection. The vials were centrifuged 20 minutes to recover the plasma serum. Then, a drop of 10 μ L of serum was imaged (Optimal, Grenoble, France) and black and white pictures, acquired with a black-thinned CCD camera at -80°C (ORCAII-BT-512G, Hamamatsu, Massy, France). Image display and analysis were obtained with the Wasabi® software (Hamamatsu, Massy, France).

Head and Neck orthotopic tumor model: In total, 65 Female athymic NMRI nude mice (5-6 weeks old) were purchased from Janvier laboratories (Le Genet sur Isle, France), and used for this study. The complete tumor model can be found in the supplementary section, and in Atallah et al (7).

Biodistribution study: After tumor growth, AuNCs were injected IV (200 μ l at [Au] = 5 mg/mL, n=24 for biodistribution and n=12 for imaging). The nanoparticles' biodistribution was investigated using *in vivo* fluorescence imaging (Optimal, Grenoble, France), as previously described (16).

Surgical study: Animals were randomized 21 days after tumor implantation to perform tumor resection under visual macroscopic guidance (n=8), using near infrared (NIR) optical imaging after AuNC PegCOOH 1:3 (n=8) or Et₂ 1:5 (n=8, one mouse died from anesthesia and was removed from the study reducing to 7 the number of mice in this group) administration. Later in the manuscript, these 2 AuNCs groups were merged. Surgery was performed under general anesthesia (intraperitoneal injection of a mix of medetomidin (0.2 μ g/g) / ketamine (0.1 mg/g)) associated with a subcutaneous injection of buprenorphine (0.1 mg/kg)), as described in the supplementary information section.

Histology and confocal imaging: The removed residues were embedded into OCT and sliced at 8 μ m. The sections were then H&E stained for histology. Adjacent slices were mounted with a coverglass for confocal microscopy analysis. The microscopy of the frozen remaining tissues was carried out using a confocal microscope (LSM510, Zeiss Jena, Germany) with a 10x objective. The AuNCs were excited by a 488-nm, or 405-nm emission laser and their emission was collected using a long-pass filter at 600 nm.

Results

Library of nanoclusters

AuNCs are ultra-small gold particles with core size between 1 and 3 nm. To protect the body from the reactive gold species, the core of the NCs can be shelled by various ligands. In this study, 5 NCs were synthesized: 2 with a lipoic zwitterionic ligand (*i.e.* $ZwEt_2$), 2 with the pegylated ligand PegCOOH and the last one with glutathione (SG). Thickness of the zwitterionic and pegylated layers covalently bonded to the gold core could be tuned during the synthesis while keeping a similar core size as represented in the **Figure S1**. The increase of the organic shell leads to an obvious increase of the molecular weight of AuNCs, which is confirmed by electron-spray ionization mass spectrometry (ESI-

MS). For instance AuZwE⁵ has an average molecular weight around 17.5 kDa, which is 22% bigger than AuZwEt₂ 1:2 with a molecular weight around 14.5 kDa (see Figure S2). Surprisingly, AuPegCOOH 1:3 is smaller than AuZwEt₂ 1:2 with a molecular weight estimated at \sim 9 kDa but an increase of the pegylated ligand during the synthesis for AuPegCOOH 1:5 leads to a molecular weight (MW) around ~ 22 kDa heavier than AuZwEt₂ 1:5. Despite a similar lipoic acid moiety to anchor the gold core, the difference in size between zwitterionic and pegylated ligands might be related to the electrostatic interaction between the ligands during the AuNC's formation in solution. This could influence the number of ligand per AuNCs considering no significant change of the metal core size determined by microscopy measurements (data not shown). However, this observation needs to be considered carefully because of the quite broad MW distribution obtained by ESI-MS for these AuNCs. In addition and as previous reported (25), ESI-MS analysis also demonstrated that the effective charges (z_{eff}) extracted from the measured Zeta-potential (ζ) of NPs in solution were partially correlated with the average values of charge Zaverage of NPs in gas phase. Interestingly, this correlation seems also valid for AuNCs investigated in this study, where a nice correlation between the Zetapotential and the average charge state of Zaverage is observed (see Table 1). The atomically precise AuNCs stabilized by glutathione Au₂₅SG₁₈ have a molecular weight of 10.4 kDa.

Hydrodynamic diameters measured by dynamic light scattering (DLS) show a size below 10 nm for all types of AuNCs with an increase of diameter for thicker organic shell. From zeta potential measurements, all AuNCs were negatively charged at pH 7, and less charged for the zwitterionic species AuZwEt₂. The main physico-chemical characteristics and properties of the different NCs are summarized in the **Table 1**. Absorbance profiles for AuZwEt₂, AuPegCOOH, and Au₂₅SG₁₈ present similar pattern with a decrease of signal at longer wavelength (**Figure S3**). All types of AuNCs emit in the red/near-infrared region with a blue-shift and an increase of their brightness for thick organic shell (**Figure S3**, **Table 1**). This behavior has been extensively reported and is correlated to the nature, the density, and the rigidity of the ligands stabilizing the metal core of AuNCs (26-28).

By knowing both MW (by ESI-MS) and size (by DLS), it $\mathbf{r} = \mathbf{i}$ ible to address the density of AuNCs investigated in this study. While AuZwEt₂ 1:5, AuPegCOOH 1:3, and AuPegCOOH 1 = Cs present similar densities, AuZwEt₂ 1:2 NCs display a density higher than one order of magnitude. This is due to the fact AuZwEt₂ 1:2 NCs have a relatively high MW and a small size, as compared to other AuNCs. This phenomenon might be due to the synthesis protocols that may lead for AuZwEt₂ 1:2 to a higher gold core and smaller number of ligands in the outer shell, as compared to the other NCs.

Toxicity profiles and cell internalization of the different NCs

The toxicity of the different NCs was determined at 50 and 100 μ g gold/mL on two different human HNSCC cell lines, namely CAL-33 and SQ30B cells (**Figure 1**). The viability assay was performed after a 24-hour exposure followed by a further 48-hour incubation, *i.e.* 72 hours in total. Due to the natural blue-color of the AuNCs, the presto-blue assay was performed in fluorescence mode, to avoid any overlapping due to the solutions themselves.

If most of the tested NCs were not or weakly toxic, the main toxicities were measured for the AuPegCOOH, with a particular susceptibility of the SQ20B cells for AuPegCOOH (1:3) at hig concentration (*i.e.* 100 μ g/mL). For these AuNCs, the density of the ligands in the NCs' shell did not affect the safety profile of the NCs: both ligand densities were equally safe, except for the SQ20B cells exposed to AuPegCOOH (1:3), as described in the Figure 1B.

The cell uptake of the NCs was evaluated using flow cytometry on CAL-33 cells. As summarized in the **Figure 2**, after 8 hours of incubation NCs were moderately internalized. Only the fluorescence signal of the AuZwEt₂ (1:5), and AuPegCOOH (1:3) were recorded inside the CAL-33 cells. Percentages of cells positively stained by the AuNCs reach 17% and 38% for the AuPegCOOH (1:3)

and the AuZwEt₂ (1:5), respectively (see **Figure 1D**). We hypothesized that the weak AuPegCOOH (1:5) uptake may be in part attributed to a higher contribution of the Peg coating as compared to AuPegCOOH (1:3), which exhibit anti-fouling effect (29).

In vivo distribution and behavior of the NCs

The distribution of the NCs was evaluated in mice-bearing sub-cutaneous CAL-33 tumors, using optical imaging. Organs were sampled 5 hours post-intravenous (IV) administration and analyzed the results are summarized in the Figure 3, and the Table S1. As previously reported, most of the AuNCs were rapidly eliminated through the urine, *i.e.* after renal filtration, due to their small size (15, 16). The remained NCs were mainly distributed in the hepato-biliary system (liver and spleen), and the kidneys. We noticed some uptake in the stomach for $AuZwEt_2$ (1:2) while the others AuNCs were not specifically accumulated in this organ. This accumulation might be due to its hepato-biliary elimination. In addition, the very high density of this AuNC might also explain its particular behavior leading to a loner stomach and liver retention, as compared to the other clusters. The AuNCs were then mostly found in the skin and the tumor, 5 hours post injection. Interestingly, the AuZwEt₂ 1:5, and the Pegylated AuNCs were rapidly eliminated from the body, with very moderate to low liver and kidney accumulations. Therefore, the most promising AuNCs were selected for next P = nd imaging investigations. Due to its long liver retention, the AuZwEt₂ (1:2) was not selected for the *in vivo* studies. AuZwEt₂ (1:5), and the pegylated AuNCs were injected to healthy mice to determine their plasma half-lives, and compared to Au₂₅SG₁₈. The blood samples were collected directly after the intravenous administration, and over the next 2 hours. As indicated in the Figure 4, the plasma halflives are longer than that of Au₂₅SG₁₈ (see also Suppl. Table S2), with prolonged exposure. The nature of the ligand and the thickness of this organic layer stabilizing the gold core have a significant effect on the pharmacokinetics. All the AuNCs presented plasma half-life fitting with two-phase decay equation, which is a combination of 2 plasma half-lives, *i.e.* a fast and a slow half-life. Indeed, zwitterionic ligand Et_2 (1:5) prolonged the biopersistence of the AuNCs in the plasma, reaching almost 4 min and 11.5 minutes for fast and slow half-lives respectively. For pegylated AuNCs, the fast halflives were very short with 0.45 and 0.32 min for AuPegCOOH (1:3), and AuPegCOOH (1:5), respectively. The slow half-lives were longer, reaching almost 10 minutes for AuPegCOOH (1:3), and more than 13 minutes for AuPegCOOH (1:5). Such compounds with both fast and slow half-lives are partially absorbed in organs, such as the liver, before being released from this one into the plasma, and available for clearance. Such two-phase decay equation was expected, and previously reported by Zheng and collaborators with pegylated AuNCs (18). One should note that the Pegylated AuNC from this group was \approx 5.5 nm size, but possesses very long half-lives of 56 minutes and 9 hours. Their pegylated AuNCs were also retained in the kidneys around 10% of ID/g until 48 h post injection. In our case, the density of the peg should be higher, leading to more extended structure of the peg around the gold core, leading to the increase of the final size of the AuNC. However, in our case, the AuPegCOOH are well eliminated from the kidneys, and the blood. The dose-normalized AUC indicated a strong enhancement of the bio-availability of the AuNCs stabilized by organic ligands, with an increased by a factor 4 to 6.7 for the pegylated, and 10.8 for the zwitterionic ligand, respectively, as compared to Au₂₅SG₁₈. Such increased availability should favor the amount of AuNCs reaching the tumor region.

In the perspective of image-guided surgery, the imaging properties of these AuNCs were determined, in terms of Tumor/Skin ratios. This investigation was necessary for the selection of the best AuNCs, able to reach the highest Tumor/Skin imaging ratios in the context of orthotopic tumors, and for the adjustment of the surgery protocol, *i.e.* the time between the injection of the AuNC and the surgery itself, for optimized distribution. As represented in the **Figure 5**, the pegylated AuNCs presented similar behaviors, *i.e.* a rapid tumor uptake reaching a Tumor/Skin ratio value of 1.5 to 2 since the first 30 minutes post-injection (see **Figure 5B**). The zwitterionic AuZwEt₂ exhibited a stable Tumor/Skin

ratio of 1.5 from 1 to 5 hours post-injection. In view of these data, we decided to use the NCs AuPegCOOH 1:3 and the AuZwEt₂ 1:5 for the following image-guided surgery investigations; however, as both compounds presented similar results, the data were merged for these two AuNCs.

After orthotopic CAL-33 tumor engraftment, the tumors were measured and the mice were split into 2 groups: (i) control mice whose tumors were removed without any contrast agent (n = 8), (ii) mice treated with the AuNC, either AuZwEt₂ (1:5) or AuPegCOOH (1:3), before surgery (n = 15). The surgeon first removed the main tumor mass using the white light (macroscopic tumor resection), and for the group (ii), used the optical imaging as a quality control. If any fluorescent mass persisted in the cheek of the animal, the surgeon used the optical live imaging system to localize the tumor residue and to remove it (**Figure 6**). The residues removed by the optical imaging were counted, and further analyzed by histology to ensure the presence of tumor cells, and by confocal imaging to localize the AuNCs within the tissues (**Figure 6F-G**).

As shown in the **Figure 7A**, the main tumor masses macroscopically removed were almost similar in the different groups, reaching a mean value of 180 mg for the control group, *versus* 170 mg for the AuNC group. Following the surgery, the animals were monitored for tumor relapse. All the animals of the control group relapsed rapidly and were euthanized for ethical reasons within 40 days, reaching a mean survival time of 34.8 ± 5.95 days. The image-guided surgery allowed the increase of the mean survival time to 46.1 ± 24 days, corresponding to 32.8 % increase in life span (ILS) *vs.* control animals. The quality of the image-guided surgery facilitated the removal of the tumor residues for 4 mice with prolonged survival, including 3 mice (20% of the animal of the image-guided surgery group) without any local tumor recurrence until the end of the experiment on day 90. All the removed residues were analyzed by histology and revealed the presence of tumor cells (**Figure 6E**). In addition, the presence of AuNCs was observed by confocal imaging on selected residues. The AuNCs were heterogeneously distributed in the tumor mass, with a particular accumulation in some cells into small and cytoplasmic vesicles (**Figure 6F-G**).

Discussion

AuNCs with different surface chemistries were synthetized, characterized and biologically evaluated in this study. The nature of the biocompatible ligands protecting the gold metal core and their density have been tuned to construct 4 different structures that were compared to the well-defined Au₂₅SG₁₈ NCs. An increase of zwitterionic or pegylated coating on the gold core leads a photoluminescence enhancement of the AuNCs due to a more efficient energy transfer of the gold shell, and a better protection from the environment (26, 27). As expected, a thicker ligand coating on AuNCs that still remains quite small (<22 kDa) seems to enhance the interaction with cell surface, through stronger cell internalization with zwitterionic ligand and antifouling effect for charged pegylated ligand.

In this study, we confirmed the efficient renal clearance of these AuNCs as already reported for such small sized nano-objects (16, 30). In addition, their rapid renal clearance should contribute to limit their toxicity, if any. However, a small part of the AuNCs was also trapped by the liver and the spleen, as already reported by us and other teams (15, 16, 31-33). As expected, the pharmacokinetics, *i.e.* AUC slicated that smaller AuNCs as $Au_{25}SG_{18}$ were rapidly eliminated from the blood (half-life < 2 min) while the 17.5 kDa zwitterionic AuNCs could reach a half-live around 10-15 min, which is 2 times longer than other zwitterionic AuNCs recently reported (12, 15). One should note the pegylated AuNCs were cleared from the blood stream by a two-phase decay kinetics, with a first fast clearance (<1 min). In absence of specific targeting ligand at the surface of the AuNC, the NCs are weakly internalized in monolayer cell cultures. *In vivo*, they are able to reach the tumor site after intravenous

administration, and furthermore are internalized inside the tumor cells, into small vesicles as demonstrated by fluorescent confocal imaging (Figure 6).

The optical properties of the AuNCs are due to their ultra-small size, and the nature of the coating ligand (21, 34, 35). Such properties might be tuned to be helpful for medical applications, in particular for image-guided surgery. In HNSCC, margin delineation impacts tumor recurrence and patients' quality of life (preservation of vital structures as nerves, swallowing and speech functions) (36). In this study, the AuNCs allowed to identify small remaining tumor lesions, after surgical tumor removal. However, in the NIR optical window, some parts of the cheek as the tendons are autofluorescent. Therefore, the optimization of the fluorescence quantum yield would facilitate the detection of the residues *versus* the nerves and tendons. In this study, both the two types of AuNCs selected showed a tumor-to-healthy tissue ratio >1.5 within the first hour after administration allowing a rapid, and prolonged tumor detection. The image-guided surgery was helpful for half of the mice (53% of the animals), allowing the detection and removal of undetected tumor residues. Such strategy increased the mean survival time of the animals of 32.8% as compared to the control group. However, improvement of the fluorescent quantum yield leading to higher sensitivity of detection, and tumor accumulation.

To conclude, the protection of the gold core by small biocompatible ligands as zwitterionic or pegylated moieties helped to improve the optical properties of the AuNCs, and to prolong their plasma half-life while conserving their renal elimination. One of the major interests of AuNCs is their multiple uses for both optical imaging, enhanced radiation therapy (13, 33), similarly to larger Au nanoparticles, or photothermal therapy (37, 38). The combination of image-guided surgery with a curative modality could reinforce the treatment efficacy. Such combining modalities would be of great interest in the next development of the AuNCs for the therapeutic care of Head and Neck pathologies. A particular interest would be the development of SWIR emitted AuNCs with good quantum yield for better tumor to healthy tissue ratios.

Acknowledgements

We acknowledge the Rhône-Alpes Auvergne region for the financial support CLARA-Oncostarter (CVPPRCAN000162) and ARC (RAC17012CCA).

Disclosure

The authors declare no conflicts of interest.

Captions

Table 1: Main physicochemical characteristics of the AuNCs. The Zeta-potential was measured at pH 7, and the maximum emission was obtained for any excitation from 350 to 600 nm. *: The quantum yield as determined at the maximum emission wavelength using QD705 as reference. ^{a)} The average charge state $Z_{average}$, is calculated from the observed charge state distribution in ESI-MS spectra (plotted in m/z) using the formula: $Z_{average} = \frac{\sum N_i z_i}{\sum N_i}$ where N_i corresponds to the number of ions of charge state z_i (25).

Figure 1: Cell viability assay performed 72-hours after incubation with the NCs at 50 and 100 μ g gold/mL on HNSCC CAL-33 (A), and SQ20B (B). Staurosporine was used as a cell-death inducer (red control diagram). Results are expressed as the mean of cell viability (% vs. control) ± standard deviation (SD).

Figure 2: NCs' uptake in CAL-33 cells after 8 hours of NCs exposure at 50 μ g/mL. (A-C): Smooth histograms of the cells normalized to the control condition. The positive cells were gated with the marker M1, assuming that less than 1% of the control cells induce autofluorescence signal. The percentage of isolated cells positively stained for the NCs is presented in the table (D).

Figure 3: Distribution of the different AuNCs, 5 hours after intravenous administration in micebearing sub-cutaneous CAL-33 tumor. The results are expressed as the mean of the fluorescence intensity/pixel/100 ms of 3 mice/group, and the error bar represents the SD.

Figure 4: Blood PK of selected NCs after intravenous injection. The NCs concentrations were determined from the fluorescence intensity values of the plasmas collected just after the injection, and at 5, 10, 15, 30, 60, and 120 min, for AuZwEt₂ (1:5) (A), AuPegCOOH (1:3) (B), AuPegCOOH (1:5) (C), and Au₂₅SG₁₈ (D). Two PKs parameters are summarized in the table (E). DN AUC_{0-end}* corresponds to the area under the curve taken from the injection time to the end of blood plasma sampling, normalized to the dose of 1 mg of gold. DN AUC_{0-end}* is expressed as min*mg/mL. T_{1/2} is the blood plasma half-life expressed in minutes. The AuNCs were best fitted with two-phase decay equation, generating a fast and a slow half-lives (see also Table S2 with goodness of fit).

Figure 5: Kinetic of the tumor-to-skin ratios obtained from the optical analysis. (A): The Tumor/Skin ratios were measured at 0.5, 1, 2.5, and 5 hours post injection in mice-bearing orthotopic CAL-33 tumors. The Tumor/Skin ratios are expressed as the mean of the fluorescent ratios normalized to T=0 \pm SD (n=3/group). (B): Example of pictures obtained after administration of AuPegCOOH (1:3).

Figure 6: Illustration of the image-guided surgery principle. The mouse was injected with AuPegCOOH (1:3) 30 minutes before the fluorescence imaging (A). Then, the main tumor mass was removed (B), and the animal was imaged to check the presence of any tumor residue. In (C), the naturally fluorescent tendon is clearly seen (white arrow), and a tumor residue is also observed (yellow arrow, and (D). This residue presents tumor cells (yellow arrows). (E) Histology image of a

representative removed residue. The yellow arrows indicate the tumor areas. Confocal microscopy confirmed the presence of AuNCs in the outer (F) and in the center (G) of the tumor residue. Scale bar: $10 \ \mu m$.

Figure 7: Image-guided surgery and animal survival. (A): The animals were split in 2 groups: without (control) and with image-guided surgery (AuNCs). The tumors were macroscopically removed and weighted. The results are presented as a box-plot with the median value in red. (B): Animal survival for control and AuNCs groups. (C): The survival time of the animals is expressed as the mean \pm the standard deviation in days, but also as the median survival time (MeST). The increase in life-span (ILS) is expressed as the percentage *versus* the life-span of control group. The number of mice with image-guided tumor residue removal is indicated, as the percentage of tumor positive residues.

References

1. Iseli TA, Lin MJ, Tsui A, Guiney A, Wiesenfeld D, Iseli CE. Are wider surgical margins needed for early oral tongue cancer? J Laryngol Otol. 2012;126(3):289-94.

2. van Driel PB, van der Vorst JR, Verbeek FP, Oliveira S, Snoeks TJ, Keereweer S, et al. Intraoperative fluorescence delineation of head and neck cancer with a fluorescent anti-epidermal growth factor receptor nanobody. Int J Cancer. 2014;134(11):2663-73.

3. Rosenthal EL, Warram JM, de Boer E, Chung TK, Korb ML, Brandwein-Gensler M, et al. Safety and Tumor Specificity of Cetuximab-IRDye800 for Surgical Navigation in Head and Neck Cancer. Clin Cancer Res. 2015;21(16):3658-66.

4. van den Berg NS, Miwa M, KleinJan GH, Sato T, Maeda Y, van Akkooi AC, et al. (Near-Infrared) Fluorescence-Guided Surgery Under Ambient Light Conditions: A Next Step to Embedment of the Technology in Clinical Routine. Ann Surg Oncol. 2016;23(8):2586-95.

5. Atallah I, Milet C, Coll JL, Reyt E, Righini CA, Hurbin A. Role of near-infrared fluorescence imaging in head and neck cancer surgery: from animal models to humans. Eur Arch Otorhinolaryngol. 2015;272(10):2593-600.

6. Atallah I, Milet C, Quatre R, Henry M, Reyt E, Coll JL, et al. Role of near-infrared fluorescence imaging in the resection of metastatic lymph nodes in an optimized orthotopic animal model of HNSCC. Eur Ann Otorhinolaryngol Head Neck Dis. 2015;132(6):337-42.

7. Atallah I, Milet C, Henry M, Josserand V, Reyt E, Coll JL, et al. Near-infrared fluorescence imaging-guided surgery improves recurrence-free survival rate in novel orthotopic animal model of head and neck squamous cell carcinoma. Head Neck. 2016;38 Suppl 1:E246-55.

8. de Boer E, Warram JM, Tucker MD, Hartman YE, Moore LS, de Jong JS, et al. In Vivo Fluorescence Immunohistochemistry: Localization of Fluorescently Labeled Cetuximab in Squamous Cell Carcinomas. Sci Rep. 2015;5:10169.

9. Prabhu RS, Hanasoge S, Magliocca KR, Hall WA, Chen SA, Higgins KA, et al. Lymph node ratio influence on risk of head and neck cancer locoregional recurrence after initial surgical resection: implications for adjuvant therapy. Head Neck. 2015;37(6):777-82.

10. Moore LS, Rosenthal EL, Chung TK, de Boer E, Patel N, Prince AC, et al. Characterizing the Utility and Limitations of Repurposing an Open-Field Optical Imaging Device for Fluorescence-Guided Surgery in Head and Neck Cancer Patients. J Nucl Med. 2017;58(2):246-51.

11. Yu M, Zheng J. Clearance Pathways and Tumor Targeting of Imaging Nanoparticles. ACS Nano. 2015;9(7):6655-74.

12. Yu M, Zhou C, Liu L, Zhang S, Sun S, Hankins JD, et al. Interactions of Renal-Clearable Gold Nanoparticles with Tumor Microenvironments: Vasculature and Acidity Effects. Angew Chem Int Ed Engl. 2017;56(15):4314-9.

13. Zhang XD, Luo Z, Chen J, Song S, Yuan X, Shen X, et al. Ultrasmall glutathione-protected gold nanoclusters as next generation radiotherapy sensitizers with high tumor uptake and high renal clearance. Sci Rep. 2015;5:8669.

14. Chen Y, Montana DM, Wei H, Cordero JM, Schneider M, Le Guevel X, et al. Shortwave Infrared in Vivo Imaging with Gold Nanoclusters. Nano Lett. 2017;17(10):6330-4.

15. Shen D, Henry M, Trouillet V, Comby-Zerbino C, Bertorelle F, Sancey L, et al. Zwitterion functionalized gold nanoclusters for multimodal near infrared fluorescence and photoacoustic imaging. APL Materials. 2017;5:053404.

16. Le Guevel X, Henry M, Motto-Ros V, Longo E, Montanez M, Pelascini F, et al. Elemental and optical imaging evaluation of zwitterionic gold nanoclusters in glioblastoma mouse models. Nanoscale. 2018;10(39):18657-64.

17. Du B, Jiang X, Das A, Zhou Q, Yu M, Jin R, et al. Glomerular barrier behaves as an atomically precise bandpass filter in a sub-nanometre regime. Nat Nanotechnol. 2017;12(11):1096-102.

18. Liu J, Yu M, Ning X, Zhou C, Yang S, Zheng J. PEGylation and zwitterionization: pros and cons in the renal clearance and tumor targeting of near-IR-emitting gold nanoparticles. Angew Chem Int Ed Engl. 2013;52(48):12572-6.

19. Fernandez TD, Pearson JR, Leal MP, Torres MJ, Blanca M, Mayorga C, et al. Intracellular accumulation and immunological properties of fluorescent gold nanoclusters in human dendritic cells. Biomaterials. 2015;43:1-12.

20. Mei BC, Susumu K, Medintz IL, Mattoussi H. Polyethylene glycol-based bidentate ligands to enhance quantum dot and gold nanoparticle stability in biological media. Nat Protoc. 2009;4(3):412-23.

21. Porret E, Sancey L, Martin-Serrano A, Montanez M, Seeman R, Yahia-Ammar A, et al. Hydrophobicity of Gold Nanoclusters Influences Their Interactions with Biological Barriers. Chem Mater. 2017;29(17):7497-506.

22. Shibu ES, Muhammed AH, Tsukuda T, Pradeep T. Ligand exchange of Au25SG18 leading to functionalized gold clusters: Spectroscopy, kinetics, and luminescence. J Phys Chem C. 2008;112:12168-76.

23. Waszkielewicz M, Olesiak-Banska J, Comby-Zerbino C, Bertorelle F, Dagany X, Bansal AK, et al. pH-Induced transformation of ligated Au25 to brighter Au23 nanoclusters. Nanoscale. 2018;10(24):11335-41.

24. Truillet C, Lux F, Tillement O, Dugourd P, Antoine R. Coupling of HPLC with electrospray ionization mass spectrometry for studying the aging of ultrasmall multifunctional gadolinium-based silica nanoparticles. Anal Chem. 2013;85(21):10440-7.

25. Girod M, Antoine R, Dugourd P, Love C, Mordehai A, Stafford G. Basic vapor exposure for tuning the charge state distribution of proteins in negative electrospray ionization: elucidation of mechanisms by fluorescence spectroscopy. J Am Soc Mass Spectrom. 2012;23(7):1221-31.

26. Le Guevel X, Tagit O, Rodriguez CE, Trouillet V, Pernia Leal M, Hildebrandt N. Ligand effect on the size, valence state and red/near infrared photoluminescence of bidentate thiol gold nanoclusters. Nanoscale. 2014;6(14):8091-9.

27. Pyo K, Thanthirige VD, Kwak K, Pandurangan P, Ramakrishna G, Lee D. Ultrabright Luminescence from Gold Nanoclusters: Rigidifying the Au(I)-Thiolate Shell. J Am Chem Soc. 2015;137(25):8244-50.

28. Wu Z, Jin R. On the ligand's role in the fluorescence of gold nanoclusters. Nano Lett. 2010;10(7):2568-73.

29. Lee S, Tong X, Yang F. Effects of the poly(ethylene glycol) hydrogel crosslinking mechanism on protein release. Biomater Sci. 2016;4(3):405-11.

30. Zhang XD, Wu D, Shen X, Liu PX, Fan FY, Fan SJ. In vivo renal clearance, biodistribution, toxicity of gold nanoclusters. Biomaterials. 2012;33(18):4628-38.

31. Chen F, Goel S, Hernandez R, Graves SA, Shi S, Nickles RJ, et al. Dynamic Positron Emission Tomography Imaging of Renal Clearable Gold Nanoparticles. Small. 2016;12(20):2775-82.

32. Ning X, Peng C, Li E, Xu J, Vinluan R, Yu M, et al. Physiological stability and renal clearance of ultrasmall zwitterionic gold nanoparticles: Ligand length matters. APL Materials. 2017;5(5):053406.

33. Zhang XD, Chen J, Luo Z, Wu D, Shen X, Song SS, et al. Enhanced tumor accumulation of sub-2 nm gold nanoclusters for cancer radiation therapy. Adv Healthc Mater. 2014;3(1):133-41.

34. Jin R, Zeng C, Zhou M, Chen Y. Atomically Precise Colloidal Metal Nanoclusters and Nanoparticles: Fundamentals and Opportunities. Chem Rev. 2016;116(18):10346-413.

35. Zhang L, Wang E. Metal nanoclusters: New fluorescent probes for sensors and bioimaging. Nano Today. 2014;9:132-57.

36. Liao CT, Chang JT, Wang HM, Ng SH, Hsueh C, Lee LY, et al. Analysis of risk factors of predictive local tumor control in oral cavity cancer. Ann Surg Oncol. 2008;15(3):915-22.

37. Gamaleia NF, Shton IO. Gold mining for PDT: Great expectations from tiny nanoparticles. Photodiagnosis Photodyn Ther. 2015;12(2):221-31.

38. Gao X, Yue Q, Liu Z, Ke M, Zhou X, Li S, et al. Guiding Brain-Tumor Surgery via Blood-Brain-Barrier-Permeable Gold Nanoprobes with Acid-Triggered MRI/SERRS Signals. Adv Mater. 2017;29(21).

AuNC	Size by DLS (nm)	Size by ESI-MS (kDa)	Z _{average} a)	Density (kg/m³)	Zeta potential (mV) at pH7	λ _{em.} (nm)	QY (%)*
AuZwEt ₂ 1:2	3.1±0.7	14.5	3.5	1543.4	-18.0±0.5	780	5.7
AuZwEt ₂ 1:5	8.6±1.1	17.5	3.5	87.2	-18.0±0.2	720	7.1
AuPegCOOH 1:3	7.2±1.6	8-10	5	76.4	-31.4±1.0	780	8.0
AuPegCOOH 1:5	10.5±2.4	20-24	7.5	60.2	-35.5±2.5	720	9.0
Au ₂₅ GSH ₁₈	1.4±0.2	10.4	-	-	-32.0±2.5	800	0.5





Condition	Auto-fluo	AuZwEt ₂ (1:2)	AuZwEt ₂ (1:5)	AuPegCOOH (1:3)	AuPegCOOH (1:5)	$\mathrm{Au}_{25}\mathrm{SG}_{18}$	
Positive cells (%)	0.99	2.69	38.33	16.97	1.52	1.40	





А







Figure7 Click here to download high resolution image



	n	Survival time (Days)		
Condition		Mean +/- SD	MeST	
Control mice (macroscopic tumor resection)	8	34.8 ± 5.95	34	
-	-	÷		

Condition	n	Survival time (Days)		ILS vs.	Nb of	% of tumor-	
		Mean +/- SD	MeST	control	removed residues	residue	
Control mice (macroscopic tumor resection)	8	34.8 ± 5.95	34	-	<u></u>	5 <u>4</u> /	
AuNCs mice (image- guided surgery)	15	46.1 ± 24	39	32.8 %	8/15	100	

С

Supplementary Material Click here to download Supplementary Material: Supplementary information.pdf