

# Surface modifications at the oxide/water interface: implications for Cu binding, solution chemistry and chemical stability of iron oxide nanoparticles

Edwige Demangeat, Mathieu Pédrot, Aline Dia, Martine Bouhnik-Le Coz, Mélanie Davranche, Francisco Cabello-Hurtado

# ▶ To cite this version:

Edwige Demangeat, Mathieu Pédrot, Aline Dia, Martine Bouhnik-Le Coz, Mélanie Davranche, et al.. Surface modifications at the oxide/water interface: implications for Cu binding, solution chemistry and chemical stability of iron oxide nanoparticles. Environmental Pollution, 2020, 257, pp.113626. 10.1016/j.envpol.2019.113626 . hal-02359506

# HAL Id: hal-02359506 https://hal.science/hal-02359506

Submitted on 17 Sep 2020

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

1	Surface modifications at the oxide/water interface: implications for Cu
2	binding, solution chemistry and chemical stability of iron oxide
3	nanoparticles
4	Edwige Demangeat <sup>a</sup> , Mathieu Pédrot <sup>a,*</sup> , Aline Dia <sup>a</sup> , Martine Bouhnik-Le-Coz <sup>a</sup> , Mélanie Davranche <sup>a</sup>
5	and Francisco Cabello-Hurtado <sup>b</sup>
6 7	<sup>a</sup> Univ. Rennes, CNRS, Géosciences Rennes - UMR 6118, 35000 Rennes, France <sup>b</sup> Univ. Rennes, CNRS, Ecobio - UMR 6553, 35000 Rennes, France

# 8 Abstract

9 The oxidation of magnetite into magnemite and its coating by natural organic constituents are 10 common changes that affect the reactivity of iron oxide nanoparticles (IONP) in aqueous environments. Certain ubiquitous compounds such as humic acids (HA) and phosphatidylcholine 11 (PC), displaying a high affinity for both copper (Cu) and IONP, could play a critical role in the 12 interactions involved between both compounds. The adsorption of Cu onto four different IONP 13 was studied: magnetite nanoparticles (magnNP), maghemite NP (maghNP), HA- and PC-coated 14 15 magnetite NP (HA-magnNP and PC-magnNP, respectively). According to the results, the percentage of adsorbed Cu increases with increasing pH, irrespective of the IONP. Thus, 16 protonation/deprotonation reactions are likely involved within Cu adsorption mechanism. 17 Contrary to the other studied IONP, HA-magnNP favor Cu adsorption at most of the pH tested 18 including acidic pH (pH = 3), suggesting that part of the active surface sites for  $Cu^{2+}$  were not 19 20 grabbed by protons. The Freundlich adsorption isotherm of HA-magnNP provides the highest sorption constant K<sub>F</sub> (bonding energy) and n value which supports a heterogeneous sorption 21 process. The heterogeneous adsorption between HA-magnNP and  $Cu^{2+}$  can be explained by both 22 the diversity of the binding sites HA procured and the formation of multidendate complexes 23 between Cu<sup>2+</sup> and some of the HA functional groups. Such favorable adsorption process was 24 25 neither observed on PC-coated-magnNP nor on maghNP, whose behaviors were comparable to that of magnNP. On another hand, HA and PC coatings considerably reduced iron (Fe) 26 27 dissolution from magnNP as compared with magnNP. It was suggested that HA and PC coatings either provided efficient shield against Fe leaching or fostered dissolved Fe re-adsorption onto the 28 functional groups at the coated magnNP surfaces. Thus, this study can help to better understand 29

the complex interfacial reactions between cations-organic matter-colloidal surfaces which arerelevant in environmental and agricultural contexts.

This work showed that magnetite NP properties can be affected by surface modifications, which
 drive NP chemical stability and Cu adsorption, thereby affecting the global water chemistry.

*Keywords:* magnetite oxidation, surface coating, humic acid, phosphatidylcholine, copper
 adsorption, copper speciation

36 \* Corresponding author: <u>mathieu.pedrot@univ-rennes1.fr</u> Phone (+33)2 23 2360 83

#### 37 Declarations of interest: none

#### 38 **1. Introduction**

39 For almost two decades, engineered nanoparticles (NP), one of many nanomaterials, have been revolutionary tools to human kind. Due to their nano-scale size, NP displays a high surface to 40 volume ratio which provides them with promising properties in many areas (Gupta and Gupta, 41 2005, Afkhami et al, 2010, Dabrowski et al., 2004). More specifically, engineered iron oxide NP 42 43 (IONP) display high reactivity, magnetic properties and biocompatibility that allow their use in many technical applications. Examples of these uses range from medical therapies (Wu et al., 44 45 2015, Karimi et al., 2013), imaging and recording technologies to remediation methods and 46 agricultural practices (Sabbatini et al., 2010, Khot et al., 2012). The application of iron 47 nanoparticles (IONP) for soils and water remediation, in particular, has been explored for a few decades and several studies have highlighted the affinity of metals and metalloids for these 48 49 objects (Wang et al., 2012, Ahmed et al., 2013, Pan et al., 2010).

50 Sorption reactions with both organic and inorganic compounds play a key role in the transport and fate of many trace elements in natural systems (Ye et al., 2017). Binding of metals 51 52 on oxide minerals, in particular, involves predominantly electrostatic interaction (non-specific 53 sorption) or chemical interaction (specific sorption) (Smith, 1999). According to Hu et al., (2006), metal ion sorption onto magnetite has been shown to involve both electrostatic attraction 54 and ligand exchange at various pH conditions. In aqueous environments, IONP are amphoteric 55 solids that become charged in response to the (de)protonation reactions of the Fe-OH surface 56 sites (Pang et al., 2007). Consequently, dissolved cationic species are attracted to IONP at pH 57 values higher than their pHzpc (point of zero charge), where the surfaces of the IONP are 58

negatively charged. In fact, the mechanisms responsible for IONP and metal interactions are 59 dependent upon several geochemical parameters such as pH, ionic strength, temperature and soil 60 solution chemistry including the initial metal concentration and the adsorbent (IONP) 61 concentration (Stumm, 1992; Smith, 1999). To take into account the role of these parameters and 62 describe the resulting binding mechanisms of cations (or protons) onto oxide mineral surfaces, 63 surface complexation models are implemented based on similar principles (sorption of ions 64 occurs at specific coordination sites; sorption equations are described by mass law equations; 65 sorption of ions control solid surface charge; electrostatic effects on ions binding are considered) 66 (Smith, 1999). 67

The physico-chemical properties of IONP also do play a key role in cation adsorption 68 69 processes (Parkinson, 2016). These intrinsic properties are likely modified when IONP are 70 released in natural environments because of the numerous transformations that IONP undergo 71 and the interactions that occur with natural constituents and living organisms (Joo and Zhao, 2017, Amde et al., 2017). Phase transformations, affecting the whole mineral structure, can stem 72 73 from dissolution, precipitation, oxidation-reduction reactions, photochemical transformations or other internal structural changes (Tang and Lo, 2013, Löhr et al., 2017). In addition, co-74 75 precipitation, sorption and certain biotransformations can also affect the interactions occurring at the surfaces of the IONP and thus modify their reactivity as well as the behavior of some 76 77 constituents, such as metal speciation (Nowack and Bucheli, 2007).

78 Once released into the ecosystems, IONP may be coated with organic substances due to the pervasiveness of these compounds in natural areas (Tang et al., 2014). As part of the 79 80 dissolved organic matter, humic acids (HA), consist of a complex, heterogeneous arrangement of high- to low-molecular weight species exhibiting different water solubilities and reactivities. 81 Hence, HA displays a high affinity for magnetite, and the adsorption of HA onto magnetite NP 82 has been proven to largely impact the physicochemical properties of iron oxides such as their 83 colloidal stability (Illés and Tombacz, 2006, Ghosh et al., 2011, Hadju et al., 2009, Grillo et al., 84 2015, Tombacz et al., 2013, Demangeat et al., 2018) and also, their interactions with soil solution 85 86 species including several metals (Vindedahl et al., 2016, Davranche et al., 2013, Yu et al., 2018). Indeed, HA contain metal-binding functional groups (such as carboxylates, phenols, amines, 87 thiols) with binding affinities and ligand densities that range several orders of magnitude. 88 Phospholipids, another ubiquitous family of compounds, are also commonly found in natural 89

waters. Phosphatidylcholine (PC), in particular, is a major component of living organisms and it 90 91 is largely employed in the agro-industry (Brown et al., 1999). Therefore, it is expected that phosphatidylcholine can cover the surfaces of the IONP in surface waters and possibly, interfere 92 in the interactions between the metals and the IONP (Debnath et al., 2010). PC likely form lipid 93 bilayers onto mineral surfaces in aqueous mediums because of their amphiphilic character and 94 they can form various structures depending on the properties of these molecules (Mulder et al., 95 96 2006, Giri et al., 2005). Therefore, PC coating can impact the surface structure of the IONP and the ensuing interactions between the coated surface and metal ions mainly via electrostatic 97 interactions (Solis-Calero et al., 2015). In addition to surface coatings, magnetite is also 98 chemically unstable. The oxidation of magnetite NP into maghemite NP likely induces structural 99 100 and chemical changes which are of great concern towards contaminant interactions, including metal adsorption (Frison et al., 2013, Gorski et al., 2010, Hu et al., 2005). 101

102 IONP interactions with metals are relevant towards many applications because of the ensuing environmental and societal impacts (Kah, 2015). Many studies have focused on the 103 104 adsorption capacity between some IONP and certain metals with the aim to investigate the potential of some new depollution means or to precise the limits of such environmental 105 106 applications. However, although the effects related to the properties of the medium are often investigated to decipher the adsorption process itself, their impacts on the behavior and fate of 107 108 IONP are frequently neglected despite their relevance towards several other mechanisms (such as, NP dissolution, metal co-precipitation, etc.). Besides, much interest should be given to the 109 110 interactions between IONP and copper (Cu) since these compounds are of increasing concern in various sectors whether it is for industrial, agricultural or environmental purposes (Li et al., 2016, 111 Adrees et al., 2015). Significant quantities of iron (in the form of IONP) along with dissolved 112 113 copper are released into the acidic waters coming from mining wastes and acid mine drainage (Mohan et al., 2006, Otero-Farina et al., 2015). Besides, the use of pesticides, fungicides, 114 wastewater irrigation and other industrial effluents (related to petroleum refining, electroplating, 115 foundries) also result in high concentrations of copper in soils and waters (Mohan et al., 2006; 116 117 Adrees et al., 2015). In these mediums, toxic level of Cu most often hampers sustainable agriculture as well as food and health safety (Adrees et al., 2015). In this frame, several studies 118 have shown the potential of IONP to remove  $Cu^{2+}$  from aqueous solutions as well as the effects 119 of HA coating onto magnetite nanoparticles reactivity (Christl and Kretzschmar, 2001; Liu et al., 120

2008). However, the impacts of IONP/Cu interactions on the nanoparticle stability and on the
solution chemistry (especially Cu speciation) still raise a number of questions that are rarely
tackled.

In the present study, the adsorption capacity of four different IONP was investigated 124 using increasing amounts of Cu. The IONP included magnetite NP (magnNP), its oxidized form 125 maghemite (maghNP), magnetite NP coated with humic acid (HA-magnNP) and magnetite NP 126 coated with phosphatidylcholine (PC-magnNP). Thus, the scenario tested in this study is intended 127 to: (i) identify the physico-chemical modifications induced by oxidation and by two different 128 129 surface coatings on magnNP, (ii) decipher how these modifications are involved regards to magnNP chemical stability (dissolution rate), (iii) and how they can drive Cu adsorption at the 130 131 surface of the IONP, and, (iv) provide insights into the relationships that possibly exist between IONP dissolution, IONP reactivity and their colloidal stability. 132

133

# 134 **2. Materials and methods**

- 135 **2.1. IONP**
- 136

#### 2.1.1. Synthesis procedures

Magnetite (Fe<sub>3</sub>O<sub>4</sub>) NP were synthesized following the method of Khalafalla and Reimers (1980)
and Massart (1981) using FeCl<sub>2</sub>.4H<sub>2</sub>O and FeCl<sub>3</sub>.6H<sub>2</sub>O salts.

139 **Maghemite**  $(\gamma - Fe_2O_3)$  NP were prepared based on the method of Zasonska et al. (2016), by 140 oxidizing the magnetite nanoparticles.

- Coatings of magnetite NP were performed using HA (Elliott Soil Humic Acid Standard IV IHSS) and PC (1, 2-bis (10, 12-tricosadiynoyl)-sn-glycero-3-phosphocholine Avanti Polar
  Lipid, CAS Registry Number: 76078-28-9).
- 144 A precise description of the synthesis procedures of IONP is located in the Supporting145 Information file (SI-A).
- 146 **2.1.2. Characterization**

High Resolution Transmission Electron Microscopy (HR-TEM) was conducted with a
JEOL2100F electron microscope (voltage 200 kV) magnNP, maghNP, HA-magnNP and PCmagnNP.

Multipoint N<sub>2</sub>–Brunauer Emmett Teller (BET) technique was carried out on magnNP and maghNP using a Coulter (SA 3100) analyzer to measure the surface area of the IONP. BET analyses were not performed on HA- and PC- magnNP because the coated molecules were shown to contain highly narrow microporosity, which adsorbs no N<sub>2</sub> at 77K (Liu et al., 2008, Fu et al., 2015).

Attenuated Total Reflectance-Fourier Transform InfraRed (ATR-FTIR) was performed on
 magnNP, maghNP, HA-magnNP and PC-magnNP samples in the 650 - 3700 cm<sup>-1</sup> region using
 an IS50 Nicolet spectrometer.

158

Fe(II)/Fe(III) ratio of magnNP and maghNP were determined by the measure of dissolved Fe(II)
and Fe(III) concentrations, after acid digestion, using the 1.10 phenanthroline colorimetric
method (AFNOR NF T90-017) (Komadel and Stucki, 1988).

162 The pH-dependent **surface charge**  $(\mathbf{pH}_{zpc})$  of magnetite was determined by potentiometric acid-163 base titration using a self-developed titration system with two titrators (794 Basic Titrino -164 Metrohm).

165 More information about these characterization techniques can be found in the SI file (SI-A).

166

#### 2.2. Batch reactions

167 The adsorption experiments investigated the affinity of copper (Cu) for bare magnetite NP 168 (magnNP), HA coated magnetite NP (HA-magnNP), PC coated magnetite NP (PC-magnNP) and 169 maghemite NP (maghNP). Three experiments were conducted to investigate: (i) the Cu 170 adsorption kinetics, (ii) the effect of pH on the Cu adsorption capacity and (iii) the Cu adsorption 171 capacity for the four IONP studied.

172

### 2.2.1. Experimental set-up

173 Copper adsorption kinetic experiments were conducted to determine the equilibration time 174 prior to the Cu adsorption experiments, performed at different pH values and variable Cu

concentrations. The kinetic experiments were performed in triplicate for each IONP in a 0.5  $\pm$ 175 0.05 g L<sup>-1</sup> solution (400 mL) at pH = 6 with constant Cu = 0.05 mM. The solutions were shaken 176 for 48 h and for each replicate, 10 samples were collected through time. The accurate total Cu 177 and IONP concentrations were controlled for each experiment. Major- and trace-element 178 concentrations were determined by ICP-MS (Agilent 7700x) as described in Demangeat et al. 179 (2018) and using SLRS-5 geostandard (Yéghicheyan et al., 2013). Other aliquots were filtered 180 using ultrafiltration units (2 kDa, cellulose nitrate membranes) and the TE concentrations of the 181 filtrate were determined as the dissolved fractions. Thus, dissolved Cu (< 2 kDa) was considered 182 183 as non-adsorbed Cu and dissolved Fe was monitored to highlight possible Fe dissolution, which was expected to occur at acidic pH. The results showed that equilibration was achieved within 15 184 185 min. All of the following experiments, which lasted several hours, were therefore performed at equilibrium. 186

To investigate the effect of pH on the Cu adsorption capacity of the IONP, the initial Cu 187 concentration was set at 0.05 mM by diluting a 250 mg L<sup>-1</sup> Cu stock solution in tubes containing 188 20 mL of 0.5 g L<sup>-1</sup> IONP suspension. The pH was adjusted using 0.1 M NaOH or HCl to reach 189 the targeted pH (pH 3, 4, 5, 6 and 7). In the last experiment, Cu was added to 20 mL of 0.5 g L<sup>-1</sup> 190 191 IONP suspension in appropriate amounts to obtain concentrations of Cu = 0.5 mM, Cu = 0.1 mM, Cu = 0.05 mM, Cu = 0.01 mM and Cu = 0.005 mM. The pH was adjusted to pH =  $6 \pm 0.1$  using 192 193 0.1 M NaOH. Experiments were performed in triplicate for each IONP. After shaking under anaerobic conditions for 18 h, each sample was split into two aliquots to perform the total and 194 195 dissolved ICP-MS analyses, as previously described.

196

#### 2.2.2. Adsorption studies

197 The amount of adsorbed Cu on the four investigated IONP was calculated according to198 the following equation:

199 Removal efficiency (%) =  $C_0 - C_e / C_0 * 100$  (1)

where  $C_0 \text{ (mg } L^{-1})$  and  $C_e \text{ (mg } L^{-1})$  are the initial dissolved Cu concentrations and dissolved concentrations of metal ions after adsorption, respectively. The equilibrium adsorption capacity,  $Q_e \text{ (mg } g^{-1})$  represents the adsorbed Cu per g of IONP and was calculated using the following mass balance equation: 204  $Q_e = (C_0 - C_e) V/m$  (2)

where V (L) is the sample volume, and m (g) is the mass of adsorbent.

To parameterize the adsorption behavior of  $Cu^{2+}$  onto the IONP, the Langmuir and 206 Freundlich isotherms were employed. Several mathematical models exist to describe the 207 adsorption of molecules and diverse materials onto solid surfaces, and the choice depends on the 208 209 characteristics of the studied system (Sheng et al., 2010). Langmuir and Freundlich models are commonly used to describe metal ion adsorption equilibrium onto mineral surfaces (Sheng et al., 210 211 2010, Panneerselvam et al., 2011, Mamindy-Pajany et al., 2011). The Langmuir model is adapted to describe dynamic equilibrium adsorption processes, assuming that uptake of metal ions occurs 212 213 on a homogeneous surface by monolayer adsorption and that no interaction exists between the sorbed species. The Langmuir equation is expressed as: 214

215 
$$C_e/Q_e = 1/(Q^\circ.b) + C_e/Q^\circ$$
 (3)

where  $C_e$  is the concentration of the solute at equilibrium (mg L<sup>-1</sup>),  $Q_e$  is the mass of the contaminant adsorbed per unit weight of the adsorbent (mg g<sup>-1</sup>),  $Q^{\circ}$  (mg g<sup>-1</sup>) and b (L mg<sup>-1</sup>) are constants related to the adsorption capacity and energy of adsorption, respectively.

The Freundlich isotherm describes non-ideal and reversible adsorption. It is commonly used for adsorbents having irregular surface or for single solute systems within a define concentration range (Shaker and Albishri, 2014). The model assumes multilayer adsorption, meaning that different adsorption sites with different adsorption energy exist at the surface of the solid, characterized by non-uniform distribution of adsorption heat and affinities over a heterogeneous surface (Sigg et al, 2011). The Freundlich isotherm is represented as follows:

225 
$$Q_e = K_F \times [C_e]^{1/n}$$
 (4)

where  $C_e$  is the concentration of the solute at equilibrium (mg L<sup>-1</sup>),  $Q_e$  is the mass of the contaminant adsorbed per unit weight of the adsorbent (mg g<sup>-1</sup>), K<sub>F</sub> and n are Freundlich constants which relate to the adsorption capacity and to the degree of dependence of adsorption at equilibrium concentration, respectively. When it is expressed in the logarithmic form, Equation (4) gives:

231 
$$\log Q_e = \log K_F + (1/n) \log C_e$$
 (5)

The adsorption data were plotted according to Equation (3) (Langmuir model) and (5) 232 233 (Freundlich model) using the Cu concentrations obtained in triplicates in the last experiment. The adsorbent concentrations in the solutions were equal to 0.5 g  $L^{-1}$  and the pH was adjusted to pH = 234 235 6.

236

# 2.3. Cu speciation

237 Copper speciation in the presence of IONP was investigated using Visual Minteq 3.1. In particular, the concentration of the different Cu species was calculated relative to the pH in our 238 experimental conditions (21 °C, 0.005 M NaCl). The model considered the presence of IONP 239 (0.5 g L<sup>-1</sup>) including the properties of IONP determined from the BET analyses and 240 potentiometric titration (i.e. number of adsorption sites, pKa<sub>1</sub> and pKa<sub>2</sub>). From the potentiometric 241 titration experiment conducted at NaCl = 0.005 M, we calculated pKa<sub>1</sub>=4.6 and pKa<sub>2</sub>=7.8 for 242 magnNP. For maghNP,  $pKa_1=5.4$  and  $pKa_2=9.3$  were estimated from literature considering 243 maghemite nanoparticles with similar properties as those used in this study (Jarbling et al., 2005). 244 245 The surface site density of IONP, Ns =  $1.59 \pm 0.05$  sites per nm<sup>2</sup> was calculated from potentiometric titration of magnNP based on the Granplot method (Jolstera et al., 2012, Cheng et 246 al., 2018). The obtained value is close to those found in previous works using the same method 247 248 (Jolstera et al., 2012, Cheng et al., 2018, Lucas et al., 2007). The stability constant was deduced from the best fit obtained between experimental data and modelled data at  $\log K = 0.6$ . 249

The sorption constant was fitted using the experimental datasets of the adsorption isotherm 250 251 experiments. The best fit was validated by the calculation of the RMSE. Calculations were performed at pH values ranging from 3 to 8 to obtain the concentrations of the significant Cu 252 species  $(Cu^{2+}, CuOH^+, Cu(OH)_2(aq), Cu(OH)^{3-}, Cu_3(OH)_4^{2+}, Cu(OH)_2(s))$  as well as the 253 saturation index of the possible Cu solids (Cu(OH)<sub>2</sub>(s), Tenorite). The adsorption of Cu onto HA-254 255 magnNP and PC-magnNP was not modeled because Visual Minteq3.1 considers HA and PC as 256 additional ligands instead of surface materials.

257

#### 3. Results and discussion 258

259

# 3.1. Impacts of oxidation and surface coating on magnNP

**3.1.1. IONP physicochemical properties** 260

Magnetite and maghemite. As determined from the HR-TEM analyses (SI-B), maghNP were 261 262 spherical and had a mean diameter close to  $7 \pm 2$  nm. Although the transformation of magnNP into maghNP did not show any change in size, the BET measurements highlighted an increase in 263 the surface area from  $115 \pm 4 \text{ m}^2 \text{ g}^{-1}$  before oxidation (magnNP) to  $130 \pm 4 \text{ m}^2 \text{ g}^{-1}$  after oxidation 264 (maghNP). It has further been demonstrated that maghemite has a disordered crystal structure in 265 which vacancies could favor cation scavenging (Frison et al., 2013, Gorski et al., 2010). On 266 another hand, the Fe(II)/Fe(III) ratio of magnNP in the adsorption experiment decreased from 267  $0.38 \pm 0.02$  at the beginning of the experiment to  $0.34 \pm 0.02$  after the interaction, corresponding 268 to non-stoichiometric magnetites (Schwaminger et al., 2017, Lohdia et al., 2010). The 269 270 Fe(II)/Fe(III) ratio is worth considering as it has an influence on the interactions with the 271 surrounding dissolved species, as Fe(II) likely facilitates the transfer of electrons (Auffan et al., 2008). In a previous study, we showed that after nine days Fe(II)/Fe(III) rapidly decreased to 272 Fe(II)/Fe(III) = 0.1 in aerobic conditions due to oxidation of magnetite into maghemite 273 (Demangeat et al., 2018). In the present study, the Fe(II)/Fe(III) ratio of maghNP was measured 274 275 at  $0.05 \pm 0.02$ . Besides, the pHzpc of magnNP obtained from potentiometric titration experiment gave a pHzpc=6.2 whereas the pHzpc of maghNP was determined at 7.35. 276

HA- and PC- coated magnetite. Neither HA nor PC coatings induced any significant size 277 278 change, indicating that the modifications occurred at the surface of magnNP (Fu et al., 2015, 279 Koesnarpadi et al., 2015). According to the obtained infrared spectra (SI-C), PC- and HAmagnNP have bands of pure PC and HA, respectively, as well as bare magnNP, which support 280 the successful coating of PC and HA, respectively, onto the oxide surface (Niu et al., 2011). In 281 the spectra of Fe<sub>3</sub>O<sub>4</sub>-PC, as observed in pure PC sample, the absorption bands at 2849 cm<sup>-1</sup> and 282 2940 cm<sup>-1</sup> were assigned to symmetric and asymmetric methylene (CH<sub>2</sub>) and methyl (CH<sub>3</sub>) 283 vibrations, respectively (Debnath et al., 2010). The bands at 1272 cm<sup>-1</sup>, 1088 cm<sup>-1</sup>, 970 cm<sup>-1</sup> and 284 820 cm<sup>-1</sup> were attributed to the presence of  $PO_4^{3-}$  group onto magnetite surface (Debnath et al., 285 2010), and those at 1470 cm<sup>-1</sup> and 1412 cm<sup>-1</sup> were ascribed to CH<sub>2</sub> scissoring. The anchoring of 286 PO4<sup>3-</sup> supports the successful coating of PC on magnNP surface, most likely via chemisorption, 287 which involves the covalent binding between the phosphate groups and the hydroxyl groups of 288 magnNP (Le et al., 2014). In the spectra of HA-magnNP, the band at ~1614 cm<sup>-1</sup> was attributed 289 to the sorption of carboxylates onto the magnetite surface. This absorption band likely resulted 290 from the shift, after its binding to the FeO, of the 1709 cm<sup>-1</sup> vibration band (C=O stretch of free 291

carboxylic acid) observed in pure HA spectra. The band at 1410 cm<sup>-1</sup> could be related to COO<sup>-</sup> 292 293 symmetric stretch (Demirel et al., 2006). HA is likely fractionated during its adsorption to the magnNP and it has been demonstrated that low molecular weight, -O and -N rich functional 294 groups would preferentially adsorbed onto the IONP surface. These smaller size-fractions would 295 display enhanced probability for ligand-exchange reactions (Illès and Tombacz, 2004). Indeed, 296 the binding of carboxylate with the surface hydroxyl site of iron oxide has been reported to 297 298 involve ligand exchange mechanism (Liu et al., 2008, Maity and Agrawal, 2007). The surface chemical modifications induced by HA and PC coatings to magnNP are relevant regards to the 299 300 numerous interactions occurring between IONP and the solution constituents, including metal ions. Indeed, if the same sites for binding HA and metals are used, the binding of HA directly on 301 302 mineral surface may hamper metal sorption due to the site blockage and competition. If not, the binding of HA at the IONP surface can become favorable to the uptake of metals because of the 303 304 complexation between HA and metals.

305

#### 3.1.2. Chemical stability of IONP

306 The increased Fe concentrations (dissolved Fe measurements) highlighted the preferential dissolution of magnNP at acidic pH (Table 1). After 18 hours, dissolved Fe accounted for 1.5% 307 of the total Fe content in magnNP at pH = 3 and it decreased to 0.4% when the pH increased to 308 pH = 4. These values fall in the range of previously reported dissolved Fe concentrations in close 309 experimental conditions (Missana et al., 2009). However, the time of the experiment being much 310 shorter in our study compared with that of Missana et al. (2009), it appears that the dissolution 311 rate was much higher for the 7-nm-sized magnNP than for the 50-200 nm magnetite nanocrystals 312 313 of Missana's work. Previous studies have indeed highlighted that increased dissolution rate 314 preferentially occurred to smaller-sized particles (Mudunkotuwa and Grassian, 2011, Liu et al., 315 2009). MaghNP displayed a lower amount of released Fe than magnNP, from 0.43% at pH = 3 to 0.09% at pH = 4. The decrease in released Fe between magnNP and maghNP stemmed from the 316 different compositions of both Fe oxides. While maghemite only contains Fe(III) in its structure, 317 318 magnetite (Fe<sub>3</sub>O<sub>4</sub>) also contains Fe(II), which is a much more soluble species than Fe(III) 319 (Jolstera et al., 2012, Maity and Agrawal, 2007). Therefore, magnetite is prone to higher Fe 320 leaching than maghemite, which has previously been observed (Jolstera et al., 2012). The transformation of magnetite to magnetite stems from the solubilization of Fe(II). In our study, 321

322 the dissolved Fe concentrations were negligible for PC-magnNP and HA-magnNP at acidic pH, suggesting that dissolution was almost ineffective at low pH values, and thus, that the 323 transformation of magnetite into maghemite was reduced in the presence of these organic 324 coatings. From these observations, we inferred that PC and HA yield comparable protecting 325 effects against IONP dissolution, probably related to the presence of an efficient barrier at the 326 surface of magnNP (Scherer and Neto, 2005, Lu et al., 2007). Nevertheless, another possibility is 327 328 that HA and PC surface coatings can provide binding sites to dissolved Fe (Peng et al., 2019, Catrouillet et al., 2014). Re-adsorption of aqueous Fe would limit the measured total dissolved Fe 329 330 content, as observed from the ICP-MS measurements performed in the present study. Although different modes of interaction have been proposed to explain the adsorption of HA and PC onto 331 332 magnNP, it is likely that several mechanisms are involved, and their relative contribution may 333 vary depending on the intrinsic properties of the organic molecules, those of magnNP and those 334 of the solution chemistry as well. In our study, the coating of magnNP by HA was performed at basic condition in order to increase HA resistance to leaching. Although low pH promotes HA 335 336 attraction to positively charged iron oxide surface, the formation of specific surface complexes onto mineral surfaces can effectively be achieved even if the oxide surfaces and the organic 337 338 molecules are both negatively charged (Aiken et al., 2011, Yu et al., 2018). At high pH, HA exists in a rather linear or stretched structure which favors multiple sites binding with magnetite, 339 340 and by the same, reduce the Fe and HA leaching from HA-coated magnetite (Liu et al., 2008, 341 Grillo et al., 2015). According to Liu et al (2008), Fe and HA leaching would be negligible and 342 undergo only slight modification after 6 hours (0.03% and 1.3% respectively), 12 hours (0.07% and 3.5% respectively) and 12 days (0.21% and 0.33% respectively). Results of this study were 343 based on the concentration of Fe and DOC in the supernatant obtained from the resuspension of 344 HA-coated magnetite NP in deionized water (constant pH = 6) over different periods of time. It is 345 346 corroborated to other studies, which showed that the leaching of HA from iron oxide is generally 347 negligible in tap waters and deionized waters (Gu et al., 1994).

- 348
- 349

### 3.2. How do magnNP modifications constrain Cu adsorption?

350

3.2.1. Effects of pH on Cu adsorption

351 **MagnNP.** For bare magnNP and Cu = 0.05 mM, the percentage of Cu adsorbed (Cu% 352 adsorbed) increased with the increasing pH (**Figure 1**). In compliance with the measured  $pH_{zpc} =$ 

6.2, the Cu% adsorbed at  $pH > pH_{zpc}$  (at pH 6 and 7) was high (almost 100% Cu adsorbed) as 353 354 compared to the weak Cu% adsorbed (<10% Cu adsorbed) at low pH (pH 3 and 4). At pH > pH<sub>zpc</sub>, the IONP surfaces became negatively charged resulting from deprotonation reactions. The 355 decreasing protons concentration at magnetite surface favors cation attraction and allows Cu<sup>2+</sup> to 356 complex onto the FeO<sup>-</sup> surface sites (Madden et al., 2006, Huang and Chen, 2009). According to 357 ATR-FTIR analyses performed on magnNP after Cu addition (Cu = 0.5 mM) (SI-D), the 358 adsorption of Cu onto magnNP was discernable by the vibration at 1350 cm<sup>-1</sup>. This absorption 359 band was observed in the IR spectrum obtained for Cu in the solution, and in the IR spectrum of 360 magnNP/Cu at pH 5, 6, 7 and 8, whereas no absorption band was recorded at 1350 cm<sup>-1</sup> in the IR 361 362 spectrum of bare magnNP (before Cu addition). On the contrary, the IR spectrum of magnNP/Cu 363 at pH 3.5 resembled that of magnNP before NP/Cu interaction, with no absorption band at 1350 cm<sup>-1</sup> suggesting that no Cu was adsorbed on magnNP surface at pH 3.5. The broad band at 3150 -364 3400 cm<sup>-1</sup> and the band at circa 1630 cm<sup>-1</sup> are characteristic of, respectively, the stretching and 365 bending vibration of hydroxyl groups at the surface of magnNP (Maity and Agrawal, 2007, 366 367 Ahmad et al., 2012) and their intensity is clearly decreased with increasing pH as deprotonation occurs and Cu<sup>2+</sup> ions are adsorbed onto the surface of the adsorbent. ATR-FTIR results are 368 369 consistent with previous ICP-MS data, highlighting that Cu adsorption is favored at  $pH \ge 5$  and thus that protonation/deprotonation reaction is a major mechanism controlling Cu sorption onto 370 371 magnNP.

MaghNP. Cu adsorption onto maghNP followed the same trend as on magnNP, and Cu% 372 373 adsorbed increased with increasing pH. Therefore, magnetite and maghemite likely had similar 374 surface properties. In particular, as magnNP is not perfectly stoichiometric, it is suggested that its 375 surface is partially oxidized. Hence, fully oxidized maghemite and partially surface-oxidizedmagnetite displayed similar adsorption capacity for Cu. Furthermore, since no improvements in 376 Cu sorption onto maghemite were observed, the surface area increase observed after oxidation 377 did not enhance the adsorption of Cu, which was expected to increase. To address this issue, 378 379 Jarbling et al. (2005) proposed that the increased surface area was related to the microporous 380 surface structure of maghemite, which includes non-active surface sites. On another hand, surface area determined by BET measurements was conducted at a favorable pH to form stable 381 maghemite suspension, whereas magnetite likely aggregated at the same pH. Thus, the surface 382 area of magnNP might have been lowered due to its aggregation during the measurements. 383

**PC-magnNP.** The results for PC-magnNP showed that Cu adsorption started from pH = 4384 (4% Cu adsorbed) and reached its maximum at pH = 6 (100% Cu adsorbed), hence following the 385 same trend as for bare magnNP. In fact, PC anchoring did not modify the pH<sub>zpc</sub> of magnNP in a 386 great extent as PC is electrically neutral at pH = 7. The pH-dependency of Cu adsorption onto 387 PC-magnNP may yet remain on the zwitterionic head group in PC (containing a positively 388 charged trimethylethanolammonium group and a negatively charged glycerophosphate group), 389 which likely created a dipole, impacted the surface hydration of the NP and thus the interaction 390 with Cu (Shinoda, 2016). In this frame, Cu could coordinate with the electronegative oxygen in 391 the carbonyl group deeper in the bilayer as was reported for  $Zn^{2+}$  (Alsop et al., 2016). 392 Furthermore, cation binding is expected to occur more or less close to the phosphate group (or to 393 the glycerol group) possibly depending on the size of the ion. Divalent Ca<sup>2+</sup> was found to 394 coordinate and bind electrostatically with oxygen molecules on four adjacent lipid molecules, 395 whereas Mg<sup>2+</sup> bound closer to the phosphate group and coordinated with water oxygens 396 (Melcrová et al., 2016). Thus, the PC coating does not necessarily represent a barrier to metal 397 398 cations and therefore Cu could bind to some of the PC functional groups. Nevertheless, it is still difficult to specify the interaction between Cu and PC-magnNP as it is not known whether PC 399 400 encapsulated the whole surface of magnNP or if it formed patchy coatings around the magnNP (leaving some of the magnNP surfaces lipid-free). 401

402 HA-magnNP. Copper adsorption onto magnNP coated with HA rapidly increased with the increasing pH. The rapid removal capacity of Cu<sup>2+</sup> by HA-magnNP shows that HA provided 403 readily accessible sorption sites to  $Cu^{2+}$ . It is believed that HA improve metal adsorption in HA-404 coated NP by providing numerous phenolic and carboxylic groups to HA-coated NP (Illès and 405 Tombacz, 2004, Gomes de Melo et al., 2016). Besides, the surface chemical modifications 406 induced by HA coating likely lowered the pHzpc of bare magnNP because of the acidic oxygen-407 containing functional groups content (Liu et al., 2008, Gomes de Melo et al., 2016, Peng et al., 408 2012, Chekli et al., 2013). HA pH<sub>zpc</sub> is close to pH = 2.3 (Liu et al., 2008). Hence,  $Cu^{2+}$ 409 adsorption onto HA-magnNP was favored when the pH increased. Decreased pH<sub>zpc</sub> resulting 410 411 from HA coating was shown to favor the adsorption of several metals (such as Cu(II), Cd(II), Hg(II), Pb(II), Zn(II)) since HA imparted negative surface charge to IONP which increased the 412 affinity of mineral surfaces for cations over a wide pH range (Liu et al., 2008, Illès and Tombacz, 413 2004, Lin et al., 2011). On the other hand, HA likely formed a network around coated magnNP 414

which could influence the aggregation of the IONP, especially with increased time exposure, and 415 416 favors metal trapping and adsorption (Zhang et al., 2009, Liu et al., 2008). Hence, the adsorption capacity of HA-coated magnetite is generally higher than that of magnNP and HA alone. The 417 effects of pH on HA own conformation also do play an important role in driving HA / metals 418 interactions. In fact, HA exists in a rather linear or stretched structure at high pH, which favors 419 420 multiple sites binding with inorganic species including Cu cations (Liu et al., 2008; Grillo et al., 2015). Furthermore, results show that adsorbed Cu% to HA-magnNP was high even at acidic pH 421 (Figure 1). Hence, HA likely promoted the adsorption of  $Cu^{2+}$  to HA-magnNP through the 422 formation of strong complexes, with a covalent character, and resistant against proton exchange 423 (Kostic et al., 2011; Senesi et al., 1986). In fact, it was shown that most Cu species bind to HA by 424 forming inner-sphere complexes with the acidic functional groups in HA, although binding 425 through hydrated outer-sphere surface complexes is also expected under favorable conditions (Li 426 et al., 2015; Komy et al., 2014; Otero-Farina et al., 2015). 427

- 428
- 429

#### 3.2.2. Adsorption isotherms

430 The adsorption data were fitted with the Langmuir and Freundlich adsorption equations to determine the adsorption parameters and the consistency with the models. The Freundlich 431 adsorption model provided the best fit regarding the experimental results (SI-E) with higher R<sup>2</sup> 432 obtained for the four IONP investigated. The calculated linear regression coefficients  $(R^2)$ 433 434 calculated from Freundlich linearized plots were higher than 0.95 suggesting a strong linear relationship between log  $Q_e$  and log  $C_e$  (SI-F). The obtained  $K_F$  and n values are comparable to 435 the Freundlich parameters reported in previous studies (Kakavandi et al., 2015; Karami, 2013). 436 The K<sub>F</sub> data highlight the highest affinity of Cu to HA-magnNP (in the following order of 437 438 affinity: HA-magnNP >> maghNP > PC-magnNP = magnNP). The values decreased in the range 439 usually reported for the adsorption of trace metals onto nanomaterials in aqueous solution (Vatta et al., 2006). For the n parameter, the values lie between 1 and 10, indicating a favorable and 440 specific adsorption (chemisorption) of Cu to the IONP over the entire range of Cu concentration 441 investigated. In particular, the adsorption isotherm of HA-magnNP was implemented based on 442 443 the obtained high n value (SI-G), highlighting a high heterogeneity in the process of Cu sorption to HA-magnNP (Xu et al. 2012; Li et al., 2015). Metals, including Fe and Cu, can be held to very 444 445 strong binding sites onto humic substances. It was already reported (Tipping, 2002) that the sorption between HA and metals formed complexes with either the carboxylic and phenolic
groups of HA or through specific binding between metals and the N and S groups of HA.
Therefore, the heterogeneous adsorption between HA-magnNP and Cu can be explained by both
the diversity of the binding sites provided by HA and the formation of multidendate complexes
between Cu and some HA functional groups.

- 451
- 452

# 3.2.3. Cu speciation

Copper speciation was studied relative to the pH, at three Cu concentrations (Cu = 0.05453 454 mM, Cu = 0.1 mM and Cu = 0.5 mM) and taking into account the leaching of Fe (SI-H). At the lowest Cu concentration (Cu = 0.05 mM), Cu speciation displayed the same pattern with magnNP 455 and maghNP. Dissolved  $Cu^{2+}$  was the predominant species up to pH = 5. Beyond this pH, most of 456 the Cu was bound to the surface of the IONP and most of the dissolved Cu species occurred in 457 minor amounts ( $< 1.10^{-5}$  mM). When the initial Cu concentration increased up to Cu = 0.5 mM, 458  $Cu^{2+}$  was the dominant species until pH = 6.5. Copper adsorption occurred from pH 4 to 6.5. Cu 459 precipitation was expected as the pH reached 6.5, as observed in previous studies (Hidmi and 460 461 Edwards, 1999; Boukhalfa et al., 2007, Balintova and Petrilakova, 2011).

#### 462 Several conclusions can be drawn from the speciation calculation and the present results:

- the pH edges obtained for magnetite and maghemite at Cu = 0.05 mM turned out to be
   consistent with our results showing an increasing adsorbed Cu% with the increasing
   pH (pH > 4);
- the decreasing adsorbed Cu%, observed with the increasing Cu concentrations, was
  both related to the precipitation of Cu and, mostly, to the surface site saturation of
  magnNP;
  - no Cu precipitation was expected for Cu = 0.05 mM, whereas the increasing Cu concentration up to Cu = 0.5 mM induced saturation and precipitation at pH values above 6.5;
  - modeled data displayed a good consistency with our experimental results and therefore the use of the diffuse layer surface complexation model, along with the characteristics of the IONP, could be used to predict Cu dynamics in the presence of IONP.

469

#### 3.3. Environmental implications

470

#### 3.3.1. Impacts of IONP dissolution on the IONP stability and solution chemistry

471 IONP dissolution is relevant regards to several environmental issues (Goswani et al., 2017). From the nanoparticle perspective, IONP dissolution is expected to favor the formation of 472 smaller-sized IONP with new intrinsic properties as compared with pristine particles 473 (Mudunkotuwa and Grassian, 2011). Increase in the surface free energy (Guzman et al., 2006), 474 475 resulting from IONP size decrease, could favor the aggregation of IONP. Nevertheless, the last 476 hypothesis was not verified in our study since magnNP dissolution occurred at pH=3 and pH=4, 477 which refers to pH where magnNP are less aggregated (Figure 1). On another hand, aggregation 478 of IONP could limit their dissolution by forming larger bulk particles (thereby decreasing the 479 surface contact in between the IONP) (Mudunkotuwa and Grassian, 2011). Dissolution of IONP 480 resulting from pH decrease (proton-promoted dissolution) also induced Fe release in the solution. The presence of dissolved Fe could modify the solution chemistry and influence the 481 482 stoichiometry, reactivity and recrystallization of magnNP in aqueous environments (Gorski et al., 2010). Doing so, the release of Fe(II) induced by IONP dissolution plays a key role in a wide 483 484 range of biogeochemical processes (Byrne et al., 2015, Peng et al., 2018, Peng et al., 2019). Fe(II) interactions with IONP are also of great concern in several environmental applications 485 486 such as remediation, by influencing the mobility and the redox state of heavy metals (Gorski et al., 2012). Besides, IONP dissolution can also directly control TE release in the environment and 487 488 lead to some more interactions with aqueous Fe or other dissolved species (complexation, 489 precipitation, etc.) upon certain environmental conditions (Bhatt and Tripathi, 2011). And these 490 interactions may become more complex in the presence of other ligands such as HA (Aiken et al., 491 2011, Pédrot et al., 2011) since HA can prevent mineral precipitation, even at high cation 492 concentration and high pH, by increasing cations adsorption (which decreased the saturation index of metal). 493

494

#### 3.3.3. Is there any link in between IONP aggregation and Cu adsorption?

In a previous study, we inferred that, in addition to pH, the surface area and surface chemistry (HA and PC coatings) turned out to be key drivers in controlling the aggregation of IONP (Demangeat et al., 2018), resulting mainly from electrostatic and combined electrosteric interactions. In the present study, the observations of Cu adsorption onto IONP showed that adsorption was likely dependent upon the available active sites for Cu. Nevertheless, the

distribution, density and surface binding geometries may vary with the morphology of the 500 501 aggregates (Gilbert et al., 2009). Therefore, the aggregation of IONP was expected to influence Cu adsorption. By correlating aggregates' sizes, Cu adsorption and pH, no clear relationship can 502 be established between IONP aggregation and Cu adsorption capacities (Figure 1). For magnNP, 503 in particular, although adsorption experiments showed that increasing pH lead to increasing Cu 504 adsorption, the aggregation study highlighted that larger magnNP aggregates were formed at pH 505 506 > 5. In a previous study (Demangeat et al., 2018), the same size-distribution were observed at pH 3, 4 and 5 (with about 80% of magnNP being particles with diameter  $\leq 100$  nm) whereas, in the 507 508 present study, the proportion of adsorbed Cu increased when pH increased from pH 4 to pH 5. Thus, the proportion of Cu is modified regardless of magnNP colloidal state. Furthermore, the 509 proportion of these small size particles (with diameter  $\leq 100$  nm) diminished to 65% at pH 6 and 510 7.5, the optimum pH for Cu adsorption in the present work. Hence, instead of diminishing the 511 512 available reactive surface, aggregation did not prevent Cu from being adsorbed onto those bigger particles. We therefore hypothesized that the aggregation of IONP would rest on weak attraction 513 514 forces and result in the formation of loosely packed aggregates, without any loss of reactive surface area. 515

Although no clear link is concluded regarding the impact of IONP colloidal behavior on Cu adsorption capacity, IONP colloidal stability may still have an impact on Cu dynamics. It was shown that less aggregation between IONP yielded lower rates of sedimentation and increased the mobility of adsorbed cations (Ju-Nam and Lead, 2008). Consequently, rather than being involved directly within the adsorption step, IONP colloidal stability could play a key role in Cu transport, mobility, bioavailability and toxicity once the metal is bound to the IONP (Baumann et al., 2014, Bottero et al., 2011).

### 523 4. Conclusion

IONP can undergo many changes in natural waters and soils. In this study, oxidation of magnetite and HA and PC natural organic coatings induced surface changes that affected both the behavior of the IONP in aqueous solution and the interactions occurring at oxide/water interface. In term of Cu adsorption capacity, the structural and chemical diversity of HA decreased the pH<sub>zpc</sub> of HA-magnNP and provided a large amount of hydrophobic and heteroaliphatic functional groups, which also favored the formation of strong surface complexes onto HA-magnNP over a

wide pH-range. Contrary to HA-magnNP, PC-magnNP and maghNP displayed similar behavior 530 531 than pristine magnNP showing that neither PC coating nor magnNP oxidation affected Cu adsorption capacity. On another hand, both HA and PC surface coatings prevented Fe release 532 from the IONP at low pH. Oxidation of mixed-oxidation state magnNP to maghNP also 533 considerably reduced its dissolution rate, suggesting that  $Fe^{2+}$  in magnNP is more soluble than 534 Fe<sup>3+</sup> in maghNP. Last, if aggregation did not affect the adsorption of Cu, it could be secondarily 535 involved in driving the metal fate by impacting its speciation and thus its mobility and solubility. 536 Deciphering the interactions between IONP, cations and organic molecules as well as 537 investigating the behavior and fate of IONP in the environment (aggregation, transport, toxicity) 538 could have strong implications towards diverse scientific issues including water quality, 539 540 agronomics, and environmental remediation.

# 541 Acknowledgments

We are thankful to A. Beauvois for his kind help to perform potentiometric titrations and Dr R. Marsac for the thorough advice he gave to build the models. We are also grateful to Dr. K. Hanna for providing access to the analytical facilities in his laboratory. This study was funded by the CNRS-INSU/INEE EC2CO and the Interdisciplinary Mission programs through the 'NanoOrgaTraces' and 'ALIEN' projects, awarded to Dr M. Pédrot and the University of Rennes, respectively, through the "Défis Scientifiques Emergents" program awarded to Dr A. Dia. Dr S. Mullin is acknowledged for post-editing the English style (http://www.proz.com/profile/677614).

# 549 **References**

Adrees, M., Ali, S., Rizwan, M., Ibrahim, M., Abbas, F., Farid, S., Zia-ur-Rehman, M., Irshad,

551 M.K., Bharwana, S.A., 2015. The effect of excess copper on growth and physiology of important

552 food crops: a review. Environ. Sci. Pollut. Res. 22, 8148-8162. http://dx.doi.org/10.1007/s11356-

553 015-4496-5

Afkhami, A., Saber-Tehrani, M., Bagheri, H., 2010. Modified maghemite nanoparticles as an

efficient adsorbent for removing some cationic dyes from aqueous solution. Desalinisation 263,
240-248. http://dx.doi.org/10.1016/j.desal.2010.06.065

Ahmad, R., Kumar, R., Haseeb, S., 2012. Adsorption of Cu<sup>2+</sup> from aqueous solution onto iron
oxide coated eggshell powder: Evaluation of equilibrium, isotherms, kinetics and regeneration
capacity. Arabian J. Chem. 5, 353-359. https://doi.org/10.1016/j.arabjc.2010.09.003

- Ahmed, M.A., Ali, S.M., El-Dek, S.I., Galal, A., 2013. Magnetite-hematite nanoparticles
- prepared by green methods for heavy metal removal from water. Mater. Sci. Eng., B 178, 744-
- 562 751. http://dx.doi.org/10.1016/j.mseb.2013.03.011
- Aiken, G.R., Hsu-Kim, H., Ryan, J.N., 2011. Influence of Dissolved Organic Matter on the
  environmental Fate of Metals Nanoparticles, and Colloids. Environ. Sci. Technol. 45, 3196-3201.
  http://dx.doi.org/10.1021/es103992s
- Alsop R.J., Schober, R.M., Rheinstädter, M.C., 2016. Swelling of phospholipid membranes by
- 567 divalent metal ions depends on the location of the ions in the bilayers, Soft Matter 12, 6737-6748.
  568 http://dx.doi.org/10.1039/c6sm00695g
  - Made M., Liu, J.F., Tan, Z.O., Bekana, D., 2017. Transformation and bioavailability of metal
    oxide nanoparticles in aquatic and terrestrial environments, A review. Environ. Pollut. 230, 250-
  - 571 267. http://dx.doi.org/10.1016/j.envpol.2017.06.064
  - 572 Auffan, M., Achouak, W., Rose, J., Roncato, M.A., Chanéac, C., Waite, D.T., Masion, A.,
  - 573 Woisik, J.C., Wiesner, M.R., Bottero, J.Y., 2008. Relation between the redox state of iron-based
  - nanoparticles and their cytotoxicity toward Escherichia coli. Environ. Sci. Technol. 42, 6730-
  - 575 6735. http://dx.doi.org/10.1021/es800086f
  - 576 Balintova, M., Petrilakova, A., 2011. Study of pH Influence on Selective Precipitation of Heavy
  - 577 Metals from Acid Mine Drainage. Chemical Engineering Transactions 25, 345-350.
  - 578 http://dx.doi.org/10.3303/CET1125058
  - 579 Baumann, J., Köser, J., Arndt, D., Filser, J., 2014. The coating makes the difference: Accute
  - effects of iron oxide nanoparticles on Daphnia magna. Sci. Total Environ. 484, 176-184.
    http://dx.doi.org/10.1016/j.scitotenv.2014.03.023
  - Bhatt, I., Tripathi, B.N., 2011. Interaction of engineered nanoparticles with various components
    of the environment and possible strategies for their risk assessment. Chemosphere 82, 308-317.
    http://dx.doi.org/10.1016/j.chemosphere.2010.10.011
  - Bottero, J.Y., Auffan, M., Rose, J., Mouneyrac, C., Botta, C., Labille, J., Masion, A., Thill, A.,
  - 586 Chaneac, C., 2011. Manufactured metal and metal-oxide nanoparticles: properties and perturbing
  - mechanisms of their biological activity in ecosystems. C.R. Geosci. 343, 168-176.
  - 588 http://dx.doi.org/10.1016/j.crte.2011.01.001
  - C. Boukhalfa, A. Mennour, L. Reinert, M. Dray, L. Duclaux, 2007. Removal of copper from
    aqueous solution by coprecipitation with Hydrated Iron Oxide. Asian J. Chem. 19 (6), 42674276.
  - Jr Brown, G.E., Henrich, V.E., Casey, W.H., Clark, D.L., Eggleston C., Felmy A., Goodman,
  - 593 D.W., Grätzel, M., Maciel, G., McCarthy, M.I., Nealson, K.H., Sverjensky, D.A., Toney M.F.,

- Zachara J.M., 1999. Metal Oxide Surfaces and Their Interactions with Aqueous Solutions and
   Microbial Organisms. Chem. Rev. 99(1), 77-174. https://doi.org/10.1021/cr980011z
- 596 Byrne, J.M., Klueglein, N., Pearce, C., Rosso, K.M., Appel, E., Kappler, A., 2015. Redox cycling
- of Fe(II) and Fe(III) in magnetite by Fe metabolizing bacteria. Science 347, 1473-1476.
- 598 http://dx.doi.org/10.1126/science.aaa4834.
- 599 Catrouillet, C., Davranche, M., Dia, A., Bouhnik-Le Coz, M., Marsac, R., Pourrret, O., Gruau,
- 600 G., 2014. Geochemical modeling of Fe(II) binding to humic and fulvic acids. Chem. Geol. 372, 100 118 http://dx.doi.org/10.1016/j.ehemgeo.2014.02.010
- 601 109-118. http://dx.doi.org/10.1016/j.chemgeo.2014.02.019
- Chekli, L., Phuntsho, S., Roy, M., Shon, H.K., 2013. Characterization of Fe-oxide nanoparticles
  coated with humic acid and Swannee River natural organic matter. Sci. Total Environ. 461-462,
  19-27. http://dx.doi.org/10.1016/j.scitotenv.2013.04.083
- 605 Cheng, W., Marsac, R., Hanna, K., 2018. Influence of magnetite stoichiometry on the binding of
- 606 emerging organic contaminants. Environ. Sci. Technol. 52(2), 467-473.
- 607 http://dx.doi.org/10.1021/acs.est.7b04849
- Christl, I., Kretzschmar, R., 2001. Interaction of copper and fulvic acid at the hematite water
  interface. Geochim. Cosmochim. Acta (65) 20, 3435-3442. https://doi.org/10.1016/S00167037(01)00695-0
- Dabrowski, A., Hubicki, Z., Podkoscielny, P., Robens, E., 2004. Selective removal of the heavy
- 612 metal ions from waters and industrial wastewaters by ion-exchange method. Chemosphere 56,
- 613 91-106. http://dx.doi.org/10.1016/j.chemosphere.2004.03.006
- Davranche, M., Dia, A., Fakih, M., Nowack, B., Gruau, G., Ona-Nguema, G., Petitjean, P.,
- Martin, S., Hochreutener, R., 2013. Organic matter control on the reactivity of Fe(III)-
- oxyhydroxides and associated As wetland soils: a kinetic modeling study. Chem. Geol. 335, 24-
- 617 35. http://dx.doi.org/10.1016/j.chemgeo.2012.10.040
- Debnath, S., Hausner, D.B., Strongin, D.R., Kubicki, J., 2010. Reducive dissolution of
- 619 ferrihydrite by ascorbic acid and the inhibiting effect of phospholipids. J. Colloid Interface Sci.
- 620 341, 215-223. http://dx.doi.org/10.1016/j.jcis.2009.09.035
- 621 Demangeat, E., Pédrot, M., Dia, A., Bouhnik-le-Coz, M., Grasset, F., Hanna, K., Kamagaté, K.,
- 622 Cabello-Hurtado, F., 2018. Colloidal and Chemical stabilities of iron oxide nanoparticles in
- 623 aqueous solutions: the interplay of structural, chemical and environmental drivers. Environ. Sci.
- 624 Nano, 5, 992-1001. http://dx.doi.org/10.1039/c7en01159h
- 625 Demirel, C.U., Bekbolet, M., Swietlik, J., 2006. Natural organic matter: definitions and
- 626 characterization. Publishers, Nova Science Chap 5.1., 25pp. Inc. ISBN 1-60021-322-7

- 627 Frison, R., Cernuto, G., Cervellino, A., Zaaharko, O., Colonna, G.M., Guagliardi, A.,
- Masciocchi, N., 2013. Magnetite-Maghemite Nanoparticles in the 5-15 nm range: correlating the
- 629 core-shell composition and surface structure to the magnetic properties. A total scattering study.
- 630 Chem. Mater. 25, 4820-4828. http://dx.doi.org/10.1021/cm403360f
- Fu, Q., Zhou, X., Xu, L., Hu, B., 2015. Fulvic acid decorated Fe<sub>3</sub>O<sub>4</sub> magnetic nanocomposites for
- the highly efficient sequestration of Ni(II) from an aqueous solution. J. Mol. Liq. 208, 92-98.
- 633 http://dx.doi.org/10.1016/j.molliq.2015.04.017
- Ghosh, S., Jiang, W., McClements, J.D., Xing, B., 2011. Colloidal Stability of Magnetic Iron
- Oxide nanoparticles: Influence of Natural Organic Matter and Synthetic Polyelectrolytes.
  Langmuir 27, 8036-8043. http://dx.doi.org/10.1021/la200772e
- Gilbert, B., Ono, R.K., Ching, K.A., Kim, C.S., 2009. The effects of nanoparticles aggregation
- processes on aggregates structure and metal uptake. J. Colloid Interface Sci. 339, 285-295.
  http://dx.doi.org/10.1016/j.jcis.2009.07.058
- Giri, J., Thakurta, S.G., Bellare, J., Nigam, A.K., Bahadur, D., 2005. Preparation and
- 641 characterization of phospholipid stabilized uniform sized magnetite nanoparticles. J. Magn.
- 642 Magn. Mater. 293, 62-68. http://dx.doi.org/10.1016/j.jmmm.2005.01.044
- Gomes de Melo, B.A., Motta, F.L., Santana, M.H.A, 2016. Humic acids: Structural properties
- and multiple functionalities for novel technological developments. Mater. Sci. Eng., C 62, 96797. http://dx.doi.org/10.1016/j.msec.2015.12.001
- 646 Gorski, C.A., Nurmi, J.T., Tartneyk, P.G., Hofstetter, T.B., Sherer, M.M., 2010. Redox behaviour
- 647 of magnetite: implications for contaminant reduction. Environ. Sci. Technol. 44, 55-60.
- 648 http://dx.doi.org/10.1021/es9016848
- Gorski, C.A., Handler, R.M., Beard, B.L. Pasakarnis, T., Johnson, C.M., Sherer, M.M., 2012. Fe
  atom exchange between aqueous Fe<sup>2+</sup> and magnetite. Environ. Sci. Technol. 46, 12399-12407.
  http://dx.doi.org/10.1021/es204649a
- Goswani, L., Kim, K.H., Deep, A., Das, P., Bhattacharya, S.S., Kumar, S., Adelodun, A.A., 2017.
- Engineered nanoparticles: Nature, behavior, and effect on the environment. J. Environ. Manage.
- 654 196, 297-315. http://dx.doi.org/10.1016/j.jenvman.2017.01.011
- 655 Grillo, R., Rosa, A.H, Fraceto, L.F., 2015. Engineered nanoparticles and organic matter: A
- review of the state-of-the-art. Chemosphere 119, 608-619.
- 657 http://dx.doi.org/10.1016/j.chemosphere.2014.07.049
- Gu, B., Schmitt, J., Chen, Z., Liang, L., McCarthy, J.F., 1994. Adsorption and desorption of
- natural organic matter on iron oxide: mechanisms and models. Environ. Sci. Technol. 28, 38-46.
  http://dx.doi.org/10.1021/es00050a007

- 661 Gupta, A.K., Gupta, M., 2005. Synthesis and surface engineering of iron oxide nanoparticles for
- biomedical applications. Biomaterials 26, 3995-4021.
- 663 http://dx.doi.org/10.1016/j.biomaterials.2004.10.012
- 664 Guzman, KAD., Finnegan, M.P., Banfield, J.F., 2006. Influence of surface potential on
- aggregation and transport of titania nanoparticles. Environ. Sci. Technol. 40, 7688-7693.
  http://dx.doi.org/10.1021/es060847g
- Hadju, A., Illès, E., Tombacz, E., Borbath, I., 2009. Surface charging, polyanionic coating and
- 668 colloid stability of magnetite nanoparticles. Colloids Surf., A 347, 104-108.
- 669 http://dx.doi.org/10.1016/j.colsurfa.2008.12.039
- Hidmi, L., Edwards, M., 1999. Role of temperature and pH in Cu(OH)<sub>2</sub> solubility. Environ. Sci.
  Technol. 33 (15), 2607–2610. http://dx.doi.org/10.1021/es981121q
- Hu, J., Chen, G., Lo, I.M.C., 2005. Removal and recovery of Cr(VI) from wastewater by
- maghemite nanoparticles. Water Res. 39, 4528-4536.
- 674 http://dx.doi.org/10.1016/j.watres.2005.05.051
- Hu, J., Chen, G., Lo, I.M.C., 2006. Selective removal of heavy metals from industrial wastewater
- using maghemite nanoparticles: performance and mechanisms. J. Environ. Eng. 132, 709-715.
- 677 http://dx.doi.org/10.1061/(ASCE)0733-9372(2006)132:7(709)
- Huang, S.H., Chen, D.H., 2009. Rapid removal of heavy metal cations and anions from aqueous
- solutions by an amino-functionalized magnetic-adsorbent. J. Hazard. Mater. 163, 174-179.
  http://dx.doi.org/10.1016/j.jhazmat.2008.06.075
- 681 Illès, E., Tombacz, E., 2004. The role of variable surface charge and surface complexation in the
- adsorption of humic acid on magnetite. Colloids Surf., A 230, 99-109.
- 683 http://dx.doi.org/10.1016/j.colsurfa.2003.09.017
- 684 Illés, E., Tombacz, E., 2006. The effect of humic acid adsorption on pH-dependent surface
- charging and aggregation of magnetite nanoparticles. J. Colloid Interface Sci. 295, 115-123.
  http://dx.doi.org/10.1016/j.jcis.2005.08.003
- Jarbling, M., Gunneriusson, L., Hussmann, B., Forsling, W., 2005. Surface complex
- 688 characteristics of synthetic maghemite and hematite in aqueous suspensions. J. Colloid Interface
- 689 Sci. 285, 212-217. http://dx.doi.org/10.1016/j.jcis.2004.11.005
- 690
- and magnesium (II) sorption onto maghemite and magnetite. J. Colloid Interface Sci. 386, 260-
- 693 267. http://dx.doi.org/10.1016/j.jcis.2012.07.031
- 694

- Joo, S.H., Zhao, D., 2017. Environmental dynamics of metal oxide nanoparticles in
- heterogeneous systems: a review. J. Hazard. Mater. 322, 29-47.
- 697 http://dx.doi.org/10.1016/j.jhazmat.2016.02.068
- Ju-Nam, Y, Lead, J.R., 2008. Manufactured nanoparticles: An overview of their chemistry,
- interactions and potential environmental implications. Sci. Total Environ. 400, 396-414.
  http://dx.doi.org/10.1016/j.scitotenv.2008.06.042
- Kah, M., 2015. Nanopesticides and nanofertilizers: emerging contaminants or opportunities for
   rick mitigation? Front. Chem. 64, 1-6. http://dx.doi.org/10.3389/fchem.2015.00064
- Kakavandi, B., Kalantary, R.R., Jafari, A.J., Nasseri, S., Ameri, A., Esrafili, A., Azari, A., 2015.
- 704 Pb(II) Adsorption Onto a Magnetic Composite of Activated Carbon and Superparamagnetic
- Fe<sub>3</sub>O<sub>4</sub> Nanoparticles: Experimental and Modeling Study. CLEAN, Soil, Air, Water 43, 1157-
- 706 1166. http://dx.doi.org/10.1002/clen.201400568
- Karami, H., 2013. Heavy metal removal from water by magnetite nanorods. Chem. Eng. J. 219,
  209-216. http://dx.doi.org/10.1016/j.cej.2013.01.022
- 709 Karimi, Z., Karimi, L., Shokrollahi, H., 2013. Nano-magnetic particles used in biomedicine: Core
- and coating materials. Mater. Sci. Eng., C 33, 2465–2475.
- 711 http://dx.doi.org/10.1016/j.msec.2013.01.045
- 712 Khalafalla, S.E., Reimers, G.W., 1980. Preparation of dilution-stable aqueous magnetic fluids.
- 713 IEEE Trans. Magn. 16(2), 178-183. http://dx.doi.org/10.1109/TMAG.1980.1060578
- 714
- 715 Khot, L.R., Sankaran, S., Maja J.M., Ehsani, R., Schuster, E.W., 2012. Applications of
- nanomaterials in agricultural production and crop protection: a review. Crop Prot. 35, 64-70.
- 717 http://dx.doi.org/10.1016/j.cropro.2012.01.007
- 718 Koesnarpadi, S., Santosa, S.J., Siswanta, D., Rusdiarso, B., 2015. Synthesis and characterization
- of magnetite nanoparticles coated humic acid ( $Fe_3O_4/HA$ ). Procedia Environ. Sci. 30, 103-108.
- 720 http://dx.doi.org/10.1016/j.proenv.2015.10.018
- Komadel, P., Stucki, J.W., 1988. Quantitative assay of minerals for  $Fe^{2+}$  and  $Fe^{3+}$  using 1,10-
- phenantroline: III. a rapid photochemical method . Clays Clay Miner. 36 (4), 379-381.
- 723 DOI:10.1346/CCMN.1988.0360415
- Komy, Z.R., Shaker, A.M., Heggy, S.E.M., El-Sayed, M.E.A., 2014. Kinetic study for copper
- adsorption onto soil minerals in the absence and presence of humic acid. Chemosphere 99, 117-
- 726 124. http://dx.doi.org/10.1016/j.chemosphere.2013.10.048

- 727 Kostic, I., Andelkovic, T., Nikolic, R., Bojic, A., Purenovic, M., Blagojevic S., Andelkovic, D.,
- 728 2011. Copper(II) and lead (II) complexation by humic acid and humic-like ligands. J. Serb.
- 729 Chem. Soc. 76 (9), 1325-1336. http://dx.doi.org/10.2298/JSC110310115K
- Le, Q.C., Ropers, M.H., Terrisse, H., Humbert, B., 2014. Interactions between phospholipids and
- titanium dioxide particles. Colloids Surf., B 123, 150-157.
- 732 http://dx.doi.org/10.1016/j.colsurfb.2014.09.010
- Li, J., Hu, J., Ma, C., Wang, Y., Wu, C., Huang, J., Xing, B., 2016. Uptake, translocation and
- physiological effects of magnetic iron oxide ( $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>) nanoparticles in corn (*Zea mays* L.).
- 735 Chemosphere 159, 326-334. http://dx.doi.org/10.1016/j.chemosphere.2016.05.083
- 736 Li, C.L., Ji, F., Wang, S., Zhang, J.J., Gao, Q., Wu, J.G., Zhao, L.P., Wang, L.C., Zheng, L.R.,
- 737 2015. Adsorption of Cu(II) on humic acids derived from different organic materials. J. Integr.
- 738 Agric. 14(1), 168-177. https://doi.org/10.1016/S2095-3119(13)60682-6
- Lin, J., Zhan, Y., Zhu, Z., 2011. Adsorption characteristics of Copper (II) ions from aqueous
- solution onto humic acid-immobilized surfactant-modified zeolite. Colloids Surf., A 384, 9-16.
- 741 http://dx.doi.org/10.1016/j.colsurfa.2011.02.044
- Liu, J.F., Zhao, Z.S., Jiang, G.B., 2008. Coating Fe<sub>3</sub>O<sub>4</sub> nanoparticles with humic acid for high
- r43 efficient removal of heavy metals in water. Environ. Sci. Technol. 42, 6949-6954.
- 744 http://dx.doi.org/10.1021/es800924c
- Liu, J., Arguete, D.M., Murayama, M., Hochella Jr., M., 2009. Influence of size and aggregation
- on the reactivity of an environmentally and industrially relevant nanomaterial (PbS). Environ.
- 747 Sci. Technol. 43, 8178-8183. http://dx.doi.org/10.1021/es902121r
- Lohdia, J., Mandarano, G., Ferris, N.J., Eu, P., Cowell, S.F., 2010. Development and use of iron
  oxide (Part 1): synthesis of iron oxide for MRI. Biomed. Imaging Intervention J. 6 (2), 1-11.
- 750 http://dx.doi.org/10.2349/biij.6.2.e12
- Löhr, S.C., Murphy, D.T., Nothdurft, L.D., Bohlar, R., Piazolo, S., Siegel, C., 2017. Maghemite
- soil nodules reveal the impact of fire on mineralogical and geochemical differentiation at the
- Earth's surface. Geochim. Cosmochim. Acta 200, 25-41.
- 754 http://dx.doi.org/10.1016/j.gca.2016.12.011
- Lu, A.H., Salabas, E.L., Schuth, F., 2007. Magnetic Nanoparticles: Synthesis, Protection,
  Functionalization, and Application. Angew. Chem. Int. Ed. 46, 1222 -1244.
  http://dx.doi.org/10.1002/anie.200602866
- Lucas, I., Durand-Vidal, S., Dubois, E., Chevalet, J., Turq, P., 2007. Surface Charge Density of
- 759 Maghemite Nanoparticles: Role of Electrostatics in the Proton Exchange. J. Phys. Chem. C 111,
- 760 18568-18576. http://dx.doi.org/10.1021/jp0743119

- 761 Madden, A.S., Hochella Jr, M.F., Luxon, T.P., 2006. Insights for size-dependent reactivity of
- hematite nanomineral surfaces through Cu<sup>2+</sup> sorption. Geochim. Cosmochim. Acta 70, 40954104. http://dx.doi.org/10.1016/j.gca.2006.06.1366
- Maity, D., Agrawal, D.C., 2007. Synthesis of iron oxide nanoparticles under oxidizing
- renvironment and their stabilization in aqueous and non-aqueous media. J. Magn. Magn. Mater.
  308, 46-55. http://dx.doi.org/10.1016/j.jmmm.2006.05.001
- 767 Mamindy-Pajany, Y., Hurel, C., Marmier, N., Roméo, M., 2011. Arsenic (V) adsorption from
- aqueous solution onto goethite, hematite, magnetite and zero-valent iron: Effects of pH,
- concentration and reversibility. Desalination 281, 93-99.
- 770 http://dx.doi.org/10.1016/j.desal.2011.07.046
- 771 Massart, R., 1981. Preparation of aqueous magnetic liquids in alkaline and acidic media.
- 772 IEEE Trans. Magn. 17, 1247-1248. http://dx.doi.org/10.1109/TMAG.1981.1061188
- 773 Melcrová, A., Pokorna, S., Pullanchery, S., Kohagen, M., Jurkiewicz, P., Hof, M., Jungwirth, P.,
- 774 Cremer, P.S., Cwiklik, L., 2016. The complex nature of cation interaction with phospholipid
- bilayers. Sci. Rep. 38035 (6), 1-12. http://dx.doi.org/10.1038/srep38035
- 776 Missana, T., Alonso, U., Scheinost, A.C., Granizo, N., Garcia-Gutierrez, M., 2009. Selenite
- retention by nanocrystalline magnetite: role of adsorption, reduction and dissolution/co-
- precipitation processes. Geochim. Cosmochim. Acta 73, 6205-6217.
- 779 http://dx.doi.org/10.1016/j.gca.2009.07.005
- 780 Mohan, D., Pittman Jr., C.U., Steele, P.H., 2006. Single, binary and multi-component adsorption
- of copper and cadmium from aqueous solution on kraft-lignin a biosorbent. J. Colloid Interface
   Sci. 297, 489-504. https://doi.org/10.1016/j.jcis.2005.11.023
- 782 Sci. 297, 489-504. https://doi.org/10.1016/j.jcis.2005.11.023
- 783 Mudunkotuwa, I.A., Grassian, V.H., 2011. The devil is in the details (or the surface): impact of
- surface structure and surface energetics on understanding the behavior of nanomaterials in the
   environment. J. Environ. Monit. 13, 1135-1144. http://dx.doi.org/10.1039/c1em00002k
- 786 Mulder, W.J., Strijkers, G.J., van Tilborg, G.A.F., Griffioen, A.W., Nicolay, K., 2006.
- 787 Lipid-based nanoparticles for contrast-enhanced MRI and molecular imaging. NMR Biomed. 19,
- 788 142-164. http://dx.doi.org/10.1002/nbm.1011
- Niu, H., Zhang, D., Zhang, S., Zhang, X., Meng, Z., Cai, Y., 2011. Humic acid coated Fe<sub>3</sub>O<sub>4</sub>
- magnetic nanoparticles as highly efficient Fenton-like catalyst for complete mineralization of
- 791 sulfathiazole. J. Hazard. Mater. 190, 559-565. http://dx.doi.org/10.1016/j.jhazmat.2011.03.086
- Nowack, B., Bucheli, T.D., 2007. Occurrence, behavior and effects of nanoparticles in the
- renvironment. Environ. Pollut. 150, 5-22.
- 794 http://dx.doi.org/10.1016/j.envpol.2007.06.006

- 795 Otero-Farina, A., Gago, R., Antelo, J., Fiol, S., Arce, F., 2015. Surface complexation modelling
- of Arsenic and Copper Immobilization by Iron oxide precipitates derived from Acid Mine
- 797 Drainage. Boletin de la Sociedad Geologica Mexicana 67, 493-508.
- 798 http://dx.doi.org/10.18268/BSGM2015v67n3a12
- 799 Pan, B., Qiu, H., Pan, B., Nie, G., Xiaio, L., Lv, L., Zhang, W., Zhang, Q., Zheng, S., 2010.
- 800 Highly efficient removal of heavy metals by polymer-supported nanosized hydrated Fe(III)
- 801 oxides: behavior and XPS study. Water Res. 44, 815-824.
- 802 http://dx.doi.org/10.1016/j.watres.2009.10.027
- Pang, S.C., Chin, S.F., Anderson, M.A., 2007. Redox equilibria of iron oxides in aqueous-based
  magnetite dispersions: Effect of pH and redox potential. J. Colloid Interface Sci. 311, 94-101.
- 805 http://dx.doi.org/10.1016/j.jcis.2007.02.058
- Panneerselvam, P., Morad, N., Aik Tan, K., 2011. Magnetic nanoparticle (Fe<sub>3</sub>O<sub>4</sub>) impregnated
  onto tea waste for the removal of nickel(II) from aqueous solution. J. Hazard. Mater. 186, 160-
- 808 168. https://doi.org/10.1016/j.jhazmat.2010.10.102
- 809 Parkinson, G.S., 2016. Iron oxides surfaces. Surf. Sci. Rep., 71(1), 272-365.
- 810 https://doi.org/10.1016/j.surfrep.2016.02.001
- Pédrot, M., Boudec, A.L., Davranche, M., Dia, A., Henin, O., 2011. How does organic matter
- constrain the nature, size and availability of Fe nanoparticles for biological reduction? J. Colloid
- 813 Interface Sci. 359, 75-85. http://dx.doi.org/10.1016/j.jcis.2011.03.067
- 814 Peng, L., Qin, P., Lei, M., Zeng, Q., Song, H., Yang, J., Shao, J., Liao, B., Gu, J., 2012.
- 815 Modifying  $Fe_3O_4$  nanoparticles with Humic acids for removal of Rhodamine B in water. J.
- 816 Hazard. Mater. 209-210, 193-198. http://dx.doi.org/10.1016/j.jhazmat.2012.01.011
- 817 Peng, H., Pearce, C.I., N'Diaye, A.T., Zhu, Z., Ni, J., Rosso, K.M., Liu, J., 2019. Redistribution
- 818 of electron equivalents between magnetite and aqueous  $Fe^{2+}$  induced by a Model Quinone
- 819 Compound (AQDS). Environ. Sci. Technol. 53 (4), 1863-1873.
- 820 https://doi.org/10.1021/acs.est.8b05098
- Peng, H., Pearce, C.I., Huang, W., Zhu, Z., N'Diaye, A.T., Rosso, K.M., Liu, J., 2018. Reversible
- Fe(II) uptake/release by magnetite nanoparticles. Environ. Sci. Nano, 5, 1545-1555.
- 823 http://dx.doi.org/10.1039/C8EN00328A
- 824 Sabbatini, P., Yrazu, F., Rossi, F., Thern, G., Marajofsky, A., Fidalgo de Cortalezzi, M.M., 2010.
- 825 Fabrication and characterization of iron oxide ceramic membranes for arsenic removal. Water
- 826 Res. 44, 5702-5712. https://doi.org/10.1016/j.watres.2010.05.059
- 827 Scherer, C., Neto, A.M.F., 2005. Ferrofluids: properties and applications. Braz. J. Phys. 35 (3A),
- 828 718-727. http://dx.doi.org/10.1590/S0103-97332005000400018

- 829 Schwaminger, S.P., Bauer, D., Fraga-García, P., Wagner, F.E., Berensmeier, S., 2017. Oxidation
- of magnetite nanoparticles: impact on surface and crystal properties. CrystEngComm. 19, 246-
- 831 255. http://dx.doi.org/10.1039/c6ce02421a
- 832 Senesi, N., Sposito, G., Martin, J.P., 1986. Copper and iron complexation by soil humic acids: an
- 833 IR and ESR study. Sci. Total Environ. 55, 351-362. https://doi.org/10.1016/0048-
- 834 9697(86)90192-0
- 835 Shaker, MA., Albishri, H.M., 2014. Dynamics and thermodynamics of toxic metals adsorption
- onto soil-extracted humic acid. Chemosphere 111, 587-595.
- 837 http://dx.doi.org/10.1016/j.chemosphere.2014.04.088
- 838 Sheng, G., Li, J., Shao, D., Hu, J., Chen, C., Chen, Y., Wang, X., 2010. Adsorption of copper(II)
- on multiwalled carbon nanotubes in the absence and presence of humic or fulvic acids. J. Hazard.
- 840 Mater. 178, 333-340. https://doi.org/10.1016/j.jhazmat.2010.01.084
- 841 Shinoda, W., 2016. Permeability across lipid membranes. Biochim. Biophys. Acta, Biophys. Incl.
- 842 Photsynth. 1858, 2254-2265. http://dx.doi.org/10.1016/j.bbamem.2016.03.032
- 843 Sigg, L., Behra, P., Stumm, W., 2011. Aquatic chemistry, 5<sup>th</sup> edition, 391pp.
- 844 Smith, K.S., 1999. Metal sorption on mineral surfaces: an overview with examples relating to 845 mineral deposits. Reviews in Economic Geology, 6A-6B, Chapter 7, 161-182.
- 846 Solis-Calero, C., Ortega-Castro, J., Frau, J., Munoz, F., 2015. Non-enzymatic reactions above
- 847 phospholipid surfaces of biological membranes: reactivity of phospholipids and their oxidation
- derivatives. Oxid. Med. Cell. Longevity 15, 1-22. http://dx.doi.org/10.1155/2015/319505
- Stumm, W., 1992. Chemistry of the Solid-Water interface. Processes at the Mineral-Water and
  Particle-Water interface in natural systems. Wiley-VCH, 448pp. ISBN: 978-0-471-57672-3.
- Tang, S.C.N., Lo, I.M.C., 2013. Magnetic nanoparticles: Essential factors for sustainable
- environmental applications. Water Res. 47, 2613-2632.
- 853 http://dx.doi.org/10.1016/j.watres.2013.02.039
- Tang, W.W., Zeng, G.M., Gong, J.L., Liang, J., Xu, P., Zhang, C., Huang, B.B., 2014. Impact of
- 855 Humic/fulvic acid on the removal of heavy metals from aqueous solutions using nanomaterials: A
- 856 review. Sci. Total Environ. 468-469, 1014-1027.
- 857 http://dx.doi.org/10.1016/j.scitotenv.2013.09.044
- Tipping, E., 2002. Cation binding to humic substances. Cambridge University Press, 2002.
- 859 https://doi.org/10.1017/CBO9780511535598

- Tombacz, E., Toth, I.Y., Nesztor, D., Illés, E., Hadju, A., Szekeres, M., Vékas, L., 2013.
- Adsorption of organics on magnetite nanoparticles, pH dependent stability and salt tolerance.
- 862 Colloids Surf., A 435, 91-96. http://dx.doi.org/10.1016/j.colsurfa.2013.01.023
- Vatta, L.L., Sanderson, R.D., Koch, K.R., 2006. Magnetic nanoparticles: properties and potential
  applications. Pure Appl. Chem. 78, 1793-1801. https://doi.org/10.1351/pac200678091793
- Vindedahl, A.M., Strehlau, J.H., Arnold, W.A., Penn, R.L., 2016. Organic matter and iron oxide
  nanoparticles: aggregation, interactions and reactivity. Environ. Sci. Nano, Critical Review 3,
  494-505. http://dx.doi.org/10.1039/c5en00215j
- Wang, L., Li, J., Jiang, Q., Zhao, L., 2012. Water-soluble Fe<sub>3</sub>O<sub>4</sub> nanoparticles with high
  solubility for removal of heavy-metal ions from waste water. Dalton Trans. 41, 4544-4551.
- 870 http://dx.doi.org/10.1039/c2dt11827k
- Wu, W., Wu, Z., Yu, T., Jiang, C., Kim, W.S., 2015. Recent progress on magnetic iron oxide
- 872 nanoparticles: synthesis, surface functional strategies and biomedical applications. Sci. Technol.
- 873 Adv. Mater. 16, 023501 023544. http://dx.doi.org/10.1088/1468-6996/16/2/023501
- 874 Xu, P., Zheng, G., Huang, D., Lai, C., Zhao, M., Wei, Z., Li, N., Huang, C., Xie, G., 2012.
- 875 Adsorption of Pb(II) by iron oxide nanoparticles immobilized Phanerochaete chrysosporium:
- 876 Equilibrium, kinetic, thermodynamic and mechanisms analysis. Chem. Eng. J. 203, 423-431.
- 877 http://dx.doi.org/10.1016/j.cej.2012.07.048
- Ye, S., Zheng, G., Wu, H., Zhang C., Dai, J., Liang, J., Yu, J., Ren, X., Yi, H., Cheng, M., Zhang,
- M., 2017. Biological technologies for the remediation of co-contaminated soil. Crit. Rev.
- Biotechnol. 37(8), 1062-1076. https://doi.org/10.1080/07388551.2017.1304357
- 881 Yéghicheyan, D., Bossy, C., Bouhnik Le Coz, M., Douchet, C., Granier, G., Heimburger,
- A., Lacan, F., Lanzanova, A., Rousseau, T.C.C., Seidel, J.L., Tharaud, M., Candaudap,
- 883 F., Chmeleff, J., Cloquet, C., Delpoux, S., Labatut, M., Losno, R., Pradoux, C., Sivry, Y., Sonke,
- J.E., 2013. A compilation of silicon, rare earth element and twenty-one other trace element
- concentrations in the natural river water reference material slrs-5 (nrc-cnrc). Geostand. Geoanal.
- 886 Res. 37(4), 449-467. https://doi.org/10.1111/j.1751-908X.2013.00232.x
- Yu, S., Liu, J., Yin, Y., Shen, M., 2018. Interactions between engineered nanoparticles and
- dissolved organic matter: a review on mechanisms and environmental effects. J. Environ. Sci. 63,
- 889 198-217. http://dx.doi.org/10.1016/j.jes.2017.06.021
- Zasonska, B.A., Bober, P., Jostr, P., Eduard, P., Bostik, P., Horak, D., 2016. Magnetoconductive
- 891 maghemite core/polyaniline shell nanoparticles: Physico-chemical and biological assessment.
- 892 Colloids Surf., B 14, 382-389. http://dx.doi.org/10.1016/j.colsurfb.2016.01.059

- Zhang, Y., Chen, Y., Westerhoff, P., Crittenden, J., 2009. Impact of natural organic matter and
- divalent cations on the stability of aqueous nanoparticles. Water Res. 43, 4249-4257.
- 895 http://dx.doi.org/10.1016/j.watres.2009.06.005

896



**Figure 1:** Adsorbed Cu%, aggregates sizes and Fe dissolution versus pH on the four IONP: (a) magnNP, (b) maghNP, (c) PC-magnNP and (d) HA-magnNP. The data were obtained at the same initial NP concentration (NP= 0.5 g L<sup>-1</sup>), ionic strength =  $5 \ 10^{-3}$  M NaCl, and starting Cu = 0.05 mM. The error bars, resulting from triplicates, are within the markers. The intensity of IONP dissolution is represented by dark areas (black to light grey refer to high to decreased dissolution rate).

919

**Table 1:** Fe concentrations (mg L<sup>-1</sup>) released from the IONP relative to the pH (from triplicates). The 921 experiments were conducted at 0.5 g L<sup>-1</sup> IONP suspensions with a constant ionic strength of  $5.10^{-3}$  M

922 NaCl. LQ refers to the Fe limit of quantification (0.12  $\mu$ g L<sup>-1</sup>).

# 

	рН 3	рН 4	рН 5	pH 6	pH 7
MagnNP	$5.23 \pm 0.08$	$1.34 \pm 0.07$	$0.005 \pm 0.001$	<lq< th=""><th><lq< th=""></lq<></th></lq<>	<lq< th=""></lq<>
MaghNP	$1.63 \pm 0.07$	$0.33 \pm 0.05$	<lq< th=""><th><lq< th=""><th><lq< th=""></lq<></th></lq<></th></lq<>	<lq< th=""><th><lq< th=""></lq<></th></lq<>	<lq< th=""></lq<>
PC-magnNP	$0.009 \pm 0.001$	$0.001 \pm 0.001$	<lq< th=""><th><lq< th=""><th><lq< th=""></lq<></th></lq<></th></lq<>	<lq< th=""><th><lq< th=""></lq<></th></lq<>	<lq< th=""></lq<>
HA-magnNP	$0.006\pm0.001$	$0.0007 \pm 0.001$	<lq< th=""><th><lq< th=""><th><lq< th=""></lq<></th></lq<></th></lq<>	<lq< th=""><th><lq< th=""></lq<></th></lq<>	<lq< th=""></lq<>