



HAL
open science

Effect of Zn^{2+} and Cu^{2+} -bearing salts on the dissolution of silicate glasses

Odile Majérus, Victor de Seauve, Fanny Alloteau, Daniel Caurant, Grégory Lefèvre, Patrice Lehuédé, Isabelle Biron

► To cite this version:

Odile Majérus, Victor de Seauve, Fanny Alloteau, Daniel Caurant, Grégory Lefèvre, et al.. Effect of Zn^{2+} and Cu^{2+} -bearing salts on the dissolution of silicate glasses. *Glass Atmospheric Alteration: Cultural Heritage, Industrial and Nuclear Glasses*, Hermann, 2019, 9782705697945. hal-02375046

HAL Id: hal-02375046

<https://hal.science/hal-02375046>

Submitted on 21 Nov 2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

O. Majérus, V. de Seauve, F. Alloteau, D. Caurant, G. Lefèvre, P. Lehuédé, I. Biron.

in *Glass Atmospheric Alteration: Cultural Heritage, Industrial and Nuclear Glasses*, Eds. I. Biron, F. Alloteau, P. Lehuédé, O. Majérus, D. Caurant, Hermann Ed., ISBN978-2705697945, Paris (France) (2019) 235-237.

Effect of Zn²⁺ and Cu²⁺-bearing salts on the dissolution of silicate glasses

Odile Majérus***

Victor de Seauve***

Fanny Alloteau*

Daniel Caurant***

Grégory Lefèvre*

Patrice Lehuédé**

Isabelle Biron***

* Institut de Recherche de Chimie Paris, Chimie ParisTech, CNRS, PSL University, F-75005 Paris, France

** Centre de Recherche et de Restauration des Musées de France (C2RMF), F-75001 Paris, France

Zn²⁺-bearing salts have been used for a long time to protect the glass surface against corrosion of glassware in dishwashers¹, or of flat glass during transport and storage². However, the mechanisms by which Zn²⁺ ions diminish the extent of glass corrosion are not well known. In parallel to the study of the effects of Zn(II) salts on the kinetics and morphology of glass alteration in *atmospheric* conditions³, we investigated the effects of these salts on the glass alteration in *immersion* conditions, by measuring the glass dissolution kinetics in solutions bearing increasing concentrations of salts. In this text, the results for a mixed (Na,K) glass, of which composition is 71.3 SiO₂, 0.8 Al₂O₃, 0.8 MgO, 5.0 CaO, 11.0 Na₂O, 11.0 K₂O (wt%), are described and discussed. All the studied alkali, alkaline-earth-silicate glasses behaved the same way in these dissolution experiments, although their dissolution rate was different.

The experiments were conducted at 80°C and free pH, with an S/V ratio (S, exposed surface of glass, and V, volume of the solution) of about 0.5 cm⁻¹, according to the procedure described in (Tournié *et al.*, 2013). ICP-AES⁴ was used for solution analysis. Two observations can be first reported: (i) Whatever the nature of the counter-ion of the zinc salt in solution (chloride, ZnCl₂, nitrate, Zn(NO₃)₂, or citrate, Zn₃(C₆H₅O₇)₂), the results were the same. These counter-ions thus played no role in the dissolution experiments. (ii) The effects of the Zn(II) salts were apparent from a concentration of 10⁻³ M. This concentration is slightly above the solubility of Zn²⁺ ions with respect to Zn(OH)₂ at 80°C and pH = 6.5 (1.8.10⁻⁴ M). The normalized mass losses⁵, NL, in Na and in Si are shown as a function of time in figures 1a and 1b, for the experiments in pure water and in water with 10⁻³ M ZnCl₂. In pure water, the dissolution of the glass is incongruent. The release rate of alkalis is almost 10 times higher than that of Si and Ca (K and Ca NL are not shown). In water

¹ See the text of Karlheinz Hahn in this book

² See the text of Sophie Papin et al., in this book

³ See the text of Fanny Alloteau et al., in this book

⁴ Inductively-Coupled Plasma – Atomic Emission Spectroscopy

⁵ The normalized mass loss in element *i* is calculated by : $NL_i = \frac{c_i \times V}{m \times x_i \times \Sigma}$, where *c_i* is the concentration of element *i* in solution (g.L⁻¹), *V* is the volume of solution, *m* and *Σ* are the mass and specific surface of the glass powder exposed to the solution and *x_i* is the weight fraction of element *i* in the glass.

bearing 10^{-3} M ZnCl_2 salt, the release rate of alkalis was unchanged (figure 1a), while no release of Si and Ca could be detected for the first 20 days of the experiment (figure 1b). During this 20 days period, the Zn^{2+} concentration decreased in the solution (figure 1b), and the pH was constant around 7 (figure 1a). The leaching of alkalis corresponds to a pH increase well observed in the pure water experiment (up to pH 10.5, not shown). The leaching rate was the same in the experiment with ZnCl_2 solution, but the pH stayed neutral because the formation of hydroxide anions was immediately followed by the precipitation of the Zn^{2+} ions, forming zinc hydroxide. This direct relationship is demonstrated in figure 2: the total amount of cations in the solution was constant, the loss in Zn^{2+} compensating exactly the release in alkalis. After 20 days, when all Zn^{2+} ions have precipitated, the pH started to increase (figure 1a) and Si started to dissolve (figure 1b).

The nature of the Zn(II) hydroxide precipitates is unclear. At the end of the experiments, only hemimorphite of composition $\text{Zn}_4\text{Si}_2\text{O}_7(\text{OH})_2 \cdot \text{H}_2\text{O}$, was observed in the altered glass powder (figure 3). Hemimorphite is a deeply insoluble hydroxysilicate phase: in equilibrium with this phase, the Si solubility is $3.2 \cdot 10^{-9}$ M at 80°C and pH 7 (according to the solubility constant given in (Mc Phail *et al.*, 2006)). The observation of hemimorphite raised two questions: (a) Was Si entirely immobilized in hemimorphite during these first 20 days? (b) Was the existence of such an insoluble phase, responsible for the Zn(II) precipitation and the related buffering power of the ZnCl_2 solution? By assuming that all Zn^{2+} ions eventually formed hemimorphite, we calculated that only one third of the Si, that had not been released compared with the pure water experiment, had been fixed in hemimorphite crystals. The two other thirds had not been dissolved, probably thanks to the neutral pH that had stabilized the silicate network with respect to dissolved silica. To answer question (b), the same experiments were carried out with CuCl_2 bearing solutions. According to available thermodynamic data⁶, Cu^{2+} ions and Zn^{2+} ions have the same solubilities (with respect to their hydroxides), but Cu^{2+} ions do not form insoluble hydroxysilicates analogous to hemimorphite. Indeed, the dissolution behaviors were the same with CuCl_2 and with ZnCl_2 (not shown). Only a brown precipitate bearing Cu and no Si (according to SEM-EDX) was observed and attributed to amorphous $\text{Cu}(\text{OH})_2$. Thus, the existence of hemimorphite has no link with the dissolution behavior, which is rather explained by the supersaturation of the solution with respect to the metal hydroxide. In the ZnCl_2 experiment, it is possible that $\text{Zn}(\text{OH})_2$ precipitated first and transformed into hemimorphite after some induction time.

Therefore, a possible explanation for the beneficial effect of Zn(II) salts on glass aqueous alteration relies on the buffering power of supersaturated Zn(II) solutions in contact with the glass (the glass surface probably plays a nucleating role in the Zn(II) hydroxide precipitation, as demonstrated in (Spark *et al.*, 1995) for amorphous silica surface). In such a solution, alkalis are released “normally”, but the pH is maintained neutral thanks to Zn(II) precipitation. Consequently, the silicate network of the glass is protected: the glass is leached, but it does not appear “corroded”. It is possible that part of the protection may also be due to the passivation of the glass surface by Zn(II) chemisorption, as demonstrated for the atmospheric alteration conditions. This passivation would vanish when hemimorphite forms. Further studies are necessary to address this question.

References

Mc Phail, D. C., Summerhayes, E., Jayaratne, V., Christy, A., "Hemimorphite solubility and stability of low-T zinc minerals", *Geochim. Cosmochim. Acta*, 70, 2006, A414.

Spark, K. M., Johnson, B. B., Wells, J. D., "Characterizing heavy-metal adsorption on oxides and

⁶ Database (log K values at 20°C) provided by the Hydra and Medusa softwares, by Ignasi Puigdomenech, Department of Chemistry, Kungliga Tekniska Högskolan, Stockholm, Sweden (2013).

oxyhydroxides", *Eur. J. Soil Sci.*, 46, 1995, p. 621–631.

Tournié, A., Majérus, O., Lefèvre, G, Rager, M.-N., Walmé, S., Caurant, D., Barboux, P., "Impact of boron complexation by Tris buffer on the initial dissolution rate of borosilicate glasses", *J. Colloid Interface Sci.*, 400, 2013, p. 1261–1267.




Fig. 1a: Na normalized leached fraction of glass powder as a function of time, in pure water (black dots) and in ZnCl₂ solution (pink squares). The pH of the ZnCl₂ solution during the experiment is depicted on the right axis (blue crosses).




Fig. 1b: Si normalized leached fraction of glass powder as a function of time, in pure water (black dots) and in ZnCl₂ solution (pink squares). The Zn²⁺ concentration of the ZnCl₂ solution during the experiment is depicted on the right axis (green diamonds).




Fig. 2: Ionic concentrations in the ZnCl₂ solution during the dissolution experiment. The alkali and alkaline-earth concentration increases with time due to glass leaching (green dots). The Zn²⁺ concentration decreases with time because of subsequent zinc hydroxide precipitation (pink dots). The total cationic concentration stays constant for electroneutrality reasons (black squares).




Fig. 3: SEM image (secondary electrons) of the altered glass powder after the dissolution experiment in the ZnCl₂ solution. The surface of the glass grain is covered by hemimorphite precipitated crystals (Zn₄Si₂O₇(OH)₂.H₂O).