

# Influence of two-dimensional oxide nanosheets seed layers on the growth of (100)BiFeO3 thin films synthesized by chemical solution deposition

V. Bouquet, F. Baudouin, Valérie Demange, S. Députier, Sophie Ollivier, Loïc Joanny, L. Rault, A. Fouchet, M. Guilloux-Viry

# ▶ To cite this version:

V. Bouquet, F. Baudouin, Valérie Demange, S. Députier, Sophie Ollivier, et al.. Influence of twodimensional oxide nanosheets seed layers on the growth of (100)BiFeO3 thin films synthesized by chemical solution deposition. Thin Solid Films, 2020, E-MRS Oxide Films VII, 693, pp.137687. 10.1016/j.tsf.2019.137687 . hal-02378433

# HAL Id: hal-02378433 https://hal.science/hal-02378433

Submitted on 3 Feb 2020

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# **Highlights**

- Synthesis of BiFeO<sub>3</sub> thin films by chemical solution deposition.
- Randomly oriented growth of BiFeO3 films on silica and (100)Si.
- Highly (100) oriented growth of BiFeO3 on Ca2Nb3O10 nanosheets seed layers.
- Low cost processes at low temperature on inexpensive large area substrates.

buind

# Influence of two-dimensional oxide nanosheets seed layers on the growth of (100)BiFeO<sub>3</sub> thin films synthesized by chemical solution deposition

V. Bouquet<sup>a\*</sup>, F. Baudouin<sup>a</sup>, V. Demange<sup>a,b</sup>, S. Députier<sup>a</sup>, S. Ollivier<sup>a</sup>, L. Joanny<sup>b</sup>, L. Rault<sup>b</sup>,

A. Fouchet<sup>b</sup>, M. Guilloux-Viry<sup>a,b</sup>

<sup>a</sup>Univ Rennes, CNRS, ISCR - UMR 6226, 263 Avenue du Général Leclerc, F-35042 Rennes,

France

<sup>b</sup>Univ Rennes, CNRS, ScanMAT - UMS 2001, 263 Avenue du Général Leclerc, F-35042

Rennes, France

<sup>c</sup>NORMANDIE UNIV, ENSICAEN, UNICAEN, CNRS, CRISMAT, 6 Boulevard du Maréchal

Juin, F-14050 Caen, France

\* Corresponding author

E-mail address: valerie.bouquet@univ-rennes1.fr

## ABSTRACT

Complex oxide thin films of high quality, such as the multiferroic BiFeO<sub>3</sub> (BFO) material, are required for integrated oxides electronics. However, the properties of these materials are strongly dependent on their crystalline orientation and their optimal performances are usually obtained on expensive single-crystal substrates. A lower cost alternative approach is the use of oxide nanosheets seed layers that can be deposited on any substrate, including silicon (Si) used in CMOS technology, for the growth of complex oxides with the desired crystallographic orientation.

In this work, BFO films were deposited by chemical solution deposition using polymeric precursor method. First, the optimization of synthesis parameters was performed on amorphous silica and on (100)Si substrates. The structural and microstructural characterizations revealed a polycrystalline growth of the BFO films on both substrates and showed the influence of the synthesis temperature, in particular to obtain the pure perovskite phase. The influence of a two-dimensional nanosheets seed layer was then investigated. Ca<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub><sup>-</sup> nanosheets were prepared by the exfoliation process of HCa<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub> phase that is obtained by cation exchange of the layered KCa<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub> niobate in an acidic solution. The nanosheets were deposited directly on both substrates by Langmuir-Blodgett process, followed by the subsequent deposition of BFO by chemical solution deposition. X-ray diffraction and transmission electronic microscopy experiments showed a highly oriented (100) growth of the BFO thin films confirming the great interest of two-dimensional nanosheets seed layers.

Keywords: bismuth ferrite; thin films; chemical solution deposition; oxide nanosheets

## 1. Introduction

In microelectronics, the ever decrease of device dimensions, *i.e.* the miniaturization of the electronic elements, arrives at a limit due to intrinsic physical limitations for Si-based electronics. In addition to miniaturization, the integration of multifunctional materials can offer the inclusion of advanced functionalities of the marketed devices. In this context, complex oxides have potential applications due to their wide range of versatile functionalities. However, the properties of these multifunctional materials are strongly dependent on their crystalline orientation. Thus deposition on costly and sized-limited single-crystal substrates is usually required to obtain high performances. For integrated oxide electronic, it is possible to use two-dimensional (2D) oxide nanosheets seed layers that can be deposited on any substrate, including silicon used in CMOS technology, and to grow complex oxides with the desired crystallographic orientation. Highly oriented perovskites (SrTiO<sub>3</sub>, Pb(Zr,Ti)O<sub>3</sub>, etc.) and binary oxide films (such as TiO<sub>2</sub>, ZnO) have been obtained on glass, silicon or stainless steel substrates using 2D nanosheets seed layers with different crystallographic properties in the 2D network, for example square lattice for Ca<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub><sup>-</sup> or hexagonal lattice for MoO<sub>2</sub><sup>0,4-</sup> [1-6].

Among many functional oxides, multiferroic materials are of first interest thanks to their both ferroelectric and ferromagnetic properties and the possible magnetoelectric coupling. In particular, the BiFeO<sub>3</sub> (BFO) material has attracted much attention because of its room temperature multiferroic properties [7]. In fact, this material has a rhombohedral distorted perovskite structure and presents high ferroelectric and magnetic transition temperatures: 1103 K for  $T_c$  (Curie temperature) and 643 K for  $T_N$  (Néel temperature) in bulk material, respectively. These properties, including magnetoelectric coupling effects, make this

material very promising for multifunctional devices in different fields of applications (electronics, spintronics, piezotronics, etc.) [8]. Moreover, it is a non-toxic and lead free material.

Many different deposition methods have been used to grow BFO thin films including pulsed laser deposition [9, 10], chemical vapor deposition [11, 12], sputtering [13, 14] and chemical solution deposition using the sol-gel process [15, 16] or the polymeric precursor method [17, 18]. The chemical solution deposition (CSD) consists in the deposition of a solution on a substrate, typically by dip or spin coating, followed by subsequent annealing treatments of the wet film in order to crystallize the desired material [19]. The CSD presents various advantages: the possibility of depositing on large area surfaces, a precise control of the stoichiometry, low temperatures of synthesis and the use of simple equipment without vacuum or controlled atmosphere necessity. To prepare the coating solution, the polymeric precursor method, derived from the Pechini process [20], is particularly attractive because it is carried out in aqueous media with the use of relatively cheap precursors [21-23].

In this context, the aim of the present work is to study the growth of BFO thin films by CSD, using polymeric precursor method, on amorphous silica and (100) silicon substrates. In particular the influence of 2D oxide nanosheets seed layers was investigated in order to provide a low-cost route for the integration of oriented BFO thin films which is favorable for high performances in microelectronics. The calcium niobate nanosheet with pseudo-perovskite structure,  $Ca_2Nb_3O_{10}$ , was selected as seed layer to promote the oriented growth of BFO because its crystallographic 2D unit cell is close to that of the perovskite.

#### 2. Experimental details

# 2.1. Synthesis of BFO films by CSD

The BFO thin films were prepared by CSD using the polymeric precursor method to prepare the coating solution. This method based on the Pechini process [20] consists in preparing a polymeric resin where the metallic ions are uniformly dispersed at the atomic level. This resin is obtained by complexing the metallic cations with citric acid in an aqueous solution. Then the addition of ethylene glycol provokes the polymerization of these metal citrates at a slightly increased temperature. The precursors used in this study were bismuth nitrate Bi(NO<sub>3</sub>)<sub>3</sub>;5H<sub>2</sub>O, iron nitrate Fe(NO<sub>3</sub>)<sub>3</sub>;9H<sub>2</sub>O, monohydrated citric acid C<sub>6</sub>H<sub>8</sub>O<sub>7</sub>;H<sub>2</sub>O and ethylene glycol  $C_2H_6O_2$ . In a first step, the bismuth and iron solutions were prepared separately. The iron citrate solution was prepared by dissolving citric acid and iron nitrate in water, and ethylene glycol was then added. The bismuth precursor was first dissolved in ethylene glycol in order to avoid the formation of insoluble bismuth oxynitrate and then citric acid was introduced. For each cationic solution of iron and bismuth, the [citric acid:cation] molar ratio was [3:1] and the [citric acid:ethylene glycol] mass ratio was [40:60]. In a second step, the two cationic solutions were mixed in appropriate amounts (Bi:Fe = 1:1) and heated at 90°C under stirring. An excess of 5% in mass of Bi was added aiming to minimize the bismuth loss during the subsequent thermal treatments [17, 18]. Indeed the pure phase could not be obtained without bismuth addition. The viscosity of the obtained polymeric resin was then adjusted to  $\sim 40$  cP by controlling the water content (by addition or evaporation of water) and measured using a Brookfield DVII - Pro viscometer.

The obtained coating solution was spin coated at 1000 rpm for 3 seconds followed by a rotational speed at 4000 rpm for 10 seconds (Spin 150 SPS Europe) on amorphous silica (surface: 10x10 mm<sup>2</sup>, 0.5 mm thick) and on (100)Si substrates (surface: 10x10 mm<sup>2</sup>, 0.7 mm thick). The wet films were then submitted to two thermal treatments in air (i) pyrolysis at 400°C for 3 hours to eliminate the organic matter, (ii) calcination in the range 450°C-600°C for 2 hours in order to determine the optimal temperature of the phase synthesis on both

6

substrates. Two layers of coating solution were deposited for each film. The pyrolysis was carried out after each deposition step, whereas the crystallization treatment was only performed once the 2 layers were deposited. In order to study the influence of a 2D nanosheets seed layer, BFO films (2 layers) were also deposited by CSD on  $Ca_2Nb_3O_{10}^{-1}$  nanosheets layers previously deposited on both substrates by Langmuir-Blodgett process.

# 2.2. Synthesis of nanosheets seed layers by Langmuir-Blodgett process

The synthesis of oxide nanosheets is based on the exfoliation of layered phases [1-6, 24]. In this present work, the layered perovskite Dion-Jacobson KCa<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub> phase ( $P2_1/m$ , a = 7.741 Å, b = 7.707 Å, c = 14.859 Å,  $\beta = 97.51^{\circ}$ , JCPDS card No. 01-075-9853) was first synthesized by solid state reaction at 1100°C for 10 h from K<sub>2</sub>CO<sub>3</sub>, Nb<sub>2</sub>O<sub>5</sub> and CaCO<sub>3</sub> precursors in a molar ratio of 1.35:4:3. The potassium calcium niobate was then protonated by exchange in 6 M HNO<sub>3</sub> for 3 days. During this step, the potassium ions K<sup>+</sup>, located between negatively charged perovskite slabs (made of three NbO<sub>6</sub> corner-shared octahedra layers) are exchanged by protons, to form hydrated protonated HCa<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub> '1.5H<sub>2</sub>O compound (a = 3.854 Å, c = 16.225 Å, JCPDS card No. 00-39-0915). The protonated phase was then exfoliated by reaction with tetra(n-butyl)ammonium hydroxide (TBAOH) in a molar ratio 1:1 for 14 days. The exfoliated (TBA<sup>+</sup>, Ca<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub><sup>-</sup>) nanosheets thus form a stable aqueous colloidal suspension.

After dilution, the colloidal suspension was deposited on amorphous silica and (100)Si by Langmuir-Blodgett process [25-27] with a KSV NIMA instrument. In this method, the colloidal suspension was placed in a trough. The nanosheets float at the air/water interface due to the moderate amphiphilic role of tetra(n-butyl)ammonium cations. Subsequently, the substrate was immersed vertically in the suspension and two barriers were then moved to compress the air-liquid interface (compression speed of 0.5 mm.s<sup>-1</sup>) until an optimized surface

pressure of 15 mN.m<sup>-1</sup>. The substrate was then slowly withdrawn from the dispersion and the obtained nanosheets seed layer was then dried at 110°C for 1-2 hours and treated under UV light for 45 minutes to remove water and to decompose TBA<sup>+</sup> ions.

# 2.3. Characterizations

The structural characteristics were investigated by X-ray diffraction (XRD) by using a  $\theta - 2\theta$  diffractometer (D8 Advance, BRUKER) with a monochromatized CuK<sub>a1</sub> wavelength ( $\lambda = 1.54056$  Å). The surface and the cross-section of the films were observed at 10 kV by scanning electron microscopy (SEM, JSM 7100F, JEOL) in order to determine their morphology and their thickness. Atomic Force microscopy (AFM) images were performed (NT-MDT NTEGRA) with silicon point probe.

Transmission electron microscopy (TEM) experiments were performed using a LaB<sub>6</sub> Jeol 2100 instrument equipped with an Oxford Aztec 80 mm<sup>2</sup> SDD device for EDXS analysis. Transmission electron brightfield and electron diffraction patterns were recorded using a GATAN Orius SC200D CCD (charge coupled device) camera and high-resolution images were recorded using a GATAN US 1000XP camera. Plane-view film samples were obtained by scratching the thin film from the substrate with a diamond tip and by collecting the obtained fragments on an amorphous carbon copper grid (Agar). Cross-section samples were glued together with film sides facing each other, then thinned by using diamond-lapping films, followed by dimpling with diamond pastes and Ar-milling in a 1010 Fischione instrument.

# 3. Results and discussion

#### 3.1. BFO thin films grown on amorphous silica and (100)Si

Fig. 1a and 1b show the XRD patterns obtained for BFO films deposited on amorphous silica and (100)Si, respectively, and heat-treated at different temperatures. The pure BFO phase was obtained for all the synthesis temperatures on both substrates except for 600°C where some additional peaks of weak intensity were observed. Many authors have reported the presence of secondary phases such as Bi<sub>2</sub>O<sub>3</sub>, Bi<sub>2</sub>Fe<sub>4</sub>O<sub>9</sub> or iron oxides in BFO thin films synthesized by different methods and often deposited on Pt/Ti/SiO<sub>2</sub>/ Si substrates [9, 10, 15, 17, 18]. The presence of these phases mainly depends on the deposition or heat treatment temperatures of the films. However, F. Tyholdt *et al.* have reported the possible presence of Bi<sub>2</sub>SiO<sub>5</sub> phase for a BFO film deposited on glass substrate by CSD and treated at 600°C [15]. In this present work, the additional peaks of weak intensity at 20 =11.6°, 23.3° and 35.3° observed at 600°C can be ascribed to the (200), (400) and (600) reflections of Bi<sub>2</sub>SiO<sub>5</sub>, respectively (*Cmc*2<sub>1</sub>, *a* = 15.217 Å, *b* = 5.477 Å and *c* = 5.325 Å, JCPDS card No. 00-036-0287). The small extra peak at 20 = 29.2° can be attributed to the main peak of the bulk Bi<sub>2</sub>SiO<sub>5</sub> phase, *i.e.* the (311) reflection. The formation of the (100) highly oriented Bi<sub>2</sub>SiO<sub>5</sub> is probably due to a reaction of BFO with the substrate at 600°C.

For all samples, the BFO peaks were indexed in the rhombohedral structure (R3m, a = 3.962 Å,  $\alpha = 89.40^{\circ}$ , JCPDS card No. 01-074-2016) and as expected, no preferential orientation was observed on both substrates (polycrystalline films). Indeed, random orientation of BFO is not surprising on amorphous substrate such as silica, and on silicon (cubic structure, a = 5.430 Å, JCPDS No. 00-27-1402) due to the incompatibility between their respective crystalline structure and the presence of amorphous SiO<sub>2</sub> on the substrate surface which is not removed with CSD method.

The SEM and AFM images of the films obtained at 500°C on silica and on (100)Si are displayed in Fig. 2. The films are crack-free and homogeneous on both substrates and present similar microstructures (Fig. 2a,b) with a uniform grain size around 80 nm (Fig. 2c,d). No

significant change of the microstructure was observed in SEM images as a function of heat treatment temperature (not shown here). The films have a thickness around 200 nm and 150 nm on silica and (100)Si respectively, as observed on the SEM cross-sectional views (insets Fig. 2a,b).

#### 3.2. BFO thin films grown on nanosheets seed layers

Fig. 3a and 3b show the XRD patterns obtained for BFO films deposited on nanosheets/ silica and on nanosheets/(100)Si respectively, and calcined at 500°C-2h. In contrast to the polycrystalline films directly deposited on silica and Si at this temperature, two intense peaks can be observed and indexed as (100) and (200) reflections of the distorted perovskite structure of BFO, which indicate clearly that the films deposited on nanosheets present a highly (100) oriented growth. The Ca<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub> nanosheets have a perovskite-related structure with a 2D pseudo-square lattice of *a* close to 0.386 nm [1], which is close to the BFO lattice parameter (a = 0.3962 nm), giving a small lattice mismatch of +2.64 %. Thus nanosheets seed layer can induce an oriented growth of BFO, synthesized by CSD, even on amorphous substrates or on substrates presenting structural incompatibilities. The mechanism of the film growth is a local epitaxy of the BFO phase on each nanosheet.

Nagasaka *et al.* [28] reported the preferential (100) growth of Mn-doped BFO films (300 nm thick) synthesized by CSD (using methoxyethanol solvent) at 500°C on Ca<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub> nanosheets layers previously deposited on (111)Pt/TiO<sub>2</sub>/(100)Si and(111)Pt/ stainless steel substrates. In the case of platinized silicon substrate, the presence of the Bi<sub>2</sub>Fe<sub>4</sub>O<sub>9</sub> secondary phase was observed. Dral *et al.* [29] reported the epitaxial growth of a stack of SrTiO<sub>3</sub> (42 nm thick), SrRuO<sub>3</sub> (18 nm) and BiFeO<sub>3</sub> (20 nm) grown by pulsed laser deposition at 700°C on Ca<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub><sup>-</sup> nanosheets layers previously deposited on (001) phlogopite mica substrates. In our case, phi-scans XRD patterns (not shown here) performed with a 4-circle texture

diffractometer revealed no in-plane preferential orientation of the BFO films. This result is not surprising since the nanosheets of several micrometers in lateral size are randomly turned on the substrates surface (Fig. 4).

On the XRD patterns of Fig. 3a and 3b, some other peaks of weak intensities can be observed that could be attributed to a reaction of the nanosheets with BFO and/or with the substrate leading to the formation of secondary phases, possibly  $Bi_{5.96}Ca_{1.76}Nb_{0.28}O_{11.14}$  (JCPDS card No. 00-079-9855) for the peak located at  $2\theta = 19.8^{\circ}$ . However, it is quite difficult to confirm with certainty the composition of this phase with only one visible peak. H. Yan *et al.* [30] reported reaction of  $Ti_{0.87}O_2$  nanosheet seeds with grown TiO<sub>2</sub>. However, in their case, the reaction occurred because of the similar composition. The other observed extra peaks may correspond to the preferential orientation of a layered phase with a lattice constant equal to about *c* = 14.1-14.3 Å. In order to check if these last peaks may be associated to some of the nanosheets, XRD pattern was performed on a nanosheets layer deposited on Si. Magnification of this pattern (Fig. 3c) displays peaks corresponding to an inter-reticular distance of about 15.4 Å, in agreement with a previous study [31]. The shift of the extra peaks observed in the BFO films on nanosheets (from 15.4 to 14.1-14.3 Å) may correspond to the formation of a layered Bi/Si-Ca<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub>. Further investigations are underway to determine the exact composition of these secondary phases.

The TEM-EXDS analyses performed on the films confirmed the presence of Bi, Fe, O, Ca and Nb with a Bi/ Fe molar ratio equal to 1.

The SEM and AFM images of the films deposited on nanosheets seed layers on both substrates are displayed in Fig. 4. The films are relatively dense and homogeneous (Fig. 4a,b) with a uniform grain size around 80 nm (Fig. 4c,d) and present similar microstructures to those obtained for the films directly deposited on bare substrates. They have a thickness around 150 nm, as observed on the cross-sectional views (insets in Fig. 4a,b). Figure 4e and

4f show the AFM images of the nanosheets deposited on silica and (100)Si by Langmuir-Blodgett process, before the BFO deposition. Nanosheets of several micrometers lateral size are clearly observed with a relatively good coverage on both substrates.

The TEM images performed on the BFO film deposited on nanosheets/(100)Si are displayed in Fig. 5. The in-plane view (Fig. 5a) revealed that the film is made of 50-100 nm wide crystals. Fig. 5b shows a [100] zone axis selected-area electron diffraction pattern of the film from an in plane-view specimen, in agreement with the preferential orientation observed by XRD. On the cross-sectional view (Fig 5c), the thickness of the 2 slabs of the film glued together is estimated to 640 nm, thus a film thickness of ~ 320 nm. Other areas observed by TEM (not shown) indicate local variations of film thickness from 150 to 400 nm. The BFO film is made of small grains and present some porosities.

Fig. 5d is a high magnification TEM micrograph of the cross-sectional sample, showing the morphology of the BFO film on the nanosheets/Si substrate. It can be observed the  $SiO_2$  layer (in white) and above a layer with a continuous 6 nm thick layer. The secondary phase previously observed by XRD, possibly identified as  $Bi_{5.96}Ca_{1.76}Nb_{0.28}O_{11.14}$ , could be located in this 6 nm thick layer.

# 4. Conclusions

Single-phase BFO thin films were obtained at 400°-500°C by CSD using polymeric precursor method on bare amorphous silica and (100)Si substrates. These randomly oriented films present homogeneous microstructures with uniform grains size of 80 nm. The introduction of a nanosheets seed layer did not change the films microstructure but induced a highly oriented (100) growth of BFO on both substrates. However, secondary phases were

observed that could be attributed to  $Bi_{5.96}Ca_{1.76}Nb_{0.28}O_{11.14}$  and to a layered Bi/ Si-Ca<sub>2</sub>Nb<sub>3</sub>O<sub>10</sub> with a lattice constant equal to about c = 14.1-14.3 Å. These results are nevertheless promising to provide a low-cost route for the integration of oriented BFO thin films in microelectronics. Indeed, the methods of synthesis for BFO thin films as well as for the nanosheets seed layer use low-cost precursors and simple equipment, and enable large area of deposition at low temperature on inexpensive substrates.

## Acknowledgement

The authors thank the French "Agence Nationale de la Recherche" (ANR) in the framework of the POLYNASH project (ANR-17-CE08-0012). SEM and TEM experiments were performed on CMEBA and THEMIS platforms (ScanMAT, UMS 2001, University of Rennes 1-CNRS). ISCR and ScanMAT received a financial support from the Région Bretagne, Rennes Métropole, the Département d'Ille et Vilaine and the European Union (CPER-FEDER 2007–2014 and CPER 2015-2020 MULTIMAT ScanMAT).

## **Declaration of interest**

None

# **Author Contributions Section**

V. Bouquet: Investigation, Validation, Writing - Original Draft, Writing - Review & Editing,
Visualization. F. Baudouin: Investigation, Writing - Review & Editing. V. Demange:
Investigation, Writing - Review & Editing, Funding acquisition. S. Députier: Investigation,
Writing - Review & Editing. S. Ollivier: Investigation, L. Joanny: Investigation, L. Rault:
Investigation, A. Fouchet: Project administration, Funding acquisition, Writing - Review &
Editing. M. Guilloux-Viry: Investigation, Writing - Review & Editing.

# References

- [1] T. Shibata, K. Fukuda, Y. Ebina, T. Kogure, T. Sasaki, One-Nanometer-Thick Seed Layer of Unilamellar Nanosheets Promotes Oriented Growth of Oxide Crystal Films, Adv. Mater. 20 (2008) 231. doi:10.1002/adma.200701381.
- M. Nijland, S. Kumar, R. Lubbers, D.H.A. Blank, G. Rijnders, G. Koster, J.E. ten Elshof, Local Control over Nucleation of Epitaxial Thin Films by Seed Layers of Inorganic Nanosheets, ACS Appl. Mater. Interfaces 6 (2014) 2777. doi:dx.doi.org/10.1021/am4052624.
- [3] Y. Minemura, D. Ichinose, K. Nagasaka, J.W. Kim, H. Shima, K. Nishida, T. Kiguchi, T.J. Konno, N. Oshima, H. Funakubo, H. Uchida, Polar-axis-oriented crystal growth of tetragonal PZT films on stainless steel substrate using pseudo-perovskite nanosheet buffer layer, AIP Adv. 5 (2015) 77139. https://doi.org/10.1063/1.4927208.
- [4] T. Shibata, H. Takano, Y. Ebina, D.S. Kim, T.C. Ozawa, K. Akatsuka, T. Ohnishi, K. Takada, T. Kogure, T. Sasaki, Versatile van der Waals epitaxy-like growth of crystal films using two-dimensional nanosheets as a seed layer: orientation tuning of SrTiO<sub>3</sub> films along three important axes on glass substrates, J. Mater. Chem. C 2 (2014) 441. doi:10.1039/c3tc31787k.
- [5] K. Kikuta, K. Noda, S. Okumura, T. Yamaguchi, S-i. Hirano, Orientation control of perovskite thin films on glass substrates by the application of a seed layer prepared from oxide nanosheets. J. Sol-Gel Sci. Technol. 42 (2007) 381. doi:10.1007/s10971-006-0200-z.
- [6] M. D. Nguyen, H. Yuan, E. P. Houwman, M. Dekkers, G. Koster, J. E. ten Elshof, G. Rijnders, Highly oriented growth of piezoelectric thin films on silicon using two-dimensional nanosheets as growth template layer, ACS Appl.Mater.& Interf. 82 (2016) 31120. doi: 10.1021/acsami.6b09470.

- [7] G. Catalan, J. Scott, Physics and Applications of Bismuth Ferrite, Adv. Mater. 21 (2009) 2463. doi:10.1002/adma.200802849.
- [8] D. Sando, A. Barthélémy, M. Bibes, BiFeO<sub>3</sub> epitaxial thin films and devices: past, present and future, J. Phys. Condens. Matter 26 (2014) 473201. doi:10.1088/0953-8984/26/47/473201.
- [9] T. Ahmed , A. Vorobiev, S. Gevorgian, Growth temperature dependent dielectric properties of BiFeO<sub>3</sub> thin films deposited on silica glass substrates, Thin Solid Films 520 (2012) 4470. doi:10.1016/j.tsf.2012.02.082.
- [10] H. W. Chang, F.T.Yuan, S.H. Tien, C.Y. Shen, C.R.Wang, S. U. Jen, Effect of Substrates on the Structure and Ferroelectric Properties of Multiferroic BiFeO<sub>3</sub> Films, IEEE Trans. on magnetics, 50, No.1 (2014) 2500604. doi:10.1109/TMAG.2013.2278702.
- [11] N. Deepak, P. Carolan, L. Keeney, P. F. Zhang, M. E. Pemble, R. W. Whatmore, Bismuth Self-Limiting Growth of Ultrathin BiFeO<sub>3</sub> Films, Chem. Mater. 27 (2015) 6508. doi:10.1021/acs.chemmater.5b03034.
- [12] J. Thery, C. Dubourdieu, T. Baron, C. Ternon, H. Roussel, F. Pierre, MOCVD of BiFeO<sub>3</sub>
   Thin Films on SrTiO<sub>3</sub>, Chem. Vap. Deposition 13 (2007) 232.
   doi:10.1002/cvde.200606571.
- [13] G.A. Gomez-Iriarte, C. Labre, L.A.S. de Oliveira, J.P. Sinnecker, Pure phase BiFeO<sub>3</sub> thin films sputtered over Si: A new route towards high magnetization, J. Magn. Magn. Mater. 460 (2018) 83. https://doi.org/10.1016/j.jmmm.2018.03.056.
- [14] M. Gaidi, N. Somrani, L. Stafford, In situ investigation of magnetron sputtering plasma used for the deposition of multiferroic BiFeO<sub>3</sub> thin films, J Mater Sci: Mater Electron 28 (2017) 15749. doi:10.1007/s10854-017-7178-x.

- [15] F. Tyholdt, S. Jørgensen, H. Fjellvåg, A.E. Gunnæs, Synthesis of oriented BiFeO<sub>3</sub> thin films by chemical solution deposition: Phase, texture, and microstructural development, J. Mater. Res., 20 (2005) 2127. doi:10.1577/JMR.2005.0263.
- [16] R. R. Awasthi, K. Asokan, B. Das, Effect of molar concentration on structural, magnetic domain and optical properties of BiFeO<sub>3</sub> thin films, Appl. Phys. A 125 (2019) 338 1. https://doi.org/10.1007/s00339-019-2560-6.
- [17] A. Z. Simões , A. H. M. Gonzalez, L. S. Cavalcante, C. S. Riccardi, E. Longo, J. A. Varela, Ferroelectric characteristics of BiFeO<sub>3</sub> thin films prepared via a simple chemical solution deposition, J. Appl. Phys. 101 (2007) 074108. https://doi.org/10.1063/1.2715513.
- [18] C.R. Foschini, M.A. Ramirez, S.R. Simoes, J.A. Varela, E. Longo, A.Z. Simoes, Piezoresponse force microscopy characterization of rare-earth doped BiFeO<sub>3</sub> thin films grown by the soft chemical method, Ceram. Int. 39 (2013) 2185. http://dx.doi.org/10.1016/j.ceramint.2012.08.083.
- [19] I. Bretos, R. Jiménez, J. Ricote, M. L. Calzada, Low-temperature crystallization of solution derived metal oxide thin films assisted by chemical processes, Chem. Soc. Rev. 47 (2018) 291. doi: 10.1039/c6cs00917d.
- [20] M. Pechini, Method of Preparing Lead and Alkaline-Earth Titanates and Niobates and Coating Method Using the Same to Form a Capacitor, US Patent 3330697, 1967.
- [21] Q. Simon, V. Bouquet, A. Perrin, M. Guilloux-Viry, Synthesis of KTa<sub>x</sub>Nb<sub>1-x</sub>O<sub>3</sub> (KTN) powders and thin films by polymeric precursor method, Solid State Sci. 11 (2009) 91. doi:10.1016/j.solidstatesciences.2008.06.015.
- [22] M. C. F. Alves, R. M. M. Marinho, G. P. Casali, M. Siu-Li, S. Députier, M. Guilloux-Viry, A. G. Souza, E. Longo, I. T. Weber, I.M.G. Santos, V. Bouquet, Influence of the network modifier on the characteristics of MSnO<sub>3</sub>(M = Sr and Ca) thin films synthesized

by chemical solution deposition, J. Solid State Chem. 199 (2013) 34. http://dx.doi.org/10.1016/j.jssc.2012.11.014

- [23] A.L. Menezes de Oliveira, V. Bouquet, V. Dorcet, S. Ollivier, S. Députier, A. G.de Souza, M. Siu-Li, E. Longo, I. T.Weber, I. M. G. dos Santos, M. Guilloux-Viry, Evolution of the structural and microstructural characteristics of SrSn<sub>1-x</sub>Ti<sub>x</sub>O<sub>3</sub> thin films under the influence of the composition, the substrate and the deposition method, Surf. and Coatings Technol. 313 (2017) 361. http://dx.doi.org/10.1016/j.surfcoat.2017.01.082.
- [24] A. S. Maia, F. Cheviré, V. Demange, V. Bouquet, M. Pasturel, S. Députier, R. Lebullenger, M. Guilloux-Viry, F. Tessier, Preparation of niobium based oxynitride nanosheets by exfoliation of Ruddlesden-Popper phase precursor, Solid State Sci. 54 (2016) 17. http://dx.doi.org/10.1016/j.solidstatesciences.2015.11.013.
- [25] M. Muramatsu, K. Akatsuka, Y. Ebina, K. Wang, T. Sasaki, T. Ishida, K. Miyake, M. Haga, Fabrication of densely packed titania nanosheet films on solid surface by use of Langmuir–Blodgett deposition method without amphiphilic additives. Langmuir 21 (2005) (14) 6590. doi:10.1021/la050293f.
- [26] H. Yuan, R. Lubbers, R. Besselink, M. Nijland, and J. E. ten Elshof, Improved Langmuir-Blodgett titanate films via in situ exfoliation study and optimization of Deposition parameters. ACS Appl. Mater. Interfaces 6 (2014), 8567. dx.doi.org/10.1021/am501380d.
- [27] H. Yuan, M. Timmerman, M. van de Putte, P. Gonzalez Rodriguez, S. Veldhuis, J. E. ten Elshof, Self-Assembly of metal oxide nanosheets at liquid-air interfaces in colloidal solutions. J. Phys. Chem. C 120 (2016), 25411. doi: 10.1021/acs.jpcc.6b07961.
- [28] K. Nagasaka, N. Oshima, J. W. KIM, H. Shima, A. Akama, T. Kiguchi, K. Nishida, T. J. Konno, H. Funakubo, H. Uchida, Fabrication of (100)<sub>c</sub>-oriented Mn-doped bismuth ferrite

films on silicon and stainless steel substrates using calcium niobate nanosheets, J. Ceram. Soc. Jpn 123 (2015) 322. http://dx.doi.org/10.2109/jcersj2.123.322.

- [29] A.P. Dral, M. Nijland, G. Koster, J. E. ten Elshof, Film transfer enabled by nanosheet seed layers on arbitrary sacrificial substrates, APL Mater. 3 (2015) 056102. https://doi.org/10.1063/1.4921070.
- [30] H. Yuan, K. Han, D. Dubbink, G. Mul, G, J.E. ten Elshof, Modulating the external facets of functional nanocrystals enabled by two-dimensional oxide crystal templates. Acs Catalysis, 7 (2017), 6858. doi: 10.1021/acscatal.7b02605.
- [31] B.-W. Li, M. Osada, Y. Ebina, K. Akatsuka, K. Fukuda, T.Sasaki, High thermal robustness of molecularly thin perovskite nanosheets and implications for superior dielectric properties, ACSNano. 8 (2014) 5449. doi:10.1021/nn502014c

Journal

# **Figures captions**



Fig. 1: XRD patterns of BFO thin films deposited on silica (a) and on (100)Si (b) and heat-

treated at different temperatures.

out o



Fig.2: SEM and AFM images of BFO thin films synthesized at 500°C on silica (a,c) and on

(100)Si (b,d).



**Fig. 3:** XRD patterns of BFO thin films synthesized at 500°C on nanosheets (NS)/silica (a) and on nanosheets (NS)/(100)Si (b). Magnification of XRD pattern of nanosheets (NS)/ Si (c).



**Fig.4:** SEM and AFM images of BFO thin films synthesized at 500°C on nanosheets/silica (a,c) and on nanosheets/(100) Si (b,d). AFM images of nanosheets (before BFO deposition) on silica (e) and on (100)Si (f).



**Fig. 5:** TEM micrographs of the BFO thin film synthesized at 500°C on nanosheets/(100)Si: (a) in-plane view of the BFO film, (b) [100] zone axis electron diffraction pattern of a BFO film grain, (c,d) cross-sectional view of the sample at low and high magnification.