



HAL
open science

Magnetogyrotropic reflection from quantum wells induced by bulk inversion asymmetry

L. Kotova, V. Kats, A. Platonov, V. Kochereshko, R. André, L. Golub

► **To cite this version:**

L. Kotova, V. Kats, A. Platonov, V. Kochereshko, R. André, et al.. Magnetogyrotropic reflection from quantum wells induced by bulk inversion asymmetry. *Physical Review B*, 2019, 99 (3), pp.035302. 10.1103/PhysRevB.99.035302 . hal-02410545

HAL Id: hal-02410545

<https://hal.science/hal-02410545>

Submitted on 2 Dec 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Bulk inversion asymmetry induced magnetogyrotropic reflection from quantum wells

L. V. Kotova¹, V. N. Kats², A. V. Platonov², V. P. Kochereshko², R. André³, and L. E. Golub²

¹*ITMO University, 197101 St. Petersburg, Russia*

²*Ioffe Institute, 194021 St. Petersburg, Russia and*

³*Université Grenoble Alpes, CNRS, Institut NEEL, F-38000 Grenoble, France*

Bulk inversion asymmetry (BIA) of III-V and II-VI semiconductor quantum wells is demonstrated by reflection experiments in magnetic field oriented in the structure plane. The linear in the magnetic field contribution to the reflection coefficients is measured at oblique incidence of s and p polarized light in vicinity of exciton resonances. We demonstrate that this contribution to the reflection is caused by magnetogyrotropy of quantum wells, i.e. by the terms in the optical response which are linear in both the magnetic field strength and light wavevector. Theory of magnetogyrotropic effects in light reflection is developed with account for linear in momentum BIA induced terms in the electron and hole effective Hamiltonians. Theoretical estimates agree with the experimental findings. We have found the electron BIA splitting constant in both GaAs and CdTe based quantum wells is about three times smaller than that for heavy holes.

I. INTRODUCTION

In low-symmetry semiconductor quantum wells (QWs), various remarkable effects are present which are absent in bulk semiconductors and symmetric structures. The examples are spin-dependent phenomena, e.g. electrical spin orientation, conversion of nonequilibrium spin into electric current, electric-field induced spin rotations, as well as nonlinear optical effects like photogalvanics, for a review see Ref. [1]. These effects are symmetry-allowed in gyrotropic systems where some components of vectors (e.g. electric current) and pseudovectors (spin, magnetic field) transform identically under point symmetry operations [2]. The sources of gyrotropy are the bulk and the structure inversion asymmetries present in most of QW structures grown from III-V or II-VI semiconductors. The Structure Inversion Asymmetry (SIA) is present if the QW has different barrier materials or an electric field removes symmetry in the growth direction. Bulk Inversion Asymmetry (BIA) is present even in QWs with symmetric heteropotential. BIA is caused by an absence of inversion center in the bulk material forming the QW layer. The most popular (001) QWs have the point symmetry group D_{2d} which is gyrotropic, and the BIA-induced effects are studied intensively [3].

Gyrotropy manifests itself in optics, and a powerful tool for its study is light reflection experiments. In particular, gyrotropy results in conversion of light polarization state at reflection. In QWs, an equivalence of the in-plane components of the photon momentum to an effective magnetic field result in natural optical activity [4]. The new group of phenomena called *magnetogyrotropic* effects take place in the presence of an external magnetic field [5, 6]. Magnetogyrotropy means the terms in the optical response which are linear in both the magnetic field strength and the photon wavevector. The magnetogyrotropy is absent in centrosymmetric systems, and in QWs it also stems from inversion asymmetry. The SIA induced magnetogyrotropy has been

demonstrated recently in reflection experiments [7]. The combination of SIA and magnetic field result in interesting phenomena in light emission which are greatly enhanced in semimagnetic QWs with grating [8]. However, for the study of these effects, special asymmetric design of QWs and hybrid plasmonic structures has been used in Refs. [7, 8]. By contrast, the BIA-induced magnetogyrotropy does not require special technological efforts. In the present work we use the fact that any QW grown from GaAs or CdTe is gyrotropic due to BIA, and demonstrate the BIA-induced magnetogyrotropy effects. We investigate reflection from QWs in vicinity of exciton resonances where the magnetogyrotropic effects are greatly enhanced.

Symmetry analysis allows us to choose a proper orientation of magnetic field and light incidence plane for study of the BIA contribution to light reflection. For this purpose we find the BIA contribution bilinear in both the photon wavevector \mathbf{q} and magnetic field \mathbf{B} to the non-local dielectric susceptibility tensor $\hat{\chi}$. For (001) QWs (point symmetry group D_{2d}), symmetry analysis and the Onsager principle yield the following magnetogyrotropic contributions to the susceptibility

$$\begin{aligned}\chi_{xx} \pm \chi_{yy} &= T_{\pm}(q_x B_x \mp q_y B_y), \\ \chi_{xy} = \chi_{yx} &= T(q_y B_x - q_x B_y).\end{aligned}\quad (1)$$

Here x, y are $\langle 100 \rangle$ axes in the QW plane, and T, T_+, T_- are three linearly-independent functions which will be found below.

In experiments, magnetogyrotropy manifests itself as an additional birefringence caused by both the magnetic field \mathbf{B} and light wavevector \mathbf{q} . These magnetogyrotropic contributions can be probed in reflection experiments. By contrast, the pure \mathbf{B} -linear terms in the reflection are forbidden by the time-inversion symmetry. It follows from Eq. (1) that the reflection coefficients at oblique incidence acquire the contributions linear in both \mathbf{q} and \mathbf{B} for s and p polarized light

$$\Delta r \propto q_{\parallel} B_{\parallel}, \quad (2)$$

where symbol \parallel denotes projections onto the QW plane. This relation holds for incidence plane oriented along $\langle 100 \rangle$ crystallographic directions. Equation (2) demonstrates that in the \mathbf{B} -linear contribution to the reflection coefficient is present due to BIA if the magnetic field lies in the light incidence plane. We note that the contribution caused by SIA is absent in this geometry. For its observation the magnetic field should be oriented perpendicular to the incidence plane [7]. This allows us to study pure BIA magnetogyrotropic effect by choosing the geometry $\mathbf{B} \parallel \mathbf{q}_{\parallel}$.

The paper is organized as follows. In Sec. II we describe our experiments and deduce the size of the magnetogyrotropy signal for studied QWs. In Sec. III, the microscopic theory accounting for BIA terms in the electron and hole effective Hamiltonians is developed allowing for finding the magnetoinduced correction to the reflection coefficient. In Sec. IV we compare experimental results with theory and estimate the electron and hole BIA spin-splittings. Concluding remarks are given in Sec. V.

II. EXPERIMENT

For experimental investigation of BIA-induced magnetogyrotropic effects we studied CdTe- and GaAs based samples with single (001) QWs, Fig. 1(a). A triangular GaAs/AlGaAs QW was grown by the molecular beam epitaxy method on a semi-insulating substrate. The structure contains a 200 nm wide $\text{Al}_{0.28}\text{Ga}_{0.72}\text{As}$ barrier followed by the 8 nm wide QW. Then the other sloping barrier was grown with Al concentration smoothly increasing from 4 % to 28 % on a layer of width 27 nm. The rectangular 8 nm wide $\text{Cd}_{0.9}\text{Zn}_{0.1}\text{Te}/\text{CdTe}/\text{Cd}_{0.4}\text{Mg}_{0.6}\text{Te}$ QW with 90 nm wide barriers was grown on a buffer layer to a $\text{Cd}_{0.96}\text{Zn}_{0.04}\text{Te}$ substrate. The design of both structures is identical to that of the samples used in Ref. [7].

Magnetic field was oriented in the QW plane. The magnetic field up to 1 T was produced by the electromagnet with a ferromagnetic core. Experiment was per-




FIG. 1. Left: Experimental geometry. The magnetic field \mathbf{B} lies the plane of the QW and the light incidence plane contains \mathbf{B} . Right: Reflectance spectrum measured from CdTe asymmetric heterostructure in the vicinity of the X_{hh} resonance.




FIG. 2. Signal D , Eq. (3), for p polarized incident light reflected from CdTe sample in the vicinity of the X_{hh} resonance at magnetic fields $B = 0.05$ T and $B = 0.95$ T. The arrow indicates the signal amplitude A plotted in Fig. 3.

formed at temperature $T = 3$ K in closed cycle helium cryostat which was located in the core gap. The geometry of electromagnet and cryostat allowed for oblique light incidence. We measured polarization of the reflected light at oblique incidence with the incidence angle $\theta_0 = 27^\circ$. A halogen lamp was used as a light source for reflection measurements. Lenses and slits formed parallel light beam. Glan-Taylor prisms produced linearly polarization. Excitation was linearly polarized in the plane of incidence (p polarization) and perpendicular to the incidence plane (s polarization). Spectral dependencies of the reflected light were registered by a CCD camera conjoined with a monochromator. Strong exciton resonances are present in experimental data for both samples. As an example, the reflection spectrum is shown in Fig. 1(b) for CdTe QW structure. The heavy-hole exciton resonance X_{hh} is clearly seen.

We measured the polarization components of the reflected light in magnetic fields from -1 T to $+1$ T. We used both s and p polarized light and detected the reflection coefficients $r_{s,p}$. We analyzed the odd in \mathbf{B} contribution to reflection:

$$D = \frac{r(\mathbf{B}) - r(-\mathbf{B})}{r(\mathbf{B}) + r(-\mathbf{B})}. \quad (3)$$

The spectra $D(\omega)$ for CdTe QW are plotted in Fig. 2 for p polarization. In order to quantify the effect of magnetic field we determine the amplitude A from each reflection spectrum. The dependencies of the amplitudes on the magnetic field strength are shown in Fig. 3. The dependencies $A(B)$ are linear up to $B = 0.75$ T. The amplitude is larger for p polarization.

We performed the same studies on the sample with the GaAs QW. The spectra $D(\omega)$ for five values of the magnetic field are shown in Fig. 4. Increase of the signal amplitude is clearly seen. The dependence of the amplitude A on the magnetic field is shown in Fig. 5 for both




FIG. 3. Magnetic field dependencies of the signal amplitudes defined in Fig. 2 for s and p polarized incident light for the CdTe sample. The lines are guides for eyes.




FIG. 5. Magnetic field dependencies of the signal amplitudes for the GaAs/AlGaAs sample. The amplitudes are defined as in Fig. 2 for s - and p polarized light.




FIG. 4. The signal for p polarized incident light reflected from GaAs/AlGaAs asymmetric heterostructure at $T = 3$ K. The heavy-hole and light-hole exciton resonances are indicated.

s - and p polarization of incident light.

To summarize the experimental part, the amplitudes of the B -linear contribution to the reflection coefficients in the CdTe QWs are equal to $2.8 \times 10^{-3} B \text{ T}^{-1}$ and $1.5 \times 10^{-3} B \text{ T}^{-1}$ for p and s polarization, respectively. For GaAs structure, the amplitudes are $1.5 \times 10^{-3} B \text{ T}^{-1}$ and $0.75 \times 10^{-3} B \text{ T}^{-1}$.

III. THEORY

With account for the nondiagonal terms of the Luttinger effective Hamiltonian [9], the heavy-hole wavefunctions in QWs at $B = 0$ have the form

$$\Psi_{hh1,\pm 3/2}^{B=0} = \phi_{hh1}(z)u_{\pm 3/2} \mp \frac{\gamma_3 \hbar^2}{m_0} \sum_n \frac{\{k_z k_{\pm}\} \phi_{lhn}(z)}{E_{hh1} - E_{lhn}} u_{\pm 1/2}. \quad (4)$$

Here \mathbf{k} is the hole wavevector, $k_{\pm} = k_x \pm ik_y$, $\{\dots\}$ denotes the anticommutator, ϕ_{hh1} and ϕ_{lhn} are the functions of size quantization of corresponding levels of heavy and light holes, E_{hh1} and E_{lhn} are their energies, γ_3 is the Luttinger parameter, and u_{μ} are the Bloch amplitudes for the states of the top of the valence band.

In magnetic field $\mathbf{B} \perp z$, we choose the vector potential $\mathbf{A} = z(B_y, -B_x, 0)$, and the Peierls substitution yields $k_{\pm} \rightarrow k_{\pm} \mp izB_{\pm}e/(\hbar c)$. Therefore we obtain the \mathbf{B}_{\parallel} -dependent wavefunction

$$\Psi_{hh1,\pm 3/2}^B = \phi_{hh1}(z)u_{\pm 3/2} + B_{\pm}F(z)u_{\pm 1/2} \equiv |h, \mp 1/2\rangle, \quad (5)$$

where

$$F(z) = \frac{\gamma_3 e \hbar}{m_0 c} \sum_n \frac{\{ik_z z\} \phi_{lhn}(z)}{E_{hh1} - E_{lhn}}. \quad (6)$$

The matrix elements of exciton creation are $\mathbf{e} \cdot \mathbf{d}_{e,s;h,m} = \langle e, s | \mathbf{e} \cdot \hat{\mathbf{d}} | \mathcal{K}(h, m) \rangle$ where \mathbf{e} is the light polarization vector, $\hat{\mathbf{d}}$ is the dipole momentum operator, and $\mathcal{K} = i\sigma_y \mathcal{K}_0$ is the time inversion operator with \mathcal{K}_0 being the complex conjugation operation. Here $s = \pm 1/2$

and $m = \pm 1/2$ enumerates the spin-degenerate states in the conduction and valence bands, respectively. As a result of the magnetic field induced mixing of the hole states, Eq. (5), all four optical transitions become allowed. The matrix elements of the components of the dipole momentum operator $\mathbf{e} \cdot \mathbf{d}_{e,s,h,m}$ in the basis $e, \pm 1/2, h, \pm 1/2$ are given by

$$\mathbf{e} \cdot \mathbf{d} = d_{\perp} \begin{pmatrix} e_+ + 2\zeta B_+ e_z & -e_- \zeta B_- \\ -e_+ \zeta B_+ & e_- - 2\zeta B_+ e_z \end{pmatrix}. \quad (7)$$

Here $d_{\perp} = iep_{cv} \langle e1 | hh1 \rangle / (m_0 \omega_0 \sqrt{2})$, p_{cv} and ω_0 are the interband momentum matrix element and the exciton frequency, respectively, and the parameter ζ is given by

$$\zeta = \frac{\langle e1 | F(z) \rangle}{\langle e1 | hh1 \rangle} = \frac{\gamma_3 e \hbar}{m_0 c \sqrt{3} \langle e1 | hh1 \rangle} \sum_n \frac{\langle e1 | \{ i k_z z \} | l h n \rangle}{E_{hh1} - E_{lh n}}. \quad (8)$$

Here summation is performed over the light-hole states with even envelopes ($n = 1, 3, 5 \dots$).

The nonlocal exciton dielectric polarization \mathbf{P} in quantum wells depends on the growth-direction coordinate z

$$\mathbf{P}(\mathbf{q}, z) = \Phi(z) \sum_{\nu} \mathbf{d}_{\nu}^*(\mathbf{q}) C_{\nu}(\mathbf{q}). \quad (9)$$

Here summation is performed over four exciton states $\nu = (e, s; h, m)$, $s, m = \pm 1/2$, and $\Phi(z)$ is the envelope function of the exciton size quantization at coinciding coordinates of electron and hole [9]. The coefficients C_{ν} satisfy the equation

$$[(\hbar\omega_0 - \hbar\omega - i\Gamma)\delta_{\nu\nu'} + \mathcal{H}_{\nu\nu'}(\mathbf{q})] C_{\nu} = \int dz' \Phi^*(z') \mathbf{E}(z') \cdot \mathbf{d}_{\nu}(\mathbf{q}). \quad (10)$$

Here ω_0 and Γ are the heavy-hole resonant frequency and linewidth, $\hat{\mathcal{H}}$ is the contribution to the exciton Hamiltonian caused by the spin-orbit interaction, and $\mathbf{E}(z)$ is the total electric field. The first order in the spin-orbit interaction correction to the polarization describing the magnetogyrotropy is given by

$$\delta\mathbf{P}(\mathbf{q}, z) = -\frac{\Lambda_0 \Phi(z)}{(\hbar\omega_0 - \hbar\omega - i\Gamma)^2} \sum_{\nu\nu'} \mathbf{d}_{\nu}^* \mathcal{H}_{\nu\nu'}(\mathbf{d}_{\nu'} \cdot \mathbf{E}_0). \quad (11)$$

Here $\Lambda_0 = \int dz \Phi^*(z) \exp(iq_z z)$, and we neglect radiative renormalizations of ω_0 and Γ .

We account for BIA via the \mathbf{k} -linear spin-orbit splitting of the conduction- and valence band states. As a result the total spin-orbit Hamiltonian is a sum of the electron and hole terms which have the following forms in the basis $e1 \uparrow, e1 \downarrow$ of the electron states and $|h, 1/2\rangle, |h, -1/2\rangle$ of the hole states [10, 11]:

$$\mathcal{H} = \mathcal{H}^e + \mathcal{H}^h, \quad \mathcal{H}^{e,h} = \beta_{e,h} (\sigma_x^{e,h} k_x^{e,h} - \sigma_y^{e,h} k_y^{e,h}). \quad (12)$$

Here $x \parallel [100]$, $y \parallel [010]$, $\mathbf{k}^{e,h}$ are the electron and hole wavevectors in the QW plane, and $\beta_{e,h}$ are the two-dimensional Dresselhaus constants. Using Eqs. (7), (11)

and (12) we obtain the magnetogyrotropic contributions to the nonlocal susceptibility $\hat{\chi}$ defined as $\delta\mathbf{P}(z) = \int dz' \hat{\chi}(z, z') \mathbf{E}(z')$ in the form of Eqs. (1) with

$$T_+ = \tilde{\beta}_e G(z, z'), \quad T_- = T = \tilde{\beta}_h G(z, z'). \quad (13)$$

Here we used the relation between the wavevectors of exciton and carriers $\mathbf{k}^{e,h} = \mathbf{q}_{\parallel} m_{e,h} / (m_e + m_h)$ and introduced the constants

$$\tilde{\beta}_{e,h} = \beta_{e,h} \frac{m_{e,h}}{m_e + m_h}, \quad (14)$$

where m_h and m_e are the heavy-hole mass in the QW plane and the electron effective mass, respectively. The function $G(z, z')$ describes a nonlocality of the QW exciton optical response:

$$G(z, z') = -4\zeta \frac{\Phi(z) \Phi^*(z') |d_{\perp}|^2}{(\hbar\omega_0 - \hbar\omega - i\Gamma)^2}. \quad (15)$$

Solving the problem of light reflection from the QW in vicinity of the exciton resonance [9], we obtain the magnetogyrotropic correction to the Jones reflection matrix. For the incidence plane (100) ($\mathbf{q}_{\parallel} \parallel [100]$) we get

$$\begin{bmatrix} \Delta r_s & r_{sp} \\ r_{ps} & \Delta r_p \end{bmatrix} = 4\zeta q_{\parallel} \frac{i\Gamma_0 \cos \theta}{(\hbar\omega_0 - \hbar\omega - i\Gamma)^2} \times \begin{bmatrix} (\tilde{\beta}_e - \tilde{\beta}_h) B_x & \tilde{\beta}_h \cos \theta B_y \\ \tilde{\beta}_h \cos \theta B_y & (\tilde{\beta}_e + \tilde{\beta}_h) \cos^2 \theta B_x \end{bmatrix}. \quad (16)$$

Here $q_{\parallel} = (\omega/c) \sin \theta_0$, θ_0 and θ are the light incidence angle and the angle of light propagation inside the sample, respectively, and $\Gamma_0 = 2\pi \hbar |d_{\perp}|^2 |\Lambda_0|^2 q / \varepsilon_b$ is the X_{hh} oscillator strength for normal incidence with ε_b being the background dielectric constant of the QW material.

In the $\langle 110 \rangle$ axes, $x' \parallel [1\bar{1}0]$, $y' \parallel [110]$, the BIA spin-orbit interaction (12) has the form

$$\mathcal{H}_{\text{SO}} = \beta_e (\sigma_x^e k_{y'}^e + \sigma_y^e k_{x'}^e) + \beta_h (\sigma_x^h k_{y'}^h + \sigma_y^h k_{x'}^h). \quad (17)$$

Calculation for the incidence plane (110) when $\mathbf{q}_{\parallel} \parallel [110]$ yields

$$\begin{bmatrix} \Delta r_s & r_{sp} \\ r_{ps} & \Delta r_p \end{bmatrix} = 4\zeta q_{\parallel} \frac{i\Gamma_0 \cos \theta}{(\hbar\omega_0 - \hbar\omega - i\Gamma)^2} \times \begin{bmatrix} (\tilde{\beta}_e + \tilde{\beta}_h) B_{y'} & -\tilde{\beta}_h \cos \theta B_{x'} \\ -\tilde{\beta}_h \cos \theta B_{x'} & (\tilde{\beta}_e - \tilde{\beta}_h) \cos^2 \theta B_{y'} \end{bmatrix}. \quad (18)$$

In this coordinate system, the reflection plane (110) exists. The corresponding reflection keeps the combination $q_{x'} B_{y'}$ invariant and, hence, it can be present in Δr_s and Δr_p . The combination $q_{x'} B_{x'}$ changes its sign under the reflection in the (110) plane, and this allows for the corresponding term in $r_{sp} = r_{ps}$ because, at this reflection, the s and p components of the electric field are odd and even, respectively.

IV. DISCUSSION

The derived expressions demonstrate that the geometry $\mathbf{q}_{\parallel} \parallel \mathbf{B}_{\parallel} \parallel \langle 100 \rangle$ is suitable for observation of Δr_s and Δr_p caused by BIA, while in the geometry $\mathbf{q}_{\parallel} \parallel \mathbf{B}_{\parallel} \parallel \langle 110 \rangle$ the polarization conversion coefficient $r_{sp} = r_{ps}$ induced by BIA can be measured. The experimental configuration used in the present work, Fig. 1, $\mathbf{q}_{\parallel} \parallel \mathbf{B}$, allows for maximal corrections to the reflection coefficients Δr_s and Δr_p . In addition, these corrections have the resonant behavior $\propto (\omega_0 - \omega - i\Gamma/\hbar)^{-2}$ at the X_{hh} frequency. This is clearly seen in the experimental data, Figs. 2 and 4.

The derived Eqs. (16), (18) yield the following estimation for the magnetogyrotropic corrections: $\Delta r_{s,p} \sim (\beta q \Gamma_0 / \Gamma^2)(a/l_B)^2$, where a is the QW width and l_B is the magnetic length. For $q = 2.5 \times 10^4 \text{ cm}^{-1}$, $\beta = 140 \text{ meV \AA}$ [11], $\Gamma = 1 \text{ meV}$, $\Gamma_0 = 0.1 \text{ meV}$ and $a = 100 \text{ \AA}$, we obtain $\Delta r_{s,p} \sim 10^{-3} B \text{ T}^{-1}$. This value agrees in the order of magnitude with the experimental data for both GaAs and CdTe based QWs, Figs. 3 and 5.

We have also estimated other magnetogyrotropic contributions caused by BIA. Account for \mathbf{k} -odd terms in the bulk valence-band Hamiltonian as well as the interface inversion asymmetry terms also results in magnetogyrotropy due to admixture of the $\mp 1/2$ states to the $\pm 3/2$ states. However the corresponding contribution to the reflection has an order $\gamma_v q / (\Delta E_{lh} l_B^2)$ where γ_v is the valence-band cubic in k spin-orbit splitting constant and $\Delta E_{lh} \sim 10 \text{ meV}$ is the energy splitting between the size-quantized heavy- and light-hole levels. This value at $B = 1 \text{ T}$ has an order of 10^{-5} which is two orders of magnitude smaller than the contributions (16), (18). Therefore we see that the BIA-induced spin-orbit splitting of the electron and hole states in QWs gives the dominant contribution to the magnetogyrotropic corrections to the reflection coefficients.

The ratio of the corrections for p and s polarized incident light according to Eq. (16) is given by

$$\left| \frac{\Delta r_p}{\Delta r_s} \right| = \cos^2 \theta \left| \frac{\tilde{\beta}_e + \tilde{\beta}_h}{\tilde{\beta}_e - \tilde{\beta}_h} \right|. \quad (19)$$

In the experiment, the signal for p polarization is about twice stronger for both samples, see Figs. 3 and 5. Since $\cos^2 \theta \approx 1$ and $m_e \approx m_h$, the ratio agrees with the experiment at coinciding signs of β_e and β_h and at $\beta_h \approx 3\beta_e$.

V. CONCLUSION

From magnetoreflexion experiments in vicinity of exciton resonances we registered and analysed the magnetogyrotropic terms in the optical response of II-VI and II-V semiconductor QWs. We demonstrate that the q_{\parallel} - and B_{\parallel} -linear contribution to the reflection has an order of 0.1 % in both QWs under study. The developed theory accounting for BIA spin-orbit splittings of electron and hole states in QWs agrees with the experimental findings. Comparison of the theory with experimental data allowed for determination of the ratio of the electron and heavy-hole BIA spin-splitting constants.

ACKNOWLEDGMENTS

We thank I. A. Akimov, A. N. Poddubny and E. L. Ivchenko for fruitful discussions. L. V. K. is supported by Russian Science Foundation (project 16-12-10503). L. E. G. thanks the Presidium of RAS and the Foundation for advancement of theoretical physics and mathematics ‘‘BASIS’’.

-
- [1] S. D. Ganichev and L. E. Golub, Interplay of Rashba/Dresselhaus spin splittings probed by photogalvanic spectroscopy - A review, *Phys. Status Solidi B* **251**, 1801 (2014).
 - [2] Y. Tokura and N. Nagaosa, Nonreciprocal responses from non-centrosymmetric quantum materials, *Nat. Commun.* **9**, 3740 (2018).
 - [3] E. Marcellina, A. R. Hamilton, R. Winkler, and D. Culcer, Spin-orbit interactions in inversion-asymmetric two-dimensional hole systems: A variational analysis, *Phys. Rev. B* **95**, 075305 (2017).
 - [4] L. V. Kotova, A. V. Platonov, V. N. Kats, V. P. Kochereshko, S. V. Sorokin, S. V. Ivanov, and L. E. Golub, Optical activity of quantum wells, *Phys. Rev. B* **94**, 165309 (2016).
 - [5] V. Kochereshko, V. Kats, A. Platonov, V. Sapega, L. Besombes, D. Wolverson, H. Mariette, Nonreciprocal magneto-optical effects in quantum wells, *Phys. Status Solidi C* **11**, 1610 (2014).
 - [6] S. Hayami, M. Yatsushiro, Y. Yanagi, and H. Kusunose, Classification of atomic-scale multipoles under crystallographic point groups and application to linear response tensors, *Phys. Rev. B* **98**, 165110 (2018).
 - [7] L. V. Kotova, V. N. Kats, A. V. Platonov, V. P. Kochereshko, R. André, and L. E. Golub, Magnetospatial dispersion of semiconductor quantum wells, *Phys. Rev. B* **97**, 125302 (2018).
 - [8] F. Spitzer, A. N. Poddubny, I. A. Akimov, V. F. Sapega, L. Klompmaker, L. E. Kreilkamp, L. V. Litvin, R. Jede, G. Karczewski, M. Wiater, T. Wojtowicz, D. R. Yakovlev, and M. Bayer, Routing the emission of a near-surface light source by a magnetic field, *Nat. Phys.* **14**, 1043 (2018).
 - [9] E. L. Ivchenko, *Optical Spectroscopy of Semiconductor Nanostructures* (Alpha Science Int., Harrow, UK, 2005).
 - [10] A. A. High, A. T. Hammack, J. R. Leonard, S. Yang, L. V. Butov, T. Ostatnický, M. Vladimirova, A. V. Kavokin, T. C. H. Liew, K. L. Campman, and A. C. Gossard, Spin

Currents in a Coherent Exciton Gas, *Phys. Rev. Lett.* **110**, 246403 (2013).

- [11] M. V. Durnev, M. M. Glazov, and E. L. Ivchenko, Spin-orbit splitting of valence subbands in semiconductor

nanostructures, *Phys. Rev. B* **89**, 075430 (2014).