

Supporting Information

Investigating the properties of humins foams, the porous carbonaceous materials derived from biorefinery by-products


Pierluigi Tosi,^{a,b} Gerard P. M. van Klink,^b Charlotte Hurel,^c Claire Lomenech,^c Alain Celzard,^d Vanessa Fierro,^d Clara Delgado-Sanchez,^d Alice Mija^{a*}

^a Université Côte d'Azur, Institut de Chimie de Nice, UMR CNRS 7272, 06108 Nice Cedex 02, France. (e-mail: Alice.Mija@unice.fr)


^b Avantium Chemicals B.V. - Zekeringstraat 29, 1014 BV Amsterdam, The Netherlands

^c University Côte d'Azur, CNRS, Institute of Physics of Nice (INPHYNI UMR 7010), 06100 Nice, France

^d Université de Lorraine, CNRS, IJL, 88000, Epinal, France



SI 1 – Volume of the pores < 2 nm (x) in function of the variation of CO₂ adsorption between 50 °C and 100 °C (y) of F²500, F²700 and F²900..



SI 2 – Volume of the pores < 1nm (x) in function of the variation of CO_2 adsorption between 50 °C and 100 °C (y) of F²500, F²700 and F²900.

F250 has been neglected because of the presence of the surface oxygen species that can influence the CO_2 adsorption as specific interaction rather than as texture effect. As observed in SI 1 and SI 2, due to a high distribution in micropores volume, we don't find a linear relationship between values when pores < 2 nm are considerate (SI 1). When pores < 1 nm are considered (SI 2) we find a relation between values is almost perfect ($R^2 = 0.99$).