



HAL
open science

Optimizing heat harvesting in a membrane based planar μ TEG: modelling and fabrication, & vice versa

Zahia Bougrioua, Ibrahim Bel-Hadj, Katir Ziouche

► To cite this version:

Zahia Bougrioua, Ibrahim Bel-Hadj, Katir Ziouche. Optimizing heat harvesting in a membrane based planar μ TEG: modelling and fabrication, & vice versa. ECT 2019 – 17th European Conference on Thermoelectrics, Sep 2019, Limassol, Cyprus. . hal-02906736

HAL Id: hal-02906736

<https://hal.science/hal-02906736>

Submitted on 9 Dec 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Optimizing heat harvesting in a membrane based planar μ TEG: modelling and fabrication, & vice versa

Limassol (CYPRUS)
September 23rd-25th, 2019.


ACKNOWLEDGMENT:
This work was partly supported by RENATECH,
the French National Nanofabrication Network.

Zahia BOUGRIOUA*, Ibrahim BEL-HADI, Katir ZIOUCHE

IEMN, Institut d'Electronique de Micro-electronique et de Nanotechnologie,
CNRS and Lille University, avenue Poincaré, 59652 Villeneuve d'Ascq, FRANCE

E-mail *: zahia.bougrioua@iemn.fr

1/ Introduction




Micro-thermoelectric generators (μ TEGs) are energy harvesting solutions to supply electrical power for autonomous microsystems and other miniature applications. We study here original all-Silicon μ TEGs with a planar configuration in which the heat to harvest flows in-plane of a TE thin film. Such planar modules are based on a polySi/Au thermopile periodically distributed onto dielectric membranes; a heat-collector permits to concentrate the energy to harvest onto half the junctions of the thermopile. This planar topology allows the implementation of thermopiles with a high aspect ratio compared to classical vertical TEGs. Heat concentrator is able to collect any form of lost heat (even evaporation enthalpy a priori, or radiation...)

2. IEMN μ TEG design & process



1st Initial design : semi-3D micro thermoelectric generator, planar structure, CMOS compatible process of microfabrication. Surface foot-print $\sim 1/3$ cm², build up with 2 parts:

- Bottom part: N_M membranes periodically etched in a Si(100) substrate & made of a dielectric bilayer (1.4 μ m SiO₂/Si₃N₄). A poly-Silicon (pSi, $e_{pSi} \sim 0.3-0.9$ μ m thick, first thermopile) strip is deposited on this bilayer & is periodically covered with gold (Au, 2nd thermopile). This defines a zig-zag shaped thermopile, series of pSi/Au thermopiles (TC) : N_M tested : 1, 2, 5, 10
- * The pSi width ($L=50, 70$ or 200 μ m) is larger than the Au plated parts (10 μ m) \rightarrow this modulated-width thermopile has a reduced internal electrical resistance R_{int} \rightarrow electrical & thermal simulations show a gain in output power generated for larger stripes.
- * The TC number, N , is a function of N_M and L : $N = x \cdot N_M$ ($x=144, 112, 46$ for $L=50, 70, 200$ μ m). For fixed L , R_{int} is the same.
- * The whole is covered with a 15 μ m thick Polyimide layer (robustness & electrical isolation): 15 μ m is a compromise (for 2m- μ G up to 32% higher ΔT for 30 μ m PI but the benefits fastly diminish with N_M , for 10 μ m TEG it is even worse; see evolution in figure section 4.C...)
- Second part : heat concentrator HC ($surf \sim 0.3$ cm²) also fabricated starting from Si(100). It has as much pillars (N_{HC}) as there are membranes (200 μ m thick, 5.1 mm long & width optimised versus N_M). Pillars catalyze the heat flow to harvest (Φ , that arrives on its surface) into half of the thermopile junctions. A periodical ΔT is created at each TC.



3. Characterisation of μ TEG performance


Typical μ TEG experimental behaviour : at RT, the heat to harvest is varied from low to very high ($\Phi : 0 \rightarrow 8$ W)
Open circuit voltage is measured \rightarrow it gives Seebeck voltage generated V_{oc} and the difference of temperature ΔT is deduced using $\Delta T_{TC} = V_{oc} / (N \cdot \alpha_{TE/Au})$
Here is given : characterization of μ TEG integrating optimum n or p type polySi as the TE layer.




4. Thermal Modelling - Reducing heat losses & considering superior TE layer properties

Renewed design to improve the performance: a few routes to be validated by forthcoming experiments


4.A/ 3D thermal modelling using COMSOL Multiphysics®




4.D/ Modelling the impact of TE thermal conductivity & optimisation of generated output power



4.B/ Geometrical structure optimisation ($\Phi=1$ W)



4.C/ Reducing the heat lost in the bosses of the heat-concentrator



5 - Conclusions

- All-Silicon planar μ TEG with a modular thermal resistance (11-113 K/W) are fabricated by CMOS compatible microtechnology, integrating a thermopile built up with micro/nano-structured polySi as TE material. The number of membranes on which is periodically laying the thermopile can be varied and the heat to harvest is collected through a pillar-based Si-concentrator. The weak point of our μ TEG is their high internal electrical resistance: P_{MAX} are moderate: up to 62 μ W/cm², 164 μ W/cm², and 86 μ W/cm², for respectively 2, 5 or 10 membranes μ TEGs (1W heat injected).
- To better clarify further improvements to be carried out, while keeping the high R_{TH} values, COMSOL 3D thermal simulation was done for different new situations:
 - Better dimensioning: the optimum membrane number is 4 (not 5): same P_{MAX} and higher R_{TH} - use larger stripe (L=200 μ m versus currently 70 μ m) should be considered (20% increase in P_{MAX})
 - Elimination of parasitic heat losses:
 - polyimide layer: confirmation of an optimal thickness (around 15 μ m)
 - a modified heat-collector/concentrator with corner bosses made of porous Silicon allows to generate up to 64% more power, but this requires to be validated by experiments (soon)
 - Higher Power Factor (PF) effect: considering a thermopile integrating a Constantan layer can double P_{MAX} (~ 300 μ W/cm² for 1W injected). Compared to modules with non optimum polySi (ie. with PF < 10 μ W/K²cm or so) this represent a reliable way to enhance P_{MAX} by a factor of up to 3. However this is only valid for a TE stripe length of L=50 μ m (for larger L it decreases) \rightarrow this is being evaluated (together with 4-membranes configuration and porous bosses in the heat-concentrator)
 - High PF but bad microstructure of the TE layer : it results in poorer module performance ("cold case" explained : codoped polySi layer may have $\lambda > 60$ W/K/m...)
 - Considering nanostructured TE layer with a thermal conductivity λ reduced by a factor of 10 compared to polySi (ie even better than Cn) should result in a higher ΔT (24,6% for 5m- μ TEG), so in a P_{MAX} 65% higher (assuming same PF as our best p-type polySi) \rightarrow in such a case 550-660 μ W/cm² should be obtained for a 5m- μ TEG harvesting 1W input heat.