## Resonant Inelastic X-ray Scattering Study of Excitations in Cuprate Superconductors

## L.Chaix

## Université Grenoble Alpes, CNRS, Institut Néel, Grenoble, France <u>laura.chaix@neel.cnrs.fr</u>

The mechanism of high-Tc superconductivity in cuprates remains an unsolved question since its discovery in 1986. Answering the question of its microscopic origin turns out to be a great challenge, complexity arises from the coexistence of several phases along with the superconductivity. Although electron-phonon coupling may not be the main origin of the Cooper pairing, its role across the phase diagram is still controversial, particularly in the under-doped region [1-3]. A direct way to probe the electron-phonon coupling has emerged thanks to the recent progress made in high resolution Resonant inelastic X-ray scattering (RIXS), which now allows to resolve phonons [4]. Theoretical studies suggested that the RIXS phonon cross-section directly reflects the momentum-dependent electronphonon coupling strength [5,6]. In this talk, we will focus on the dynamical properties of the underdoped cuprate Bi<sub>2</sub>Sr<sub>2</sub>CaCu<sub>2</sub>O<sub>8+δ</sub>. Low energy excitations were investigated using RIXS at the Cu L<sub>3</sub>-edge with an energy resolution of 40–45 meV [4]. In the quasi-elastic region, an incommensurate charge density wave (CDW) was observed in this system, confirming its existence in this compound. In addition, this RIXS study resolved the bond-stretching phonon in the energy-momentum space. Importantly, it also revealed that the phonon dispersion changes at the CDW wave-vector indicating that the CDW unambiguously affects the lattice. RIXS measurements on another superconducting cuprate, Ca2-xNaxCuO2Cl2, will be also discussed.

## References

- M. K. Crawford, W. E. Farneth, E. M. McCarronn, R. L. Harlow, A. H. Moudden. Oxygen Isotope Effect and Structural Phase Transitions in La<sub>2</sub>CuO<sub>4</sub>-Based Superconductors. *Science* 1990, 250, 1390.
- 2. K.-P. Bohnen, R. Heid, M. Krauss. Phonon dispersion and electron-phonon interaction for YBa<sub>2</sub>Cu<sub>3</sub>O<sub>7</sub> from first-principles calculations. *Europhys. Lett.* **2003**, *64*, 104.
- 3. M. d'Astuto, I. Yamada, P. Giura, L. Paulatto, A. Gauzzi, M. Hoesch, M. Krisch, M. Azuma, M. Takano. Phonon anomalies and lattice dynamics in the superconducting oxychlorides Ca<sub>2-x</sub>CuO<sub>2</sub>Cl<sub>2</sub>. *Phys. Rev. B* **2013**, *88*, 014522.
- 4. L. Chaix, G. Ghiringhelli, Y. Y. Peng, M. Hashimoto, B. Moritz, K. Kummer, N. B. Brookes, Y. He, S. Chen, S. Ishida; et al. Dispersive charge density wave excitations in Bi<sub>2</sub>Sr<sub>2</sub>CaCu<sub>2</sub>O<sub>8+ s</sub>. *Nat. Phys.* **2017**, *13*, 952–956.
- 5. L. J. P. Ament, M. van Veenendaal, J. van den Brink. Determining the electron-phonon coupling strength from Resonant Inelastic X-ray Scattering at transition metal L-edges. *Europhys. Lett.* **2011**, *95*, 27008.
- T. P. Devereaux, A. M. Shvaika, K. Wu, K. Wohlfeld, C. J. Jia, Y. Wang, B. Moritz, L. Chaix, W.-S. Lee, Z.-X. Shen; et al. Directly characterizing the relative strength and momentum dependence of electron-phonon coupling using resonant inelastic X-Ray scattering. *Phys. Rev. X* 2016, *6*, 041019.