



HAL
open science

Packing Polydisperse Colloids into Crystals: When Charge-Dispersity Matters

Guillaume Bareigts, Pree-Cha Kiatkirakajorn, Joaquim Li, Robert Botet, Michael Sztucki, Bernard Cabane, Lucas Goehring, Christophe Labbez

► **To cite this version:**

Guillaume Bareigts, Pree-Cha Kiatkirakajorn, Joaquim Li, Robert Botet, Michael Sztucki, et al.. Packing Polydisperse Colloids into Crystals: When Charge-Dispersity Matters. *Physical Review Letters*, 2020, 124 (5), 10.1103/PhysRevLett.124.058003 . hal-03035380

HAL Id: hal-03035380

<https://hal.science/hal-03035380v1>

Submitted on 8 Dec 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Packing polydisperse colloids into crystals: when charge-dispersity matters

Guillaume Bareigts,¹ Pree-Cha Kiatkirakajorn,² Joaquim Li,³ Robert Botet,⁴
 Michael Sztucki,⁵ Bernard Cabane,³ Lucas Goehring,^{6,*} and Christophe Labbez^{1,†}

¹ICB, CNRS UMR 6303, Univ. Bourgogne Franche-Comté, 21000 Dijon, France

²Max Planck Institute for Dynamics and Self-Organisation (MPIDS), Göttingen 37077, Germany

³LCMD, CNRS UMR 8231, ESPCI, 10 rue Vauquelin, 75231 Paris Cedex 05, France

⁴Physique des Solides, CNRS UMR 8502, Univ Paris-Sud, F-91405 Orsay, France

⁵ESRF-The European Synchrotron, CS40220, 38043 Grenoble Cedex 9, France

⁶School of Science and Technology, Nottingham Trent University, Nottingham, NG11 8NS, UK

(Dated: January 20, 2020)

Monte-Carlo simulations, fully constrained by experimental parameters, are found to agree well with a measured phase diagram of aqueous dispersions of nanoparticles with a moderate size polydispersity over a broad range of salt concentrations, c_s , and volume fractions, ϕ . Upon increasing ϕ , the colloids freeze first into coexisting compact solids then into a body centered cubic phase (bcc) before they melt into a glass forming liquid. The surprising stability of the bcc solid at high ϕ and c_s is explained by the interaction (charge) polydispersity and vibrational entropy.

How do polydisperse particles pack and order? This basic question concerns diverse systems, including granular beads, micro-emulsions, micro-gels, macromolecules and solid nanoparticles and is, thus, largely debated. For a fluid of hard-sphere (HS) particles, Pusey et al. [1, 2] proposed a critical value of polydispersity (δ), above which particles would not crystallize. This concept of a terminal polydispersity was first based on experimental observations, and later supported also by numerical simulations [3, 4]. However, using simulations of HS systems, Kofke et al. [5] found that the concept of a terminal polydispersity should only apply to a solid phase, rather than the entire system of particles. More precisely, that a stable crystalline phase whose constituent components exceeded a polydispersity of 5.7% could not be formed from a fluid phase. Questioning the ultimate fate of an amorphous solid of high δ , they proposed that fractionation should enable an HS fluid of arbitrary polydispersity to precipitate in a fcc solid phase in coexistence with a fluid phase. Sollich et al. [6, 7] further theorized that, when compressed, a relatively polydisperse HS system should crystallize into a myriad of coexisting fcc crystalline phases each having a distinct size distribution and a narrower δ than the mother distribution, as in Fig. 1(a).

Our recent experiments [8] on dispersions of charged hard spheres (CS) with a broad and continuous size polydispersity ($\delta = 14\%$) empirically demonstrated the case of the fractionation of a colloidal fluid into multiple coexisting phases. Interestingly, this crystallization turns out to be more complex than that theorized by Sollich et al. for HS. Indeed, as in Fig. 1(b), the CS were observed to coexist in a fluid phase, a bcc lattice and a Laves MgZn_2 superlattice. The latter had been previously known only from *binary* distributions of particles [10–12]. Matching lattice simulations can also reproduce the experimental findings, including the Laves phase [8, 13]. Very recent simulations [9, 14, 15] with polydisperse HS of $\delta > 6\%$ show a similar, or even greater, level of complexity and




FIG. 1. Colloidal crystallisation in a polydisperse system can lead to: (a) A set of distinct crystals of the same structure (e.g. fcc) and narrow monomodal size distributions, which together span the available range of particle sizes [6]; (b) More complex phases such as AB_2 [8] or AB_{13} [9] structures, which utilise a bimodal subset of particles. These may coexist with simpler phases (e.g. as above, bcc [8]); (c) The appearance of crystals of different structures (e.g. bcc, fcc, hcp) and monomodal size distributions, as reported in this paper. In all sketches the shaded area shows the parent particle size distribution while the various open curves describe the particles found in any specific crystal structure and site.

thus indicate that our findings with CS are representative of a more general rule: polydispersity enables complex crystal formation. In particular, Frank-Kasper phases, as well as various Laves AB_2 and AB_{13} phases were found in simulations of HS of δ from 6% to 24% and at high packing fractions (ϕ). These results are also in line with the earlier simulations of Fernandez et al. [16], of neutral soft spheres, even though the exact natures of the crystal phases obtained there were not identified. On the other hand, the coexistence of multiple crystal phases of the same symmetry, but different lattice constants, has only been observed in systems of plate-like particles [17].




FIG. 2. As the dispersion is concentrated, colloidal crystals appear. The scattering intensities, I , of the spectra shown here, for $c_s = 5$ mM, demonstrate the typical sequence of (a) fcc ($\phi = 19\%$), (b) a mixture of fcc and bcc ($\phi = 20\%$) and (c) bcc ($\phi = 21\%$) crystals, as ϕ increases. A broad liquid peak is present in all spectra, and the most prominent crystal peaks are typically at least twice as intense as this liquid background. Additionally, a much weaker peak is often visible at lower q , consistent with an hcp structure of the same particle density, or stacking faults in an fcc lattice.

Here, we demonstrate that even with a moderate size polydispersity CS systems can show a complex phase behavior. This is achieved on a similar CS system to that in [8] but with a moderate size dispersity (9%). The magnitude and polydispersity of the charge, and thus of the interaction polydispersity, are tuned with the salt concentration, c_s and pH of the bulk solution (see Supplemental Material [18]). Using x-ray scattering methods the $c_s - \phi$ phase diagram is constructed. We observe that on gradually increasing the osmotic compression the CS fluid crystallises and fractionates into coexisting phases of different structures, i.e. bcc, fcc and hcp, as in Fig. 1(c). Unexpectedly, the stability region of the bcc crystals covers a large area of the phase diagram, considerably more than in the monodisperse case. The first appearance of the bcc phase is always at a higher ϕ than that of fcc crystals, at the same c_s (i.e. opposite to their order of occurrence in monodisperse CS [19]). Upon further compression, the system becomes a glass forming liquid. To help explain these results, we use Monte Carlo (MC) simulations of our multi-component model (MCM) for charge regulating polydisperse colloids parametrized with independent experimental data [20]. Allowing for only a slight adjustment of δ , the simulations almost perfectly reproduce the experimental phase diagram.

For the experiments, we used industrially produced, nanometric and highly charged silica particles, dispersed in water (Ludox TM50, Sigma-Aldrich). These were cleaned and concentrated as detailed elsewhere [8, 21–23]. Briefly, dispersions were filtered and dialysed against aqueous NaCl solutions of various concentrations (from 0.5 to 50 mM) at pH 9 ± 0.5 (by addition of NaOH). Next, they were slowly concentrated via the osmotic stress method, by the addition of polyethylene glycol (mw 35000, Sigma-Aldrich) outside the dialysis sack. Samples were then taken and sealed in quartz capillary tubes, on which small-angle x-ray scattering (SAXS) experiments were performed at the ESRF, beamline ID02 [24]. The particle size distribution was measured in the dilute limit (see the Supplemental Material [18]) to have a mean size of $\bar{R} = 13.75 \pm 1$ nm and a polydispersity of $\delta = 9 \pm 1\%$, consistent with prior observations [25]. Over a range of concentrations the scattering spectra showed sharp peaks characteristic of fcc and bcc crystal phases, as shown in Fig. 2. A weak peak representing a minority hcp phase (or evidence of stacking faults [26]) was frequently seen alongside either crystal phase. Additional characterisation of the liquid and glass phases is given in the Supplemental Material [18].

The experimental phase diagram in the $c_s - \phi$ plane is given in Fig. 3(a), and represents the phases that have nucleated and are experimentally stable over days-to-weeks. Whatever the background salinity, a fluid region is observed for low ϕ followed by a region with crystal formation at intermediate ϕ , which ends in a re-entrant amorphous phase at high ϕ . The latter behaves macroscopically as a solid (i.e. retains its shape as a soft gel or paste). As c_s is increased, the first appearance of crystals shifts to higher ϕ , in response to the screening of the electrostatic interactions. The same is true for the re-entrant melting transition. Both observations are consistent with phase diagrams of other experimental CS systems although at much lower c_s , (e.g. [27, 28]). The predominant ordered phases appearing are bcc and fcc crystals, also known from monodisperse CS systems (although the hcp phase is not typically seen there, other than in shear-ordered samples [29]). However, the stability region of the bcc phase is observed at higher ϕ than the fcc phase, for all screening lengths studied (i.e. all c_s). This was also the case where we made a more continuous probe across ϕ as assessed by interdiffusion experiments (see the Supplemental Material [18] for details). This phase behavior contrasts strongly with that of monodisperse particles, where a *bcc-fcc* transition with increasing ϕ (rather than the *fcc-bcc* transition seen here) is invariably observed [27, 28]. Essentially, this demonstrates that even a moderate polydispersity can have a complex influence on crystal stability, and modify the relative stability of various phases.

Although predicted to occur for soft colloids [30, 31] an inversion of the stability regions of the bcc and fcc phases




FIG. 3. Phase diagram in the $c_s - \phi$ plane of the TM50 silica dispersion at pH 9 as obtained from (a) SAXS analysis of dialysed samples and (b) MC simulations of the MCM. For clarity, the hcp phase is not represented. The shaded areas of (a,b) delimit the region where crystals are found in the simulations, and demonstrate the good correspondence with experiments.

has rarely been observed. To our knowledge, it has only been reported for soft spheres [32]. The possibility that polydispersity could help stabilise the bcc phase in CS systems was conjectured by some of us, based on an energetic argument which shows that the bcc structure is more tolerant to interaction polydispersity than the fcc one [13]. This argument was made via *lattice* MC simulations in the Gibbs ensemble on a system with a pre-supposed bcc/fcc coexistence of CS with $\delta = 15\%$. The particles were found to be divided up between a narrow monomodal distribution (fcc) and a bimodal one (bcc), similar to the situation given in Fig 1(b). However, our reanalysis of this model shows that it also predicts the formation of a CsCl structure on the sites of the bcc phase (i.e. alternating larger and smaller particles), which is not compatible with our experimental findings (as additional scattering peaks would be present in this case).

Here we employed, instead, MC simulations for *continuous* systems at set density (NVT) or pressure (NPT) which do not require any prior information on the phases at equilibrium. They were performed at the experimental c_s and pH conditions in the framework of the MCM de-




FIG. 4. Simulation results (at pH 9) show: (a) agreement of the simulated and measured equation of state (EoS) of the TM50 silica dispersion at various ionic strengths; (b) the predicted variation of the phase composition with ϕ at $c_s = 5$ mM; (c) and particle size distributions of the various crystalline phases in comparison with the parent size distribution (dashed curve) for the model silica dispersion at $\phi = 20.5\%$, $c_s = 5$ mM.

tailed in Ref. [20], which includes the charge regulation of the silica particles through the pH dependent ionization of their surface active groups, $\text{Si-OH} \rightleftharpoons \text{Si-O}^- + \text{H}^+$. A truncated and discretized Gaussian size distribution

with the same \bar{R} as measured was used, but with a somewhat lower polydispersity of $\delta = 7\%$ (rather than 9%). Simple particle translations combined with swap moves [33] allow for efficiently sampling the phase space up to high ϕ [34]. Simulations were run with $N = 19\,991$ particles in a cubic box with periodic boundary conditions. Up to several tens of million of MC cycles (each consisting of N MC moves) for equilibration were used; production runs lasted for 10^5 MC cycles. The local bond order parameters were used to analyze the obtained structures [35], and further details of the analysis and simulation are given in the Supplemental Material [18].

As shown in Fig. 3(b), a very good agreement is achieved between the experimental and simulated (MCM) phase diagrams. The same is true for the equation of state (EoS) of the TM50 silica dispersion in the all range of c_s and ϕ studied as seen in Fig 4(a) (experimental data from Refs. [23, 36]). Not only is the inversion of the stability regions of the bcc and fcc phases well predicted, but also the position of the freezing transition matches with the experiments, although an exact phase diagram would require a free energy calculation not developed here (see the Supplemental Material for discussion). In line with the experimental observations [23], a re-entrant amorphous phase at high ϕ is found, in which colloids present very weak diffusion.

The phase composition of the system upon compression at $c_s = 5$ mM and an example of the size distributions at the coexistence of the hcp/bcc/fcc phases are shown in Fig 4(b,c). The freezing transition is found to be first-order, and is characterized by both a discontinuity in the EoS and an abrupt change in the liquid/fcc phase composition at $\phi \approx 16\%$, as in Fig 4(a). The fcc-bcc phase transition is, on the other hand, found to be much more progressive. Simulation snapshots at the bcc/fcc/hcp phase coexistence show, instead, textures characteristic of a micro-phase separation (for further detail, see the Supplemental Material [18]).

The fcc-bcc phase transition is also characterized by a small size fractionation, as in Fig 4(c), which tends to increase with ϕ (see the Supplemental Material [18]). The bcc phase is found to be more tolerant to polydispersity, while incorporating a larger number of small particles than the fcc structure. The particle distribution of the bcc phase thus presents a larger δ and smaller R than of the fcc phase. One consequence of this is that there will be only a small difference in the calculated particle number densities between both crystalline phases and the bulk, less than 4%, with a slight tendency of the fcc phase to be the densest. This is consistent with our experimental observations, although the difference in phase densities falls within the uncertainty of the measurements (see the Supplemental Material [18]).

These results are in line with our energetic argument mentioned earlier [13]. In other words, the interaction polydispersity favors the formation of bcc crystals with a

larger particle distribution (or charge distribution), thus being more tolerant to polydispersity, as compared to fcc crystals. As ϕ is progressively increased, the fcc phase, compared to the bcc phase, becomes less and less tolerant to the charge polydispersity. Note that the latter is not constant but increases with ϕ , see [20]. Consequently, the fcc ordered phase progressively disappears in favor of the bcc and fluid phases. Conversely, in the absence of interaction polydispersity the system can, to a good approximation, be reduced to that of point Yukawa particles [19]. In such a case, the charge of colloid i satisfies the equality $Z_i^* \exp(-\kappa^* R_i)/(1 + \kappa^* R_i) = C \neq 0 \forall R_i$, where C is a constant (see the Supplemental Material [18]). The inversion of the stability regions of the bcc and fcc phases is then lost [37]. In this case also, the stability region of the bcc phase is restricted to the very diluted $c_s - \phi$ domain only. In absence of charge (i.e. $C = 0$), the bcc phase simply disappears, see e.g. the recent work of Bommineni on polydisperse HS systems [9]. All this further illustrates the importance of charge dispersity in the inversion of the stability regions of the bcc and fcc phases.

Obviously, the phase behavior observed in our experiments and simulations is not only a consequence of the system's internal energy, but the result of the balance between energy and entropy. In an attempt to elucidate the entropic contributions in the stabilization of the bcc phase we further performed lattice simulations in the Gibbs ensemble, as in Ref. [13], with the MCM of the TM50 silica dispersion. As in the continuous simulations, a small size fractionation is obtained. However, a CsCl superlattice structure, instead of a bcc phase, is found (see the Supplemental Material [18]). Recognizing that lattice simulations only account for the mixing contribution to the entropy, one can deduce from this qualitative difference that the bcc phase observed in our experiments (and continuous simulations) is most probably stabilized by vibrational entropy (the missing thermodynamic ingredient in lattice simulations). A large size fractionation in distinct phases is, on the other hand, prevented by the mixing entropy at this relatively small δ and range of ϕ . When the size polydispersity is increased (see the Supplemental Material [18]), the mixing entropy takes over, and a MgZn₂ Laves phase in coexistence with a bcc phase is predicted to occur in good agreement with our previous experimental findings [8].

Not discussed so far is the striking agreement obtained between the simulations and experiments on the position of the re-entrant melting line. At a first sight, this would suggest that the amorphous phase is stable. Preliminary results obtained well inside the amorphous region with more advanced simulation techniques show, however, that it can crystallize. A close look at the EoS also shows a sudden increase in the osmotic pressure. These results, which will be developed elsewhere, strongly suggest that it is a glass forming liquid. Still, we were

unable to come with a reasonable explanation for the troubling coincidence between our simulation and experimental results on the (non-thermodynamic) re-entrant melting transition.

To conclude, using a combined and detailed theoretical and experimental study of charged nano-colloids with a moderate polydispersity, we provide evidence that the packing of polydisperse particles into crystals is much more diverse than initially thought, even for relatively small polydispersities. In particular, the system is found to separate into coexisting solid phases with a limited size fractionation. Under compression, the system first solidifies in compact lattice structures, fcc/hcp. Upon further compression, the fcc phase dissolves progressively into a less compact bcc structure, which proves to be more tolerant to the interaction (charge) polydispersity. Our simulations strongly suggest that the limited size fractionation and the stabilization of the bcc phase are due to the mixing and vibrational entropies, respectively. Compressed even further, the colloidal crystals melt into an amorphous phase, most probably a glass forming liquid. The astonishingly good agreement obtained between our experimental results and simulated predictions further gives a strong support to the simulation methods employed and the parameter-free force field developed. We anticipate that these tools should help in the finding of new colloidal crystal phases and in providing a better understanding of colloidal glasses in CS systems. Still, the exact phase boundaries and equilibrium phase behavior of polydisperse CS, in particular at high densities, remain open questions which will require the development of advanced simulation techniques to be tackled.

We acknowledge the European Synchrotron Radiation Facility for provision of synchrotron radiation facilities and assistance in using beamline ID02. G.B. and C.L. thanks financial support from the Region Bourgogne Franche-Comté and CNRS, as well as computational support from CRI, Université de Bourgogne. P.-C.K. thanks the Thai DPST and the Royal Government of Thailand for funding. G.B. and P.-C.K. contributed equally to this work.

* lucas.goehring@ntu.ac.uk

† Christophe.labbez@u-bourgogne.fr

- [1] P. N. Pusey, “The effect of polydispersity on the crystallization of hard spherical colloids,” *J. Phys. France* **48**, 709–712 (1987).
- [2] P. N. Pusey, “Colloidal suspensions,” in *Les Houches Session L1: Liquids, Freezing, and the Glass Transition* (edited by J. P. Hansen, D. Levesque, and J. Zinn-Justin (North-Holland, 1991), 1991) pp. 765–942.
- [3] Stefan Auer and Daan Frenkel, “Suppression of crystal nucleation in polydisperse colloids due to increase of the surface free energy,” *Nature* **413**, 711–713 (2001).
- [4] P. N. Pusey, E. Zaccarelli, C. Valeriani, E. Sanz, Wilson C. K. Poon, and Michael E. Cates, “Hard spheres: Crystallization and glass formation,” *Philos. Trans. R. Soc. Lond. Math. Phys. Eng. Sci.* **367**, 4993–5011 (2009).
- [5] David A. Kofke and Peter G. Bolhuis, “Freezing of polydisperse hard spheres,” *Phys Rev E* **59**, 618–622 (1999).
- [6] Moreno Fasolo and Peter Sollich, “Equilibrium Phase Behavior of Polydisperse Hard Spheres,” *Phys Rev Lett* **91**, 068301 (2003).
- [7] Peter Sollich and Nigel B. Wilding, “Crystalline Phases of Polydisperse Spheres,” *Phys. Rev. Lett.* **104**, 118302 (2010).
- [8] Bernard Cabane, Joaquim Li, Franck Artzner, Robert Botet, Christophe Labbez, Guillaume Bareigts, Michael Sztucki, and Lucas Goehring, “Hiding in Plain View: Colloidal Self-Assembly from Polydisperse Populations,” *Phys. Rev. Lett.* **116**, 208001 (2016).
- [9] Praveen K. Bommineni, Nydia Roxana Varela-Rosales, Marco Klement, and Michael Engel, “Complex Crystals from Size-Disperse Spheres,” *Phys. Rev. Lett.* **122**, 128005 (2019).
- [10] Elena V. Shevchenko, Dmitri V. Talapin, Nicholas A. Kotov, Stephen O’Brien, and Christopher B. Murray, “Structural diversity in binary nanoparticle superlattices,” *Nature* **439**, 55–59 (2006).
- [11] Antti-Pekka Hynninen, Job H. J. Thijssen, Esther C. M. Vermolen, Marjolein Dijkstra, and Alfons van Blaaderen, “Self-assembly route for photonic crystals with a bandgap in the visible region,” *Nat. Mater.* **6**, 202–205 (2007).
- [12] N. Schaertl, D. Botin, T. Palberg, and E. Bartsch, “Formation of Laves phases in buoyancy matched hard sphere suspensions,” *Soft Matter* **14**, 5130–5139 (2018).
- [13] Robert Botet, Bernard Cabane, Lucas Goehring, Joaquim Li, and Franck Artzner, “How do polydisperse repulsive colloids crystallize?” *Faraday Discuss.* **186**, 229–240 (2016).
- [14] Daniele Coslovich, Misaki Ozawa, and Ludovic Berthier, “Local order and crystallization of dense polydisperse hard spheres,” *J. Phys.: Condens. Matter* **30**, 144004 (2018).
- [15] Beth A. Lindquist, Ryan B. Jadrich, and Thomas M. Truskett, “Communication: From close-packed to topologically close-packed: Formation of Laves phases in moderately polydisperse hard-sphere mixtures,” *J. Chem. Phys.* **148**, 191101 (2018).
- [16] L. A. Fernández, V. Martín-Mayor, and P. Verrocchio, “Phase Diagram of a Polydisperse Soft-Spheres Model for Liquids and Colloids,” *Phys Rev Lett* **98**, 085702 (2007).
- [17] D. V. Byelov, M. C. D. Mourad, I. Snigireva, A. Snigirev, A. V. Petukhov, and H. N. W. Lekkerkerker, “Experimental Observation of Fractionated Crystallization in Polydisperse Platelike Colloids,” *Langmuir* **26**, 6898–6901 (2010).
- [18] See Supplemental Material at <http://XX>, which includes Refs. [8,13,14,20,25,33–35,38–48], for an extended materials and methods section, as well as for details of the suspension size distribution, interdiffusion experiments, phase composition, glassy state, simulation convergence and lattice simulations.
- [19] Antti-Pekka Hynninen and Marjolein Dijkstra, “Phase diagrams of hard-core repulsive Yukawa particles,” *Phys. Rev. E* **68**, 021407 (2003).
- [20] Guillaume Bareigts and Christophe Labbez, “Jellium and cell model for titratable colloids with continuous size distribution,” *J. Chem. Phys.* **149**, 244903 (2018).

- [21] Bo Jönsson, J. Persello, J. Li, and B. Cabane, “Equation of State of Colloidal Dispersions,” *Langmuir* **27**, 6606–6614 (2011).
- [22] Joaquim Li, Martin Turesson, Caroline Anderberg Haglund, Bernard Cabane, and Marie Skepö, “Equation of state of PEG/PEO in good solvent. Comparison between a one-parameter EOS and experiments,” *Polymer* **80**, 205–213 (2015).
- [23] Lucas Goehring, Joaquim Li, and Pree-Cha Kiatkirakajorn, “Drying paint: From micro-scale dynamics to mechanical instabilities,” *Phil. Trans. R. Soc. A* **375**, 20160161 (2017).
- [24] T. Narayanan, M. Sztucki, P. Van Vaerenbergh, J. Léonardon, J. Gorini, L. Claustre, F. Sever, J. Morse, and P. Boesecke, “A multipurpose instrument for time-resolved ultra-small-angle and coherent X-ray scattering,” *J. Appl. Crystallogr.* **51**, 1511–1524 (2018).
- [25] Verena Goertz, Nico Dingenouts, and Hermann Nirschl, “Comparison of Nanometric Particle Size Distributions as Determined by SAXS, TEM and Analytical Ultracentrifuge,” *Part. Part. Syst. Charact.* **26**, 17–24 (2009).
- [26] A. G. Shabalin, J.-M. Meijer, R. Dronyak, O. M. Yefanov, A. Singer, R. P. Kurta, U. Lorenz, O. Y. Gorobtsov, D. Dzhigaev, S. Kalbfleisch, J. Gulden, A. V. Zozulya, M. Sprung, A. V. Petukhov, and I. A. Vartanyants, “Revealing Three-Dimensional Structure of an Individual Colloidal Crystal Grain by Coherent X-Ray Diffractive Imaging,” *Phys. Rev. Lett.* **117**, 138002 (2016).
- [27] Yiannis Monovoukas and Alice P Gast, “The experimental phase diagram of charged colloidal suspensions,” *Journal of Colloid and Interface Science* **128**, 533–548 (1989).
- [28] E. B. Sirota, H. D. Ou-Yang, S. K. Sinha, P. M. Chaikin, J. D. Axe, and Y. Fujii, “Complete phase diagram of a charged colloidal system: A synchrotron x-ray scattering study,” *Phys. Rev. Lett.* **62**, 1524–1527 (1989).
- [29] Heiner Versmold, “Neutron Diffraction from Shear Ordered Colloidal Dispersions,” *Phys. Rev. Lett.* **75**, 763–766 (1995).
- [30] D. Gottwald, C. N. Likos, G. Kahl, and H. Löwen, “Phase Behavior of Ionic Microgels,” *Phys. Rev. Lett.* **92**, 068301 (2004).
- [31] Josep C. Pàmies, Angelo Cacciuto, and Daan Frenkel, “Phase diagram of Hertzian spheres,” *J. Chem. Phys.* **131**, 044514 (2009).
- [32] P. S. Mohanty and W. Richtering, “Structural Ordering and Phase Behavior of Charged Microgels,” *J. Phys. Chem. B* **112**, 14692–14697 (2008).
- [33] Tomás S. Grigera and Giorgio Parisi, “Fast Monte Carlo algorithm for supercooled soft spheres,” *Phys Rev E* **63**, 045102(R) (2001).
- [34] Carolina Brito, Edan Lerner, and Matthieu Wyart, “Theory for Swap Acceleration near the Glass and Jamming Transitions for Continuously Polydisperse Particles,” *Phys. Rev. X* **8**, 031050 (2018).
- [35] Wolfgang Lechner and Christoph Dellago, “Accurate determination of crystal structures based on averaged local bond order parameters,” *The Journal of Chemical Physics* **129**, 114707 (2008).
- [36] Pree-Cha Kiatkirakajorn, *Morphological Instabilities in Drying Colloids*, PhD Thesis, Georg-August University, Göttingen (2018).
- [37] S. Hamaguchi, R. T. Farouki, and D. H. E. Dubin, “Triple point of Yukawa systems,” *Phys. Rev. E* **56**, 4671–4682 (1997).
- [38] Robert Botet and Bernard Cabane, “Simple inversion formula for the small-angle X-ray scattering intensity from polydisperse systems of spheres,” *J. Appl. Crystallogr.* **45**, 406–416 (2012).
- [39] Joaquim Li, Bernard Cabane, Michael Sztucki, Jérémie Gummel, and Lucas Goehring, “Drying Dip-Coated Colloidal Films,” *Langmuir* **28**, 200–208 (2012).
- [40] Niels Boon, Guillermo Ivan Guerrero-García, René van Roij, and Monica Olvera de la Cruz, “Effective charges and virial pressure of concentrated macroion solutions,” *PNAS* **112**, 9242–9246 (2015).
- [41] G. H. Bolt, “Determination of the Charge Density of Silica Sols,” *J. Phys. Chem.* **61**, 1166–1169 (1957).
- [42] Christophe Labbez, Bo Jonsson, Michal Skarba, and Michal Borkovec, “Ion-ion correlation and charge reversal at titrating solid interfaces,” *Langmuir* **25**, 7209–7213 (2009).
- [43] P. M. Dove and C. M. Craven, “Surface charge density on silica in alkali and alkaline earth chloride electrolyte solutions,” *Geochim Cosmochim Acta* **69**, 4963–4970 (2005).
- [44] D. Frenkel and B. Smit, *Understanding Molecular Simulation* (Academic Press, San Diego, 2002).
- [45] Nigel B. Wilding and Peter Sollich, “Phase behavior of polydisperse spheres: Simulation strategies and an application to the freezing transition,” *The Journal of Chemical Physics* **133**, 224102 (2010).
- [46] Loup Verlet, “Computer “Experiments” on Classical Fluids. II. Equilibrium Correlation Functions,” *Phys. Rev.* **165**, 201–214 (1968).
- [47] Jean-Pierre Hansen and Loup Verlet, “Phase Transitions of the Lennard-Jones System,” *Phys. Rev.* **184**, 151–161 (1969).
- [48] Mathieu Leocmach, John Russo, and Hajime Tanaka, “Importance of many-body correlations in glass transition: An example from polydisperse hard spheres,” *The Journal of Chemical Physics* **138**, 12A536 (2013).