

Pearl-necklace assembly of human serum albumin with the poly(acrylic acid) polyelectrolyte investigated using small angle X-ray scattering (SAXS)

Charaf E. Merzougui, Pierre Roblin, Pierre Aimar, Antoine Venault, Yung Chang, Christel Causserand, Patrice Bacchin

▶ To cite this version:

Charaf E. Merzougui, Pierre Roblin, Pierre Aimar, Antoine Venault, Yung Chang, et al.. Pearlnecklace assembly of human serum albumin with the poly(acrylic acid) polyelectrolyte investigated using small angle X-ray scattering (SAXS). Soft Matter, 2020, 16 (43), pp.9964-9974. 10.1039/d0sm01221a . hal-03037857

HAL Id: hal-03037857 https://hal.science/hal-03037857

Submitted on 3 Dec 2020

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Open Archive Toulouse Archive Ouverte

OATAO is an open access repository that collects the work of Toulouse researchers and makes it freely available over the web where possible

This is an author's version published in: http://oatao.univ-toulouse.fr/ 26985

Official URL : https://doi.org/10.1039/d0sm01221a

To cite this version:

Merzougui, Charaf E. and Roblin, Pierre and Aimar, Pierre and Venault, Antoine and Chang, Yung and Causserand, Christel and Bacchin, Patrice Pearl-necklace assembly of human serum albumin with the poly(acrylic acid) polyelectrolyte investigated using small angle X-ray scattering (SAXS). (2020) Soft Matter, 16 (43). 9964-9974. ISSN 1744-683X Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

Pearl-necklace assembly of Human serum albumin with poly (acrylic acid) polyelectrolyte explored by small angle X-ray scattering (SAXS)

Charaf E. Merzougui §*, Pierre Roblin §*, Pierre Aimar §, Antoine Venault I, Yung Chang

", Christel Causserand §, Patrice Bacchin §.

§ Laboratoire de Génie Chimique, Université de Toulouse, CNRS, INPT, UPS,

Toulouse, France

R&D Center for Membrane Technology, Chung Yuan Christian University, Chung Li,

Taiwan

Keywords

Human Serum Albumin, poly(acrylic acid), interaction, ionic strength, pH, SAXS.

Abstract

Soft Matter Accepted Manuscript

Soft Matter

In this comprehensive study, interaction of human serum albumin (HSA) with poly(acrylic

View Article Online DOI: 10.1039/D0SM01221A

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

acid) (PAA) was explored using Small Angle X-ray Scattering (SAXS) combined to chromatography. Results revealed the formation of a complex between HSA macromolecules and PAA chains but solely at some specific conditions of ionic strength and pH of the medium. In fact, this binding has found to take place only at pH close to 5 and low ionic strength (0.15M). Otherwise, for higher pH and salts concentration 0.75M the HSA-PAA complex tends to dissociate completely showing the reversibility of the complexation. The assessment of the influence of the HSA/PAA molar ratio on the complex radius of gyration suggests that 4 HSA molecules could bind to each PAA 100kDa chain. Besides the Porod volume evaluation for the same range of HSA/PAA ratio confirms this assumption. Finally, an all atom SAXS modelling study using BUNCH program has been conducted to find a compatible model that fit HSA-PAA complex scattering data. This model allows to portray the HSA/PAA complex as a pear-necklace assembly with 4 HSA on the 100 kDa PAA chain.

Introduction

Soft Matter

View Article Online DOI: 10.1039/D0SM01221A

Interactions between proteins and polymeric surfaces, whether linear (polyelectrolyte brushes)^{1,2} or spherical (functional nanoparticles) ^{3–5}, have received growing attention over the past few decades. Many processes involve this phenomenon in several fields and for versatile applications, as protein separation ^{5,6}, drugs delivery ^{7,8}, ligands uptake ⁹, enzyme immobilization ¹⁰, antibacterial encapsulation ¹¹, among many other applications in chemistry and biology ¹².

Biomaterials and medical devices design are among the fields in which this interaction is relevant ^{13,14}. Biomaterials are often used for the treatment of diseases such as cardiac failure, but also in medical applications such as wound healing, deep skin injury repair, dentistry or orthopedics ¹⁵. In many cases, these biomaterials get into direct contact with blood. One of the fastest growing areas for biomaterials is the development of new systems for controlled and targeted drug delivery. For example, suitable membrane advanced technologies could be proposed to address several critical needs related to blood cells screening and the concentration of the growth factors stored inside the granules of platelets and expressed after their activation, and which role in the wound healing process of diabetic ulcers is predominant. For that, the architecture of membrane

biointerface at the nanoscale is often customized by grafting on it some functional groups

such as poly acrylic acid (PAA). It is a negatively charged bioactive polymer in aqueous medium widely used to modify polymeric surfaces for drugs release and many other applications¹⁶. One of them is the enhancement of platelets adhesion, especially when it's conjugated to proteins such as fibrinogen. However, nonspecific interactions between other blood components and polymers used for interface modification could hamper the capture of platelets. Among those blood components, Human Serum Albumin (HSA) is an abundant plasma protein ([HSA]~42mg.mL⁻¹ in blood ¹⁷) that maintains the blood pH and osmotic pressure and transports some molecules in the blood. This protein is able to decrease platelet adhesion and activation on a solid surface by being adsorbed onto that particular surface ¹⁸. Therefore, in the purpose of designing functionalized membrane surfaces to selectively separate thrombocytes from other blood cells, the control of these nonspecific interactions is required.

According to the literature, a number of protein-polyelectrolyte complexes have been studied in a variety of physicochemical conditions via several analytical techniques ^{19,20}. Concerning complexes of serum albumin and polymers, the interaction of bovine serum

4

Soft Matter

View Article Online DOI: 10.1039/D0SM01221A

albumin (BSA) with spherical polyelectrolyte brushes in solution was evidenced using Small Angle X-ray and neutron scattering (SAXS and SANS) ^{21,22}. Interactions between BSA and planar synthetized poly(acrylic acid) were also the object of a dedicated work ²³. Furthermore, binding of HSA with small polyelectrolyte brushes of PAA (with 25 repeating units only)^{25,} and with dendritic polyglycerol sulfate²⁶, has also been discussed by isothermal calorimetry (ITC). In fact, it has been proved that only one HSA is bound per chain of PAA 1.8 kDa. Then, for a pH maintained at 7.2, a study on the effect of salt concentration revealed that this binding was dominated by an attractive electrostatic potential between the two solutes ²⁴. Using Total Internal Reflection Fluorescence (TIRF) spectroscopy, it also has been proven that negatively charged BSA is strongly adsorbed on planar PAA (278 AA units ~20kDa) at low ionic strength and pH > 5 due to electrostatic interactions ²⁶. However, the current knowledge does not permit to give the exact stoichiometry of the polyelectrolyte-protein complexes for larger polymer, and if it is correlated to the size of the polyelectrolyte.

In the present study, we used SAXS combined to chromatography to assess the affinity of HSA to bind to a larger PAA (100 kDa) to check out the formation of multiprotein-

polymer complexes compared to the 1HSA-1PAA binding reported in the literature using

smaller polyelectrolyte ²⁴. First, as a starting point for further experiment with polymers, the structure of native HSA was examined in Phosphate buffer solution. Then, the HSA/PAA complexation was studied in media with different ionic strengths or pH in order to find the conditions leading to an attractive interaction. After that, a detailed study modeling the Porod volume was conducted to determine the stoichiometry of the (nHSA-PAA) complex formed. For this purpose, the influence of the HSA/PAA molar ratio on the complex size (radius of gyration and Porod volume) was appraised. Eventually, a compatible model has been found using BUNCH program ²⁷ to fit the HSA-PAA complex scattering data. It allowed us to propose an all atoms pearl necklace model that describes the structure of complex at the ionic strength and at the pH outlined in the preceding paragraphs, and it also validated the proposed stoichiometry.

Experimental section

Materials and sample preparation

Human serum albumin (HSA, lyophilized powder, \geq 96% agarose gel electrophoresis) with a molecular weight of 66,478 g.mol⁻¹ was purchased from Sigma Aldrich and used

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM

Soft Matter

View Article Online DOI: 10.1039/D0SM01221A

as received, as well as the poly acrylic acid (PAA) of molecular weight around 100,000 g.mol⁻¹ (35 wt. % in H_2O).

HSA powder was dissolved in PBS 1X (0.012M phosphate buffer solution at pH 7.4, ionic strength 0.137M) to obtain a stock solution of 50 g.L⁻¹ HSA (750 μ M), from which samples of lower concentration were prepared. The same way, the polymer solutions were prepared by dilution in PBS 1X buffer from a stock PBS solution of 100 g.L⁻¹ PAA (1 mM).

For the investigation of native HSA structure in solution and HSA-PAA interaction, the concentration of the HSA was set at 5 g.L⁻¹ to avoid repulsion between particles which can distort the measured intensity in small angles. The pH effect was studied using different buffer solutions at 0.1 M (TRIS base pH 8, HEPES pH 7, MES pH 6, mixture of sodium citrate di-hydrate and citric acid at pH 4-5). As for the ionic strength influence, the salts concentration was adjusted by adding the needed amounts of 4 M NaCl solution.

Then, all samples, whether protein free, polymer free or a mixture of both, were stirred using a Thermo Scientific mini centrifuge (mySPIN 12) at 10 000 rpm for 2 minutes at least, to ensure good dissolution of the solutes, before being pipetted into the samples holder for the SAXS measurement. Out of use, the samples were stored at 4°C in a refrigerator.

Chromatography measurement

The chromatography unit used consisted of an Agilent 1260 infinity system connected to a UV-VIS detector set at a wavelength of 280 nm. Analyses were performed using an Agilent Bio Sec-3 (3µm, 4.6x300 mm, 300 Å) size exclusion column at room temperature. In a typical analytical run, 50µL of a 75µM protein solution was injected, and PBS 1X was used as mobile phase for protein structure investigation at a flow rate of 0.4 ml.min⁻¹. As for protein-polymer complexation study, a 75µM HSA+ 50µM PAA solution was injected and the mobile phase was PBS solution containing 50 µM PAA.

SAXS measurement

SAXS measurements were performed at Laboratoire de Genie Chimique, Toulouse, on the XEUSS 2.0 bench equipped with a copper internal source (Genix3D) that produces an X-ray beam with an energy of 8 keV and a flow of 30.10⁶ ph. mm².s⁻¹ with a beam sized at 500x500 µm. The SAXS bench is equipped with an HPLC online (Agilent 1260

View Article Online DOI: 10.1039/D0SM01221A

infinity) connected to the SAXS cell allowing to add a purification step by size exclusion chromatography. In direct injection mode, that is, without size exclusion chromatography step, 50 µL of sample are pipetted from the samples holder maintained at a constant temperature (20 °C) using a circulating water bath, and are injected to the measurement cell placed under vacuum to limit air absorption. Data were collected on a 150x150 mm area DECTRIS detector (Pilatus 1M) with a sample to detector distance of 1216 mm. The scattering intensity l(q) experimentally determined is expressed as a function of the scattering vector q (in Å⁻¹) resulting from a photon of wavelength λ scattering off the sample at an angle *20*.

$$q = \frac{4\pi \sin\left(\theta\right)}{\lambda} \#(1)$$

Each scattering curve reported in this paper is an average of at least 6 measurements on the same sample, and each SAXS measure corresponds to a data collection time of 1800s. Scattering curves were recorded within the range 0.005 < q < 0.5 Å⁻¹. Finally, actual solutes scattering intensity *l(q)* was obtained by subtracting the buffer solution contribution from the total SAXS signal.

9

Soft Matter

Porod volume calculation

From SAXS experiments, it is possible to obtain the Porod volume of an object from the

Porod invariant Q^{28} :

$$V_{obj} = \frac{2\pi^2 I(0)}{Q} * \frac{1-\phi}{S(0)} \#(2)$$

When the dispersion is diluted the volume fraction $\phi \rightarrow 0$, $S(0) \rightarrow 1$ and the Porod volume can be determined by knowing the zero angle intensity I(0) and Q. Q is called the Porod invariant because its value does not depend on the structure but

on the volume fraction and the contrast between two phases $\Delta \rho$:

$$Q = \int_{0}^{\infty} q^{2} (I(q) - K) dq = 2\pi^{2} \phi (1 - \phi) r_{e}^{2} (\Delta \rho)^{2} \#(3)$$

Where K is a constant defined to ensure the asymptotical intensity decay proportional to q⁻⁴ at higher angles ²⁹.

The value of Q can be roughly obtained from the integration of the Kratky plot (classically with a limited integration boundary at q=0.25) by considering K=0:

$$Q = \int_{0}^{0.25} q^2 I(q) dq \#(4)$$

When the intensity decreases too slowly at large q (less than q^{3}) as for polymeric

systems ³⁰ it is well more accurate to integrate the original equation after determining the constant *K*. Whereby the constant *K* is calculated from the Porod asymptote l(q). q^{d} versus q^{d} at higher angles. In these calculations, the asymptote has been always determined for the same range of *q* between 0.3 and 0.445 with a homemade code to keep the control of the calculation. The code is given with the plots that shows the determination of *K* (Fig. 4-5) in **Supplementary Information SI-2**, as well as the corrected dimensionless Kratky plot obtained by subtracting *K* from l(q), (Fig. 6 in **SI-2**). It can be seen that the subtraction of the asymptote *K* leads to a curve that tends to zero for high *q* which then permit a good integration of the invariant *Q*.

Results and discussion

Study of single HSA

The structure of native HSA was first examined in a 0.012M phosphate buffer solution at pH 7.4, and the obtained SAXS scattering intensities were compared to those calculated from the crystal data of HSA on the Protein Data Bank (6EZQ). In order to



chromatographic system is coupled upstream of the SAXS.

Figure 1. Experimental SAXS scattering intensity l(q) of HSA 75 µM (blue line) compared to the SAXS intensity calculated with CRYSOL from HSA crystal structure 6EZQ (red curve). The inset represents the Guinier plot (*Ln I(q) vs q*² in red line) with the residual (green curve) that allow to determine the radius gyration using Primus. The HSA 3D structure shown in cartoon representation using PyMOL software.

Figure 1 shows that the experimental SAXS spectrum from purified commercial HSA (blue line) matches very well the calculated intensity from the crystal structure (red line), evidencing that the HSA used for this study is correctly folded at 75 μ M in the PBS buffer condition. These preliminary results validate the use of HSA as a template to study protein

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

polymer interaction. In these conditions we can expect that the SAXS will be precise enough to sense an interaction between HSA and PAA.

The HSA radius of gyration R_g was then evaluated by fits using Foxtrot or Primus ^{28,31} Both software consider the Guinier approximation that allows to determine R_g from the slope of the linear fit at low q of I(q) vs q^2 (Figure 1), as it gives the forward scattering intensity I(0) from the intercept based on the following equation:

$$\lim_{q \to 0} I = I_0 exp\left(-\frac{1}{3}q^2 R_g^2\right) \#(5)$$

The result yields approximately 30 Å (30.4±0.2 Å), which is almost what was found with R_g (30.2 ± 0.4 Å) in a SAXS study for HSA with the same purity >96% ¹⁷.

Likewise, the Porod volume and molecular weight were estimated using Primus that consider the Porod law (Supplementary Information SI-2), and found to be around 100,000 Å ³ and 64.5 kDa respectively. These results seem to be consistent with the molecular weight of HSA (66.5 kDa), which validates the use of Primus to evaluate such parameters in further experiments.

HSA-PAA interaction

The characterization of single protein was then followed by assessing the interactions

Soft Matter Accepted Manuscript

between HSA and the polyelectrolyte chains. For that, we first studied the effect of an increase in PAA concentration on the SAXS scattering intensity for an HSA/PAA molar ratio ranging from 0 (protein alone as a reference) to a molar ratio of 3/2. As shown in Figure 2, starting from 40 µM of PAA with 75 µM HSA, a strong change in the signal at small angles is observed, which could be due to the formation of an HSA-PAA complex, while in the intermediate and high q-range the SAXS curves remain almost unchanged by the complexation. Indeed, the evolution of the slope P of the corresponding power law $I(q) = q^{P}$ shows that at intermediate angles (0.1 to 0.2 Å⁻¹), P slightly varies from 3.8 for single HSA and the mixture of HSA+10, 20 and 30µM PAA, to 4 when increasing the PAA concentration to 40 and 50µM (Figure 2). These results indicate a same type of surface despite the big change in the general shape shown by an increase in the slope at small angles (0.005 to 0.05 Å⁻¹). In fact, the difference is more obvious, where the slope is going from almost a tray (P=0.3) for single HSA, to a slope of 1.2 when adding 50µM PAA, which corresponds to the slope of an elongated object ³².

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.



Figure 2. Scattering intensities of HSA-PAA mixture and pH evolution for [HSA]=75 μ M as a function of PAA concentration ([PAA]=0 to 50 μ M). Evolution of the slope of the power law *I(q) = q*^{-*P*} corresponding to small and intermediate angles.

PAA, despite being in PBS buffer, strongly influences the pH of the solution. Thus, we can suppose that the change in the SAXS curve could be correlated to a pH variation rather than to an effect of the concentration of PAA (explicitly discussed later in the paper). In order to confirm that the change in the SAXS signal at small angles is due to the formation of a new object being an HSA-PAA complex, we compared the SAXS curves from the HSA alone at 75 μ M (blue line), the PAA alone at 60 μ M (green line), the mixture

of both kipping the same initial concentrations (yellow line) and the sum (red line) of the SAXS signals of HSA at 75 μ M and PAA at 60 μ M (Figure 3A).

For the first three curves, the data were processed with GNOM ³³ to determine biophysical parameters such as the radius of gyration R_g , the maximal distance D_{max} using the autocorrelation function P(r). This function was calculated by an indirect Fourier transformation applied to the scattering intensity I(q) using the following equation:

$$P(r) = \frac{r^2}{2\pi r_e^2} \int_0^\infty q^2 I(q) \frac{\sin(qr)}{qr} \, dq \, \#(6)$$

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

The pair distribution function refers to the distribution of electrons averaged over a radius *r*. It entirely depends on the shape and the size of the particle and vanishes at their maximum electron pair distance (D_{max}) . The radius of gyration can be then derived from P(r) using the following expression: : $R_g^2 = \frac{\int_0^{Dmax} r^2 P(r) dr}{2\int_0^{Dmax} P(r) dr} \#(7)$

This alternative estimate of R_g makes use of the whole scattering curve, and is much less sensitive to interactions or to the presence of a small fraction of oligomers. The results of the radius of gyration (29.7 Å for HSA and 110.3 Å for the complex) extracted from the *P(r)* were almost the same compared to those obtained by fits from the Guinier plot (30.4 Å for HSA and 108.9 Å for the complex). The Porod volumes (V_p) for the HSA and the complex were also evaluated. For a flexible system such as polymer chains in solution it's difficult to evaluate the exact V_p . All parameters are reported in the table attached to Figure 3A. Although the curves are calibrated in cm⁻¹, it is impossible to directly determine the mass concentration of the hetero-complex from the *I(0)* because we do neither know the association stoichiometry nor precisely the experimental specific volume and contrast of the PAA.

As observed in Figure 3A, the SAXS curve of HSA is consistent with a 3D object with a large plateau at small angles and a typical decrease at intermediate angles, whereas PAA exhibits a behavior of a flexible polymer in solution (large decrease following a power law $l(q) = q^{P}$ with *P* close to 1.7 which corresponds to polymers with local rigidity) ³⁴. The SAXS curve obtained for the complex presents a combination of properties of HSA and PAA. it shows a constant decrease at small angles and the same signal of HSA starting from 0.05 Å⁻¹. The direct comparison with a linear combination of HSA and PAA SAXS curves (sum curve in Figure 3A) in the same conditions of concentration reflecting the case without interactions between both partners, discloses clearly that the SAXS curve

observed corresponds to the creation a new object resulting from interactions between



HSA and PAA.

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

Figure 3. A) Scattering intensities of [HSA]=75 µM (blue curve), [PAA]= 60 µM (green curve), the mixture of HSA and PAA at same concentrations (yellow curve) and the sum of both contributions without interaction (red curve). Table summarizing the radius of gyration, the maximal distance and the Porod volume of HSA, PAA and the complex. B) Autocorrelation function determined with GNOM of the complex and table summarizing the biophysical parameters extracted from the complexes' SAXS data.

The evaluation of R_q and V_p shows that the complex is five times larger than HSA alone but the difficulty to evaluate correctly the Porod volume of PAA (in the complex) or its contribution in the measured I(0) does not allow to give directly the numbers of HSA and PAA forming the complex. The form of the autocorrelation function corresponding to the

400

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM

diameter.

complex in Figure 3B shows a skewed distribution with a clear maximum at small distances corresponding to the radius of the cross-section $R_c(R_c=39 \text{ Å from } P(r) \text{ Figure})$ 3B). This distribution is typical of elongated objects such as cylinders, rather than corresponding to amorphous aggregates 35 . With these considerations, the length L of this cylinder can be calculated using the following relationship $L = (12.R_a^2.R_c^2)^{0.5}$. The diameter of the cylinder and the calculated length L and all evaluated parameters are summarized in the table attached to Figure 3B. The value of the calculated length (404 Å) is consistent with the maximal distance (390 Å) determined with *P(r)* calculation. One can assume that the complex of HSA/PAA-100 kDa exhibits a behavior in solution equivalent to the one of a solid cylinder measuring around 400 Å in length and 78 Å in

To validate this hypothesis predicting a formation of a defined object instead of amorphous aggregates, solutions of HSA-PAA were flowed in various mobile phases through a size exclusion chromatography column (**Supplementary Information SI-1**). The chromatographic profiles were then compared to that of the single HSA detected mainly at 7.74 min and as classically with a small amount of dimers at 6.9 min (Figure 4).

Soft Matter Accepted Manuscript

In fact, in a PBS mobile phase (without PAA) at pH 7.4, a peak at 7.7 min of retention time was obtained, corresponding to the molecular weight of HSA alone. This experiment shows that the complex can be dissociated in a dilute medium of PAA, illustrating the reversibility of the complex formation. On the other hand, if 50 µM of PAA is added to the mobile phase, the pH decreases to 5.2 and the elution profile is modified with a strong shift of the elution peak towards high molecular weights (Figure 4). This observation proves that the protein is no longer single in the solution but bound to the PAA chains. The Gaussian shape of the peak eluted at 5.8 min corresponds to a profile of unique object in solution and not to a continuous distribution of mass such as in aggregates.



Figure 4. Comparison of chromatographic profiles for HSA 75 μM in PBS 1X mobile phase (red peak) and

for (75 µM-50 µM) HSA-PAA mixture in PBS+50 µM PAA solution mobile phase (orange peak).

Soft Matter

These experiments were run at PBS ionic strength (0.137 M) and at pH controlled by the PAA concentration, ranging from 5.2 to 7.4 as mentioned above (Figure 2). Since the pH remains higher than the HSA isoelectric point (4.7) and knowing that PAA exhibits a pKa of 4.5, we expect repulsive forces that keep them away from each other. It is because they both theoretically bear negative charges. Yet, the adsorption of HSA molecules on PAA chains is found to happen. Attractive interactions between a polyelectrolyte and a protein having the same net charge were reported by several authors ^{20,36–38}. Since the proteins can carry both positive and negative charges, this binding found to occur in our study could be due to the attractive electrostatic potential between the positive charged patches on the surface of HSA and the negatively charged chains of PAA, which should be the operative force that overcome the repulsion forces. A detailed ITC study performed on the binding between HSA with negative overall charge and a negatively charged PAA ²⁴, shows the same behavior between the two solutes, where each HSA molecule has found to bind to one PAA chain causing an increase in the system entropy. It has been explained by the action of the HSA surface positive charges as a multivalent counter ion for the polyelectrolyte.

Other works doing experiments and dynamics computer simulations have addressed more deeply such phenomenon between proteins and polyelectrolytes ^{39–41}. They showed a large binding affinity between charged patchy proteins and like-charged polyelectrolyte brushes despite having the same net charge. It has been shown that the strongest attraction of typical proteins at the brush surface, is driven by multipolarity, Born energy (self-energy), and counterion-release contributions, which dominate locally over the monopolar and steric repulsions.

Ionic strength and pH effect on HSA/PAA complexation

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

For the study of ionic strength and pH effects, the [HSA] was set at 75 μ M and the [PAA] at 50 μ M (pH ~ 5 remains controlled by the polymer concentration), where the complexation was observed, while the ionic strength was varied from 0.137 M to 1 M by adding a needed amount of a 4 M NaCl solution.

Data obtained and reported below (Figure 5A) reveal a decrease in scattering intensity with the increase in ionic strength. Obviously curves are moving down especially at medium and small angles (0.005 to 0.1 Å^{-1}), changing the slope, to collapse for an ionic strength of 0.75 M and 1 M with the theoretical sum (plotted as red line) of two A)

100

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM

independent signals without interaction (signal of HSA 75 μ M+ signal of PAA 50 μ M)

obtained at I=0.137 M. This finding confirms the previous assumption and bears out the

B)

100

fact that the binding of HSA-PAA is due to electrostatic interactions.



Figure 5. Scattering intensities of HSA-PAA mixture for [HSA]=75 µM and [PAA]=50 µM, (A) as a function of ionic strength (I=0.137 to 1 M) for pH≈5, and (B) as a function of pH (pH=4.6 to 8) for I=0.137 M.

Afterwards, salts concentration was set at 0.137 M and pH was changed from 8 to 4.6 using different buffer solutions. As shown in Figure 5B, the decrease in pH down to 5 promotes the formation of the complex whereas at pH > 5 the complex is dissociated giving the same SAXS signal as a mix of two independent contributions. These experiments show the key roles of the pH and the ionic strength on complex formation correlated to the charge distribution of amino acid forming the binding pocket of HSA and

Soft Matter Accepted Manuscript

to the charge density of the PAA. The decrease in pH allows to reduce the repulsive forces until the initiation of the attractive potential between the positive charges carried on HSA and the negative polyelectrolyte chains. However, at pH lower than 5 (pH 4.6), the obtained SAXS signal (Figure 5B) is significantly different (slope P=1.5) from the one of a macromolecular complex (slope P=1.2). Since the drop of pH to 4.6 cannot sufficiently alter the net charge of the protein (isoelectric point 4.7) to create phase separation, one can consider that HSA starts being unfolded and form aggregates, because it undergoes form transition between pH 5.0 and 3.5⁴².

In order to determine the best conditions of complex formation, SAXS measurements for a matrix of conditions were performed where the ionic strength was varied from 0 to 0.75 M for each pH 5, 6 and 7. As the major effects are observable at small angles due to the increase in size when the complex appears, we decided to probe the changes by evaluating the radius of gyration determined from Guinier law for each condition. Although the PAA and the complex have close R_g values ($R_g \approx 110$ Å), the average value of R_g was found around ≈ 50 Å when the HSA and the PAA do not interact, which is much lower than that of the complex. The data are plotted in Figure 6. One can note that the radius of Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

gyration of free PAA or of single HSA found to be around 110 Å and 30 Å respectively,



do not depend on the pH.

Figure 6. Radius of gyration evolution as a function of both pH and ionic strength showing the threshold needed for complexation phenomenon to occur ([HSA]=75 µM ; [PAA]=50 µM ; pH=5 to 7 and I=0 to 0.75

M).

pH in the range 6-7 does not affect the radius of gyration of the mixture HSA+PAA, found to be approximately 50 Å for all salt concentrations investigated. This observation highlights the fact that HSA-PAA binding does not take place in these conditions. Since the radius of gyration obtained here by fits is an average of the R_g of HSA and of the one of PAA, it makes sense to obtain an average proportional to the amount of each solute in the mixture (protein/polymer ratio of 3/2). A different behavior is observed at pH 5. In fact,

Soft Matter Accepted Manuscript

increasing the ionic strength from 0 to 0.75 M has led to decrease the R_g from 110 Å, which is almost the polymer radius of gyration to 69.8 Å. This is due to the fact that beyond 0.15M of ionic strength the HSA-PAA complex particles begin to dissociate into free HSA molecules and free PAA chains. This dissociation is not complete at 0.75M and some complex particles are still in there since the obtained R_g (69.8 Å) is still higher than the average value (\approx 50 Å) found when the HSA and PAA do not interact. This outcome sustains the previous results (Figure 5) suggesting that complete dissociation of the complex is taking place between 0.75M and 1M.

We conclude from this study that the complex is stable at pH = 5 and a salt concentration below 0.15 M. As previously, we tested the stability of the complex in HPLC with elution buffers at different pH and a constant salt concentration (I = 0.137 M) in the presence and in the absence of PAA. The results show a dissociation of the complex for pH higher than 5 (**Supplementary Information SI-1**). The absence of PAA in the medium also promotes the dissociation, suggesting a large value of the constant of dissociation, which requires the presence of PAA in the buffer to form the complex. We henceforth know the conditions that lead to the assembly of HSA-PAA complexes

in bulk. Therefore, this study constitutes a first knowledge brick to tune these reversible interactions between long PAA grafted on a membrane surface and HSA. Controlling the ionic strength and the pH should enable to regulate these interactions, promoting or preventing their formation. In fact, to enhance the platelets capture on PAA, low salt concentration and pH>5 should be favored to prevent the adsorption of HSA on PAA. Now that the conditions of complex formation are controlled, the stoichiometry of complexation can be investigated.

Determination of the complex stoichiometry (PAA-nHSA)

In order to determine the number of proteins that could bind to each polymer chain, SAXS experiments were performed for a concentration of PAA set at 50 μ M a varying HSA concentration ranging between 75 and 600 μ M. In other words, the [HSA]/[PAA] molar ratio ranged from 1.5 to 12. The experiments were performed at pH 5 and salts concentration I = 0.15 M to ensure complexation.



Figure 7. Scattering profiles of HSA-PAA mixture as a function of HSA amount ([HSA]=75 to 600 μ M ; [PAA]=50 μ M ; pH=5 and I=0.15 M).

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

For a HSA concentration lower than 225 μ M, the SAXS curve increases without a significant change of slope at small and middle angles (0.005 to 0.1 Å⁻¹ Figure 7). This shift of the curves corresponds to an increase in concentration of complex, considering that the contribution of PAA is negligible, compared to the one of the complex (cf. Figure 3A). Given the ratio of Porod volumes between HSA and the complex of R = 1:5, it is expected to have several HSA molecules per chain of PAA. Such behavior in solution

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

View Article Online DOI: 10.1039/D0SM01221A

would suggest that the HSA binding mechanism to PAA is cooperative, without intermediates depending on the concentration of HSA.

When HSA concentration is close to 225 μ M, the signal does not increase any more with the concentration. Beyond 225 μ M, the signal changes at small angles, with a decrease in R_g and I(0) values. At large angles, one observes a change in the SAXS profile. This change is due to an accumulation of free HSA in the medium and eventually the measured signal is a combination of the one of all PAA molecules involved in the complexes and of the un-bound HSA.

Table 1 summarizes the values of R_g and Porod volumes for each ratio of HSA/PAA. Table 1. The evolution of radius of gyration as well as the Porod volume for the HSA-PAA mixture as function of the molar ratio ([PAA]=50 μ M ; [HSA]=75-600 μ M).

[HSA]µM	75	75	150	180	225	300	450	600
nHSA/PAA	Free HSA	1.5	3	3.6	4.5	6	9	12
R _g (±3Å)	30.4	108.3	107	110.1	108.6	90.6	81	74.1
V _p .10 ³ (Å ³)	99.1	428	502	500	491	400	305	239

Soft Matter Accepted Manuscript

From the values of R_g reported in Table 1, it can be concluded that the attachment of proteins to the polymer chains has taken place on all the polyelectrolyte chains available for HSA/PAA molar ratios ranging between 3.6 and 4.5.

To support this hypothesis, the Porod volume was evaluated for the different HSA/PAA molar ratios. From SAXS experiments it is possible to obtain the Porod volume of an object from the Porod invariant *Q* as shown in the experimental section. (plots given in **Supplementary Information SI-2**)

The calculated Porod volumes (reported in Table 1) show the same behavior as that of the radius of gyration. For a HSA/PAA molar ratio of 3.6, the Porod volume is found to be around 500.10³ Å³ which represents the complex Porod volume (Figure 3). Then, we notice that raising the HSA concentration reduces the volume to 239.10³ Å³ for a molar ratio of 12. That makes sense because after saturation of all PAA chains, the excess of HSA contributes to the average of the Porod volume.

On the other hand, a complexation model has been developed to describe the evolution of the Porod volume for the same range of HSA/PAA molar ratio, taking into account the following complexation reaction:

$$n HSA + 1 PAA \rightarrow 1 complex(PAA - nHSA)$$

Where n is the number of HSA in each complex particle.

Thus, for a given initial [HSA]₀/[PAA]₀ molar ratio, it is possible to define [HSA], [PAA] and [c] as the molar concentrations in the mixture during the complexation progress of HSA, PAA and the complex, respectively. It is also possible to determine the relative volume fraction of each solute /in the mixture as follows: (Supplementary Information SI-

3)

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

$$\varphi_i = \frac{N_{Avo}.[i].V_i}{\Phi} \#(8)$$

 ϕ is the volume fraction of the mixture of solutes in solution and it is expressed as:

$$\phi = N_{Avo} \left([c] V_c + [HSA] V_{HSA} + [PAA] V_{PAA} \right) \#(9)$$

Where V_c , V_{HSA} , V_{PAA} are the volume of a molecule of the complex, HSA and PAA respectively. These volumes were estimated using Primus from SAXS spectra of single solutes and found to be: 500.10³, 100.10³ and 50.10³ Å³ for the complex, HSA and PAA, respectively.

Accordingly, the Porod volume could be estimated using a theoretical model. According

to the literature when the dispersion is made of n kinds of particles of volume V_i and

number N_{i} , for a dilute dispersion S (0) =1, the average volume can be written as follows

(O. Spalla eq. 54) 30:

$$V_M = \frac{\sum_i^n N_i V_i^2}{\sum_i^n N_i V_i} \#(10)$$

The Porod volume of the mixture can be written then as a function of the relative volume fraction of solute, φ_i :

$$V_M = \frac{\sum_{i}^{n} \varphi_i V_i}{\sum_{i}^{n} \varphi_i} = \sum_{i}^{n} \varphi_i V_i \#(11)$$

$$V_M = \varphi_c V_c + \varphi_{HSA} V_{HSA} + \varphi_{PAA} V_{PAA} \# (12)$$

Porod volume calculations whether from SAXS experiments or from the theoretical model were performed using a code written in Python (**Supplementary Information SI-2**). The results show that a complex model containing 4 HSA with 1 PAA gives a better fit than those run assuming 3 or 5 HSA per PAA (Figure 8), which corroborates the binding stoichiometry proposed previously. As a matter of fact, when the initial [HSA]₀/[PAA]₀ ratio

is below 4, the mixture is composed of PAA and of the HSA-PAA complex. The Porod

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

volume is then rising up quickly when increasing HSA ratio, from the one of PAA to the one of the complex. For a [HSA]₀/[PAA]₀ ratio of 4, one can consider that there is only the complex (PAA-4HSA) in the mixture and that the SAXS data gives access to the Porod volume of the complex. When the [HSA]₀/[PAA]₀ is larger than 4, the mixture is composed of the complex plus some free HSA.

The complexation model (Supplementary Information SI-3) can then explain the decrease in the mean Porod volume due to the presence of non-associated HSA in addition to the HSA-PAA complex.



Figure 8. The Porod volume evolution as function of the initial [HSA/[PAA] ratio, using experimental SAXS

data and calculation from the complexation model for different stoichiometry coefficient n.

33

Since the stoichiometry of the complex has been now determined, the amount of HSA that could be adsorbed on a PAA of the same size grafted onto a membrane interface can be estimated if the amount of the grafted polyelectrolyte is known.

HSA-PAA complex structure investigation

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

According to the analysis of the autocorrelation function P(r), we can fit the data at small and medium q (less than 0.2 Å⁻¹) using a cylinder of axial length close to 400 Å and diameter equal to 78Å. Thus, the cylinder body was tested to fit the HSA-PAA complex experimental *I(q)* using Sasview (Supplementary Information SI-4). This model can provide information on the global shape of the complex, but provides no structural information on the internal organization of the complex. To propose a model that could be compatible with the SAXS data, we used an approach based on rigid bodies molecular modelling, completing the missing parts with dummies residues (BUNCH). The atomic structure of HSA can be used as a template for rigid bodies and the PAA polymer forms the missing part. As shown by Ballauff and all ²⁴, PAA can interact with HSA in a pocket charged positively, giving a starting point to lock a portion of PAA at the surface of HSA. These portions of HSA-PAA complex are connected each other as a pearl necklace. The rest of PAA is flexible and the conformation can be modified by the program. The program

View Article Online DOI: 10.1039/D0SM01221A

BUNCH ²⁷ is working directly with residues of protein rather than with different types of polymer. However, the chemical structure of PAA is close to a peptides' residue and the PAA polymer can be transformed into poly-glycine chain. As both chains present a difference of mass (Δ =1.26), the individual form factor of the dummies residues is increased in BUNCH program to compensate this default of mass. In total, the 100 kDa PAA chain can be modelled with a poly glycine chain containing 1389 residues.

Soft Matter Accepted Manuscript

Figure 9. Superimposition of SAXS data of the HSA-PAA complex and the SAXS data compatible model calculated with the program Bunch. The SAXS scattering intensity for HSA-PAA complex as dotted thick dark circle, and the model as red line.

During the molecular modelling process against SAXS data, the position and the orientation of individual HSA is free and the conformation of polymer chain is modified in order to describe the space occupied by the PAA. The result obtained is an all atoms model compatible with SAXS data reflecting a possible organization of the complex in solution. Interestingly, the complex forms an elongated structure as a cylinder with a nonspecific orientation of the HSA. The absence of correlation peak in the data suggests that HSA does not present a periodic or partially aligned structure in the complex. This model proposes a globally flexible organization in alternative layers composed of HSA and unfold PAA without frozen structures (Figure 9). Many tests have been performed with different templates and all converge to the same organization with some variations in the position or orientation of HSA. However, the distance between two monomers of HSA always ranges between 80 and 100 Å. Besides, the distance between the extremities of the complex remains constant, found to be 414 Å (Figure 9). These results are consistent

36

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM

with the length of the complex previously evaluated whether from the P(r) or from the fit of the experimental I(q) of the complex performed using Sasview (Supplementary Information SI-4).

Conclusion

An assessment of the HSA protein interaction with PAA polyelectrolyte has been presented in this study combining SAXS and chromatography. The study of the HSA-PAA interactions revealed a complexation phenomenon of protein molecules with the polymer chains. Tests on the effect of the ionic strength showed that this HSA-PAA binding is chiefly an electrostatic interaction, where attractive and repulsive interactions are competing. Decreasing the pH to 5 permits to reduce the negative overall charge of the protein until the electrostatic attraction between the PAA chains and the positive patches on the protein dominates. Besides, this complexation was found to be reversible: the HSA-PAA complex tends to dissociate once put in a diluted medium (without PAA) or a pH greater than 5. That known, it is now possible to control the interactions between HSA and PAA at the membrane interface by changing the physicochemical conditions (pH, ionic strength).

An evaluation of the complex size suggests the attachment of several protein molecules to each polymer chain. The effect of the ratio of the protein concentration to the polymer concentration was also explored, and revealed that 4 HSA could be bound to each 100 kDa PAA chain. A complexation model was proposed, which allowed to describe the Porod volume of the mixture for the different HSA/PAA ratios. From this model, it could be possible to quantify the adsorbed amount of HSA on PAA of the same size grafted to a membrane surface.

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

A SAXS modelling study aimed at describing the complex structure has been also conducted. The cylinder body was found to fit well the experimental SAXS scattering intensities giving an idea of the global shape of the complex, but without providing any structural information. Finally, an all atom pearl necklace model was developed using BUNCH program to better describe the final structure of the complex.

It would be interesting in the future to evaluate the stoichiometry of complexation with different sizes of PAA. As it would be also interesting to assess the reproducibility of this

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

complexation between HSA and a PAA grafted into a membrane surface for the different

physiochemical conditions discussed in this article.

AUTHOR INFORMATION

Corresponding Authors

*E-mail: merzougui@chimie.ups-tlse.fr

*E-mail: roblin@chimie.ups-tlse.fr

Author Contributions

The manuscript was written through contributions of all authors. All authors have given

approval to the final version of the manuscript.

Notes

The authors declare no competing financial interest. There are no conflicts of interest to

declare.

ACKNOWLEDGMENT

Soft Matter Accepted Manuscript

The authors would like to acknowledge the Agence Nationale de la Recherche (MOST-ANR International Program: ANR 17-CE08-0041) for financial support, the FERMaT Federation FR3089 for providing Small Angle X-Ray Scattering laboratory facility. This work benefited from the use of the SasView application (https://www.sasview.org), originally developed under NSF award DMR-0520547. SasView contains code developed with funding from the European Union's Horizon 2020 research and innovation programme under the SINE2020 project, grant agreement No 654000.

References

Senaratne, W.; Andruzzi, L.; Ober, C. K. Self-Assembled Monolayers and Polymer
 Brushes in Biotechnology: Current Applications and Future Perspectives.
 Biomacromolecules 2005, *6* (5), 2427–2448.

(2) de Vos, W. M.; Biesheuvel, P. M.; de Keizer, A.; Kleijn, J. M.; Cohen Stuart, M. A.

Adsorption of the Protein Bovine Serum Albumin in a Planar Poly(Acrylic Acid) Brush Layer As Measured by Optical Reflectometry. *Langmuir* **2008**, *24* (13), 6575–6584.

(3) Henzler, K.; Wittemann, A.; Breininger, E.; Ballauff, M.; Rosenfeldt, S. Adsorption

of Bovine Hemoglobin onto Spherical Polyelectrolyte Brushes Monitored by Small-Angle X-Ray Scattering and Fourier Transform Infrared Spectroscopy. *Biomacromolecules* **2007**, *8*(11), 3674–3681.

(4) Welsch, N.; Lu, Y.; Dzubiella, J.; Ballauff, M. Adsorption of Proteins to Functional Polymeric Nanoparticles. *Polymer* **2013**, *54* (12), 2835–2849.

(5) Wang, S.; Chen, K.; Xu, Y.; Yu, X.; Wang, W.; Li, L.; Guo, X. Protein Immobilization and Separation Using Anionic/Cationic Spherical Polyelectrolyte Brushes Based on Charge Anisotropy. *Soft Matter* **2013**, *9* (47), 11276–11287.

(6) Mattison, K. W.; Brittain, I. J.; Dubin, P. L. Protein-Polyelectrolyte Phase Boundaries. *Biotechnol. Prog.* **1995**, *11* (6), 632–637.

(7) Pourjavadi, A.; Tehrani, Z. M. Mesoporous Silica Nanoparticles with Bilayer Coating of Poly(Acrylic Acid-Co-Itaconic Acid) and Human Serum Albumin (HSA): A PH-Sensitive Carrier for Gemcitabine Delivery. *Materials Science and Engineering: C* 2016, *61*, 782–790.

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM

(8) Das, M.; Mardyani, S.; Chan, W. C. W.; Kumacheva, E. Biofunctionalized PH-

Responsive Microgels for Cancer Cell Targeting: Rational Design. *Advanced Materials* **2006**, *18* (1), 80–83.

(9) Yu, S.; Kent, B.; Jafta, C. J.; Petzold, A.; Radulescu, A.; Schuchardt, M.; Tölle, M.; van der Giet, M.; Zidek, W.; Ballauff, M. Stability of Human Serum Albumin Structure upon Toxin Uptake Explored by Small Angle Neutron Scattering. *Polymer* **2018**, *141*, 175–183.

(10) Chen, H.; Hsieh, Y.-L. Enzyme Immobilization on Ultrafine Cellulose Fibers via Poly(Acrylic Acid) Electrolyte Grafts. *Biotechnology and Bioengineering* **2005**, *90* (4), 405–413.

(11) Rastogi, L.; Arunachalam, J. Synthesis and Characterization of Bovine Serum Albumin–Copper Nanocomposites for Antibacterial Applications. *Colloids and Surfaces B: Biointerfaces* **2013**, *108*, 134–141.

(12) Dubin, P.; Bock, J.; Davis, R.; Schulz, D. N.; Thies, C. *Macromolecular Complexes*

in Chemistry and Biology, Springer Science & Business Media, 2012.

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM

View Article Online DOI: 10.1039/D0SM01221A

(13) Nel, A. E.; Mädler, L.; Velegol, D.; Xia, T.; Hoek, E. M. V.; Somasundaran, P.;

Klaessig, F.; Castranova, V.; Thompson, M. Understanding Biophysicochemical Interactions at the Nano-Bio Interface. *Nat Mater* **2009**, *8*(7), 543–557.

(14) Wei, Q.; Becherer, T.; Angioletti-Uberti, S.; Dzubiella, J.; Wischke, C.; Neffe, A. T.;
Lendlein, A.; Ballauff, M.; Haag, R. Protein Interactions with Polymer Coatings and
Biomaterials. *Angewandte Chemie International Edition* **2014**, *53* (31), 8004–8031.

(15) Bhat, S.; Kumar, A. Biomaterials and Bioengineering Tomorrow's Healthcare. *Biomatter* **2013**, *3*(3), e24717.

(16) Tarvainen, T.; Nevalainen, T.; Sundell, A.; Svarfvar, B.; Hyrsylä, J.; Paronen, P.;
Järvinen, K. Drug Release from Poly(Acrylic Acid) Grafted Poly(Vinylidene Fluoride)
Membrane Bags in the Gastrointestinal Tract in the Rat and Dog. *Journal of Controlled Release* 2000, *66*(1), 19–26.

(17) Leggio, C.; Galantini, L.; Viorel Pavel, N. About the Albumin Structure in Solution:
Cigar Expanded Form versus Heart Normal Shape. *Physical Chemistry Chemical Physics*2008, *10* (45), 6741–6750.

(18) Zhang, C.; Jin, J.; Zhao, J.; Jiang, W.; Yin, J. Functionalized Polypropylene Non-

Woven Fabric Membrane with Bovine Serum Albumin and Its Hemocompatibility Enhancement. *Colloids and Surfaces B: Biointerfaces* **2013**, *102*, 45–52.

(19) Cooper, C. L.; Dubin, P. L.; Kayitmazer, A. B.; Turksen, S. Polyelectrolyte–Protein

Complexes. Current Opinion in Colloid & Interface Science 2005, 10(1), 52–78.

(20) Basak Kayitmazer, A.; Seeman, D.; Baykal Minsky, B.; L. Dubin, P.; Xu, Y. Protein

-Polyelectrolyte Interactions. Soft Matter 2013, 9(9), 2553-2583.

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM

(21) Rosenfeldt, S.; Wittemann, A.; Ballauff, M.; Breininger, E.; Bolze, J.; Dingenouts,

N. Interaction of Proteins with Spherical Polyelectrolyte Brushes in Solution as Studied

by Small-Angle x-Ray Scattering. *Physical Review E* 2004, 70(6).

(22) Wang, W.; Li, L.; Henzler, K.; Lu, Y.; Wang, J.; Han, H.; Tian, Y.; Wang, Y.; Zhou,

Z.; Lotze, G.; Narayanan, T.; Ballauff, M.; Guo, X. Protein Immobilization onto Cationic

Spherical Polyelectrolyte Brushes Studied by Small Angle X-Ray Scattering.

Biomacromolecules **2017**, *18* (5), 1574–1581.

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

(23) Topuzoğulları, M.; Çimen, N. S.; Mustafaeva, Z.; Mustafaev, M. Molecular-Weight

View Article Online DOI: 10.1039/D0SM01221A

Distribution and Structural Transformation in Water-Soluble Complexes of Poly(Acrylic Acid) and Bovine Serum Albumin. *European Polymer Journal* **2007**, *43*(7), 2935–2946. (24) Yu, S.; Xu, X.; Yigit, C.; van der Giet, M.; Zidek, W.; Jankowski, J.; Dzubiella, J.;

Ballauff, M. Interaction of Human Serum Albumin with Short Polyelectrolytes: A Study by Calorimetry and Computer Simulations. *Soft Matter* **2015**, *11* (23), 4630–4639.

(25) Ran, Q.; Xu, X.; Dey, P.; Yu, S.; Lu, Y.; Dzubiella, J.; Haag, R.; Ballauff, M. Interaction of Human Serum Albumin with Dendritic Polyglycerol Sulfate: Rationalizing the Thermodynamics of Binding. *The Journal of Chemical Physics* **2018**, *149* (16), 163324.

(26) Hollmann, O.; Czeslik, C. Characterization of a Planar Poly(Acrylic Acid) Brush as a Materials Coating for Controlled Protein Immobilization. *Langmuir* **2006**, *22*(7), 3300– 3305. (27) Petoukhov, M. V.; Svergun, D. I. Global Rigid Body Modeling of Macromolecular Complexes against Small-Angle Scattering Data. *Biophysical Journal* **2005**, *89*(2), 1237– 1250.

(28) Konarev, P. V.; Volkov, V. V.; Sokolova, A. V.; Koch, M. H. J.; Svergun, D. I. PRIMUS: A Windows PC-Based System for Small-Angle Scattering Data Analysis. *J Appl Cryst* **2003**, *36* (5), 1277–1282.

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM

(29) Petoukhov, M. V.; Konarev, P. V.; Kikhney, A. G.; Svergun, D. I. ATSAS 2.1 – towards Automated and Web-Supported Small-Angle Scattering Data Analysis. *J Appl Cryst* **2007**, *40* (s1), s223–s228.

(30) *Neutron, X-Rays and Light. Scattering Methods Applied to Soft Condensed Matter,* New edition edition.; North Holland: Amsterdam; Boston, 2002.

(31) David, G.; Pérez, J. Combined Sampler Robot and High-Performance Liquid Chromatography: A Fully Automated System for Biological Small-Angle X-Ray Scattering Experiments at the Synchrotron SOLEIL SWING Beamline. *J Appl Cryst* **2009**, *42* (5), 892–900. Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM

View Article Online DOI: 10.1039/D0SM01221A

(32) Koch, M. H. J.; Vachette, P.; Svergun, D. I. Small-Angle Scattering: A View on the

Properties, Structures and Structural Changes of Biological Macromolecules in Solution.

Quarterly Reviews of Biophysics 2003, 36 (2), 147-227.

(33) Svergun, D. I. Determination of the Regularization Parameter in Indirect-Transform Methods Using Perceptual Criteria. *J Appl Cryst* **1992**, *25* (4), 495–503.

(34) Chu, B.; Hsiao, B. S. Small-Angle X-Ray Scattering of Polymers. Chem. Rev.

2001, *101* (6), 1727–1762.

(35) Svergun, D. I.; Koch, M. H. J. Small-Angle Scattering Studies of Biological Macromolecules in Solution. *Rep. Prog. Phys.* **2003**, *66* (10), 1735–1782.

(36) Xu, X.; Angioletti-Uberti, S.; Lu, Y.; Dzubiella, J.; Ballauff, M. Interaction of Proteins with Polyelectrolytes: Comparison of Theory to Experiment. *Langmuir* **2019**, *35* (16), 5373–5391.

(37) Seyrek, E.; Dubin, P. L.; Tribet, C.; Gamble, E. A. Ionic Strength Dependence of Protein-Polyelectrolyte Interactions. *Biomacromolecules* **2003**, *4* (2), 273–282.

(38) Xu, Y.; Mazzawi, M.; Chen, K.; Sun, L.; Dubin, P. L. Protein Purification by Polyelectrolyte Coacervation: Influence of Protein Charge Anisotropy on Selectivity. *Biomacromolecules* **2011**, *12* (5), 1512–1522.

(39) Yigit, C.; Heyda, J.; Ballauff, M.; Dzubiella, J. Like-Charged Protein-Polyelectrolyte Complexation Driven by Charge Patches. *J. Chem. Phys.* **2015**, *143* (6), 064905.

(40) Yigit, C.; Heyda, J.; Dzubiella, J. Charged Patchy Particle Models in Explicit Salt:
Ion Distributions, Electrostatic Potentials, and Effective Interactions. *J. Chem. Phys.* **2015**, *143* (6), 064904.

Published on 21 September 2020. Downloaded by Karolinska Institutet University Library on 9/21/2020 8:09:57 PM.

(41) Yigit, C.; Kanduč, M.; Ballauff, M.; Dzubiella, J. Interaction of Charged Patchy
Protein Models with Like-Charged Polyelectrolyte Brushes. *Langmuir* 2017, *33* (1), 417–427.

(42) Dockal, M.; Carter, D. C.; Rüker, F. Conformational Transitions of the Three Recombinant Domains of Human Serum Albumin Depending on PH. *J. Biol. Chem.* **2000**, *275* (5), 3042–3050.

Page 49 of 50

179x133mm (96 x 96 DPI)