

Development of a new insulating bio-based composite made from sunflower stalk aggregates and chitosan: Thermal, mechanical and acoustical characterizations

Narimane Mati-Baouche, Hélène de Baynast, Shengnan Sun, Cédric Delattre, Carlos Javier Sacristán López-Mingo, Philippe Leclaire, André Lebert, Philippe Michaud

► To cite this version:

Narimane Mati-Baouche, Hélène de Baynast, Shengnan Sun, Cédric Delattre, Carlos Javier Sacristán López-Mingo, et al.. Development of a new insulating bio-based composite made from sunflower stalk aggregates and chitosan: Thermal, mechanical and acoustical characterizations. Journées Scientifiques et Techniques - JST AMAC/SFA/AFM, Apr 2014, Nevers, France. 2014. hal-03040136

HAL Id: hal-03040136 https://hal.science/hal-03040136

Submitted on 5 Apr 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Development of a new insulating bio-based composite made from sunflower stalk aggregates and chitosan: Thermal, mechanical and acoustical characterizations

N. Mati-Baouche⁽¹⁾, H. de Baynast⁽¹⁾, Shengnan Sun⁽¹⁾, Cédric Delattre⁽¹⁾, C. J. S. Lopez Mingo⁽²⁾, P. Leclaire⁽²⁾, A. Lebert⁽¹⁾, P. Michaud⁽¹⁾

(1) Clermont Université, Université Blaise Pascal, Institut Pascal UMR CNRS 6602, 24 avenue des Landais, BP-206, 63174, Aubière Cedex, France (2) Université de Bourgogne, Laboratoire DRIVE, ISAT, 49 rue Mademoiselle Bourgeois, B-P. 3158027, Nevers Cedex, France

Introduction

The ANR DEMETHER project certified by Cereal Valley and Viaméca has for objective to use sunflower stem by-products as reinforcement of panels to insulate existing buildings. The originality of this approach consists in using natural binders such as chitosan in the aim to obtain competitive bio-based materials for their thermal, mechanical, acoustical, economical and environmental performance.



Process of Characterization



Composites Production

An experimental design was established to find the optima parameters which influence the thermal and mechanical properties of the bio-based composite: the size grading of particles, the ratio chitosan/sunflower particles and the compaction pressure during manufacture :

Area of variations of the operating parameters.

Level	Particle size (mm)	Ratio (%)	Compaction pressure (10 ⁻³ MPa)
+1.68	6.30	15.3	574
+1	5.00	13.3	373
0	3.12	10.0	156
-1	2.00	6.6	32
-1.68	1.60	4.3	1



Heat conductivity (κ) determination by Hot Wire method (Neotim FP2C)



Thermal, mechanical & acoustical analyses

Process of obtaining agro-composite from sunflower stalks and chitosan. (A) sunflower stalks (LG5474), (B) chitosan solutions at 2-9% (w/v), (C) sunflower stalk particles (1–6 mm), (D) PVC mold, (E) composite sunflower/chitosan obtained for compressive analysis, (F) composites obtained for the tensile analysis.



Sound absorption coefficient (α) determination by Impedance Tube method Young modulus (E') and maximum stress (σ_{max}) determination by Tensile and Compressive analysis (Zwick/Roell)

Results

Results of the experimental design obtained on both mechanical and thermal properties of composites chitosan/sunflower stalks aggregates, as a function of the applied compaction pressure, the size of sunflower particles and the ratio chitosan/sunflower.

	Optimal properties	Compaction (10 ⁻³ MPa)	Size of particles (mm)	Ratio (w/w) chitosan/sunflower (%)
Tensile mode	E' = 250 MPa	574	3.1	15.38
	$\sigma_{max} = 2 MPa$	574	6.3	/ ^a
	$\kappa = 0.056 \text{ W m}^{-1} \text{ K}^{-1}$	574	6.3	4.38
Compressive mode	E' = 25 MPa	574	6.3	15.38
	$\sigma_{\rm max} = 2.6 {\rm MPa}$	574	6.3	15.38
	$\kappa = 0.058 \text{ W m}^{-1} \text{ K}^{-1}$	1	6.3	4.38

^a No significant effect was observed.

> Bio-based composite = thermal insulator ($\kappa = 0.06$ W.m⁻¹.k⁻¹)

► Bio-based composite: σ_{max} in tensile mode $\approx \sigma_{max}$ in compression mode ≈ 2 MPa

>Mechanical performances are superior to the specification of the building in Europe (DIN 4108-10 maximum stress of 0.05 MPa)

>Confirmation of chitosan's potential to be employed as a linker to bond plant particles

 \triangleright Low acoustical performance of the bio-based composite $\alpha = 0.2$ in the frequency of 2500-4000 Hz

Conclusions & Perspectives

> Composites having a heat conductivity of 0.06 W.m⁻¹.k⁻¹ and a maximum stress of 2 MPa were obtained with a ratio of chitosan of 4.3 % (w/w) and a size grading of particles of 6.3 mm. These mechanical and thermal performance are superior to the other insulating bio-based materials available on the market.

> Study the aging of the bio-based composites, as a function of temperature, ultra-violet radiations and relative humidity, is a perspective.

Acknowledgements

This work was supported by the French National Research Agency (ANR-DEMETHER 10-ECOT-004 grant) and the French clusters: Céréales Vallée and Viaméca.