



HAL
open science

Luminescent Yb³⁺,Er³⁺-Doped α -La(IO₃)₃ Nanocrystals for Neuronal Network Bio-Imaging and Nanothermometry

Geraldine Dantelle, Valérie Reita, Cécile Delacour

► **To cite this version:**

Geraldine Dantelle, Valérie Reita, Cécile Delacour. Luminescent Yb³⁺,Er³⁺-Doped α -La(IO₃)₃ Nanocrystals for Neuronal Network Bio-Imaging and Nanothermometry. *Nanomaterials*, 2021, 11 (2), pp.479. 10.3390/nano11020479 . hal-03142279

HAL Id: hal-03142279

<https://hal.science/hal-03142279>

Submitted on 26 Feb 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Luminescent Yb³⁺,Er³⁺-doped α-La(IO₃)₃ nanocrystals for neuronal network bio-imaging and nanothermometry

Géraldine Dantelle ^{1,*}, Valérie Reita ¹ and Cécile Delacour ^{1,*}

¹ Univ. Grenoble Alpes, CNRS, Grenoble INP, Institut Néel, 38000 Grenoble, France; geraldine.dantelle@neel.cnrs.fr (GD); valerie.reita@neel.cnrs.fr (VR); cecile.delacour@neel.cnrs.fr (CD)

* Correspondence: geraldine.dantelle@neel.cnrs.fr (GD); cecile.delacour@neel.cnrs.fr (CD)

Abstract: Dual-light emitting Yb³⁺,Er³⁺-codoped α-La(IO₃)₃ nanocrystals, known to exhibit both second harmonic signal and photoluminescence (PL), are evaluated as optical nanoprobe and thermal sensors using both conventional microscope and more sophisticated micro-PL setup. When loaded in cortical and hippocampal neurons for a few hours at a concentration of 0.01 mg/ml, visible PL signal arising from the nanocrystals can be clearly detected using an epifluorescent conventional microscope, enabling to localize the nanocrystals along the stained neurons and to record PL variation with temperature of 0.5 % K⁻¹. No signal of cytotoxicity, associated with the presence of nanocrystals, is observed during the few hours of the experiment. Alternatively, a micro-PL setup can be used to discriminate the different PL lines. From ratiometric PL measurements, a relative thermal sensitivity of 1.2 % K⁻¹ was measured.

Keywords: luminescence, harmonic iodate nanocrystals, neurons, biophotonics, nanothermometry

1. Introduction

Temperature is a robust parameter that describes and predicts the state of many systems [1]. In neuronal networks, it is strongly linked with the metabolism and state of cells, triggering biochemical reactions, activation rates and thermal sensitive ionic channels. Slight changes of temperature can affect the dynamics and the reactivity of molecular processes, or reveal disfunction and abnormal developments leading to pathological states. At sub-cellular scales, the expected changes of temperature associated to cellular functions or disfunction is expected to be very weak (100 mW, 10⁻⁵ K) or/and localized (100 - 1 nm) which makes the measure highly challenging [2]. Such small variations could remain hidden and screened by the surrounding extracellular solution which exhibits high thermal conductivity, close to water around 0.6 Wm K⁻¹ [3].

In order to detect subtle temperature differences in neurons, one needs non-invasive, local, stable measurements and highly sensitive thermosensors around metabolism temperature (37 ± 3 °C). The use of luminescent nanoprobe, whose emission properties are dependent on temperature, can be the solution for intracellular thermometry as it is still less invasive and can provide high spatiotemporal resolution [4,5]. Luminescent nanoprobe can be internalized by neurons or adsorbed on their membranes and be in closed contact with the reactive sites, providing a way to sense local and weak variations of temperature along many individual cells at the same time [6,7].

There are many ways to measure temperature through photoluminescence (PL), monitoring either the excited state lifetime, the luminescence intensity, the variation of emission peak position, etc. [8]. Several thermal nanoprobe have been investigated, such fluorescent proteins [9], gold metal nanoclusters [10], nanodiamonds [6], polymer [11] or quantum dots [12], carbon nanodots [13], perovskite nanocrystals [14]. Among them, lanthanide-doped inorganic nanocrystals are of particular interest for their narrow emission lines, related to the f-f orbitals of lanthanide ions involved in the optical transitions and allowing spectral discrimination, for their relatively long excited state lifetime allowing autofluorescence removal by time-gated experiments and for their numerous emission lines covering the visible and near-infrared range [15]. With these nanoprobe, typical luminescence-based nanothermometry consists in a ratiometric approach, consisting in measuring the luminescence intensity ratio (LIR) of two emission peaks that are in thermal equilibrium. To compare the thermal performances of different types of nanoprobe, a relative thermal sensitivity, S_r , has been defined as [16]:

$$S_r = \frac{1}{LIR} \frac{\partial LIR}{\partial T} \quad (1)$$

Many Nd³⁺-doped nanocrystals (SrF₂ [17], LaF₃ [18], NaGdF₄ [19], CaF₂ [20], NaHoF₄ [21], YAG [22]) have been developed for *in-vivo* imaging as Nd³⁺ present emission lines in the biological transparency windows situating in

the near-infrared range (680 to 1700 nm), limiting autofluorescence from the tissues [23,24,25]. However, these Nd³⁺-doped single-band nanothermometers present a moderate S_r (~ 0.1 to 0.5 % K⁻¹, depending on the host matrix [26]), leading to a relatively high temperature uncertainty δT , of the order of 2°C at 37 °C [27,28,29] with:

$$\delta T = \frac{\delta LIR}{LIR} \frac{1}{S_r} \quad (2)$$

with δLIR , the standard deviation of the LIR.

For *in-vitro* experiments, for which visible-emitting nanoprobe can be used, Er³⁺,Yb³⁺-doped nanocrystals present a good alternative as they offer higher S_r values (> 0.2 % K⁻¹), reducing consequently the uncertainty to less than 1 °C and even 0.1 °C in some matrices and in some more complex core-shell architectures [15,30,31]. The high performances of Er³⁺-based nanothermometers have been very recently confirmed theoretically by M. Suta and A. Meijerink, who demonstrated that Er³⁺ ions fulfil all requirements for optimum performances (high S_r in the physiological temperature range) [32].

Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals were recently developed with the goal of proposing multi-functional nanoprobe for *in-vitro* for imaging. The key advantage of these nanocrystals lies in their dual emission properties [33,34]: (1) as non-centrosymmetric nanostructures, non-linear optical signal such as Second Harmonic can be generated upon near-infrared femto-second excitation [35] and (2) the facile, thus efficient, substitution of La³⁺ by Er³⁺ and Yb³⁺ ions leads to PL properties in the visible and near-infrared range [34]. Such combination paves the way to bio-imaging using multiple and complementary imaging techniques: fluorescence imaging using a conventional epifluorescent microscope and in-depth imaging using a two-photon microscope equipped with a short-pulse excitation laser. We report here an additional feature of these Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals and demonstrate, as a proof of principle, their capacity to be used as nanothermometers in neuronal cells. After the measurement of the thermal sensitivity in various environments (powder, liquids), the nanocrystals are loaded in cortical and hippocampal neurons for *in-vitro* bioimaging and temperature measurements.

2. Materials and Methods

Nanocrystal synthesis. Yb³⁺,Er³⁺ doped α -La(IO₃)₃ nanocrystals (La_{0.895}Yb_{0.1}Er_{0.005}(IO₃)₃) synthesis. LaCl₃·6H₂O, ErCl₃·6H₂O and YbCl₃·6H₂O (Strem Chemicals, purity > 99.9%) were mixed, in stoichiometric proportions, in water (10 mL) with a total concentration of 0.05 mol/L. Separately, HIO₃ (Sigma Aldrich, purity > 99.5 %) was also dissolved in water, with a molar concentration of 0.15 mol/L. Both solutions were mixed together and poured into a quartz vessel, then placed into a Anton-Paar Multiwave PRO microwave oven. The heating was conducted at 250 °C for 10 minutes to crystallize the α -La(IO₃)₃ phase [36]. After cooling down, the white precipitate is retrieved by filtering and washed several times with distilled water before drying at room temperature for 24 h.

Nanocrystal structural characterizations. Powder X-ray diffraction (XRD) pattern was recorded on a Siemens D8 Advance diffractometer ($\lambda_{Cu} = 1.54056$ Å) at room temperature. Scans were collected in the 2θ range 16-90°, with a step of 0.005° and 1 s of acquisition time. Transmission electron microscopy (TEM) images were recorded using a Philips CM300 microscope, operating at 300 kV and equipped with a TemCam F416 TVIPS camera. Because of the lack of stability of the iodate nanocrystals under the electron beam, the experiment was performed using a liquid-nitrogen cooled sample holder. The experiment at lower temperature (estimated between 77 and 170 K) allows preserving the nanocrystals from being modified under the beam.

Photoluminescence measurements. PL and PL excitation spectra of powdered Yb³⁺,Er³⁺ doped α -La(IO₃)₃ nanocrystals were measured using a commercial Safas fluorimeter (Xenius) at room temperature. Using a tunable vertically polarized femtosecond laser (Insight X3 Spectra-Physics, 80 MHz, 100-120 fs) as the excitation source, the non-linear properties of these nanocrystals dispersed in solution were recorded, as detailed in [34]. Temperature-dependent PL measurements were performed using a micro-PL setup coupled with a temperature stage (Linkam THMS600). The excitation was performed using a CW Argon laser (488 nm, typical power: 100 kW.cm⁻²) and focused on the sample through an Olympus objective ($\times 60$). The emission was collected through the same microscope objective and detected, after a razor edge filter at 488 nm, through a T6400 spectrometer equipped with a Symphony Camera detector cooled at 77 K. During the cell culture, the photoluminescence is collected in liquids using an upright-style epifluorescent Olympus BX51 microscope. The incident illumination (white light, Xenon lamp) is filtered at $\lambda_{exc} = 488 \pm 20$ nm and focused on the sample with a $\times 60$ water-immersion objective. The emitted photons are collected through the same objective and filtered at $\lambda_{em} = 535 \pm 25$ nm. A High pass dichroic mirror at $\lambda_{dic} = 510$ nm suppresses the contribution of the incident photons on the signals that is recorded with sCMOS camera cooled between 80-70K.

Cell culture. E16.5 pregnant mice were killed by cervical elongation. Hippocampi were dissected from the mouse embryos in HBSS-HEPES (Gibco), incubated 15 min in Trypsin 2,5% (Gibco), rinsed in HBSS-HEPES twice, and mechanically dissociated by repeatedly pipetting in 1 mL attachment medium (MEM supplemented with 10% foetal bovine serum, 1% glutamine and 0.05% peniciline/streptomycine, Gibco). Cells were seeded with a density of 150 000 cells/mL on the glass coverslip previously sterilized and coated with poly-L-lysine (PLL, 1mg/mL) to ensure neurons adhesion. Neurons were then incubated at 37°C and 5% CO₂ in the attachment medium, and replaced a few hours later by serum-free glial conditioned medium supplemented with 1 mM AraC.

Nanocrystals loading. Nanocrystals were dispersed in 37°C culture medium with ultrasonic bath to prevent large aggregates, and add to the cells medium at a final concentration ranging from 0.1 to 0.001 mg/mL. Constant agitation was maintained during few minutes. Then cells with nanocrystals were incubated at 37 °C and 5% CO₂ until observations (around 3 h).

Immunostaining. After PL acquisition neurons were fixed in 3,9% paraformaldehyde (10 min), permeabilized in PBS-0.1% Triton-X100 (3 min) and blocked in PBS-2% bovine serum albumin (10 min). After each step, the solution (PFA, PBS-Triton or PBS-BSA) is removed and cells are rinsed at least three times in PBS. Primary antibody anti-YL1/2 (1:1000, BioRad) is diluted in PBS-2% BSA (1:1000), incubated with cell 1 hour and incubated with cell for 1 hour. Then the solution is replaced by FITC-conjugated secondary antibodies (Alexa Fluor, dilution 1/500) for 1 hour. Lastly, cells are then incubated with DAPI (1:1000, Sigma-Aldrich) to visualize cells body. The two stainings (YL1/2 and DAPI) enable to label the microtubule cytoskeleton and the soma respectively to locate the neurites and the cells body. Finally, cells were washed again in PBS, mounted in Mowiol (Sigma-Aldrich) mounting medium between two coverslips. Optical and immunofluorescence images were collected using either an Olympus BX51 and Zeiss AxioImager M2 microscope.

3. Results

3.1. Temperature dependent PL of nanocrystals

Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals (with doping concentrations of 0.5 mol.% Er³⁺ and 10 mol.% Yb³⁺) were prepared by a microwave-assisted hydrothermal method as reported in [36]. Obtained nanocrystals, imaged by low-temperature transmission electron microscopy (TEM, **Figure 1a**), present an average size of 40 nm and a good polydispersity (\pm 10 nm), obtained by the size analysis on more than one hundred nanocrystals. The PL and PL excitation properties of powdered nanocrystals were recorded in the visible range and are presented on **Figure 1b**. The main excitation peak is situated at 380 nm, corresponding to the ⁴I_{15/2} \rightarrow ⁴G_{11/2} transition of Er³⁺. There are two intense emission peaks upon a 380 nm excitation, situated at 522 nm and 544 nm, corresponding to the ²H_{11/2} \rightarrow ⁴I_{15/2} and ⁴S_{3/2} \rightarrow ⁴I_{15/2} transitions of Er³⁺, respectively. A small PL peak is observed around 660 nm, corresponding to the ⁴F_{9/2} \rightarrow ⁴I_{15/2} transition of Er³⁺. This weak intensity attests from a low population rate of the emitting level (⁴F_{9/2}). As this level is populated either from non-radiative de-excitations from the ⁴S_{3/2} level or through Er³⁺-Er³⁺ cross-relaxation mechanisms, the latter being very unlikely at this low Er³⁺ concentration (0.5 mol%) [37,38], it shows that non-radiative mechanisms are not dominating in the considered nanocrystals. Under a 1064-nm femto-second excitation, these nanocrystals exhibit Second Harmonic signal (**Figure 1c**).




Figure 1. (a) Low-temperature TEM image of Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals. The inset shows the powder X-ray diffraction pattern associated with these nanocrystals. (b) Room-temperature PL and PL excitation spectra of Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals. The PL spectrum was recorded under a 380 nm excitation, whereas the PL excitation was recorded while monitoring the emission at 545 nm spectrum. (c) Second Harmonic Scattering signal from Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals in ethylene glycol under a 1064-nm excitation.

Using a micro-PL setup, the emission spectrum of Yb³⁺,Er³⁺-doped α-La(IO₃)₃ nanocrystals dried on a silicon substrate was recorded in the 500 to 560 nm range. Because of the much better spectral resolution of this setup, compared to the one of the fluorimeter, the sub-structure of the emission peaks, whose maximal intensity lies at 522 nm and 544 nm, can be visualized (**Figure 2a**), corresponding to the transitions from the multiple Stark sublevels of the ²H_{11/2} and ⁴S_{3/2} levels to the Stark sublevels of the ⁴I_{5/2} ground state of Er³⁺.

Thanks to a temperature stage (Linkam THMS600) coupled to the micro-PL setup, PL spectra were recorded at different temperatures (varying between 25 and 70 °C) after a 10 min thermalisation at each temperature. When temperature increases, the intensity of the two emission peaks at 522 nm and at 544 nm, respectively labelled I₅₂₂ and I₅₄₄, tends to equalize, as the two emitting levels, ²H_{11/2} and ⁴S_{3/2}, are in close proximity in energy and their population is ruled by Boltzmann equation [39,40]:

$$\frac{I_{522}}{I_{544}} = LIR = A \exp\left(-\frac{\Delta E}{k_B T}\right) \quad (3)$$


with A is a constant depending on the host matrix, ΔE the energy difference between the ⁴S_{3/2} and ²H_{11/2} levels, k_B the Boltzmann constant, and T the absolute temperature. The evolution of LIR , plotted in a logarithmic scale, as a function of $1/T$, follows a linear evolution in agreement with Boltzmann theory (**Figure 2b**). The slope allows for the calculation of $\Delta E \sim 730 \text{ cm}^{-1}$. This value can be compared to the value calculated from the PL spectrum, taking into account the barycentre of both peaks at 522 and 544 nm, situated respectively at 19160 cm^{-1} and 18410 cm^{-1} , which gives a gap between the ²H_{11/2} and ⁴S_{3/2} levels of 750 cm^{-1} , in good agreement with the ΔE value obtained from the nanothermometry measurements.

In order to compare the thermal sensitivity of these Yb³⁺,Er³⁺-doped α-La(IO₃)₃ nanocrystals with other luminescent nanoprobes, their relative thermal sensitivity S_r was calculated from **Eq. 1**. As the $\partial LIR/\partial T$ term is the derivative of the function described in **Eq. 3**, S_r can be further evaluated by [41,42]:

$$S_r = \frac{\Delta E}{k_B T^2} \quad (4)$$

At 25 °C, the S_r value for our system is $1.2 \% \text{ K}^{-1}$, which is comparable the values obtained in other Yb³⁺,Er³⁺ doped oxide or fluoride nanocrystals [15,43]. Under those experimental conditions, the temperature uncertainty, δT , is evaluated at $\sim 0.5 \text{ }^\circ\text{C}$.

The same experiment was repeated on nanocrystals dispersed in two different liquid environments: in ethylene glycol, which is known to stabilize these nanocrystals [33] and in water at pH 7 for further prospects in biology. Once the nanocrystals have sedimented onto the silicon substrate, their emission was recorded as a function of temperature and the LIR value can be studied as a function of temperature (**Figure 2b**). Like in powder, the linear evolution of LIR with $1/T$ attests from a Boltzmann distribution of the two excited state levels. One can note that the value of LIR varies according to the environment, which can be explained by a change of thermal conductivity at the nanocrystals interface. Recent works report the key role of the environment and interfaces of nanothermometry: A.R.N. Bastos *et al.* evidence a significant variation of S_r values for nanocrystals dispersed in water and in D₂O [44]. It should be specified that all our experiments were performed using a micro-PL set-up involving high excitation power density ($\sim 100 \text{ kW cm}^{-2}$) at 488 nm, where heating of the liquid medium is very likely. In order to assess the reliability of these nanocrystals as nanothermometers, further work would be required, measuring PL dependence according to on the environment (pH, nature of the tissues, etc) and the operating conditions (excitation power densities, excitation wavelength, etc) [45].



181
182
183

Figure 2. (a) Normalized PL spectrum of Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals dried on a silicon wafer, normalized at 544 nm, as a function of temperature ($\lambda_{exc} = 488$ nm, 100 kW.cm⁻²). (b) Evolution of the LIR = I₅₂₂/I₅₄₄ ratio with temperature, for Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals in different media.

184

3.2. Impact of the nanocrystals on cultured neurons.

185
186
187
188
189
190
191
192

As previously described [46], cortical and hippocampal neurons are extracted from mouse embryos (E16.5) (detailed in *Material and Methods*). Cells are plated on glass coverslip previously coated with cell adhesive polymers (poly-L-lysine at 1mg/ml), and then incubated at 37°C and 5% CO₂. Then nanocrystals are loaded several days of culture (DIV4 or 5) and few hours before the recordings. Depending on the incubation time, nanocrystals will penetrate the plasmid membrane or remain adsorbed on neurons membranes. For each condition, Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals are dispersed in water, at high concentration (0.1 mg/mL) using ultrasonication (stock solution). Then, few amounts of the nanocrystal suspension (5-50 μ l) are added to the cell medium under constant agitation during 10 min. Finally, cells are incubated before the observations to recover.


193
194
195
196
197
198

We adjusted the concentration of nanocrystal, ranging from 0.01 to 0.001 mg/ml. High concentration 0.1 mg/mL appears lethal for neurons, while low concentration reduces significantly the probability to attach nanocrystals on neurites. The final concentration was fixed at 0.01 mg/mL, which enables to keep healthy neurons and several sensing sites where nanocrystals and neurites are colocalized. Most of the large aggregates are removed during media changes (**Figure 3a**). The remaining large ones provide controls for measuring PL of the nanocrystals, while smaller nanocrystals are rather internalized or attached on the membranes of neurons (**Figure 3a-d**).

199
200
201
202
203
204

Figure 3 illustrates the typical shape of 5 days old neurons incubated 3-4 hours with nanocrystals. The neurons appear healthy despite the presence of nanocrystals, with the expected cell density, number of neurites per cell and neurite length for this maturation stage. The spreading of neurites over all the substrate indicates also the healthy state of cells. No neurite bundles neither large soma aggregates are observed which are first signs of stress or cytotoxic effects within *in-vitro* neural networks. Also, there is no sign of membrane disruption.

205



206

207
208
209
210
211

Figure 3. Bright field and fluorescent micrographs of hippocampal neurons (after five days in culture) loaded with Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals (concentration of 0.01 mg/mL). Neurons are stained with DAPI (blue), YL-1/2-FITC (green) and synapsin-TRITC (red) to locate the soma, neurites and synapses. FITC fluorescent signals of Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals and microtubules are superimposed ($\lambda_{exc}=488$ nm, $\lambda_{em},= 525 \pm 15$ nm, 6 mW). We can clearly distinguish the large clusters of nanocrystals by comparing optical and fluorescent images (a-b), as well as smaller nanocrystals along the somas (c) and the neurites (d) as highlighted with the arrows. Scales bares (a-b) 30 μ m, (c-d) 10 μ m.

212


3.2. Temperature dependence of the nanocrystals PL in neuronal environment.

We assess here the ability to monitor the PL of the nanocrystals in standard conditions of cells observation using an epifluorescent Olympus BX51 microscope, equipped with FITC-filter cube (excitation 480 nm +/- 20nm; dichroic mirror 505LP; emission filter 535 +/- 25nm). Nanocrystals (0.01 mg/ml) were seeded on bare coverslips (batch #1) and on neurons cultured five days on glass coverslip (batch #2). To record the PL signals, we used high magnification fluorescent objective (x 60) immersed in the suspension containing the nanocrystals and the neurons. The temperature of the solution is varied from room temperature 20°C to 40°C or 45°C, with and without neurons respectively, by using the same temperature stage (Linkam THMS600) than the one used on the micro-PL setup. Samples are maintained at the desired temperature for 5 min before the measurement. Emitted photons are collected during 50 ms with an sCMOS Camera (Andor Zhyla 5.5) for each temperature steps, while keeping constant all other parameters such the incident illumination (6 mW), the grey scale, or the dynamic range (16 bits). The total intensities emitted from the nanocrystals are then extracted with *imageJ* software.

PL of the Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals is clearly observed on the optical micrograph as illustrated within **Figure 3**. The transmitted wavelengths of the FITC cube ranges from 510 and 550 nm (>80%) with a maximum at 525 nm (95%), and enables to collect the main emission spectra of the nanocrystals with two main emission peaks at 522 and 544 nm (**Figure 1**). Large aggregates identified in dark field (dark clusters within **Figure 3a**) correlated with fluorescent cluster on FITC-micrograph, as the one highlighted by the arrows to give an example (**Figure 3b**). Also, smaller crystals that are barely seen in visible, appear clearly in the FITC range, characterized by small fluorescent dots along the neurites and the somas that can be distinguished from the microtubule filaments stained with YL1/2-FITC markers (closer views, **Figures 3c-d**).

Regarding the PL dependence with temperature, we observe a change of PL intensity when increasing the temperature from 20°C to 45°C. This change is reversible when decreasing the temperature. Without cells (red dots, **Figure 4**) in liquid, the nanocrystal PL exhibits a rather linear dependence with the temperature, varying of about 15% from room temperature to 45°C with a maximal variation of the PL intensity around 0.5 % K⁻¹ (given by the slope of the red curve, **Figure 4**). This value is close to the variation measured in micro-PL spectroscopy: $\partial LIR/\partial T \sim 0.65$ % K⁻¹ (**Figure 2**). The slightly lower sensitivity obtained with the epifluorescence microscope is expected as we cannot distinguish the contribution of the two PL peaks of the nanocrystals, but only the resulting contribution of both. The contribution of the first PL peak (522 nm) is the most sensitive to temperature change and corresponds the maximum of the transmission of the FITC filter. But its variations may be hidden by the second peak which exhibits higher PL signals (almost twice).

In the presence of cells, the PL intensity still decreases when increasing the temperature and the observed variations remain in the expected ranges of intensity, with a maximum sensitivity around 37°C. But the recorded variations are weaker and the dependence with the temperature is unclear around 25°C. At the wavelengths of interest (in the range 488-550 nm), neurons are not optically transparent, they can either absorb or scatter the optical signals. In particular, the scattering coefficient is high in the visible range [47] and could impact the collected intensity in a significant manner, that may explain the non-linear dependence with the temperatures that we observed. Additionally, cells could act as a thermal barrier between the regulated substrate and the nanocrystals, making slightly less efficient the thermal coupling between the bath and the temperature stage. In both cases, such effects may contribute to increase the non-linearities on the recorded PL signals and make more difficult the extraction of the PL signal of interest around room temperatures. These possible artefacts can be overcome using the PL intensity ratio over the absolute PL intensity variation that lies in more sensitive to temperature change.



256 **Figure 4.** Temperature dependence of the PL of $\text{Yb}^{3+}, \text{Er}^{3+}$ -doped $\alpha\text{-La}(\text{IO}_3)_3$ nanocrystals monitored with an epifluorescent
 257 microscope (Olympus BX51), without and with neurons (red and green/blue dots respectively). The intensity per pixel is collected
 258 with $\times 60$ water-immersion objective, as function the substrate temperature adjusted with a Linkam controller. FITC-filters cube
 259 enables to select the incident illumination (Xenon lamp) at the nanocrystal excitation wavelength $\lambda_{\text{exc}} = 488 \pm 20$ nm and to collect
 260 their emission around $\lambda_{\text{em}} = 535 \pm 25$ nm. High pass dichroic mirror at $\lambda_{\text{dic}} = 510$ nm suppresses the contribution of the incident
 261 photons on the recorded signals. Signal is monitored with sCMOS Andor Zhyla 5.5 camera at constant exposure time 50 ms.

262 To enhance the thermal sensitivity and repeatability we could isolate the contribution of the two nanocrystals PL
 263 peaks at 522 and 544 nm. This could be obtained by adding dichroic mirrors on a second emission line to select the
 264 first and/or the second peak only. Its contribution can then be isolated and subtracted from the first emission line to
 265 improve the signal on noise ratio.

266 As an alternative, we assessed the possibility to measure temperature of a neuronal network with the micro-PL setup
 267 (previously described). An aqueous solution of $\text{Yb}^{3+}, \text{Er}^{3+}$ -doped $\alpha\text{-La}(\text{IO}_3)_3$ nanocrystals ($c = 0.1$ mg/mL) was dispersed
 268 onto neuronal network (**Figure 5a**). Once the nanocrystals have sedimented, the excitation beam is focused onto a
 269 small nanocrystal aggregate situated onto a dendrite (circled in black in **Figure 5a**) in order to record the PL spectra at
 270 different temperatures in the physiological range. The PL signal of small aggregates is easily detectable despite the
 271 increase of luminescence background, attributed to the microscope cover slide. In agreement with the measurements
 272 made using the conventional microscope, the overall PL intensity decreases with the temperature increase. The *LIR*
 273 varies linearly with temperature, in a similar manner as for the nanocrystals in water (**Figure 5b**), in agreement with
 274 previous experiments using Quantum Dots as thermal sensors [7]; however, the overall accuracy is decreased due to
 275 the presence of a background signal due to the glass coverslip, leading to a temperature uncertainty, δT of 2 °C. This
 276 value could be improved by using a different sample container.




Figure 5. (a) Optical image of $\text{Yb}^{3+},\text{Er}^{3+}$ -doped $\alpha\text{-La}(\text{IO}_3)_3$ nanocrystals loaded onto neuronal cells with a concentration of 0.1 mg/mL, in water (Scale bar: 12 μm). (b) Evolution of LIR of the nanocrystals adsorbed on neurons as a function of temperature.

4. Discussion

In this work, we demonstrate the possibility to use two different optical microscopy techniques to get a local temperature measurement within cultured neurons networks: fluorescent-based imaging and micro-PL spectroscopy. This includes possible observations with epi-fluorescent microscope mounted with conventional FITC-filter, which makes the technology ready to use in cell culture laboratory. Fluorescence-based imaging is a promising strategy for cell thermometry because it can be non-invasive and can have a high spatial resolution (diffraction limited level, around 200 nm) on a wide field of view (mm^2). When associated with highly sensitive luminescent thermometers, it could enable to follow tiny temperature change along single neuron and large network. As luminescent nanoprobe, we investigate here $\text{Yb}^{3+},\text{Er}^{3+}$ -doped $\text{La}(\text{IO}_3)_3$. Many rare-earth-doped nanocrystals are known as Boltzmann-based nanothermometers, whose temperature variation is monitored by following the PL intensity ratio of two emission lines of Er^{3+} . Though developed a few decades again, many challenges still remain for their use in biology, including the control of the nanocrystal size, morphology, stability, optical efficiency and thermal sensitivity.

Under a conventional microscope, the temperature-dependent PL intensity of the nanoprobe deposited on a glass substrate follows a typical Boltzmann distribution (Figure 4, red data), which is as expected for temperature-sensitive fluorescent materials. Nonradiative processes increases with the temperature, while radiative transition rate remains constant which results in a decrease of the emission from the excited state [48,49]. Inversely, the PL intensity increases when reducing the temperature. As a result, the chronograms of PL intensity provide a direct, local and fast temperature measurement (between 0.2 s and 2 ms depending on the PL intensity) over millimeter scale network area. In comparison, quantum dots based on red-shift emission require multiple acquisition of the PL spectrum which are usually too long (typ. 0.5 s – 1 s) and limited to one specific location per spectrum, preventing larger scale thermal mapping [50].

We demonstrated here that $\text{Yb}^{3+},\text{Er}^{3+}$ -doped $\alpha\text{-La}(\text{IO}_3)_3$ nanocrystals can either enter into neuronal cells or remain adsorbed on cell membrane, enabling dual extra and intracellular measurements over physiological temperature range 20–40°C with a maximum sensitivity at 37°C. The variation of PL intensity over temperature that we reached (0.5 % K^{-1}) is enough to capture thermal difference of few degrees. These thermal gradients are expected within cell compartments [51,52] or during neurostimulation [53,54] to give few examples. However further enhancements would be required to reveal weaker changes (10^{-4} – 10^{-5} K) associated to cell activity [2,55].

Although there are numerous papers reporting the thermal performances of nanothermometers [15], fewer of them deal with *in-vitro* experiments [56]. From the ratiometric approach on the micro-PL setup, we measured a relative thermal sensitive S_r of $\text{Yb}^{3+},\text{Er}^{3+}$ -doped $\alpha\text{-La}(\text{IO}_3)_3$ nanocrystals of 1.2 % K^{-1} in neuronal cells, higher than previously reported values for other inorganic materials, including Green Fluorescent Proteins (GFP) [57], Nd^{3+} -doped nanocrystals (0.1 % K^{-1}) [18] or quantum dots [58] (Table 1). This value is comparable to that of other Er^{3+} -doped materials [59,60] or hybrid materials [61], as a consequence of the energy gap between the two emitting levels of Er^{3+} ($^4\text{S}_{3/2}$ and $^2\text{H}_{11/2}$) whose splitting does not differ much with the host matrix. More complex systems, such as the

association of rare-earth doped nanocrystals with chromophores presenting Triplet-Triplet Annihilation mechanism, can provide higher sensitivity (7 % K⁻¹) and high thermal resolution (0.1 K) [62].

Table 1. Comparison of relative thermal sensitivity (S_r) and thermal resolution (δT) of different fluorescent thermal sensors used in cells.

Samples, ref.	S_r (% K ⁻¹)	δT (K)	Type of cells
La(IO ₃) ₃ : Er ³⁺ , Yb ³⁺ [†]	1.2	< 1	Cultured neurons
Fluorescent proteins [57,63]	0.4	0.5	Cultured HeLa cells
NaYF ₄ :Nd ³⁺ [18]	0.1	< 1	HeLa cancer cells
Quantum dots [58]	1.0	< 1	Cancer cells
NaYF ₄ :Er ³⁺ , Yb ³⁺ [60]	1.6	< 1	HeLa cancer cells
Luminescent nanogels [64]	NP	0.3-0.5	Living COS7 cells

[†] this work. NP: not provided

Scattering and absorption may be non-negligible for neuronal sensing especially when the number of collected photons are low, as it could impact both the number of collected photons or cell metabolism. Although this effect should be less within *in-vitro* cultured neurons than for *in-vivo* applications, it could impact the measurements and the temperature dependence of the collected PL intensity. Future works should investigate how absorption and scattering by neurons could introduce significant artefacts on the measurements, as well as the stability of the measurement depending on the position of the emitters within the cell. Extraction of the PL depth-profile within the cellular layer might be a way to perform such analysis that would be required for *in-vivo* and *in-vitro* applications.

In addition, future work will investigate the gain that could be reached using a conventional microscope with dedicated set of emission/excitation filters to capture separately the emission of the two excited states at 525 nm and at 542 nm, as using the PL intensity ratio over the absolute PL intensity variation lies in more sensitive to temperature change. Indeed, it allows to get rid of the fluctuations of the experimental conditions (excitation beam power, mechanical drift, etc) and thus reducing possible measurement artefacts.

For all these reasons, Yb³⁺,Er³⁺-doped La(IO₃)₃ nanocrystals developed here appears as suitable candidates for contactless (luminescent) thermometers. It is worth noting that in this work, Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals were excited at 488 nm, i.e. directly in an excited level of Er³⁺. However, to envision future experiments, including *in-vivo* experiments, which require an excitation in a transparency window of the biological tissue (i.e. in the near infra-red), it will be possible to excite these nanocrystals at 980 nm, i.e. in the Yb³⁺ ions, which already prove to efficiently transfer their energy to Er³⁺ via up-conversion processes.

5. Conclusions

Amongst the different nanoprobe that are developed for nanomedicine applications, one of the most desired features is their versatility, which allows for their use under different conditions and/or environment and for different purposes (e.g. diagnostics, therapy). Yb³⁺,Er³⁺-doped α -La(IO₃)₃ nanocrystals already exhibit two different functionalities: the Second Harmonic Generation and the photoluminescence, which are rarely obtained at the nanoscale. These properties enable to visualize them using conventional fluorescence microscopes, commonly available in biology and also with non-linear microscopes along for in-depth imaging. In addition to this dual-light emission, we show here that these nanocrystals, exhibiting a relative thermal sensitivity of 1.2 % K⁻¹ and a PL intensity variation with temperature of 0.5 % K⁻¹, appear as promising candidates for *in-vitro* bio-imaging and thermal sensing of neuronal cells. Indeed, they combine both a high spatial resolution and large field of view and enable measurements over physiological temperature range (20–40°C) with epi-fluorescent microscopy which makes the technique ready to use in cell culture laboratory.

Author Contributions: All authors contributed to the experimental work presented in this paper and have read and agreed to the published version of the manuscript.

Funding: This research was funded by the French-Swiss Interreg V (Project OncoNanoscreen) and by the French Research Agency (ANR Nanomesh, grant number: ANR-18-CE42-0003)

359
360
361
362
363
364

Acknowledgments: G.D. acknowledges Y. Mugnier and R. Le Dantec from Symme Laboratory, Annecy, France for the Second Harmonic characterization.

Conflicts of Interest: The authors declare no conflict of interest.

References

1. McCabe, K.; Hernandez, M. Molecular Thermometry, *Pediatric Research* **2010**, *67*, 469-475
2. Baffou, G.; Rigneault, H.; Marguet, D.; Jullien, L. A critique of methods for temperature imaging in single cells. *Nature methods*, **2014**, *11*(9), 899-901
3. Ramires, M.L.V.; Nieto de Castro, C.A. Standard Reference Data for the Thermal Conductivity of Water. *J. Physical and Chemical Reference Data* **1995**, *24*, 1377
4. Bai, T., & Gu, N. Micro/nanoscale thermometry for cellular thermal sensing. *Small*, **2016**, *12*(34), 4590-4610
5. Brites, C.D.S.; Lima, P.P.; Silva, N.J.O.; Millan, A.; Amaral, V.S.; Palacio, F.; Carlos, L.D. "Thermometry at the nanoscale. *Nanoscale*, **2012**, *4*, 4799-4829
6. Simpson, D. A.; Morrisroe, E.; McCoe, J. M.; Lombard, A. H.; Mendis, D. C.; Treussart, F.; Hall, L.T.; Petrou, S.; Hollenberg, L. C.; Non-neurotoxic nanodiamond probes for intraneuronal temperature mapping. *ACS nano* **2017**, *11*(12), 12077-12086.
7. Tanimoto, R., Hiraiwa, T., Nakai, Y., Shindo, Y., Oka, K., Hiroi, N., & Funahashi, A. Detection of temperature difference in neuronal cells. *Scientific reports*, **2016**, *6*, 22071
8. Jaque, D.; Vetrone, F. Luminescence nanothermometry *Nanoscale*, **2012**, *4*, 4301-4326
9. Donner, J.S.; Thompson, S.A.; Kreuzer, M.P.; Baffou, G.; Quidant, R. Mapping intracellular temperature using green fluorescent protein. *Nano letters*, **2012**, *12*(4), 2107-2111
10. Zhang, L.; Wang, E. Metal nanoclusters: new fluorescent probes for sensors and bioimaging. *Nano Today*, **2014**, *9*(1), 132-157
11. Okabe, K.; Inada, N.; Gota, C.; Harada, Y.; Funatsu, T.; Uchiyama, S. Intracellular temperature mapping with a fluorescent polymeric thermometer and fluorescence lifetime imaging microscopy. *Nature communications*, **2012**, *3*(1), 1-9
12. Yang, J. M., Yang, H., Lin, L. Quantum dot nano thermometers reveal heterogeneous local thermogenesis in living cells. *ACS nano* **2011**, *5*(6), 5067-5071
13. Gan, Z.; Hao, Y.; Shan, Y. Temperature-Dependent Dual Emission from Sucrose-Derived Carbon Nanodots: A Ratiometric Fluorescent Thermometer. *Chem. Nano. Mat.* **2016**, *2*, 171-175
14. Yuan, S.; Zhang, X.; Cao, W.; Sheng, Y.; Liu, C.; Yu, L.; Di, Y.; Chen, Z.; Dong, L.; Gan, Z. Fluorescence enhancement of perovskite nanocrystals using photonic crystals. *J. Mater. Chem. C*, **2021**, *9*, 908-915
15. Brites, C. D. S.; Balabhadra, S.; Carlos, L.D. Lanthanide-Based Thermometers: At the Cutting-Edge of Luminescence Thermometry. *Adv. Optical Mater.*, **2018**, 1801239
16. Zhou, J.; del Rosal, B.; Jaque, D.; Uchiyama, S.; Jin, D. Advances and challenges for fluorescence nanothermometry. *Nature Methods* **2020**, *17*, 967-980
17. Villa, I.; Vedda, A.; Cantarelli, I. X.; Pedroni, M.; Piccinelli, F.; Bettinelli, M.; Speghini, A.; Quintanilla, M.; Vetrone, F.; Rocha, U.; Jacinto, C.; Carrasco, E.; Rodriguez, F.; Juarranz, A.; del Rosal, B.; Ortgies, D.; Gonzalez, P.; Sole Garcia, J.; Jaque, D. 1.3 μm Emitting SrF₂:Nd³⁺ Nanoparticles for High Contrast In Vivo Imaging in the Second Biological Window. *Nano Res.* **2015**, *8*(2), 649-665
18. Rocha, U.; Jacinto da Silva, C.; Ferreira Silva, W.; Guedes, I.; Benayas, A.; Martinez Maestro, L.; Acosta Elias, M.; Bovero, E.; van Veggel, F. C. J. M.; Garcia Sole, J.A.; Jaque D. Subtissue Thermal Sensing Based on Neodymium-Doped LaF₃ Nanoparticles *ACS Nano* **2013**, *7*(2), 1188-1199
19. Chen, G.; Ohulchanskyy, T.Y.; Liu, S.; Law, W.-C.; Wu, F.; Swihart, M. T.; Agren, H.; Prasad P.N. Core/Shell NaGdF₄:Nd³⁺/NaGdF₄ Nanocrystals with Efficient Near-Infrared to Near-Infrared Downconversion Photoluminescence for Bioimaging Applications" *ACS Nano* **2012**, *6*(4), 2969-2977
20. Yu, Z.F.; Shi, J.P.; Li, J.L.; Li, P.H.; Zhang, H.W. Luminescence enhancement of CaF₂:Nd³⁺ nanoparticles in the second near-infrared window for in vivo imaging through Y³⁺ doping *J. Mater. Chem. B*, **2018**, *6*, 1238
21. Feng, Y.; Xiao, Q.; Zhang, Y.; Li, F.; Li, Y.; Li, C.; Wang, Q.; Shi, L.; Lin H. Neodymium-doped NaHoF₄ nanoparticles as near-infrared luminescent/T₂-weighted MR dual-modal imaging agents in vivo *J. Mater. Chem. B*, **2017**, *5*, 504
22. Dantelle, G.; Matulionyte, M.; Testemale, D.; Cantarano, A.; Ibanez, A.; Vetrone, F. Nd³⁺-doped Gd₃Sc₂Al₃O₁₂ nanocrystals: towards efficient nanoprobe for temperature sensing" *Physical Chemistry Chemical Physics* **2019**, *21*, 11132-11141
23. Del Rosal, B.; Pérez-Delgado, A.; Misiak, M.; Bednarkiewicz, A.; Vanetsev, A.S.; Orlovskii, Y.; Jovanović, D.J.; Dramićanin, M.D.; Rocha, U.; Kumar, K.U.; Jacinto, C.; Navarro, E.; Rodríguez, E.M.; Pedroni, M.; Speghini, A.; Hirata, G.A.; Martín, I.R.; Jaque, D. Neodymium-doped nanoparticles for infrared fluorescence bioimaging: The role of the host. *J. Appl. Physics* **2015**, *118*, 143104.
24. Hemmer, E.; Benayas, A.; Légaré, F.; Vetrone, F. Exploiting the Biological Windows: Current Perspectives on Fluorescent Bioprobes Emitting above 1000 nm. *Nanoscale Horiz.* **2016**, *1*, 168-184.

-
25. Cantarano, A.; Yao, J.; Matulionyte, M.; Lifante, J.; Benayas, A.; Ortgies, D.; Vetrone, F.; Ibanez, A.; Gérardin, C.; Jaque, D.; Dantelle G. Autofluorescence-free in vivo imaging using polymer-stabilized Nd³⁺-doped YAG nanocrystals. *ACS Applied Materials & Interfaces* **2020**, *12*(46), 51273-51284
26. Suta, M.; Antić, Ž.; Đorđević, V.; Kuzman, S.; Dramićanin, M.D.; Meijerink, A. Making Nd³⁺ a Sensitive Luminescent Thermometer for Physiological Temperatures—An Account of Pitfalls in Boltzmann Thermometry *Nanomaterials* **2020**, *10*(3), 543
27. Skripka, A.; Morinvil, A.; Matulionyte, M.; Cheng, T.; Vetrone, F. Advancing Neodymium Single-Band Nanothermometry *Nanoscale* **2019**, *11*, 11322-11330.
28. Huang, P.; Zheng, W.; Tu, D.; Shang, X.; Zhang, M.; Li, R.; Xu, J.; Liu, Y.; Chen, X. Unraveling the Electronic Structures of Neodymium in LiLuF₄ Nanocrystals for Ratiometric Temperature Sensing *Adv. Sci.* **2019**, *6*, 1802282.
29. Rocha, U.; Jacinto da Silva, C.; Ferreira Silva, W.; Guedes, I.; Benayas, A.; Martinez Maestro, L.; Acosta Elias, M.; Bovero, E.; van Veggel, F.C.J.M.; Garcia Sole, J.A.; Jaque, D. Subtissue Thermal Sensing Based on Neodymium-Doped LaF₃ Nanoparticles *ACS Nano* **2013**, *7*(2), 1188-1199.
30. Balabhadra, S.; Debasu, M.L.; Brites, C. D. S.; Ferreira, R.A.S.; Carlos, L.D. Upconverting Nanoparticles Working As Primary Thermometers In Different Media *J. Phys. Chem. C* **2017**, *121*, 13962-13968
31. Nigoghossian, K.; Messaddeq, Y.; Boudreau, D.; Ribeiro, S.J.L. UV and Temperature-Sensing Based on NaGdF₄:Yb³⁺:Er³⁺@SiO₂-Eu(tta)₃ *ACS Omega* **2017**, *2*, 2065-2071
32. Suta, M.; Meijerink, A. A Theoretical Framework for Ratiometric Single Ion Luminescent Thermometers—Thermodynamic and Kinetic Guidelines for Optimized Performance *Adv. Theory Simul.* **2020**, *3*, 2000176
33. Regny, S.; Riporto, J.; Mugnier, Y.; Le Dantec, R.; Kodjikian, S.; Pairis, S.; Gautier-Luneau, I.; Dantelle, G. Microwave synthesis and up-conversion properties of SHG-active α-(La,Er)(IO₃)₃ nanocrystals *Inorganic Chemistry* **2019**, *58*(2), 1647-1654
34. Regny, S.; Ledrilet, K.; Riporto, J.; Gautier-Luneau, I.; Mugnier, Y.; Le Dantec, R.; Dantelle G. Dual-emitting Yb³⁺,Er³⁺-doped α-La(IO₃)₃ iodate nanocrystals: Up-Conversion Emission & Second Harmonic Generation *MRS Communications* **2019**, *9*(4), 1221-1226
35. Bonacina, L. Nonlinear Nanomedicine: Harmonic Nanoparticles toward Targeted Diagnosis and Therapy. *Mol. Pharmaceutics* **2013**, *10*, 783-792
36. Regny, S.; Suffren, Y.; Leynaud, O.; Gautier-Luneau, I.; Dantelle, G. Evidence of reaction intermediates in microwave-assisted synthesis of SHG-active α-La(IO₃)₃ *Crystal Engineering Comm.* **2020**, *22*, 2517-2525
37. Patra, A.; Friend, C.S.; Kapoor, R.; Prasad, P.N. Fluorescence Upconversion Properties of Er³⁺-Doped TiO₂ and BaTiO₃ Nanocrystallites *Chem. Mater.* **2003**, *15*, 3650-3655
38. Dantelle, G.; Mortier, M.; Patriarche, G.; Vivien, D. Er³⁺-doped PbF₂: Comparison between nanocrystals in glass-ceramics and bulk single crystals *J. Solid State Chem.* **2006**, *179*, 1995-2003
39. Aigouy, L.; Saïdi, E.; Lalouat, L.; Labéguerie-Egée, J.; Mortier, M.; Löw, P.; Bergaud, C. AC thermal imaging of a microwire with a fluorescent nanocrystal: Influence of the near field on the thermal contrast *J. Appl. Phys.* **2009** *106*, 074301
40. Vetrone, F.; Naccache, R.; Zamarron, A.; Juarranz de la Fuente, A.; Sanz-Rodriguez, F.; Martinez Maestro, L.; Martín Rodriguez E.; Jaque, D.; Garcia Sole, J.; Capobianco, J.A. Temperature Sensing Using Fluorescent Nanothermometers *ACS Nano* **2010**, *4*, 3254
41. Dong, B.; Liu, D. P.; Wang, X.J.; Yang, T.; Miao, S.M.; Li, C.R. Optical thermometry through infrared excited green upconversion emissions in Er³⁺-Yb³⁺ codoped Al₂O₃ *Appl. Phys. Lett.* **2007**, *90*, 181117
42. Rodrigues, E.M.; Gálico, D.A.; Mazali, I.O.; Sigoli, F.A. Self-supported films of poly(methylmethacrylate) (PMMA) containing TmIII-doped up-converting core@shell nanoparticles as high sensitivity temperature optical probe *Sensors and Actuators A* **2019**, *291*, 1-6
43. Lin, M.; Xie, L.; Wang, Z.; Richards, B.S.; Gao, G.; Zhong, J. Facile synthesis of mono-disperse sub-20 nm NaY(WO₄)₂:Er³⁺,Yb³⁺ upconversion nanoparticles: a new choice for nanothermometry. *J. Mater. Chem. C*, **2019**, *7*, 2971--2977
44. Bastos, A.R.N.; Brites, C.D.S.; Rojas-Gutierrez, P.A.; DeWolf, C.; Ferreira, R.A.S.; Capobianco, J.A.; Carlos, L.D. Thermal Properties of Lipid Bilayers Determined Using Upconversion Nanothermometry. *Adv. Funct. Mater.* **2019**, *29*, 1905474
45. Bednarkiewicz, A.; Marciniak, L.; Carlos, L.D.; Jaque, D. Standardizing luminescence nanothermometry for biomedical applications. *Nanoscale* **2020**, *12*, 14405-14421.
46. Veliev, F., Briançon-Marjollet, A., Bouchiat, V., Delacour, C. Impact of crystalline quality on neuronal affinity of pristine graphene. *Biomaterials*, **2016**, *86*, 33-41
47. Jacques, S. L. Optical properties of biological tissues: a review. *Physics in Medicine & Biology*, **2013**, *58*(11), R37.
48. Blasse, G.; Grabmaier, B.C. Luminescent Materials, Springer-Verlag, 1994.
49. Gan, Z.; Wu, X.; Zhang, J.; Zhu, X.; Chu, P.K. In Situ Thermal Imaging and Absolute Temperature Monitoring by Luminescent Diphenylalanine Nanotubes. *Biomacromolecules* **2013**, *14*, 2112-2116
50. Li, S.; Zhang, K.; Yang, J.-M.; Lin, L. & Yang, H. Single quantum dots as local temperature markers. *Nano letters* **2007**, *7*, 3102-3105
51. Okabe, K.; Inada, N.; Gota, C.; Harada, Y.; Funatsu, T.; Uchiyama, S. Intracellular temperature mapping with a fluorescent polymeric thermometer and fluorescence lifetime imaging microscopy. *Nat. Commun.* **2012**, *3*, 705.

-
52. Zohar, O.; Ikeda, M.; Shinagawa, H.; Inoue, H.; Nakamura, H.; Elbaum, D.; Alkon, D.L.; Yoshioka, T. Thermal Imaging of Receptor-Activated Heat Production in Single Cells. *Biophysical J.* **1989**, *74*, 82–89
53. Moreau, D.; Lefort, C.; Burke, R.; Leveque, P.; O'Connor, R.P. Rhodamine B as an optical thermometer in cells focally exposed to infrared laser light or nanosecond pulsed electric fields. *Biomed. Opt. Exp.* **2015**, 4105
54. Song, J.; Joshi, R.P.; Schoenbach, K. H. Synergistic effects of local temperature enhancements on cellular responses in the context of high-intensity, ultrashort electric pulses, *Medical & Biological Engineering & Computing*, **2011**, *49*, 713–718
55. Tasaki, I., Kusano, K., Byrne, P. Rapid mechanical and thermal changes in the garfish olfactory nerve associated with a propagated impulse. *Biophysical journal*, **1989**, *55(6)*, 1033-1040.
56. del Rosal, B.; Ximendes, E.; Rocha, U.; Jaque, D. In Vivo Luminescence Nanothermometry: from Materials to Applications. *Adv. Funct. Mater.* **2017**, *5*, 1600508
57. Donner, J.S.; Thompson, S.A.; Alonso-Ortega, C.; Morales, J.; Rico, L.G.; Santos, S.I.C.O.; Quidant, R. Imaging of Plasmonic Heating in a Living Organism. *ACS Nano* **2013**, *7*, 8666–8672
58. del Rosal, B.; Carrasco, E.; Ren, F.; Benayas, A.; Vetrone, F.; Sanz-Rodríguez, F.; Ma, F.; Juarranz, A.; Jaque, D. Infrared-Emitting QDs for Thermal Therapy with Real-Time Subcutaneous Temperature Feedback, *Adv. Funct. Mater.* **2016**, *26*, 6060–6068
59. Wu, Y.; Xu, S.; Xiao, Z.; Lai, F.; Huang, J.; Fu, J.; Ye, X.; You, W. A universal strategy to enhance the absolute sensitivity for temperature detection in bright Er³⁺/Yb³⁺ doped double perovskite Gd₂ZnTiO₆ phosphors. *Mater. Chem. Front.*, **2020**, *4*, 1182
60. Rodríguez-Sevilla, P.; Zhang, Y.; Haro-González, P.; Sanz-Rodríguez, F.; Jaque, F.; García Solé, J.; Liu, X.; Jaque, D. Thermal Scanning at the Cellular Level by an Optically Trapped Upconverting Fluorescent Particle. *Adv. Mater.* **2016**, *28*, 2421–2426
61. Kaczmarek, A.M.; Suta, M.; Rijckaert, H.; Abalymov, A.; Van Driessche, I.; Skirtach, A.G.; Meijerink, A.; Van Der Voort, P. Visible and NIR Upconverting Er³⁺–Yb³⁺ Luminescent Nanorattles and Other Hybrid PMO-Inorganic Structures for *In Vivo* Nanothermometry. *Adv. Funct. Mater.* **2020**, *30*, 2003101
62. Xu, M.; Zou, X.; Su, Q.; Yuan, W.; Cao, C.; Wang, Q.; Zhu, X.; Feng, W.; Li, F. Ratiometric nanothermometer in vivo based on triplet sensitized upconversion. *Nature Comm.* **2018**, *9*, 2698.
63. Nakano, M.; Arai, Y.; Kotera, I.; Okabe, K.; Kamei, Y.; Nagai, T. Genetically encoded ratiometric fluorescent thermometer with wide range and rapid response. *PLoS One*, **2017**, *12(2)*:e0172344.
64. Gota, C.; Okabe, K.; Funatsu, T.; Harada, Y.; Uchiyama, S. Hydrophilic Fluorescent Nanogel Thermometer for Intracellular Thermometry. *J. Am. Chem. Soc.* **2009**, *131*, *8*, 2766–2767