



**HAL**  
open science

## High-frequency transducer for MR-guided FUS

Spiros Kotopoulos, Han Wang, Sandy Cochran, Michiel Postema

► **To cite this version:**

Spiros Kotopoulos, Han Wang, Sandy Cochran, Michiel Postema. High-frequency transducer for MR-guided FUS. *Biomedical Engineering = Biomedizinische Technik*, 2012, 57 (Suppl. 1), pp.972. 10.1515/bmt-2012-4135 . hal-03193199

**HAL Id: hal-03193199**

**<https://hal.science/hal-03193199>**

Submitted on 11 Apr 2021

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# High-frequency transducer for MR-guided FUS

Spiros Kotopoulis, Department of Physics and Technology, University of Bergen, Bergen, Norway;

Han Wang, IMSaT, University of Dundee, Dundee, Scotland;

Sandy Cochran, IMSaT, University of Dundee, Dundee, Scotland;

Michiel Postema, Department of Physics and Technology, University of Bergen, Bergen, Norway; and Carnegie Physics Laboratory, School of Engineering, Physics and Mathematics, University of Dundee, Scotland.

e-Mail: Michiel.Postema@ift.uib.no

## Introduction

High-intensity focused ultrasound is finding increasing therapeutic use. However, the frequencies at which it operates are typically limited to below 5 MHz, preventing research into therapy with ultrahigh spatial precision. A reason for this is that the design and fabrication of high-frequency biomedical ultrasound transducers to produce high intensities is an engineering challenge, especially for operating frequencies above 30 MHz, primarily because of the acoustic impedance mismatch and the high attenuation of water of 6dB/cm at 50 MHz leading to a low penetration depth. Commonly used materials such as PZT do not have the ability to produce a high enough intensity, due to de-poling or cracking. A potential application of high-intensity high-frequency ultrasound is non-invasive microsurgery.

## Methods

To overcome these problems, we used Y-360 Lithium Niobate (LiNbO<sub>3</sub>). This crystal has a high Curie temperature and is much more difficult to de-pole at high-power inputs. In addition, Y-360 LiNbO<sub>3</sub> has a resonant frequency of 3.3 MHz mm<sup>-1</sup>, thus allowing for much thicker elements at higher frequencies compared to PZT. A bowl transducer was manufactured using a total of 7 0.5-mm thick elements (4 hexagonal and 5 pentagonal) with a maximum width of 25 mm. The bowl had a curvature radius of 50 mm. The transducer was microballoon-backed in order to simplify the manufacturing process. The pentagonal elements were linked and driven by a 50-dB amplifier, whereas the hexagonal elements were linked and driven by a 55-dB amplifier. To test the available working frequency; single element transducers were manufactured with element thickness ranging from 500 µm to 200 µm, having working frequencies between 6.6 MHz and 20 MHz.

## Results

The multi-element focused transducer generated a modulated sound field with an enveloped wavelength of 550 kHz at a frequency of 6.6 MHz with a maximum peak-to-peak pressure of 24.3 MPa; equivalent to mechanical index of 4.7. The modulation could be varied by changing the phase of either the pentagonal or hexagonal linked elements. The microballoon-backed transducers had a 5% reduced acoustic output compared to the air-backed transducer. Single-element transducers produced a maximum peak-to-peak pressure of 14 MPa at 6.3 MHz in the acoustic focus at 12 mm. These transducers were capable of producing over 6 MPa and 4 MPa at the 3rd and 5th harmonics, respectively, corresponding to frequencies of 21 MHz and 35 MHz.

## Conclusion

We have established that manufacturing a high frequency, high intensity, multi-element, focused ultrasound transducer using LiNbO<sub>3</sub> is feasible. We have also shown it is possible to use the resonant frequency and up to the 5<sup>th</sup> harmonic to achieve higher working frequencies.