



HAL
open science

On the contact law within a poroelastic granular material

Nicolas Dauchez, Chourouk Hentati, Stéphane Job, Jean-Philippe Crété,
Mohamed Taktak, Mohamed Haddar

► **To cite this version:**

Nicolas Dauchez, Chourouk Hentati, Stéphane Job, Jean-Philippe Crété, Mohamed Taktak, et al.. On the contact law within a poroelastic granular material. Forum Acusticum, Dec 2020, Lyon, France. pp.619-620, 10.48465/fa.2020.0560 . hal-03240283

HAL Id: hal-03240283

<https://hal.science/hal-03240283>

Submitted on 12 Jun 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

ON THE CONTACT LAW WITHIN A POROELASTIC GRANULAR MATERIAL

Nicolas Dauchez¹ Chourouk Hentati^{1,3} Stéphane Job²
Jean-Philippe Crété² Mohamed Tacktak³ Mohamed Haddar³

¹ Sorbonne Université, Université de Technologie de Compiègne, Laboratoire Roberval, Compiègne Cedex, France

² Laboratoire Quartz, EA 7393, Institut Supérieur de Mécanique de Paris - Supméca, Saint-Ouen, France

³ National School of Engineers of Sfax, ENIS, LA2MP, Sfax University, Sfax, Tunisia
nicolas.dauchez@utc.fr

Keywords: Granular material, poroelastic material, Kelvin cell, contact stiffness, Hertz theory

1. INTRODUCTION

Poroelastic materials are widely used for acoustic treatments due to their efficient sound absorption. Granular materials present also interesting properties according to nonlinear wave propagation and attenuation and their ability to cope with the transmission of vibrations and mechanical shocks. In this work, we study the properties of poroelastic spheres made of polymer foam. The objective is to determine the contact stiffness between a poroelastic sphere and a rigid plane, the aim being to homogenize a poroelastic granular material for sound propagation.

2. MEASUREMENT

First, we present experimental results obtained with poroelastic half-spheres, made of the same materials (melamine foam) but with different radii R . They are subjected to a quasistatic strain imposed by the displacement δ of a rigid plane. The experimental set-up is presented in Fig. 1. The lens allows carefully setting the reference position at which the half sphere (Sample) starts to be in contact with the rigid plane (Still plate).




Figure 1. Experimental set-up for quasistatic measurement of the contact force of a melamine half sphere sample.

The results presented in Fig. 2 show two regimes: a nonlinear Hertzian regime at high strain corresponding to a displacement higher than 200 μm , which is radius-dependent, preceded by a regime common to all samples at low strain, which relies on the features of the surface.




Figure 2. Force as function of displacement for 3 half spheres of different radius.

3. SIMULATION

The limit between the two regimes is further studied by a numerical approach using a finite element model of a representative volume. The poroelastic grain is modeled by asymmetrical Kelvin cells within Abaqus software and takes into account the geometrical non-linearity during the deformation. Fig. 3 shows a detail of the numerical model at the contact location between the sphere and the plane.




Figure 3. Detail of the model at the contact point between the rigid plane and the half sphere modeled by Kelvin cells.

Fig. 4 shows that above a given displacement the Hertz law applies: $F = c ER^{1/2} \delta^{3/2}$, where E is the Young's modulus of the porous material and c the prefactor. Before this limit, no general tendency can be given since the results is function of the number of contact points between the ligaments and the plane.




Figure 4. Numerical results: force F as function of displacement δ .

More details are available in International Journal of Solids and Structures, “On the contact law of open-cell poro-granular materials” co-authored by C. Hentati, S. Job, J.-P. Cr  t  , M.Taktak, M. Haddar and N. Dauchez, 2020 <https://doi.org/10.1016/j.ijsolstr.2020.10.023>