

Use of Solid-State NMR Spectroscopy for the Characterization of Molecular Structure and Dynamics in Solid Polymer and Hybrid Electrolytes

Gabrielle Foran, Nina Verdier, David Lepage, Cédric Malveau, Nicolas Dupré, Mickaël Dollé

▶ To cite this version:

Gabrielle Foran, Nina Verdier, David Lepage, Cédric Malveau, Nicolas Dupré, et al.. Use of Solid-State NMR Spectroscopy for the Characterization of Molecular Structure and Dynamics in Solid Polymer and Hybrid Electrolytes. Polymers, 2021, 13 (8), pp.1207. 10.3390/polym13081207. hal-03266215

HAL Id: hal-03266215 https://hal.science/hal-03266215

Submitted on 20 Oct 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

² Use of Solid-State NMR Spectroscopy for the Characterization of ³ Molecular Structure and Dynamics in Solid Polymer and Hybrid ⁴ Electrolytes

Gabrielle Foran 1*, Nina Verdier 1, David Lepage 1, Cédric Malveau 1, Nicolas Dupré 2 and Mickaël Dollé 1.* 6 ¹ Université de Montréal, Département of Chemistry, 1375 Avenue Thérèse-Lavoie-Roux, Montréal, Québec, 7 8 Canada, H2V 0B3; mickael.dolle@umontreal.ca 9 ² Université de Nantes, CNRS, Institut des Matériaux Jean Rouxel, IMN, F-44000 Nantes, France; Nico-10 las.Dupre@cnrs-imn.fr 11 Correspondence: GF gabrielle.foran@umontreal.ca, MD mickael.dolle@umontreal.ca 12 Abstract: Solid-state NMR spectroscopy is an established experimental technique which 13 is used for the characterization of structural and dynamic properties of materials in their 14 native state. Many types of solid-state NMR experiments have been used to characterize 15 both lithium-based and sodium-based solid polymer and polymer-ceramic hybrid elec-16 trolyte materials. This review describes several solid-state NMR experiments that are 17 18 commonly employed in the analysis of these systems: pulse field gradient NMR, electrophoretic NMR, variable temperature T₁ relaxation, T₂ relaxation and linewidth analy-19 sis, exchange spectroscopy, cross polarization, Rotational Echo Double Resonance and 20 isotope enrichment. In this review, each technique is introduced with a short description 21 of the pulse sequence, and examples of experiments that have been performed in real 22 23 solid-state polymer and/or hybrid electrolyte systems are provided. The results and conclusions of these experiments are discussed to inform readers of the strengths and 24 weaknesses of each technique when applied to polymer and hybrid electrolyte systems. It 25 is anticipated that this review may be used to aid in the selection of solid-state NMR ex-26 periments for the analysis of these systems. 27 28 Keywords: Solid-state NMR spectroscopy, polymer electrolytes, hybrid electrolytes, ion 29 30 dynamics, electrochemistry 31

32 1. Introduction

33

34

35

36 37

38

39

40

41

42 43

1

5

Solid-state electrolytes for use in lithium batteries have been extensively studied as potential replacements to commercialized liquid electrolyte systems and have been touted as safer options as a result of being non-flammable, non-corrosive and non-volatile [1, 2]. There are three main classes of solid-state electrolytes: ceramic, polymer and ceramic-polymer hybrids [3]. Depending on their crystal structure and their composition, ceramic electrolytes tend to have good lithium ion conductivity (generally on the order of 10⁻⁴ S/cm at ambient temperature which is about one to two orders of magnitude lower than liquid electrolytes however, Kato et al. have prepared Li_{9.54}Si_{1.74}P_{1.44}S_{11.7}Cl_{0.3} electrolytes with conductivities that rival those of liquid electrolytes) [4–8], good thermal stability and adequate mechanical strength to impede dendrite formation [9, 10]. However, these materials are rigid and tend to cause significant interfacial resistance when in contact with solid electrodes [10]. Polymer electrolytes tend to have good mechanical stability, minimal interfacial resistance with solid electrolytes and are suitable for use in flexible battery applications [10]. However, lithium ion conductivity tends to be much lower in most polymer systems at room temperature than in liquid or some ceramic electrolytes (on the order of 10^{-8} to 10^{-6} S/cm at room temperature with lithium transference numbers below 0.5) and dendrite formation may still occur [11]. Hybrid electrolytes, which contain both solid polymers and ceramic particles, were created to capitalize on the advantages of both of these systems: they have higher lithium conductivities (on the order of 10^{-5} to 10^{-4} S/cm at ambient temperature) [12–15] than polymer electrolytes and are more flexible and interface compatible than ceramic electrolytes [16]. The ceramic particles can be either active or inert, where active ceramics are lithium conductors themselves and inert ceramics are non-conductive and are present to decrease crystallinity in the polymer electrolyte. However, lithium conductivities tend to remain lower than those of ceramic electrolytes as lithium ions must cross a complex series of polymer-ceramic interfaces for macroscopic-scale conductivity to occur [16]. In addition to complexities due to the presence of different electrolyte materials and the interfaces between them, microscale properties of the polymer electrolyte such as porosity and pore radii, along with the salt concentration and the possibility of concentration gradients can impact ionic conductivity in polymer and hybrid electrolytes [17, 18]. These complexities can make hybrid systems difficult to characterize. In addition to lithium-based all-solid-state batteries, similar systems have been developed using sodium as the mobile species. Solid-state sodium batteries, which have been in development since the 1980's, have been touted as being a more environmentally friendly technology relative to lithium-based batteries as a result of the higher abundancy and lower cost of sodium versus lithium [19, 20]. Sodium polymer electrolytes tend to have ion conductivities on the order of 10⁻⁷ to 10⁻⁶ S/cm at ambient temperature whereas sodium hybrid electrolytes tend to have conductivities between 10-6 to 10-5 S/cm at the same temperature [21–25]. Due to a growing interest in improving materials for flexible battery systems, this review will focus on the characterization of molecular structure and ion mobility in polymer and hybrid electrolyte systems. Many characterization techniques have been employed in the analysis of these materials with some of the most frequently used being: impedance spectroscopy, cyclic voltammetry, linear sweep voltammetry, differential scanning calorimetry, thermal gravimetric analysis, Raman spectroscopy, infrared spectroscopy, microscopy techniques, x-ray diffraction and both solution-state and solid-state nuclear magnetic resonance (NMR) spectroscopy [26–28]. This review will focus on the use of solid-state NMR spectroscopy to analyze molecular structure and dynamics in polymer and hybrid electrolytes. NMR spectroscopy can be performed on any nucleus where spin, a quantized nuclear property, is non-zero [29]. Therefore, in addition to being non-destructive, NMR spectroscopy is an isotopically sensitive method for investigating several nuclei that typically exist in solid electrolytes [28]. For example, nuclei such as 6Li, 7Li, 19F and 23Na are generally used to study dynamic processes whereas 1H and ¹³C tend to be used to characterize polymer structure [30, 31]. NMR is particularly suited to this task as it is sensitive to changes in local environments that occur on a microsecond to second timescale [30]. In addition to being sensitive to small changes in chemical environments, solid-state NMR has the added advantage of allowing materials in solid electrolyte systems to be analyzed in their native state.

44

45

46 47

48

49

50

51 52

53 54

55

56 57

58 59

60

61

62

63

64

65

66

67

68

69

70

71

72 73

74

75

76

77 78

79 80

81

82

83

84

85

86

87

88

89

90

91

92

93 94

95

96

97

The purpose of this document is to introduce a series of solid-state NMR spectroscopy experiments that are commonly used in the analysis of solid polymer and hybrid electrolytes to an audience who studies these systems but may not have an extensive familiarity with solid-state NMR spectroscopy. To this end, each technique discussed in this manuscript will be introduced starting with the pulse sequence, a description of important setup parameters and specific advantages and disadvantages of applying the technique to lithium- and sodium-based systems. Additionally, readers will be directed to Table S1 (supplementary information) where information on required equipment and experimental timescales are provided. Where applicable, comparisons between the NMR technique and common electrochemical experiments will be provided. The purpose of these comparisons is to inform the reader of differences in information that can be determined via NMR and electrochemical methods as well as the advantages and disadvantages that are associated with each technique. Each section also includes examples of previous uses of the NMR experiment in the analysis of real solid-state polymer or hybrid electrolyte systems with the goal of demonstrating the use of these techniques in real systems. The significance of these works along with the findings and conclusions of their authors are presented. Although similar reviews on crystalline electrolytes and reviews focusing on specific polymers have been recently published, a comprehensive review on the use of solid-state NMR spectroscopy for the analysis of polymer electrolytes has not been produced in the past decade [32–34]. This work hopes to showcase the use of NMR spectroscopy in the analysis of recent electrolyte systems and to provide a more thorough description of the experiments themselves relative to what has been presented in previous work.

2. Solid State NMR Spectroscopy Techniques

2.1. Transference Number Determination

2.1.1. Pulse Field Gradient NMR

Pulse field gradient (PFG) NMR is an experiment that is used to measure the self-diffusion coefficient of molecules or ions in solids or solutions where self-diffusion is the random translational motion that is driven by internal kinetic energy [35]. These motions typically occur on a local scale and are therefore not necessarily equivalent to the transference numbers, that can be directly measured via electrochemical methods, which describe ion motion on a macroscopic scale [15, 36]. Additionally, the NMR technique cannot distinguish single ions from poorly dissociated ion pairs and clusters which tends to result in an underestimation of the self-diffusion coefficient [36–38].

PFG NMR experiments have previously been performed using a modified spin echo pulse sequence (90° pulse - 180° pulse) where homogenous gradient pulses with duration δ and strength g are applied on either side of the 180° pulse [39]. However, the experiment is more commonly performed using a stimulated echo pulse sequence (Table S1). This experiment is generally considered to be more efficient, as the magnetization lies mainly along the z axis during the diffusion time (Δ), and is therefore subject to spin-lattice relaxation time (T_1) , instead of spin-spin relaxation time (T_2) as in the spin-echo experiment. T_2 is usually significantly shorter than T_1 which is especially true in inhomogeneous systems. A drawback of the stimulated pulse sequence is the loss of half the signal, compared to the spin-echo experiment. The stimulated echo pulse sequence therefore allows the diffusion time to be longer [40]. The basic stimulated echo PFG pulse sequence is comprised of three 90° pulses (Figure 1) [40, 41]. The application of the first 90° pulse initiates the preparation phase of the experiment where the first gradient pulse (with duration δ and magnitude g) is applied resulting in the Larmor frequency becoming spatially labeled in the direction of the gradient [35, 39, 40]. The gradient pulse is followed by the central pulse that causes the effective gradient to be zero as only the z component of the magnetization vector is of interest [39, 40]. During this store phase spins are allowed to diffuse for a time (Δ) which is usually dependent on the spin-lattice relaxation of the system [39, 40]. Due to the effective gradient being zero, the read and preparation phases are equivalent in terms of magnetization [40]. Therefore the application of the second gradient pulse, which occurs during the read phase after the application of a third 90° pulse, either cancels out the effects of the first gradient pulse if no motion has occurred or results in an attenuation of the total signal that is proportional to the translational motion that has taken place [35, 39, 40]. PFG NMR can be used to measure diffusion along any axis depending on how the x, y and z gradients are used [35, 42].



Figure 1. Stimulated echo PFG pulse sequence.

In the study of solid polymer or hybrid electrolytes, PFG NMR spectroscopy is commonly used to measure self-diffusion coefficients of anions and cations of the salt species as these are dissociated in the polymer or hybrid network. This is typically accomplished by performing ⁷Li (cation mobility) and ¹⁹F (anion mobility) experiments as both nuclei have high magnetic susceptibilities [43]. Additionally, PFG NMR can be performed on ¹H and ¹³C to measure the mobility of the polymer chains as this motion can have a significant impact on the overall ion mobility in these systems [44-46]. PFG NMR is not usually used to measure sodium diffusion in sodium-conducting electrolytes because quadrupolar effects cause relaxation at ²³Na sites be much faster than relaxation at 7Li sites [47]. Transport numbers for sodium ions therefore tend to be measured via electrochemical methods such as potentiostatic polarization [48]. Larger self-diffusion coefficients generally indicate higher ion mobility. Self-diffusion coefficients (D) can be calculated based on the degree of signal attenuation for each peak in the NMR spectrum using the Stejskal-Tanner equation (equation 1) [39, 42], where I and I_0 are the spectral integrals with and without the application of the gradient pulses, γ is the gyromagnetic ratio of the measured nucleus, g is the gradient strength, δ is the gradient pulse duration and Δ is the diffusion time. Usually, D is calculated by fitting the plot of signal intensity as a function of the gradient strength, keeping all delays and gradient duration constant. This allows the effects of relaxation on signal intensity to be removed. The Stejskal-Tanner equation is used for the spin echo experiment. When PFG NMR is performed using other pulse sequences, the Δ and δ quantities are modified to take the parameters of the experiment into account.

$$I = I_0 \exp\left(-\gamma^2 g^2 \delta^2 D\left(\Delta - \frac{\delta}{3}\right)\right) \qquad (1)$$

Self-diffusion coefficients (D_+ the diffusion coefficient for the cation and D_- the diffusion coefficient for the anion), which are used to gauge the mobility of ions in a system, can also be used to calculate the activation energy for local-scale ion motion by plotting these values in a Arrhenius plot [49].

Additionally, the transference number (*t*_{NMR⁺}), which is a measure of cation mobility relative to anion mobility (mole of cation transferred by migration per Faraday of charge) in a dilute system with no concentration gradients or ion association, can be calculated using self-diffusion coefficients (equation 2) where *z*₊ and *z*₋ are the charges on the cation and anion respectively [50, 51]. This method for measuring the transference number works best in dilute systems as it assumes negligible ion-ion interactions and does not take into account the motion of associated species (sees everything as ions) [51].

$$t_{NMR}^{+} = \frac{z_+ D_+}{z_+ D_+ - z_- D_-}$$
(2)

150 151

152

153

154

155

156

157

158 159

160

161

162

163

164

165 166

167

168

169

170

171

172 173

174

175

176 177

178 179

180 181

182

183

As mentioned previously, transference numbers can also be experimentally determined using electrochemical methods. A commonly used method is to couple a potentiostatic polarization with electrochemical impedance spectroscopy (EIS). This is typically done by employing the Bruce-Vincent method which involves polarizing a Li 11 Li cell using a small potential difference (~10 mV) until a constant current is reached [51, 52]. The resultant steady state conditions can then be used to calculate the transference number (t_{PP}) via equation 3 where ΔV is the applied potential difference, I_0 is the initial current, I_{ss} is the steady state current, R_0 is the resistance prior to polarization and R_{ss} is the resistance after polarization [51]. As for the NMR measurement, this approach is only valid in systems where the concentration gradient is negligible [51]. In more concentrated systems ([Li⁺]/[O] > 0.1), the potentiostatic polarization experiment results in the diffusion of neutral ion pairs resulting in the over estimation of t_{PP} [51, 53].

$$t_{PP} = \frac{I_{ss}(\Delta V - I_o R_o)}{I_0(\Delta V - I_{ss} R_{ss})}$$
(3)

To better represent ion diffusion in concentrated solutions, the Balsara-Newman method can be used [54]. The Balsara-Newman method for the determination of transference numbers is an extension of the Bruce-Vincent method that takes into account concentrated solution theory such that the contribution of ion pairs and clusters in bulk ionic motion can be accounted for [55]. With this approach, the transference number has a complex dependence on salt concentration and becomes negative when ion transport is dominated by ion clusters. While the Balsara-Newman method has the advantage of accurately measuring transference number in concentrated solutions, the method tends to be experimentally demanding as several parameters must be determined experimentally including the ionic conductivity (σ) from EIS, the steady-state transference number (*tss*) from potentiostatic polarization, the restricted diffusion coefficient (D) from PFG NMR and the potential of the concentrated cell (U). These parameters are combined with the bulk electrolyte concentration (c), the molality of the solution (m), ionic charge (z), the total number of ions when the salt dissociates (v), the number of cations when the salt dissociates (v_{+}) and Faraday's constant (F) to obtain the transference number (t_{Ne}) (equation 4).

$$t_{Ne} = 1 - \frac{(v_{+}z_{+})^{2}}{v} \frac{2FDc}{\sigma} \left(1 - \frac{1}{t_{SS}}\right) \left(\frac{d\ln m}{dU}\right)$$
(4)

The Hittorf method (also called Tubandt when applied to solids) is another electrochemical technique, suitable for use in concentrated solutions, that can be used in the experimental determination of transference numbers in solid polymer electrolytes [56]. The electrolyte is subdivided into sections where each fragment is placed between polarized electrodes and is subjected to polarization by a known charge [51, 57]. The transference number of the anion can be determined based on the change in the number of moles of the cation following polarization of the compartment that is closest to the cathode as shown in equation 5 where Δm is the change in the number of moles of cation, *F* is the Faraday constant and *Q* is the amount of charge that was passed through the compartment.

$$t_{+} = 1 + \frac{\Delta mF}{Q} \qquad (5)$$

Bruce et al. used the Hittorf method to measure t_{+} in a poly(ethylene oxide) (PEO)-LiClO₄ electrolyte [57]. t_{+} was found to be 0.06 which is lower than what has been previously reported by PFG NMR and potentiostatic polarization: 0.2 to 0.3 [57]. The differences between the transference numbers can be attributed to the fact that the Hittorf method does not measure the mobility of neutral species because the charge is not applied for a long enough period for a concentration gradient to develop in each subsection of the polymer. Therefore, transference numbers can be overestimated if significant quantities of ion pairs are formed [57]. Although the Hittorf method specifically measures charged species, it can be difficult to perform with polymer electrolyte samples

because PEO-based samples are often too adhesive to be easily subdivided into sections. Additionally, the technique requires a specialized electrochemical cell and the sample must be divided into at least four different compartments making it difficult to obtain accurate results [51].

Differences in transference numbers calculated via PFG NMR and various electrochemical techniques can be evaluated in the context of the dissociation ratio of the ionic species. The dissociation ratio describes the extent to which the ionic species are dissolved in a sample, with 1 indicating perfect dissociation and 0 indicating no dissociation [58]. As PFG NMR does not distinguish between dissociated and un-dissociated species, transference numbers reported via PFG NMR tend to be artificially higher than those determined via electrochemical methods as the motion of neutral pairs, dissociated ions and charged clusters is usually included in the measurement [58, 59]. It can therefore be concluded that in samples where similar transference numbers are achieved via NMR and electrochemical methods, nearly complete dissociation of the ionic species has been achieved.

Several examples of experiments that illustrate these differences between PFG NMR and electrochemical methods are described here. For example, a study of lithium bis(trifluoromethanesulfonyl)imide (LiTFSI)-doped PEO, which is discussed here for the purpose of demonstrating that different transference numbers can be determined for the same system using different experimental methods, showed that transference numbers as a function of the molar ratio of lithium ion to ether oxygens (*r*) varied between 0.17 and 0.30 based on PFG NMR data, between 0.06 and 0.26 based on potentiostatic polarization experiments and between -0.38 and 0.45 by the Balsara and Newman method, from *r* = 0 to *r* = 0.3 with the lowest value of -0.38 being observed at *r* = 0.16 (Figure 2) [53, 55]. The difference between the values calculated based on PFG NMR and potentiostatic polarization which depend on dilute solutions and those calculated based on the Balsara-Newman method suggest that the ionic species are not completely dissociated in this system.



Figure 2. Transference number for Li+ in a PEO-LiTFSI system as a function of the molar ratio of lithium ion to ether oxygens (r) measured via PFG NMR (t+,NMR), potentiostatic polarization (t+,SS) and the Balsara-Newman method (t+). © Journal of the Electrochemical Society, 2017 [53].

However, transference numbers determined by electrochemical methods can also be subject to overestimation. This as was demonstrated by Sun et al., who showed that potentiostatic polarization can cause the diffusion of neutral species in concentrated systems and can result in an over estimation of the transference number via electrochemical methods [36]. Li⁺ transference numbers in a poly(trimethylene carbonate)-ε-caprolactone copolymer were 0.32 via PFG NMR and 0.66 via potentiostatic polarization [36]. These differences were attributed to the migration of neutrally charged aggregates and could be avoided by using the Hittorf method [36]. Work by Tominaga and Yamazaki showed that the overestimation of transference numbers measured via

PFG NMR and potentiostatic polarization can even differ within the same study [60]. Their comparison of transference numbers in PEO-lithium bis(fluorosulfonyl)imide (LiFSI) (0.11 via potentiostatic polarization and 0.24 via NMR) and in poly(ethylene carbonate) (PEC)-LiFSI (0.54 via potentiostatic polarization and 0.24 via NMR) showed that the degree of ion dissociation in their prepared materials was not consistent [60]. These differences demonstrate that understanding the factors that influence transference numbers measured via both techniques is important when interpreting data.

Despite limitations related to the extent of salt dissociation, previous PFG NMR studies have demonstrated that Li⁺ transference numbers can be dependent on both the segmental motion of polymer chains and the affinity of the lithium cation for the polymer. For example, Xu et al. and Sun et al. have found that cation mobility tends to be lower than anion mobility in LiTFSI-doped PEO at high lithium loading as the cation has increased affinity for the polymer matrix [27, 36]. As a result, segmental motion of polymer chains can impact short- and long-range Li⁺ diffusion [36]. Therefore, PFG NMR experiments have been performed to demonstrate that interventions designed to increase segmental motion such as the synthesis of block co-polymers[61], the addition of inert ceramic fillers[60, 62] and increased sample temperature[63, 64] can increase the mobility of Li⁺ in polymer electrolytes. The above experiments are important as they provide insight into the fact that polymer segment mobility, in addition to the extent of ion dissociation, contributes to observed transference numbers.

The above examples have focused on free ion diffusion: the random diffusion of ions that occurs as a result of thermal energy. However, PFG NMR can also be used to measure confined diffusion where the motion of ions is impeded by encountering boundaries [42]. The possibility to measure confined diffusion with three dimensional PFG NMR (using x, y and z gradients) may allow for more precise mapping of lithium ion diffusion in electrolyte systems [42]. Engelke et al. performed ⁷Li PFG NMR to follow the three dimensional motion of a lithiated liquid electrolyte in a porous silicon wafer to map the pore structure of the wafer (Figure 3) [42]. The dimensions of the pores in the wafer were determined by calculating the mean square displacement of the lithium ions using their self-diffusion coefficients [42]. Although Engelke et al. performed their experiments on a confined liquid, similar methodology could be applied to polymer or hybrid electrolytes.



Figure 3: One dimensional slice from a ⁷Li PFG NMR (7.1 T) experiment of lithiated liquid electrolyte in a porous silicon wafer. The inserts show calculated mean square displacements for each lithiated environment as a function of diffusion time. Reproduced from ref. [42] with permission from the PCCP Owner Societies.

8 of 40

The three-dimensional PFG NMR experiment could be particularly useful in the study of hybrid polymer electrolytes that contain inert ceramics as it could be used to determine the position of these particles and ascertain how Li⁺ ions pass through the electrolyte. The analysis of electrolytes containing active ceramics is more complex as there is the potential for multiple mobile lithium species resulting in multiple diffusion coefficients. To demonstrate the use of PFG NMR in the analysis of a hybrid electrolyte, a system containing 70 % PEO, 12 % LiTFSI, 9 % Li_{0.34}La_{0.51}TiO₃ and 9 % succinonitrile (all weight percent) was analyzed. PFG NMR showed the existence of two mobile lithium species between 30 and 55 °C and a single mobile lithium species between 55 and 70 °C (Figure 4) [65]. Although a single peak was observed via 1D ⁷Li NMR, the diffusion curve was best fit using two components between 30 and 55 °C [65].



Figure 4: Diffusion coefficients from the hybrid ceramic-polymer electrolyte as a function of temperature as determined by PFG NMR. © Journal of the Electrochemical Society, 2020 [65].

These diffusion coefficients were attributed to lithium conduction in the polymer and lithium conduction in the active ceramic. As the transition from two mobile lithium species to one mobile lithium species occurs around the melting point of PEO, it has been proposed that the associated decrease in polymer crystallinity results in lithium conduction occurring preferentially through the polymer at high temperatures [65]. At lower temperatures, where the polymer is expected to be crystalline, the presence of two diffusion coefficients suggests that both the polymer and ceramic participate in lithium conduction [65]. This example illustrates the primary advantage of PFG NMR over electrochemical techniques: the ability to measure species-specific diffusion coefficients in multi-component systems. This is particularly welcome in the analysis of hybrid electrolytes containing active ceramic fillers as both components of the electrolyte may participate in lithium transport. However, two-dimensional exchange spectroscopy experiments (described in section 2.3) would be needed to quantify ion exchange between these components.

2.1.2 Electrophoretic NMR

Electrophoretic NMR is a one dimensional diffusion method, that is used to measure the flow of ions, from which transference numbers can be derived [66–68]. This experimental method, involving a double stimulated echo and an applied electric field, has been previously used for the characterization of ion mobility in liquid electrolytes [66, 69]. However, it has had limited application in solid-state electrolytes outside of the work of Rosenwinkle and Schönhoff who used the method to determine transference numbers for lithium cation motion in PEO doped with various concentrations of LiTFSI [69]. The method is similar to PFG NMR in the sense that the pulse sequence is comprised of a series of gradient pulses with length δ and strength g within an echo comprised of 90° pulses (Table S1) (Figure 5). In the absence of the electric field, the random translational motion of mobile species in the direction of the magnetic field gradient results in random phase shifts and thus loss of net magnetic phase coherence, as in standard NMR diffusion experiments [66]. However, because the polarization of the electric field is switched after the first half of the pulse sequence to cancel out non-electrophoretic directional motion, only directional motion contributes to the measured phase shift (ϕ) [69].



Figure 5: Electrophoretic NMR pulse sequence.

The electrophoretic drift of the observed species is signified by a phase shift (\emptyset) in the NMR signal when the gradient strength (g) is changed. The phase shift can be calculated using equation 6 where γ is the gyromagnetic ratio of the observed nuclei, δ is the gradient pulse length, g is the gradient strength, Δ is the observation time, E is the strength of the applied electric field and μ is the electrophoretic mobility which is used to calculate the transference number.

$\phi = \gamma \delta g \Delta E \mu \qquad (6)$

The electrophoretic mobility, which can be extracted from a plot of phase shift as a function of electric field strength using equation 6 is proportional to the drift velocity (v) and the electric field strength (equation 7). The drift velocity for free cations is defined as positive while the drift velocity for free anions is defined as negative. This relationship remains true when a plot of the phase shift as a function of gradient strength remains linear (Figure 6).

$$v = \mu E \qquad (7)$$



Figure 6: Plot of phase shift, determined via electrophoretic NMR, as a function of gradient strength for lithium cations in LiTFSI-doped PEO at 90 °C and a molar ratio of lithium to ether oxygen of 0.16. © Journal of the Electrochemical Society, 20 [69].

370 371

372

373

374 375

376

377

378 379

380

381

382

383

384

385 386

387

388

389

390

391

392

393

394

395 396

397

398

399

400

401

While the electrophoretic mobility can be impacted by electric field-induced changes in polymer chain orientation and electroosmotic drift, these effects can be canceled by extrapolating the phase shift as a function of field strength to zero electric field [69]. The electrophoretic mobilities of the cation and the anion (μ_{+} and μ_{-}) can be used directly to calculate transference number (t_{eNMR}) using equation 8.

$$t_{eNMR} = \frac{\mu_+}{\mu_+ - \mu_-}$$
 (8)

A PEO-LiTFSI system was used to demonstrate that transference numbers in solid systems can be determined via electrophoretic NMR. These experiments showed that cation mobility decreased with increasing salt content as a result of coordinating interactions between the salt and the polymer causing decreased side chain mobility [69]. The authors compared the t_{eNMR} values with transference numbers obtained via PFG NMR (*t*_{*PFG*}). Transference numbers obtained via both techniques were found to be in close agreement (*t*_{PFG}: 0.21, 0.17, 0.17 and *t*_{eNMR}: 0.23, 0.19, 0.15) for lithium at ether oxygen ratios of 0.06, 0.10 and 0.16 respectively, indicating that the samples contained mostly free cations [69]. As electrophoretic mobility is less impacted by the presence of ion pairs and agglomerations, it is anticipated that it can be used to provide more accurate values for transference numbers than PFG NMR in undiluted media. A direct comparison between electrophoretic NMR and electrochemical methods would be needed to determine the relative strengths of these methods for the determination of transference numbers in various types of samples. However, a lesser reliance on dilute systems suggests that electrophoretic NMR would be particularly useful in the analysis of systems with multiple mobile lithium environments such as hybrid electrolytes containing active ceramics. 2.2 Variable Temperature NMR

As lithium and sodium conductivities are temperature-dependent in many solid polymer and hybrid electrolytes, variable temperature NMR spectroscopy has been used to evaluate ion dynamics in these systems. Experiments that have been regularly performed for site-specific analysis of molecular dynamics include spin-lattice (T₁) relaxation, spin-spin (T₂) relaxation and linewidth analysis. Pulse sequences used to perform these techniques, along with examples of their use in the study of solid-state polymer and hybrid electrolytes, are discussed in this section. It must be noted that the larger quadrupolar moment of sodium, relative to lithium, means that quadrupolar coupling may have a significant impact on these parameters.

2.2.1 Spin Lattice Relaxation (T1)

The application of radio frequency pulses during NMR experiments perturbs the magnetization vector away from its equilibrium position. The process through which the magnetization vector returns to equilibrium is termed relaxation [29]. In this work, the impact of temperature on T₁ relaxation for the study of ion mobility in solid electrolyte systems will be discussed. T₁ relaxation is characterized by the flow of energy out of the spin system and into the lattice and can be conceptualized as the time required for a perturbed magnetization vector to return to its equilibrium position following the application of a radio frequency pulse [29, 70]. T₁ relaxation generally occurs on the order of seconds to milliseconds but can be up to several minutes long for some nuclei in some environments. This relaxation process can be influenced by properties of the sample such as ion mobility and dipolar and quadrupolar interactions [70]. T₁ relaxation is typically measured using the inversion recovery pulse sequence (Table S1) (Figure 7) which is comprised of a 180° pulse which inverts all signals, a variable delay time (vd) during which relaxation back to equilibrium is allowed to occur and a 90° pulse for spectral acquisition [29].



Figure 7: Inversion recovery pulse sequence.

This experiment produces a series of spectra of differing signal intensity as a function of variable delay time. T₁ relaxation can be calculated by fitting a plot of signal intensity as a function of variable delay time (*vd*) with one (or a series of) exponential functions. The fit can be performed using equation 9 where S_{vd} is the signal intensity at a given variable delay time and S_0 is the signal when *vd* is equal to zero [70, 71]. *K* is a fitted constant (with a value that is close to but does not exceed 2) that accounts for imperfect 180° pulses and the use of non-optimal repetition times.

$$S_{vd} = S_0 \left(1 - K e^{\frac{-vd}{T_1}} \right) \quad (9)$$

It is worth noting that as a quadrupolar nuclei (spin greater than $\frac{1}{2}$), T₁ build up curves for ⁷Li spectra should in theory be fit using a double exponential function [72, 73]. However, as a result of the small quadrupolar moment of ⁷Li (~0.04 MHz) [74], deviations from a single exponential fit are difficult to detect [72]. The T₁ relaxation time can also be quickly approximated using the variable delay time that results in net zero magnetization (*T*_{null}) (equation 10) [70].

$$T_1 = \frac{T_{null}}{\ln 2} \qquad (10)$$

Meanwhile, ²³Na has a much larger quadrupolar moment which ranges between close to 0 and up to 7 MHz depending on the symmetry of the internal coordination sphere with highly symmetrical coordination spheres giving rise to low quadrupolar moments and coordination spheres with low symmetry giving rise to larger quadrupolar moments [75]. Therefore, T₁ build-up curves coming from sodium-based electrolytes may need to be fit using two or more exponentials depending on the magnitude of the quadrupolar moment.

 NMR spectroscopy is highly sensitive to the impact of polymer chain dynamics on T₁ relaxation times [72]. As cation mobility and the mobility of the polymer backbone generally occur on the order of microseconds to seconds, these quantities can be evaluated via T₁ relaxation [76]. Many researchers have measured T₁ relaxation as a function of temperature to study the impact that this variable has on Li⁺ and polymer chain segmental mobility [76, 77]. As activation energy for these processes can be calculated based on Arrhenius and/or Vogel-Tamman-Fulcher (VTF) plots of T₁ values, these quantities can be directly coupled with EIS data to provide a site-specific view of which motional processes contribute to long-range lithium conductivity [72, 78].

When calculating activation energies from T₁ values, temperature-dependent changes in ionic conductivity in polymer electrolytes must be taken into account as a result of changes that occur in polymer chain mobility above and below the glass transition temperature (T_g) [78]. At low temperatures, ionic conductivity in polymers is typically a result of the dissociated ionic pairs migrating through interstitial defects [78]. The activation energy for this process can be described by the Arrhenius behavior. Above T_g, ionic transport increases as a result of increased motion in the polymer side chains as they become less crystalline [79]. The activation energy for this process is best described by the VTF equation which was originally developed to describe the viscosity of supercooled liquid (Equation 11) [78], where σ is the ionic conductivity, *A* is a pre-exponential factor that is related to the concentration of the charge carrier, *E_a* is the activation energy which is typically related to the segmental motion of the polymer chains, *R* is the ideal gas constant, *T_o* is the Vogel temperature which is equal to the glass transition temperature in ideal glasses [80]. This is typically taken to be 50 °C below the glass transition temperature in polymer electrolytes [80].

 $\sigma = A e^{\frac{E_a}{R(T-T_o)}} \quad (11)$

Lower T₁ values are typically associated with increased mobility in solids. This is because spins that require changes in energy to relax can transfer that energy to or from motional processes [81]. An example that illustrates the impact motional processes on the rate of T₁ relaxation can be found in the work of Peng et al. who compared ⁷Li T₁ relaxation times of a Li2O-Al2O3-SiO2-P2O5-TiO2-GeO2 (LICGC) ceramic, a mobile lithium-containing polymer phase and an immobile lithium-containing polymer phase in a PEO-LiTf-LICGC hybrid electrolyte [82]. T₁ relaxation times were longer for all lithium-containing phases of the hybrid electrolyte relative to the plain LICGC sample and a PEO-LiTf electrolyte [82]. The observed lower lithium ion mobility was attributed to a Lewis acid/based interaction between the polymer and the ceramic creating increased resistance in the ceramic-polymer interfacial layer [82]. Other interactions that can increase the rate of T1 relaxation include paramagnetism and dipolar or quadrupolar coupling. Paramagnetic samples contain unpaired electrons which have large magnetic moments and are particularly effective at promoting relaxation [81]. Paramagnetism is particularly relevant in hybrid systems as many ceramics contain paramagnetic transition metals. Dipolar and/or quadrupolar coupling interactions tend to decrease T_1 relaxation times by providing an alternate pathway through which the relaxation process can occur [81]. This means that coupling interactions between ions and the membrane can also influence T₁ relaxation with stronger interactions resulting in decreasing T₁. However, as lower T₁ values are typically associated with more mobile as opposed to membrane-bound Li⁺ ions, it can be assumed that motional processes have a more significant impact on T₁ relaxation in these systems than dipolar coupling interactions do.

Similar relationships between T1 relaxation and site mobility have been observed in sodium-based polymer electrolytes. Schantz and Kakihana observed two sodium sites in a poly(propylene oxide) sample that contained NaCF₃SO₃ [83]. The observation of two distinct sites (one narrow and one broad) was attributed to the presence of two different nuclear coordination environments which were made visible by differences in quadrupolar coupling between these sites [75, 83]. The narrow site, which had a T1 relaxation time of 9 µs, was attributed to mobile dissociated ions whereas the broad site (with a T₁ relaxation time of 13 ms) was attributed to ion pairs which tend to have low mobility [83]. Similar observations regarding the impact of motional processes on T1 relaxation in sodium-based polymer systems were made by Pak et al. in a poly(propylene oxide)-NaB(C₆H₅)₄ system [84]. This sample also contained two sodium sites which could be attributed to mobile dissociated ions and less mobile ion pairs [84]. The T₁ relaxation time for the mobile site was about 10 ms at room temperature with the T1 relaxation time for the broad site being about ten times longer. The difference between these relaxation times, and the faster T_1 relaxations times that are found in most sodium-containing polymer electrolytes such as those studied by Schantz and Kakihana, was stated to be a result of complexation between the sodium cation the large $B(C_6H_5)_4$ anion [83, 84]. It was additionally observed that the T₁ relaxation continued to decrease with increasing temperature and did not plateau at the T_g of poly(propylene oxide) as has been previously observed in several similar systems [84]. This suggests that ion motion primarily occurs independently of the motion of the polymer chain.

Sample mobilities can also be compared using a quantity called T₁ minimum. The T₁ minimum occurs at the temperature where the variations in relaxation rate are on the order of the Larmor frequency [30, 76]. The T₁ minimum can more directly be described as the temperature at which T_1 relaxation occurs most rapidly [81]. Species where the T_1 minimum occurs at a higher temperature have lower ion mobility as more energy must be transferred to or from the spin system for the maximum rate of T₁ relaxation to occur [30, 76, 81]. The correlation between differences in T_1 minimum and differences in ionic mobility was demonstrated through the analysis of LiClO₄ doped polyurethane-poly(dimethylsiloxane) copolymers [76]. In this system, the temperature where the T_1 minimum occurred was found to increase with increasing LiClO₄ loading (Figure 8a) [76]. These findings were well-correlated with impedance spectroscopy data as samples with T₁ minima at higher temperatures were found to be less conductive (Figure 8b) [76]. Although the determination of the T1 minimum is generally time consuming and requires a probe and a variable temperature control with an extensive range, it can provide more information on the thermal properties of the polymer system in question than more typical T₁ measurements allowing for potential comparisons to differential scanning calorimetry data and the analysis of materials or samples that are not amenable to differential scanning calorimetry.



491

492

493

494

495

496

497

498 499

500

501

502

503 504

505 506

507

508

509 510

511

512 513

514

515

516

517

518

519 520

521

522

523

524 525

526 527

528

529

530

Figure 8: a) Variable temperature T₁ relaxation times for a series of LiClO₄-doped polyurethane-poly(dimethylsiloxane) copolymers with various salt concentrations. b) Ionic conductivity as a function of temperature for a series of LiClO₄-doped polyurethane-poly(dimethylsiloxane) copolymers with various salt concentrations. Reprinted with permission from [76] Copywrite 2002 American Chemical Society.

533

534

535

536 537

538

539

540

541 542

543

544

545

546 547

548

549

550

551

552 553

554

555

556

557

558

559

560

561

562

563

564

565

566

567

568

569 570

571

572

573

574

575

576

577 578

579

580

581

582 583

584 585 In the example presented in Figure 8, activation energies were calculated based on the low temperature T₁ data by fitting the slope of an Arrhenius plot [76]. The activation energy was found to increase from 6.3 to 11.3 kJ/mol when the molar ratio between the lithium salt and the polyurethane-poly(dimethylsiloxane) copolymer was increased from 0.2 to 1.5 [76]. Activation energies were not calculated for the high temperature region as a result of a kink in the T₁ data around 0 °C corresponding to the transition from Arrhenius to VTF conductive behavior in the polymer sample thus indicating a link between NMR and conductivity measurements [76].

Lin et al. and Daigle et al. have measured variable temperature T₁ in polyethylene glycol (PEG)-based co-polymer systems containing lithium salts [31, 76]. In both cases T₁ was observed to decrease with increasing temperature indicating increased mobility of both the polymer segment and the Li⁺ ions. These results can often be correlated with conductivity data. In these works, the low temperature portion of the T₁ buildup as a function of temperature curve is used to calculate activation energies for Li⁺ transport in these systems, a method that can be used in samples that are not suitable for analysis via EIS [85]. It is worth noting that this method does present some challenges as it requires the ability to measure NMR spectra at low temperatures (down to -50 °C in Lin et al.[76]) since temperatures above about -10 °C are around the T₁ minimum where significant changes in T₁ as a function of temperature no longer occur [85]. An additional challenge is peak overlap. Despite differences in T₁ relaxation times between sites, Lin et al. reported that it was difficult to deconvolute signals from the polymer backbone and the mobile Li⁺ species resulting in the reported activation energies potentially including contributions from both species.

The differences between characterizing Li⁺ mobility in a polymer electrolyte using T₁ relaxation and EIS are illustrated in the outcome of the study by Jeon and Kwak [72]. The variable analysis temperature T_1 of а poly(vinylidene fluoride-co-hexafluoropropylene) network doped with P(EO-EC)-LiCF₃SO₃ between -40 and 70 °C showed that T_1 relaxation time and T_1 derived activation energy for lithium motion decreased with increasing temperature and increasing P(EO-EC)-LiCF₃SO₃ doping [72]. Both are consistent with increased lithium mobility. Decreasing activation energy was also observed with increasing temperature and increasing P(EO-EC)-LiCF₃SO₃ doping via EIS [72]. However, the activation energies were not equal. The activation energy that was calculated based on T1 relaxation (9.8-13.1 kJmol-1) was lower than that which was calculated based on lithium conductivity (41.2-50.1 kJmol⁻¹) [72].

The difference in activation energies is a result of NMR and EIS measuring ion motion on different length scales. NMR effectively measures local-scale mobility while EIS measures global mobility. It is anticipated that the higher activation energy as measured by EIS is a result of more energy being required for long-range motion than for local-scale motion [72]. Additionally, in samples with multiple lithiated chemical environments, site-specific activation energies, which may not contribute to global ionic conductivity, can be determined by NMR. This is not the case with impedance spectroscopy of polymer samples as one conductivity value typically represents all components of a sample that are in the same phase and that contribute to long-range ionic conductivity. There may however be the possibility of distinguishing multiple phases via EIS in ceramic or hybrid samples due to the presence of multiple semi-circles. The difference in motional scale, along with the possibility to measure site-specific mobility in NMR are the reasons why activation energies calculated via these techniques may not match and should not be compared directly. However, comparing these properties qualitatively (increasing or decreasing) can be done to support claims of increased or decreased mobility in a sample.

2.2.2 Spin-Spin Relaxation (T₂)

586

587 588

589

590

591 592

593

594

595

596 597

598 599

600

601

602

603

604

605 606

607

608

609

610

611

612 613

614

615

616

617

618

619

620

621

622

623

624

625

T₂ relaxation, also called transverse relaxation or spin-spin relaxation, is the relaxation of the x and y components of the magnetization vector without energy transfer to the lattice [70]. This process occurs as the magnetization vector precesses about the xy plane after a pulse has been applied [70]. During this time, individual spins that make up the magnetization vector fan out across the xy plane which destroys coherence (the orientation of magnetization in the same direction) and can result in line broadening. This process is due to small fluctuations of local microscopic magnetic field caused by local mobility. This effect, which depends on the orientation of the nucleus with respect to the magnetic field and the scalar coupling in electrons is particularly apparent when T₂ relaxation times are short [70]. Short T_2 relaxation times can cause significant signal loss if the T2 is shorter than the delay times that are used in some pulse sequences. T2 relaxation times can be particularly affected by the quadrupolar interaction as it is also orientation dependent and heavily dependent on the structure of the local coordination sphere [86]. Changes in the quadrupolar interaction tend to minimize T₂ relaxation time which causes significant line broadening [86]. Line broadening can complicate spectral interpretation by causing peaks originating from distinct chemical environments to overlap.

T₂ relaxation can be measured using the spin-echo pulse sequence which is comprised of a 90° pulse followed by a delay time (τ), a 180° pulse and a second delay period (τ) [87, 88]. However, the Carr-Purcell-Meiboom-Gill (CPMG) pulse sequence (Table S1) is probably more commonly used to measure T₂ relaxation [89, 90]. This pulse sequence begins with a 90° pulse, a delay period (τ) and a 180° pulse as in the spin echo sequence, but also includes a train of 180° pulses at $2n\tau$ delay periods following the first 180° pulse which results in a series of spin echoes that occur at time $2n\tau$ (Figure 9) [90]. The echo train continues until the signal has decayed [89, 90]. The advantage of using the CPMG pulse sequence over the spin echo pulse sequence is that the train of 180° pulses minimizes the potential loss of magnetization due to random spin diffusion, which prevents complete magnetization refocusing [90]. Both the spin-echo and the CPMG pulse sequences are used in some of the experiments that are discussed here.



Figure 9: CPMG pulse sequence.

In single-pulse experiment, observed signal decay is caused by a combination of T₂ relaxation and decay due to magnetic field inhomogeneity[29]. However, the spin echo pulse sequence allows losses due to field inhomogeneity to be recovered. Following the application of the 90° pulse, magnetic field inhomogeneity causes spins in regions of relatively high magnetic field to precess faster than spins that are in a region of relatively low magnetic field [29]. After the spins have evolved for time τ , the phases of magnetization of different regions are sufficiently different to cause a decrease in the overall magnetization. This is illustrated in equation 12 where T_2^* is the observed decay, T_2 is the transverse magnetization, γ is the gyromagnetic ratio and ΔH_0 is the inhomogeneity of the magnetic field.

$$\frac{1}{T_2^*} = \frac{1}{T_2} + \gamma \Delta H_0 \qquad (12)$$

However, the spins in each individual region of the magnetic field are still coherent and precessing in the transverse plane [29]. This dephasing effect is then reversed by the application of a 180° pulse as all transverse spins are reflected in the direction of the applied pulse [29]. This reverses the motion of the spins and, because faster spins get de-phased at a faster rate, after the second delay period all spins are back in phase and the total magnetization reaches a maximum (yielding a spin echo) [89]. The height of the spin echo shows what the free induction decay would have been at a time of 2π if no field inhomogeneities were present [90]. For the CPMG pulse sequence, 180° pulses are repeated until the echo has completely decayed. In this case, T₂ is calculated using equation 13 where $I(2n\tau)$ is the signal after the nth echo and I(0) is the initial signal.

$$I(2n\tau) = I(0)e^{\left(\frac{-2n\tau}{T_2}\right)} \quad (13)$$

 T_2 relaxation, as determined using the spin-echo pulse sequence, has been used in a few instances in the analysis of polymer films as an alternative method for measuring the effects of electrolyte hydration and lithium salt addition [88, 91]. This was the case in the work of Donoso et al. who compared T₂ values in hydrated and anhydrous PEO-LiBF4 polymer electrolytes [91]. T₂ relaxation was found to increase with hydration with the anhydrous film having a T₂ of 45 μ s and the hydrated film having a T₂ of 130 μ s [91]. The increase in T_2 relaxation time was attributed to the fact that water is predicted to act as a plasticizer in this system by both increasing the mobility of the polymer chains and by increasing the volume of the mobile segments [91]. The fact that changes in polymer chain mobility can be observed via T2 relaxation was also used by Forsyth et al. as an alternative means of determining Tg in PAN-LiTf films that were not amenable for analysis via DSC [88]. The T_g was identified as the temperature at which a large increase in T_2 , which was correlated with increased polymer chain mobility, was observed (Figure 10). In this case the pure polymer had a T_g of 107 °C whereas the sample containing 67 % LiTf had a T_g of 72 °C showing that increased salt content increased polymer plasticity [88]. It is noted by the authors that the T_g value for the pure PAN sample is about 10 degrees higher than the standard DSC value. The above studies show that T_2 relaxation can be used instead of or in combination with differential scanning calorimetry to elucidate the impact of temperature on polymer mobility and thermal properties.



Figure 10: T₂ relaxation as a function of temperature for pure PAN and PAN electrolytes containing 30 and 67 % by weight LiTf. T_g was designated as the temperature where T₂ relaxation changed significantly which was indicative of significant polymer chain motion. Reprinted from [88] Copywrite 2000 with permission from Elsevier.

661

626

627

628 629

630

631 632

633

634 635

636

637

638 639

640

641 642

643

644

645

646 647

648 649

650

651

652

653

654

655

656

657

658 659

660

662 663

The Carr-Purcell pulse sequence has been used to identify environments with different mobilities in polymer electrolytes. The ability to identify and characterize multiple species in the same sample is typically one of the advantages of using NMR spectroscopy over electrochemical techniques. This has been demonstrated in the context of T₂ relaxation by several authors including Franco et al. who found that segments in a PEO polymer containing LiClO4 and 20 wt% carbon black have two distinct mobilities via 1H NMR [92]. The site with the longer T_2 was attributed to the mobile polymer chains and the site with the shorter T₂ was attributed to the immobile backbone [92]. A similar experiment was performed by Kwaks et al. who measured ¹H T₂ in polymer electrolytes comprised of poly(oligo oxyethylene methacrylate) and LiTFSI [93]. They found three separate T₂ values which corresponded to the mobile side chain ($T_2 = 70$ ms), the interface between the polymer chains ($T_2 = 10$ ms) and the immobile polymer backbone ($T_2 = 1$ ms) [93]. The characterization of three distinct lithium environments in a single system would not have been possible via most electrochemical methods. T₂ relaxation was also used by Kidd et al. to identify two distinct lithium environments in PEO-based polymer electrolytes that are crosslinked to polyvinylidene fluoride (PVDF) filaments [94]. These materials were soaked in a mixture of ethylene carbonate, dimethyl carbonate and lithium triflate and contained 10, 20 or 30 wt% pentaerythritol triacrylate (PETA). Two distinct lithium environments, one with a long T_2 (195-310 ms depending on PETA content) and another with a shorter T₂ (12-21 ms depending on PETA content) were identified by the authors [94]. The length of the lithium environment with short T_2 was estimated at 3 μ m based on a combination of the 2τ delay period and diffusion data from PFG experiments [94]. This finding, and the fact that the fraction of the long T₂ environment increased from 26 to 79 % when the PETA weight percent was increased from 10 to 30, allowed the environment with the short T₂ being assigned to the PVDF filaments and the environment with long T₂ being assigned to the PEO between the filaments. The results of the above studies suggest that T_2 relaxation measurements can be performed as a method of determining, among other things, the number of sites present in a sample, their mobilities and their thermal properties.

2.2.3 Linewidth

666 667

668

669

670 671

672 673

674

675

676 677

678 679

680 681

682

683

684

685

686

687 688

689

690

691

692 693

694

695 696

697

698

699 700

701

702

703

704

705

706 707

708

709 710

711

712

713 714

715

716

Similar to T₁ or T₂ relaxation, changes in spectral linewidth as a function of temperature can be compared to assess the relative mobility of species in a sample with narrower lineshapes indicating increased mobility [95, 96]. The analysis involves fitting individual peaks in an NMR spectrum and measuring the full width at half maximum (FWHM) of each site. This technique is widely used to assess mobility as it does not necessarily require complex NMR experiments to be performed (Table S1). However, techniques such as magic angle spinning (MAS) and proton decoupling are often used to produce narrower lineshapes which can be more readily deconvoluted and fit. While changes in FWHM can be used to quantify the relative mobilities of sites in a sample under the same experimental conditions, this technique is not suitable for the direct quantitative comparison of ion dynamics when different NMR experiments are performed as experimental parameters can impact FWHM. However, linewidth analysis can be used to quantitatively assess site-specific ionic motion between samples and/or under different experimental conditions if changes in FWHM are used to calculate activation energy. Activation energies can be calculated from Arrhenius plots of FWHM as a function of temperature (Figure 11) and, like T₁ relaxation, linewidth analysis can be coupled with electrochemical impedance spectroscopy measurements to describe the contributions of site-specific motions to global lithium transport [76, 97, 98].



717 718

719

720

721 722

723

724

725

726

727

728 729

730 731

732

733

734

735 736

737

738

739

740

741

742

743

744

745

746

747

748

Figure 11: Arrhenius plot based on FWHM measurement from a series of PEO-polydimethylsiloxane (PDMS) films doped with varying amounts of LiClO₄. Reprinted with permission from [76] Copywrite 2002 American Chemical Society.

Linewidth analysis is commonly used to assess the mobility of sodium sites in solid polymer electrolytes. However, as the ²³Na quadrupolar moment can be significant (up to about 7 MHz), these interactions can significantly impact linewidth making it difficult to discern which contributions to the total linewidth come from temperature-dependent ion mobility and which are caused by second order quadrupolar effects [99]. In addition to impacting linewidth, quadrupolar interactions can also alter the chemical shift from its isotropic value [100]. Despite the potential drawbacks of the quadrupolar interaction in sodium-based systems, the quadrupolar contribution to the linewidth can reveal a significant quantity of information about the sodium sites' immediate coordination environment.

Variable temperature lineshape analysis has been used to evaluate species mobility in complex polymer electrolyte systems [101]. An example of this is the use of 7Li NMR to evaluate differences in ion mobility in a polymer-gel electrolyte mixture that was comprised of polyacrylonitrile (PAN), polypropylene carbonate, ethylene carbonate and LiClO₄ salt [95]. In this case, significant line narrowing was observed in the gel component while the peak corresponding to the PAN remained broad, signaling low ion mobility in the polymer component [95]. In addition to probing component mobility in polymer-gel systems, variable temperature linewidth analysis has also been used to evaluate PEO systems containing inert and active ceramic dopants [13, 96, 102]. Chung et al. prepared PEO-LiClO₄ films containing 10 wt% TiO₂ [96]. The addition of the ceramic nanoparticles resulted in an increase in the FWHM relative to the TiO₂-free sample. This was attributed to decreased segmental motion of the polymer chains as a result of crosslinking between the polymer and the TiO₂ nanoparticles [96]. Bonizzoni et al. used variable temperature ⁷Li NMR to analyze a PEO-LiTFSI system containing Li_{1.3}Al_{0.3}Ti_{1.7}(PO₄)₃ (LATP) between 25 and 75 °C [13]. Coalescence between peaks corresponding to two lithiated sites in the ceramic indicated that the rate of lithium ion exchange between these sites increased with temperature. [13]. The peak corresponding to LiTFSI narrowed indicating increased lithium mobility [13]. Menkin et al. used ⁷Li variable temperature NMR to evaluate the impact of LiAlO₂ content on a PEO-lithium iodide (LiI) system [102]. It was found that increasing sample temperature resulted in peak narrowing between 25 and 50 °C for the peak corresponding to lithium ions in PEO and the appearance of a sharp peak (from a previously existing shoulder) at 80 °C which was assigned to the polymer-ceramic interface [102]. No changes in linewidth were observed in the peak corresponding to the bulk ceramic indicating that it did not participate in ion conduction (Figure 12) [102]. It can be seen that lineshape analysis can be particularly useful in distinguishing mobility at different sites in complex systems such as hybrid electrolytes where differences in ion dynamics between the polymer and ceramic components, as well as any interfaces, can be expected.



Figure 12: Variable temperature ⁷Li NMR spectra (7.1 T, 5 kHz) of a PEO-LiI polymer matrix containing LiAlO₂ (a). Deconvolution of the spectrum at 80 °C (b). Reprinted from [102] Copywrite 2019 with permission from Elsevier.

In addition to its use in variable temperature NMR, lineshape analysis has also been used at constant temperatures to evaluate the effects of inert and active ceramic doping on the polymer matrix in hybrid electrolyte systems [103, 104]. Xu et al. used ¹H NMR to measure the hydrogen bonding interaction between a PEO-LiClO₄ polymer matrix and an inert SiO₂ nanoparticle dopant in order to evaluate the effects of SiO₂ doping on PEO crystallinity [103]. They found that interactions between the SiO₂ nanoparticles and the polymer chain reduced crystallinity in the PEO matrix. These interactions produced narrower lineshapes which indicated increased segment mobility which is typically associated with increased conductivity (Figure 13) [103].



Figure 13: ¹H NMR spectra (9.4 T) of PEO-LiClO₄ membrane containing various mass percentages of SiO₂. Reprinted with permission from [103] Copywrite 2020 American Chemical Society.

Conversely, Zheng and Hu, who used 6Li NMR to analyze a PEO-LiTFSI electrolyte containing 20 and 50 wt% Li7La3Zr2O12 (LLZO) (an active ceramic) system, reported that increasing ceramic content increased the linewidth of the peak corresponding to the polymer as a result of decreasing crystallinity in the PEO polymer matrix [104]. As increased sample disorder may result in line broadening, the dual effects of sample disorder must be considered when evaluating NMR spectra. The types of interactions that are possible between the ceramic, either active or inert, and the polymer must therefore be well-understood to be able to determine whether changes in linewidth are indicative of changes in sample mobility or interactions between the polymer and the ceramic additive.

In addition to tracking lithium mobility, analysis of FWHM as a function of temperature was used by Lago et al. to compare the mobility of the TFSI anion in a PEO-LiTFSI electrolyte and an electrolyte system that was comprised of Al₂O₃ nanoparticles grafted to PEG and TFSI in a PEO-diglycidyl ether of poly(ethylene glycol) polymer matrix [105]. Analysis of ¹⁹F FWHM revealed that the TFSI anion was significantly more mobile in the PEO-LiTFSI electrolyte than in the grafted composite electrolyte [105]. This situation is of interest as lower anion mobility serves to increase cation transference number. Line width analysis is one of the most commonly used techniques to analyze differences in mobility of sodium environments in polymer electrolytes [83, 99, 100]. Wong and Zax tracked changes in FWHM for a hybrid electrolyte comprised of PEO, lithium salt and the sodium-containing silicate montmorillonite [99]. Measuring sodium FWHM between -73 and 77 °C revealed a general decrease in linewidth with temperature which suggests that the dipolar contribution to the linewidth dominates in this system. The observation of two low temperature plateaus in a plot of sodium linewidth as a function of temperature indicates that quadrupolar interactions also contribute to the observed linewidth [99]. Work by Forsyth et al. showed that the linewidth of a poly(ethylene oxide-co-propylene-oxide) polymer electrolyte containing NaCF3SO3 decreased from 4.2 to 0.6 ppm between -67 and 20 °C [100]. This is indicative of increased sodium mobility in this system and suggests that dipolar contributions to the linewidth also dominate in this system. In addition to affecting FWHM, the quadrupolar interaction

806

807

808

775

can also cause the observed chemical shift to differ from its isotropic value. This phe-809 evaluated by Spindler and Shriver 810 nomenon was in а poly(methyl-hydrosiloxane)-monomethyl ether poly(ethylene glycol) co-polymer that 811 contained Na[SO₃C₃F₃] [106]. The 23 Na chemical shift was observed to become more pos-812 itive when either sample temperature or salt content were increased [106]. This observa-813 tion was attributed to increased interaction between cations and anions in this system. 814 815 2.3 Exchange Spectroscopy 816 817 Like relaxation and linewidth analysis, exchange spectroscopy (EXSY) can be used to quantify changes in ion motion as a function of sample temperature or doping. EXSY is 818 typically used to identify site-specific exchange processes and provides quantitative data 819 820 including rates of chemical exchange and activation energies for these processes. In one dimensional NMR spectra, chemical exchange is typically manifested as coalescence 821 822 where the approximate rate of exchange can be evaluated based on the degree of peak overlap: minimal overlap indicates slow exchange, significant overlap with two sites still 823 824 resolvable indicates intermediate exchange and complete overlap with line narrowing (motional exchange counteracts peak broadening) indicates fast exchange [107]. 825 EXSY is a two dimensional NMR experiment that is generally used to analyze sys-826 tems undergoing slow and intermediate exchange processes [107]. Slow and intermediate 827 exchange rates correspond to processes that occur prior to coalescence where the rate of 828 829 exchange is less than the difference in Larmor frequency between the two sites [107]. The EXSY pulse sequence (Figure 14) is comprised of three 90° pulses (Table S1). The first 830 pulse frequency labels all spins in the system which are then allowed to evolve over a 831 variable delay period t_1 [108]. The second pulse inverts all spins which relax and possibly 832 undergo chemical exchange during the mixing time t_m and are observed following the 833 application of a third pulse [108]. All spins maintain the labeling that was created by the 834 first pulse which causes signals related to chemical exchange between sites to appear as 835 836 off-diagonal cross peaks. Off-diagonal peaks have different coordinates on each frequency axis in the two dimensional spectrum, whereas diagonal peaks (same coordinates 837 on each axis) represent the fraction of spin which didn't undergo chemical exchange 838 (Figure 15) [108]. Multiple exchange processes are represented by multiple sets of 839 crosspeaks. Quantitative data from EXSY experiments is obtained by fitting the inte-840 grated area of the cross peaks and the diagonal peaks. The cross peak area is normalized 841 with respect to the diagonal peak area and can be plot as a function of mixing time to 842 843 extract exchange rates [108]. Arrhenius plots of exchange rates can be fit to obtain activation energies for individual exchange processes. These activation energies are site specific 844 and can be compared to electrochemical data to determine which local exchange pro-845 cesses do, and do not, contribute to long range conductivity. However, a disadvantage of 846 obtaining kinetic parameters via EXSY is that the experiment is time consuming since 847 two dimensional experiments must be performed at several mixing times for each tem-848 849 perature to obtain reliable rates of chemical exchange. 90° 90° 90°



Figure 14: EXSY pulse sequence.



Figure 15: Sample EXSY spectrum. Diagonal peaks (1,1 and 2,2 along the dotted line) represent the original position of each spin and have the same frequency coordinates on both axes. Cross peaks (1,2 and 2,1) represent exchanged spins and have different frequency coordinates on each axis.

A first disadvantage to using EXSY to measure chemical exchange is that the exchange rate must be equal to or greater to the spin-lattice relaxation time [109]. This limitation can result in significant constraints when ²³Na NMR is considered as the quadrupolar interaction in many sodium environments causes T₁ relaxation to occur more quickly relative to T₁ relaxation in ⁷Li systems [47]. Chemical exchange processes that occur on a timescale that is slower than the spin-lattice relaxation cannot be observed via ESXY as crosspeaks are not produced during the mixing time, t_m in Figure 15 [109]. A second disadvantage that is relevant to the use of EXSY to analyze the chemical exchange of quadrupolar nuclei is that quadrupolar interactions typically cause line broadening as a result of second order effects not being attenuated by regular MAS spectroscopy [110]. Significant line broadening has previously been shown to obscure otherwise observable crosspeaks by decreasing peak separation and therefore increasing the minimum correlation time for a motional process to produce observable crosspeaks [111].

In the analysis of solid polymer electrolytes, EXSY has been used to demonstrate polymer mobility and to establish lithium conduction pathways in solid polymer and hybrid electrolytes. To this end, Liu et al. used ¹³C EXSY to analyze polymer chain dynamics in a PEO-LiAsF₆ system where the impact of various molecular weights of PEO on segmental motion was evaluated [112]. Analysis of the two dimensional spectrum revealed cross peaks that were consistent with polymer chain diffusion [112]. The cross peaks that were observed between pairs of carbon atoms were consistent with forward and backward chain motion with the integrated area of the cross peaks being representative of the rate of this motion [112]. Chain diffusion was found to increase with PEO

molecular weight as it was associated with amorphous regions in the polymer matrix which remain small at low molecular weights [112].

880

881

882

883

884

885

886

887 888

889

890

891

892 893

894 895

896

897

898 899

900

901 902

903 904

905

906 907

908

909

910 911

912 913

914

915

916

917

In addition to its use in the characterization of polymers, 7Li EXSY was also used to determine which lithiated environments are involved in ion conduction in a PEO-LiAsF6 system that is encased in a series of α -cyclodextrin nanochannels [113]. Prior to performing the two dimensional experiment, five lithium environments were identified via one dimensional NMR techniques: Li-1 was attributed to lithium ions in PEO, Li-2 was attributed to interfacial lithium between PEO and the cyclodextrin nanochannels, Li-3 was attributed to "free" lithium ions and Li-4 and Li-5 were attributed to lithium ions in the cyclodextrin nanochannels [113]. Cross peaks were found between Li-1 and Li-2 as well as between Li-2 and Li-4 suggesting that lithium ions pass through an interfacial layer when they are transferred between PEO and the nanochannel (Figure 14) [113]. The lithium exchange rate that was calculated from the EXSY data was greater than the measured conductivity which suggests that not all local-scale motional processes contribute to long range lithium conductivity in this system [113]. However, the activation energy that was calculated via EXSY was lower than that obtained via EIS indicating additional energy barriers for long-range lithium motion in this system (Figure 16) [113]. This work demonstrates that EXSY can be used to characterize several exchange processes in a single system provided that each signal in the NMR spectrum has been previously well-characterized. It also illustrates the role that many species can play in local-scale ion motion which is not generally characterizable by electrochemical methods.



Figure 16: 7Li EXSY spectra of PEO-LiAsF₆ in cyclodextrin nanochannels (14 T, 5 kHz MAS) with a mixing time of 300 ms. Spectrum (a) was collected with no dipolar coupling and showed correlation between the PEO and the interface. Spectrum (b) was collected with dipolar coupling where correlation between the interface and the cyclodextrin layer is observed. Activation energies calculated based on EXSY NMR data and EIS data (c). Reprinted with permission from [113] Copywrite 2014 Wiley and Sons.

EXSY is not limited to homogeneous systems and, as such, was also used to measure lithium exchange between the polymer matrix and active ceramic additives in hybrid systems. Zheng et al. analyzed a PEO-LiClO₄ membrane containing LLZO, an active ceramic [114]. Their 1D 7Li experiments identified peaks attributed to the LiClO₄ in the polymer matrix, LLZO and an interfacial layer [114] The EXSY experiments revealed crosspeaks between the polymer and the interfacial layer [114]. No crosspeaks were observed between LLZO and the polymer or LLZO and the interface [114]. These results suggest that lithium ion conduction does not occur directly through the ceramic in this system. Conversely, the use of EXSY by Zagórski et al. to study a PEO-LiTFSI system containing LLZO revealed that no interface layer is formed and that lithium ion exchange instead occurs between the ceramic and the polymer directly (Figure 17) [115]. However, electrochemical impedance spectroscopy studies that were performed on this system suggest that it is not lithium exchange between the polymer and the ceramic, but the motion of lithium ions through the polymer, that is responsible for the majority of the lithium conductivity in this system [115]. The differences in the role of the polymer-ceramic interface in lithium conduction pathways in these materials could be a result of differences in LLZO content. The study by Zheng et al., where an interface was observed, involved samples containing 50 wt% LLZO while the samples used in the work of Zagórski et al. contained 10 wt% LLZO [114, 115]. It is possible that the lower LLZO content of the samples in the latter study resulted in an insufficient quantity of interfacial lithium to detect. Additionally, lithium conduction is predicted to proceed primarily through the polymer matrix in hybrid systems with low ceramic loading [104].





2.4 Dipolar Coupling

2.4.1 Cross Polarization

Like EXSY, cross polarization NMR spectroscopy (Table S1) can be used to measure correlation between chemical environments in complex systems. However, instead of relating environments based on chemical exchange, cross polarization is used to identify sites based on the strength of the heteronuclear dipolar coupling interaction that exists



931

932 933

934 935

936

937

938

939 940

between nuclei. The cross polarization experiment involves the transfer of magnetization from an abundant spin to a dilute spin [116]. The magnetization transfer happens as a result of the heteronuclear dipolar coupling interaction which is a distance-dependent through-space interaction that arises as a result of the interacting magnetic dipole moments of proximal nuclei [117]. As a result, stronger signals are indicative of stronger dipolar couplings whereas weaker signals indicate weaker dipolar couplings. The main advantages of the technique are improved sensitivity for low abundancy nuclei (up to the ratio of gyromagnetic ratios) and a reduction in experimental time as the T₁ of the abundant spin, which is generally shorter, is used during the experiment [116].

The cross polarization experiment (Figure 18) begins with the application of a 90° pulse on the abundant spin which is followed by a pulse that spin locks the magnetization of the abundant spin along the y-axis [116]. During this time, a pulse of same length is applied on the dilute spin which puts both magnetization vectors along the y-axis such that spin exchange can occur [116]. After the spin lock pulse, the radio frequency on the dilute spin is turned off to allow for signal acquisition while the abundant spin is decoupled [116].



Figure 18: Cross polarization pulse sequence for the transfer of magnetization between an abundant spin (I) and a dilute spin (S).

For spin exchange to occur, the Hartmann-Hahn matching condition (equation 14), where both nuclei have equal rates of precession and equal effective energies, must be met [118]. This condition is obtained by setting the effective field (B_1) on each channel such that the difference between the product of the effective magnetic field and the gyromagnetic ratio (γ) is equal to n times the MAS rate in kilohertz where n is equal to ± 0, 1, 2...

$$\gamma_I B_{1I} - \gamma_S B_{1S} = nMAS \qquad (14)$$

As magnetization transfer between spins is dependent on the strength of the dipolar coupling interaction, the resultant spectral intensities can be used to gauge distances between chemical environments (stronger signals are indicative of spin environments being closer together) and site mobility (increased motion decreases the strength of the dipolar coupling interaction).

Although CP NMR has yet to be used to measure sodium-ion or sodium-polymer interactions in polymer or hybrid electrolytes, it must be noted that CP NMR spectroscopy is possible between quadrupolar and non-quadrupolar nuclei as well as between two quadrupolar nuclei. In the case of cross polarization between a spin 3/2 or 5/2 nucleus and a spin ½ nucleus, the Hartmann-Hahn condition (equation 14) may be satisfied by matching the RF field strength of the spin ½ nucleus to the nutation frequency of the quadrupolar nucleus [119]. This condition is generally achieved by preceding the CP portion of the pulse sequence with a technique used to generate multiple quantum coherence from the quadrupolar nucleus such as multiple quantum magic angle spinning [119]. In the case of two quadrupolar nuclei, RF irradiation during MAS induces spin state mixing which makes extremely difficult to achieve the simultaneous spin-locking that is required to satisfy the Hartmann-Hahn condition (equation 14) [120]. However, Puls and Eckert were able to perform ²³Na-7Li CPMAS on the mixed cation glass [(Li₂O)_x(Na₂O)_{1-x}]_{0.3}[B₂O₃]_{0.7} by first acquiring a detailed understanding of the quadrupolar coupling behaviour of both nuclei by performing multiple quantum excitation and satellite transition MAS spectroscopy prior to commencing any CPMAS experiments [120].

978

979

980

981

982

983

984

985

986

987

988

989

990

991

992 993

994

995

996 997

998

999 1000

1001

1002

1003

1004 1005

1006 1007

1008

1009

1010

1011 1012

1013 1014

1015

1016

1017

1018 1019

1020

1021

1022

1023

1024

Cross polarization NMR experiments have been performed to monitor nanochannel formation in a PEO-LiAsF₆ α -cyclodextrin electrolyte systems [113, 121]. ¹H-¹³C cross polarization experiments showed that the conformation of the glucose units in the cyclodextrin changed upon nanochannel formation and was used as an indicator to demonstrate that this polymer configuration was achieved [113, 121]. Additionally, in the study by Yang et al., a combination of isotope labelling and cross polarization NMR was used to assign lithium environments to the PEO moiety or the nanochannel [113]. This was done by labeling the PEO moiety with deuterium such that the lithium environments that were visible via 2H-7Li cross polarization NMR could be assigned to the PEO whereas environments that were visible via 1H-7Li cross polarization NMR could be assigned to the nanochannel. Lithium environments that were not observed in either experiment were deemed to be free lithium as larger lithium-hydrogen distances would reduce the visibility of these sites as a result of reduced dipolar coupling interactions [113]. Limited proton exchange between the nanochannel and the PEO domains was essential for allowing deuterium enrichment to be used as a method of distinguishing between lithium environments in this system [113]. Isotope labeling experiments will be discussed in more detail in the following section.

The intensity of cross polarization spectra can also be used to gauge ion mobility as increased mobility tends to reduce the strength of the dipolar coupling interaction [122]. ¹H-¹³C cross polarization NMR has been used to compare the segmental mobilities of different polymer segments in PEG-based co-polymers. For example, in their analysis of a polystyrene PEG-methylmethacrylate co-polymer system, Daigle et al. found that the polystyrene backbone is less mobile than the PEG-methyl methacrylate sidechains as a result of the presence of attenuated peaks in a ¹H-¹³C cross polarization spectrum [31]. However, as was determined via cross polarization NMR by Lin et al. in their analysis of a PEG-PDMS co-polymer, the mobility of the sidechain groups varied based on the degree of lithium salt loading [76]. Polymer side chains containing more lithium salt tended to be less mobile as a result of stronger ethylene oxide lithium salt interactions. Additionally, increased sample temperature, which contributes to increased polymer mobility resulted in attenuation of the ¹H-¹³C cross polarization signal (Figure 19) [31]. These works show that cross polarization NMR provides enhanced characterization of a complex polymer system relative to what is possible with most single nucleus experiments. Additionally, cross polarization is a one-dimensional experiment meaning that a detailed characterization of the polymer structure and site interactions can be achieved more quickly than is possible using most two-dimensional techniques.



Figure 19: ¹H-¹³C cross polarization NMR spectra of a polystyrene PEG-methylmethacrylate co-polymer at various temperatures (9.4 T, 20 kHz MAS). Magnetochemistry 2018 [31].

2.4.2 REDOR

Rotational echo double resonance (REDOR) experiments (Table S1) are similar to cross polarization experiments in the sense that dipolar coupling interactions are used to transfer magnetization between two spins [123]. However, the REDOR experiment is generally used to provide more specific structural information as it yields site-selective dipolar coupling information for isolated spin pairs which allows internuclear distances to be determined [123, 124]. The dipolar coupling interaction, which is normally averaged out during MAS conditions, is re-introduced during the pulse sequence (Figure 20) by the application on the non-observed spin S of a train of 180° pulses that serves to invert the sign of the dipolar Hamiltonian making the average interaction non-zero [124]. The detected spin I is observed by the application of a rotor synchronized spin echo pulse sequence (Figure 20) where the 90° pulse is applied at the beginning of the experiment and the 180° pulse is applied following 2N rotor periods (T_r) where N is the number of cycles [123, 125].





Dipolar coupling constants for isolated spin pairs can be extracted from REDOR spectra by plotting the ratio of the REDOR intensity (ΔS) and the normal rotational angle intensity (S_0) as a function of the dipolar evolution time as the REDOR build up curve has a universal shape in this scenario [123–125]. The intensity of the REDOR spectrum (ΔS) is expected to decrease with increasing strength of the dipolar coupling interaction. In multi-spin systems, dipolar build up curves tend to be more complex as they are influenced by the shape and geometry of the system [124, 126, 127]. However, the strength of the dipolar coupling interaction can still be approximated by fitting the early part of the REDOR build up curve before these factors have a significant influence on the shape of the curve [126, 127]. In addition, the fact that the examples that are discussed here involve dipolar coupling between protons and quadrupolar 7Li, the impact of the quadrupolar coupling interaction can also be important. However, it has been determined that the use of the pulse sequence shown in Figure 20, coupled with the low strength of the quadrupole moment in ⁷Li results in the quadrupolar coupling being cancelled out as it has an equal effect on both ΔS and S_0 which allows equation 15, where I is the spin of the I spin, *m* is the magnetic quantum number, NT_r is the dipolar evolution time and M_2 is the second moment which can be extracted from the $\Delta S/S_0$ using a parabola fit [124].

$$\frac{\Delta S}{S_0} = \frac{1}{2I+1} \left(\sum_{m=-1}^{I} (2m)^2 \right) \frac{1}{\pi^2 (I+1)I} (NT_R)^2 M_2 \quad (15)$$

Voigt and Wüllen used REDOR to assign lithium environments in polymer electrolyte samples that were comprised of PAN and LiBF₄ [128]. Two samples with differing proportions of LiBF₄ (67 wt% and 14 wt%) were analyzed. ¹H-⁷Li cross polarization spectra revealed two lithium sites, at -1.3 ppm and -2.0 ppm that were coupled to protons. As the analyzed samples were prepared by solution casting in deuterated DMSO, these sites were attributed to interactions between the lithium cations and the polymer [128]. The signal at -1.3 ppm showed no attenuation between the spin echo spectrum and the REDOR spectrum indicating limited dipolar coupling interactions. This was attributed to fast lithium motion decreasing the strength of the dipolar coupling interaction [128]. This site was therefore assigned to mobile lithium cations. The significant attenua-

1046

1047

1048

1054

1055 1056

1057

1058

1059

1060

1061

1062

1063

tion of the signal at -2.0 ppm was observed when the spin echo spectrum was compared to the REDOR spectrum indicating stronger dipolar coupling interactions [128]. A plot of $\Delta S/S_0$ as a function of recoupling time revealed that the dipolar coupling in the sample containing 67 wt% LiBF₄ was 1.4 kHz and that the dipolar coupling in the sample containing 14 wt% LiBF₄ was 1.8 kHz indicating that having a greater percentage of PAN increases interactions between the salt and the polymer [128]. Voigt and Wüllen also performed a ¹³C-⁷Li REDOR experiment using a PEO-LiBF₄ polymer electrolyte (36 wt % PEO and 4 wt% LiBF₄) which also contained 60 wt% succinonitrile [129]. The spin echo experiment revealed two ¹³C signal that were correlated to lithium. One signal at 66.2 ppm exhibited a significant REDOR response and was attributed to polymer matrix containing the lithium salt [129]. The other signal at 70.7 ppm did not experience attenuation during the REDOR experiment and was attributed to an amorphous succinonitrile-based phase with little to no dipolar coupling interactions as a result of fast ion motion in the plasticized polymer [129]. As REDOR signal intensity is dependent on the strength of dipolar coupling interactions, it can be used, as shown here, to determine how changes in electrolyte composition affect polymer-salt interactions and predict subsequent ion mobilities. It is also anticipated the variable temperature REDOR experiments could be performed to determine how changes in temperature impact polymer-salt interactions and therefore ion mobility.

2.5 Isotope Enrichment

1075

1076

1077

1078

1079

1080

1081

1082 1083

1084

1085

1086

1087 1088

1089 1090

1091

1092

1093

1094 1095 1096

1097 1098

1099

1100

1101

1102

1103

1104 1105

1106

1107

1108

1109

1110

1111

1112

1113

1114

1115

1116 1117

1118

1119

1120

1121

1122

1123

1124

As mentioned in the ¹H-¹³C cross polarization analysis of PEO in cyclodextrin nanochannels performed by Yang et al., isotope enrichment can be performed to enhance other types of NMR experiments [113]. Isotope enrichment experiments are typically performed to highlight specific regions of a sample as was demonstrated above via the use of ²H doping to distinguish hydrogen in PEO and cyclodextrin environments [113]. Since NMR spectroscopy can be performed using any isotope where the nuclear spin is greater than zero, there exists isotope enrichment options for several nuclei. The most common isotope enrichment experiment that is performed in solid polymer electrolyte research is replacing 7Li with 6Li. Often, these experiments are not performed using enriched samples as ⁶Li has a natural abundance of 7.6 % [43]. A particular advantage of performing 6Li NMR as opposed to 7Li NMR is that 6Li nuclei experience less homonuclear dipolar coupling than 7Li nuclei as a result of its lower gyromagnetic ratio with respect to that of 7Li (3.937 vs 10.398 x10-7 rad s-1 T-1) [43]. This results in narrower lineshapes making it easier to identify individual chemical environments in a sample. This technique was used by Zheng et al. to observe a peak attributed to a lithiated polymer-ceramic interface in a PEO-LiClO4 sample containing LLZO particles, an active ceramic [114].

⁶Li NMR is used in the analysis of solid-state polymer electrolytes to track the motional pathways of lithium in the electrolyte layer. This is done by cycling against ⁶Li foils such that the regions that experience ⁶Li enrichment post-cycling are identified as being a part of the lithium conduction pathway. This is because, during cycling, ⁶Li ions are stripped from the foil and travel through the electrolyte. These replace existing ⁷Li ions in the polymer matrix and/or ceramic and leave a trail of ⁶Li-enhanced regions showing the lithium migration pathway through the electrolyte (Figure 21) [130]. The main strength of this method is that the regions involved in lithium conduction can be observed directly. However, this technique is most effective in systems where motion between domains (i.e. lithium in the polymer and lithium in the ceramic) is limited as some lithium exchange can occur under ambient conditions and would result in a slight ⁶Li enrichment of the whole system.



Figure 21: ⁶Li foil cycling experiment performed on a PEO-LiTFSI system containing LLZO (14.1 T, 25 kHz MAS). Reprinted with permission from [130] Copywrite 2014 Wiley and Sons.

This experiment has been performed by several researchers using different polymer ceramic blends [114, 131–135]. The exact conduction pathway seems to be dependent on many factors including: type of polymer used, type of ceramic used and amount of ceramic in the system. This is likely a result of the fact that it is possible for lithium to travel through the polymer only, through the interface that is produced when ceramic is introduced into a polymer matrix or through the ceramic additive only [104].

In this vein, it has been suggested that in systems which contain high quantities of ceramic, lithium conduction occurs primarily through the ceramic particles. This was observed by Zheng et al. in a PEO-LiClO₄ system containing 50 wt% LLZO, an active ceramic [114]. Yang et al. prepared polymer electrolytes from polyvinylidene fluoride-hexafluoropropylene and LiTFSI that contained 30 wt% Lio.33Lao.557Ti1-xAlxO3 nanowires [135]. Following cycling with 6Li foil, the majority of the lithium signal (87.9 mol% by peak area) was located in the ceramic [135]. At lower ceramic contents, lithium conduction was observed to be more likely to occur through the interface that forms as a result of interactions between ceramic additives and the polymer matrix. In a PEO-LiTFSI system containing 25 wt% of the active ceramic LiZr₂(PO₄)₃ (LZP), it was found that the most significant 6Li enrichment occurred in the disordered polymer environment that was believed to surround the ceramic particles [131]. Cycling a PEO-succinonitrile-LiTFSI system containing the active ceramic Li1+xAlxGe2-x(PO4)3 (LAGP) against 6Li foils revealed the appearance of a new lithium environment whose integrated intensity increased with increasing LAGP doping suggesting that lithium conductivity occurs through this interfacial environment [132]. It is believed that lithium conduction occurs primarily through the polymer-ceramic interface at lower levels of ceramic doping as there is not sufficient ceramic volume to form a continuous ceramic network through the sample. At even lower ceramic content, lithium conduction was found to occur primarily through the polymer matrix. This was demonstrated via a 6Li foil cycling experiment by Xu et al. who used a PEO-LiTFSI system containing 10 wt% of the active ceramic Li_{3/8}Sr_{7/16}Zr_{1/4}O₃ (LSTZ) and Yang et al. who used a PAN-LiClO4 system containing 5 % LLZO nanowire [133, 134]. These experiments suggest that cycling a system against an 6Li foil is an effective way of identifying ion conduction pathways in hybrid electrolytes with various levels of ceramic loading. It is anticipated that similar results could be obtained using ⁶Li-enriched ceramics as changes in spectral intensity would indicate whether/to what extent these species participate in ion transport.

3. Future Work

1125

1126

1127

1128

1129

1130

1131

1132

1133

1134

1135

1136

1137

1138

1139

1140

1141

1142

1143

1144

1145

1146

1147

1148 1149

1150

1151

1152

1153

1154

1155

1156

1157

1158

1159

1160

1161

1162

1163 1164 Despite the advantages of NMR spectroscopy for the analysis polymer and hybrid electrolytes, improvements can still be made to better characterize these materials. To this end, an additional technique, fast field cycling NMR relaxometry, in which the variance in T₁ relaxation changes with changes in the magnetic field is used to calculate correlation times and surface diffusion associated with mobile species will be discussed here. This has had limited use in the analysis of polymer or hybrid electrolytes. However, this technique has been previously used to analyze segmental motion in polymeric materials and ion mobility in confined ionogels [136–138] and therefore has the potential to be employed in future studies in this field. These techniques can be tailored to selectively analyze specific chemical environments in a sample via sample synthesis or experimental setup allowing for even further selectivity during analysis.

Future work in the analysis of polymer and hybrid electrolytes for use in all-solid-state batteries could also focus on sodium-based batteries as the high availability and high energy density of sodium is creating increased interest in these devices. However, the higher quadrupole moment, relative to Li, can complicate the analysis of these systems by NMR spectroscopy. Future studies to investigate the ion mobility in and the molecular structure of sodium electrolytes could include NMR techniques such as multiple quantum magic angle spinning and satellite transition magic angle spinning which are specifically used to determine the number of sites present, along with their quadrupole parameters. These experiments would provide information on the nuclear environments of sodium species and inform lineshape fitting. Quadrupolar lineshape fitting could then be used to determine the impacts of electrolyte structure and external factors such as sample temperature on nuclear environments and molecular dynamics in these electrolytes.

4. Conclusions

The above examples show that solid-state NMR spectroscopy is a useful method for the analysis of molecular structure and ion dynamics in solid polymer and hybrid electrolytes. PFG NMR, which is commonly used to measure transference number in electrolyte systems, was shown to be good at characterizing local-scale ion mobility but typically worse than EIS-based measurements at describing long-range diffusion as it cannot distinguish between free ions and aggregates. Although not widely used in the analysis of solid polymer electrolytes, electrophoretic NMR is an experimentally demanding method to obtain species-specific transference numbers with accuracy that is not limited to dilute solutions. The ability of NMR based techniques to accurately describe local-scale motions that are not necessarily correlated with long-range processes can be observed in the use of variable temperature-assisted techniques for the quantification of mobility and the calculation of site-specific activation energies: T₁ relaxation, linewidth analysis and EXSY. Solid-state NMR can also be used to determine molecular structure and mobility simultaneously. This has been done via cross polarization and isotope replacement experiments. All things considered, solid-state NMR, alone or coupled with electrochemical analysis, is a powerful technique for characterizing molecular structure and ion mobility in polymer and hybrid electrolyte materials

Supplementary Materials: The following are available online at www.mdpi.com/xxx/s1, Table S1: Requirements for the analysis of solid polymer electrolytes using the NMR spectroscopy experiments that are presented in the text

Author Contributions: Conceptualization, G.F. and M.D.; writing—original draft preparation, G.F.; writing—review and editing, N.V., D.L., C.M., N.D. and M.D.; supervision, M.D.; project administration, D.L. and M.D.; funding acquisition, M.D. All authors have read and agreed to the published version of the manuscript.

1213 1214 1215 1216		Funding: This research was funded by National Sciences and Engineering Research Council of Canada (NSERC) and Total Canada Inc, NSERC Collaborative Research and Development grant number: RDCPJ 528052-18
1217		Data Availability Statement: This study did not generate any data.
1218		Conflicts of Interest: The authors declare no conflict of interest.
1219	Refere	ences
1220 1221	1.	Xia S, Wu X, Zhang Z, et al (2019) Practical Challenges and Future Perspectives of All-Solid-State Lithium-Metal Batteries. Chem 5:753–785. https://doi.org/10.1016/j.chempr.2018.11.013
1222 1223	2.	Kerman K, Luntz A, Viswanathan V, et al (2017) Review — Practical challenges hindering the development of solid state Li ion batteries. J Electrochem Soc 164:A1731–A1744. https://doi.org/10.1149/2.1571707jes
1224 1225	3.	Yao P, Yu H, Ding Z, et al (2019) Review on Polymer-Based Composite Electrolytes for Lithium Batteries. Front Chem 7:1–17. https://doi.org/10.3389/fchem.2019.00522
1226 1227	4.	Bucharsky EC, Schell KG, Hupfer T, et al (2016) Thermal properties and ionic conductivity of Li1,3Ti1,7Al0,3(PO4)3 solid electrolytes sintered by field-assisted sintering. Ionics (Kiel) 22:1043–1049. https://doi.org/10.1007/s11581-015-1628-3
1228 1229	5.	Hupfer T, Bucharsky EC, Schell KG, et al (2016) Evolution of microstructure and its relation to ionic conductivity in Li1+xAlxTi2-x(PO4)3. Solid State Ionics 288:235–239. https://doi.org/10.1016/j.ssi.2016.01.036
1230 1231	6.	Hanghofer I, Gadermaier B, Wilkening A, et al (2019) Lithium ion dynamics in LiZr2(PO4)3 and Li1.4Ca0.2Zr1.8(PO4)3. Dalt Trans 48:9376–9387. https://doi.org/10.1039/c9dt01786k
1232 1233 1234	7.	Li W, Sun C, Jin J, et al (2019) Realization of the Li + domain diffusion effect via constructing molecular brushes on the LLZTO surface and its application in all-solid-state lithium batteries . J Mater Chem A 7:27304–27312. https://doi.org/10.1039/c9ta10400c
1235 1236	8.	Kato Y, Hori S, Saito T, et al (2016) High-power all-solid-state batteries using sulfide superionic conductors. Nat Energy 1:1–7. https://doi.org/10.1038/nenergy.2016.30
1237 1238	9.	Epp V, Ma Q, Hammer EM, et al (2015) Very fast bulk Li ion diffusivity in crystalline Li1.5Al0.5Ti1.5(PO4)3 as seen using NMR relaxometry. Phys Chem Chem Phys 17:32115–32121. https://doi.org/10.1039/c5cp05337d
1239 1240 1241	10.	Yu X, Manthiram A (2020) A Long-cycle-life All-solid-state Lithium Battery with a Ceramic-polymer Composite Electrolyte A Long-cycle-life All-solid-state Lithium Battery with a Ceramic- polymer Composite Electrolyte. ACS Appl Energy Mater. https://doi.org/10.1021/acsaem.9b02547
1242 1243	11.	Tominaga Y, Yamazaki K, Nanthana V (2015) Effect of anions on lithium ion conduction in poly(ethylene carbonate)-based polymer electrolytes. J Electrochem Soc 162:A3133–A3136. https://doi.org/10.1149/2.0211502jes
1244 1245	12.	Chen L, Li Y, Li SP, et al (2018) PEO/garnet composite electrolytes for solid-state lithium batteries: From "ceramic-in-polymer" to "polymer-in-ceramic." Nano Energy 46:176–184. https://doi.org/10.1016/j.nanoen.2017.12.037
1246 1247	13.	Bonizzoni S, Ferrara C, Berbenni V, et al (2019) NASICON-type polymer-in-ceramic composite electrolytes for lithium batteries. Phys Chem Chem Phys 21:6142–6149. https://doi.org/10.1039/c9cp00405j
1248	14.	Yan C, Zhu P, Jia H, et al (2020) Garnet-rich composite solid electrolytes for dendrite-free, high-rate, solid-state

- 1249 lithium-metal batteries. Energy Storage Mater 26:448–456. https://doi.org/10.1016/j.ensm.2019.11.018
- 1250 15. Liu W, Lee SW, Lin D, et al (2017) Enhancing ionic conductivity in composite polymer electrolytes with well-aligned 1251 ceramic nanowires. Nat Energy 2:17035. https://doi.org/10.1038/nenergy.2017.35
- Boaretto N, Meabe L, Martinez-Ibañez M, et al (2020) Review Polymer Electrolytes for Rechargeable Batteries: From
 Nanocomposite to Nanohybrid. J Electrochem Soc 167:070524. https://doi.org/10.1149/1945-7111/ab7221
- 1254 17. Liang M, Liu Y, Xiao B, et al (2018) An analytical model for the transverse permeability of gas diffusion layer with electrical
 1255 double layer effects in proton exchange membrane fuel cells. Int J Hydrogen Energy 43:17880–17888.
 1256 https://doi.org/10.1016/j.ijhydene.2018.07.186
- 1257 18. Liang M, Fu C, Xiao B, et al (2019) A fractal study for the effective electrolyte diffusion through charged porous media. Int J
 1258 Heat Mass Transf 137:365–371. https://doi.org/10.1016/j.ijheatmasstransfer.2019.03.141
- 1259 19. West K, Zachau-Christiansen B, Jacobsen T, et al (1988) Poly(Ethylene Oxide)-Sodium Perchlorate Electrolytes in
 1260 Solid-State Sodium Cells. Br Polym J 20:243–246. https://doi.org/10.1002/pi.4980200315
- Wang Y, Song S, Xu C, et al (2019) Development of solid-state electrolytes for sodium-ion battery–A short review. Nano
 Mater Sci 1:91–100. https://doi.org/10.1016/j.nanoms.2019.02.007
- 1263 21. Colò F, Bella F, Nair JR, et al (2015) Cellulose-based novel hybrid polymer electrolytes for green and efficient Na-ion
 1264 batteries. Electrochim Acta 174:185–190. https://doi.org/10.1016/j.electacta.2015.05.178
- Hashmi SA, Chandra S (1995) Experimental investigations on a sodium-ion-conducting polymer electrolyte based on
 poly(ethylene oxide) complexed with NaPF6. Mater Sci Eng B 34:18–26. https://doi.org/10.1016/0921-5107(95)01219-2
- 1267 23. Luo H, Liang X, Wang L, et al (2014) Highly mobile segments in crystalline poly(ethylene oxide) 8:NaPF6 electrolytes
 1268 studied by solid-state NMR spectroscopy. J Chem Phys 140:. https://doi.org/10.1063/1.4865109
- Guo M, Zhang M, He D, et al (2017) Comb-like solid polymer electrolyte based on polyethylene glycol-grafted sulfonated
 polyether ether ketone. Electrochim Acta 255:396–404. https://doi.org/10.1016/j.electacta.2017.10.033
- Bhide A, Hariharan K (2008) Composite polymer electrolyte based on (PEO)6:NaPO3 dispersed with BaTiO3. Polym Int
 57:523–529. https://doi.org/10.1002/pi
- 1273 26. Zhang Q, Liu K, Ding F, Liu X (2017) Recent advances in solid polymer electrolytes for lithium batteries. Nano Res
 10:4139–4174. https://doi.org/10.1007/s12274-017-1763-4
- 1275 27. Xu K (2014) Electrolytes and interphases in Li-ion batteries and beyond. Chem Rev 114:11503–11618.
 1276 https://doi.org/10.1021/cr500003w
- Pecher O, Carretero-Gonzalez J, Griffith KJ, Grey CP (2017) Materials' methods: NMR in battery research. Chem Mater
 29:213–242. https://doi.org/10.1021/acs.chemmater.6b03183
- 1279 29. Keeler J (2002) Understanding NMR Spectroscopy, second. Cambridge University Press, Cambridge, UK
- Roach DJ, Dou S, Colby RH, Mueller KT (2012) Nuclear magnetic resonance investigation of dynamics in poly(ethylene
 oxide)-based lithium polyether-ester-sulfonate ionomers. J Chem Phys 136:014510. https://doi.org/10.1063/1.3669449
- 1282 31. Daigle J-C, Arnold A, Vijh A, Zaghib K (2018) Solid-State NMR Study of New Copolymers as Solid Polymer Electrolytes.

- 1283 Magnetochemistry 4:13. https://doi.org/10.3390/magnetochemistry4010013
- Morales DJ, Greenbaum S (2020) NMR Investigations of Crystalline and Glassy Solid Electrolytes for Lithium Batteries: A
 Brief Review. Int J Mol Sci 21:3402. https://doi.org/10.3390/ijms21093402
- 33. Zujovic Z, Kilmartin PA, Travas-sejdic J (2020) The Applications of Solid-State NMR to Conducting Polymers . The Special
 Case on Polyaniline. Molecules 25:444
- Abbrent S, Greenbaum SG (2010) Using nuclear magnetic resonance spectroscopy in polymer electrolyte research. In:
 Polymer Electrolytes Fundamentals and Applications. Woodhead publishing series in electronic and optical materials, pp
 278–313
- 35. Price W (1997) Pulsed-Field Gradient Nuclear Magnetic Resonance as a Tool for Studying Translational Diffusion: Part 1.
 Basic Theory. pp 299–336
- Sun B, Mindemark J, Morozov E V., et al (2016) Ion transport in polycarbonate based solid polymer electrolytes:
 Experimental and computational investigations. Phys Chem Chem Phys 18:9504–9513. https://doi.org/10.1039/c6cp00757k
- 1295 37. Liu X, Ding G, Zhou X, et al (2017) An interpenetrating network poly(diethylene glycol carbonate)-based polymer 1296 electrolyte for solid state lithium batteries. J Mater Chem A 5:11124–11130. https://doi.org/10.1039/c7ta02423a
- 1297 38. Shah FU, Gnezdilov OI, Gusain R, Filippov A (2017) Transport and Association of Ions in Lithium Battery Electrolytes on Glycol Ether Halogen-Free Orthoborate Rep 1298 Based Mixed with Ionic Liquid. Sci 7:1-13. https://doi.org/10.1038/s41598-017-16597-7 1299
- 39. Stejskal EO, Tanner JE (1965) Spin diffusion measurements: Spin echoes in the presence of a time-dependent field gradient.
 J Chem Phys 42:288–292. https://doi.org/10.1063/1.1695690
- 40. Cotts RM, Hoch MJR, Sun T, Markert JT (1989) Pulsed field gradient stimulated echo methods for improved NMR diffusion
 measurements in heterogeneous systems. J Magn Reson 83:252–266. https://doi.org/10.1016/0022-2364(89)90189-3
- 1304 41. Tanner JE (1970) Use of the stimulated echo in nmr diffusion studies. J Chem Phys 52:2523–2526.
 1305 https://doi.org/10.1063/1.1673336
- Engelke S, Marbella LE, Trease NM, et al (2019) Three-dimensional pulsed field gradient NMR measurements of
 self-diffusion in anisotropic materials for energy storage applications. Phys Chem Chem Phys 21:4538–4546.
 https://doi.org/10.1039/c8cp07776b
- Harris RK, Becker ED, Goodfellow R, Granger P (2002) NMR nomenclature: nuclear spin properties and conventions for
 chemical shifts. IUPAC recommendations 2001. Magn Reson Chem 40:489–505. https://doi.org/10.1002/mrc.1042
- 131144.Adebahr J, Best AS, Byrne N, et al (2003) Ion transport in polymer electrolytes containing nanoparticulate TiO2: The1312influence of polymer morphology. Phys Chem Chem Phys 5:720–725. https://doi.org/10.1039/b208454f
- Hosseinioun A, Nürnberg P, Schönhoff M, et al (2019) Improved lithium ion dynamics in crosslinked PMMA gel polymer
 electrolyte. RSC Adv 9:27574–27582. https://doi.org/10.1039/c9ra05917b
- 46. Foran G, Mankovsky D, Verdier N, et al (2020) The Impact of Absorbed Solvent on the Performance of Solid Polymer
 Electrolytes for Use in Solid-State Lithium Batteries. iScience 23

- Greenbaum SG (1993) NMR studies of ion mobility and association in polyether-based polymer electrolytes. Polym Adv
 Technol 4:172–178. https://doi.org/10.1002/pat.1993.220040217
- Yang L, Jiang Y, Liang X, et al (2020) Novel sodium-poly(tartaric acid)borate-based single-ion conducting polymer
 electrolyte for sodium-metal batteries. ACS Appl Energy Mater 3:10053–10060. https://doi.org/10.1021/acsaem.0c01756
- 49. Verdier N, Lepage D, Zidani R, et al (2020) Crosslinked polyacrylonitrile-based elastomer used as gel polymer electrolyte
 in Li-ion battery applications. Appl Energy Mater 3:1099–1110. https://doi.org/10.1021/acsaem.9b02129
- 132350.Fong KD, Self J, Diederichsen KM, et al (2019) Ion Transport and the True Transference Number in Nonaqueous1324Polyelectrolyte Solutions for Lithium Ion Batteries. ACS Cent Sci 5:1250–1260. https://doi.org/10.1021/acscentsci.9b00406
- 1325 51. Mindemark J, Lacey MJ, Bowden T, Brandell D (2018) Beyond PEO—Alternative host materials for Li+-conducting solid
 1326 polymer electrolytes. Prog Polym Sci 81:114–143. https://doi.org/10.1016/j.progpolymsci.2017.12.004
- 1327 52. Evans J, Vincent CA, Bruce PG (1987) Electrochemical measurement of transference numbers in polymer electrolytes.
 1328 Polymer (Guildf) 28:2324–2328. https://doi.org/10.1016/0032-3861(87)90394-6
- 1329 53. Pesko DM, Timachova K, Bhattacharya R, et al (2017) Negative Transference Numbers in Poly(ethylene oxide)-Based
 1330 Electrolytes. J Electrochem Soc 164:E3569–E3575. https://doi.org/10.1149/2.0581711jes
- Balsara NP, Newman J (2015) Relationship between Steady-State Current in Symmetric Cells and Transference Number of 1331 54. Electrolytes Comprising Univalent and Multivalent Ions. I Electrochem Soc 162:A2720-A2722. 1332 https://doi.org/10.1149/2.0651514jes 1333
- 1334 55. Pesko D (2018) Complete Electrochemical Characterization of Ion Transport in Polumer Electrolytes. University of
 1335 California, Berkeley
- 1336 56. Hittorf W (1853) Ueber die Wanderungen der lonen Wahrend der Electrolyse. Ann Phys 165:177–211.
 1337 https://doi.org/10.1002/andp.18531650602
- Bruce PG, Hardgrave MT, Vincent CA (1992) The determination of transference numbers in solid polymer electrolytes
 using the Hittorf method. Solid State Ionics 53–56:1087–1094. https://doi.org/10.1016/0167-2738(92)90295-Z
- Kaneko F, Wada S, Nakayama M, et al (2009) Dynamic transport in li-conductive polymer electrolytes plasticized with
 poly(ethylene glycol)-borate/aluminate ester. ChemPhysChem 10:1911–1915. https://doi.org/10.1002/cphc.200900191
- 1342 59. Chintapalli M, Timachova K, Olson KR, et al (2016) Relationship between Conductivity, Ion Diffusion, and Transference
 1343 Number in Perfluoropolyether Electrolytes. Macromolecules 49:3508–3515. https://doi.org/10.1021/acs.macromol.6b00412
- 134460.Tominaga Y, Yamazaki K (2014) Fast Li-ion conduction in poly(ethylene carbonate)-based electrolytes and composites1345filled with TiO2 nanoparticles. Chem Commun 50:4448–4450. https://doi.org/10.1039/c3cc49588d
- 1346 61. Timachova K, Sethi GK, Bhattacharya R, et al (2019) Ion diffusion across a disorder-to-order phase transition in a
 1347 poly(ethylene oxide)-: B -poly(silsesquioxane) block copolymer electrolyte. Mol Syst Des Eng 4:357–364.
 1348 https://doi.org/10.1039/c8me00077h
- Cheung IW, Chin KB, Greene ER, et al (2003) Electrochemical and solid state NMR characterization of composite
 PEO-based polymer electrolytes. Electrochim Acta 48:2149–2156. https://doi.org/10.1016/S0013-4686(03)00198-1

- Bhattacharja S, Smoot SW, Whitmore DH (1986) Cation and Anion Diffusion in the Amorphous Phase of the Polymer
 Electrolyte (PEO)8LiCF3SO3. Solid State Ionics 18–19:306–314. https://doi.org/10.1017/CBO9781107415324.004
- Gorecki W, Donoso P, Berthier C, et al (1988) NMR, DSC and conductivity study of the polymer solid electrolytes P(EO)
 (LiCp+1F2p+3SO3)x. Solid State Ionics 28–30:1018–1022. https://doi.org/10.1016/0167-2738(88)90323-2
- Al-Salih H, Huang A, Yim C-H, et al (2020) A Polymer-Rich Quaternary Composite Solid Electrolyte for Lithium Batteries. J
 Electrochem Soc 167:070557. https://doi.org/10.1149/1945-7111/ab7fb8
- 1357 66. Zhang Z, Madsen LA (2014) Observation of separate cation and anion electrophoretic mobilities in pure ionic liquids. J
 1358 Chem Phys 140:. https://doi.org/10.1063/1.4865834
- Stilbs Ρ, 1359 67. Furó Ι (2006)Electrophoretic NMR. Curr Opin Colloid Interface Sci 11:3-6. https://doi.org/10.1016/j.cocis.2005.09.016 1360
- 1361 68. Pettersson E, Furó I, Stilbs P (2004) On experimental aspects of electrophoretic NMR. Concepts Magn Reson Part A Bridg
 1362 Educ Res 22:61–68. https://doi.org/10.1002/cmr.a.20012
- Rosenwinkel MP, Schönhoff M (2019) Lithium Transference Numbers in PEO/LiTFSA Electrolytes Determined by
 Electrophoretic NMR. J Electrochem Soc 166:A1977–A1983. https://doi.org/10.1149/2.0831910jes
- 1365 70. Harris RK (1983) Nuclear Magnetic Resonance Spectroscopy. Pitman Publishing INC, Marshfield, Massachesetts
- 1366 71. Foerster H, Struppe J, Steuernager S, et al (2009) Solid State NMR AVANCE Solids User Manual
- 1367 72. Jeon JD, Kwak SY (2006) Variable-temperature 7Li solid-state NMR investigation of Li-ion mobility and its correlation with
 1368 conductivity in pore-filling polymer electrolytes for secondary batteries. Macromolecules 39:8027–8034.
 1369 https://doi.org/10.1021/ma061521v
- 1370 73. Abragam A (1961) The Principles pf Nuclear Magnetism. Clarendon Press
- 1371 74. Stone NJ (2001) Table of nuclear magnetic dipole and electric quadrupole moments
- 1372 75. Kentgens APM (1997) A practival guide to solid-state NMR of half-integer quadrupolar nuclei with some applications to
 1373 disordered systems. Geoderma 80:271–306
- Lin CL, Kao HM, Wu RR, Kuo PL (2002) Multinuclear solid-state NMR, DSC, and conductivity studies of solid polymer
 electrolytes based on polyurethane/poly(dimethylsiloxane) segmented copolymers. Macromolecules 35:3083–3096.
 https://doi.org/10.1021/ma012012q
- 1377 77. Stallworth PE, Greenbaum SG, Croce F, et al (1995) Lithium-7 NMR and ionic conductivity studies of gel electrolytes based
 1378 on poly(methylmethacrylate). Electrochim Acta 40:2137–2141. https://doi.org/10.1016/0013-4686(95)00153-6
- 1379 78. Kumar B, Marsh R (1991) Polymer Batteries. SAE Trans 100:408–412
- Chen-Yang YW, Chen HC, Lin FJ, Chen CC (2002) Polyacrylonitrile electrolytes: 1. A novel high-conductivity composite 1380 79 150:327-335. polymer electrolyte based PAN, LiClO4 and α -Al2O3. Solid State Ionics 1381 on https://doi.org/10.1016/S0167-2738(02)00457-5 1382
- 138380.Diederichsen KM, Buss HG, McCloskey BD (2017) The Compensation Effect in the Vogel-Tammann-Fulcher (VTF)1384Equation for Polymer-Based Electrolytes. Macromolecules 50:3831–3840. https://doi.org/10.1021/acs.macromol.7b00423

- 1385 81. Keeler J (2004) Chapter 8. Relaxation. http://www-keeler.ch.cam.ac.uk/lectures/understanding/chapter_8.pdf. Accessed 26
 1386 Feb 2019
- Peng J, Xiao Y, Clarkson DA, et al (2020) A Nuclear Magnetic Resonance Study of Cation and Anion Dynamics in
 Polymer–Ceramic Composite Solid Electrolytes. ACS Appl Polym Mater 2:1180–1189.
 https://doi.org/10.1021/acsapm.9b01068
- 1390 83. Schantz S, Kakihana M (1990) NMR study of a poly(propylene oxide)-NaCF3SO3 polymer electrolyte. Solid State Ionics
 1391 40-41:645-647. https://doi.org/10.1515/znb-1965-0902
- 139284.Pak YS, Adamic KJ, Greenbaum SG, et al (1991) Complex impedance and multifrequency 23Na NMR study of poly1393(propylene oxide) complexed with NaB (C6H5)4. Solid State Ionics 45:277–284. https://doi.org/10.1016/0167-2738(91)90162-5
- 1394 85. Daigle J-C, Arnold A, Vijh A, Zaghib K (2018) Solid-State NMR Study of New Copolymers as Solid Polymer Electrolytes.
 1395 Magnetochemistry 4:13. https://doi.org/10.3390/magnetochemistry4010013
- 1396 86. Forsyth M, MacFarlane DR, Meakin P, et al (1995) An nmr investigation of ionic structure and mobility in plasticized solid
 1397 polymer electrolytes. Electrochim Acta 40:2343–2347. https://doi.org/10.1016/0013-4686(95)00190-P
- Atta-ur-Rahman, Choudhary MI, Atia-tul-Wahab (2016) Spin-Echo and Polarization Transfer. In: Solving Problems with
 NMR Spectroscopy, second. Academic Press, pp 133–190
- 1400 88. Forsyth M, Jiazeng S, MacFarlane DR (2000) Novel high salt content polymer electrolytes based on high Tg polymers.
 1401 Electrochim Acta 45:1249–1254. https://doi.org/10.1016/S0013-4686(99)00328-X
- 1402 89. Carr HY, Purcell EM (1954) Effects of diffusion on free precession in nuclear magnetic resonance experiments. Phys Rev
 1403 94:630–638. https://doi.org/10.1103/PhysRev.94.630
- Meiboom S, Gill D (1958) Modified spin-echo method for measuring nuclear relaxation times. Rev Sci Instrum 29:688–691.
 https://doi.org/10.1063/1.1716296
- 1406 91. Donoso JP, Cavalcante MG, Bonagamba TJ, et al (1995) Magnetic resonance study of water absorption in some peo-lithium
 1407 salt polymer electrolytes. Electrochim Acta 40:2357–2360. https://doi.org/10.1016/0013-4686(95)00193-I
- Franco RWA, Donoso JP, Magon CJ, et al (2000) NMR and DSC study of polymer electrolyte-Carbon Black composites.
 Solid State Ionics 136–137:1181–1187. https://doi.org/10.1016/S0167-2738(00)00582-8
- 1410 93. Kwak GH, Tominaga Y, Asai S, Sumita M (2003) Effect of reaction kinetics of polymer electrolyte on the ion-conductive
 1411 behavior for poly(oligo oxyethylene methacrylate)-LiTFSI mixtures. J Appl Polym Sci 89:2149–2156.
 1412 https://doi.org/10.1002/app.12375
- 1413 94. Kidd BE, Forbey SJ, Steuber FW, et al (2015) Multiscale Lithium and Counterion Transport in an Electrospun Polymer-Gel
 1414 Electrolyte. Macromolecules 48:4481–4490. https://doi.org/10.1021/acs.macromol.5b00573
- Huang B, Wang Z, Chen L, et al (1996) The Mechanism of Lithium Ion Transport in Polyacrylonitrile-Based Polymer
 Electrolytes. Solid State Ionics 91:279–284. https://doi.org/10.1016/0921-5107(89)90175-X
- 1417 96. Chung SH, Wang Y, Persi L, et al (2001) Enhancement of ion transport in polymer electrolytes by addition of nanoscale
 1418 inorganic oxides. J Power Sources 97–98:644–648. https://doi.org/10.1016/S0378-7753(01)00748-0

- 1419 97. Liu TM, Saikia D, Ho SY, et al (2017) High ion-conducting solid polymer electrolytes based on blending hybrids derived
 1420 from monoamine and diamine polyethers for lithium solid-state batteries. RSC Adv 7:20373–20383.
 1421 https://doi.org/10.1039/c7ra01542a
- 1422 98. Munoz S, Greenbaum S (2018) Review of recent nuclear magnetic resonance studies of ion transport in polymer electrolytes.
 1423 Membranes (Basel) 8:1–23. https://doi.org/10.3390/membranes8040120
- Wong S, Zax DB (1997) What do NMR linewidths tell us? Dynamics of alkali cations in a PEO-based nanocomposite
 polymer electrolyte. Electrochim Acta 42:3513–3518. https://doi.org/10.1016/S0013-4686(97)00040-6
- 1426 100. Forsyth M, Smith ME, Meakin P, MacFarlane DR (1994) 23Na NMR in urethane cross-linked polyether solid polymer
 1427 electrolytes. J Polym Sci Part B Polym Phys 32:2077–2084. https://doi.org/10.1002/polb.1994.090321214
- 1428 101. Berman MB, Greenbaum SG (2015) NMR studies of solvent-free ceramic composite polymer electrolytes—A brief review.
 1429 Membranes (Basel) 5:915–923. https://doi.org/10.3390/membranes5040915
- 1430 102. Menkin S, Lifshitz M, Haimovich A, et al (2019) Evaluation of ion-transport in composite polymer-in-ceramic electrolytes.
 1431 Case study of active and inert ceramics. Electrochim Acta 304:447–455. https://doi.org/10.1016/j.electacta.2019.03.006
- 1432 103. Xu Z, Yang T, Chu X, et al (2020) Strong Lewis Acid-base and Weak Hydrogen Bond Synergistically Enhancing Ionic
 1433 Conductivity of Poly (ethylene oxide)@ SiO 2 Electrolytes for High Rate-capability Li-metal Battery. ACS Appl Mater
 1434 Interfaces 12:10341–10329. https://doi.org/10.1021/acsami.9b20128
- 1435104.Zheng J, Hu YY (2018) New Insights into the Compositional Dependence of Li-Ion Transport in Polymer-Ceramic1436Composite Electrolytes. ACS Appl Mater Interfaces 10:4113–4120. https://doi.org/10.1021/acsami.7b17301
- 1437 105. Lago N, Garcia-Calvo O, Lopezdelamo JM, et al (2015) All-Solid-State Lithium-Ion Batteries with Grafted Ceramic
 1438 Nanoparticles Dispersed in Solid Polymer Electrolytes. ChemSusChem 8:3039–3043. https://doi.org/10.1002/cssc.201500783
- Spindler R, Shriver DF (1988) Investigations of a Siloxane-Based Polymer Electrolyte Employing 13C, 29Si, 7Li, and 23Na
 Solid-State NMR Spectroscopy. J Am Chem Soc 110:3036–3043. https://doi.org/10.1021/ja00218a006
- 107. Bain AD (2003)Chemical exchange in NMR. Prog Nucl Magn Reson Spectrosc 43:63-103. 1441 https://doi.org/10.1016/j.pnmrs.2003.08.001 1442
- 1443 108. Bain AD (2008) Chemical Exchange. Annu Reports NMR Spectrosc 63:23-48. https://doi.org/10.1016/S0066-4103(07)63002-6
- 1444109.Smiley DL, Goward GR (2016) Ex Situ 23Na Solid-State NMR Reveals the Local Na-Ion Distribution in Carbon-Coated1445Na2FePO4F during Electrochemical Cycling. Chem Mater 28:7645–7656. https://doi.org/10.1021/acs.chemmater.6b02539
- 1446 110. Autschbach J, Zheng S, Schurko, Robert W (2010) Analysis of Electric Field Gradient Temsors at Quadrupolar Nuceli in
 1447 Common Structural Motifs. Concepts Magn Reson A 36:84–126. https://doi.org/10.1002/cmr.a.20155
- 1448 111. Foran GY, Goward GR Site-Speci fi c Proton Dynamics in Indium-Doped Tin Pyrophosphate Published as part of The
 1449 Journal of Physical Chemistry virtual special issue " Hellmut Eckert Festschrift " . J Phys Chem C.
 1450 https://doi.org/10.1021/acs.jpcc.0c09290
- 112. Liu Q, Li C, Wei L, et al (2014) The phase structure, chain diffusion motion and local reorientation motion: 13C Solid-state 1451 NMR study on the highly-crystalline solid polymer electrolytes. Polymer (Guildf) 55:5454-5459. 1452 1453 https://doi.org/10.1016/j.polymer.2014.08.055

- 1454113.Yang LY, Wei DX, Xu M, et al (2014) Transferring lithium ions in nanochannels: A PEO/Li+ solid polymer electrolyte1455design. Angew Chemie Int Ed 53:3631–3635. https://doi.org/10.1002/anie.201307423
- 1456114.Zheng J, Tang M, Hu Y-Y (2016)Lithium Ion Pathway within Li 7 La 3 Zr 2 O 12 -Polyethylene Oxide Composite1457Electrolytes . Angew Chemie 128:12726–12730. https://doi.org/10.1002/ange.201607539
- 1458 115. Zagórski J, López Del Amo JM, Cordill MJ, et al (2019) Garnet-Polymer Composite Electrolytes: New Insights on Local
 1459 Li-Ion Dynamics and Electrodeposition Stability with Li Metal Anodes. ACS Appl Energy Mater 2:1734–1746.
 1460 https://doi.org/10.1021/acsaem.8b01850
- 1461 116. Kolodziejski W, Klinowski J (2002) Kinetics of Cross-Polarization in Solid-State NMR : A Guide for Chemists. Chem Rev
 1462 102:613–628. https://doi.org/10.1021/cr000060n
- 1463 117. Levitt MH (2008) Spin Dynamics: Basics of Nuclear Magnetic Resonance, second. John Wiley & Sons
- 1464 118. Hartmann SR, Hahn EL (1962) Nuclear double resonance in the rotating frame. Phys Rev 128:2042–2053.
 1465 https://doi.org/10.1103/PhysRev.128.2042
- 1466 119. LIM K, Grey C (1999) Triple Quantum Cross-Polarization Nmr of 1 H/27 Al and 19 F/23 Na Spin Systemsin Solid. Chem
 1467 Phys Lett 312:45–56
- 1468 120. Puls SP, Eckert H (2006) Site discrimination in mixed-alkali glasses studied by cross-polarization NMR. J Phys Chem B
 1469 110:14253–14261. https://doi.org/10.1021/jp0622511
- 1470 121. Fu X Bin, Yang G, Wu JZ, et al (2018) Fast Lithium-Ion Transportation in Crystalline Polymer Electrolytes. ChemPhysChem
 1471 19:45–50. https://doi.org/10.1002/cphc.201701092
- 1472 122. Foran GY, Brouwer DH, Goward GR (2017) Quantifying Site-Specific Proton Dynamics in Phosphate Solid Acids by ¹H
 1473 Double Quantum NMR Spectroscopy. J Phys Chem C 121:. https://doi.org/10.1021/acs.jpcc.7b06034
- 1474 123. Gullion T, Schaefer J (1989) Rotational echo double resonance NMR. J Magn Reson 81:196–200.
 1475 https://doi.org/https://doi.org/10.1016/0022-2364(89)90280-1
- 1476 124. Eckert H (2010) Short and medium range order in ion-conducting glasses studied by modern solid state NMR techniques.
 1477 Zeitschrift fur Phys Chemie 224:1591–1653. https://doi.org/10.1524/zpch.2010.0030
- 1478 125. Garbow JR, Gullion T (1991) Improvements in REDOR NMR spectroscopy. Minimizing resonance-offset effects. J Magn
 1479 Reson 95:442–445. https://doi.org/10.1016/0022-2364(91)90236-M
- Bertmer M, Eckert H (1999) Dephasing of spin echoes by multiple heteronuclear dipolar interactions in rotational echo 1480 126. double resonance NMR experiments. Solid State Nucl Magn Reson 15:139-152. 1481 https://doi.org/10.1016/S0926-2040(99)00050-8 1482
- 1483 127. Chan JCC, Eckert H (2000) Dipolar Coupling Information in Multispin Systems: Application of a Compensated REDOR
 1484 NMR Approach to Inorganic Phosphates. J Magn Reson 147:170–178. https://doi.org/10.1006/jmre.2000.2191
- 1485 128. Voigt N, Van Wüllen L (2012) The mechanism of ionic transport in PAN-based solid polymer electrolytes. Solid State Ionics
 1486 208:8–16. https://doi.org/10.1016/j.ssi.2011.11.031
- 1487 129. Voigt N, Van Wüllen L (2014) The effect of plastic-crystalline succinonitrile on the electrolyte system PEO:LiBF4: Insights

1488		from solid state NMR. Solid State Ionics 260:65-75. https://doi.org/10.1016/j.ssi.2014.03.009
1489 1490	130.	Zheng J, Tang M, Hu YY (2016) Lithium Ion Pathway within Li7La3Zr2O12-Polyethylene Oxide Composite Electrolytes. Angew Chemie - Int Ed 55:12538–12542. https://doi.org/10.1002/anie.201607539
1491 1492	131.	Wu N, Chien PH, Li Y, et al (2020) Fast Li+ Conduction Mechanism and Interfacial Chemistry of a NASICON/Polymer Composite Electrolyte. J Am Chem Soc 142:2497–2505. https://doi.org/10.1021/jacs.9b12233
1493 1494	132.	Liu M, Cheng Z, Ganapathy S, et al (2019) Tandem Interface and Bulk Li-Ion Transport in a Hybrid Solid Electrolyte with Microsized Active Filler. ACS Energy Lett 4:2336–2342. https://doi.org/10.1021/acsenergylett.9b01371
1495 1496	133.	Xu H, Chien PH, Shi J, et al (2019) High-performance all-solid-state batteries enabled by salt bonding to perovskite in poly(ethylene oxide). Proc Natl Acad Sci U S A 116:18815–18821. https://doi.org/10.1073/pnas.1907507116
1497 1498 1499	134.	Yang T, Zheng J, Cheng Q, et al (2017) Composite Polymer Electrolytes with Li7La3Zr2O12 Garnet-Type Nanowires as Ceramic Fillers: Mechanism of Conductivity Enhancement and Role of Doping and Morphology. ACS Appl Mater Interfaces 9:21773–21780. https://doi.org/10.1021/acsami.7b03806
1500 1501 1502	135.	Yang H, Bright J, Chen B, et al (2020) Chemical interaction and enhanced interfacial ion transport in a ceramic nanofiber-polymer composite electrolyte for all-solid-state lithium metal batteries. J Mater Chem A 8:7261–7272. https://doi.org/10.1039/c9ta12495k
1503 1504	136.	Martini F, Carignani E, Nardelli F, et al (2020) Glassy and Polymer Dynamics of Elastomers by 1H Field-Cycling NMR Relaxometry: Effects of Cross-Linking. Macromolecules 2:. https://doi.org/10.1021/acs.macromol.0c01439
1505 1506 1507	137.	Jayakody NK, Fraenza CC, Greenbaum SG, et al (2020) NMR Relaxometry and Diffusometry Analysis of Dynamics in Ionic Liquids and Ionogels for Use in Lithium-Ion Batteries. J Phys Chem B 124:6843–6856. https://doi.org/10.1021/acs.jpcb.0c02755
1508 1509 1510	138.	Rachocki A, Andrzejewska E, Dembna A, Tritt-Goc J (2015) Translational dynamics of ionic liquid imidazolium cations at solid/liquid interface in gel polymer electrolyte. Eur Polym J 71:210–220. https://doi.org/10.1016/j.eurpolymj.2015.08.001