

Polymerization of glycidyl methacrylate from the surface of cellulose nanocrystals for the elaboration of PLA-based nanocomposites

Manon Le Gars, Julien Bras, Hanène Salmi-Mani, Marisol Ji, Diana Dragoe, Sandra Domenek, Hajar Faraj, Naceur Belgacem, Philippe Roger

▶ To cite this version:

Manon Le Gars, Julien Bras, Hanène Salmi-Mani, Marisol Ji, Diana Dragoe, et al.. Polymerization of glycidyl methacrylate from the surface of cellulose nanocrystals for the elaboration of PLA-based nanocomposites. Carbohydrate Polymers, 2020, 234, pp.115899. 10.1016/j.carbpol.2020.115899. hal-03322807

HAL Id: hal-03322807 https://hal.science/hal-03322807

Submitted on 21 Jul 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial 4.0 International License

1 Polymerization of glycidyl methacrylate from the

2 surface of cellulose nanocrystals for the elaboration of

3 PLA-based nanocomposites

- 4 Manon Le Gars ^a (manon.le-gars@lgp2.grenoble-inp.fr), Julien Bras ^a
- 5 (julien.bras@grenoble-inp.fr), Hanène Salmi-Mani^b (hanene.salmi@u-psud.fr), Marisol Ji^b
- 6 (mji1119@hotmail.com), Diana Dragoe^b (diana.dragoe@u-psud.fr), Hajar Faraj^c
- 7 (hajar.faraj@agroparistech.fr), Sandra Domenek ^c (sandra.domenek@agroparistech.fr),
- 8 Naceur Belgacem^{a, d} (naceur.belgacem@pagora.grenoble-inp.fr), Philippe Roger^{b, 1}
- 9 (philippe.roger@u-psud.fr)
- 10 *a Univ. Grenoble Alpes, CNRS, Grenoble INP², LGP2, F-38000 Grenoble, France*
- 11 ^b Institut de Chimie Moléculaire et des Matériaux d'Orsay (ICMMO), UMR 8182, Université Paris Sud, CNRS,
- 12 Université Paris-Saclay, 91405 Orsay, France
- 13 ^c UMR Ingénierie Procédés Aliments, AgroParisTech, INRA, Université Paris Saclay, F-91300 Massy, France
- 14 ^d Institut Universitaire de France (IUF), 75000 Paris, France

15 Abstract

Cellulose nanocrystals (CNCs) are used to design nanocomposites because of their high aspect ratio 16 17 and their outstanding mechanical and barrier properties. However, the low compatibility of hydrophilic CNCs with hydrophobic polymers remains a barrier to their use in the nanocomposite field. To 18 19 improve this compatibility, poly(glycidyl methacrylate) (PGMA) was grafted from CNCs containing 20 α -bromoisobutyryl moieties *via* surface-initiated atom transfer radical polymerization. The novelty of 21 this research is the use of a reactive epoxy-containing monomer that can serve as a new platform for further modifications or crosslinking. Polymer-grafted CNC-PGMA-Br prepared at different 22 polymerization times were characterized by XRD, DLS, FTIR, XPS and elemental analysis. 23 Approximately 40% of the polymer at the surface of the CNCs was quantified after only 1 h of 24

¹ **Corresponding author** : Université Paris-Sud, 15 rue Georges Clémenceau, 91405 Orsay Cedex, France, +33 1 69 15 47 16

² Institute of Engineering Univ. Grenoble Alpes

polymerization. Finally, nanocomposites prepared with 10 wt% CNC-PGMA-Br as nanofillers in a
poly(lactic acid) (PLA) matrix exhibited an improvement in their compatibilization based on SEM
observation.

Keywords: Cellulose nanocrystals; Chemical grafting; Surface-initiated atom transfer radical polymerization; Poly(glycidyl methacrylate); Poly(lactic acid)-based nanocomposites;

47 **1. Introduction**

48 Because of its abundance and availability from a wide variety of sources, cellulose is currently a 49 polymer of choice in the field of bio-based materials. Recently, several novel nanomaterials have been 50 extracted from this natural biopolymer. Indeed, cellulose nanofibrils (CNFs) have been classically 51 obtained since the 1980s by applying a mechanical treatment to a cellulose suspension (Nechyporchuk 52 et al., 2016). Conversely, since the 1960s, CNCs are produced by performing an acid hydrolysis, meaning removing the amorphous part of cellulose (Habibi et al., 2010; Kargarzadeh et al., 2018). 53 54 Such nanomaterials are relevant for a large number of research fields, like nanocomposites (Ferreira et 55 al., 2017; Habibi, 2014; Kargarzadeh et al., 2018; Oksman et al., 2016), coatings (Ferrer et al., 2017; 56 Hubbe et al., 2017), packaging (Ferrer et al., 2017; Hubbe et al., 2017), and biomedical applications 57 (Domingues et al., 2014; Jorfi & Foster, 2015; Lin & Dufresne, 2014). They exhibit interesting 58 properties like biodegradability, renewability, and mechanical and barrier properties that endow them 59 with particular advantages. In the past decade, accelerated industrialization and commercialization of such cellulosic nanomaterials has occurred, in parallel with an ever-increasing demand from industry. 60

61 Among nanocelluloses, CNCs exhibit interesting properties. Acid hydrolysis of native cellulose from various sources (cotton, wood, natural fibres, etc.) using sulfuric acid H₂SO₄ leads to CNCs with 62 63 different dimensions and aspect ratios. The resulting sulfuric-acid-hydrolyzed CNCs hold sulfate half ester groups (-OSO3⁻) on their surface (Beck et al., 2015; Foster et al., 2018), with a surface charge 64 density generally in the range from 80 to 350 µmol.g⁻¹ (Foster et al., 2018; Reid et al., 2016). These 65 surface charges combined with their nanometric size — 150-500 nm in length (up to 1000 nm), 5-20 66 nm in width according to their source (Foster et al., 2018; Kargarzadeh et al., 2018) - induce 67 colloidal stability of aqueous suspensions (Beck et al., 2015; Foster et al., 2018). In addition to their 68 69 high aspect ratio, CNCs exhibit a high surface area (Foster et al., 2018; Natterodt et al., 2017), high 70 crystallinity (Klemm et al., 2011), and a large availability of hydroxyl groups on their surface (Foster 71 et al., 2018; Natterodt et al., 2017). Moreover, their rod-like shape, their high mechanical strength 72 (Young's modulus between 120 and 200 GPa) (Dufresne, 2018; Lin et al., 2012), and their 73 sustainability make them attractive materials as fillers in nanocomposites (Boujemaoui et al., 2017; E. 74 Espino-Pérez et al., 2016; Etzael Espino-Pérez et al., 2018; Oksman et al., 2016).

However, the hydrophilicity of CNCs – resulting from the three OH groups per anhydroglucose unit
 (AGU) – limits their dispersion in several polymer matrices, especially non-polar matrices. Moreover,
 CNCs begin to degrade at approximately 200-300°C (Moon et al., 2011), depending on their

78 morphology, crystallinity, and source. These two last points are challenging when such nanomaterials 79 are used for nanocomposite processing, where high temperatures are reached with expected well-80 dispersed nanofillers (Belgacem, 2008; Siqueira, Bras, & Dufresne, 2010). These challenges can be 81 overcome through chemical or physico-chemical modifications of CNCs (Eyley & Thielemans, 2014; 82 Habibi, 2014; Natterodt et al., 2017), by grafting single molecules (de Castro et al., 2016; Etzael 83 Espino-Pérez et al., 2014; Eyley & Thielemans, 2014) or polymers chains (Azzam et al., 2010; 84 Boujemaoui et al., 2017; Goffin et al., 2011) at the surface of CNCs, or by adsorbing various molecules, involving ionic or low-energy bonding phenomena (Abitbol, 2014; Kargarzadeh et al., 85 2018; Kedzior et al., 2017). 86

87 Chemical modifications are carried out by modifying multiple hydroxyl groups at the surface of CNCs 88 to provide the nanomaterials with specific properties. To improve the compatibility of CNCs with a 89 hydrophobic polymer matrix, grafting single molecules or polymer chains are classically described in 90 the literature and in reviews. Focusing on the second strategy, two major approaches are commonly 91 used to introduce polymeric chains at the surface of CNCs. In the grafting-onto strategy, CNCs, ether 92 pre-functionalized or not, are directly grafted with previously polymerized and characterized polymer 93 chains (Kloser & Gray, 2010; Sessini et al., 2018; Zhou et al., 2018), leading to limited surface 94 grafting density because of the steric hindrance between polymers. In the grafted-from approach — on 95 which this study focuses — monomers are polymerized from pre-functionalized CNCs with initiator 96 sites (Boujemaoui et al., 2017; Habibi et al., 2008; Morandi et al., 2009). This two-step strategy leads 97 to an overall controlled structure and higher surface grafting density because of the facilitated access to 98 the activated initiator sites on CNCs, although characterization of grafted polymer chains is more 99 challenging (Zhang et al., 2018). Ring-opening polymerization (ROP) (Goffin et al., 2011; Habibi et 100 al., 2008) and atom transfer radical polymerization (ATRP) (Kedzior et al., 2016; Morandi et al., 2009; 101 Zoppe et al., 2010) are the most common types of polymerization used in the grafting-from strategy. 102 Controlled surface-initiated ATRP (SI-ATRP) from the surface of CNCs has been described in the 103 literature (Boujemaoui, Mongkhontreerat, Malmström, & Carlmark, 2015; Kedzior et al., 2016; 104 Morandi et al., 2009; Zoppe et al., 2010). However, the major issues with SI-ATRP are the difficulty 105 in characterizing grafted polymers and recovery of the free homopolymer. Control of the 106 polymerization is generally studied using polymers obtained from a sacrificial initiator, from which the 107 kinetics of the polymerization is considered similar to polymerization from the surface of CNCs. By 108 recovering and characterizing the free homopolymer, information about the grafted chains can be

acquired (Hansson et al., 2011). It should be noted that this step of cleaning is challenging and crucialfor characterizing both grafted CNCs and free polymers.

111 The aim of this study is to graft polymer brushes of various lengths at the surface of CNCs via 112 grafting-from SI-ATRP. Numerous studies have focused on the polymerization of various polymers on 113 CNCs, mostly in order to compatibilize these nanomaterials with various polymer matrices. Recently, 114 Zoppe et al. studied the synthesis of poly(N,N-dimethylacrylamide) chains at the surface of CNCs and 115 carried out an alkaline hydrolysis to remove and analyze the polymerized chains (Zoppe et al., 2016). 116 Sessini et al. reported the polymerization via grafting-from of L-lactide and ε -caprolactone at the 117 surface of CNCs and studied the morphological, thermal, and mechanical properties of such modified 118 CNCs in various polymer matrices (Sessini et al., 2018).

119 The objective of the present study is to graft the poly(glycidyl methacrylate) (PGMA) obtained from 120 the polymerization of glycidyl methacrylate (GMA), an epoxy-functional and commercially available 121 monomer (Cañamero et al., 2004) on CNCs, and to produce poly(lactic acid) (PLA)-based 122 nanocomposites. The traditional method of polymerizing GMA in a controlled manner is by atom 123 transfer radical polymerization (ATRP), with the use of an initiator and a catalyst system (Cañamero et 124 al., 2004). These methods aim to control the polymerization behavior. PGMA was selected for this 125 study because of its hydrophobicity (Nyström et al., 2006) and the presence of the highly reactive epoxy functions, which can be an active attachment point for further modifications. To our knowledge, 126 127 such a strategy is new in the field of CNC modification and with respect to this reactive polymer at the 128 surface of CNCs. Control of the polymerization is essential to quantify the polymer and is conducted 129 through SI-ATRP, as mentioned previously. To the best of our knowledge, PGMA has never been 130 polymerized at the surface of CNCs via a grafting-from SI-ATRP approach. Martinez-Sanz et al. 131 grafted PGMA via a non-controlled polymerization applied on bacterial cellulose nanowhiskers for 132 PLA nanocomposites applications (Martínez-Sanz et al., 2013). Hansson et al. grafted various 133 polymers, including PGMA from a cellulosic filter paper substrate, via activators regenerated by 134 electron transfer (ARGET) ATRP to limit the use of reducing reagents and avoid the use of a totally 135 inert atmosphere (Hansson, Östmark, Carlmark & Malmström, 2009). Malmström et al. presented 136 different ways of functionalizing cellulose papers by controlling the surface grafting (Malmström & 137 Carlmark, 2012) and grafted PGMA via SI-ATRP but the grafting was done at the surface of cellulose 138 fibres to introduce a large amount of oxirane groups. More recently, Cheng et al. performed a similar SI-ATRP of GMA from a nanoporous cellulose gel (NCG) followed by a hydrophobic modification of
polymerized NCG to produce functional materials based on NCGs (Cheng, Wei, Zhang & Cai, 2018).

PLA was chosen in this study as an example of a hydrophobic polymer matrix. This bio-based polymer is interesting because of its biodegradability. However, to compete with the synthetic polymers usually used in the packaging field, for example, the barrier and mechanical properties of PLA need to be improved. This explains the many studies performed regarding the development of PLA-based nanocomposites, particularly the introduction on nanocelluloses as fillers (Etzael Espino-Pérez et al., 2018; Miao & Hamad, 2016; Robles et al., 2015).

147 In the present paper, an efficient SI-ATRP polymerization of GMA from the surface of CNCs is 148 described. The experiment method covers various steps. First, CNCs are functionalized with a-149 bromoisobutyryl bromide (BIB), a brominated initiator commonly used in ATRP (Cañamero et al., 150 2004; Morandi et al., 2009). Then, GMA is polymerized from these initiator sites, with challenges like 151 control and recovery of the homopolymer. Polymerized CNCs at different polymerization times are 152 characterized using various techniques, from bulk characterization (FTIR, elemental analysis, TGA) to 153 surface characterization (XPS). Finally, 10 wt% of the polymerized CNCs are introduced in a PLA 154 matrix, and the resulting nanocomposites are observed using microscopic technique in order to investigate the compatibilization between CNCs and PLA. 155

156

157 **2. Materials and methods**

158 **2.1. Materials**

159 Cellulose nanocrystals (CNCs) were produced from wood pulp and purchased from CelluForce 160 (Quebec, Canada), in spray-dried form. 4-(dimethylamino)pyridine (DMAP), triethylamine (TEA), αbromoisobutyryl bromide (BIB), ethyl α-bromoisobutyrate (EBIB), and N,N,N',N'',N''-161 pentamethyldiethylenetriamine (PMDETA) were supplied from Sigma-Aldrich Chimie (Saint-162 163 Quentin-Fallavier, France) and were used as received. Copper (I) bromide (CuBr) was purchased from Sigma-Aldrich Chimie. CuBr was purified by washing in glacial acetic acid for 24 h at ambient 164 165 temperature, filtered, rinsed extensively with ethanol and diethyl ether, dried under vacuum, and 166 stored in an inert atmosphere before use (McCaig et al., 2014). Glycidyl methacrylate (GMA) was 167 purchased from Fisher Scientific (France) and purified through a basic alumina column to remove stabilizers before use. N,N-Dimethylformamide (DMF) was purchased from Sigma-Aldrich Chimie, stored, and used in anhydrous conditions. Dichloromethane (DCM) and ethanol (EtOH) were purchased from Sigma-Aldrich Chimie and used as received.

171 **2.2.** Functionalization of CNC with α-Bromoisobutyryl Bromide

Functionalization of CNC with BIB was performed by esterification reaction according to the protocol 172 173 adapted from Morandi et al. (Morandi et al., 2009). This protocol is as follows. First, 1.0 g of dry 174 CNCs was dispersed in 100 mL of anhydrous DMF and an ultrasonic treatment was applied. Then, 125 175 mg of DMAP (1.02 mmol) was solubilized in 2 mL of anhydrous DMF and added to the CNC 176 suspension. Thereafter, 2.1 mL of TEA (14.9 mmol) was added, followed by 1.9 mL of BIB (14.9 177 mmol). The reaction was performed at room temperature for 24 h, under argon flow. At the end of the 178 reaction, the functionalized CNC-Br were washed by successive cycles of centrifugation (9000 rpm, 179 10', 5 °C): in DMF once, in DCM twice, in a mixture of DCM/EtOH (1/1, v/v) once, and in EtOH 180 twice. CNC-Br were then dried under vacuum.

181 2.3. SI-ATRP of Glycidyl Methacrylate on functionalized CNC-Br

182 The method for SI-ATRP of GMA onto CNCs was adapted from classical ATRP of this monomer 183 (Cañamero et al., 2004). First, 0.5 g of previously functionalized CNC-Br was redispersed in a Schlenk in 10 mL of anhydrous DMF and magnetically stirred under argon, before being treated with 184 ultrasound. Then, 0.054 mL of EBIB, 0.076 mL of PMDETA, and 4.8 mL of purified GMA were 185 186 successively added to the suspension ($[GMA]_0$: $[EBIB]_0$: $[PMDETA]_0$: $[CuBr]_0 = 100$:1:1:1). The 187 sacrificial EBIB was added to react as a sacrificial initiator, assuming that the polymerization of GMA 188 occurred from this initiator, in the same manner as from the surface of our CNC-Br. Next, 0.054 g of 189 CuBr was introduced quickly and at the last moment, to avoid oxidation, noticeable by a colour change. 190 A flow of argon was set up in the closed Schlenk under magnetic stirring. A total of 7 freeze-thaw 191 cycles were carried out to completely remove oxygen from the suspension. The mixture was then 192 magnetically stirred under argon at room temperature for 24 h. Study of the polymerization kinetics 193 was performed by collecting aliquots of the reaction media with a purged argon syringe. At the end of 194 the reaction, a small amount of DCM was added to recover all the mixture and a first centrifugation 195 cycle (9000 rpm, 15', 5 °C) was carried out. The supernatant containing PGMA polymerized from the 196 sacrificial initiator was recovered for characterization. The centrifuged part was further washed in 197 DCM with five cycles of centrifugation (9000 rpm, 15', 5 °C) to eliminate all the free homopolymer 198 and to only retrieve CNC-PGMA-Br. The solubilized PGMA homopolymer recovered in the DCM

supernatant was purified on a basic alumina column, precipitated in cold methanol, filtered, and driedunder vacuum.

201 2.4. Polymerization of homopolymer PGMA

The reference homopolymer PGMA was prepared by ATRP according to the previously described method. Indeed, the same protocol was used without CNC and a sacrificial initiator and with $[GMA]_0:[PMDETA]_0:[CuBr]_0 = 100:1:1$. After 7 freeze-thaw cycles, polymerization occurred at room temperature for 1 h. At the end of the reaction, solubilized PGMA was purified on a basic alumina column and precipitated in cold methanol. After filtration and drying, PGMA homopolymer was characterized by ¹H-NMR, and a conversion rate of 52% and a theoretical molar mass of 7300 g.mol⁻¹ was calculated. This homopolymer was used as reference PGMA in this study.

209 2.5. PLA-based nanocomposites preparation

210 First, a 10 wt% PLA solution was prepared by dissolving PLA pellets in dichloromethane under 211 constant magnetic stirring for a whole night. Neat CNCs or polymerized CNC-PGMA-Br were solvent 212 exchanged to dichloromethane and introduced into the PLA solution. The mixture was then 213 homogenized using an Ultra-Turrax homogenizer (IKA) following by an ultrasound treatment (10 kJ.g_{CNC}⁻¹), and then poured into a Teflon petri dish. The latter was left to evaporate under a fume hood 214 215 for 48 h. The recovered films were then hot pressed between two Teflon sheets and with the use of a 150-µm-thick mould. Hot pressing was performed at 180 °C, first for 3 min without pressure, and then 216 217 for 1 min under 150 bar pressure. After the compression, the samples were cooled down to room 218 temperature. The films prepared with 10 wt% of neat CNCs or polymerized CNC-PGMA-Br are 219 respectively referenced as PLA_CNC10 or PLA_CNC-PGMA-Br10.

220 **2.6. Characterization methods**

221 2.6.1. Atomic Force Microscopy (AFM)

AFM images of CNC suspensions were recorded using a Dimension Icon Brucker equipped with a silicon-coated micro cantilever (O-TESPA) using tapping mode. Droplets of diluted CNC suspension (10^{-4} wt\%) were deposited on clean mica plates, which were allowed to dry by evaporation overnight. Approximately ten scans of 10 µm x 10 µm and 3 µm x 3 µm were obtained for each sample to analyze the morphology of the nanoparticles by measuring the dimensions of at least 50 CNC samples using ImageJ software.

228 2.6.2. Transmission Electron Microscopy (TEM)

TEM copper grids with thin amorphous carbon films were submitted to glow discharge in an easiGlow station (Pelco). A 4-μL diluted CNC suspension droplet was deposited on the carbon film, followed by a droplet of uranyl acetate (2 wt%). Negative dye in excess was absorbed, and the remaining film was dried. The CNC suspension was observed through a transmission electron microscope FEI/Philips CM200 with the microscopy NanoBio-ICMG platform (Grenoble, France), under an acceleration voltage of 200 kV. Pictures were recorded with a digital camera TVIPS TemCam F216 (2040 x 2040 pixels). Representative images were selected for the analysis.

236 2.6.3. X-Ray Diffraction and Crystallinity Index (CI)

The crystallinity of CNCs was investigated with spectra obtained from wide-angle X-ray diffraction analyses. An X'Pert Pro MPD diffractometer supplied by PANalytical equipped with an X' accelerator detector and a copper anode (K α (Cu) = 1.5419 Å) was used for the symmetric scan of the reflection (theta/2theta in Bragg Brentano geometry) of the sample. Scans were performed from 5° to 60°. The crystallinity index of samples was determined according to the Segal height peak method (Ahvenainen et al., 2016; Park et al., 2010; Segal et al., 1959) (**Equation 1** below).

- 243 $CI = (1 I_{am}/I_{002}).100$
- 244

Equation 1. Cristallinity index (CI) according to the Segal height peak method

where I_{am} corresponds to the intensity at the minimum (at $2\theta \approx 18.3^{\circ}$) and I_{002} corresponds to the main crystalline peak (at $2\theta \approx 22.5^{\circ}$). This method is the most widely used, although it slightly overestimates the value of the crystallinity and provides qualitative values of the crystallinity. The measures were duplicated.

249 2.6.4. Dynamic Light Scattering (DLS)

250 The hydrodynamic diameters of CNCs were measured using a Zeta Sizer NanoZS supplied by Malvern Instruments (Orsay, France), operated with DTS software. Suspensions of CNCs at 10⁻² wt% 251 252 in DCM were freshly prepared before each measurement and treated in an ultrasonic bath. A total of 5 253 acquisitions with 15 measurements at 25 °C were performed and particle size average values are 254 presented. These values correspond to the diameter of the sphere diffusing at the same rate as the measured particle. Moreover, the Brownian motion-induced particle speed is correlated to the size of 255 256 the particle by the Stokes-Einstein equation. Boluk and Danumah (Boluk & Danumah, 2014) provided 257 details of this principle applied to CNC analysis.

- 258 2.6.5. Thermogravimetric Analysis (TGA)
- 259 TGA thermograms were recorded using a thermal analyzer (NETZSCH STA 449 F3 Jupiter) from the 260 LRMO team of the Commissariat à l'énergie atomique et aux énergies alternatives (CEA, Saclay, France). Dried samples were introduced in aluminum crucibles and were heated from 30 °C to 500 °C 261 262 at 10 °C/min under helium flow at 60 mL/min. Data were at least duplicated and analyzed using 263 Proteus software.
- 264 2.6.6. Fourier-Transform Infrared Spectroscopy (FTIR)

- 265 Infrared spectra of CNCs were performed on a Bruker IFS 66 spectrometer using an attenuated total
- 266 reflectance (ATR) module composed of diamond crystals from Pike technologies. Absorbance spectra
- 267 were registered between 600 and 4000 cm⁻¹, with a resolution of 4 cm⁻¹ and 300 scans. Spectra were
- 268 visualized and normalized using OPUS software and were at least duplicated.
- 269 2.6.7. Elemental Analysis
- 270 Elemental analyses of CNCs were performed by the "Institut des Sciences Analytiques" (Villeurbanne, 271 France), using an ISA-CNRS micro analyzer. Based on elemental organic microanalysis, the carbon, hydrogen, oxygen and sulfur contents of the samples were determined with a precision of $\pm 0.4\%$ by at 272 273 least duplicates. The data can be used for the determination of the degree of substitution (DS) of the grafted CNCs, equivalent to the number of functionalized hydroxyl groups per anhydroglucose unit 274 275 (AGU), in accordance with Equation 2 below (Etzael Espino-Pérez et al., 2014):
- 276

277

$$DS = (M(C)_{AGU} - \omega_C \cdot (M_{AGU} + DS_{SO3} \cdot M_{SO3})) / (\omega_C \cdot M_{grafted} - M(C)_{grafted})$$

Equation 2. Degree of substitution (DS)

278 where $M(C)_{AGU}$ is the carbon molar mass of an AGU, M_{AGU} is the molar mass of an AGU, ω_C is the 279 carbon weight fraction (in %) obtained from elemental analysis, Mgrafted is the molar mass of the 280 grafted moieties, and $M(C)_{\text{grafted}}$ is the carbon molar mass of the grafted moieties. DS_{SO3} is the degree 281 of substitution of sulfate half ester groups similarly calculated from the sulfur weight fraction (S%), 282 M_{SO3} is the molar mass of -OSO3⁻ groups and M_S the sulfur molar mass of -OSO3⁻ groups, as shown in Equation 3 below: 283

- 284 $DS_{SO3} = (S\%.M_{AGU})/(M_{S} - \%S.M_{SO3})$
- 285

Equation 3. Degree of substitution of half sulfate ester groups (DS_{SO3})

286 Taking the presence of these groups into account allows the correction of the values of carbon and oxygen weight fractions by multiplying the experimental values by $1+((DS_{SO3}.M_{SO3})/M_{AGU})$. Other 287

correction methods have also been proposed in the literature (Etzael Espino-Pérez et al., 2014;
Siqueira, Bras, & Dufresne, 2010).

290 2.6.8. X-Ray Photoelectron Spectroscopy (XPS)

291 XPS measurements were carried out on a K-Alpha Thermo Fisher spectrometer, equipped with a 292 monochromatic X-ray source (Al Ka, 1486.6 eV). A spot size of 400 mm was used for all 293 measurements, and a hemispherical analyzer was operated in constant analyzer energy mode with a 294 pass energy of 200 eV and a step size of 1 eV (for survey spectra) and a pass energy of 50 eV and a 295 step size of 0.1 eV (for high-resolution spectra). To neutralize the accumulation of charge, a dual-beam 296 flood gun was used. Data treatment was carried out with Avantage software (Thermo Fisher). 297 Background subtraction (Shirley type) and normalization of peak areas (using Scofield sensitivity 298 factors) were performed before any calculation of elemental composition. Binding energies are 299 referenced to the C1s neutral carbon peak at 285.4 eV.

300 2.6.9. ¹H-Liquid State Nuclear Magnetic Resonance (1H-NMR)

¹H-NMR analyses were performed on a Bruker 360 MHz spectrometer in deuterated chloroform at
 room temperature, with a residual signal appearing at 7.24 ppm. Chemical shift values were calculated
 with TMS as the first reference. Spectra were analyzed using NMR Notebook software.

304 2.6.10. Size-Exclusion Chromatography (SEC)

305 Polymeric samples were dissolved in tetrahydrofuran (THF) at a concentration of 1 mg/mL. SEC 306 analyses were carried out with a two-column ViscoGel mixed bed from Viscotek (7.8 x 300 mm, type 307 GMHH r-H). This mixed bed was mounted on a device equipped with a refractive index detector 308 (Waters 410). The injected volume of sample solution was equal to 50 μ L. The calibration range 309 corresponded to linear polystyrene standards. The process was duplicated.

310 2.6.11. Scanning Electron Microscopy (SEM)

Sample cross-sections of PLA_CNC10 and PLA_CNC-PGMA-Br10 were prepared by cryofracture or at ambient temperature. Briefly, each sample was fractured in liquid nitrogen and was allowed to return at room temperature. Fractured samples of 3 nm thickness were then metallized with gold/palladium. On the other hand, 90-nm-thick sample cuts at room temperature were performed using an ultra-microtome UC6 (LEICA) equipped with a diamond knife, and were then metallized as previously described. For each sample, cross-sections obtained by both cryofracture or at ambient

- 317 temperature were analyzed using a Quanta 250 FEG (Thermofischer) device at a 2.5 kV voltage in
- 318 high vacuum mode. Cross-sections images were processed using ImageJ software.

319 **3. Results and discussion**

320 **3.1.** Characterization of cellulose nanomaterials

Commercial spray-dried cellulose nanocrystal powder was used in this study (**Figure 1 a**). These CNCs are produced from wood by sulfuric acid hydrolysis of bleached pulp (Reid et al., 2016) and can easily be redispersed at low concentration in water and polar organic solvents (such as DMF or DMSO) using ultrasound treatment with an ultrasonic probe (Viet, Beck-Candanedo & Gray, 2007).



325326

Figure 1. a) Spray-dried CNC from CelluForce; b) AFM height image of CNC and c) TEM image of CNC

Using the AFM and TEM images (Figure 1 b and c), morphology of the neat nanomaterials can be confirmed, and the average length is 108 +/- 33 nm and average diameter is 4 +/- 1 nm, confirming the values found in the literature (Foster et al., 2018; Reid et al., 2016). The X-Ray diffractograms (Figure 2 a) display three main peaks, at 16.2° (signal 110), 22.6° (signal 200), and 34.6° (signal 004), characteristic of the cellulose I crystalline form. Moreover, the CI calculated according to Equation 1 has a value equal to 91%, consistent with the high crystallinity of CNC presented in the literature (Habibi et al., 2010).

334 3.2. Preparation of initiator modified CNC

BIB is a common reagent used in the CNC functionalization based on ATRP. As found in the literature (Boujemaoui et al., 2015; Morandi et al., 2009; Nyström et al., 2006), this grafting introduces highly reactive brominated functionality at the surface of nanomaterials. These functionalized sites can then be used as initiator sites for further controlled radical polymerization reactions. In the present study, the brominated functionalized site at the surface of the CNC-Br served as initiators for the SI-ATRP

- 340 applied to the GMA monomer. The functionalization of CNCs with BIB, leading to CNC-Br, is
- 341 illustrated in **Scheme 1** below.



342

343

Scheme 1. Procedure for to the preparation of CNC-Br and CNC-PGMA-Br materials

Conservation of the structure of the CNCs after their functionalization is crucial and has been investigated by XRD analyses. **Figure 2 a** shows wide-angle diffractogram of modified CNC-Br, whose spectra correspond to cellulose I *beta*. The calculated CI is equal to 86%, confirming the conservation of the crystalline structure of CNC-Br. Modified CNC-Br are well-dispersed in DCM, with a mean apparent diameter size of 122 nm, which is similar to that of neat CNC dispersed in DCM (**Figure 2 b**). Even if the dispersion of CNC in DCM does not lead to conclusions regarding their

- 350 dispersion in DMF, the dispersion state in DCM provides some insight about their dispersion in polar
- 351 DMF. This dispersion should theoretically be greater. Thus, it is likely that isolated CNC-Br in DMF
- 352 would provide a large accessible surface for further polymerization.



353

Figure 2. a) X-ray diffractograms of neat CNCs, pre-functionalized CNC-Br, CNC-PGMA-Br after 1 h and 24 h of
 polymerization and PGMA homopolymer; b) DLS curves of neat CNC, pre-functionalized CNC-Br and CNC-PGMA-Br
 after two different polymerization times in dichloromethane; and c) FTIR spectra of PGMA homopolymer, unmodified CNC,
 grafted CNC-Br, polymerized CNC-PGMA-Br-1h, and CNC-PGMA-Br_24h

FTIR analyses carried out on neat CNC and modified CNC-Br clearly show the efficiency of the grafting of BIB. Indeed, in addition to the characteristic peaks of cellulose (i.e., large peak between 3000 cm^{-1} and 3700 cm^{-1} corresponding to the stretching vibrations bands of the -OH bonds of hydroxyl groups, as well as peaks at 1110 cm⁻¹, 1060 cm⁻¹ and 1035 cm⁻¹ corresponding to the vibration of the -C-O bonds of carbons from the repeating unit of cellulose), the peak at 1730 cm⁻¹ is correlates to the -C=O vibration band resulting from ester functional units introduced at the surface of CNC (**Figure 2 c**).

Moreover, no peak near 1760-1800 cm⁻¹ corresponding to the (-C=O)-Br bond from unreacted BIB is 365 366 observed. This confirms the efficiency of the washing steps after the reaction. Elemental analyses were 367 carried out on unmodified CNC and grafted CNC-Br to confirm this grafting (Table 1). Corrected 368 values were obtained by considering the presence of half-sulfate ester groups at the surface of CNCs, 369 and the DS of the grafts on the CNCs that were equal to 0.17 was calculated according to Equation 2. 370 Differences between the corrected values for neat CNC and theoretical values for pure cellulose can be 371 attributed to the presence of hemicelluloses and impurities in the raw materials. The calculations 372 performed in this study are based on the values corrected according to the method proposed previously 373 (Equation 2).

	Experimental				Corrected values	Export	Theoretical				
Sample	values			DSso3		ues			DS	%PGMA	
	%C	%0	%H	%S		%C	%0	0/0	0/0		
Neat CNC	40.7	50.8	6.4	0.8	0.04	41.5	51.8	1.2	1.1	-	0
CNC-Br	42.0	45.3	6.0	0.8	0.04	42.8	46.2	1.1	0.8	0.17	0
CNC-PGMA-	49.6	37.0	6.9	0.6	0.03	50.6	37.7	0.7		-	48
Br_1h	.,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,,	2710	015	0.0	0.00	2010	0,11	0.7	0.7		
CNC-PGMA-	53.2	367	69	0.2	0.01	54.2	37.4	0.7	0.7	_	70
Br_24h	55.2	50.7	0.9	0.2	0.01	51.2	57.1	0.7			/0
PGMA	_	_	_	_	_	59.1	33.8	_	0.6	_	100
(theoretical)		_				57.1	55.0	-	0.0		100

374 375

 Table 1. Atomic composition of neat CNCs, CNC-Br, CNC-PGMA-Br_1h and CNC-PGMA-Br_24h obtained by elemental analysis

To further determine and quantify the grafting at the surface of CNC-Br, XPS measurements were taken allowing the characterization of the surface of the materials as being approximately 10 nm in depth (Morandi et al., 2009). **Figure 3 a** shows the XPS surveys of neat CNC and grafted CNC-Br. Both spectra are composed of two main peaks at approximately 534 and 288 eV corresponding to the oxygen and carbon components, respectively. A peak at 71 eV correlated with a bromine component is 381 visible in the CNC-Br survey, and quantification of the Br3d spectrum leads to an atomic percentage

of bromine equal to 1.0% at the surface of CNC-Br. **Figure 3 b and c** show the decomposition spectra

383 of the C1s signal for both neat and grafted CNC-Br.



384

CNC-PGMA-Br_24h

PGMA homopolymer

70

72

30

28

0.43

0.39



21

30

17

31

-

-

16

13

18

13

28

13

The neat CNC spectrum displays three peaks, at 285.4 eV, 287.0 eV ($\Delta eV = 1.6 eV$), and 288.4 eV ($\Delta eV = 3 eV$), corresponding to C1 (C-C/C-H), C2 (C-O), and C3 (O-C-O/C=O) bonds respectively. The C1 signal is present in the neat CNC spectrum but is related to the contribution of non-oxidized alkane-type carbon atoms and impurities, residual lignin, or extractive compounds, justifying its presence. The C2 signal is related to the presence of ether groups from pure cellulose, as well as the hydroxyl groups of the unmodified CNCs and of the end of the cellulose chains, explaining its 394 presence in both samples. The C3 signal corresponds to acetal moieties from AGU units and should 395 not change significantly after chemical modification, because the corresponding carbon is not affected. 396 Subsequent to α -bromoisobutyryl bromide grafting, a C4 contribution appears in the CNC-Br spectrum 397 and is correlated to the introduction of (O-C=O) bonds on the material with a ratio of 5%, which 398 confirms the success of the bromide derivative grafting, as previously described in the literature (Tian 399 et al., 2014) (Figure 3 b) and d)). In addition, the oxygen to carbon ratio (O/C) associated with the 400 sample before and after modification changed from 0.79 (close to that of pure cellulose ≈ 0.83 401 (Dufresne, 2018)) for the neat CNCs to 0.72 for the CNC-Br as a result of the α -bromoisobutyryl bromide moiety grafted at the surface of CNCs (Figure 3 e). From these results, it is possible to 402 403 conclude the efficient grafting of CNC-Br. Thus, the presence of initiator sites for the further 404 polymerization of GMA on CNC-Br is clearly confirmed.

405 **3.3. Kinetics of the SI-ATRP of GMA**

406 Prior to any polymerization and characterization, it is essential to determine that no parallel reaction — 407 especially adsorption — occurs between cellulose and the monomer. This point was investigated by 408 applying a similar treatment to that of SI-ATRP, but without an initiator, catalyst, or ligand. Only neat 409 CNCs dispersed in anhydrous DMF in the same proportions and the GMA monomer were 410 magnetically stirred for 24 h. CNCs were then recovered after five centrifugation cycles in DCM, and 411 FTIR spectra were obtained after evaporation of the solvent (Figure 4 a). There is no change in the 412 FTIR spectra of neat CNC after being mixed with the monomer for 24 hours; in particular, there is no peak related to a C=O bond from GMA at approximately 1720 cm⁻¹. At this stage, it can be assumed 413 414 that further evidence of the presence of characteristic groups of GMA and PGMA do not come from 415 possible adsorbed monomer on CNC.

416 After being grafted, CNC-Br were then polymerized at their brominated initiator sites with GMA, as 417 illustrated in Scheme 1. Glycidyl methacrylate (GMA) is a monomer that has never been used as part 418 of the polymerization from the surface of wood CNC, to the best of our knowledge. In the literature, 419 only a few studies describe ATRP of GMA (Barbey et al., 2013; Cañamero et al., 2004) on cellulose, presented as a well-known and controlled polymerization. In our case, the difficulty of the 420 421 polymerization lays in the high reactivity of the epoxy groups of PGMA which can rapidly open. 422 Nevertheless, opening of these epoxy functional groups has been avoided by the reaction at room 423 temperature, in anhydrous conditions, and with the absence of any reagents that can react with these 424 groups. Moreover, it has been shown in the literature that a similar system for SI-ATRP of GMA on a 425 substrate (CuBr/PMDETA) leads to the conservation of active epoxy groups on the polymer chains 426 (Wang et al., 2017). Meanwhile, the presence of these epoxy groups at the surface of polymerized 427 CNC is one objective of this polymerization and is precisely investigated in this study. Kinetics is the 428 key point in the understanding of a polymerization, and was investigated in this study. At different 429 times during SI-ATRP of GMA initiated by CNC-Br materials, aliquots were withdrawn from the 430 reaction media and analyzed by ¹H-liquid NMR to determine the polymerization conversion by 431 following the disappearance of peaks related to vinyl protons from the monomer and the appearance of 432 peaks related to protons from the methyl groups of the polymer (Figure 4 b).



433

Figure 4. a) FTIR spectra of GMA, neat CNC and recovered CNC after mixing with GMA in conditions similar to
polymerization; b) ¹H-liquid NMR spectra of the recovered reaction media after three different polymerization times, where
(a) and (a') correspond to the protons of the end of the double-bond carbon-carbon of the monomer GMA and (B), (B'), and
(B'') to the protons of the methyl groups of the polymer PGMA and equation of the conversion rate X calculation with I
corresponding to the integral related to the area below the curve of the peak a (I(a)) or of the three peaks B, B' and B''
(I(B,B',B'')); and c) representation of the evolution of conversion as a function of polymerization time

The recorded NMR spectra show decreasing peak intensity at 5.6 and 6.1 ppm related to the vinyl protons of the monomer. In parallel, the intensity of the peaks between 0.9 and 1.2 ppm related to the protons from the methyl group from the growing polymer clearly increased. Conversion (p) of the

GMA into PGMA can be calculated using the formula presented in Figure 4 b, where the value I 443 444 corresponds to the integration of the peaks. The evolution of the conversion is represented by plotting 445 the ratio $\ln(1/(1-p))$ as a function of time (**Figure 4 c**), showing the two rates of polymerization with a higher rate in a shorter time period (between 0 and 4 h) and a slower rate after a longer polymerization 446 447 time period. From each collected aliquot the PGMA homopolymer was recovered after filtration on 448 basic alumina and precipitated in cold methanol. Each homopolymer sample was subjected to SEC 449 analysis to obtain the value of its molar mass (according to the equivalent polystyrene). Polydispersity 450 index Đ was calculated as the ratio of weight average molar mass (Mw) to the number average molar 451 mass (Mn). The results are presented in Figure 5 a.

452 The evolution of the PGMA molar masses calculated by SEC analyses as a function of the conversion 453 follows the same trend as previously mentioned with two different rates of polymerization. Indeed, in 454 the first 3 h of polymerization, the molar masses increased from 8179 g.mol⁻¹ to 9791 g.mol⁻¹, 455 followed by a slower rate of polymerization reaching molar masses equal to 10343 g.mol⁻¹ after 24 h 456 of reaction (Figure 5 d). This behavior has been previously described for a similar system 457 (GMA/CuBr/PMDETA) in the literature (Xiao et al., 2011), where it was attributed to the 458 heterogeneous character of the system inducing side-reactions at high conversion rates. Indeed, radical 459 bromine elements from the cellulose surface could be lost, inducing termination at the level of the 460 CNCs. Nevertheless, polymerization would continue in the system solution. Figure 5 b shows the 461 FTIR spectra of CNC-PGMA-Br at different polymerization times, recovered from the aliquots after 462 centrifugation in DCM. Qualitative analysis of these spectra confirms the polymerization on CNCs, with an increase in the peak at 1725 cm⁻¹ related to the C=O stretching of ester groups and the 463 presence of a peak at 910 cm⁻¹ related to the C-O stretching from epoxy groups. It is interesting to note 464 465 that ATRP polymerization applied on the GMA monomer, involving the present CuBr/PMEDETA 466 catalytic system, ensures the preparation of an epoxy functional polymer. In fact, as shown in the the 467 literature (Sabatini, 2007), decribing the grafting of multiwalled carbon nanotubes with PGMA 468 polymer using the same ATRP polymerization procedure, a further post modification to introduce 469 molecules of interest is possible by taking advantage of the epoxy functional groups.



u							
¹ H-liquid NMR			Sec (Con	ventional)	FTIR absorbance ratio		
Time (h)	Conversion (%)	Mn _{theoretical} (g.mol ⁻¹)	Mn (g.mol ⁻¹)	Dispersity (Ð)	Epoxy (intensity at 910 cm ⁻¹) / Cellulose (intensity at 1110 cm ⁻¹)	Ester (intensity at 1725 cm ⁻¹) / Cellulose (intensity at 1110 cm ⁻¹)	
0	0	4944	/	/	0.08	0	
0.3	35	6660	8200	1.2	0.45	1.13	
1	46	7552	8900	1.3	0.37	1.0	
2	53	8209	9800	1.3	0.65	1.33	
3	58	8529	9800	1.3	0.54	1.60	
17	80	11391	10000	1.4	0.59	1.85	
24	85	12145	10300	1.4	0.58	1.84	

d

Figure 5. a) Molar masses of homopolymer and dispersities obtained by conventional SEC analyses; b) FTIR spectra of
 recovered CNC-PGMA-Br at different polymerization times; c) ratios of peak intensities related to epoxy groups/cellulose
 and ester groups/cellulose; and d) summary of kinetics study data obtained from ¹H-liquid NMR, SEC (conventional), and
 FTIR (* Mntheoretical = (p*([GMA]/[EBIB])*MGMA)+MEBIB with p the conversion, [GMA] the initial concentration in monomer,
 [EBIB] the initial concentration in initiator, MGMA the molar mass of GMA and MEBIB the molar mass of EBIB (the
 calculation takes into account the polymer chain extremities))

477 Furthermore, to quantitatively analyze these spectra, the ratios of the absorbance values of both C=O 478 and C-O peaks and cellulose (1110 cm⁻¹) were plotted as a function of time. The obtained curves 479 (Figure 5 c) follow the previously mentioned trend: with short polymerization time (1 to 3 h), there is an increase in the polymer chain length at the surface of cellulose, which becomes slower at longer 480 481 times (4 to 24 h). Taking into account these results (summarized on Figure 5 d), one hypothesis might 482 be that the decreasing polymerization rate is due to the deactivation of brominated active sites grafted 483 at the surface of CNC as well as those from the sacrificial initiator. A transfer reaction resulting from 484 the hydroxyl -OH groups of CNC could be an explanation for this deactivation. In the remainder of 485 this study, we will focus on the characterization of CNC-PGMA-Br polymerized at two different 486 polymerization times (1 h and 24 h): CNC-PGMA-Br_1h and CNC-PGMA-Br_24h, respectively.

487 **3.4. SI-ATRP of functionalized CNC-Br at different polymerization times**

- 488 CNC-PGMA-Br_1h and CNC-PGMA-Br_24h were polymerized in larger batches for characterization, 489 according to the previously detailed protocol. *Grafting-from* of polymers at the surface of CNCs is a 490 widely studied procedure that allows the grafting of a high density of polymer at the surface of CNCs. 491 In the case of the PGMA grafted as an amorphous polymer, the morphology of the final materials was 492 investigated. Figure 2 a shows X-ray diffractograms of CNC-PGMA-Br_1h, CNC-PGMA-Br_24h, 493 and PGMA homopolymer, which is not crystallized and whose XRD signature corresponds to 494 consecutive large humps. The CNC-PGMA-Br 1h diffractogram is a combination of diffractograms of 495 PGMA and cellulose I beta, with the presence of characteristic peaks at 22.6° and 34.6°. Similar to 496 CNC-PGMA-Br 1h, CNC-PGMA-Br 24h diffractogram shows characteristic peaks of cellulose I beta, 497 but the presence of the amorphous PGMA polymer is more highlighted here. These results confirm the 498 growth of the PGMA on CNCs with increasing polymerization time.
- Moreover, according to **Figure 2 b**, the diameter of polymerized CNC-PGMA-Br in DCM increases with the polymerization duration. Indeed, after 1 h, apparent diameter size is equal to 164 nm (122 nm for neat CNC and functionalized CNC-Br), which is reasonable for dispersed CNC suspension. Nevertheless, after 24 h, CNC-PGMA-Br_24h show a higher mean apparent diameter equal to 255 nm

- 503 and a larger peak, leading to a worse dispersion of grafted nanoparticles in the suspension. Inter-
- 504 particle coupling reactions between CNC-PGMA-Br is a possible explanation.

505 The thermal properties of polymerized CNC were investigated through TGA analyses, whose 506 thermograms and derivative thermogravimetry (DTG) curves are presented in Figure 6 a, showing 507 that polymerization of PGMA at the surface of CNC enhances the thermal stability of the materials. 508 Indeed, the primary onset of the degradation temperature of CNCs before and after 1 and 24 h of 509 polymerization increases from 305 °C to 314 °C and 326 °C respectively. Moreover, the CNC 510 thermogram shows one weight loss peak between 250 °C and 350 °C. In a recent study, Zhang et al. 511 studied different ways to characterize grafted polymers on CNCs, including the use of TGA analysis 512 (Zhang et al., 2018). Their method appears to be not totally applicable in our case because of the 513 presence of a weight loss peak of PGMA in the same temperature ranges as for cellulose. Moreover, 514 the presence of a second weight loss peak for PGMA, polymerized CNC-PGMA-Br_1h, and CNC-515 PGMA-Br_24h between 350 °C and 480 °C allows an approximation of the amount of PGMA 516 polymerized on CNC. Indeed, taking into account the slight weight loss of cellulose in this second 517 temperature range for calculation, and considering that samples are only composed of cellulose and 518 polymer, a weight percentage of PGMA equal to 38% and 83% respectively for CNC-PGMA-Br_1h 519 and CNC-PGMA-Br_24h are calculated (Figure 6 b). The large amount of grafted polymer after 24 h 520 of polymerization is confirmed. Moreover, even after a short polymerization time, nearly 40% by mass 521 of the sample is PGMA, corresponding to the previous kinetic study of this polymerization.



Ē			
	5		
	ľ	h	h

Sample	% weight loss (350°C-480°C)	Thermal degradation onset T_{onset} (°C)	PGMA (%wt)
CNC	14	305	0
CNC-PGMA-Br_1h	30	314	38
CNC-PGMA-Br_24h	49	326	83
PGMA homopolymer	56	319	100

522

 Figure 6. a) TGA thermograms and DTG curves of neat CNC, CNC-PGMA-Br_1h, CNC-PGMA-Br_24h, and homopolymer
 PGMA; and b) thermal degradation onset temperatures and calculated amount of PGMA in both CNC-PGMA-Br_1h and CNC-PGMA-Br_24h

526 By regarding only the morphology of polymerized CNC-PGMA-Br, 1 h of polymerization ensures the 527 conservation of the crystallinity, which is critical for further applications, while introducing a 528 significant amount of PGMA.

529 3.5. Efficiency of SI-ATRP on CNCs

530 The efficiency of the polymerization of GMA from brominated initiator sites previously grafted on 531 CNC was first investigated by FTIR analysis, whose spectra are shown in Figure 2 c. Results confirm 532 the conclusion drawn from Figure 5 b, proving the efficiency of the polymerization and the growth of 533 the polymer over time. Indeed, peaks at 910 cm⁻¹, 906 cm⁻¹, 1728 cm⁻¹, and between 2840 cm⁻¹ and 3000 cm⁻¹ are respectively characteristic of the epoxy groups, terminal vinyl groups and ester bonds 534 535 from carbonyl groups, and $-CH_2$ and $-CH_3$ carbons from the PGMA backbone polymer. The clear 536 increase in those peaks for the CNC-PGMA-Br_1h and CNC-PGMA-Br_24h spectra demonstrates the 537 polymerization of PGMA at the level of CNCs over time. These results are confirmed by elemental 538 analyses (Table 1). Indeed, for both CNC-PGMA-Br 1h and CNC-PGMA-Br 24h, an increase in 539 the %C values and a decrease in the %O values are notable and consistent with the introduction of the 540 polymer PGMA $(C_7H_{10}O_3)_n$ on CNCs. This is reaffirmed by the decrease in the O/C ratio for these 541 polymerized CNCs, which is also similar to the corresponding theoretical calculated ratio and to those 542 of pure PGMA. The slight difference between the O/C ratios of CNC-PGMA-Br and PGMA confirms 543 the presence of cellulose in the sample. Note that values are corrected according to the previously 544 described method by considering the presence of half-sulfate ester groups at the surface of CNCs, 545 without however considering the presence of impurities like hemicelluloses in the samples, which 546 could influence the values, so they must be interpreted comparatively. Moreover, considering that 547 CNC-PGMA-Br_1h and CNC-PGMA-Br_24h are composed of cellulose and PGMA, an estimation of 548 the weight percentage of PGMA may also be calculated in both cases, as presented in **Table 1**. Values 549 are not totally equal to those previously calculated through TGA thermograms (Figure 6 b), but the 550 trend is similar, keeping in mind that TGA and elemental analysis have different sensitivities and 551 involve different approaches. The amount of PGMA with increasing polymerization time, and 552 approximately 48% and 70% by mass of PGMA is attached to CNCs after 1 h and 24 h respectively.

553 One of the primary challenges to SI-ATRP on CNCs involves the characterization and quantification 554 of the grafted polymer at the surface of the nanomaterials. Hansson at al. (Hansson et al., 2011) 555 investigated this point by proving that the kinetics of the polymerization at the surface of CNCs is

similar to those in the media from a sacrificial initiator. Previous characterizations allow the proof of

- 557 the polymerization as well as an estimate of the calculated amount of polymer. The surfaces of
- 558 polymerized CNC-PGMA-Br_1h and CNC-PGMA-Br_24h were investigated by XPS analyses; the
- be decompositions spectra of the C1s signal are presented in **Figure 7 c** and **d**.





561 Figure 7. Decomposition of the C1s peak of a) CNC-PGMA-Br_1h, b) CNC-PGMA-Br_24h, and c) PGMA homopolymer obtained by XPS analyses

563 In **Figure 7 b**, the decomposition spectra of the C1s peak of PGMA homopolymer shows the presence 564 of characteristic peaks of the polymer: at 285.4 eV, 286.1 eV ($\Delta eV = 0.7 eV$), 287.1 eV ($\Delta eV = 1.7$ 655 eV), 287.5 eV (Δ eV = 2.1 eV), and 289.5 eV (Δ eV = 4.1 eV) for respectively the C-C/C-H, C*-C=O-, 566 C-O, C-O-C (epoxy ring), and O-C=O bonds. The CNC-PGMA-Br_1h and CNC-PGMA-Br_24h 567 (**Figure 7 c** and **d**) decomposition spectra show the same characteristics, as well as a peak 568 characteristic of cellulose at 288.2 eV (Δ eV = 3.3 eV) related to the C3 signal (O-C-O or C=O) from 569 the neat CNCs. It is important to note that the intense C2 signal from cellulose is also present but is 570 superimposed over other C-O and C-O-C peaks. This result confirms the grafting of a PGMA polymer 571 layer onto CNCs.

Moreover, the determination of the O/C ratio (Figure 3 e) leads to a value of 0.47 for CNC-PGMA-572 573 Br_1h materials, whereas a ratio of 0.42 is observed for CNC-PGMA-Br_24h, which is similar to the 574 theoretical value associated with pure PGMA polymer (Beamson & Briggs, 1993 reference). This 575 result could explain the increasing grafted polymer weight with time, as shown in Figure 5 d. 576 According to the XPS results, it is possible to make a conclusion about the presence of PGMA over 577 the surface of CNC. Moreover, it is possible to observe in Figure 7 that after 1 h of polymerization, 578 the intensity of the peak associated with the epoxy C-O-C bond is less intense than that of the 579 homopolymer reference. After 24 h of polymerization, this intensity is closer to that of the 580 homopolymer, confirming that the amount of polymerized PGMA is more important. Quantification of 581 the polymer is not possible considering these results, but the presence of PGMA at the surface of 582 CNCs is clearly highlighted. Moreover, highly reactive epoxy rings are conserved during the 583 polymerization and are available at the surface of both CNC-PGMA-Br_1h and CNC-PGMA-Br_24h.

584 **3.6. PLA-based nanocomposites**

585 To investigate the effect of PGMA on the surface of CNCs on their compatibilization with a 586 hydrophobic polymeric system - and especially with PLA - cross-sections of PLA_CNC10 and 587 PLA_CNC-PGMA-Br10 nanocomposites were observed by SEM. Related images are presented in Figure 8. Figure 8 a and b were obtained from cross-sections prepared respectively without and with 588 589 cryofracture. In Figure 8 a, large micrometric aggregates can be observed. Moreover, sedimentation of 590 these aggregates can be noted and may be related to the casting method used for nanocomposite films 591 preparation. Figure 8 b allows the observation of very distinguishable CNC aggregates. Moreover, 592 cavities are visible and demonstrate the lack of adhesion between the micrometric fillers and the 593 polymeric matrix.



594

595Figure 8. SEM images of cross-sections of PLA_CNC10 nanocomposite film a) without and b) with cryofracture and of596PLA_CNC-PGMA-Br10 nanocomposite film c) without and d) with cryofracture

597 Figure 8 c and d show SEM images of PLA-based nanocomposites prepared with modified CNC-598 PGMA-Br after 1 h of polymerization. The cross-section prepared without cryofracture (Figure 8 c) 599 presents a homogeneous surface. Indeed, no micrometric aggregates are visible. Moreover, the 600 cryofractured sample (Figure 8 d) also exhibits a homogeneous cross-section, as no micrometric 601 particles or cavities are visible. This result emphasizes the enhancement of the filler dispersion in the 602 matrix, and thus the improvement of the adhesion between cellulosic nanofillers CNC-PGMA-Br and 603 the PLA matrix. The interface between CNC-PGMA-Br and PLA is therefore improved and is the key 604 point in the elaboration of nanocomposites, because of its influence on the physico-chemical properties 605 of final materials.

606 **4. Conclusion**

607 CNCs were initially modified with BIB as an initiator of SI-ATRP of PGMA; the efficiency of the 608 functionalization was highlighted using bulk and surface characterization. After ensuring that only the 609 polymerized monomer is present at the level of CNCs after washing, polymerized CNC at two 610 different polymerization times were recovered and characterized using FTIR, XRD, TGA, XPS and 611 elemental analysis. After only 1 h of polymerization, PGMA covers almost all the surface of CNCs, 612 with a weight percentage of approximately 40% relative to CNC. After 24 h of polymerization, the 613 weight proportion of PGMA represents almost 80% of the total weight, but the obtained polymerized 614 CNCs are more aggregated in non-polar solvent. In both cases, the presence of characteristic bonds of 615 the polymer, and especially carbonyl groups and epoxy rings are highlighted, although 1 h of 616 polymerization seems to optimize the reaction conditions for the preparation of well-dispersed, 617 polymerized, hydrophobized CNCs for further incorporation in hydrophobic polymer matrices or 618 further chemical modification. SEM images of PLA_CNC-PGMA-Br10 nanocomposites highlight the 619 improvement of the adhesion between the polymer and the cellulosic nanofillers. Currently, this issue 620 remains the main challenge in nanocomposite field. The results presented in this study are encouraging 621 and could lead to the improvement of the barrier and mechanical properties of PLA-based materials.

622 Acknowledgements

623 This work was supported by the French National Research Agency (ANR) as part of the program 624 ANR-16-CE08-0040. LGP2 is part of the LabEx Tec 21 (Investissements d'Avenir – grant agreement n° ANR-11-LABX-0030), of PolyNat Carnot Institute (Investissements d'Avenir – grant agreement n° 625 626 ANR-16-CARN-0025-01) and of CDP Glyco@Alps (ANR-15-IDEX-02). This research was made 627 possible by the facilities of the TekLiCell platform, funded by the Région Rhône-Alpes (ERDF: 628 European regional development fund). The authors would like to thank Ludovic Costa from ICMMO 629 (Orsay, France), Thierry Encinas from CMTC (Grenoble, France) and Jean-Luc Putaux and Christine 630 Lancelon-Pin from Cermav (Grenoble, France) for SEC, XRD and SEM analyses, respectively.

631 **References**

- Abitbol, T. (2014). Surface modification of cellulose nanocrystals with cetyltrimethylammonium
- bromide. *Nordic Pulp and Paper Research Journal*, 29, 046-057.
- Ahvenainen, P., Kontro, I., & Svedström, K. (2016). Comparison of sample crystallinity determination
- 635 methods by X-ray diffraction for challenging cellulose I materials. *Cellulose*, 23, 1073-1086.
- Azzam, F., Heux, L., Putaux, J.-L., & Jean, B. (2010). Preparation By Grafting Onto, Characterization,
- and Properties of Thermally Responsive Polymer-Decorated Cellulose Nanocrystals. *Biomacromolecules*, *11*, 3652-3659.

- Barbey, R., Laporte, V., Alnabulsi, S., & Klok, H.-A. (2013). Postpolymerization Modification of
 Poly(glycidyl methacrylate) Brushes : An XPS Depth-Profiling Study. *Macromolecules*, 46,
 6151-6158.
- Beamson, G., & Briggs, D. (1993). High Resolution XPS of Organic Polymers: The Scienta
 ESCA300 Database. *Journal of Chemical Education*, 70, A25.
- Beck, S., Méthot, M., & Bouchard, J. (2015). General procedure for determining cellulose nanocrystal
 sulfate half-ester content by conductometric titration. *Cellulose*, 22, 101-116.
- 646 Belgacem, M. N. (2008). Monomers, polymers and composites from renewable resources.
 647 Amsterdam: Elsevier.
- Boluk, Y., & Danumah, C. (2014). Analysis of cellulose nanocrystal rod lengths by dynamic light
 scattering and electron microscopy. *Journal of Nanoparticle Research*, *16*, 2174.
- Boujemaoui, A., Cobo Sanchez, C., Engström, J., Bruce, C., Fogelström, L., Carlmark, A., &
 Malmström, E. (2017). Polycaprolactone Nanocomposites Reinforced with Cellulose
 Nanocrystals Surface-Modified via Covalent Grafting or Physisorption : A Comparative Study. *ACS Applied Materials & Interfaces*, 9, 35305-35318.
- 654 Boujemaoui, A., Mongkhontreerat, S., Malmström, E., & Carlmark, A. (2015). Preparation and
- characterization of functionalized cellulose nanocrystals. *Carbohydrate Polymers*, *115*, 457464.
- Cañamero, P. F., de la Fuente, J. L., Madruga, E. L., & Fernández-García, M. (2004). Atom Transfer
 Radical Polymerization of Glycidyl Methacrylate : A Functional Monomer. *Macromolecular Chemistry and Physics*, 205, 2221-2228.
- Cheng, D., Wei, P., Zhang, L., & Cai, J. (2018). Surface-initiated atom transfer radical polymerization
 grafting from nanoporous cellulose gels to create hydrophobic nanocomposites. *RSC Advances*,
 8, 27045-27053.

- de Castro, D. O., Bras, J., Gandini, A., & Belgacem, N. (2016). Surface grafting of cellulose
 nanocrystals with natural antimicrobial rosin mixture using a green process. *Carbohydrate Polymers*, 137, 1-8.
- Domingues, R. M. A., Gomes, M. E., & Reis, R. L. (2014). The Potential of Cellulose Nanocrystals in
 Tissue Engineering Strategies. *Biomacromolecules*, *15*, 2327-2346.
- Dufresne, A. (2018). *Nanocellulose : From nature to high performance tailored materials* (2. edition).
 Berlin Boston: de Gruyter.
- 670 Espino-Pérez, E., Gilbert, R. G., Domenek, S., Brochier-Salon, M. C., Belgacem, M. N., & Bras, J.

671 (2016). Nanocomposites with functionalised polysaccharide nanocrystals through aqueous free
672 radical polymerisation promoted by ozonolysis. *Carbohydrate Polymers*, *135*, 256-266.

- Espino-Pérez, Etzael, Bras, J., Almeida, G., Plessis, C., Belgacem, N., Perré, P., & Domenek, S.
 (2018). Designed cellulose nanocrystal surface properties for improving barrier properties in
 polylactide nanocomposites. *Carbohydrate Polymers*, 183, 267-277.
- Espino-Pérez, Etzael, Domenek, S., Belgacem, N., Sillard, C., & Bras, J. (2014). Green Process for
 Chemical Functionalization of Nanocellulose with Carboxylic Acids. *Biomacromolecules*, *15*,
 4551-4560.
- Eyley, S., & Thielemans, W. (2014). Surface modification of cellulose nanocrystals. *Nanoscale*, *6*,
 7764-7779.
- Ferreira, F. V., Pinheiro, I. F., Gouveia, R. F., Thim, G. P., & Lona, L. M. F. (2017). Functionalized
 cellulose nanocrystals as reinforcement in biodegradable polymer nanocomposites. *Polymer Composites*, *39*, E9-E29.
- Ferrer, A., Pal, L., & Hubbe, M. (2017). Nanocellulose in packaging: Advances in barrier layer
 technologies. *Industrial Crops and Products*, 95, 574-582.

686	Foster, E. J., Moon, R. J., Agarwal, U. P., Bortner, M. J., Bras, J., Camarero-Espinosa, S., Chan, K. J.
687	Clift, M. J. D., Cranston, E. D., Eichhorn, S. J., Fox, D. M., Hamad, W. Y., Heux, L., Jean, B.
688	Korey, M., Nieh, W., Ong, K. J., Reid, M. S., Renneckar, S., Youngblood, J. (2018)
689	Current characterization methods for cellulose nanomaterials. Chemical Society Reviews, 47
690	2609-2679.

- Goffin, A.-L., Raquez, J.-M., Duquesne, E., Siqueira, G., Habibi, Y., Dufresne, A., & Dubois, P.
 (2011). From Interfacial Ring-Opening Polymerization to Melt Processing of Cellulose
 Nanowhisker-Filled Polylactide-Based Nanocomposites. *Biomacromolecules*, *12*, 2456-2465.
- Habibi, Y. (2014). Key advances in the chemical modification of nanocelluloses. *Chem. Soc. Rev.*, 43,
 1519-1542.
- Habibi, Y., Goffin, A.-L., Schiltz, N., Duquesne, E., Dubois, P., & Dufresne, A. (2008).
 Bionanocomposites based on poly(ε-caprolactone)-grafted cellulose nanocrystals by ringopening polymerization. *Journal of Materials Chemistry*, *18*, 5002-5010.
- Habibi, Y., Lucia, L. A., & Rojas, O. J. (2010). Cellulose Nanocrystals : Chemistry, Self-Assembly,
 and Applications. *Chemical Reviews*, *110*, 3479-3500.
- Hansson, S., Antoni, P., Bergenudd, H., & Malmström, E. (2011). Selective cleavage of polymer grafts
 from solid surfaces : Assessment of initiator content and polymer characteristics. *Polymer Chemistry*, 2, 556-558.
- Hansson, S., Östmark, E., Carlmark, A., & Malmström, E. (2009). ARGET ATRP for Versatile
 Grafting of Cellulose Using Various Monomers. *ACS Applied Materials & Interfaces*, *1*, 2651
 -2659.
- Hubbe, M. A., Ferrer, A., Tyagi, P., Yin, Y., Salas, C., Pal, L., & Rojas, O. J. (2017). Nanocellulose in
 Thin Films, Coatings, and Plies for Packaging Applications : A Review. *BioResources*, *12*,
 2143-2233.

- Jorfi, M., & Foster, E. J. (2015). Recent advances in nanocellulose for biomedical applications. *Journal of Applied Polymer Science*, *132*, 41719-41738.
- Kargarzadeh, H., Mariano, M., Gopakumar, D., Ahmad, I., Thomas, S., Dufresne, A., Huang, J., & Lin,
 N. (2018). Advances in cellulose nanomaterials. *Cellulose*, 25, 2151-2189.
- 714 Kedzior, S. A., Graham, L., Moorlag, C., Dooley, B. M., & Cranston, E. D. (2016). Poly(methyl
- methacrylate)-grafted cellulose nanocrystals : One-step synthesis, nanocomposite preparation,
 and characterization. *The Canadian Journal of Chemical Engineering*, *94*, 811-822.
- Kedzior, S. A., Marway, H. S., & Cranston, E. D. (2017). Tailoring Cellulose Nanocrystal and
 Surfactant Behavior in Miniemulsion Polymerization. *Macromolecules*, *50*, 2645-2655.
- Klemm, D., Kramer, F., Moritz, S., Lindström, T., Ankerfors, M., Gray, D., & Dorris, A. (2011).
 Nanocelluloses : A New Family of Nature-Based Materials. *Angewandte Chemie International Edition*, *50*, 5438-5466.
- Kloser, E., & Gray, D. G. (2010). Surface Grafting of Cellulose Nanocrystals with Poly(ethylene
 oxide) in Aqueous Media. *Langmuir*, 26, 13450-13456.
- Lin, N., & Dufresne, A. (2014). Nanocellulose in biomedicine : Current status and future prospect.
 European Polymer Journal, 59, 302-325.
- Lin, N., Huang, J., & Dufresne, A. (2012). Preparation, properties and applications of polysaccharide
 nanocrystals in advanced functional nanomaterials : A review. *Nanoscale*, *4*, 3274-3294.
- Malmström, E., & Carlmark, A. (2012). Controlled grafting of cellulose fibres an outlook beyond
 paper and cardboard. *Polymer Chemistry*, *3*, 1702-1713.
- Martínez-Sanz, M., Abdelwahab, M. A., Lopez-Rubio, A., Lagaron, J. M., Chiellini, E., Williams, T.
 G., Wood, D. F., Orts, W. J., & Imam, S. H. (2013). Incorporation of
 poly(glycidylmethacrylate) grafted bacterial cellulose nanowhiskers in poly(lactic acid)

- nanocomposites : Improved barrier and mechanical properties. *European Polymer Journal*, 49,
 2062-2072.
- McCaig, H. C., Myers, E., Lewis, N. S., & Roukes, M. L. (2014). Vapor Sensing Characteristics of
 Nanoelectromechanical Chemical Sensors Functionalized Using Surface-Initiated
 Polymerization. *Nano Letters*, *14*, 3728-3732.
- Miao, C., & Hamad, W. Y. (2016). In-situ polymerized cellulose nanocrystals (CNC)-poly(l-lactide)
 (PLLA) nanomaterials and applications in nanocomposite processing. *Carbohydrate Polymers*, *153*, 549-558.
- Moon, R. J., Martini, A., Nairn, J., Simonsen, J., & Youngblood, J. (2011). Cellulose nanomaterials
 review : Structure, properties and nanocomposites. *Chemical Society Reviews*, 40, 3941-3994.
- Morandi, G., Piogé, S., Pascual, S., Montembault, V., Legoupy, S., & Fontaine, L. (2009). ATRP and
 ROMP : Modular chemical tools for advanced macromolecular engineering. *Materials Science and Engineering: C*, *29*, 367-371.
- Morandi, Gaelle, Heath, L., & Thielemans, W. (2009). Cellulose Nanocrystals Grafted with
 Polystyrene Chains through Surface-Initiated Atom Transfer Radical Polymerization (SIATRP). *Langmuir*, 25, 8280-8286.
- Natterodt, J. C., Petri-Fink, A., Weder, C., & Zoppe, J. O. (2017). Cellulose Nanocrystals : Surface
 Modification, Applications and Opportunities at Interfaces. *CHIMIA International Journal for Chemistry*, *71*, 376-383.
- Nechyporchuk, O., Belgacem, M. N., & Bras, J. (2016). Production of cellulose nanofibrils : A review
 of recent advances. *Industrial Crops and Products*, 93, 2-25.
- Nyström, D., Lindqvist, J., Östmark, E., Hult, A., & Malmström, E. (2006). Superhydrophobic biofibre surfaces via tailored grafting architecture. *Chem. Commun.*, *34*, 3594-3596.

756	Oksman, K., Aitomäki, Y., Mathew, A. P., Siqueira, G., Zhou, Q., Butylina, S., Tanpichai, S., Zhou,
757	X., & Hooshmand, S. (2016). Review of the recent developments in cellulose nanocomposite
758	processing. Composites Part A: Applied Science and Manufacturing, 83, 2-18.

- Park, S., Baker, J. O., Himmel, M. E., Parilla, P. A., & Johnson, D. K. (2010). Cellulose crystallinity
 index : Measurement techniques and their impact on interpreting cellulase performance.
 Biotechnology for Biofuels, *3*, 1-10.
- Reid, M. S., Villalobos, M., & Cranston, E. D. (2016). Benchmarking cellulose nanocrystals : From
 the laboratory to industrial production. *Langmuir*, *33*, 1583–1598.
- Robles, E., Urruzola, I., Labidi, J., & Serrano, L. (2015). Surface-modified nano-cellulose as
 reinforcement in poly(lactic acid) to conform new composites. *Industrial Crops and Products*,
 766 71, 44-53.
- 767 Sabatini, D. M. (2007). Leading Edge Nanotechnology Research Developments. Nova Publishers.
- Segal, L., Creely, J. J., Martin, A. E., & Conrad, C. M. (1959). An Empirical Method for Estimating
 the Degree of Crystallinity of Native Cellulose Using the X-Ray Diffractometer. *Textile Research Journal*, 29, 786-794.
- 771 Sessini, V., Navarro-Baena, I., Arrieta, M. P., Dominici, F., López, D., Torre, L., Kenny, J. M., Dubois,
- 772 P., Raquez, J.-M., & Peponi, L. (2018). Effect of the addition of polyester-grafted-cellulose
- nanocrystals on the shape memory properties of biodegradable PLA/PCL nanocomposites.
- 774 *Polymer Degradation and Stability*, *152*, 126-138.
- Siqueira, G., Bras, J., & Dufresne, A. (2010a). New Process of Chemical Grafting of Cellulose
 Nanoparticles with a Long Chain Isocyanate. *Langmuir*, 26, 402-411.
- Siqueira, G., Bras, J., & Dufresne, A. (2010b). Cellulosic Bionanocomposites: A Review of
 Preparation, Properties and Applications. *Polymers*, 2, 728-765.

779	Tian, C., Fu, S., Habibi, Y., & Lucia, L. A. (2014). Polymerization Topochemistry of Cellulose
780	Nanocrystals : A Function of Surface Dehydration Control. Langmuir, 30, 14670-14679.

- Viet, D., Beck-Candanedo, S., & Gray, D. G. (2007). Dispersion of cellulose nanocrystals in polar
 organic solvents. *Cellulose*, 14(2), 109-113. https://doi.org/10.1007/s10570-006-9093-9
- Wang, X., Jing, S., Liu, Y., Qiu, X., & Tan, Y. (2017). Preparation of dithiocarbamate polymer brush
 grafted nanocomposites for rapid and enhanced capture of heavy metal ions. *RSC Advances*, *7*,
 13112-13122.
- Xiao, M., Li, S., Chanklin, W., Zheng, A., & Xiao, H. (2011). Surface-initiated atom transfer radical
 polymerization of butyl acrylate on cellulose microfibrils. *Carbohydrate Polymers*, 83, 512-
- 788 519.
- Zhang, Z., Tam, K. C., Sèbe, G., & Wang, X. (2018). Convenient characterization of polymers grafted
 on cellulose nanocrystals via SI-ATRP without chain cleavage. *Carbohydrate Polymers*, *199*,
 603-609.
- Zhou, L., He, H., Li, M.-C., Huang, S., Mei, C., & Wu, Q. (2018). Grafting polycaprolactone diol onto
 cellulose nanocrystals via click chemistry: Enhancing thermal stability and hydrophobic
 property. *Carbohydrate Polymers*, *189*, 331-341.
- Zoppe, J. O., Habibi, Y., Rojas, O. J., Venditti, R. A., Johansson, L.-S., Efimenko, K., Österberg, M.,
 & Laine, J. (2010). Poly(N-isopropylacrylamide) Brushes Grafted from Cellulose
 Nanocrystals via Surface-Initiated Single-Electron Transfer Living Radical Polymerization. *Biomacromolecules*, 11, 2683-2691.
- Zoppe, J. O., Xu, X., Känel, C., Orsolini, P., Siqueira, G., Tingaut, P., Zimmermann, T., & Klok, H.-A.
 (2016). Effect of Surface Charge on Surface-Initiated Atom Transfer Radical Polymerization
 from Cellulose Nanocrystals in Aqueous Media. *Biomacromolecules*, *17*, 1404-1413.