

### **EBSN2019: Electron Beam Spectroscopy for Nanophotonics 2019**

16-18 September 2019, Laboratoire de Physique des Solides (LPS), Orsay, France



Claiting

Comprendre le monde, construire l'avenir®

### STM-induced excitonic luminescence of a 2D semiconductor

D. Pommier<sup>1</sup>, R. Bretel<sup>1</sup>, L. E. Parra-Lópes<sup>2</sup>, F. Fabre<sup>2</sup>, A. Mayne<sup>1</sup>, E. Boer-Duchemin<sup>1</sup>, G. Dujardin<sup>1</sup>, G. Schull<sup>2</sup>, S. Berciaud<sup>2</sup>, <u>E. Le Moal</u><sup>1</sup>



<sup>1</sup> Institute of Molecular Sciences of Orsay, France
<sup>2</sup> Institute of Physics and Chemistry of Materials of Strasbourg, France

# Transition-Metal Dichalcogenides





(a) Ball-and-stick model of TMD monolayers

Clainte

- (b) Typical band structure for MoX<sub>2</sub> monolayers (DFT)
- (c) Schematics of the valence and conduction bands in a single-particle picture
- (d) Electroluminescence of a single layer MoS<sub>2</sub> field-effect transistor

TMD: *MX*<sub>2</sub> (*M* = Mo, W; *X* = S, Se, Te)

Strategic for future optoelectronic devices :

- Strong light-matter interactions
- Direct bandgap at the monolayer limit
- Excitonic effects at room temperature

Understanding TMD's properties requires investigations on the physics of excitons at the nanoscale.

## Experimental



STM-induced generation of excitons in 2D semiconductors has never been reported, up until now.

PARIS

### Our approach:

monolayer MoSe<sub>2</sub> on ITO/glass, no surface plasmons within the investigated frequency range, STM in air + optical microscopy with spatial, angular & spectral resolution.

Excitons in monolayer TMDs at room temperature may diffuse micrometers away from the excitation source before radiatively decaying.

D. Pommier, et al, Phys. Rev. Lett. 123, 027402 (2019)

Clantification

### **Emission mechanism**



Calification

#### STM-LE spectra match PL spectra

 $\rightarrow$  same emission mechanism:

radiative decay of A excitons in MoSe<sub>2</sub>

norendre le mond

(+ hot emission from B excitons).

This rules out other emission mechanisms (black-body radiation, radiative electronic transitions between tip and surface states)







STM-LE onset is at electron energies ( $eV_s$ ) as low as the *optical* bandgap of MoSe<sub>2</sub>.  $\rightarrow$  Resonance energy transfer (RET) from the tunneling current to the excitons in the semiconductor.

Differs from the diode-like mechanism (charge injection), which requires an energy level arrangement that does not occur at electron energies lower than the *electronic* bandgap.



UNIVERSITE PARIS SUD

omprendre le monde

Photon emission quantum

efficiency (photon/e-

10<sup>-8</sup>

10<sup>-9</sup>

**10**<sup>-10</sup>

FWHM

20 nm

P3

160

fold

1.0



## Conclusions



We report the observation of STM-induced excitonic luminescence from a 2D semiconductor.

Our approach, based on the absence of coupling to a plasmonic tip or nanocavity, makes it possible to probe locally the "native" excitonic properties of a 2D semiconductor.

The excited excitons may diffuse over micrometers from the STM tip before radiatively decaying; however, the exciton creation process itself is highly localized, which yields a lateral resolution on the order of 10 to 20 nm in photon maps.

Our results open up broad prospects for investigating the excitonic dynamics and the optoelectronic properties of 2D semiconductors at the nanoscale, which is a key to the development of all technologies based on 2D materials.

Thank you for your attention!



D. Pommier, et al, Phys. Rev. Lett. 123, 027402 (2019)



(a) Fourier-space optical image of the STM-LE measured on monolayer MoSe<sub>2</sub>.

Cliffe

(b-d) Theoretical emission patterns in Fourier-space, calculated for an oscillating point-like electric dipole on an air-glass interface.

The dominant emission process is the radiative decay of *bright* (spin-allowed) A excitons, which have their transition dipole moment in the plane of the monolayer.

1.5

UNIVERSITE PARIS

norendre le mon