



Growth and Polarized Spectroscopy of Red-Emitting Monoclinic Eu:CsGd(MoO₄)₂ Crystal with a Layered Structure

Anna Volokitina, Pavel Loiko, Anatoly Pavlyuk, Sami Slimi, Rosa Maria Sole,
Magdalena Aguiló, Francesc Diaz, Xavier Mateos

► To cite this version:

Anna Volokitina, Pavel Loiko, Anatoly Pavlyuk, Sami Slimi, Rosa Maria Sole, et al.. Growth and Polarized Spectroscopy of Red-Emitting Monoclinic Eu:CsGd(MoO₄)₂ Crystal with a Layered Structure. 2021 Conference on Lasers and Electro-Optics Europe & European Quantum Electronics Conference (CLEO/Europe-EQEC), Jun 2021, Munich, France. pp.1-1, 10.1109/CLEO/Europe-EQEC52157.2021.9542333 . hal-03368300

HAL Id: hal-03368300
<https://hal.science/hal-03368300v1>

Submitted on 7 Oct 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Growth and Polarized Spectroscopy of Red-Emitting Monoclinic Eu:CsGd(MoO₄)₂ Crystal with a Layered Structure

Anna Volokitina^{1,2,*}, Pavel Loiko³, Anatoly Pavlyuk⁴, Sami Slimi¹, Rosa Maria Solé¹, Magdalena Aguiló¹, Francesc Díaz¹, and Xavier Mateos¹

1. Universitat Rovira i Virgili (URV), Marcel·lí Domingo 1, 43007 Tarragona, Spain

*2. ITMO University, 49 Kronverkskiy Pr., 197101 St. Petersburg, Russia. *E-mail: anna.itmo@gmail.com*

3. Centre de Recherche sur les Ions, les Matériaux et la Photonique (CIMAP), UMR 6252 CEA-CNRS-ENSICAEN, Université de Caen

Normandie, 6 Boulevard du Maréchal Juin, 14050 Caen Cedex 4, France

4. A.V. Nikolaev Institute of Inorganic Chemistry, Siberian Branch of Russian Academy of Sciences, 3 Lavrentyev Ave., 630090 Novosibirsk, Russia

Trivalent europium ions (Eu³⁺) are known as luminescent centers leading to red emission of high color purity; the property utilized in red phosphors. Eu³⁺ ions are also recognized as structural probes (their luminescence is sensitive to the local site symmetry and its distortion). Recently, CW laser action was also demonstrated in certain Eu³⁺-doped crystals such as double tungstates KRE(WO₄)₂ (RE = Gd or Y) [1]. The laser operation was relying on the $^5D_0 \rightarrow ^7F_4$ transition corresponding to the deep-red spectral range (~700 nm). We report on the growth, structural study and polarized spectroscopy of another promising crystal, CsGd(MoO₄)₂, suitable for Eu³⁺ doping in high concentrations.

Single-crystals of cesium gadolinium double molybdate, 17 at.% Eu:CsGd(MoO₄)₂ (Eu:CsGdMo) were grown from the flux under low thermal gradients using cesium trimolybdate (Cs₂Mo₃O₁₀) as a solvent by A. Pavlyuk [2]. The as-grown crystals were transparent and had rose coloration, Fig. 1(a). Their structure (monoclinic, sp. gr. P2/c) was determined by powder XRD (lattice parameters: $a = 9.5180(8)$ Å, $b = 5.0775(3)$ Å, $c = 8.0791(4)$ Å, $\beta = 90.8998(0)$ °, obtained by the Le Bail method), Fig. 1(b). Eu:CsGdMo possesses a layered structure: the stacking of alternating layers – [Gd|EuO₈] - [MoO₄] – Cs – ... – occurs along the a -axis, Fig. 1(c). This determines the perfect natural cleavage of this material along the (100) plane, Fig. 1(d).




Fig. 1 17 at.% Eu:CsGdMo crystal: (a) Photograph of the as-grown crystal, the growth direction is along the [100] axis; (b) X-ray powder diffraction (XRD) pattern showing the Le Bail refinement, (hkl) – Miller's indices; (c) fragment of structure: a supercell ($2a \times 2b \times 2c$) in projection to the a - c plane; (d) ESEM image of a cleaved crystal plate (side view).

Under excitation by an UV lamp, Eu:CsGdMo provides intense red emission, see Fig. 2(a). Its color coordinates (CIE 1931) are determined. Eu³⁺ ions in CsGdMo exhibit extremely strong polarization-anisotropy of emission properties, Fig. 2(b), which is due to the low symmetry of the rare-earth site (C₂) and the layered crystal structure. The observed emissions originate from the $^5D_0 \rightarrow ^7F_J$ ($J = 1 \dots 6$) Eu³⁺ transitions. No spectroscopic evidence of Eu²⁺ species is found. The most intense emission at ~614 nm is due to the ED allowed transition to the 7F_2 multiplet. The stimulated-emission (SE) cross-sections, σ_{SE} , for the potential laser transition, $^5D_0 \rightarrow ^7F_4$, are determined using the experimental branching ratio $\beta_{JJ'}$ of 15.9%, see Fig. 2(c). The maximum σ_{SE} is $1.81 \times 10^{-20} \text{ cm}^2$ at 703.3 nm for light polarization $E \parallel b$. The luminescence decay from the metastable 5D_0 state is single exponential with a luminescence lifetime $\tau_{lum} = 693 \mu\text{s}$. Highly-doped Eu:CsGdMo crystals are promising for solid-state lighting and laser applications.




Fig. 2 Emission properties of Eu³⁺ ions in monoclinic CsGdMo: (a) photograph of red luminescence under excitation by an UV lamp; (b) polarized luminescence spectra, $\lambda_{exc} = 488$ nm; (c) SE cross-sections, σ_{SE} , for the $^5D_0 \rightarrow ^7F_4$ transition; (d) luminescence decay curve, $\lambda_{exc} = 532$ nm, $\lambda_{lum} = 616$ nm.

The reported study was funded by RFBR, project number 19-32-90199.

References

- [1] V. I. Dashkevich, S. N. Bagayev, V. A. Orlovich, A. A. Bui, P. A. Loiko, K. V. Yumashev, A. S. Yasukevich, N. V. Kuleshov, S. M. Vatnik, and A. A. Pavlyuk, “Red Eu,Yb:KY(WO₄)₂ laser at ~702 nm,” *Laser Phys. Lett.* **12**(8), 085001 (2015).
- [2] P. Loiko, A. Pavlyuk, S. Slimi, R. M. Solé, E. B. Salem, E. Dunina, A. Kornienko, P. Camy, U. Griebner, V. Petrov, F. Díaz, M. Aguiló, and X. Mateos, “Growth, spectroscopy and laser operation of monoclinic Nd:CsGd(MoO₄)₂ crystal with a layered structure,” *J. Lumin.* **231**, 117793-1-10 (2021).