

The brown seaweed Cystoseira schiffneri as a source of sodium alginate: Chemical and structural characterization, and antioxidant activities

Abdelkarim Benslima, Sabrine Sellimi, Marwa Hamdi, Rim Nasri, Mourad

Jridi, Didier Cot, S.M. Li, Moncef Nasri, Nacim Zouari

▶ To cite this version:

Abdelkarim Benslima, Sabrine Sellimi, Marwa Hamdi, Rim Nasri, Mourad Jridi, et al.. The brown seaweed Cystoseira schiffneri as a source of sodium alginate: Chemical and structural characterization, and antioxidant activities. Food Bioscience, 2021, 40, pp.100873. 10.1016/j.fbio.2020.100873 . hal-03369728

HAL Id: hal-03369728 https://hal.science/hal-03369728

Submitted on 7 Oct 2021

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

1	The brown seaweed Cystoseira schiffneri as a source of sodium alginate: Chemical and
2	structural characterization, and antioxidant activities
3	
4	
5	
6	Abdelkarim Benslima ^{1,2} , Sabrine Sellimi ¹ , Marwa Hamdi ¹ , Rym Nasri ¹ , Mourad Jridi ^{1,3} ,
7	Didier Cot ⁴ , Suming Li ⁴ , Moncef Nasri ¹ and Nacim Zouari ^{1,2*}
8	
	¹ Laboratory of Enzyme Engineering and Microbiology, Engineering National School of Sfax (ENIS), University of Sfax, Sfax, Tunisia
9	² High Institute of Applied Biology of Medenine (ISBAM), University of Gabes, Medenine,
10	Tunisia
11	³ Higher Institute of Biotechnology of Beja (ISBB), University of Jendouba, Beja, Tunisia.
12	⁴ European Membrane Institute, UMR CNRS 5635, University of Montpellier, Montpellier
13	Cedex 5, France
14	
15	*Corresponding author: Pr Nacim Zouari, ISBAM, University of Gabes, 4100 Medenine,
16	Tunisia. Phone: +216 97750220; E-mail address: znacim2002@yahoo.fr
17	
18	
19	
20	Running title:
21	Sodium alginate from Cystoseira schiffneri
22	
23	
24	

25 Abstract

26 Sodium alginates were extracted from brown seaweeds (Cystoseira schiffneri) 27 collected from a Tunisian island (Kerkennah, Sfax) in different seasons (December, April, July and September). The structural features and antioxidant properties of C. schiffneri 28 29 sodium alginates (CSSA) were characterized. Micro-elementary analysis showed the absence 30 of nitrogen and sulfur in alginate fractions. All alginate isolates were high in uronic acids (47.4-66.4%) and ash (24.3-39.4%). ATR-FTIR, NMR and circular dichroism data showed 31 32 that all CSSA were of the polyguluronate-type. Average molecular masses determined using 33 high performance size exclusion chromatography showed variations ranging from 4.49 to 1230 kDa. Thermogravimetric analysis suggested that CSSA were stable until 400°C except 34 35 for that collected in September, which was observed to only be stable until 200°C. Antioxidant activity of CSSA from different seasons was measured using DPPH• radical-36 scavenging, reducing power and Fe²⁺ chelating ability assays. Antioxidant potential of CSSA 37 38 varied significantly with respect to the season and the main factor controlling antioxidant 39 properties was the molecular mass.

40 Keywords: brown seaweed; *Cystoseira schiffneri*; sodium alginate; polyguluronate;
41 antioxidant activities.

42

43

44

- 45
- 46

47

48

50 **1. Introduction**

51 Seaweeds are known for their bioactive polysaccharides (Sanjeewa et al., 2017; Zhao 52 et al., 2018; Rengasamy et al., 2020). Algal polysaccharides are biodegradable, non-toxic and 53 biocompatible (Liu et al., 2015). Alginates are a family of linear copolymers containing 54 blocks of (1,4)-linked β -D-mannuronic acid (M) and α -L-guluronic acid (G) residues. Blocks 55 are composed of consecutive G residues or M residues or alternating M and G residues (Yang 56 et al., 2011). Structural features of alginates vary depending on species, season, geographic 57 location, among other parameters (Setyawidati et al., 2018). Alginates possess numerous 58 biological activities including antioxidant (Kumar et al., 2019; Sellimi et al., 2015), 59 antimicrobial(Li et al., 2017) and gastroprotective activities (Ammar et al., 2018). Their biological properties are closely related to the proportion and distribution of M and G residues 60 61 as well as the molecular mass (MM).

Companies may use synthetic antioxidants, such as butylated hydroxyanisole (BHA) and butylated hydroxytoluene (BHT) to control oxidation (Lorenzo et al., 2013). However, the use of these synthetic compounds has been linked to carcinogenic effects (KahlandKappus, 1993). Moreover, free radicals are the main cause of many diseases, such as diabetes, cancer and neurodegenerative pathologies (Liu, 2020). A protection could occur when free radicals were neutralized or trapped by antioxidant compounds (Schramm et al., 2003). Naturally occurring antioxidants may be able to replace these synthetic compounds.

69 The brown seaweed *Cystoseira schiffneri*, collected from Kerkennah island during 4 70 seasons, was chosen as a natural matrix to extract and evaluate bioactive polysaccharides. The 71 annual cycle of the Mediterranean *Cystoseira* passes through a growth period between 72 February and May, a breeding period from June-July to August-September followed by a rest 73 period between October and December (Pellegrini et al., 1997). Hence, the current study aims

to assess the effect of seasonal variation on the structural features and antioxidant activities of *C. schiffneri* sodium alginate (CSSA).

76 2. Material and methods

77 2.1. Reagents

1,1-Diphenyl-2-picrylhydrazyl (DPPH•), butylated hydroxyanisole (BHA), ethylene
diamine tetra-acetic acid (EDTA), 3-(2-pyridyl)-5,6-diphenyl-1,2,4-triazine-disulfonic acid
monosodium salt hydrate (ferrozine), Folin-Ciocalteu's reagent, phloroglucinol, glucose,
guluronic acid, sodium carbonate (Na₂CO₃), hydrochloric acid (HCl), ferrous chloride
(FeCl₂), 3,5 dimethylphenol, trichloroacetic acid (TCA), potassium ferrocyanide (C₆FeK₄N₆),
sulfuric acid (H₂SO₄), acetone, methanol, chloroform, 95% ethanol and other chemicals were
purchased from Sigma Chemical Co. (St. Louis, MO, USA).

85 2.2. Sample collection and preparation

86 The Cystoseira schiffneri samples were collected from Kerkennah islands (Tunisia) 87 around the point (34°39'30.07"N, 11°8'12.27"E) during low tide. Collections were done in 88 different seasons (December 2015, and April, July and September 2016). The identification of 89 collected seaweed was made by Pr. Asma Hamza from the National Institute of Marine 90 Science and Technology (Sfax, Tunisia). Seaweed fronds were washed with sea water to 91 eliminate impurities, and then transported to the laboratory in dark plastic bag for a period not 92 exceeding 12 h. Once arrived, seaweed fronds were washed with tap water followed by 93 distilled water to eliminate salts. After that, they were dried away from sunlight at room temperature (25°C) for 20 days until reaching stable moisture. Dried fronds were ground 94 95 using a coffee grinder (Moulinex, Mayenne, France) and sieved through a 200 µm mesh size. The powders were conserved at room temperature for a maximum of 8 wk in dried and sealed 96 97 dark glass containers.

2.3. Sodium alginate extraction

99 Crude sodium alginate extraction was done as previously described by Sellimi et al. 100 (2015). C. schiffneri powder (50 g) was defatted and depigmented using maceration twice (24 101 h, 30°C, 200 rpm) in acetone:methanol (7:3, v:v) (500 ml) followed by chloroform (300 ml). 102 Depigmented and defatted powder was air-dried, then demineralized by incubation (2 h, 103 60°C, 250 rpm) in 110.1 M HCl (pH 2). After cooling at room temperature, the residues were 104 recovered using centrifugation (20 min, 4000 $\times g$) in a Rotofix 32 centrifuge (Hettich, 105 Tuttlingen, Germany), washed with distilled water until neutral pH and then treated in 3% 106 Na₂CO₃ solution (pH11) for 2 h at 60°C and 250 rpm to solubilize alginate in the sodium salt 107 form. After centrifugation (20 min, 4000 $\times g$), the supernatant was recovered and two volumes 108 of absolute ethanol were added. Mixtures were left for 12 h at 4°C to precipitate sodium 109 alginate. The precipitated sodium alginate was suspended in distilled water and acidified 110 using 6 M HCl (pH 3) to allow gelation and thereby precipitation of alginate in its acidic 111 form. Precipitated alginic acids were recovered using centrifugation (20 min, 4000 $\times g$), then 112 suspended in distilled water and neutralized to pH 7.5 using 6 M NaOH. The crude sodium 113 alginate was precipitated using two volumes of absolute ethanol, dissolved again in distilled 114 water and lyophilized (Bioblock Scientific Christ ALPHA 1-2, IllKrich-Cedex, France). The 115 crude alginates extracted from C. schiffneri collected at December, April, July and September 116 were referred to AD AA AJ and AS, respectively.

117 2.4. Chemical analysis

The total sugars were determined using the method of Dubois et al. (1956). Briefly, to 0.3 ml CSSA solution (0.1 g/ml), 1 ml 5% phenol solution and 5 ml 12 NH₂SO₄ were added. The mixture was incubated for 20 min at 30°C then the optical density was measured, using a spectrophotometer (T70 UV-visible spectrometer PG Instruments Ltd., Lutterworth, England), at 490 nm against a standard curve prepared using glucose. The uronic acids (U) were determined using the method of Scott (1979). To 0.3 ml CSSA solution (0.1 g/ml), 5 ml 12 N H₂SO₄ and 0.3 ml of a solution containing 20 g/l NaCl and 30 g/l H₃BO₃ were added. The mixture was incubated at 70°C for 40 min, then cooled to room temperature for 1 h before adding 0.2 ml 3,5-dimethylphenol. After 10 min at room temperature, the absorbance was measured at 400 and 450 nm against a standard curve of galacturonic acid. U (%) were calculated using equation 1.

129 U (%) =
$$(\Delta A \times V \times D \times C_s \times 0.91 \times 100)/(\Delta A_s \times m)(1)$$

130 Where ΔA = the difference in absorbance, V = the total solution volume (ml), D = the 131 sample dilution, Cs = the standard concentration, ΔAs = the difference in the absorbance of 132 the standard (100 µg/ml), m = the mass of the test sample (mg), and 0.91 is the conversion 133 factor of the experimental determination of monosaccharides to polysaccharides.

Total phenolics were determined using slightly modified methods described by Cicco et al. (2009). Phloroglucinol was used as the standard. Briefly, 100 μ l of sample solution (2 mg/ml) was mixed with 100 μ l 2 N Folin-Ciocalteu's reagentand 800 μ l 5% Na₂CO₃solution. The mixture was incubated at 40°C for 20 min, then absorbancies were measured at 760 nm against a standard curve of phloroglucinol.

139 2.5. *Micro-elementary analysis*

Elemental composition of CSSA was done using an EDX analyzer (X-Max ^N SDD
EDX Instrument, Oxford, UK). Results were treated using Oxford AZTEC software 2011
(Oxford Instruments, Abingdon, UK). The samples were metalized previous to analyses using
a Quorum Technologies metalizer (Quorum Technologies, Guelph, ONT, Canada).

144 2.6. Circular dichroism

A Jasco J-815 CD spectrometer (Jasco Corp., Tokyo, Japan) was used to obtain circular dichroism spectrum in the range of 190-260 nm. The sample solution was at a concentration of 0.25 mg/ml. A circular dichroism spectrum is often reported in ellipticity 148 degrees (θ) expressed as milli-degrees. The ratio of peak height to trough depth was 149 calculated using equation 2 (Morris et al., 1980).

150

Peak/trough ratio = $(q_{trough} - q_{peak})/q_{trough}(2)$

151 2.7. ATR-FTIR spectroscopy

Attenuated total reflectance (ATR)-Fourier transform infrared (FTIR) spectra of CSSA were obtained in the range of 4000–600 cm⁻¹ at room temperature using 30 scans and 4 cm⁻¹ resolution. A FTIR Spectrum 100 spectrometer (Perkin-Elmer, Norwalk, CT, USA) with ATR accessory containing a diamond/ZnSe crystal was used to obtain infrared spectrums.

156 2.8. NMR spectroscopy analysis

157 ¹H-NMR spectra were obtained using a Bruker 300 spectrometer (Bruker Biospin AG, 158 Fallanden, Switzerland) at 60°C. Results were treated using Mestre Nova (MNova) software 159 version 5.3.0 (Mestrelab Research S.L., Santiago de Compostela, Spain). Samples were 160 deuterium-exchanged using lyophilization with D₂O and then studied as 1% (m/v) solutions in 161 D₂O (99.96%). Signals in the anomeric region (4.4-5.1 ppm) were studied to determine the 162 CSSA structure. Therefore, F_M, F_G, F_{GG}, F_{MM}, F_{GM} and F_{MG} blocks of CSSA were calculated 163 based on the areas of signals (I), (II) and (III) (Fertah et al., 2017) and using equations 3, 4,5, 164 6 and 7. In addition, M/G ratio can be calculated based on the equation 8.

- 165 $F_G = A_I / (A_{II} + A_{III})$ (3)
- 166 $F_M = 1 F_G(4)$
- $167 F_{GG} = A_{III}/(A_{II} + A_{III}) (5)$
- 168 $F_{MG} = F_{GM} = F_G F_{GG}(6)$
- 169 $F_{MM} = F_M F_{MG}(7)$
- 170 $M/G = F_M/F_G(8)$

171

2.9. MM distribution

172 The number-average molecular mass (Mn), the average molecular mass (M) and 173 polydispersity index (PDI) of CSSA were determined using a Waters Alliance model 174 GPCV2000 (Waters, Milford, MA, USA). High performance size exclusion chromatography 175 (HPSEC) equipped with a multi-angel laser light scattering (MALLS) detector from Wyatt 176 (Wyatt Technology, Santa Barbara, CA, USA). Before injection, the apparatus was calibrated with toluene and normalized with a solution of polyethylene oxide (72 kDa) in 0.1 M NaCl 177 178 and the samples were filtered through a 0.45 µm pore size membrane (Merck, Darmstadt, 179 Germany). The sample (100 µl) of 3 mg/ml was injected in a column TSK-G2000 SWXL (7.8 180 \times 300 mm). Elution was carried out at 25°C using 0.1 M NaCl as eluent at a flow rate of 0.5 181 ml/min. The refractive index increment (dn/dc) was 0.155. Data collected from the refractive 182 index detector (RID) and MALLS were treated using ASTRA software version 4.72.03 183 (Wyatt Technology, Goleta, CA, USA).

184 *2.10. Thermogravimetric analyses*

Thermogravimetric analyses (TGA) of the extracted sodium alginates were done on a
TGA Q500 instrument (TA Instruments, Newcastle, DE, USA). Nitrogen flow rate was 60
ml/min and the temperature increase from 20 to 1000°C by 20°C/min.

188 2.11. Rheological analysis

189 Rheological analyses of sodium alginates solutions (3%,m/v) from different seasons 190 were done on a Physica MCR 301 rheometer (Anton-Paar GmbH, Graz, Austria) using the 191 dispositive plan-plan 50 with a measurement gap of 0.1 mm and temperature of 20°C. 192 Viscosity was measured as a function of shear rate (0.1-100 s⁻¹). Storage modulus (G') and 193 loss modulus (G'') were measured as a function of frequency (2-100 Hz).

194 *2.12. Antioxidant activity*

195

2.12.1. DPPH• radical-scavenging activity

196 Radical-scavenging activity was measured as described by Kirby and Schmidt(1997) 197 with slight modifications. Sample solutions were prepared at different concentrations from 198 0.125 to 1.5 mg/ml. In each tube, 500 µl of the sample solution was reacted with 375 µl of 199 ethanol solution and 125 µl of DPPH• solution (0.2 mM in ethanol) as the free radical source. 200 The reaction mixtures were incubated for 60 min in the dark at room temperature and the 201 reduction of DPPH• radical was measured at 517 nm. Control (without sample) and blanks 202 (without DPPH•) were prepared. Results of DPPH• scavenging activity are shown as IC₅₀ 203 values (µg/ml), defined as the extract concentration needed to scavenge 50% DPPH•.

204

2.12.2. Reducing power

205 Ferrous reducing activity was measured as previously described by Yildirim et al. 206 (2001). Sample solutions were prepared at different concentrations from 50 to 500 μ g/ml. 207 Sample solution (0.5 ml) was added to 1.25 ml 0.2 M sodium phosphate buffer (pH 6.6) and 208 1.25 ml 1% (m/v) potassium ferrocyanide. Mixtures were incubated for 30 min at 50°C. After 209 incubation, 1.25 ml 10% (m:v) TCA was added and the mixture was centrifuged at 11000 $\times g$ 210 for10 min. From each supernatant, 1.25 ml was transferred and diluted with 1.25 ml ultrapure 211 water. Finally, FeCl₃ (250 μ l) were added and absorbancies were measured at 700 nm after 10 212 min incubation at room temperature. Blanks without FeCl₃ were prepared for each 213 concentration. The reducing power is shown as the extract concentration ($EC_{0.5}$) providing 0.5 214 absorbance at 700 nm.

215 2.12.3. Fe^{2+} chelating ability

The CSSA capacity to complex ferric ions were measured using the method reported by Carter (1971). Sample solutions were prepared at different concentrations from 0.1 to 1 mg/ml. Briefly, 100 μ l of sample solution, 50 μ l 2 mM FeCl₂ and 450 μ l distilled water were mixed and incubated for 3 min at room temperature. Volumes of 200 μ l 5 mM ferrozine were added and mixtures were incubated again at room temperature for 10 min before measuring absorbancies at 562 nm. Blanks without ferrozine and control without sample were prepared. Results of metal (Fe²⁺) chelating ability are shown by IC₅₀ values (μ g/ml), defined as the extract concentration needed to chelate 50% Fe²⁺.

224 2.13. Statistical analysis

All analytical determinations were done in triplicate. One-way analysis of variance (ANOVA) was done using the statistical package for the social sciences (SPSS) software for WindowsTM (version 17, SPSS Inc., Chicago, IL, USA). Duncan's multiple range tests (p<0.05) was used to compare the average responses between samples.

229 **3. Results and discussion**

3.1.Extraction yield

231 The extraction yields of CSSA from different seasons are shown in Table 1. Extraction 232 yield of AJ was higher than AA and AD. While, AS showed the lowest extraction yield. The 233 results were comparable to those reported for Dictyota dichotoma (20.9%), Padina 234 boergesenii (24.3%) and Sargassum tenerrimum (32.6%) (Parthiban et al., 2012), but 235 significantly higher than those of D. caribaea (7.4%) and P. perindusiata (5.4%) (García-Ríos 236 et al., 2012). Alginate extraction yield is dependent on the season and thereby the 237 development stage of C. schiffneri. Kumar and Sahoo (2017) reported that the highest alginate 238 yield from S. wightii was obtained in March (32%), however, the lowest one (24%) was 239 obtained in July. Setyawidati et al. (2018) described that extraction yields of alginate from S. 240 aquifolium were higher during the dry season (May, June) (39%) than during the wet season 241 (November) (24%). On the other hand, *P. boryana* showed extraction yields of 9% during the 242 wet season against 6% during the dry season. Therefore, the seasonal variation of alginate 243 yield did not follow one trend line for all species.

3.2. Chemical analysis

245 Moisture, ash, total phenolics, total sugars and U of CSSA from different seasons are 246 shown in Table 1. High amounts of U and ash were observed for all seasons, while markedly 247 low amounts of total sugars were measured. However, traces of phenolic compounds were 248 found. U and neutral sugars of CSSA were comparable to those of C. barbata alginate (58.1 249 and 9.3%, respectively) (Sellimi et al., 2015). Similarly, Ammar et al. (2018) showed that U 250 are 60% for three species C.compressa, P. pavonica and *Dictyopteris* 251 membranacea. Similarly, alginate isolated from C. compressa had traces of phenolic 252 compounds (1.11%) (Hentati et al., 2018). Standard alginates also showed the presence of 253 impurities. Dusseault et al. (2006) detect proteins (5.9 mg/g) and polyphenols (13.8 AFU) in 254 food-grade sodium alginate.

255

3.3. Elementary analysis

The elemental composition of CSSA from all seasons is shown in Table 1. High levels of carbon, oxygen and sodium while low contents of Mg, Cl, Si and K were measured. Sulfur and nitrogen were not found, which indicated the absence of proteins and fucans in the extracted alginates. Elementary analysis therefore suggested that CSSA fractions occurred as a sequence of U linked predominately to sodium ions.

3.4. FTIR spectroscopy

Fig. 1. shows the spectral data relative to the ATR-FTIR spectroscopy analysis of the CSSA fractions. The bands at 3354 and 2935 cm⁻¹ were assigned to O–H and C–H stretching vibrations, respectively (Hentati et al., 2018). Signals at 1605 and 1423 cm⁻¹ were attributed, respectively to asymmetric and symmetric C=O stretching vibrations. The band at 1025 cm⁻¹ assigned to C-O-C of glycosidic linkage was the polysaccharides characteristic band (Hentati et al., 2018). The bands, in the anomeric region (750-950 cm⁻¹), were assigned to U residues (Chandía, 2001; Chandía et al., 2004). The peak ratio at 1125 and 1025 cm⁻¹ allows the estimation of M/G ratio (Gómez Ordóñez and RupérezAntón, 2011). Overall, the estimated
M/G ratios of CSSA for the 4 seasons ranged between 0.062 and 0.065 (Table 2), which
suggest that all CSSA were of the polyguluronate-type.

272 3.5

3.5. Circular dichroism

273 The M/G ratios of sodium alginate fractions could also be determined from circular 274 dichroism spectra based on the empirical correlation between the peak (~195 nm) to depth 275 (~205 nm) ratio (Morris et al., 1980). The CSSA spectra showed that peaks ~195 nm were 276 almost absent for all samples (Fig. 2). Therefore, the calculated M/G ratios did not exceed 277 0.022 (Table 2). The CSSA fractions were, therefore, composed essentially by G residues, 278 which confirmed the FTIR data. Ramos et al. (2018) reported that low M/G ratio of alginates 279 resulted in strong and big gels with interactions with calcium ions. The CSSA fractions seem 280 to be interesting for strong gels applications and this during all algae development stages.

281 *3.6. MM distribution*

MM distributions of CSSA were determined and results are shown in Table 3. For all seasons, the CSSA fractions were polydisperse (PDI>1). The polydispersity may be due to the use of the whole thalli. Handå et al. (2013) reported that alginate MM varied as a function of the thalli part. Hence, the MM of alginate was an average over the whole distribution.

The highest MM was obtained for AD, followed by AJ, AA and AS. The AA and AJ fractions had MM comparable to commercial sodium alginates CR8133 (M = 90-180 kDa) and CR8223 (M= 250-350 kDa), respectively (Ramos et al., 2018). MM of CSSA for all the seasons, except for December, were observed to be lower than those of sodium alginates extracted from 8 species of *Saccharina* (511-616 kDa) (Suzuki et al., 2016).

The important variation noted between seasons for MM may be related to the life cycle of *C. schiffneri*. In December at the rest period thalli are formed entirely of old stems characterized by high MM. In April, during the growth period new stems with low MM appear on old stems and continue growing gaining higher MM. In September, after
reproduction it appears new thalli formed entirely by the new stems that are characterized by
low MM (Handå et al., 2013)

297

3.7. NMR spectroscopy analysis

298 ¹H-NMR spectra of CSSA from the different seasons are shown in Fig. 3. Characteristic 299 bands were observed to be around 1.5, 2.0, 4.5, 5.0 and 5.5 ppm for all the seasons. The 300 distribution of M and G could be studied based on signals from the anomeric region (Fertah et 301 al., 2017). Signal (I) that correspond to G-1 anomeric proton of G was obtained at 5.35 ppm. 302 Signal (II), that was due to the overlap between the M anomeric proton (M-1) and the C-5 of 303 the alternating blocks (GM-5), was obtained at 4.93 ppm. Similarly, signal (III) characterizing 304 H-5 G proton (GG-5G) was obtained at 4.84 ppm. The calculated F_G, F_M, F_{GG}, F_{MM}, F_{MG} and 305 F_{GM} are shown in Table 4. The results of the calculated M/G ratios (Table 2) were consistent 306 with the circular dichroïsm and FTIR spectroscopy data, in which the CSSA fractions were 307 defined as polyguluronates. Higher M/G ratios were described by Mohammed et al. (2020) 308 (M/G=0.45), Okolie et al.(2020) (M/G=0.87), Davis et al. (2003) (M/G=0.19) and Larsen et 309 al. (2003) (M/G=0.45). There were no previous studies describing comparable or lower M/G 310 ratios. The CSSA fractions might be the first reported as polyguluronates. The results for 311 structural composition showed through the year high F_G and F_{GG} values and low F_M, F_{MM} and 312 F_{MG} values. These results suggested that CSSA fractions were composed essentially by G 313 blocks punctuated with low amounts of M and MG blocks. Gelling properties of alginate are 314 related to G blocks responsible for the "Egg Box" structure (Xiao et al., 2015). High F_{GG} 315 values for CSSA fractions with high M/G ratio suggested the possibility to form a strong and 316 rigid gel.

317 Results for the M/G ratio determined using three methods suggested that through the 318 year the CSSA fractions were of the polyguluronate-type with low amounts of M. However,

the values obtained from one method to another. Hence, it should be pointed out that the M/G ratio calculated from FTIR spectra were only an approximation. The circular dichroism, which determines the ratio of M to G based on empirical correlation, gives more accurate results. Overall, NMR spectra gave the best calculations not only for the M/G ratio but also for GGG, MGM, MG, MM, GGM and MGG. Hence, Hentati et al.(2018) reported that NMR is the only reliable and accurate method to study the alginate structure.

325

3.8. Thermogravimetric analysis

326 The mass losses of CSSA from the 4 seasons as function of temperature are shown in Fig. 4. Idris et al. (2012) reported that the combustion had three phases namely drying (50-327 328 220°C), pyrolysis (220-500°C) and char combustion (>500°C). The first mass loss was 329 attributed to the evaporation of non-bonded water and it occurred between 50 and 150°C 330 (Mallick et al., 2018). The second mass loss, between 150 and 220°C, was assigned to the loss 331 of bonded water. Fig. 4 shows that the most important mass loss was observed around 400°C 332 for all CSSA fractions, except for AS (around 200°C), which was due to the degradation of 333 the osidic monomers. The decrease of temperature degradation of AS compared to others 334 alginates could be related to their lower MM. Mallick et al. (2018) reported that low MM 335 molecules had high volatility and could therefore accelerate degradation. Differences among 336 seasons could be explained by the MM differences and the presence of minerals. López-337 González et al. (2014) reported that alkali metals catalyzed combustion that was characterized 338 by multiple and small mass losses.

- 339 *3.9. Rheological properties*
- 340 *3.9.1 Rotational analysis*

341 The viscosities of AA, AJ and AS decreased with shear rates indicating a shear-342 thinning behaviors (Fig. 5). However, Newtonian behavior was observed for AD at shear rates 343 $>10 \text{ s}^{-1}$ indicating that the CSSA flow has encountered more resistance at high shear rate 344 (Benchabane and Bekkour, 2008). Comparable viscosities were observed for all the seasons 345 except for AD that showed low viscosity. The difference of AD behavior from other CSSA 346 fractions might be related to its higher MM giving more intermolecular entanglements. 347 Comparable results were shown by Rezende et al. (2009) for alginate showing shear-thinning 348 behaviors. Hentati et al. (2020) reported that at low concentrations (0.25-2%) of C. compressa 349 alginate, shear-thinning behavior was observed at low shear-rates that turn to Newtonian 350 behavior at high shear-rates. However, at high concentrations (3-5%) only shear-thinning 351 behaviors were shown. The shear-thinning behavior observed for the CSSA fractions 352 facilitates the flow compared with a Newtonian fluid allowing high flow rates for equal 353 pressures (Rezende et al., 2009).

354 3

3.9.2. Oscillatory analysis

The increase in G' for AD with increasing frequencies suggested that elastic behavior becomes dominant (Fig. 6). However, for AA, AJ and AS, G' remained almost constant with the increase of frequency indicating no elastic behavior for alginate solutions (Böhning et al., 2019). All samples showed viscous liquid-like behavior as the G'' values were greater than the G' for all the samples (Hentati et al., 2020). The elastic behavior of AD seemed to be due to the high MM. However, the CSSA from other seasons should be considered as non-viscous liquids, which could be important for some manufacturing uses (Rezende et al., 2009).

- *362 3.10. Antioxidant activity*
- 363

3.10.1. DPPH• radical-scavenging ability

The DPPH• radical-scavenging test reflects the ability of a sample to stabilize free radicals by donating a proton. Fig. 7 shows the concentration dependent radical-scavenging activity of CSSA and the IC_{50} values are shown in Table 5. The AS with the lowest MM showed the lowest IC_{50} value and therefore the best activity. However, radical-scavenging activity of CSSA remained lower than that of BHA. Overall, the CSSA fractions were

369 observed to show higher antiradical activity than alginate hydrolysates (IC₅₀=10.4 mg/ml) 370 (Zhu et al., 2016). However, Hentati et al. (2018) reported that C. compressa sodium alginate 371 with MM of 1.105 g/mol had higher activity (IC₅₀ = 560 μ g/ml) than those of AD, AA and 372 AJ, but remained lower than that of AS. A positive correlation between radical-scavenging 373 activity at 1500 μ g/ml and MM (R²=0.31) was observed. Therefore, the main factor 374 controlling the antioxidant properties of sodium alginates seems to be the MM. Accordingly, 375 Kelishomi et al. (2016) showed that radical-scavenging activity of alginates was inversely 376 proportional to the MM. Higher MM polysaccharides had a more compact structure, resulting 377 in stronger intramolecular hydrogen bonds and thus restricting the hydrogen groups. 378 Therefore, the access of active groups to oxidant molecules is more difficult.

379

3.10.2. Reducing power

380 The ability of CSSA to stabilize oxidants by donating an electron was measured and 381 results are shown in Fig. 7. The CSSA fractions showed a reducing power in a concentration-382 dependent manner and the $EC_{0.5}$ values are shown in Table 5. The highest activities were 383 obtained for AS and AD followed by AJ. However, the EC_{0.5} values of CSSA from all seasons 384 remained lower than that of BHA. All CSSA fractions, except AA, showed higher reducing 385 power than that of C. barbata sodium alginate (absorbance of 0.7at 0.5 mg/ml) (Sellimi et al., 386 2015). Comparable results to AJ were reported for C. compressa sodium alginate that showed 387 absorbance ~1 at 0.5 mg/ml (Hentati et al., 2018). The reducing power of polysaccharides 388 was directly related to their MM and to the hydroxyl and carboxyl groups of U (Raza et al., 389 2011; Shang et al., 2018). However, the present study showed contradictory results, where the 390 reducing abilities of CSSA fractions were not correlated with either their MM or their U. 391 However, inconsistent results were also described by others. Cheng et al. (2013) indicated that 392 polysaccharide fractions from *Epimedium acuminatum* with high MM had high antioxidant 393 activity. Kardošová and Machová (2006) reported that for some polysaccharides and oligosaccharides the MM was not correlated with the antioxidant levels. Hence, the MM-antioxidant activity relation of alginate is still uncertain.

396

3.10.3. Fe^{2+} chelating ability

The chelating abilities of CSSA was dependent on the concentration and the results are 397 398 shown in Fig. 7, and the IC₅₀ values are shown in Table 5. The highest activity was obtained for AS followed by AD and AJ, while the lowest Fe^{2+} chelating ability was measured for AA. 399 400 Nevertheless, the CSSA from all the samples showed lower chelating abilities than EDTA. The AS, which had the lowest MM, had the highest Fe^{2+} chelating ability. These results were 401 consistent with the results of Wang et al. (2016) who reported that the Fe²⁺ chelating ability of 402 403 polysaccharides decreased with increased MM. However, AD with higher MM showed higher 404 chelating ability. Similarly, Cheng et al. (2013) reported that polysaccharide fractions from 405 Epimedium acuminatum with high MM had more antioxidant activity. Kardosová and 406 Machová (2006) showed that MM of some polysaccharides and oligosaccharides was not 407 significantly related to the antioxidant properties. The chelating ability was mostly due to OH, 408 -COOH, -C=O and -O-groups (Wang et al., 2016). The relationships between antioxidant 409 activity and physico-chemical properties or structural features have not been comprehensively 410 elucidated and confirmed. Conflicting results have been observed in the literature. Extraction 411 source and methods, and even drying procedures can influence the results. Furthermore, other 412 antioxidant substances, such as polyphenol may be retained in polysaccharides fractions and 413 should be taken into account. Overall, the antioxidant potential of polysaccharides is not 414 determined by a single factor but a combination of several related ones (Wang et al., 2016).

415 **4. Conclusion**

The seasonal variation effect on structural features and antioxidant activities of sodium alginate extracted from *C. schiffneri* (CSSA) was studied. The isolated alginates fractions were of the polyguluronate-type and most of them were stable until 400°C. The CSSA showed season-dependent structural characteristics and antioxidant activities. The technofunctional properties of the CSSA should be studied and compared to commercial alginates.
The CSSA might be used in a variety of applications including food and biomedical
formulations.

423 Acknowledgments

Financial assistance for this study was provided by the Ministry of Higher Education and Scientific Research, Tunisia and supported by the Utique-PHC program (project SEAPOLYMERHYDROGEL) N° 19G0815 of the CMCU funded by the Ministry of Higher Education and Scientific Research, Tunisia.

428 **Conflicts of interest**

429 The authors confirm that they have no conflicts of interest with respect to the study430 described in this manuscript.

431 **References**

Ammar, H. H., Lajili, S., Sakly, N., Cherif, D., Rihouey, C., Le Cerf, D., Bouraoui, A.,
&Majdoub, H. (2018). Influence of the uronic acid composition on the
gastroprotective activity of alginates from three different genus of Tunisian brown
algae. *Food Chemistry*, 239, 165–171.
https://doi.org/10.1016/j.foodchem.2017.06.108

437

Benchabane, A., &Bekkour, K. (2008). Rheological properties of carboxymethyl cellulose
(CMC) solutions. *Colloid and Polymer Science*, 286(10), 1173.
https://doi.org/10.1007/s00396-008-1882-2

Böhning, M., Frasca, D., Schulze, D., &Schartel, B. (2019). Multilayer graphene/elastomer
nanocomposites. In S. Yaragalla, R. K. Mishra, S. Thomas, N. Kalarikkal, & H. J.
Maria (Eds.), *Carbon-Based Nanofillers and Their Rubber Nanocomposites*. New
York:Elsevier. p 139–200.https://doi.org/10.1016/B978-0-12-817342-8.00006-8

445 Carter, P. (1971). Spectrophotometric determination of serum iron at the submicrogram level
446 with a new reagent (ferrozine). *Analytical Biochemistry*, 40(2), 450–458.
447 https://doi.org/10.1016/0003-2697(71)90405-2

- Chandía, N. (2001). Alginic acids in *Lessoniatrabeculata*: Characterization by formic acid
 hydrolysis and FT-IR spectroscopy. *Carbohydrate Polymers*, 46(1), 81–87.
 https://doi.org/10.1016/s0144-8617(00)00286-1
- 451 Chandía, N. P., Matsuhiro, B., Mejías, E., &Moenne, A. (2004). Alginic acids in
 452 *Lessoniavadosa*: Partial hydrolysis and elicitor properties of the polymannuronic acid
 453 fraction. *Journal of Applied Phycology*, *16*(2), 127–133.
 454 https://doi.org/10.1023/B:JAPH.0000044778.44193.a8
- 455 Cheng, H., Feng, S., Shen, S., Zhang, L., Yang, R., Zhou, Y., & Ding, C. (2013). Extraction, 456 activities of antioxidant and antimicrobial *Epimediumacuminatum*Franch. 457 polysaccharide. Carbohydrate Polymers, 96(1), 101–108. https://doi.org/10.1016/j.carbpol.2013.03.072 458
- 459 Cicco, N., Lanorte, M. T., Paraggio, M., Viggiano, M., & Lattanzio, V. (2009). A
 460 reproducible, rapid and inexpensive Folin-Ciocalteu micro-method in determining
 461 phenolics of plant methanol extracts. *Microchemical Journal*, *91*(1), 107–110.
 462 https://doi.org/10.1016/j.microc.2008.08.011
- 463 Davis, T., Llanes, F., Volesky, B., &Mucci, A. (2003). Metal selectivity of *Sargassum spp*.
 464 and their alginates in relation to α-L-guluronic acid content and conformation.
 465 *Environmental Science* & *Technology*, 37, 261–267.
 466 https://doi.org/10.1021/es025781d
- 467 DuBois, Michel., Gilles, K. A., Hamilton, J. K., Rebers, P. A., & Smith, F. (1956).
 468 Colorimetric method for determination of sugars and related substances. *Analytical*469 *Chemistry*, 28(3), 350–356. <u>https://doi.org/10.1021/ac60111a017</u>

- Dusseault, J., Tam, S. K., Ménard, M., Polizu, S., Jourdan, G., Yahia, L., &Hallé, J.P. (2006).
 Evaluation of alginate purification methods: Effect on polyphenol, endotoxin, and
 protein contamination. *Journal of Biomedical Materials Research. Part A*, *76*(2), 243–
 251.https://doi.org/10.1002/jbm.a.30541
- 474 Fertah, M., Belfkira, A., Dahmane, E. Montassir, Taourirte, M., &Brouillette, F. (2017).
 475 Extraction and characterization of sodium alginate from Moroccan
 476 *Laminariadigitata*brown seaweed. *Arabian Journal of Chemistry*, *10*, S3707–S3714.
 477 https://doi.org/10.1016/j.arabjc.2014.05.003
- 478 García-Ríos, V., Ríos-Leal, E., Robledo, D., & Freile-Pelegrin, Y. (2012). Polysaccharides
 479 composition from tropical brown seaweeds. *Phycological Research*, 60(4), 305–315.
 480 <u>https://doi.org/10.1111/j.1440-1835.2012.00661.x</u>
- 481 Gómez Ordóñez, E., &Rupérez, P. (2011). FTIR-ATR spectroscopy as a tool for
 482 polysaccharide identification in edible brown and red seaweeds.*Food Hydrocolloids*,
 483 25(6), 1514–1520. https://doi.org/10.1016/j.foodhyd.2011.02.009
- Handå, A., Forbord, S., Wang, X., Broch, O. J., Dahle, S. W., Størseth, T. R., Reitan, K. I.,
 Olsen, Y., &Skjermo, J. (2013). Seasonal- and depth-dependent growth of cultivated
 kelp (*Saccharinalatissima*) in close proximity to salmon (*Salmo salar*) aquaculture in
 Norway. *Aquaculture*, 414, 191–
 201.https://doi.org/10.1016/j.aquaculture.2013.08.006

489

490 Hentati, F., Delattre, C., Ursu, A. V., Desbrières, J., Le Cerf, D., Gardarin, C., Abdelkafi, S., 491 Michaud, P., & Pierre, G. (2018). Structural characterization and antioxidant activity 492 of water-soluble polysaccharides from the Tunisian brown seaweed 198. 493 *Cystoseiracompressa*.*Carbohydrate* Polymers. 589-600. 494 https://doi.org/10.1016/j.carbpol.2018.06.098

- Hentati, F., Pierre, G., Ursu, A. V., Vial, C., Delattre, C., Abdelkafi, S., & Michaud, P.
 (2020). Rheological investigations of water-soluble polysaccharides from the Tunisian
 brown seaweed *Cystoseiracompressa*. *Food Hydrocolloids*, *103*, 105631.
 https://doi.org/10.1016/j.foodhyd.2019.105631
- Idris, S. S., Rahman, N. A., & Ismail, K. (2012). Combustion characteristics of Malaysian oil
 palm biomass, sub-bituminous coal and their respective blends via thermogravimetric
- 501
 analysis
 (TGA).
 Bioresource
 Technology,
 123,
 581–591.

 502
 https://doi.org/10.1016/j.biortech.2012.07.065
- Li, J., He, J., & Huang, Y. (2016). Role of alginate in antibacterial finishing of textiles. *International Journal of Biological Macromolecules*, 94(Pt A), 466–473.
 https://doi.org/10.1016/j.ijbiomac.2016.10.054
- Kahl, R., &Kappus, H. (1993). Toxikologie der synthetischenantioxidantien BHA und BHT
 im vergleichmitdemnatürlichenantioxidans vitamin E. *ZeitschriftfürLebensmittel- Untersuchung und Forschung*, *196*(4), 329–338. https://doi.org/10.1007/BF01197931
- 509Kardosová, A., & Machová, E. (2006). Antioxidant activity of medicinal plant510polysaccharides.*Fitoterapia*, 77(5), 367–
- 511 373.<u>https://doi.org/10.1016/j.fitote.2006.05.001</u>
- Kelishomi, Z. H., Goliaei, B., Mahdavi, H., Nikoofar, A., Rahimi, M., Moosavi-Movahedi, A.
 A., Mamashli, F., & Bigdeli, B. (2016). Antioxidant activity of low molecular weight
 alginate produced by thermal treatment. *Food Chemistry*, *196*, 897–902.
 <u>https://doi.org/10.1016/j.foodchem.2015.09.091</u>
- 516 Kirby, A. J., & Schmidt, R. J. (1997). The antioxidant activity of Chinese herbs for eczema
 517 and of placebo herbs I. *Journal of Ethnopharmacology*, 56(2), 103–108.
- 518 https://doi.org/10.1016/s0378-8741(97)01510-9

Kumar, P., Pawaria, S., Dalal, J., Ravesh, S., Bharadwaj, S., Jerome, A., Kumar, D., Jan, M.
H., & Yadav, P. S. (2019). Sodium alginate potentiates antioxidants, cryoprotection
and antibacterial activities of egg yolk extender during semen cryopreservation in
buffalo. *Animal Reproduction Science*, 209, 106166.
https://doi.org/10.1016/j.anireprosci.2019.106166

- Kumar, S., &Sahoo, D. (2017). A comprehensive analysis of alginate content and biochemical
 composition of leftover pulp from brown seaweed *Sargassumwightii*. *Algal Research*,
 23, 233–239. https://doi.org/10.1016/j.algal.2017.02.003
- Larsen, B., Salem, D. M. S. A., Sallam, M. A. E., Mishrikey, M. M., &Beltagy, A. I. (2003).
 Characterization of the alginates from algae harvested at the Egyptian Red Sea coast. *Carbohydrate Research*, *338*(22), 2325–2336. <u>https://doi.org/10.1016/s0008-6215(03)00378-1</u>
- Liu, S., Liu, G., & Yi, Y. (2015). Novel vanadyl complexes of alginate saccharides:
 Synthesis, characterization, and biological activities. *Carbohydrate Polymers*, *121*,
 86–91. <u>https://doi.org/10.1016/j.carbpol.2014.11.069</u>
- Liu, Z.Q. (2020). Bridging free radical chemistry with drug discovery: A promising way for finding novel drugs efficiently. *European Journal of Medicinal Chemistry*, *189*,
- 536 112020. <u>https://doi.org/10.1016/j.ejmech.2019.112020</u>
- 537 López-González, D., Fernandez-Lopez, M., Valverde, J. L., & Sanchez-Silva, L. (2014).
 538 Pyrolysis of three different types of microalgae: Kinetic and evolved gas analysis.
 539 *Energy*, 73(C), 33–43.
- 540 Lorenzo, J. M., González-Rodríguez, R. M., Sánchez, M., Amado, I. R., & Franco, D. (2013).
 541 Effects of natural (grape seed and chestnut extract) and synthetic antioxidants
- 542 (buthylatedhydroxytoluene, BHT) on the physical, chemical, microbiological and

543 sensory characteristics of dry cured sausage "chorizo." *Food Research International*,

544 54(1), 611–620. https://doi.org/10.1016/j.foodres.2013.07.064

- 545Mallick, D., Poddar, M. K., Mahanta, P., &Moholkar, V. S. (2018). Discernment of546synergism in pyrolysis of biomass blends using thermogravimetric analysis.547BioresourceTechnology,261,294–305.
- 548 <u>https://doi.org/10.1016/j.biortech.2018.04.011</u>
- Mohammed, A., Rivers, A., Stuckey, David. C., & Ward, K. (2020). Alginate extraction from *Sargassum* seaweed in the Caribbean region: Optimization using response surface
 methodology. *Carbohydrate Polymers*, 245, 116419.
- 552 <u>https://doi.org/10.1016/j.carbpol.2020.116419</u>
- Morris, E. R., Rees, D. A., & Thom, D. (1980). Characterisation of alginate composition and
 block-structure by circular dichroism. *Carbohydrate Research*, 81(2), 305–314.
 https://doi.org/10.1016/S0008-6215(00)85661-X
- Okolie, C. L., Mason, B., Mohan, A., Pitts, N., &Udenigwe, C. C. (2020). Extraction
 technology impacts on the structure-function relationship between sodium alginate
 extracts and their*in vitro* prebiotic activity. *Food Bioscience*, *37*, 100672.
 https://doi.org/10.1016/j.fbio.2020.100672
- Parthiban, C., Parameswari, K., Saranya, C., Hemalatha, A., &Anantharaman, P. (2012).
 Production of sodium alginate from selected seaweeds and their physiochemical and
 biochemical properties. *Asian Pacific Journal of Tropical Biomedicine*, 1, 1–4.
- Pellegrini, M., Valls, R., & Pellegrini, L. (1997). Chimiotaxonomie et marqueurs chimiques *dans les algues brunes.* Lagascalia, 19, 145–164.
 https://idus.us.es/xmlui/handle/11441/63026
- Ramos, P. E., Silva, P., Alario, M. M., Pastrana, L. M., Teixeira, J. A., Cerqueira, M. A., &
 Vicente, A. A. (2018). Effect of alginate molecular weight and M/G ratio in beads

- properties foreseeing the protection of probiotics. *Food Hydrocolloids*, 77, 8–16.
 https://doi.org/10.1016/j.foodhyd.2017.08.031
- Raza, W., Makeen, K., Wang, Y., Xu, Y., &Qirong, S. (2011). Optimization, purification,
 characterization and antioxidant activity of an extracellular polysaccharide produced
 by *Paenibacilluspolymyxa* SQR-21. *Bioresource Technology*, *102*(10), 6095–6103.
- 573 https://doi.org/10.1016/j.biortech.2011.02.033
- 574 Rengasamy, K. R., Mahomoodally, M. F., Aumeeruddy, M. Z., Zengin, G., Xiao, J., & Kim, 575 D. H. (2020). Bioactive compounds in seaweeds: An overview of their biological 576 properties and safety. Food and Chemical Toxicology, 135, 111013. 577 https://doi.org/10.1016/j.fct.2019.111013
- Rezende, R. A., Bártolo, P. J., Mendes, A., &Filho, R. M. (2009). Rheological behavior of
 alginate solutions for biomanufacturing. *Journal of Applied Polymer Science*, *113*(6),
 3866–3871. <u>https://doi.org/10.1002/app.30170</u>
- Sanjeewa, K. K. A., Lee, J. S., Kim, W. S., & Jeon, Y. J. (2017). The potential of brown-algae
 polysaccharides for the development of anticancer agents: An update on anticancer
 effects reported for fucoidan and laminaran. *Carbohydrate Polymers*, *177*, 451–459.
 https://doi.org/10.1016/j.carbpol.2017.09.005
- 585 Schramm, D. D., Karim, M., Schrader, H. R., Holt, R. R., Cardetti, M., & Keen, C. L. (2003).

586 Honey with high levels of antioxidants can provide protection to healthy human

- 587 subjects. Journal of Agricultural and Food Chemistry, 51(6), 1732–1735.
- 588 <u>https://doi.org/10.1021/jf025928k</u>
- Scott, R. W. (1979). Colorimetric determination of hexuronic acids in plant materials.
 Analytical Chemistry, *51*(7), 936–941. <u>https://doi.org/10.1021/ac50043a036</u>
- Sellimi, S., Younes, I., Ayed, H. B., Maalej, H., Montero, V., Rinaudo, M., Dahia, M.,
 Mechichi, T., Hajji, M., &Nasri, M. (2015). Structural, physicochemical and

- antioxidant properties of sodium alginate isolated from a Tunisian brown seaweed. *International Journal of Biological Macromolecules*, 72, 1358–1367.
 https://doi.org/10.1016/j.ijbiomac.2014.10.016
- Setyawidati, N. A. R., Puspita, M., Kaimuddin, A. H., Widowati, I., Deslandes, E.,
 Bourgougnon, N., &Stiger-Pouvreau, V. (2018). Seasonal biomass and alginate stock
 assessment of three abundant genera of brown macroalgae using multispectral high
 resolution satellite remote sensing: A case study at Ekas Bay (Lombok, Indonesia). *Marine* Pollution Bulletin, 131, 40–48.
- 601 <u>https://doi.org/10.1016/j.marpolbul.2017.11.068</u>
- 602 Shang, H., Zhou, H., Duan, M., Li, R., Wu, H., & Lou, Y. (2018). Extraction condition 603 optimization and effects of drying methods on physicochemical properties and 604 antioxidant activities of polysaccharides from comfrey (Symphytumofficinale L.) root. 605 International Journal of **Biological** Macromolecules, 112, 889-899. 606 https://doi.org/10.1016/j.ijbiomac.2018.01.198
- Suzuki, S., Ono, M., Toda, T., & Kitamura, S. (2016). Preparation and intestinal
 immunostimulatingactivity of low molecular weight alginate from *Saccharina*(*Laminaria*) species in Japan. *Journal of Applied Glycoscience*, 63(1), 1–5.
 https://doi.org/10.5458/jag.jag.JAG-2015_017
- Wang, J., Hu, S., Nie, S., Yu, Q., &Xie, M. (2016). Reviews on mechanisms of *in vitro*antioxidant activity of polysaccharides. *Oxidative Medicine and Cellular*
- 613 *Longevity.2016*, Article ID 5692852, 13 pages. <u>https://doi.org/10.1155/2016/5692852</u>
- 614 Xiao, Q., Tong, Q., Zhou, Y., & Deng, F. (2015). Rheological properties of pullulan-sodium
- 615 alginate based solutions during film formation. *Carbohydrate Polymers*, *130*, 49–56.
- 616 <u>https://doi.org/10.1016/j.carbpol.2015.04.069</u>

- Yang, J.S., Xie, Y.J., & He, W. (2011). Research progress on chemical modification of
 alginate: A review. *Carbohydrate Polymers*.84(1), 33–39.<u>http://agris.fao.org/agris-</u>
 search/search.do?recordID=US201600049890
- Yildirim, A., Mavi, A., & Kara, A. A. (2001). Determination of antioxidant and antimicrobial
 activities of *RumexcrispusL.* extracts. *Journal of Agricultural and Food Chemistry*,
 49(8), 4083–4089.
- Zhao, D., Xu, J., & Xu, X. (2018). Bioactivity of fucoidan extracted from *Laminaria japonica*using a novel procedure with high yield. *Food Chemistry*, 245, 911–918.
 <u>https://doi.org/10.1016/j.foodchem.2017.11.083</u>
- Zhu, Y., Wu, L., Chen, Y., Ni, H., Xiao, A., &Cai, H. (2016). Characterization of an
 extracellular biofunctional alginate lyase from marine *Microbulbifer sp.* ALW1 and
 antioxidant activity of enzymatic hydrolysates. *Microbiological Research*, 182, 49–58.
 <u>https://doi.org/10.1016/j.micres.2015.09.004</u>
- 630
- 631
- 632

5 6	Parameters	Season				
7 8	I al ametel s	AD	AA	AJ	AS	
9	Yield	25.1±0.4°	28±1 ^b	38.4±0.3ª	21±1 ^d	
0	Moisture*	11.3±0.1 ^b	10.0±0.4°	10 ± 0.5^{d}	12.6±0.4ª	
2	Neutral sugars	9.2 ± 0.4^{a}	6.3±0.4 ^b	5.5±0.4°	6.1±0.3 ^b	
3	Uronic acids	47 ± 1^{d}	53±2°	66±2 ^a	62±1 ^b	
4	Total phenolics [*]	1.47±0.01ª	1.03±0.02 ^b	0.92±0.01°	0.66 ± 0.02^{d}	
5	Ash	39.4±0.1ª	37±0.5 ^b	24.3 ± 0.4^{d}	29±1°	
6	С	35±2 ^b	40±1 ^a	28±1°	39.6±0.3ª	
7 8	0	45.4±0.1ª	43±2 ^b	41±1°	46±1ª	
9	Na	16±1 ^b	14.9±0.4 ^b	26±1 ^a	10.5±0.3°	
0 1	S	0	0	0	0	
2	Ν	0	0	0	0	
3 4	Mg	0	0.17±0.01°	0.25±0.01 ^b	0.44±0.03	
5 6	К	0.18±0.01°	0.53±0.01ª	0.44 ± 0.04^{b}	0.17±0.019	
7	Cl	0.39±0.01 ^b	1.24±0.1ª	0.35±0.04 ^b	1.38±0.1ª	
8 9	Si	0.36 ± 0.08^{b}	0.27±0.01°	0.57±0.05ª	0.26±0.02°	

Table 1. Extraction yield(g/100 g DM) and chemical composition (g/100 g DM) of the CSSA
fractionsfromdifferent seasons.

659 660 661

661 AD, AA, AJ and AS represent sodium alginates extracted from *C. schiffneri*collected in December, April, July 662 and September, respectively; *The moisture is expressed as g/100 g lyophilized sodium alginate;*Total 663 phenolicswere expressed as g eq. phloroglucinol/100 g DM; Each value represents the mean±SD (n = 3); 664 a,b,c,dDifferent letters within different seasons of harvest (same column) indicate significant differences (p<0.05). 665

Table 2. M/G ratios of the CSSA fractionsfrom different seasons.

		Method Season				
		Methou	AD	AA	AJ	AS
		FTIR	0.062	0.064	0.065	0.062
		Circular dichroism	0	0.022	0.012	0.015
		NMR	0.093	0.024	0.037	0.080
668	AD AA AI and AS represen	t sodium alginates extracted	f from C	schiffneri c	ollected in	December

AD, AA, AJ and AS represent sodium alginates extracted from *C. schiffneri* collected in December, April, July
 and September, respectively.

Table 3.Average molecular mass (g/mol) of the CSSA fractions from different seasons.

		Season				
	AD	AA	AJ	AS		
Mn	7.62×10 ⁵	8.02×10 ⁴	1.26×10 ⁵	7.85×10 ²		
Μ	1.23×10 ⁶	1.16×10 ⁵	2.33×10 ⁵	4.49×10 ³		
PDI	1.62	1.45	1.85	5.72		

AD, AA, AJ and AS represent sodium alginates extracted from *C. schiffneri*collected in December, April, July
 and September, respectively;Mn, M, and PDI are the number-average molecular mass, the average molecular
 mass, and the polydispersity index, respectively.

680 **Table4.**Structural composition of the CSSA fractions from different seasons.

Season	F _G	F _M	F _{GG}	F _{MM}	F _{MG}	F _{GM}
AD	0.91	0.09	0.88	0.06	0.03	0.03
AA	0.98	0.02	0.97	0.01	0.01	0.01
AJ	0.97	0.03	0.96	0.02	0.01	0.01
AS	0.92	0.08	0.9	0.06	0.02	0.02

681 AD, AA, AJ and AS represent sodium alginates extracted from *C. schiffneri* collected in December, April, July

682 and September, respectively.

684	Table 5. Antioxidant	activities of the	CSSA fraction	nsfrom different seasons.

005


	Season			Standards		
	AD	AA	AJ	AS	BHA	EDTA
DPPH• scavenging activity	>1500	>1500	>1500	190±10 ^a	14.1±0.2 ^b	
Reducing power	51±1 ^b	>500	208±6 ^a	51±2 ^b	25.2±0.1°	
Fe ²⁺ chelating ability	145±1°	511±17 ^a	211±6 ^b	43±1 ^d		10.0±0.2e


686 AD, AA, AJ and AS represent sodium alginates extracted from *C. schiffneri*collected in December, April, July 687 and September, respectively;Results of DPPH• scavenging and metal (Fe²⁺) chelating assays are shownas 688 IC₅₀values (µg/ml), defined as the extract concentration needed to scavenge 50% of DPPH• and to chelate 50% 689 of Fe²⁺, respectively. The reducing power (OD 700) is shownas the extract concentration (EC_{0.5}) providing 0.5 690 absorbance at 700 nm; Each value represents the mean±SD (n = 3); ^{a,b,c,d,e}Different letters within different

691 seasons of harvest (same row) indicate significant differences (p < 0.05).

693 Figure captions

- 694 Fig. 1.ATR-FTIR spectroscopy of sodium alginates extracted from C. schiffneri collected in
- 695 December (AD), April (AA), July (AJ) and September (AS).
- 696 Fig. 2. Circular dichroism spectra of sodium alginates extracted from *C. schiffneri* collected in
- 697 December (AD), April (AA), July (AJ) and September (AS).
- 698 Fig.3. ¹H-NMR spectra of sodium alginates extracted from C. schiffneri collected in
- 699 December (AD), April (AA), July (AJ) and September (AS).
- 700 Fig. 4. Thermogravimetric analysis of sodium alginates extracted from C. schiffneri collected
- 701 in December (AD), April (AA), July (AJ) and September (AS).
- 702 Fig. 5. Viscosity of sodium alginates extracted from C. schiffneri collected in December
- 703 (AD), April (AA), July (AJ) and September (AS).
- 704 Fig. 6. Viscoelasticity of sodium alginates extracted from C. schiffneri collected in December
- 705 (AD), April (AA), July (AJ) and September (AS).
- 706 Fig. 7. Antioxidant activities of sodium alginates extracted from C. schiffneri collected in
- 707 December (AD), April (AA), July (AJ) and September (AS).





Wavelength (nm)



