



**HAL**  
open science

# Photosensitivity of barium germano-gallate Glasses Under Femtosecond Laser Writing for Mid-IR Applications

Heng Yao, Rayan Zaiter, Maxime Cavillon, Benjamin Sapaly, Thierry  
Cardinal, Ye Dai, Bertrand Poumellec, Matthieu Lancry

► **To cite this version:**

Heng Yao, Rayan Zaiter, Maxime Cavillon, Benjamin Sapaly, Thierry Cardinal, et al.. Photosensitivity of barium germano-gallate Glasses Under Femtosecond Laser Writing for Mid-IR Applications. *Ceramics International*, 2021, 10.1364/OL.99.099999 . hal-03418506

**HAL Id: hal-03418506**

**<https://hal.science/hal-03418506>**

Submitted on 7 Nov 2021

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Photosensitivity of barium germano-gallate Glasses Under Femtosecond Laser Writing for Mid-IR Applications

HENG YAO<sup>1,2</sup>, RAYAN ZAITER<sup>3</sup>, MAXIME CAVILLON<sup>2</sup>, BENJAMIN SAPALY<sup>2</sup>, THIERRY CARDINAL<sup>3</sup>, YE DAI<sup>1,\*</sup>, BERTRAND POUHELLEC<sup>2</sup> AND MATTHIEU LANCRY<sup>2,\*</sup>

<sup>1</sup> Department of Physics, Shanghai University, Shanghai 200444, China

<sup>2</sup> Institut de Chimie Moléculaire et des Matériaux d'Orsay, SP2M, CNRS, Université Paris-Saclay, 91405 Orsay, France

<sup>3</sup> Université de Bordeaux, CNRS, ICMCB, UPR 9048, F-33608 Pessac, France

\*Corresponding author: [yedai@shu.edu.cn](mailto:yedai@shu.edu.cn), [matthieu.lancry@universite-paris-saclay.fr](mailto:matthieu.lancry@universite-paris-saclay.fr)

Received XX Month XXXX; revised XX Month, XXXX; accepted XX Month XXXX; posted XX Month XXXX (Doc. ID XXXXX); published XX Month XXXX

Barium germano-gallate (BGG) glasses are attractive glass hosts for photonic applications in the mid-infrared region up to 6  $\mu\text{m}$ . In this work, we investigate the photosensitivity of such glasses under femtosecond laser, with an emphasis on the formation of refractive index changes. Six glasses with varying compositions (including addition of K, Na, Y, and La) were studied. We observed several transformation regimes in the pulse energy – repetition rate landscape: Type I (isotropic refractive index change) and a spatial broadening regime with a phase shift  $\Delta\varphi > 2\pi$  rad at 550 nm. This translates into refractive index changes  $\Delta n > 10^{-2}$  and is comparable to values obtained in most chalcogenide glasses. The effect of glass composition on  $\Delta\varphi$  appears correlated to the number of non-bridging oxygen (NBO) present in the glass and is brought to evidence by monitoring the Cations/ $\text{GaO}_{3/2}$  ratio. This provides a way to design a range of germano-gallate glasses suitable to imprinting high refractive index contrast.

© 2021 Optical Society of America

**OCIS codes:** (140.3490) Lasers, distributed-feedback; (060.2420) Fibers, polarization-maintaining; (060.3735) Fiber Bragg gratings; (060.2370) Fiber optics sensors.

<http://dx.doi.org/10.1364/OL.99.099999>

Femtosecond (fs) laser direct writing (FLDW) is a versatile tool that enables permanent modifications of physical properties inside transparent materials, including glass. FLDW is achieved by focusing a fs-laser beam on, or below, the surface of transparent materials. The tightly focused light can reach intensities of several  $\text{TW}/\text{cm}^2$ , yielding to nonlinear light absorption and permanent transformations of the pristine glass within few  $\mu\text{m}^3$  in and around

the laser focal volume. Consequently, this technique has attracted attention in fields such as, but not limited to, optomechanics, integrated photonics, graded index and diffractive optics for laser, spectroscopy and imaging applications [1-7].

The most ubiquitous glass materials employed for FLDW are silica and silicate (i.e., silica-rich glasses) [8], as they are readily available and offer both excellent optical transparency and chemical stability. However, for photonic applications, these glasses are limited to the short-wavelength-IR range (SWIR,  $< 3 \mu\text{m}$ ). This intrinsic limitation prevents their use in applications requiring longer wavelengths. This operating wavelength window is interesting in the 3D manufacturing of miniaturized, low weight and cost optical systems, for civilian (domotics, smartphone, automobile) but also security and military applications (vehicles steering, survey, weapons guidance, unmasking, countermeasure identification). Hence, to circumvent this restriction imposed by silica / silicate glasses and access the Mid-infrared (Mid-IR) range (up to 5-8  $\mu\text{m}$ ), non-silicate glass matrices must be employed, such as chalcogenides [9], fluorides [10], or heavy oxides [11]. Among these potential candidates, heavy metal oxide (HMO) glasses, and more specifically barium gallo-germanate (BGG) glasses, appear as materials of choice. They are chemically stable, manufacturable by conventional means (melt-quenching), mechanically resistant, and exhibit an extended transmission in the IR range up to 7-8  $\mu\text{m}$  [1]. Moreover, hydroxyl impurities could be eliminated by a purification method based on halogens, which produce gallo-germanate glasses with improved transparency up to  $\sim 6 \mu\text{m}$  [13].

The gallo-germanate glass family has already been investigated for a series of optical applications, including high-energy mid-IR laser output windows [12], waveguides [1], or as active optical fiber hosts [REFXX14 bordeaux]. Although this glass family has shown a consequent potential, it still must be photosensitive to laser fs-light in order to imprint specific functions. Shortly, in silica glass, which is the most common glass material investigated by the

community, there exists several types of fs-laser induced modifications, known as the first, second, and, the third regimes. They are commonly referred in the literature as IR-fs Type I, Type II and Type III, respectively [15-17]. Type I is generally observed at low pulse energies, and is characterized by a smooth and homogeneous structural modification beyond a given threshold [15]. It is also worth noting that composition fluctuation has little impact on the Type I threshold [18]. The expected material response is a permanent and isotropic refractive index variation: these conditions are desired for applications like optical waveguide or lenses. Type II regime is generally observed for slightly higher deposited energies, and is characterized by the formation of birefringent self-assembled periodic nanostructures [16]. Finally, the Type III regime is reached when the intensity of pulse energy exceeds  $\approx 10^{14}$  W/cm<sup>2</sup> in silica [17], and voids issued from micro-explosions are created inside the irradiated volume. Alternatively, another regime is commonly defined in the literature, labeled "heat accumulation regime". The latter is achieved at high repetition rate  $f$ . This regime corresponds to the conditions where the inter-pulse period approaches or becomes shorter than the heat diffusion time needed to fully evacuate the heat deposited after each pulse. This causes a net temperature increase from pulse to pulse, and a spatial broadening of the fs-laser modified area with a size that overcomes the beam size itself (provided the deposited energy is high enough) [19]. However when discussing the energy thresholds, it is not accurate to speak about heat accumulation threshold, but rather about a temperature threshold and its spatial extension. More details are provided later in this article.

The most common macroscopic photosensitive response desired is a refractive index modification with a strong index contrast ( $\Delta n$ , Type I), which can subsequently be employed to inscribe 3D free form objects and functions, such as Bragg filters, waveguides, and diffractive or exponential gradient planar lenses. In this paper we will therefore focus on this regime. In the literature, only few studies report on the photosensitivity of BGG glasses by fs-lasers. The first one, in 2017, investigated fs-response of a BBG with a molar composition of 12.5%BaO – 75%GeO<sub>2</sub> – 12.5%Ga<sub>2</sub>O<sub>3</sub>, and the Authors obtained a maximum positive refractive index contrast ( $\Delta n$ ) of  $8 \times 10^{-3}$  with respect to the pristine glass, and after varying both scanning speed and pulse energy. In the same study, the Authors investigated the effect of glass composition on its photosensitivity, in  $x\%$ BaO –  $(100-2x)\%$ GeO<sub>2</sub> –  $x\%$ Ga<sub>2</sub>O<sub>3</sub> glass molar compositions, with  $x$  taking values of 20%, 17.5%, 12.5%, and 7.5%; each glass exhibited a similar response upon fs-laser irradiation. Very recently (in 2021), the same team showed the possibility to inscribe waveguides in a 17.5%BaF<sub>2</sub> – 17.5%Ga<sub>2</sub>O<sub>3</sub> – 65%GeO<sub>2</sub> glass and managed to obtain a  $\Delta n$  of  $\approx 3 \times 10^{-3}$  [20]. Addition of a halogen component has the effect to mitigate water content during the glass synthesis [21]. However, the  $\Delta n$  is reduced by approximately 60% with respect to its all-oxide counter-part [20].

In this work, we investigate the photosensitivity of 6 BGG glasses, labeled G GK, B GGLaY1, B GGLaY2, B GGLaY3, B G GK, B G GN with capitalized letters corresponding to the principal cation species present in the respective glass compositions. The latter are provided in Table 1. These modified BBG glass compositions would present good assets between relatively high nonlinear optical properties, important hardness, high transition

temperature, and fiber drawing ability, in particular for yttrium- and lanthanum-containing glasses [22-23].

**Table 1.** Label, molar composition, and physical characteristics of the barium gallo-germanate (BGG) glass samples investigated.

Sample	Composition (%)	T <sub>g</sub> (±5°C)	n <sub>532nm</sub> (±0.01)
G GK	25Ga <sub>2</sub> O <sub>3</sub> - 50GeO <sub>2</sub> - 25K <sub>2</sub> O	661	1.63
B GGLaY1	21Ga <sub>2</sub> O <sub>3</sub> - 43GeO <sub>2</sub> - 24BaO - 6La <sub>2</sub> O <sub>3</sub> - 6Y <sub>2</sub> O <sub>3</sub>	728	1.805
B GGLaY2	15Ga <sub>2</sub> O <sub>3</sub> - 60GeO <sub>2</sub> - 13BaO - 6La <sub>2</sub> O <sub>3</sub> - 6Y <sub>2</sub> O <sub>3</sub>	736	1.796
B GGLaY3	28Ga <sub>2</sub> O <sub>3</sub> - 37GeO <sub>2</sub> - 23BaO - 6La <sub>2</sub> O <sub>3</sub> - 6Y <sub>2</sub> O <sub>3</sub>	735	1.780
B G GK	30Ga <sub>2</sub> O <sub>3</sub> - 35GeO <sub>2</sub> - 24BaO - 11K <sub>2</sub> O	642	1.701
B G GN	29Ga <sub>2</sub> O <sub>3</sub> - 39GeO <sub>2</sub> - 23BaO - 9Na <sub>2</sub> O	671	1.725

### Experimental procedure:

**Glass synthesis:** These BGG samples were prepared through conventional melt-quenching technique from high purity reagents (Ga<sub>2</sub>O<sub>3</sub>: 99.998%, Strem Chemical, GeO<sub>2</sub>: 99.999%, Strem Chemical, BaCO<sub>3</sub>: 99.95%, Alfa Aesar, K<sub>2</sub>CO<sub>3</sub>: 99%, Sigma Aldrich, La<sub>2</sub>O<sub>3</sub>: 99.9%, Sigma Aldrich, Y<sub>2</sub>O<sub>3</sub>: 99.9%, Alfa Aesar and Na<sub>2</sub>CO<sub>3</sub>: 99.95%, Sigma Aldrich). The reagent grade BaCO<sub>3</sub> decomposed high temperatures to form BaO. The powder precursors were mixed in a platinum crucible and melted at a temperature of 1300 °C for 30 min. The liquid was then quenched onto a metal plate to room temperature.

**Pristine glass characterization:** the glass transition temperatures (T<sub>g</sub>) were measured by differential scanning calorimetry (DSC) and differential thermal analysis (DTA) Netzsch Pegasus 404 apparatus and with glass chunks inserted in a Pt pan, at a heating rate of 10 °C/min. The refractive indices (n<sub>d</sub>) were characterized by the prism coupling method on a M-line Metricon 2010/M at 532 nm. Both T<sub>g</sub> and n<sub>d</sub> are reported in Table 1. Micro-Raman spectra were recorded in backscattering mode on a confocal micro-Raman spectrometer HR (Horiba / Jobin Yvon) equipped with a Synapse CCD detector using 532 nm excitation wavelength. The room temperature optical transmission measurements for each glass sample, in the UV-Visible-NIR and the IR ranges, were respectively obtained from Agilent Cary 5000 and Bruker Equinox 55 spectrophotometers. From the attenuation measurements, the absorption coefficients ( $\alpha$ , in cm<sup>-1</sup>) of the glass samples were calculated using sample thickness (typ. 1 mm). Note that  $\alpha$  was obtained after calculating internal transmittance T<sub>int</sub>( $\lambda$ ) [24] in order to remove the Fresnel losses. This further allow to calculate the excess loss  $\Delta\alpha = \alpha(\text{after irradiation}) - \alpha(\text{pristine})$ .

**Fs-laser irradiation and characterization of modified regions:** The glass samples, individually double side polished to an optical grade, were placed on a translation stage for subsequent fs-laser irradiation. A commercial Yb-doped fiber amplifier fs-laser (Satsuma, Amplitude Systèmes Ltd. Pessac, France.) was used, with the following conditions: pulse duration = 300 fs; wavelength ( $\lambda$ ) = 1030 nm; numerical aperture (NA) = 0.6; focusing depth = 300  $\mu$ m. The beam size was defined by its lateral and longitudinal waist, respectively noted  $w_r$  and  $w_z$ . Moreover, the repetition rate and the pulse energy were varied. The inscription patterns inscribed in all samples were a series of rectangles with the dimensions of 100×10  $\mu$ m<sup>2</sup>. Each rectangle was in fact composed of a series of 10 lines being 100  $\mu$ m long and with a spacing  $\Delta y$  of 1  $\mu$ m. In this work we

used a constant pulse density  $f/v = 1000$  pulses/ $\mu\text{m}$ , with  $f$  being the pulse repetition rate (Hz, or pulses/s) and  $v$  the scanning speed ( $\mu\text{m/s}$ ). The repetition rate  $f$  was varied between 20 kHz to 400 kHz and, therefore, the laser scanning speed was varied from 20  $\mu\text{m/s}$  to 400  $\mu\text{m/s}$  accordingly. Moreover, the pulse energy  $E_p$  was also varied, from 0.025 to 5  $\mu\text{J}$ . Finally, the linear laser polarization was oriented parallel to the laser scanning direction.

Following the laser irradiation, each sample was placed on an Olympus BX51 (Olympus, Tokyo, Japan) polarized optical microscope. In addition to a typical optical microscope observation, each sample was investigated using quantitative phase microscopy (QPM). This technique measures the longitudinal (i.e., along the optical microscope light path) phase retardation ( $\Delta\varphi$ , in rad) caused by the irradiated object with respect to the surrounding pristine glass. From this measurement, the refractive index modification can be calculated through the following relationship:  $\Delta n = \frac{\Delta\varphi\lambda}{2\pi d}$ , where  $\lambda$  is the wavelength of the illuminating microscope light (550 nm), and  $d$  is the thickness of the modified region.

### Results and discussion:

Figure 1a displays the Raman spectra normalized to the total scattered intensity cross-section from 200 to 1400  $\text{cm}^{-1}$ . The Raman spectra confirmed the glass nature of all samples. Moreover, and for completeness, the principal band at the vicinity of 500-550  $\text{cm}^{-1}$  corresponds to vibrations of X-O-X (X = Ga or Ge) bonds from connected tetrahedral  $\text{XO}_4$  units [25]. It is worth noticing that the signature of vibrations involving Ga or Ge cations cannot be distinguished by Raman spectroscopy due to their similar masses.

The two bands centered at 780  $\text{cm}^{-1}$  and 870  $\text{cm}^{-1}$  for GGK glass are attributed to stretching modes of Ge and Ga tetrahedral units, respectively. They are likely in an annular configuration or chain in which the charge on oxygen varies depending on the location of the potassium compensating charge cations. For all glasses beside GGK, a band located around 830  $\text{cm}^{-1}$  is observed. For all these compositions, the charge compensation of gallium oxide tetrahedra are guaranteed by the sufficient amount of positive charges  $\text{Na}^+$ ,  $\text{K}^+$ ,  $\text{Ba}^{2+}$ ,  $\text{Y}^{3+}$  or  $\text{La}^{3+}$  and the excess leads to the formation of non-bridging oxygens (NBOs) vibrating at 830  $\text{cm}^{-1}$ . The positive charge ratio of modifiers versus Ga can be estimated as follows:  $(2\text{Ba}+3\text{La}+3\text{Y}+\text{Na}+\text{K})/\text{Ga}$ , and without taking into account the real charge compensation ability of each cation. Following this, the ratio is in the following order: BGGLaY2 (3.24), BGGLaY1 (2.84), BGGLaY3 (2.11), BGGK (1.19), BGGN (1.12), and GGK (1.00). Moreover, the remaining  $\text{Ba}^{2+}$ ,  $\text{Y}^{3+}$  and  $\text{La}^{3+}$  (i.e., which do not compensate the charge of  $[\text{GaO}_4]^-$  polyhedra), participate in the formation of NBOs on  $\text{GeO}_4$  units [13]. The slight shift of the 830  $\text{cm}^{-1}$  band position is thus attributed to the nature of the cation modifier involved.

In Figure 1b are presented the absorption coefficient measurements for each glass sample. Two broad absorption bands can be observed at 3  $\mu\text{m}$  and 5  $\mu\text{m}$ . They correspond to the two broad asymmetric absorption bands assigned to the hydroxyl (OH) stretching vibrations due to the absence of purification steps during the glass synthesis. In Ref. [26], the Authors have proposed a deconvolution with four Gaussian bands in the  $\text{Ga}_2\text{O}_3\text{-GeO}_2\text{-BaO}$  glass system, where the highest frequency ones are attributed to Ga-OH and Ge-OH vibrations (free hydroxyl), while the lowest ones may be attributed to either T-O-H-O (T= Ga or Ge) strong,

or very strong, hydrogen bonds [26]. Other Authors have proposed, for tellurite glasses, that the vibrations around 5  $\mu\text{m}$  could be due to the overtone of OH bending modes [27]. One can notice that the glasses exhibiting the highest germanate content also present the highest intensity OH-associated vibrations. This effect may be related to the purity of the germanium oxide precursor but also its hydrophilic nature.

The IR mutiphonon cut-off is made up of a band at  $\sim 6.25$   $\mu\text{m}$  and a strong absorption edge above 7  $\mu\text{m}$ . There are two main points to discuss: the effect of modifiers as well as the Ga/Ge ratio on the position of the IR cut-off. The origin of the multiphonon absorption edge can be difficult to elucidate. Thus, various aspects must be taken into consideration, such as the rare-earth/Ba content and their atomic mass, the harmonic combinations of fundamental vibrational modes or the overtone of hydroxyl (OH) vibrations. The band at  $\sim 6.25$   $\mu\text{m}$  seems to decrease when the Ga/Ge ratio increases and where the band associated to  $\text{Q}^3$   $\text{GeO}_4$  units decreases. The IR spectra in Ref. [25] show a signature of the band associated to  $\text{Q}^3$   $\text{GeO}_4$  units located at 800  $\text{cm}^{-1}$ , which could lead to an overtone in the 6  $\mu\text{m}$  spectral region.

The fabrication of Mid-IR photonic devices will require first reducing the OH content and if possible, avoiding  $\text{Q}^3$  units to benefit from an extended IR transmission.




Fig. 1. (a) Normalized Raman Intensity of GGK, BGGLaY1, BGGLaY2, BGGLaY3, BGGK and BGGN glasses as a function of Raman shift. (b) Absorption coefficients of GGK, BGGLaY1, BGGLaY2, BGGLaY3, BGGK and BGGN glasses as a function of wavelength.




Fig. 2. Pulse energy – repetition rate landscape and identification of Type I regime, transition regime and spatial broadening regime in BGGLaY1 glass.

Figure 2 displays the various types of modifications, in a pulse energy – repetition rate landscape, induced by fs-laser irradiation for BGGLaY1 glass sample and characterized by optical microscopy. The other glass samples follow similar trends and the BGGLaY1 is consequently provided as an exemplar of the typical features being observed. The pulse energy – repetition rate is framed between several contributions that dictate the glass photosensitivity. At very low energies ( $<0,20\mu\text{J}$ ), there are no permanent modifications detected in the glass. As the energy is progressively increased (moving vertically upward in Figure 2), we observe the onset of Type I modification. This corresponds to an isotropic and positive phase change (hence refractive index increase) with respect to the pristine glass. This Type I corresponds to the data points in blue in Figure 2. This regime is opposed to the so-called “transition regime” and “spatial broadening regime” in a sense that there is no broadening of the laser track. This is particularly attractive to imprint compact and highly localized photo-induced transformations. The observable laser track broadening arises from two different origins depending if one moves vertically (increasing pulse energy, case 1) or horizontally (increasing repetition rate, case 2) in Figure 2.

**Case 1:** At low repetition rate, when we increase the pulse energy,  $E_p$ , the spatial distribution of the temperature profile is unchanged according to the heat equation (Fourier’s law). However, the deposited heat also increases, and so does the maximum temperature ( $T_{max}$ ) in the focal volume (yet there is no more heat build-up from pulse-to-pulse). The maximum temperature in the pulse center is  $T_{max} = \frac{AE_p}{\pi\rho C_p w_r^2 w_z}$  [ref] where  $A \times E_p$  is the energy absorbed per unit volume ( $A$  is the absorbed fraction), and  $\rho$  and  $C_p$  are the glass density and the heat capacity, respectively. The  $T_{max}$  elevation as  $E_p$  increases leads to an enlarge spatial volume within which the local temperature is higher than a transformation temperature, i.e., a temperature threshold (here corresponding to an observable positive and permanent refractive index change).

**Case 2:** When the repetition rate  $f$  increases, the spatial temperature profile changes from Gaussian to Lorentzian-Gaussian (Gaussian in the center, Lorentzian in the periphery). This has the consequence to decrease the width at half height of the temperature profile, and therefore this is not what widens the laser track. Instead, here the heat accumulation increases the

amplitude, since now the expression of the maximum temperature can be describe as  $T_{max} = \frac{3A.E_p.f}{8D\pi\rho C_p w}$  and thus the imprinted width for a given temperature that can overcome the laser beam size ( $w_r$  and  $w_z$ ) by several orders of magnitude.

Following this view, the minimum time ( $\tau_{min}$ ) needed to evacuate the heat deposited within the focal volume can be approximated by the following formula:  $\tau_{min} \approx \omega_0^2/D$ , where  $\omega_0$  is the beam waist radius,  $D$  the thermal diffusion coefficient, expressed as  $D = \kappa/(\rho \cdot C_p)$ , and with  $k$  being the thermal conductivity. In our conditions  $\omega_r \approx 1 \mu\text{m}$ . For a typical germanate glass (e.g, Schott IRG-2), one can estimate  $D$  as  $3.7 \cdot 10^{-7} \text{ m}^2/\text{s}$  [28]. This leads to a  $\tau_{min} \approx 2.7 \mu\text{s}$ . To provide a comparison, for silica glass ( $D \approx 9 \cdot 10^{-7} \text{ m}^2/\text{s}$ ) we obtain  $\tau_{min} \approx 1.1 \mu\text{s}$ . These values translate to frequencies of  $\approx 370 \text{ kHz}$  and  $\approx 890 \text{ kHz}$  for germanate and silica glasses, respectively. These calculations provide a crude estimate about the frequency onset of heat accumulation caused by an increase in the repetition rate, and show that it is expected to be much lower than what is found for silica glass. This is in relatively good agreement with trends observed in Figure 2, indicating that the spectral broadening regime is likely due to heat-accumulation that becomes preponderous in the 200-400 kHz regime.

Now that the types of fs-laser induced modifications are identified and described, we focus to the amplitude of the phase shift, hence refractive index contrast, generated during the laser irradiation. The evolution of the phase shift as a function of the pulse energy, for each glass sample, is displayed in Figure 3. Here we chose to display the data measured at a repetition rate of 100 kHz since we can best observe the transition from the Type I to the spatial broadening regime (see Figure 2). We distinguish two groups of glasses: G GK, BGGK and BGGN (Figure 3a) and BGGLaY1, BGGLaY2, and BGGLaY3 (Figure 3b). The first group the glasses contain varying amount of alkali (K and Na), while in the second group the Ge-Ga-Ba proportions are varied. Overall, we observe a positive phase shift, starting from Type I onset, increasing with pulse energy and until it reaches a plateau. The maximum  $\Delta\phi$  measured in our conditions exceeded 8 rad for G GK glass, and with a maximum value of 8.7 rad for BGGLaY3 in Figure 3b. Some features are common to all glass samples. At low pulse energies ( $< 2 \mu\text{J}$ ), each group has a similar  $\Delta\phi$  response. However, beyond  $2 \mu\text{J}$ , we observe discrepancies in the  $\Delta\phi$  magnitude. In Figure 3a, comparing BGGN and BGGK, it appears that the addition of K in the glass promotes higher phase shifting compared to the Na-containing glass for pulse energies  $> 3 \mu\text{J}$ . The variation could be related to the fictive temperature effect, i.e., the dependency between viscosity and cooling rate. In the type I regime, the magnitude of the phase shift is not sufficient to observe a composition dependence, the signal to noise ratio being too weak. In the heat accumulation region, corresponding to pulse energy above  $2 \mu\text{J}$ , the situation is clearer. The maximum phase shift in the spatial broadening regime ( $\Delta\phi$  in the 6 - 8 rad region) was higher than that in Type I regime indicating the prime candidate of BGG glasses for the inscription of waveguides.




Fig. 3. (a) Phase shift (in rad) for GGK, BGGK and BGGN glasses as a function of pulse energy. (b) Phase shift for BGGLaY1, BGGLaY2 and BGGLaY3 glasses. Left inset: optical image of BGGLaY1 in low energy. Right inset: optical image of BGGLaY1 (3  $\mu$ J and 2.5  $\mu$ J from left to right). Lines are guide-to-the-eye.

Figure 4 shows the maximum phase shift measured through QPM system as a function of Cations/GaO<sub>3/2</sub> (in cationic mol%) within the 6 studied glasses. Herein, we will limit our interpretation only to the spatial broadening regime. Figure 4 helps us to establish a link between the phase shift and the structural network in glasses. Hypothetically, the origin of the phase shift could be different between the rare earth and alkali-containing BGG glasses, therefore the data are discussed separately. Overall, the maximum phase shift decreased with the value of Cations/GaO<sub>3/2</sub> (in cationic mol%). For the rare-earth-containing glasses, the trend of  $\Delta\phi$  is obvious; it increases in the following order: BGGLaY3 > BGGLaY1 > BGGLaY2. One should note that the nature and concentrations and ratio of La and Y were kept constant. Note that the aforementioned order is preserved in terms of GaO<sub>3/2</sub>/GeO<sub>2</sub>, but is reversed in terms of the number of NBOs (before laser irradiation).

On the contrary, for the alkali-containing ones, we changed the nature of cation modifiers and their concentrations. GGK glass exhibited the maximum phase shift, and is the glass sample that possesses a ratio of Cations/GaO<sub>3/2</sub> equals to 1, or in other words

the K atoms only occupy charge-compensating sites. Comparing GGK to both BGGK and BGGN glasses, one can see that  $\Delta\phi$  decreased upon the introduction of Q<sup>3</sup> germanate units. This result highlights the importance of the charge compensation aspect concerning its effect on the phase shift. Thus, charge compensation in the network may help in the mobility of modifiers, probably inducing a higher refractive index variation.

For all studied compositions, we conclude that a lower number of NBO units (i.e., more charge compensating cations), leads to an increased value in the phase shift.




Fig. 4. Maximum phase shift ( $\Delta\phi$ , in Rad) as a function of Cations/GaO<sub>3/2</sub> (in cationic mol%).




Fig. 5. Excess loss at 2500 nm as a function of energy for GGK, BGGLaY1, BGGLaY2 and BGGLaY3 glasses after fs laser irradiation.

Furthermore, the excess losses post fs-laser irradiation at 2500 nm for GGK, BGGLaY1, BGGLaY2 and BGGLaY3 glasses were measured using FTIR spectrometer and are provided in Figure 5. Above 1.5  $\mu$ J, the excess losses increased along with pulse energy, which can be explained by the inhomogeneities (that can be seen in the optical microscope images) resulting in high light scattering. However, the excess losses remain below 2  $\text{cm}^{-1}$  for a fixed phase shift of  $\pi$  rad (a useful arrange for optical applications).

Finally, a review of the refractive index changes ( $\Delta n$ ) measured in BGG, Fluoride, Chalcogenide, Germanate and SiO<sub>2</sub> glasses is shown in Figure 6 (data collected from Refs. [29-36]). The  $\Delta n$  of BGG glasses ranges up to  $1.54 \times 10^{-2}$  and were comparable to most

chalcogenide glasses, and much higher than fluoride glasses. With the range of refractive index from 1.63 to 1.805 and the quite high  $\Delta n$ , BGG glasses exhibit a high potential and appear competitive compared to most chalcogenide glasses for id-IR applications.




Fig. 6. Ranges of refractive index variations vs. refractive index (typ. measured at 532 nm) for the BGG, chalcogenide, fluoride,  $\text{SiO}_2$  and germanate glasses.

A quick overview of the photosensitivity of high optical transparency (0.5 to 5.5  $\mu\text{m}$ ) BGG glasses exposed to IR-fs laser light was presented. The results in energy–repetition rate window evidenced that above a certain temperature threshold, a drastic increase of refractive index change  $\Delta n$  was observed that correlates with a spatial broadening of the laser tracks. According to the comparison made in 6 BGG glasses particularly in the spatial broadening regime, the ratio of Cations/ $\text{GaO}_{3/2}$  (cationic mol %) significantly impacts the maximum refractive index changes of the irradiated areas which become more important due to the charge compensation aspect and lower amount of NBOs on  $\text{GeO}_4$  units, resulting in higher index changes. Our results clearly demonstrated the potential of BGG glasses as prime candidates for the development of embedded photonic devices in the Near-IR and Mid-IR including graded index optics, diffractive optics and 3D geometric phase optics.

## References

- J. P. Bérubé, A. L. Camus, S. H. Messaddeq, Y. Petit, Y. Messaddeq, L. Canioni, and R. Vallée, *Opt. Mater. Express*, **7**, 3124-3135 (2017).
- Y. Bellouard, A. Said, and P. Bado, *Opt. Express* **13**, 6635-6644 (2005).
- K. M. Davis, K. Miura, N. Sugimoto, and K. Hirao, *Opt. Lett.* **21**, 1729-1731 (1996).
- Y. Sikorski, A. A. Said, P. Bado, R. Maynard, C. Florea, and K. A. Winick, *Electron. Lett.* **36**, 226-227 (2000).
- A. M. Streltsov and N. F. Borrelli, *Opt. Lett.* **26**, 42-43 (2001).
- T. Meany, M. Gräfe, R. Heilmann, A. Perez-Leija, S. Gross, M. J. Steel, M. J. Withford, and A. Szameit, *Laser Photon. Rev.* **9**, 363-384 (2015).
- C.-E. Athanasiou and Y. Bellouard, *Micromachines* **6**, 1365-1386 (2015).
- S. Eaton, M. Ng, R. Osellame, and P. Herman, *J. Non-Cryst. Sol.* **357**(11), 2387-2391 (2011).
- J. P. Bérubé, S. H. Messaddeq, I. Skripachev, R. Vallée, and Y. Messaddeq, *Opt. Express* **22**(23), 26103-26116 (2014).
- S. Gross, N. Jovanovic, A. Sharp, M. Ireland, J. Lawrence, and M. J. Withford, *Opt. Express* **23**(6), 7946-7956 (2015).
- J. Bai, X. Long, X. Liu, G. Huo, W. Zhao, R. Stojan, R. Hui, and G. Cheng, *Appl. Opt.* **52**(30), 7288-7294 (2013).
- S. S. Bayya, G. D. Chin, J. S. Sanghera, and I. D. Aggarwal, *Opt. Express* **14**(24), 11687-11693 (2006).

- T. Skopak, F. Calzavara, Y. Ledemi, F. Célarié, M. Allix, E. Véron, M. Dussauze, T. Cardinal, E. Fargin and Y. Messaddeq, *J. Non-Cryst. Solids* **514**, 98-107 (2019).
- X. Wen, G. W. Tang, J. W. Wang, X. D. Chen, Q. Qian and Z. M. Yang, *Opt. Express* **23**, 7722-7731 (2015).
- K. M. Davis, K. Miura, N. Sugimoto and K. Hirao, *Opt. Lett.* **21**, 1729 (1996).
- Y. Shimotsuma, P. G. Kazansky, J. Qiu and K. Hirao, *Phys. Rev. Lett.* **91**, 247405 (2003).
- E. N. Glezer and E. Mazur, *Appl. Phys. Lett.* **71**, 882 (1997).
- M. Lancry, B. Poumellec, A. Chahid-Erraji, M. Beresna, and P. G. Kazansky, *Opt. Mater. Express*, **1**, 711-723 (2011).
- S. M. Eaton, H. B. Zhang, P. R. Herman, F. Yoshino, L. Shah, J. Bovatsek, and A. Y. Arai, *Opt. Express* **13**, 4708-4716 (2005).
- A. L. Camus, Y. Petit, J. P. Bérubé, M. Bellec, L. Canioni, and R. Vallée, *Opt. Express* **29**, 8531-8541 (2021).
- S. S. Bayya, J. S. Sanghera and I. D. Aggarwal, United states patent, US007285509B2 (2007).
- T. Guérineau, C. Strutynski, T. Skopak, S. Morency, A. Hanafi, F. Calzavara, Y. Ledemi, S. Danto, T. Cardinal and Y. Messaddeq, *Opt. Mater. Express*, **9**, 2437-2445 (2019).
- C. Strutynski, F. Calzavara, T. Guérineau, L. Loi, R. Laberdesque, J. M. Rampnoux, S. Morency, Y. Ledemi, Y. Petit, M. Dussauze, F. Désévéday, F. Smektala, S. Danto, L. Canioni, Y. Messaddeq, E. Fargin, and T. Cardinal, *Opt. Mater. Express*, **11**, 1420-1430 (2021).
- H.-J. Hoffmann, *Optical glasses* (2017).
- T. Skopak, S. Kroeker, K. Levin, M. Dussauze, R. Méreau, Y. Ledemi, T. Cardinal, E. Fargin and Y. Messaddeq, *J. Phys. Chem. C* **123**, 1370-1378 (2019).
- J. M. Jewell *et al.* Structural influences on the hydroxyl spectra of barium gallogermanate glasses, *Journal of Non-Crystalline Solids*, 1995.
- G. Query *et al.* Influence of Hydroxyl Group on IR Transparency of Tellurite-Based Glasses, *International Journal of Applied Glass Science*, 2014.
- M. J. Weber, *Handbook of optical materials*, Berkeley, California (2002).
- A. Arriola, S. Gross, M. Ams, T. Gretzinger, D. L. Coq, R. P. Wang, H. Ebendorff-Heidepriem, J. Sanghera, S. Bayya, L. B. Shaw, M. Ireland, P. Tuthill, and M. J. Withford, *Opt. Mater. Express*, **7**, 698-711 (2017).
- J. Bai, X. W. Long, X. Liu, G. W. Huo, W. Zhao, R. Stojan, R. Q. Hui, and G. H. Cheng, *Opt. Mater. Express*, **52**, 7288-7294 (2013).
- S. Gross, D. G. Lancaster, H. Ebendorff-Heidepriem, T. M. Monro, A. Fuerbach and M. J. Withford, *Opt. Mater. Express*, **3**, 574-583 (2013).
- S. H. Messaddeq, J. P. Bérubé, M. Bernier, I. Skripachev, R. Vallée, and Y. Messaddeq, *Opt. Express* **20**(3), 2824-2831 (2012).
- M. Hughes, W. Yang, and D. Hewak, *Appl. Phys. Lett.* **90**, 131113 (2007).
- S. M. Eaton, M. L. Ng, R. Osellame, P. R. Herman, *J. Non-Cryst. Solids*, **357**, 2387-2391 (2011).
- S. Sebastiani, G. Nunzi Conti, S. Pelli and G. C. Righini, *Opt. Express*, **13**, 1696-1701 (2005).
- J. Hu, N. Feng, N. Carlie, L. Petit, J. Wang, *Opt. Express*, **15**, 14566-14572 (2007).