



**HAL**  
open science

## Strain and Spin-Orbit Coupling Engineering in Twisted WS<sub>2</sub>/Graphene Heterobilayer

Cyrine Ernandes, Lama Khalil, Hugo Henck, Meng-Qiang Zhao, Julien Chaste, Fabrice Oehler, Alan Johnson, Maria Asensio, Debora Pierucci, Marco Pala, et al.

► **To cite this version:**

Cyrine Ernandes, Lama Khalil, Hugo Henck, Meng-Qiang Zhao, Julien Chaste, et al.. Strain and Spin-Orbit Coupling Engineering in Twisted WS<sub>2</sub>/Graphene Heterobilayer. *Nanomaterials*, 2021, 11 (11), pp.2921. 10.3390/nano11112921 . hal-03450796

**HAL Id: hal-03450796**

**<https://hal.science/hal-03450796>**

Submitted on 26 Nov 2021

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



## Article

# Strain and Spin-Orbit Coupling Engineering in Twisted WS<sub>2</sub>/Graphene Heterobilayer

Cyrine Ernandes <sup>1</sup>, Lama Khalil <sup>1</sup>, Hugo Henck <sup>1</sup>, Meng-Qiang Zhao <sup>2</sup>, Julien Chaste <sup>1</sup>, Fabrice Oehler <sup>1</sup> , Alan T. Charlie Johnson <sup>3</sup>, Maria C. Asensio <sup>4,5</sup>, Debora Pierucci <sup>1</sup>, Marco Pala <sup>1</sup> , José Avila <sup>6,\*</sup> and Abdelkarim Ouerghi <sup>1,\*</sup>

- <sup>1</sup> Centre de Nanosciences et de Nanotechnologies, CNRS, Université Paris-Saclay, 91120 Palaiseau, France; cyrine.ernandes@universite-paris-saclay.fr (C.E.); lama.khalil@universite-paris-saclay.fr (L.K.); hugo.henck@gmail.com (H.H.); julien.chaste@c2n.upsaclay.fr (J.C.); fabrice.oehler@c2n.upsaclay.fr (F.O.); debora.pierucci@c2n.upsaclay.fr (D.P.); marco.pala@c2n.upsaclay.fr (M.P.)
- <sup>2</sup> Department of Chemical and Materials Engineering, New Jersey Institute of Technology, 138 Warren Street, Newark, NJ 07103, USA; mz24@njit.edu
- <sup>3</sup> Department of Physics and Astronomy, University of Pennsylvania, 209S 33rd Street, Philadelphia, PA 19104, USA; cjohnson@physics.upenn.edu
- <sup>4</sup> Materials Science Institute of Madrid (ICMM), Spanish Scientific Research Council (CSIC), Cantoblanco, 28049 Madrid, Spain; mc.asensio@csic.es
- <sup>5</sup> MATINEE, CSIC Research Associated Unit between the Institute of Materials Science of the Valencia University (ICMUV) and the ICMM, Cantoblanco, 28049 Madrid, Spain
- <sup>6</sup> Synchrotron-SOLEIL, Université Paris-Saclay, Saint-Aubin, BP48, 91192 Gif sur Yvette, France
- \* Correspondence: jose.avila@synchrotron-soleil.fr (J.A.); abdelkarim.ouerghi@c2n.upsaclay.fr (A.O.)



**Citation:** Ernandes, C.; Khalil, L.; Henck, H.; Zhao, M.-Q.; Chaste, J.; Oehler, F.; Johnson, A.T.C.; Asensio, M.C.; Pierucci, D.; Pala, M.; et al. Strain and Spin-Orbit Coupling Engineering in Twisted WS<sub>2</sub>/Graphene Heterobilayer. *Nanomaterials* **2021**, *11*, 2921. <https://doi.org/10.3390/nano11112921>

Academic Editors: Antonio Di Bartolomeo and Fabrizio Pirri

Received: 19 October 2021  
Accepted: 28 October 2021  
Published: 31 October 2021

**Publisher's Note:** MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



**Copyright:** © 2021 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).

**Abstract:** The strain in hybrid van der Waals heterostructures, made of two distinct two-dimensional van der Waals materials, offers an interesting handle on their corresponding electronic band structure. Such strain can be engineered by changing the relative crystallographic orientation between the constitutive monolayers, notably, the angular misorientation, also known as the “twist angle”. By combining angle-resolved photoemission spectroscopy with density functional theory calculations, we investigate here the band structure of the WS<sub>2</sub>/graphene heterobilayer for various twist angles. Despite the relatively weak coupling between WS<sub>2</sub> and graphene, we demonstrate that the resulting strain quantitatively affects many electronic features of the WS<sub>2</sub> monolayers, including the spin-orbit coupling strength. In particular, we show that the WS<sub>2</sub> spin-orbit splitting of the valence band maximum at K can be tuned from 430 to 460 meV. Our findings open perspectives in controlling the band dispersion of van der Waals materials.

**Keywords:** twisted heterobilayer; van der Waals materials; spin-orbit coupling; band structure

## 1. Introduction

The successful fabrication of monolayer graphene (Gr) by mechanical exfoliation has triggered an intense interest in transition metal dichalcogenides (TMDs, e.g., MX<sub>2</sub> with M = W, or Mo and X = S, Se, or Te), which are two-dimensional (2D) semiconductors whose optical and electronic properties can be tailored as a function of the number of layers and the stacking orientation [1]. More interestingly, assembling TMD monolayers into van der Waals (vdW) heterostructures can further modulate these properties through the choice of materials and the relative alignment between the monolayers [2]. While covalent heterostructures are governed by a fixed lattice mismatch and interlayer misorientation, vdW heterostructures present an additional degree of freedom in the arbitrary rotation angle between the layers, referred to as the “twist” angle. For small twist angles, a long wavelength periodic strain modulation arises, known as the Moiré superlattice [3]. The formation of Moiré superlattices between 2D materials directly alters the electronic band structure [4], and sometimes creates spectacular arrangements [5]. Notably, specific “magic”

twist angles have been associated to unique dispersion relations with localized flat bands in bilayer graphene and TMDs [6]. An experimental study using scanning tunneling microscopy has recently evidenced these quantum-confined electronic states near the band edges for aligned MoS<sub>2</sub>/WSe<sub>2</sub> heterobilayers [7]. Experimentally, the range of “magic” angles is much wider in TMD/TMD heterostructures than in twisted bilayer graphene (Gr/Gr), for which the flat band configuration only exists within  $\pm 0.2^\circ$  of the magic angle [3,5]. New variants of twisted hybrid heterostructures have also been proposed, in which the monolayers are made of distinct 2D materials (e.g., TMD/Gr) instead of sibling TMD crystals. In such TMD/Gr heterostructures, several electronic features can be improved with respect to the corresponding TMD monolayer structure, as in the case of WS<sub>2</sub>/Gr heterobilayers, which exhibit remarkable advantages compared to monolayer WS<sub>2</sub> [8–10]. While MX<sub>2</sub> monolayers are generally limited by a relatively low carrier mobility and photosensitivity, the MX<sub>2</sub>/Gr heterobilayers often offer much improved values, which leads to direct applications in photodetector and transistor devices [11]. Finally, recent theoretical and experimental studies have reported that strong spin-orbit interactions (SOI) can be induced in graphene using MX<sub>2</sub>/Gr heterobilayers [12–14]. The SOC prevents novel quantum states from emerging, such as the quantum anomalous Hall state. On the other hand, owing to their strong SOC, MX<sub>2</sub> provide an ideal platform to increase the SOC in graphene by the proximity effect [14–16].

However, less attention has been paid to the modification of the TMD band structure in these heterobilayers [15]. In particular, the impact of the “twist” angle variations on the band structure of WS<sub>2</sub>/Gr heterobilayers has never been investigated experimentally. Nanoscopic angle-resolved photoelectron spectroscopy (nano-ARPES) is a powerful technique used to experimentally study and visualize the band structure around the valence band edge of twisted heterobilayers. Here, using nano-ARPES, we investigate the electronic structure of WS<sub>2</sub>/Gr at different twist angles. For all our measured twist angles, we observe that the graphene bands are n-doped, and that the graphene-derived Dirac point is located within the WS<sub>2</sub> bandgap. We experimentally show that the strength of spin-orbit coupling (SOC) in the WS<sub>2</sub>-related valence band depends on the interlayer twist angle between WS<sub>2</sub> and graphene, and that the SOC value is 30 meV higher than the reference monolayer value.

## 2. Materials and Methods

The WS<sub>2</sub>/SiO<sub>2</sub> samples were grown by chemical vapor deposition (CVD) in a 1” quartz tube furnace. The growth substrate (SiO<sub>2</sub>/Si(001)) was placed in the center of the furnace and heated to 800 °C. A 25 mg sulphur pellet was placed on a piece of silicon and positioned upstream in the furnace such that its temperature was approximately 150 °C. Carrier gas (500 sccm N<sub>2</sub> and 15 sccm H<sub>2</sub>) was used to bring sulphur vapor into the furnace for a 30 min growth period. A PMMA-assisted method was employed to transfer the CVD-grown WS<sub>2</sub> onto epitaxial monolayer graphene on SiC(0001) [17]. Typical single-crystal domains with an equilateral triangle shape were obtained by the CVD growth procedure. The WS<sub>2</sub> domains transferred onto the graphene retained their triangular shapes, with lateral sizes of ~20 to ~200 μm. To further clean the surface and interface of the WS<sub>2</sub>/Gr, we annealed the samples at 350 °C for 120 min in UHV (base pressure below  $P \sim 10^{-10}$  mbar).

The  $\mu$ -PL/Raman measurements were conducted at room temperature, using a commercial confocal Horiba micro-Raman microscope (HORIBA, Palaiseau, France) with a 100× objective, and a 532 nm laser excitation [18]. The nano-ARPES measurements (spot size about 600 nm) were conducted at the Antares beamline of the SOLEIL synchrotron (Saint-Aubin, France). We used linearly polarized photons of 100 eV and a hemispherical electron analyzer scienta R4000 with horizontal slits to allow band mapping. All nano-ARPES experiments were performed at a low temperature of 70 K, and the energy resolution was about 10 meV.

The band structure calculations were realized with the QUANTUM ESPRESSO code [19]. We adopted fully relativistic pseudopotentials and performed noncollinear


simulations to include the spin-orbit interaction. For the exchange-correlation term, we considered both the PBE and the HSE hybrid functionals [20] to better estimate the band-gap energy. The self-consistent solution was obtained by adopting a  $10 \times 15 \times 1$  Monkhorst-Pack grid and a cutoff energy of 50 Ry. A vacuum space of 20 Å along the vertical direction was used to minimize the interaction between two adjacent sheets. Cell parameters and atomic positions were relaxed according to a convergence threshold for forces and energy of  $10^{-3}$  and  $10^{-4}$  (a.u.), respectively.

### 3. Results and Discussion

In the absence of other direct experimental investigations on the band structure of twisted  $\text{WS}_2$  monolayers on graphene, the present nano-ARPES study reveals original strain-related changes in the band dispersion and SOC strength of  $\text{WS}_2/\text{Gr}$  heterostructure. In a previous report, we have proved that it is possible to resolve the bands of  $\text{WS}_2$  flakes transferred on an epitaxial graphene underlayer [17]. In the present work, we followed the same procedure to obtain the  $\text{WS}_2/\text{Gr}$  heterobilayer. Here, monocrystalline mono- and few-layer  $\text{WS}_2$  flakes were first grown on a  $\text{SiO}_2/\text{Si}$  substrate using a CVD technique (see Materials and Methods), and then transferred onto a  $\text{Gr}/\text{SiC}$  substrate [21]. To ensure a proper cleaning of interfaces, the samples were annealed at 350 °C in vacuum before the nano-ARPES measurements.

A schematic of the atomic structure of the  $\text{WS}_2/\text{Gr}$  hybrid system, which can present an arbitrary in-plane twist angle,  $\theta$ , between the monolayers, is shown in Figure 1a. Figure 1b presents an optical image of the sample, showing an area with several  $\text{WS}_2$ -flake-transferred graphene. The overall coverage of the graphene surface by  $\text{WS}_2$  was approximately 30%. Because of the poor optical contrast on the  $\text{SiC}$  substrate, red contours have been drawn to outline the shape of the  $\text{WS}_2$  flakes. As is visible in Figure 1b, the optical image consists of regular triangular  $\text{WS}_2$  flakes, arbitrarily rotated with respect to the underlying graphene substrate. While it is possible to directly estimate the value of the twist angle,  $\theta$ , between the  $\text{WS}_2$  flakes and graphene from the optical image, more accurate values can be obtained using nano-ARPES. To this end, nano-ARPES constant energy maps were recorded outside and inside the  $\text{WS}_2$  flakes. The twist angle,  $\theta$ , was then defined in the reciprocal space as the angle between the  $\Gamma K_{\text{Gr}}$  and  $\Gamma K_{\text{WS}_2}$  directions. We obtained values of  $\theta = 33^\circ$ ,  $11^\circ$ ,  $43^\circ$ , and  $16^\circ$  for Flake 1, Flake 1b, Flake 2, and Flake 3, respectively.

To investigate the optical properties of the  $\text{WS}_2$  flakes,  $\mu$ -PL/Raman spectroscopy was carried out at room temperature [22]. The vibration modes of Flake 1 can be obtained by using micro-Raman ( $\mu$ -Raman) spectroscopy. Figure 1d shows the  $\mu$ -Raman scattering spectra obtained before and after transferring the  $\text{WS}_2$  flakes onto graphene. For both spectra, we observed the in-plane phonon mode,  $E_{2g}'^1$ , and the out-of-plane phonon mode,  $A_{1g}$ . In particular, the  $E_{2g}'^1(\Gamma)$  mode, observed at  $353.8 \text{ cm}^{-1}$  for  $\text{WS}_2/\text{SiO}_2$ , was redshifted of  $2 \text{ cm}^{-1}$  with respect to that of  $\text{WS}_2/\text{Gr}$ . Similarly, the  $A_{1g}(\Gamma)$  peak, observed at  $417.7 \text{ cm}^{-1}$  [23,24] for  $\text{WS}_2/\text{SiO}_2$ , also shows a small redshift of about  $1 \text{ cm}^{-1}$  with respect to that of  $\text{WS}_2/\text{Gr}$ . These shifts for both modes confirm the interlayer coupling between  $\text{WS}_2$  and graphene, as seen by the PL measurements. These shifts could also be attributed to a stress reduction when  $\text{WS}_2$  is transferred onto the graphene substrate [17]. Beside the  $A_{1g}$  and  $E_{2g}'^1$  modes, both Raman spectra present a series of overtone and combination peaks. For  $\text{WS}_2/\text{SiO}_2$ , the second order Raman peak,  $2LA(M)$ , relative to the longitudinal acoustic phonons at the M-point in the Brillouin zone (BZ), and the  $E_{2g}^1(M)$  mode, are observed at  $349.8 \text{ cm}^{-1}$  and  $350.5 \text{ cm}^{-1}$ , respectively [25]. These peaks were redshifted of  $1 \text{ cm}^{-1}$  or  $2 \text{ cm}^{-1}$ , compared to those of  $\text{WS}_2/\text{Gr}$ , attributable to a strain between the  $\text{WS}_2$  and the graphene substrate. Additional Raman peaks around  $296 \text{ cm}^{-1}$  and  $323 \text{ cm}^{-1}$  were combination modes, attributed to the  $2LA(M) - 2E_{2g}'^1(\Gamma)$  and the  $2LA(M) - E_{2g}^2(\Gamma)$  modes, respectively [8].



**Figure 1.** Structural and electronic properties of a WS<sub>2</sub>/Gr heterostructure: (a) 3D view of graphene on top of monolayer TMDs. Here,  $\theta$  is the twist angle between graphene and the TMD layers; (b) Optical image of the WS<sub>2</sub> transferred onto the graphene layer; (c,d) Room temperature PL and micro-Raman spectra of Flake 1 before (1 ML WS<sub>2</sub>/SiO<sub>2</sub>), and after (1 ML WS<sub>2</sub>/Gr), transfer.


Before transferring Flake 1 (1 ML) and Flake 1b (2 ML) onto graphene, we measured their PL spectra on the SiO<sub>2</sub> substrate (see Supplementary Information, Figure S1). As shown in Figure S1, the PL intensity of Flake 1 is one order of magnitude higher than that of Flake 1b. This is consistent with the literature and indicates that a direct to an indirect bandgap transition occurs when increasing the number of layers of WS<sub>2</sub> [26]. To study the electronic coupling between 1 ML of WS<sub>2</sub> and the graphene, we compare, in Figure 1c, 1 ML of the WS<sub>2</sub> PL spectra acquired on the SiO<sub>2</sub> and graphene substrate, respectively. We observed a drastic quench of the PL intensity for WS<sub>2</sub> on graphene, attributed to an interfacial electron transfer from the n-doped graphene substrate to WS<sub>2</sub> [27–31]. This electron transfer, thus, reflects the electronic coupling between WS<sub>2</sub> and graphene. From the PL spectrum of 1 ML of WS<sub>2</sub> on graphene, we also extracted the corresponding optical bandgap value of 1.95 eV, in agreement with previous experimental reports [32–36]. We noticed, as well, a bandgap decrease of about 40 meV in the case of the WS<sub>2</sub>/Gr. The decrease of the PL intensity and the bandgap can be explained by a charge transfer and strain induced by the graphene layer. The possible band structure and bandgap change in single layer WS<sub>2</sub> could be translated by the orientation angle of the flakes with respect to the graphene substrate and may induce a variation of the properties of WS<sub>2</sub>. Thus, despite the clean interface between WS<sub>2</sub> and graphene [8], both the PL and  $\mu$ -Raman results prove that the two layers are coupled electronically.

We now turn to the nano-ARPES characterization of the WS<sub>2</sub>/Gr heterostructures to study the coupling between the WS<sub>2</sub> and the graphene substrate. We obtained a sharp ARPES signal on the graphene and on each individual flake, which we associated with the

good material quality and sample fabrication. Combining the total valence band mapping in the reciprocal space, and the spatial information in the direct space, we were able to extract and to localize, with nanometric spatial resolution, the different contributions of each material in the final electronic band structure. In Figure 2, we can thus identify and separate the following dispersion relations: the graphene  $\pi$  bands, and the monolayer (1 ML)  $\text{WS}_2$  and the bilayer (2 ML)  $\text{WS}_2$  valence bands (Figure 2a,b). By integrating the photoemission intensity in an energy window centered around the valence band maximum (VBM), while scanning the sample in real space along the two in-plane directions, we obtained spatial maps and morphological information. Figure 2a is centered on the graphene  $\pi$  band's energy, so that high-intensity signal (red color) shows the extent of the continuous graphene underlayer, while the region covered by  $\text{WS}_2$  crystals appears as low signal (blue color). Conversely, the map in Figure 2b integrates around the  $\text{WS}_2$  VBM energy and shows three distinct regions: high (red), medium (yellow), and low (blue) intensities, which correspond to 2 ML  $\text{WS}_2$ , 1 ML  $\text{WS}_2$ , and graphene, respectively. These two  $\text{WS}_2$  and graphene nano-ARPES spatial maps (Figure 2a,b) further confirmed the stacking sequence of our heterostructure, as deduced from the previous optical characterizations (PL, Raman) in Figure 1. Each of these regions (Gr, 1 ML  $\text{WS}_2$ , and 2 ML  $\text{WS}_2$ ) displayed a uniform intensity, attributed to the homogeneity of the electronic properties. The single and robust Dirac cone at the K high-symmetry points (at  $k_{\parallel} = 1.703 \text{ \AA}^{-1}$ ) confirms that the graphene inside the heterostructure preserves its Dirac linear dispersion, and the massless relativistic character of the graphene monolayer carriers close to the Fermi level. The analysis of the  $\pi$  band dispersion, inside and outside, determines a Fermi velocity  $v_F \sim 1.1 \times 10^6 \text{ m/s}$ . The neutrality level (the Dirac point) in the band structure of the graphene was observed at a binding energy of about 0.3 eV below Fermi level. The electron doping level can be estimated to about  $9 \times 10^{12} \text{ cm}^{-2}$  (see Supplementary Information, Figure S2) and is rather high in contrast to isolated monolayer graphene. This doping is explained conventionally by donor-like states associated with the interface layer between the graphene and the SiC(0001) substrate that overcompensate for the polarization doping from the SiC substrate [30–34].

We then extracted and analyzed the electronic band parameters along the reciprocal  $\Gamma$ -K direction of the  $\text{WS}_2/\text{Gr}$  heterostructure (Flake 1 and Flake 1b), depending on the thickness of the  $\text{WS}_2$  flakes. The number of branches at the  $\Gamma$  point agreed with the number of layers: one for the monolayer, and two for the bilayer. From the ARPES data in Figure 2c,d, we clearly detect the layer-dependent band structure evolution. In particular, the change from the 1 ML  $\text{WS}_2/\text{Gr}$  to the 2 ML  $\text{WS}_2/\text{Gr}$  moves the VBM from the K point for the 1 ML  $\text{WS}_2/\text{Gr}$  (1.82 eV binding energy), to the  $\Gamma$  point for the 2 ML  $\text{WS}_2/\text{Gr}$  (binding energy of 1.62 eV). We thus expect that the 1 ML of  $\text{WS}_2/\text{Gr}$  will show a direct bandgap, VBM, and conduction band minimum (CBM) at the K point, while the 2 ML  $\text{WS}_2/\text{Gr}$  is indirect, with the VBM located at  $\Gamma$ , and the CBM at K. Therefore, the overall variation of the  $\text{WS}_2/\text{Gr}$  band structure with the  $\text{WS}_2$  thickness (1 ML, 2 ML) is in agreement with DFT theory [5]. Up to now, our results corroborate closely to those of Coletti et al. on the photoemission of an epitaxial-aligned ( $\theta = 0^\circ$ ) 1 ML  $\text{WS}_2/\text{Gr}/\text{SiC}$  heterostructure [9], for which the relatively weak  $\text{WS}_2/\text{Gr}$  interaction causes the constitutive monolayer of the heterostructure to retain most of the features of their initial band structure. However, a more detailed look at the TMD-related bands near K reveals important details. In  $\text{WS}_2$ , as in other TMD materials, the strong spin-orbit coupling (SOC) of transition-metal  $d$  orbitals leads to an energy splitting ( $\Delta_{\text{SOC}}$ ) of the valence bands at the six corners (K, K' points) of the BZ. This large  $\Delta_{\text{SOC}}$  value mainly originates from the hybridization between the W  $d_{xy}$  and  $d_{x^2-y^2}$  and the S  $p_x$  and  $p_y$  bonding states [35]. Using the experimental nano-ARPES dispersion at K, we can, thus, directly measure the value of  $\Delta_{\text{SOC}}$  in our samples. For monolayer  $\text{WS}_2$ , this value is predicted to be 430 meV [5], but Coletti et al. [9] already report a much higher value of  $\Delta_{\text{SOC}} = 462 \text{ meV}$  for epitaxial ( $\theta = 0^\circ$ )  $\text{WS}_2/\text{Gr}/\text{SiC}$  [9], which suggests that there is some degree of interaction between the  $\text{WS}_2$  and the Gr underlayers. The band splitting in our sample is about 1 ML  $\text{WS}_2/\text{Gr}$  (Flake 1,  $\Delta_{\text{SOC}} \sim 440 \text{ meV}$ ), and


2 ML WS<sub>2</sub>/Gr (Flake 1b,  $\Delta_{\text{SOC}} \sim 400$  meV) heterostructures. As those two structures differ in ML thickness (1 vs. 2 ML), and twist angle  $\theta$  ( $33^\circ$  vs.  $11^\circ$ ), the  $\Delta_{\text{SOC}}$  difference cannot be unambiguously attributed to the twist angle effect.



**Figure 2.** Comparison of the electronic band structure between single and bilayer WS<sub>2</sub>: (a,b) Spatially resolved ARPES map of the  $\pi$  graphene band and the 1 ML WS<sub>2</sub> band; (c,d) ARPES map of single and bilayer WS<sub>2</sub> along the  $\Gamma$ K high-symmetry directions.

To isolate the impact of the twist angle, we now focus on 1 ML WS<sub>2</sub>/Gr heterobilayers at K. Compared to epitaxial vdW heterostructures, which are limited to  $\theta = 0^\circ$  but always present a coupling between the layers, our transferred WS<sub>2</sub>/Gr heterobilayer can sample arbitrary twist angles, but the interlayer coupling needs to be confirmed. Figure 3a–c present the experimental valence band structures acquired by nano-ARPES for  $\theta = 33^\circ$  (Flake 1),  $43^\circ$  (Flake 2), and  $16^\circ$  (Flake 3), using the naming scheme of Figure 1. We found that the  $\Delta_{\text{SOC}}$  varied widely, starting from 460 meV at  $\theta = 16^\circ$ , down to 440 meV near  $\theta = 33^\circ$ , and about 430 meV for  $\theta = 43^\circ$ . Additionally, we observed that the energy difference between the VBM at  $\Gamma$  and K, ( $\Delta_{\Gamma\text{K}}$ ) also varied with the twisted angle. In Figure 3d–f, the second derivative spectra of the experimental data were compared with the DFT calculations obtained by HSE06 (red lines). The main ARPES features are well-reproduced by the calculations for

all twist angles, but tensile bi-axial strain must be introduced to obtain the correct  $\Delta_{\Gamma K}$  spacing. The total variation from the reference theoretical value of 430 meV is significant and confirms that our transferred 1 ML  $\text{WS}_2$  flakes effectively couple to the Gr underlayer. From these measurements, we conclude that the twist angle modulates the SOC strength in the TMD-related band of 1 ML  $\text{WS}_2/\text{Gr}$  heterobilayers, with positive variations up to 30 meV from the reference theoretical value.



**Figure 3.** Evolution of the electronic band structure of the  $\text{WS}_2/\text{Gr}$  heterobilayer at various twist angles: (a–c) ARPES band map along GK of the  $\text{WS}_2$  layer, with twist angles of 16, 33, and 43°, respectively; (d–f) Corresponding second derivative spectra of the (a–c) panels on which the calculated band structure obtained by HSE06 (red lines) is superimposed. The tensile biaxial strain used in the simulations is marked next to the experimental twist angle.

We have considered two hypotheses to explain the observed variation of the SOC in our twisted 1 ML  $\text{WS}_2/\text{Gr}$  heterobilayers: (i) electronic coupling via charge transfer; and (ii) biaxial strain at the  $\text{WS}_2/\text{Gr}$  interface [36].

- (i) First, we can consider the charge transfer probabilities occurring at specific twist angles as the main contribution to the  $\Delta_{\text{SOC}}$  variations. In the present case, the heterostructure is formed by n-type graphene and n-type  $\text{WS}_2$ , which creates a Schottky barrier. The Schottky barrier height (SBH) thus corresponds to the energy difference between the CBM of the  $\text{WS}_2$  band, and the position of the Fermi level in the graphene Dirac cone [4]. Since the graphene layer is n-doped, a charge transfer could occur from the K valley of the graphene to the CBM of the  $\text{WS}_2$ . Following [15,16], the interlayer interaction between  $\text{WS}_2$  and Gr is proportional to the transfer integral between the two lattices, which decreases exponentially with the interlayer spacing in real space, but also requires momentum matching in the reciprocal space. As illustrated in Supplementary Information (Figure S3), the positions of three specific k-vectors in the BZ of  $\text{WS}_2$  vary with the twist angle (red circles) and can approach the CBM of  $\text{WS}_2$  (green symbols). It turns out that the interlayer coupling and, hence, the spin-splitting of  $\text{WS}_2$ , is maximal when the wavevectors,  $k_1^\theta$ ,  $k_2^\theta$ , and  $k_3^\theta$ , approach the CBM of the  $\text{WS}_2$  located in the Q point (middle point between  $\Gamma$  and K) for  $\theta \sim 20^\circ$ . While this effect may occur in our structures, the expected order of magnitude (a few




- meV) and angular positions do not match our experiments. Therefore, charge transfer is not the main contributor to the observed  $\Delta_{\text{SOC}}$  variations;
- (ii) Mechanical strain is an expected feature of vdW heterostructures, which assemble materials of different lattice parameters. Although the vdW interaction is weaker than covalent bounds, it can still create Moiré superlattices that can affect the material strain and its electronic properties. The superstructure is governed by the lattice mismatch and by the rotational and translational misalignments of the two lattices. Here, the observed angular misalignment,  $\theta$  WS<sub>2</sub>/Gr, combined with the theoretical lattice mismatch, ( $a_{\text{Gr}} \sim 2.46 \text{ \AA}$ ,  $a_{\text{WS}_2} \sim 3.16 \text{ \AA}$ ), can create a long-range strain modulation, which can be grossly approximated to a uniform tensile or compressive in-plane strain [37].

Hence, the latter explanation, (ii), seems to better suit our experimental observations. To support this argument, we now compare our experimental ARPES data with band structure calculations computed using DFT. For monolayer WS<sub>2</sub>, a tensile in-plane biaxial strain will decrease the vertical distance between the upper and lower sublayers of the S atoms, which, in turn, reduces the bandgap and affects the  $\Delta_{\text{SOC}}$  at K [36,38]. In the DFT calculations, the biaxial strain is applied by modifying the lattice constant of WS<sub>2</sub>, followed by a structural relaxation to obtain the most favorable atomic positions.

To further test our calculations, we have performed additional DFT simulations using another exchange-correlation functional (PBE vs. HSE). In addition to the atomic structure, Figure 4a shows the calculated electronic band structure for WS<sub>2</sub> for the tensile and compressive biaxial strain values ( $\pm 2\%$ ). Although the overall dispersions look similar, there are differences between all the structures. To compare with the experimental ARPES result, we first focus on the top of the valence band near the K point. In agreement with the experiment, our DFT unstrained WS<sub>2</sub> monolayer is a semiconductor with a 1.58 eV direct bandgap (i.e., VBM and CBM located at K). The  $\Delta_{\text{SOC}}$  value depends on the chosen exchange-correlation functionals (430 meV PBE, 551 meV HSE). We confirm that the  $\Delta_{\text{SOC}}$  of the VBM at K increases with the tensile biaxial strain, but that the rather extreme value of 1% merely increases the  $\Delta_{\text{SOC}}$  by only 15 meV. The opposite variation is observed for compressive biaxial strain (see Supplementary Information, Figure S4). The final inferred  $\Delta_{\text{SOC}}$  variation, +15 meV per 1% in plane tensile strain, is independent of the chosen exchange-correlation functionals (PBE or HSE) and matches the existing theoretical results on WS<sub>2</sub> and WSe<sub>2</sub> [36,38]. However, the variation of  $\Delta_{\text{SOC}}$  at K is not the only marker of biaxial strain in the WS<sub>2</sub> band structure. As shown in Figure 4a, the energy position of the valence band near  $\Gamma$  also varies critically with the in-plane strain, while that near K remains mostly static. Therefore, we can estimate the biaxial strain in the WS<sub>2</sub> layer by fitting the valence band's energy position along the  $\Gamma$ –K direction. In a first approximation, we simply used the energy difference,  $\Delta_{\Gamma\text{K}}$ , and we computed tensile biaxial strains of +0.8% ( $\theta = 16^\circ$ ), +0.3% ( $\theta = 33^\circ$ ), and 0% ( $\theta = 43^\circ$ ). Such strain could arise from the fabrication process during the cooling down of the sample after the 350 °C annealing. From these results, we can recalculate, with DFT (PBE), the strain-corrected  $\Delta_{\text{SOC\_theo}}$  values of 440 meV ( $\theta = 16^\circ$ ), 434 meV ( $\theta = 33^\circ$ ), and 430 meV ( $\theta = 43^\circ$ ). Table 1 summarizes these results, along with the corresponding experimental  $\Delta_{\text{SOC}}$  data.

Compared with the experimental  $\Delta_{\text{SOC}}$  values, we see that this simple biaxial strain model reproduces the sign and the order of magnitude of the  $\Delta_{\text{SOC}}$  variations. For such large strain values, it is important to check the behavior of the conduction band. Here, the DFT results show the existence of the local minimum of the conduction band along the  $\Gamma$ –K direction (Q point), which should lead from a direct to an indirect bandgap at about 1% compressive strain (see Supplementary Information, Figure S4). Such a drastic change should be clearly visible in the optical characterization (PL), thus implying that only tensile strain was present in our samples. When comparing the charge transfer to the biaxial strain, we conclude that biaxial strain better reproduces the observed change in SOC in the TMD-related band of our WS<sub>2</sub>/Gr heterostructure.



**Figure 4.** Structural and electronic properties of WS<sub>2</sub> under strain: (a) Band structures of WS<sub>2</sub> for different strains; (b) DFT calculations of the evolution of SOC under strain (PBE and HSE06, respectively).

**Table 1.** Summary of 1 ML WS<sub>2</sub>/Gr flake properties: experimental twist angle (from ARPES); energy difference of the VBM  $\Delta_{\Gamma K}$ ; corresponding computed biaxial strain (as determined from DFT); corresponding theoretical  $\Delta_{\text{SOC,theo}}$  from PBE functional (reference value 430 meV at 0% strain); and experimental  $\Delta_{\text{SOC}}$  measurements.

	Flake #3	Flake #1	Flake #2
WS <sub>2</sub> /Gr twist angle (°)	16°	33°	43°
Valence $\Delta_{\Gamma K}$ difference (eV)	0.25	0.31	0.34
Computed biaxial strain (%)	+0.8	+0.3	0.0
Theoretical $\Delta_{\text{SOC,theo}}$ (meV) at K	440	434	430
Experimental $\Delta_{\text{SOC}}$ (meV) at K	460 ± 5	440 ± 5	430 ± 5

#### 4. Conclusions

In summary, we studied the electronic structure, using nano-ARPES, of a 1 ML WS<sub>2</sub>/Gr heterobilayer with different twist angles. Because of the relatively weak coupling between Gr and WS<sub>2</sub>, the valence bands of the heterostructure retained some resemblance to their elementary constituent, but the detailed analysis of the TMD-related bands reveals a large twist-angle dependence. Specifically, the spin-orbit splitting of the valence band maximum at K ( $\Delta_{\text{SOC}}$ ) can be tuned from 430 to 460 meV. While theoretical modeling combining the biaxial strain in the DFT calculation can reproduce some of the features of the band structure, such extreme  $\Delta_{\text{SOC}}$  variations currently elude our modeling attempts. On the practical side, this work implements yet another possible route for tailoring the band structure of TMD materials: by controlling the twist angle between the TMD/Gr heterojunctions.

**Supplementary Materials:** The following are available online at <https://www.mdpi.com/article/10.3390/nano11112921/s1>, Figure S1: Typical Band structure of graphene layer on SiC (0001) (inside and outside of the WS<sub>2</sub>), Figure S2: (a) Band-structure calculations of the monolayer WS<sub>2</sub> along the high symmetry points of the Brillouin zone for different stress levels. (b) The evolution of the three wavevectors  $k_1^0$ ,  $k_2^0$  and  $k_3^0$  as a function of the twist angle  $\theta$ . The hexagons represent the first Brillouin zone of (black) graphene, (red) WS<sub>2</sub> with  $\theta = 0$  and (magenta) WS<sub>2</sub> with  $\theta = 20^\circ$ . The green symbols represent the evolution of the Q points. (c) Distance between  $k_1^0$  and Q as a function of  $\theta$ , Figure S3: Evolution of the band-structure calculations of the monolayer WS<sub>2</sub> under strain, Figure S4: Evolution of the band-structure calculations of the monolayer WS<sub>2</sub> under strain.

**Author Contributions:** M.-Q.Z. and A.T.C.J. fabricated the samples; C.E., L.K., D.P., A.O., J.A. and M.C.A. carried out the nano-XPS/nano-ARPES experiments; J.C., H.H. and C.E. characterized the samples by means of  $\mu$ -Raman/PL spectroscopy and analyzed the Raman/PL data; M.P. carried the DFT calculation; C.E., J.C., L.K., H.H., J.A., D.P., F.O., A.O. and M.P. analyzed the data; C.E., M.P., F.O. and A.O. wrote the manuscript. All authors have read and agreed to the published version of the manuscript.

**Funding:** We acknowledge the financial support by RhomboG (ANR-17-CE24-0030), MagicValley (ANR-18-CE24-0007), and Graskop (ANR-19-CE09-0026) grants.

**Institutional Review Board Statement:** Not applicable.

**Data Availability Statement:** The datasets generated during and/or analyzed during the current study are available from the corresponding author on reasonable request.

**Conflicts of Interest:** The authors declare no conflict of interest.

#### References

1. Novoselov, K.S.; Geim, A.K.; Morozov, S.V.; Jiang, D.; Katsnelson, M.I.; Grigorieva, I.V.; Dubonos, S.V.; Firsov, A.A. Two-Dimensional Gas of Massless Dirac Fermions in Graphene. *Nature* **2005**, *438*, 197–200. [[CrossRef](#)] [[PubMed](#)]
2. Zhang, K.; Zhang, T.; Cheng, G.; Li, T.; Wang, S.; Wei, W.; Zhou, X.; Yu, W.; Sun, Y.; Wang, P.; et al. Interlayer Transition and Infrared Photodetection in Atomically Thin Type-II MoTe<sub>2</sub>/MoS<sub>2</sub> van Der Waals Heterostructures. *ACS Nano* **2016**, *10*, 3852–3858. [[CrossRef](#)]
3. Cao, Y.; Fatemi, V.; Fang, S.; Watanabe, K.; Taniguchi, T.; Kaxiras, E.; Jarillo-Herrero, P. Unconventional Superconductivity in Magic-Angle Graphene Superlattices. *Nature* **2018**, *556*, 43–50. [[CrossRef](#)]
4. Pierucci, D.; Henck, H.; Avila, J.; Balan, A.; Naylor, C.H.; Patriarche, G.; Dappe, Y.J.; Silly, M.G.; Sirotti, F.; Johnson, A.T.C.; et al. Band Alignment and Minigaps in Monolayer MoS<sub>2</sub>-Graphene van Der Waals Heterostructures. *Nano. Lett.* **2016**, *16*, 4054–4061. [[CrossRef](#)]
5. Wang, L.; Shih, E.M.; Ghiotto, A.; Xian, L.; Rhodes, D.A.; Tan, C.; Claassen, M.; Kennes, D.M.; Bai, Y.; Kim, B.; et al. Correlated Electronic Phases in Twisted Bilayer Transition Metal Dichalcogenides. *Nat. Mater.* **2020**, *19*, 861–866. [[CrossRef](#)] [[PubMed](#)]
6. Hesp, N.C.H.; Torre, I.; Rodan-Legrain, D.; Novelli, P.; Cao, Y.; Carr, S.; Fang, S.; Stepanov, P.; Barcons-Ruiz, D.; Herzig-Sheinfux, F.; et al. Collective excitations in twisted bilayer graphene close to the magic angle. *Nat. Phys.* **2019**. [[CrossRef](#)]
7. Rivera, P.; Schaibley, J.R.; Jones, A.M.; Ross, J.S.; Wu, S.; Aivazian, G.; Klement, P.; Seyler, K.; Clark, G.; Ghimire, N.J.; et al. Observation of Long-Lived Interlayer Excitons in Monolayer MoSe<sub>2</sub>-WSe<sub>2</sub> Heterostructures. *Nat. Commun.* **2015**, *6*, 6242. [[CrossRef](#)] [[PubMed](#)]
8. Bradford, J.; Shafiei, M.; MacLeod, J.; Motta, N. Synthesis and characterization of WS<sub>2</sub>/graphene/SiC van der Waals heterostructures via WO<sub>3-x</sub> thin film sulfurization. *Sci. Rep.* **2020**, *10*, 17334. [[CrossRef](#)]

9. Forti, S.; Rossi, A.; Büch, H.; Cavallucci, T.; Bisio, F.; Sala, A.; Menteş, T.O.; Locatelli, A.; Magnozzi, M.; Canepa, M.; et al. Electronic Properties of Single-Layer Tungsten Disulfide on Epitaxial Graphene on Silicon Carbide. *Nanoscale* **2017**, *9*, 16412–16419. [[CrossRef](#)] [[PubMed](#)]
10. Rossi, A.; Spirito, D.; Bianco, F.; Forti, S.; Fabbri, F.; Büch, H.; Tredicucci, A.; Krahne, R.; Coletti, C. Patterned Tungsten Disulfide/Graphene Heterostructures for Efficient Multifunctional Optoelectronic Devices. *Nanoscale* **2018**, *10*, 4332–4338. [[CrossRef](#)]
11. Henck, H.; Pierucci, D.; Chaste, J.; Naylor, C.H.; Avila, J.; Balan, A.; Silly, M.G.; Maria, C.; Sirotti, F.; Johnson, A.T.C.; et al. Electrolytic Phototransistor Based on Graphene-MoS<sub>2</sub> van Der Waals p-n Heterojunction with Tunable Photoresponse p-n Heterojunction with Tunable Photoresponse. *Appl. Phys. Lett.* **2016**, *109*, 113103. [[CrossRef](#)]
12. Ghiasi, T.S.; Kaverzin, A.A.; Blah, P.J.; Van Wees, B.J. Charge-to-Spin Conversion by the Rashba-Edelstein Effect in Two-Dimensional van Der Waals Heterostructures up to Room Temperature. *Nano. Lett.* **2019**, *19*, 5959–5966. [[CrossRef](#)]
13. Avsar, A.; Tan, J.Y.; Taychatanapat, T.; Balakrishnan, J.; Koon, G.K.W.; Yeo, Y.; Lahiri, J.; Carvalho, A.; Rodin, A.S.; O'Farrell, E.C.T.; et al. Spin-Orbit Proximity Effect in Graphene. *Nat. Commun.* **2014**, *5*, 4875. [[CrossRef](#)]
14. Wakamura, T.; Reale, F.; Palczynski, P.; Zhao, M.Q.; Johnson, A.T.C.; Guéron, S.; Mattevi, C.; Ouerghi, A.; Bouchiat, H. Spin-Orbit Interaction Induced in Graphene by Transition Metal Dichalcogenides. *Phys. Rev. B* **2019**, *99*, 245402. [[CrossRef](#)]
15. David, A.; Rakyta, P.; Kormányos, A.; Burkard, G. Induced Spin-Orbit Coupling in Twisted Graphene-Transition Metal Dichalcogenide Heterobilayers: Twistronics Meets Spintronics. *Phys. Rev. B* **2019**, *100*, 85412. [[CrossRef](#)]
16. Li, Y.; Koshino, M. Twist-Angle Dependence of the Proximity Spin-Orbit Coupling in Graphene on Transition-Metal Dichalcogenides. *Phys. Rev. B* **2019**, *99*, 075438. [[CrossRef](#)]
17. Henck, H.; Ben Aziza, Z.; Pierucci, D.; Laourine, F.; Reale, F.; Palczynski, P.; Chaste, J.; Silly, M.G.; Bertran, F.; Le Fèvre, P.; et al. Electronic Band Structure of Two-Dimensional WS<sub>2</sub>/Graphene van Der Waals Heterostructures. *Phys. Rev. B* **2018**, *97*, 155421. [[CrossRef](#)]
18. Nguétchuissi Noubé, U.; Gréboval, C.; Livache, C.; Brulé, T.; Doudin, B.; Ouerghi, A.; Lhuillier, E.; Dayen, J.-F. Ionic Glass-Gated 2D Material-Based Phototransistor: MoSe<sub>2</sub> over LaF<sub>3</sub> as Case Study. *Adv. Funct. Mater.* **2019**, *29*, 1902723. [[CrossRef](#)]
19. Giannozzi, P.; Baroni, S.; Bonini, N.; Calandra, M.; Car, R.; Cavazzoni, C.; Ceresoli, D.; Chiarotti, G.L.; Cococcioni, M.; Dabo, I.; et al. QUANTUM ESPRESSO: A Modular and Open-Source Software Project for Quantum Simulations of Materials. *J. Phys. Condens. Matter* **2009**, *21*, 395502. [[CrossRef](#)] [[PubMed](#)]
20. Heyd, J.; Scuseria, G.E.; Ernzerhof, M. Hybrid Functionals Based on a Screened Coulomb Potential. *J. Chem. Phys.* **2003**, *118*, 8207. [[CrossRef](#)]
21. Zribi, J.; Khalil, L.; Avila, J.; Chaste, J.; Henck, H.; Oehler, F.; Gil, B.; Liu, S.; Edgar, J.H.; Giorgetti, C.; et al. Structural and Electronic Transitions in Few Layers of Isotopically Pure Hexagonal Boron Nitride. *Phys. Rev. B* **2020**, *102*, 115141. [[CrossRef](#)]
22. Zribi, J.; Khalil, L.; Zheng, B.; Avila, J.; Pierucci, D.; Brulé, T.; Chaste, J.; Lhuillier, E.; Asensio, M.C.; Pan, A.; et al. Strong Interlayer Hybridization in the Aligned SnS<sub>2</sub>/WSe<sub>2</sub> Hetero-Bilayer Structure. *Npj 2d Mater. Appl.* **2019**, *3*, 27. [[CrossRef](#)]
23. Kobayashi, Y.; Sasaki, S.; Mori, S.; Hibino, H.; Liu, Z.; Watanabe, K.; Taniguchi, T.; Suenaga, K.; Maniwa, Y.; Miyata, Y. Growth and Optical Properties of High-Quality Monolayer WS<sub>2</sub> on Graphite. *ACS Nano* **2015**, *9*, 4056–4063. [[CrossRef](#)]
24. Gutiérrez, H.R.; Perea-López, N.; Elías, L.A.; Berkdemir, A.; Wang, B.; Terrones, M. Extraordinary Room-Temperature Photoluminescence in Triangular WS<sub>2</sub> Monolayers. *Nano. Lett.* **2013**, *13*, 3447–3454. [[CrossRef](#)]
25. Molina-Sánchez, A.; Wirtz, L. Phonons in Single-Layer and Few-Layer MoS<sub>2</sub> and WS<sub>2</sub>. *Phys. Rev. B* **2011**, *84*, 155413. [[CrossRef](#)]
26. Ernandes, C.; Khalil, L.; Almabrouk, H.; Pierucci, D.; Zheng, B.; Avila, J.; Dudin, P.; Chaste, J.; Oehler, F.; Pala, M.; et al. Indirect to Direct Band Gap Crossover in Two-Dimensional WS<sub>2</sub>(1-x)Se<sub>2x</sub> Alloys. *Npj 2d Mater. Appl.* **2021**, *5*, 1–7. [[CrossRef](#)]
27. Lorchat, E.; López, L.E.P.; Robert, C.; Lagarde, D.; Froehlicher, G.; Taniguchi, T.; Watanabe, K.; Marie, X.; Berciaud, S. Filtering the Photoluminescence Spectra of Atomically Thin Semiconductors with Graphene. *Nat. Nanotechnol.* **2020**, *15*, 283–288. [[CrossRef](#)]
28. Yang, B.; Molina, E.; Kim, J.; Barroso, D.; Lohmann, M.; Liu, Y.; Xu, Y.; Wu, R.; Bartels, L.; Watanabe, K.; et al. Effect of Distance on Photoluminescence Quenching and Proximity-Induced Spin-Orbit Coupling in Graphene/WSe<sub>2</sub> Heterostructures. *Nano. Lett.* **2018**, *18*, 3580–3585. [[CrossRef](#)] [[PubMed](#)]
29. Froehlicher, G.; Lorchat, E.; Berciaud, S. Charge Versus Energy Transfer in Atomically Thin Graphene-Transition Metal Dichalcogenide van Der Waals Heterostructures. *Phys. Rev. X* **2018**, *8*, 011007. [[CrossRef](#)]
30. Pallecchi, E.; Lafont, F.; Cavaliere, V.; Schopfer, F.; Mailly, D.; Poirier, W.; Ouerghi, A. High Electron Mobility in Epitaxial Graphene on 4H-SiC(0001) via Post-Growth Annealing under Hydrogen. *Sci. Rep.* **2014**, *4*, 4558. [[CrossRef](#)] [[PubMed](#)]
31. Pallecchi, E.; Ridene, M.; Kazazis, D.; Mathieu, C.; Schopfer, F.; Poirier, W.; Mailly, D.; Ouerghi, A. Observation of the Quantum Hall Effect in Epitaxial Graphene on SiC(0001) with Oxygen Adsorption. *Appl. Phys. Lett.* **2012**, *100*, 253109. [[CrossRef](#)]
32. Ohta, T.; Bostwick, A.; Seyller, T.; Horn, K.; Rotenberg, E. Controlling the Electronic Structure of Bilayer Graphene. *Science* **2006**, *313*, 951–954. [[CrossRef](#)] [[PubMed](#)]
33. Ristein, J.; Mammadov, S.; Seyller, T. Origin of Doping in Quasi-Free-Standing Graphene on Silicon Carbide. *Phys. Rev. Lett.* **2012**, *108*, 246104. [[CrossRef](#)]
34. Kopylov, S.; Tzalenchuk, A.; Kubatkin, S.; Fal'Ko, V.I. Charge Transfer between Epitaxial Graphene and Silicon Carbide. *Appl. Phys. Lett.* **2010**, *97*, 11–14. [[CrossRef](#)]

35. Dendzik, M.; Michiardi, M.; Sanders, C.; Bianchi, M.; Miwa, J.A.; Grønberg, S.S.; Lauritsen, J.V.; Bruix, A.; Hammer, B.; Hofmann, P. Growth and Electronic Structure of Epitaxial Single-Layer WS<sub>2</sub> on Au(111). *Phys. Rev. B Condens. Matter Mater. Phys.* **2015**, *92*, 245442. [[CrossRef](#)]
36. Amin, B.; Kaloni, T.P.; Schwingenschlögl, U. Strain Engineering of WS<sub>2</sub>, WSe<sub>2</sub>, and WTe<sub>2</sub>. *RSC Adv.* **2014**, *4*, 34561–34565. [[CrossRef](#)]
37. Ben Aziza, Z.; Henck, H.; Di Felice, D.; Pierucci, D.; Chaste, J.; Naylor, C.H.; Balan, A.; Dappe, Y.J.; Johnson, A.T.C.; Ouerghi, A. Bandgap Inhomogeneity of MoS<sub>2</sub> monolayer on Epitaxial Graphene Bilayer in van Der Waals p-n Junction. *Carbon N. Y.* **2016**, *110*, 396–403. [[CrossRef](#)]
38. Nakamura, H.; Mohammed, A.; Rosenzweig, P.; Matsuda, K.; Nowakowski, K.; Küster, K.; Wochner, P.; Ibrahimkuty, S.; Wedig, U.; Hussain, H.; et al. Spin Splitting and Strain in Epitaxial Monolayer WSe<sub>2</sub> on Graphene. *Phys. Rev. B* **2020**, *101*, 165103. [[CrossRef](#)]