



HAL
open science

Effect of alkali cations on the photomagnetic behavior of CoFe Prussian blue analogue nanoparticles embedded in ordered mesoporous silica

Laura Altenschmidt, Giulia Fornasieri, Eric Rivière, François Brisset,
Romuald Saint-Martin, Anne Bleuzen

► To cite this version:

Laura Altenschmidt, Giulia Fornasieri, Eric Rivière, François Brisset, Romuald Saint-Martin, et al.. Effect of alkali cations on the photomagnetic behavior of CoFe Prussian blue analogue nanoparticles embedded in ordered mesoporous silica. *Comptes Rendus. Chimie*, 2019, 22, pp.508 - 515. 10.1016/j.crci.2019.06.003 . hal-03488010

HAL Id: hal-03488010

<https://hal.science/hal-03488010>

Submitted on 20 Jul 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial 4.0 International License

Effect of the alkali-cation on the photomagnetic behavior of CoFe Prussian blue analogue nanoparticles embedded in ordered mesoporous silica

Laura Altenschmidt*, Giulia Fornasieri, Eric Rivière, François Brisset, Romuald Saint-Martin, Anne Bleuzen*

Institut de Chimie Moléculaire et des Matériaux d'Orsay, CNRS, Université Paris-Sud, Université Paris-Saclay, 91400 Orsay, France

Corresponding authors: laura.altenschmidt@u-psud.fr, anne.bleuzen@u-psud.fr

Abstract

The size of CoFe Prussian blue analogue nanoparticles containing either rubidium or cesium cations was controlled by their formation through a nucleation process inside the calibrated pores of an ordered mesoporous silica matrix. The corresponding references were synthesized in powder form using the same ratio between the metal species in the reaction solution. The obtained samples were characterized via IR-spectroscopy, X-ray diffraction and magnetometry to understand the differences arising from the size reduction and the nature of the inserted alkali cation. We were able to show that the nature of the cation has a significant influence on the photoswitching properties at the macroscale in the powders. However, on the nanoscale the influence of the surface contribution becomes more prominent and cooperative effects disappear, resulting in a new role of the alkali cation in the photomagnetic properties.

Keywords: Prussian blue analogues, Nanoparticles, Ordered Mesoporous Silica, Photomagnetism

1. Introduction

Prussian blue analogues (PBA) build a large family of compounds showing various properties (electrochemical [1, 2], adsorption [3]...), among them magnetic switching. Thus, by applying an external stimulus, such as light [4-6], temperature [7, 8] or pressure [9] on these compounds, it is possible to induce a charge transfer process in between the bimetallic pair which is accompanied by a change in the magnetic properties. Especially the CoFe PBA have been of particular interest in the past years [10-13]. During irradiation at low temperatures, the diamagnetic $\text{Co}^{\text{III}}(\text{LS})\text{-Fe}^{\text{II}}$ pairs are excited into a paramagnetic $\text{Co}^{\text{II}}(\text{HS})\text{-Fe}^{\text{III}}$ state and return to the initial state when the temperature is increased. This bistable behavior is of interest for the development of future applications, such as information storage devices [14, 15].

Several studies aiming at understanding the origin of the switching properties in photomagnetic CoFe PBA powders and showing the general dependencies of these properties have shown the crucial role of interstitial alkali cations [12, 16-19]. The introduction of alkali cations such as Rb^+ or Cs^+ into the structure is accompanied by an increase of nitrogen atoms around the cobalt causing a decrease of the Co redox potential, which triggers a charge transfer and the generation of the photoswitchable diamagnetic $\text{Co}^{\text{III}}(\text{LS})\text{-Fe}^{\text{II}}$ pairs [20]. Moreover, not only the amount of diamagnetic pairs is crucial for the photomagnetic effect but also the amount of $[\text{Fe}(\text{CN})_6]$ vacancies since the network needs to retain a certain degree of flexibility to adapt to the structural changes ($\text{Co}^{\text{II}}(\text{HS})$ to ligand bond distance is longer) during the irradiation induced charge transfer. The more alkali cations are introduced in the interstitial sites, the more rigid the network becomes. It could also be shown that the photomagnetism not only depends on the amount but also on the nature of alkali cation used [16, 20].

Further, for the elaboration of high-density storage devices, the reduction of the particle size and the control of the resulting properties is a necessary step. Our approach is the use of ordered mesoporous silica monolith with 2D hexagonal organization of the pores for the control of the different parameters (size, surrounding, chemical composition...) of the nanoparticles within the calibrated pores. The diameter of the pores, determined via transmission electron microscopy (TEM) as well as by nitrogen physisorption [21], can slightly vary from one synthesis to the other over the 5–6 nm range. A representative image of the hexagonal organization of the porous system and the filling of the pores with the monocrystalline PBA nanoparticles is shown in figures S1 and S2.

Pajerowski *et al.* [22] reported a dependence of the photomagnetic response of RbCoFe PBA nanoparticles depending on the particle size, showing that the efficiency of the photomagnetic effect decreases with particle size reduction. Our group has also previously studied the behavior of $\text{Rb}_2\text{Co}_4[\text{Fe}(\text{CN})_6]_{3.3}$ nanoparticles embedded in mesoporous silica to understand the effect of the size reduction and the environment on the switching properties [23, 24]. In comparison with the powder of the same chemical composition the mechanism behind the photomagnetic effect is the same at the scale of the bimetallic CoFe pair. However, the surface plays a peculiar role in the magnetic behavior due to its structure and composition.

It could be shown that the nanoparticles inside the silica matrix form a (Co^{III}-Fe^{II})-core-(Co^{II}-Fe^{III})-shell structure being responsible for the observed photomagnetic behavior.

In this work, we show that, it is possible to selectively vary the chemical nature of the alkali cations inserted in interstitial sites of CoFe nanocrystals while keeping the other parameters (size, surrounding) constant. We use the preparation method of nanocomposites which has been developed in our group in which ordered mesoporous silica monoliths with a 2D hexagonal organization of calibrated cylindrical pores contain PBA nanoparticles. This enables us to compare the RbCoFe and CsCoFe PBA which have been synthesized in the same conditions on the macro- and nanoscale and discuss the effect of the synthesis conditions and the size reduction on the different systems and their photomagnetic properties.

2. Material and methods

2.1 Nanoreactor synthesis: The synthesis of the monoliths has already been described elsewhere [25]. In a typical procedure, a solution was prepared by dissolving the copolymer P123 (2.4 g) in the silica precursor TMOS solution (4 g) in a 30 mL polypropylene vial while stirring at 50 °C. An aqueous cobalt(II) nitrate acidic solution (80 mg, pH 1.4, 2 mL) was quickly added to the cooled solution. The mixture was stirred for 2 min 30 sec and then divided into four vials, which were sealed and aged for 1h in a 23 °C water bath. Finally, the vials were opened and left aging at 23 °C for 1 week to give homogeneous pink silica monoliths containing P123 and Co²⁺ ions. Finally, the P123 copolymer was removed by calcination at 500 °C in air being accompanied by a color change to blue due to a change of the coordination sphere around the Co²⁺ ion.

2.2 Photomagnetic Nanocomposites: For the preparation of the photomagnetic nanocomposites either Rb⁺ or Cs⁺ were used as insertion cations. For all samples, a molar ratio of 2:1:2 for Rb/Cs:Co:Fe in the reaction solution was used. In the following these samples are called **nanoRbCoFe** and **nanoCsCoFe**.

During a typical synthesis, the blue calcined monolith was immersed in heptane. Then, a volume corresponding to 80% of the porous volume of a previously prepared acidified (80µl HNO₃ per 1 mL) solution containing Rb⁺ or Cs⁺ ions and [Fe(CN)₆]³⁻ complexes was added. The color change of the monolith from blue to dark purple is immediate, indicating the formation of the Prussian blue analogue. After 15 minutes the heptane is removed and the monolith is washed on average 5 times with distilled water until no coloration of the washing solution could be observed. Finally, the obtained nanocomposites are dried in air.

2.3 Photomagnetic References: As references, the corresponding bulk photomagnetic materials with a molar ratio of Rb/Cs:Co:Fe of 2:1:2 in the reaction solution (as in the case of the nanocomposites) have been synthesized following the protocol in reference [16] with minor changes. In a typical synthesis, 400 mL of a 2.5 mmol/L cobalt(II)nitrate solution was added to 100 mL of a 20 mmol/L solution of hexacyanoferrate(III) and 20 mmol/L of either RbNO₃ for **RbCoFe** or CsNO₃ for **CsCoFe**. Both solutions were acidified with 3 drops of HNO₃

(68%) each and the total addition time was 1 hour. The obtained purple precipitate was centrifuged 3 times, washed with distilled water and finally dried in air.

2.4 Instrumentation

Elemental analysis for the reference powders concerning the heavier elements (Rb, Cs, Fe and Co) was done by energy dispersive spectroscopy (EDS) using a Zeiss Sigma HD scanning electron microscope fitted with a SAMx Idfix EDS microanalysis system. The composition of the nanocomposites and the quantity of H, C and N was determined via standard microanalytical methods.

Infrared spectroscopy was performed in the range of 4000 cm^{-1} to 900 cm^{-1} on a Perkin Elmer Spectrum 100 in transmission mode with a resolution of 4 cm^{-1} . The compounds were mixed with nujol to obtain a suspension which was placed in between CaF_2 windows.

Powder X-ray diffraction ($\text{Cu-K}\alpha$) was done on a Philips X'Pert Diffractometer in the $10\text{--}80\ 2\theta$ range with a step size of 0.01 in the case of the powders and 0.033 for the nanocomposites.

Photomagnetic measurements were performed using a SQUID Quantum Design XL7 magnetometer. The ground samples (ca. 10 mg) were mixed with nujol, spread on cardboard and fixed in between two straws. For the references, the powder was diluted in silica to obtain the same Si/Co ratio as in the nanocomposites. These prepared samples were irradiated at 10 K inside the magnetometer with the help of a laser diode (635 nm , 50 mW/cm^2) until reaching the photostationary state. Afterwards, the magnetization value was measured while heating to 200 K with a sweeping rate of 2 K/min, followed by a measurement during the cooling process back to 10 K. The temperature dependence was determined in the $10\text{--}200\text{ K}$ range with a sweeping rate of 2 K/min before irradiation. For all the measurements, a field of 5000 Oe was applied.

3. Results and Discussion

3.1 Elemental analysis. The experimental results of the elemental analyses and therefrom proposed chemical formulas taking into account the presence of well-defined entities and the electroneutrality of the solid are gathered in table 1 for the powdered reference compounds and in table 2 for the nanocomposites.

Table 1: Chemical composition of the reference powders.

		Rb	Cs	Co	Fe	C	H	N
RbCoFe	<i>Exp.</i>	10.33	-	19.46	14.26	17.73	1.96	20.57
	<i>Calc.</i>	9.12	-	19.32	14.19	18.31	1.99	21.36
Rb_{1.3}Co₄[Fe(CN)₆]_{3.1} · 12 H₂O								
CsCoFe	<i>Exp.</i>	-	27.40	14.57	12.13	16.49	1.13	19.23
	<i>Calc.</i>	-	25.84	14.79	12.96	16.72	1.14	19.5
Cs_{3.1}Co₄[Fe(CN)₆]_{3.7} · 9 H₂O								

Table 2: Chemical composition of the nanocomposites.

		Rb	Cs	Co	Fe	C	H	N	Si
nanoRbCoFe	<i>Exp.</i>	0.52	-	0.76	0.56	0.88	1.56	0.88	37.74
	<i>Calc.</i>	0.53	-	0.77	0.60	0.78	1.59	0.91	38.43
Rb_{1.9}Co₄[Fe(CN)₆]_{3.3} @(SiO₂)₄₁₇(H₂O)₂₄₀									
nanoCsCoFe	<i>Exp.</i>	-	1.89	0.75	0.57	0.89	1.54	0.90	37.59
	<i>Calc.</i>	-	1.70	0.75	0.72	0.92	1.55	1.08	37.86
Cs₄Co₄[Fe(CN)₆]₄ @(SiO₂)₄₂₁(H₂O)₂₄₀									

Even though the synthesis conditions are the same for both reference samples, it can be seen that the Cs⁺ ion enters in a higher amount into the PBA lattice. This behavior could already be observed in previous studies of powdered compounds [16] and can also be seen in the nanocomposites. However, since the PBA nanoparticles are highly diluted in a silica matrix the determination of the exact chemical composition is hindered and a large error range is assumed. From the elemental analysis we propose the formula Rb_xCo₄[Fe(CN)₆]_{8+x/3} with x = 1.9±0.5 for **nanoRbCoFe** and Cs_xCo₄[Fe(CN)₆]_{8+x/3} with x = 4±0.5 for **nanoCsCoFe**. In comparison to the corresponding reference powders, the amount of inserted alkali cation is slightly increased in the nanocomposites, which can be explained by the confinement effects of the silica matrix and/or higher concentration of the PBA precursors in the reaction medium.

3.2 Infrared spectroscopy. The IR spectra of **nanoRbCoFe** and **nanoCsCoFe** are compared to those of the corresponding reference powder compounds over the 2200 to 2050 cm⁻¹ range

(CN stretching vibration) in Fig.1a for the Rb system and in Fig.1b for the Cs one. In the references only one main band at 2125 cm^{-1} corresponding to the $\text{Co}^{\text{III}}\text{-NC-Fe}^{\text{II}}$ linkages can be seen regardless of the inserted alkali cation in agreement with previous studies. In excess of Rb^+ or Cs^+ ions, the amount of alkali cation inserted in the structure is enough to induce a total $\text{Co}^{\text{II}}\text{Fe}^{\text{III}}$ to $\text{Co}^{\text{III}}\text{Fe}^{\text{II}}$ electron transfer during the synthesis [16].

The nanocomposites also exhibit one main band but it differs from the one in the powdered compounds and also from one alkali cation to the other. In the Rb^+ ions containing sample (Fig. 1a), the main band at 2137 cm^{-1} has been assigned to cyanide ions in $\text{Co}^{\text{III}}\text{-NC-Fe}^{\text{II}}$ linkages [24]. The slight shift of the band toward higher energies in the nanocomposites with regard to the powdered compound has already been observed in alkali cation free CoFe and NiFe PBA nanoparticles contained in a comparable silica matrix and has been explained by confinement and/or size effects [25]. In the Cs^+ ions containing nanocomposite (Fig. 1b), the main band is situated at 2125 cm^{-1} but it is significantly broader than the one observed on the spectrum of the powdered compound. The position of the band indicates the presence of CN ions in $\text{Co}^{\text{III}}\text{-NC-Fe}^{\text{II}}$ linkages as in the powdered compounds and in the Rb nanocomposite. This shows that the nanoparticles contain Cs^+ ions and the $\text{Co}^{\text{II}}\text{Fe}^{\text{III}}$ to $\text{Co}^{\text{III}}\text{Fe}^{\text{II}}$ electron transfer occurred during their formation. Nevertheless, the broadness of the band indicates that the nanoparticles are made up of CN oscillators in a wider range of environments than in the powders and in the Rb^+ containing nanoparticles. From these observations we can conclude that, in contrast to the powdered compounds prepared in comparable conditions, the Co-NC-Fe linkages in the nanoparticles significantly dependent on the inserted alkali cation. This can be explained by different interactions between the bimetallic cyanide network and the alkali cation possibly in relation with the size of the latter combined with weaker structural cooperative effects within the bimetallic cyanide network in the nanoparticles, making the structure more sensitive to these interactions.

Fig. 1. IR-spectra of a) Rb-containing samples and b) Cs-containing samples.

3.3 X-ray diffraction. The diffraction patterns of the nanocomposites and corresponding reference powders are shown in Fig. 2. Around 24° a broad peak can be seen on the diffraction pattern of the nanocomposites, which is caused by the amorphous silica matrix in which the nanoparticles are embedded. Further, the diffraction pattern of the nanocomposites exhibit diffraction lines which are less intense and broader due to the dilution inside the silica and the reduced particle size. Nevertheless, it can be seen that those peaks all well agree with the obtained diffraction lines of the reference powders. Therefore, it can be concluded that in all cases the face-centered cubic PBA structure was formed.

With the Scherrer formula an average particle size of $6.2\pm 0.5\text{ nm}$ for **nanoRbCoFe** and of $5.1\pm 0.4\text{ nm}$ for **nanoCsCoFe** was approximated. Due to the strong broadening and the weak

intensity of the diffraction peaks resulting from the dilution and small size of the particles, the error on the particle size is non negligible. It should be noted that the calculated size typically refers only to the crystallite size of the particles which in this case is similar to the particle size due to the monocrystallinity of the PBA nanoparticles. In comparison, these values are very close to those of the diameter of the cylindrical pores of the silica monoliths and therefore are in agreement with the formation of spherical nanocrystals having a size which is determined by the shortest dimension of the nanoreactors (i.e. the diameter of the pores) [26]. The slight difference in the particle size can be explained by a possible slight variation of the pore diameter from one monolith to another.

From the (200), (220) and (400) diffraction lines, the lattice parameters a were calculated. For the Rb-containing samples a value of $a = 9.96 \pm 0.01 \text{ \AA}$ for **RbCoFe** and $a = 9.96 \pm 0.1 \text{ \AA}$ **nanoRbCoFe** was found. The values of the lattice parameter of the Rb nanoparticles inside the silica and the precipitated Rb powder are very close. It can be concluded, that the lattice parameter of the PBA structure is governed by the length of the $\text{Co}^{\text{III}}\text{-NC-Fe}^{\text{II}}$ linkages with a minor effect of the particle size on it. It is known that if the crystal is composed of $\text{Co}^{\text{III}}\text{-(LS)}$ ions, the lattice parameter is typically around 9.96 \AA and in the case of $\text{Co}^{\text{II}}\text{-(HS)}$ ions the bonds are longer and the lattice parameter is about 10.30 \AA [20].

It has to be noticed here that in a previous study [24] we showed that Rb_2CoFe PBA nanoparticles confined in the pores of similar ordered mesoporous silica monoliths consist of a $\text{Co}^{\text{III}}\text{-Fe}^{\text{II}}$ core with a structure comparable to that of the bigger powder particles and a $\text{Co}^{\text{II}}\text{-Fe}^{\text{III}}$ surface. These $\text{Co}^{\text{II}}\text{Fe}^{\text{III}}$ surface species are not detected by X-ray diffraction. Due to much stronger intensity of CN stretching vibration when linked to Fe^{II} rather than to Fe^{III} ions, the identification of a contribution of $\text{Co}^{\text{II}}\text{Fe}^{\text{III}}$ surface species on the IR spectra of nanoparticles mainly made of $\text{Co}^{\text{III}}\text{Fe}^{\text{II}}$ species is not evident either.

In contrast, for the Cs samples this good agreement in between the lattice parameter value of the powdered reference compound and the nanoparticles is not observed. In Fig. 2b, it can already be seen that the peaks in the nanocomposite are shifted towards lower 2θ values. For **CsCoFe** $a = 9.97 \pm 0.01 \text{ \AA}$ was calculated which is similar to the powdered rubidium reference. In the powdered samples containing a sufficient amount of Rb^+ or Cs^+ ions, the lattice parameter of the PBA structure is governed by the length of the predominant $\text{Co}^{\text{III}}\text{-NC-Fe}^{\text{II}}$ linkages. The structure of the PBA seems to result from long-range order of the $\text{Co}^{\text{III}}\text{-NC-Fe}^{\text{II}}$ linkages with a minor effect of the interactions of the inserted alkali cation with the surrounding lattice.

For the determination of the lattice parameter in **nanoCsCoFe** only the (220) and (400) diffraction lines could be used since the (200) cannot be seen due to the low intensity. This is in agreement with a study by Escax *et al.* [18] who showed that the ratio between the (200) and (220) diffraction line decreases with increasing amount of Cs^+ in the structure. In the diffraction pattern of **nanoCsCoFe**, the (200) line is not visible and the (220) line shows a high

intensity, which is in good agreement with the results of the elemental analysis (section 3.1) that a high quantity of cesium entered the lattice structure.

Concerning the lattice parameter of the Cs-nanoparticles, a value of $a = 10.12 \pm 0.1 \text{ \AA}$ was found, which is different from the one of the Cs powdered compound and also from the one of the PBA nanoparticles in the Rb nanocomposite. This value is significantly higher than that expected for a structure governed by the length of predominant $\text{Co}^{\text{III}}\text{-NC-Fe}^{\text{II}}$ linkages. Since both Rb and Cs containing nanoparticles have on average the same size due to the confinement from the surrounding silica matrix and several monoliths containing RbCoFe PBA nanoparticles always exhibit a shorter lattice parameter [24], it can be concluded that the differences are not caused by the particle size only. The nature of the alkali cation also plays a role in its lengthening. We can propose two possible explanations for this lengthening: i) the diffracting domain of the Cs-containing nanoparticles is formed of a mixture of $\text{Co}^{\text{III}}\text{-NC-Fe}^{\text{II}}$ and $\text{Co}^{\text{II}}\text{-NC-Fe}^{\text{III}}$ linkages, ii) interactions with the bigger Cs^+ alkali cations slightly distort the structure made of $\text{Co}^{\text{III}}\text{Fe}^{\text{II}}$ linkages, which is not the case in bigger particles due to collective structural effects. These two propositions are in line with the IR study (section 3.2). The large band centered around 2124 cm^{-1} reveals the existence of a large range of CN vibrators, which can be explained by competitive interactions between the CN bridges and the transition metal ions on the one hand and the CN bridges and alkali cations on the other hand and/or the presence of a mixture of $\text{Co}^{\text{III}}\text{-NC-Fe}^{\text{II}}$ and $\text{Co}^{\text{II}}\text{-NC-Fe}^{\text{III}}$ linkages in the bimetallic cyanide network. Work is in progress in order to clarify the electronic structure of the transition metal ions.

Even though the samples were all synthesized with an equal molar ratio in the initial solutions, only the Rb-samples seem to show a similar crystal structure on the macro- and nanoscale. The Cs-samples showed significant differences. Therefore, we can conclude that the lattice on the nanoscale depends not only on the amount of the inserted alkali cation and the accompanied charge transfer leading to the formation of $\text{Co}^{\text{III}}\text{-(LS)}$ ions but also on the nature of the cation.

Fig 2. XRD pattern of a) Rb-containing samples and b) Cs containing samples. The peaks corresponding to the aluminum support in the nanocomposites (grey lines) are marked by an asterisk (*).

3.4 Magnetic measurements. The temperature dependence of the magnetization has been recorded over the 10–200 K temperature range for all samples before and after irradiation. In figure S3, the magnetization curves for the pure **RbCoFe** powder for two different irradiation times ($\lambda = 635 \text{ nm}$, $P = 50 \text{ W}\cdot\text{cm}^{-2}$) are shown.

When the sample is irradiated until the magnetization curve reaches a plateau (photostationary state), the expected magnetic behavior for the excited state of the CoFe PBA

containing Rb^+ ions in sufficient amount can be observed with a Curie temperature at 21 K and a thermally activated relaxation of the excited state over the 100–150 K temperature range. The temperature range corresponding to the thermal relaxation of the photo-excited state can be decomposed into two areas: the 100–115 K temperature range corresponding to a rather sharp drop of the magnetization followed by a very progressive return of some residual excited species to the ground state over the 115–150 K temperature range. This behavior is due to a complete photo-induced $\text{Co}^{\text{III}}(\text{LS})\text{Fe}^{\text{II}} \rightarrow \text{Co}^{\text{II}}(\text{HS})\text{Fe}^{\text{III}}$ electron transfer in the irradiated part of the sample. It can be noticed that a sigmoidal shape of the time-dependent relaxation magnetization curves due to cooperative effects was already observed by Goujon *et al.* [27] in a comparable compound. But when the irradiation is stopped prior to reaching the photostationary state (Fig. S3b), a partially excited system is obtained. Regardless of the degree of conversion, the systems fully return to the ground state over the same temperature range with the same two steps. The slowness of the photo-excitation can be explained by the dark color of the powder, which strongly absorbs in the visible range, thereby leading to a partial excitation of the sample.

Wanting to avoid the strong self-absorbance of the pure powder, the **RbCoFe** powder was diluted in pure silica in the same PBA/silica ratio as in the nanocomposites. The obtained magnetization curves are shown in Fig. 3a. When the powdered sample is diluted in silica, several observations can be made: i) the phototransformation occurs faster than in the pure powder and ii) when the laser is cut prior to the completed excitation no difference in the relaxation can be found except a lower total reached magnetization due to the incomplete transformation. This behavior can be explained by the dilution effect of the silica. The radiation is rather scattered and readily diffused towards all the PBA particles within the matrix than getting absorbed by a compact stacking of PBA particles as it was the case in the pure sample. Regarding the trend of the relaxation (Fig. S4), as was the case for the fully-transformed non-diluted powder, three areas can be identified: i) the change in magnetic ordering at 21 K from ferrimagnetic ordered to disordered, ii) the sharp drop of the magnetization over the $90\text{--}115\pm 2$ K temperature range [27] and iii) a very progressive relaxation of residual pairs from 115 to 150 ± 2 K.

Figure S5 shows the increase of the magnetization over time during irradiation of the diluted powder references. Consistent with the previous discussion, the magnetization in the diluted **RbCoFe** powder increases drastically after the beginning of irradiation revealing a fast charge transfer from iron to cobalt. In contrast, the diluted **CsCoFe** sample only shows a slow and overall small increase of the magnetization. The photomagnetic effect in **CsCoFe** is significantly decreased. The relaxation of the excited CsCoFe system is very progressive (Fig. S6) and also occurs at a lower temperature than in the Rb powder at 135 ± 2 K. This and the reduced photomagnetic effect can be explained by the presence of three cesium ions at the interstitial sites of the cubic lattice causing the lattice to become more rigid due to the reduced amount of $\text{Fe}(\text{CN})_6$ vacancies and/or more strained due to stronger interactions between the bimetallic cyanide network and alkali cations. Thereby the charge transfer accompanied by an increase of the lattice parameter is hindered and more total energy is needed. Such a reduction of the efficiency of the photomagnetic effect in powdered

compounds was already evidenced upon replacing Rb^+ by Cs^+ in a two alkali cations per unit cell-containing powder [20] and up to its disappearance in the derivative containing four Cs^+ cations per cell [16].

Fig. 3. Magnetization curves of a) **RbCoFe** and b) **CsCoFe** diluted in silica before (grey) and after (black) irradiation.

The magnetization curves of the nanocomposites before and after irradiation are shown in Fig. 4. The absolute values of the magnetization will not be discussed because the exact amount of nanoparticles in the fraction of sample used for the measurements is not exactly known. Both nanocomposite samples show an increase in the magnetization value during irradiation and therefore the photomagnetic effect is preserved at the nanoscale. The increase of the magnetization over time during irradiation is shown in Fig. S7. No significant difference between the two nanocomposites can be observed. After completed irradiation, the excited $\text{Co}^{\text{II}}(\text{HS})\text{Fe}^{\text{III}}$ pairs relax back into the $\text{Co}^{\text{III}}(\text{LS})\text{Fe}^{\text{II}}$ ground state when the temperature is increased. The relaxation temperature is defined as the temperature at which the two curves, before and after irradiation, intersect. For **nanorRbCoFe** the difference of the magnetization after and before irradiation returns to zero at 130 ± 2 K and for **nanorCsCoFe** at 127 ± 2 K. The relaxation of the photo-excited pairs is rather progressive and no significant difference can be seen in between the two nanocomposites (Fig. S8). This can be explained by the reduced size of the PBA nanoparticles, which are not large enough for the development of cooperative effects and for which surface effects predominate. Work is in progress to prepare silica matrices with various sizes of the pores, in which PBA nanoparticles with various sizes could be formed.

Fig. 4. Magnetization curves for a) **nanorRbCoFe** and b) **nanorCsCoFe** before (grey line) and after (black line) irradiation.

Since the observed photomagnetic behavior is rather similar in both nanocomposites even though the XRD and IR data showed differences, the temperature dependence of XT in the range of 10–300 K for both nanocomposites has been measured (Fig. S9). A similar trend for the cesium nanocomposite and the rubidium one can be seen and therefore a possible thermal-activated charge transfer can be excluded. This observation has also been evidenced by Cafun *et al.* [20] in PBA powders. The differences in the electronic structure observed in the ground states of the nanocomposites seem not to have a significant impact on the photomagnetic effect.

Surprisingly, the shape of the magnetization curves and therefore the photomagnetic effect is very similar regardless of the inserted alkali cation even though the structural characterizations (XRD, IR) showed significant differences in the ground state of the nanoparticles. This is all the more surprising that the photomagnetic effect of the two corresponding powders significantly depends on the nature of the inserted alkali cations. On the nanoscale, new effects and interactions between the alkali cation and the bimetallic cyanide network as well as the contribution of different surface species prevail, resulting in a different behavior than at the macroscale. A better knowledge of the effects of size reduction on cooperative effects would certainly help understand the behavior of these photomagnetic nanoparticles. Further studies are in progress to better understand these effects.

4. Conclusion

We were able to synthesize CoFe PBA nanoparticles containing alkali cations of different natures in the pores of mesoporous silica monoliths exhibiting a 2D hexagonal organization of the pores. As all other parameters were kept the same (size, crystallinity, surrounding), this enabled us to study the effect of a change of alkali cation in interstitial sites on the photomagnetic properties of the nanoparticles. Their properties were also compared to those of powders precipitated in aqueous solutions in the presence of same ratio of reactants.

The study shows that for both rubidium and cesium cations the nanoparticles exhibit a photomagnetic effect. Even though a sizable effect of the nature of the inserted alkali cation in powders on the photomagnetic effect has been reported in literature [20] and could also be observed in the here prepared rubidium and cesium references, we show that on the nanoscale the role of the inserted alkali cation is different. Whereas the big cesium cation hinders the photomagnetic effect when contained above a certain threshold in powders, such an effect does not persist at the nanoscale where cooperative and collective effects are reduced and surface contribution increases. Further studies of this behavior are needed to fully understand the interactions and contributions of the alkali cation on the nanoscale.

Appendix A: Supplementary Data

Supplementary information (Figures S1–S9)

Acknowledgments

This research was carried out with the support of the University Paris-Sud and the CNRS.

Conflict of Interest

The authors declare no conflict of interest.

References

- [1] M. Pyrasch, A. Toutianoush, W. Jin, J. Schnepf, B. Tieke, *Chem. Mater.* 15 (2003) 245-254.
- [2] X. Bie, K. Kubota, T. Hosaka, K. Chihara, S. Komaba, *J. Power Sources* 378 (2018) 322-330.
- [3] S. Natesakhawat, J. T. Culp, C. Matranga, B. Bockrath, *J. Phys. Chem. C* 111 (2007) 1055-1060.
- [4] P. Gütlich, Y. Garcia, T. Woike, *Coord. Chem. Rev.* 219-221 (2001) 839-879.
- [5] S.-I. Ohkoshi, H. Tokoro, *Acc. Chem. Res.* 45 (2012) 1749-1758.
- [6] H. Tokoro, T. Matsuda, T. Nuida, Y. Moritomo, K. Ohoyama, E. D. L. Dangui, K. Boukheddaden, S.-I. Ohkoshi, *Chem. Mater.* 20 (2008) 423-428.
- [7] S.-I. Ohkoshi, T. Matsuda, H. Tokoro, K. Hashimoto, *Chem. Mater.* 17 (2005) 81-84.
- [8] A. Bleuzen, V. Escax, A. Ferrier, F. Villain, M. Verdagner, P. Münsch, J.-P. Itie, *Angew. Chem. Int. Ed.* 43 (2004) 3728-3731.
- [9] V. Ksenofontov, G. Levchenko, S. Reiman, P. Gütlich, A. Bleuzen, V. Escax, M. Verdagner, *Phys. Rev. B* 68 (2003) 024415.
- [10] D. Aguilà, Y. Prado, E. S. Koumoussi, C. Mathonière, R. Clérac, *Chem. Soc. Rev.* 45 (2016) 203-224.
- [11] V. Escax, G. Champion, M.-A. Arrio, M. Zacchigna, C. Cartier Dit Moulin, A. Bleuzen, *Angew. Chem. Int. Ed.* 44 (2005) 4798-4801.
- [12] N. Shimamoto, S.-I. Ohkoshi, O. Sato, K. Hashimoto, *Inorg. Chem.* 41 (2002) 678-684.
- [13] J. Lejeune, J.-D. Cafun, G. Fornasieri, J.-B. Brubach, G. Creff, P. Roy, A. Bleuzen, *Eur. J. Inorg. Chem* 2012 (2012) 3980-3983.
- [14] A. Goujon, F. Varret, V. Escax, A. Bleuzen, M. Verdagner, *Polyhedron* 20 (2001) 1339-1345.
- [15] D. Li, R. Clérac, O. Roubeau, E. Harté, C. Mathonière, R. Le Bris, S. M. Holmes, *J. Am. Chem. Soc.* 130 (2008) 252-258.
- [16] A. Bleuzen, C. Lomenech, V. Escax, F. Villain, F. Varret, C. Cartier Dit Moulin, M. Verdagner, *J. Am. Chem. Soc.* 122 (2000) 6648-6652.
- [17] G. Champion, V. Escax, C. Cartier Dit Moulin, A. Bleuzen, F. Villain, F. Baudalet, E. Dartyge, M. Verdagner, *J. Am. Chem. Soc.* 123 (2001) 12544-12546.
- [18] V. Escax, A. Bleuzen, C. Cartier Dit Moulin, F. Villain, A. Goujon, F. Varret, M. Verdagner, *J. Am. Chem. Soc.* 123 (2001) 12536-12543.
- [19] C. Cartier Dit Moulin, F. Villain, A. Bleuzen, M.-A. Arrio, P. Saintavit, C. Lomenech, V. Escax, F. Baudalet, E. Dartyge, J.-J. Gallet, M. Verdagner, *J. Am. Chem. Soc.* 122 (2000) 6653-6658.
- [20] J.-D. Cafun, G. Champion, M.-A. Arrio, C. Cartier Dit Moulin, A. Bleuzen, *J. Am. Chem. Soc.* 132 (2010) 11552-11559.
- [21] P. Durand, G. Fornasieri, C. Baumier, P. Beaunier, D. Durand, E. Rivière, A. Bleuzen, *J. Mater. Chem.* 20 (2010) 9348-9354.
- [22] D. M. Pajerowski, F. A. Frye, D. R. Talham, M. W. Meisel, *New J. Phys.* 9 (2007) 222.
- [23] R. Moulin, E. Delahaye, A. Bordage, E. Fonda, J.-P. Baltaze, P. Beaunier, E. Rivière, G. Fornasieri, A. Bleuzen, *Eur. J. Inorg. Chem* 2017 (2017) 1303-1313.
- [24] A. Bordage, R. Moulin, E. Fonda, G. Fornasieri, E. Rivière, A. Bleuzen, *J. Am. Chem. Soc.* 140 (2018) 10332-10343.
- [25] E. Delahaye, R. Moulin, M. Aouadi, V. Trannoy, P. Beaunier, G. Fornasieri, A. Bleuzen, *Chem. Eur. J.* 21 (2015) 16906-16916.
- [26] G. Fornasieri, M. Aouadi, P. Durand, P. Beaunier, E. Rivière, A. Bleuzen, *Chem. Commun.* 46 (2010) 8061-8063.
- [27] A. Goujon, O. Roubeau, F. Varret, A. Dolbecq, A. Bleuzen, M. Verdagner, *Eur. Phys. J. B* 14 (2000) 115-124.







