



HAL
open science

Iron removal from raw asbestos by siderophores-producing *Pseudomonas*

Sébastien R. David, Dris Ihiawakrim, Robert Regis, Valérie A. Geoffroy

► **To cite this version:**

Sébastien R. David, Dris Ihiawakrim, Robert Regis, Valérie A. Geoffroy. Iron removal from raw asbestos by siderophores-producing *Pseudomonas*. *Journal of Hazardous Materials*, 2020, 385, pp.121563 -. 10.1016/j.jhazmat.2019.121563 . hal-03488733

HAL Id: hal-03488733

<https://hal.science/hal-03488733>

Submitted on 21 Jul 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial 4.0 International License

1 **Iron removal from raw asbestos by siderophores-producing *Pseudomonas***

2

3 Sébastien R. David ^{a,b}, Dris Ihiawakrim ^c, Robert Regis ^d, Valérie A. Geoffroy ^a

4 ^a Université de Strasbourg, CNRS-UMR7242, BSC, ESBS, 300 Bld Sébastien Brant,
5 67413 Illkirch, Strasbourg, France

6 ^b Agence de l'Environnement et de la Maîtrise de l'Energie, 20 avenue du Grésillé, BP 90406, 49004
7 Angers Cedex 01, France

8 ^c Université de Strasbourg, CNRS-UMR7504, IPCM, 23 rue du Loess, BP 43, 67034 Strasbourg,
9 France

10 ^d SOMEZ, Parc Marcel Dassault, 470 Rue Alberto Santos Dumont, 34430 Saint Jean de Vedas, France

11

12 To whom correspondence should be addressed: V. A. Geoffroy, UMR 7242, Université de Strasbourg-
13 CNRS, ESBS, Biotechnologie et Signalisation Cellulaire, Bd Brant, CS 10413, F-67412 Illkirch
14 Cedex France.

15 Email : valerie.geoffroy@unistra.fr

16 Tel. (+33) 3 68 85 47 51

17 Fax (+33) 3 68 85 48 29

18

19

20 **Abstract**

21 Asbestos, mineral present in soil, are highly toxic due to the presence of iron. Microbes-
22 mineral interactions occur naturally through various processes leading to their alteration. We
23 examined the effect of siderophore-producing *Pseudomonas* with a particular focus on the
24 role of pyoverdine and pyochelin on raw asbestos fibers such as amosite, crocidolite and
25 chrysotile. We compared the efficiency of pyoverdine to the iron chelating agent EDTA in the
26 release of iron from raw asbestos fibers. Pyoverdine was able to extract iron from all the
27 tested raw asbestos with the higher efficiency observed for chrysotile and crocidolite. When
28 asbestos were grinded, the iron removal was more important for all types. We monitored the
29 effect of bacterial growth and siderophores containing bacterial supernatant on raw asbestos
30 dissolution by solution chemistry analysis and transmission electron microscopy. The
31 siderophore-containing supernatant allowed a higher iron solubilisation than the one obtained
32 after bacterial growth. Moreover, the iron dissolution was faster with pyoverdine-containing
33 supernatant than pyochelin-containing supernatant, with approximately the same iron level for
34 the maximum extraction with a delay of 48 h. Our study clearly showed the involvement of
35 bacterial siderophores, pyoverdine and pyochelin on chrysotile, crocidolite and amosite fibers
36 weathering.

37

38 **Keywords**

40

41 **1. Introduction**

42 Asbestos has been extensively used for building constructions during the industrial
43 exploitation in 1900's before it was banned in 1997 in France. The management of huge
44 amount of wastes is a major concern today since asbestos-containing wastes represent an
45 environmental and health problem. Asbestos fibers inhalation leads to various types of toxic
46 effects in human such as inflammation and fibrogenesis of lung, mesothelioma or
47 bronchogenic carcinoma. Asbestos are natural fibrous silicates belonging to serpentine and
48 amphibole families. Chrysotile, the only member of the asbestiform serpentine is widely
49 present among wastes (90-95%), while amphibole can be found in a minor extent compared to
50 chrysotile in wastes. Among these, crocidolite and amosite are the two members of the
51 amphibole, which have been found among the greatest commercial applications. The
52 crystalline structures of fibers of amphiboles and serpentine are well described [1,2] and it
53 explains the opposite chemical susceptibility towards acids or bases, e.g. chrysotile fibers are
54 easily attacked by acidic condition while amphibole are in basic solution. The chrysotile
55 structure is composed of a double layer consisting of a tetrahedral (silicate) sheet and a
56 magnesium hydroxide octahedral sheet (brucite). This theoretical structure can vary if Fe^{2+}
57 substitutes with Mg^{2+} in the brucite sheet. Up to 5% iron can be encountered in fibers since it
58 is a relatively abundant element in many soils where asbestos natural rocks are originated. A
59 double-tetrahedral silicate chain characterized the amphibole crystalline structure combined
60 with a layer composed of ions mostly Mg^{2+} , Ca^{2+} , Na^+ , Fe^{2+} , or Fe^{3+} (Table 1). Asbestos
61 toxicity is correlated to the presence of iron as a catalyst of the Fenton reaction leading to the
62 generation of free radicals and reactive oxygen species (ROS) [3,4].

63 Iron is an essential nutrient for most living organism to sustain their growth, although it is
64 mostly unavailable in the environment. Iron is naturally abundant in soil, where it can be
65 found in iron-bearing minerals such as goethite or ferrihydrite as iron oxides or clays for
66 example. Therefore, many strategies have been developed by organisms such as fungi, plants
67 or bacteria to have access to this element essential for their growth. Siderophore production,
68 small molecules with a high affinity for Fe(III) produced in iron limited conditions, has been

69 described as one the common weathering process for fungi, plants and bacteria in various
70 interactions with minerals [5]. For example, the dissolution of goethite mediated by the
71 fungus *Suillus granulatus* [6] or various iron oxides solubilized by the phytosiderophore
72 mugineic acid has been reported [7]. Kalinowski *et al.* [8] and Rosenberg and Maurice [9]
73 reported hornblende and kaolinite dissolution rates depending on desferrioxamine-B, a
74 bacterial siderophore that enhanced iron solubilisation. Asbestos, as a fibrous silicate mineral,
75 is no exception to natural weathering by biological processes. Few studies investigated the
76 biological alteration of raw asbestos. Indeed, telluric bacteria such as *Bacillus mucilaginosus*
77 induced a mineral dissolution with an interestingly loss of crystallinity in the serpentine fibers
78 along with a pH decrease, organic acids and ligand secretion [10]. Other bacteria isolated
79 from asbestos rocks or soil from several indian mines, without species identification,
80 decreased the iron content of asbestos rocks [11]. Further studies on these mine-isolated
81 bacteria showed the production of siderophore which could be involved in the weathering
82 process, however with no evidence on the structure of the produced siderophores [12].
83 Moreover, Rajkumar *et al.* [13] described the plant growth-promoting mechanisms involving
84 siderophore-producing-bacteria in a serpentine soil where siderophore is one of the various
85 strategies to remove nutrient elements essential for plant growth. Few siderophores
86 demonstrated their ability to release iron from asbestos fibers. Indeed, iron removal by
87 desferrioxamine siderophore evidenced from raw asbestos, on chrysotile fibers [14] and
88 amphibole fibers such as crocidolite and amosite [15]. Siderophore-producing *Pseudomonas*
89 are widespread bacteria in soil and known for mineral-weathering capacity. The genus
90 *Pseudomonas* produces a wide variety of siderophores and more than 98 % of different
91 fluorescent *Pseudomonas* isolated from soil, produce detectable siderophore under iron
92 starvation [16]. The range of siderophore concentrations found in soil is wide, from tens of
93 micromoles to a few millimoles per litre [17]. *Pseudomonas aeruginosa* is an ubiquitous
94 fluorescent *Pseudomonas* found in various environment [18], whose siderophore production
95 and iron acquisition are well known [19]. *P. aeruginosa* produces two endogenous
96 siderophores, a more energy demanding high affinity molecule, pyoverdine (PVD) [20] and a
97 low affinity siderophore, pyochelin (PCH) [21]. Pyoverdine is composed of three distinct
98 structural parts i) a dihydroxyquinoline chromophore which confers the color and the
99 fluorescence of the molecule ii) a peptide chain comprising 6 to 12 amino acids bound to its

100 carboxyl group iii) a small dicarboxylic acid (or its monoamide) connected amidically to the
101 NH₂-group [22–26]. Pyoverdine chelates iron with a K_a of 10³²M⁻¹ and in 1:1 stoichiometric
102 ratio, via the catechol group of the chromophore and the two hydroxyornithines of the peptide
103 moiety [27]. The structure of pyochelin is a derivative of a salicylic acid, which chelates iron
104 with an affinity of 10^{28.8}M⁻² [28] and a 2:1 (PCH : Fe³⁺) stoichiometry : a tetra-dentate is
105 provided by one molecule of PCH and a bi-dentate by the second PCH to complete the
106 hexacoordinate octahedral geometry necessary for iron chelation [29]. Some studies were
107 shown the ability of siderophore-producing *Pseudomonas* to interact with minerals. For
108 example, *Pseudomonas mendocina* dissolved hematite or goethite, iron oxides, by iron
109 mobilization from these minerals by bacterial metabolism [30]. Moreover, Ferret *et al.* [31]
110 showed the ability of *P. aeruginosa* to solubilize structural iron from smectite, involving the
111 pyoverdine and pyochelin in release process. Smectite is, a type of clay with silicate sheet
112 structure, which structure share a common feature with asbestos minerals.

113 The aim of the present study was to investigate the bioweathering process of chrysotile or
114 amphibole type by siderophore-producing *Pseudomonas*. Therefore, we compared the
115 efficiency of pyoverdine to the chemically iron chelator, Ethylenediaminetetraacetic acid
116 (EDTA), in the release of iron from raw asbestos. We examined the role of the *P. aeruginosa*
117 siderophores, the pyoverdine and pyochelin in the asbestos alteration. This work provide a
118 better understanding of the bacterial interaction with asbestos to further develop in the
119 future a bioremediation process based on bacterial and/or siderophore alteration.

120

121 **2. Experimental**

122 2.1. Raw asbestos preparation

123 Three types of raw asbestos were used (chrysotile (CHR), crocidolite (CRO) and amosite
124 (AMO), table 1) with or without manual grinding. All asbestos samples (0.125 g) were
125 immersed in distilled water and sterilized by autoclave (121°C for 20 min). Samples were
126 then incubated at 70°C for 14 days before experiments for a complete sterilization of
127 materials. The heat removed any water allowing to weight samples with precision.

128 2.2. Pyoverdine purification

129 *P. aeruginosa* ATCC 15692 was grown in Luria Bertani medium (LB) for 15 h at 30°C under
130 shaking condition (220 rpm). 1 mL of LB culture was centrifuged (3 min at 9871 g). To
131 obtain iron starved cells, the iron-deficient succinate medium (composition in g L⁻¹: K₂HPO₄,
132 6.0; KH₂PO₄, 3.0; (NH₄)₂SO₄, 1.0; MgSO₄·7H₂O, 0.2; sodium succinate, 4.0; pH adjusted to
133 7.0 by addition of NaOH), sterilized by 0.2 µm filtration, was used [20]. The pellet, washed
134 twice with 1 ml of succinate medium, was suspended in 1 ml of succinate medium and
135 inoculated in 15 mL of sterile succinate medium, incubated at 30°C under shaking condition
136 (220 rpm). After 24 h of growth, 7.5 mL of this culture was transferred in an Erlenmeyer flask
137 containing 1 L of succinate medium. After 24 h of incubation, the culture was centrifuged
138 (2664 g for 40 min). Then, the supernatant was filtered twice with Whatman filter and once
139 on nitrocellulose filter (0.45 µm porosity). Siderophore containing supernatant was loaded,
140 after acidification (pH 6.0), on XAD-4 column, washed with two volume of purified water
141 and eluted with one volume of 50% ethanol. The green fraction was concentrated under
142 vacuum on a rotary evaporator and lyophilized.

143 2.3. Bacterial strains and growth conditions

144 We used the wild-type *P. aeruginosa* ATCC 15692 strain and two siderophore mutants,
145 PAO6297, a pyochelin-deficient strain (ΔPCH) [32] and PAO6382, a pyoverdine-deficient
146 strain (ΔPVD) [33] (Table 2). Bacteria were grown at 30°C overnight in LB broth medium at
147 200 rpm. For iron-depleted culture, cells were harvested from a LB pre-culture (24 h
148 incubation), washed twice in succinate medium and used to inoculate fresh succinate medium.
149 The cultures were incubated for 24 h under shaking (200 rpm). A second transfer in succinate
150 medium was done in the same condition. After 24 h, the culture was centrifuged (10 min at
151 9871 g) and the pyoverdine-containing supernatants were sterilized by filtration (0.22 µm
152 porosity). To prepare the bacterial suspension, cells were washed twice with sterile succinate
153 medium. Bacterial cell density was adjusted to OD₆₀₀ at 0.05 corresponding to 1-4 x 10⁷
154 CFU/ml.

156 2.4. Dissolution of iron from asbestos fibers

157 Dissolution of iron from asbestos fibers by EDTA or purified pyoverdine produced by
158 *Pseudomonas aeruginosa* ATCC 15692 was compared. Both chelators were prepared in
159 succinate media at a final concentration of 200 µM. Asbestos samples of CHR, CRO and
160 AMO, grounded manually or not, were spiked into 20 mL of each chelator. Assays were
161 incubated at 30°C under shaking condition (220 rpm) during 48 h. After this first cycle

162 contact, the assays were centrifuged 30 min at 9871 g to recover supernatants. In order to
163 continue alteration, two others cycles were repeated during 48 h and 96 h in the same
164 conditions. Each assay was done in triplicate and the results are the mean of triplicate.

165 Dissolution of iron from asbestos fibers by bacteria or bacterial supernatants was done at
166 30°C under shaking conditions (220 rpm) with the 3 types of grinded asbestos. Pyoverdine-
167 containing supernatant and bacterial cell suspension were prepared as described on paragraph
168 2.3. After a first cycle of 48 h alteration, assays were centrifuged 30 min at 9871 g. For each
169 renewal, 20 ml of siderophore-containing supernatant or a bacterial suspension of OD₆₀₀ at
170 0.05 were added to respective samples. Renewal cycles of 48 h were performed twice for both
171 conditions. Every 48 h cycle, bacterial number was determined by serially diluted and plated
172 on LB plates incubated at 30°C for 24 h. All supernatants were sterilized by filtration (0.22
173 µm porosity). Each assay was done in triplicate and the results are the mean of triplicate.
174 Samples of raw crocidolite incubated with bacteria and its abiotic control were observed by
175 transmission electron microscopy at the end of the experimental cycles.

176 In order to determine iron content in supernatant, solutions were acidified to 1% with nitric
177 acid and iron was determined by atomic absorption spectroscopy (Perkin-Elmer AAnalyst
178 400).

179

180 2.7. STEM-EDX of asbestos fibers

181 TEM (Transmission Electron Microscopy) images were recorded with a JEOL 2100
182 microscope, with a 200 kV potential applied on a LaB6 filament as an electron source.
183 Resolution of the TEM is 0.21 nm. TEM mapping was performed in STEM (Scanning
184 transmission electron microscopy) mode (resolution 2 nm) and using an SSD-EDX (Silicon
185 Drift Detector-Energy Dispersive X-ray) spectrometer to determine the chemical composition.

186

187 2.8. Statistical analysis

188 Differences of iron concentrations after pyoverdine and EDTA treatments solubilized from
189 asbestos fibers were determined using Kruskal-Wallis test (RStudio v1.0.153) followed by a
190 Conover post-hoc analysis.

191

192 **Results and discussion**

193

194 **1.1. Comparison of pyoverdine and EDTA treatments**

195 For the three asbestos, chrysotile, crocidolite and amosite, iron was released in the presence of
196 the iron-complexing agents, pyoverdine or EDTA at each renewal cycle. Whichever the
197 asbestos family, serpentine (chrysotile) or amphiboles (Amosite, Crocidolite), the iron release
198 was possible even if the crystalline structure was very different (Fig. 1). Our result showed
199 that the bacterial siderophore pyoverdine produced by fluorescent *Pseudomonas* was able to
200 remove iron from asbestos fibers. During the three incubation period, the bacterial
201 siderophore pyoverdine extracted more iron than the chemical chelator EDTA for chrysotile
202 (0.38 to 1.04 mg/L and 0.08 to 0.19 mg/L respectively) (Fig. 1A-B) and crocidolite (0.59 to
203 3.84 mg/L and 0.12 to 1.92 mg/L respectively) (Fig. 1C-D). Unlike the last two asbestos,
204 pyoverdine and EDTA revealed the same efficiency towards amosite fibers (1.07 to 3.58 and
205 0.82 to 3.64 mg/L respectively) (Fig. 1E-F). Differences between pyoverdine and EDTA
206 efficiency may be explain by their affinity and specificity for iron. Indeed, pyoverdine
207 chelates iron with an affinity of 10^{32} M^{-1} while EDTA has a lower K_a of 10^{20} M^{-1} [34]. When
208 asbestos were grinded, iron weathering increased in the presence of EDTA or pyoverdine with
209 an efficiency ranging from 1.3 times and 2 times for chrysotile and amosite respectively and 2
210 to 5 times for crocidolite (Fig. 1). Grinding lead to the amorphization of chrysotile with
211 probably the direct OH bonds between the silica and brucite sheets destroyed or opened [35].
212 Moreover, grinding may also increase the exchange surface capacity between pyoverdines
213 and asbestos, improving the extraction and accessibility of iron release. Similar results were
214 obtained by Chao *et al.* [15] where EDTA or citrate were also able to extract iron from
215 crocidolite or amosite but to a lesser extent that the bacterial siderophore desferrioxamine.
216 Werner *et al.* [36] observed the same findings on crocidolite under 30 days of contact with the
217 ranking desferrioxamine > EDTA > citrate. Ferrozine, an iron(II) chelator, was able to extract
218 iron from crocidolite and amosite, while the iron extraction from chrysotile was only possible
219 when ascorbic acid was supplemented [14]. Recently, Desferrioxamine and ferrichrome
220 extracted iron for raw chrysotile at the same level but with no synergy when organic acids
221 were supplemented or tested alone [37].

222

223 **1.2. Dissolution of iron by siderophore-producing bacteria**

224
225 We have shown that pyoverdine was able to withdraw iron from the three commonly found
226 raw asbestos fibers. Since asbestos were extracted from soils, like numerous telluric
227 microorganisms such as fluorescent *Pseudomonas*, we wanted to evaluate the role of *P.*
228 *aeruginosa* compared to potential metabolites produced during an iron-starved culture in the
229 release of iron. Therefore, asbestos samples were incubated with cells or bacterial supernatant
230 of *Pseudomonas* producing only pyoverdine, only pyochelin or producing both endogenous
231 siderophores. Removal of iron was measured after three successive contact cycles of 48 h.
232 The amount of iron released in the presence of bacterial supernatants at any given cycle was
233 higher than in the presence of bacterial cells for chrysotile and crocidolite (Fig. 2A, B, C, D).
234 During the first 48 h contact cycle (T48) with chrysotile (Fig 2A), a rapid release of iron was
235 observed for the wild-type and the Δ Pch pyoverdine-containing supernatant, which dissolve
236 iron 2 to 3 times more efficiently than the Δ Pvd supernatant, producing only pyochelin. For
237 the second cycle (T48-2), results are reversed since the Δ Pvd supernatant extracted twice as
238 much iron than the WT and Δ Pch supernatant for chrysotile, results are also valid for
239 crocidolite. Interestingly, for chrysotile and crocidolite, pyochelin containing supernatant at
240 T48-2 cycle extracted the same iron amount than the pyoverdine containing supernatant at
241 T48 but required twice as much time. For the last cycle (T48-3), the same tendency is noticed
242 for chrysotile between the 3 supernatants but to a lesser extent than the T48-2. For crocidolite
243 in the T48-3 cycle, the maximum iron content (0.78 mg/L) was observed for the WT
244 supernatant compared to previous cycles (0.41 and 0.34 mg/L for T48 and T48-2). For
245 amosite, a very low efficiency for all the supernatants was noticed between 0.04 and 0.17
246 mg/L. In the presence of bacteria, only the Δ Pch strain (0.28 mg/L) seemed to be more
247 effective in iron removal at the T48-3 cycle. No changes were observed in culture medium
248 alone or culture medium containing either fibers or bacteria (Fig. 2.). Our results showed that
249 iron dissolution is more rapid and important for chrysotile compared to amphibole. Such
250 differences can be explained by crystal structure of asbestos and the iron-binding sites [38].
251 Indeed, in the chrysotile structure the octahedral layer (brucite) magnesium can be substituted
252 by iron while in the tetrahedral layer, silicon may be rarely replaced by iron. In amphibole
253 structure, iron is bound in cationic sites present in two ribbons of silicate tetrahedra.
254 Therefore, iron is more easily available in chrysotile (brucite outer layer) compared to
255 amphibole whose iron is trapped in two silicate layers.
256 Together with these high affinity iron chelators produced in the supernatant, physiological
257 organic acids could be also encountered during bacterial growth, which may have a

258 synergistic effect in iron release [39]. Another described parameter is the grinding which
259 enhanced iron dissolution [40,41]. In our study, considering that all asbestos fibers were
260 manually grinded, this parameter could have influenced the iron solubilisation, since it was
261 difficult to obtain homogeneous grinding samples between experiments. As a consequence,
262 lower iron concentrations were observed for supernatant-treated crocidolite and amosite
263 compared to the purified pyoverdine treatment. It is well known that siderophore-mediated
264 iron removal involve siderophore adsorption on the iron-bearing mineral surface [5].
265 Therefore, the grinding may increase the specific surface area of asbestos and improve
266 accessibility of siderophores to iron on the surface. Moreover, the presence of organic acids in
267 the supernatant could have influenced the chrysotile dissolution since the amount of dissolved
268 iron at 48 h (2.54 mg/L) in the supernatant is higher compared to the purified pyoverdine
269 dissolution test (0.83 mg/L, Fig. 1B). At the second renewal, the same influence was noticed
270 with values three times higher for the supernatant (Fig. 2A) compared to the purified
271 pyoverdine (Fig. 1B). Differences could not be due to (i) pyoverdine degradation since this
272 molecule has been shown to be stable in those conditions (ii) pyoverdine concentration since
273 it was tested at the same level between the purified and the one synthesized by cells after 48
274 h.

275 Our results confirm that *Pseudomonas* was able to promote mineral dissolution concomitantly
276 with siderophore production. Compared with data related to asbestos-fungi alteration, few
277 researches were focused on asbestos-bacterial interactions. As an example of Gram-positive
278 bacteria, *Bacillus mucilaginosus* was able to accelerate serpentine powder thanks to organic
279 acids and ligands [10]. Bhattacharya *et al.* [11] isolated Gram positive and Gram negative
280 bacteria from Indian asbestos contaminated soil or asbestos rocks which induced a decrease in
281 the iron content of asbestos after bacterial weathering. Further research, focused on the Gram
282 positive previously isolated strains, revealed the production of siderophores from these
283 bacteria, with no precise identification of the produced compounds [12]. Bacterial
284 siderophores produced by *Staphylococcus* mines isolates [11,12] were also implicated in iron
285 removal from asbestos rocks, together with desferrioxamine from crocidolite fibers [42]. This
286 strategy to overcome iron limitation is also well documented for soil organisms since several
287 fungi have been reported to be involved in iron sequestration [43]. Bioweathering abilities of
288 chrysotile fibers revealed different efficiency depending on the fungi genus. Fungi such as
289 *Fusarium oxysporum* released also in the extracellular medium chelators able to extract iron
290 from both serpentine (chrysotile) and amphibole (amosite and crocidolite) asbestos fibers

291 [42]. Asbestos seems to be an iron source for various organisms described so far through the
292 siderophore strategy.

293

294 **1.3. Evidence of biofilm formation on asbestos fibers**

295

296 In the experiment of iron dissolution by siderophore-producing bacteria, we observed that all
297 raw asbestos incubated with bacteria were agglomerated, leading to a compact cluster,
298 whereas the fibers resulting from deterioration in the abiotic medium remained free. In order
299 to determine the impact of biotic condition on the material, fibers were observed by TEM
300 (Fig. 3). As an example, crocidolite fibers incubated with *Pseudomonas aeruginosa* wild type
301 or in the succinate medium after 48 h were analyzed. The analysis of the altered fibers in
302 abiotic conditions showed no detectable alteration layer. In biotic condition, fibers are
303 covered with a biofilm explaining the agglomeration of the material. *Pseudomonas* are well
304 known to form biofilm, which is a surface-attached bacteria embedded in a self-produced
305 matrix of extracellular polymeric substances (EPS) that are adherent to each other
306 and/or a surface exopolysaccharides (Fig. 3). Adhesion to surfaces has been seen as a
307 survival strategy under energy limitation [44]. Weathering of rocks is a complex process
308 where biofilm are able to accelerate or inhibit the alteration [45]. For example,
309 *Pseudomonas aeruginosa* has already been described to form a biofilm on municipal waste
310 incinerator bottom ash cementing grains together [46] or on smectite, a type of clay [31]. In
311 leachates experiments of bottom ashes, analysis of iron concentration in solution increase in
312 the presence of bacteria and bottom ash, while the concentration of others elements such as Ni
313 and Zn was higher in abiotic condition compared to the biotic medium. This could be a
314 consequence of chemical modification of the solution by bacterial development since
315 reducing conditions together with the production of organic acids and siderophores may
316 occur. Siderophore-promoted dissolution of iron-bearing minerals has been clearly
317 documented and the study of Ferret *et al.* [31] showed an increase in the dissolved silicon,
318 iron and aluminum concentrations following smectite supplementation in the presence of
319 *Pseudomonas*. In an asbestos cement pipe in drinking water distribution system, a biofilm was
320 evidenced containing metallic cations leading to decrease of the thickness of the pipe wall
321 linked to the loss of hydrated cement matrix. A consequence of this bacterial activity may
322 cause a pipe failure [47]. In our experiments, the analysis of crocidolite fibers by STEM-EDX
323 showed a slight decrease of iron content after 48 h with bacterial contact. According to results
324 in figure 2, the bacterial supernatant of the wild type *P. aeruginosa* allowed to deplete iron

325 more efficiently from fibers compared to bacterial cells. These results confirmed the active
326 dissolution driven by the siderophore-mediated and/or bacterial process (Fig. 4).

327

328 **4. Conclusions**

329 We examined the potential bioweathering ability of siderophore-producing *Pseudomonas* and
330 their produced siderophores on raw asbestos fibers. We clearly showed that biological
331 chelating agents are more efficient in iron extraction than the best known chemical chelating
332 compound EDTA. In addition, iron dissolution was more effective when fibers were manually
333 grinded. Our results demonstrated that *Pseudomonas* and their produced siderophores,
334 pyoverdine and pyochelin, were able to dissolve iron from asbestos fibers but not at the same
335 efficiency. Siderophores containing supernatants extracted more iron than the bacterial cells
336 after asbestos contact. A biofilm covering fibers was evidenced during bacterial growth and
337 the iron content in fibers decreased after bacterial contact. Moreover, pyoverdine
338 containing supernatant dissolved more rapidly iron from chrysotile and crocidolite
339 fibers than pyochelin containing supernatant. Our study clearly demonstrated that
340 either siderophores or *Pseudomonas* cells were able to weather the three types of
341 asbestos fibers. Our research has shown that asbestos can serve as a source of nutrients
342 for soil bacteria. Further investigations are required to extend these experiments on
343 asbestos wastes in order to develop a bioremediation process based on bacterial and/or
344 siderophore alteration.

345

346 **Acknowledgements**

347 This work was supported by the French Environment and Energy Management Agency
348 (ADEME) and the SOMEZ (Société Méditerranéenne des Zéolithes).

349

350 **References**

- 351 [1] W.B. Simmons, Amphibole, Encyclopædia Britannica, Inc. (2016).
352 <https://www.britannica.com/science/amphibole>.
- 353 [2] D. Bernstein, J. Dunnigan, T. Hesterberg, R. Brown, J.A.L. Velasco, R. Barrera, J.
354 Hoskins, A. Gibbs, Health risk of chrysotile revisited, Crit Rev Toxicol. 43 (2013)
355 154–183. doi:10.3109/10408444.2012.756454.
- 356 [3] S. Toyokuni, Mechanisms of asbestos-induced carcinogenesis, Nagoya Journal of
357 Medical Science. 71 (2009) 1–10.

- 358 [4] M. Valko, K. Jomova, C.J. Rhodes, K. Kuča, K. Musílek, Redox- and non-redox-
359 metal-induced formation of free radicals and their role in human disease, Arch
360 Toxicol. 90 (2015) 1–37. doi:10.1007/s00204-015-1579-5.
- 361 [5] S.M. Kraemer, Iron oxide dissolution and solubility in the presence of
362 siderophores, Aquat. Sci. 66 (2004) 3–18. doi:10.1007/s00027-003-0690-5.
- 363 [6] F. Watteau, J. Berthelin, Microbial dissolution of iron and aluminium from soil
364 minerals: efficiency and specificity of hydroxamate siderophores compared to
365 alphatic acids, European Journal of Soil Biology. 30 (1994) 1–9.
- 366 [7] S. Hiradate, K. Inoue, Dissolution of iron from iron (Hydr)Oxides by mugineic
367 acid, Soil Science and Plant Nutrition. 44 (1998) 305–313.
368 doi:10.1080/00380768.1998.10414453.
- 369 [8] B.E. Kalinowski, L.J. Liermann, S. Givens, S.L. Brantley, Rates of bacteria-
370 promoted solubilization of Fe from minerals: a review of problems and approaches,
371 Chemical Geology. 169 (2000) 357–370. doi:10.1016/S0009-2541(00)00214-X.
- 372 [9] D.R. Rosenberg, P.A. Maurice, Siderophore adsorption to and dissolution of
373 kaolinite at pH 3 to 7 and 22°C, Geochimica et Cosmochimica Acta. 67 (2003) 223–
374 229. doi:10.1016/S0016-7037(02)01082-7.
- 375 [10] M. Yao, B. Lian, H.H. Teng, Y. Tian, X. Yang, Serpentine Dissolution in the
376 Presence of Bacteria *Bacillus mucilaginosus*, Geomicrobiology Journal. 30 (2013)
377 72–80. doi:10.1080/01490451.2011.653087.
- 378 [11] S. Bhattacharya, P.J. John, L. Ledwani, Bacterial Weathering of Asbestos, Silicon.
379 7 (2015) 419–431. doi:10.1007/s12633-014-9260-9.
- 380 [12] S. Bhattacharya, P.J. John, L. Ledwani, Fungal weathering of asbestos in semi arid
381 regions of India, Ecotoxicology and Environmental Safety. 124 (2016) 186–192.
382 doi:10.1016/j.ecoenv.2015.10.022.
- 383 [13] M. Rajkumar, N. Ae, M.N.V. Prasad, H. Freitas, Potential of siderophore-
384 producing bacteria for improving heavy metal phytoextraction, Trends in
385 Biotechnology. 28 (2010) 142–149. doi:10.1016/j.tibtech.2009.12.002.
- 386 [14] L.G. Lund, A.E. Aust, Iron mobilization from asbestos by chelators and ascorbic
387 acid, Archives of Biochemistry and Biophysics. 278 (1990) 60–64. doi:10.1016/0003-
388 9861(90)90231-M.
- 389 [15] C.C. Chao, A.E. Aust, Effect of Long-Term Removal of Iron from Asbestos by
390 Desferrioxamine B on Subsequent Mobilization by Other Chelators and Induction
391 of DNA Single-Strand Breaks, Archives of Biochemistry and Biophysics. 308 (1994)
392 64–69. doi:10.1006/abbi.1994.1009.
- 393 [16] C. Cocozza, G.L. Ercolani, Siderophore production and associated characteristics
394 in rhizosphere and non-rhizosphere fluorescent pseudomonads, Annali di
395 microbiol. enzymol. 47 (1997) 17–28.
- 396 [17] L. Hersman, T. Lloyd, G. Sposito, Siderophore-promoted dissolution of hematite,
397 Geochimica et Cosmochimica Acta. 59 (1995) 3327–3330. doi:10.1016/0016-
398 7037(95)00221-K.
- 399 [18] J.B. Goldberg, *Pseudomonas*: global bacteria, Trends Microbiol. 8 (2000) 55–57.
- 400 [19] K. Poole, G.A. McKay, Iron acquisition and its control in *Pseudomonas aeruginosa*:
401 many roads lead to Rome, Front. Biosci. 8 (2003) d661-686.
- 402 [20] J.M. Meyer, M.A. Abdallah, The Fluorescent Pigment of *Pseudomonas fluorescens*:
403 Biosynthesis, Purification and Physicochemical Properties, Microbiology. 107
404 (1978) 319–328. doi:10.1099/00221287-107-2-319.
- 405 [21] C.D. Cox, K.L. Rinehart, M.L. Moore, J.C. Cook, Pyochelin: novel structure of an
406 iron-chelating growth promoter for *Pseudomonas aeruginosa*, PNAS. 78 (1981)
407 4256–4260. doi:10.1073/pnas.78.7.4256.

- 408 [22] H. Budzikiewicz, Siderophores of Fluorescent Pseudomonads, *Z. Naturforschung*
409 *C.* 52 (1997) 713–720. doi:10.1515/znc-1997-11-1201.
- 410 [23] H. Budzikiewicz, M. Schäfer, D.U. Fernández, S. Matthijs, P. Cornelis,
411 Characterization of the chromophores of pyoverdins and related siderophores by
412 electrospray tandem mass spectrometry, *Biometals.* 20 (2007) 135–144.
413 doi:10.1007/s10534-006-9021-3.
- 414 [24] H. Budzikiewicz, Siderophores of the Pseudomonadaceae sensu stricto (Fluorescent
415 and Non-Fluorescent *Pseudomonas* spp.), in: H. Budzikiewicz, T. Flessner, R.
416 Jautelat, U. Scholz, E. Winterfeldt, W. Herz, H. Falk, G.W. Kirby (Eds.), *Progress*
417 *in the Chemistry of Organic Natural Products*, Springer Vienna, Vienna, 2004: pp.
418 81–237. doi:10.1007/978-3-7091-0581-8_2.
- 419 [25] P. Demange, S. Wendenbaum, C. Linget, C. Mertz, M.T. Cung, A. Dell, M.A.
420 Abdallah, Bacterial siderophores: structure and NMR assignment of pyoverdins
421 Pa, siderophores of *Pseudomonas aeruginosa* ATCC 15692, *Biol Metals.* 3 (1990)
422 155–170. doi:10.1007/BF01140574.
- 423 [26] R. Fuchs, H. Budzikiewicz, Structural Studies of Pyoverdins by Mass
424 Spectrometry, *Curr. Org. Chem.* 5 (2001) 265–288.
425 doi:https://doi.org/10.2174/1385272013375562.
- 426 [27] A.-M. Albrecht-Gary, S. Blanc, N. Rochel, A.Z. Ocaktan, M.A. Abdallah, Bacterial
427 Iron Transport: Coordination Properties of Pyoverdin PaA, a Peptidic Siderophore
428 of *Pseudomonas aeruginosa*, *Inorg. Chem.* 33 (1994) 6391–6402.
429 doi:10.1021/ic00104a059.
- 430 [28] J. Brandel, N. Humbert, M. Elhabiri, I.J. Schalk, G.L.A. Mislin, A.-M. Albrecht-
431 Gary, Pyochelin, a siderophore of *Pseudomonas aeruginosa*: Physicochemical
432 characterization of the iron(III), copper(II) and zinc(II) complexes, *Dalton Trans.*
433 41 (2012) 2820–2834. doi:10.1039/C1DT11804H.
- 434 [29] C.-F. Tseng, A. Burger, G.L.A. Mislin, I.J. Schalk, S.S.-F. Yu, S.I. Chan, M.A.
435 Abdallah, Bacterial siderophores: the solution stoichiometry and coordination of
436 the Fe(III) complexes of pyochelin and related compounds, *J Biol Inorg Chem.* 11
437 (2006) 419–432. doi:10.1007/s00775-006-0088-7.
- 438 [30] L.E. Hersman, J.H. Forsythe, L.O. Ticknor, P.A. Maurice, Growth of *Pseudomonas*
439 *mendocina* on Fe(III) (Hydr)Oxides, *Appl. Environ. Microbiol.* 67 (2001) 4448–
440 4453. doi:10.1128/AEM.67.10.4448-4453.2001.
- 441 [31] C. Ferret, T. Sterckeman, J.-Y. Cornu, S. Gangloff, I.J. Schalk, V.A. Geoffroy,
442 Siderophore-promoted dissolution of smectite by fluorescent *Pseudomonas*,
443 *Environmental Microbiology Reports.* 6 (2014) 459–467. doi:10.1111/1758-
444 2229.12146.
- 445 [32] C. Reimann, L. Serino, M. Beyeler, D. Haa, Dihydroaeruginosic acid synthetase
446 and pyochelin synthetase, products of the pchEF, are induced by extracellular
447 pyochelin in *Pseudomonas aeruginosa*, *Microbiology.* 144 (1998) 3135–3148.
448 doi:10.1099/00221287-144-11-3135.
- 449 [33] F. Hoegy, X. Lee, S. Noel, D. Rognan, G.L.A. Mislin, C. Reimann, I.J. Schalk,
450 Stereospecificity of the Siderophore Pyochelin Outer Membrane Transporters in
451 Fluorescent Pseudomonads, *J. Biol. Chem.* 284 (2009) 14949–14957.
452 doi:10.1074/jbc.M900606200.
- 453 [34] B. Nowack, F.G. Kari, H.G. Krüger, The Remobilization of Metals from Iron
454 Oxides and Sediments by Metal-EDTA Complexes, *Water, Air, & Soil Pollution.*
455 125 (2001) 243–257. doi:10.1023/A:1005296312509.

- 456 [35] D. Spasiano, F. Pirozzi, Treatments of asbestos containing wastes, *Journal of*
457 *Environmental Management*. 204, Part 1 (2017) 82–91.
458 doi:10.1016/j.jenvman.2017.08.038.
- 459 [36] A.J. Werner, M.F. Hochella, G.D. Guthrie, J.A. Hardy, A.E. Aust, Rimstidt,
460 Asbestiform riebeckite (crocidolite) dissolution in the presence of Fe chelators:
461 Implications for mineral-induced disease, *American Mineralogist*. 80 (2015) 1093–
462 1103. doi:10.2138/am-1995-11-1201.
- 463 [37] S.K. Mohanty, C. Gonneau, A. Salamatipour, R.A. Pietrofesa, B. Casper, M.
464 Christofidou-Solomidou, J.K. Willenbring, Siderophore-mediated iron removal
465 from chrysotile: Implications for asbestos toxicity reduction and bioremediation,
466 *Journal of Hazardous Materials*. 341 (2018) 290–296.
467 doi:10.1016/j.jhazmat.2017.07.033.
- 468 [38] R.L. Virta, *Asbestos: geology, mineralogy, mining, and uses*, US Department of the
469 Interior. US Geological Survey, 2002. <http://pubs.usgs.gov/of/2002/of02-149/index.html>
470 (accessed November 16, 2016).
- 471 [39] E. Ahmed, S.J.M. Holmström, Siderophores in environmental research: roles and
472 applications, *Microbial Biotechnology*. 7 (2014) 196–208. doi:10.1111/1751-
473 7915.12117.
- 474 [40] P. Plescia, D. Gizzi, S. Benedetti, L. Camilucci, C. Fanizza, P. De Simone, F.
475 Paglietti, Mechanochemical treatment to recycling asbestos-containing waste,
476 *Waste Management*. 23 (2003) 209–218. doi:10.1016/S0956-053X(02)00156-3.
- 477 [41] A. Salamatipour, S.K. Mohanty, R.A. Pietrofesa, D.R. Vann, M. Christofidou-
478 Solomidou, J.K. Willenbring, Asbestos Fiber Preparation Methods Affect Fiber
479 Toxicity, *Environ. Sci. Technol. Lett.* 3 (2016) 270–274.
480 doi:10.1021/acs.estlett.6b00174.
- 481 [42] S. Daghino, E. Martino, I. Fenoglio, M. Tomatis, S. Perotto, B. Fubini, *Inorganic*
482 *Materials and Living Organisms: Surface Modifications and Fungal Responses to*
483 *Various Asbestos Forms*, *Chem. Eur. J.* 11 (2005) 5611–5618.
484 doi:10.1002/chem.200500046.
- 485 [43] S. Daghino, E. Martino, E. Vurro, M. Tomatis, M. Girlanda, B. Fubini, S. Perotto,
486 Bioweathering of chrysotile by fungi isolated in ophiolitic sites, *FEMS*
487 *Microbiology Letters*. 285 (2008) 242–249. doi:10.1111/j.1574-6968.2008.01239.x.
- 488 [44] K.C. Marshall, Mechanisms of Bacterial Adhesion at Solid-Water Interfaces, in:
489 D.C. Savage, M. Fletcher (Eds.), *Bacterial Adhesion: Mechanisms and*
490 *Physiological Significance*, Springer US, Boston, MA, 1985: pp. 133–161.
491 doi:10.1007/978-1-4615-6514-7_6.
- 492 [45] D. Mottershead, A. Gorbushina, G. Lucas, J. Wright, The influence of marine salts,
493 aspect and microbes in the weathering of sandstone in two historic structures,
494 *Building and Environment*. 38 (2003) 1193–1204. doi:10.1016/S0360-
495 1323(03)00071-4.
- 496 [46] G. Aouad, J.-L. Crovisier, D. Damidot, P. Stille, E. Hutchens, J. Mutterer, J.-M.
497 Meyer, V.A. Geoffroy, Interactions between municipal solid waste incinerator
498 bottom ash and bacteria (*Pseudomonas aeruginosa*), *Science of The Total*
499 *Environment*. 393 (2008) 385–393. doi:10.1016/j.scitotenv.2008.01.017.
- 500 [47] D. Wang, R. Cullimore, Y. Hu, R. Chowdhury, Biodeterioration of asbestos cement
501 (AC) pipe in drinking water distribution systems, *International Biodeterioration &*
502 *Biodegradation*. 65 (2011) 810–817. doi:10.1016/j.ibiod.2011.05.004.
- 503

504 FIGURE LEGENDS:

505

506 **Figure 1:** Iron concentration dissolved from raw asbestos grinded or not in the presence of
507 EDTA (200 μ M) (grey bars) or purified pyoverdine (200 μ M) from *Pseudomonas aeruginosa*
508 ATCC 15692 (black bars) after two 48 hours-contact time and a 96 hours contact time under
509 shaking (200 rpm) at 30°C. Iron was monitored by atomic absorption spectroscopy in the
510 absence or in the presence of asbestos (0.125 g). Raw asbestos were designed as chrysotile
511 (CHR) or grinded chrysotile (CHRb), crocidolite (CRO) or grinded crocidolite (CROb),
512 amosite (AMO) or grinded amosite (AMOb). Error bars indicates standard deviation over
513 mean of triplicate experiments. Groups without significant different iron amounts were
514 indicated by a, b, and c.

515

516 **Figure 2:** Iron concentration measured in the supernatant after bacterial growth (B,D, F) or in
517 the presence of each bacterial strain's supernatant (A, C, E) after 3 renewal cycles of 48 H
518 with raw chrysotile (A, B), raw crocidolite (C, D) and raw amosite (E, F) at 30°C. The tested
519 strains were the wild-type *Pseudomonas aeruginosa* ATCC 15691 (PAO1, red bars),
520 pyocheline-deficient mutant (\square PCH, green bars) and pyoverdine-deficient mutant (\square PVD,
521 blue bars). Error bars indicates standard deviation over mean of triplicate experiments.


522

523 **Figure 3:** STEM images of bacterial biofilm associated to crocidolite fibers (B) compared to
524 control fibers (A). Crocidolite fibers were incubated with the wild-type *Pseudomonas*
525 *aeruginosa* in succinate medium or succinate medium without bacteria during 48 h under
526 shaking condition (220 rpm). Scale bar corresponds to 500 nm.

527

528 **Figure 4:** STEM images and STEM mappings of crocidolite fibers before contact (a and b),
529 after bacterial growth (c and d) and after incubation with bacterial supernatant (e and f) during
530 48 h under shaking conditions (220 rpm). Large images obtained from the combination of the
531 three distributions of Mg, Si, and Fe with analysis areas (a, c and e). Atomic ratios of Mg/Si
532 and Fe/Si (b, d and f). Mass percentage of iron, magnesium and silicium before and after
533 contact of raw crocidolite with *P. aeruginosa* PAO1 or bacterial supernatant (g).

534



2

3

4

5

6


7

Figure 1: Iron concentration dissolved from raw asbestos grinded or not in the presence of EDTA (200 μ M) (grey bars) or purified pyoverdine (200 μ M) from *Pseudomonas*


8 *aeruginosa* ATCC 15692 (black bars) after two 48 hours-contact time and a 96 hours
9 contact time under shaking (200 rpm) at 30°C. Iron was monitored by atomic absorption
10 spectroscopy in the absence or in the presence of asbestos (0.125 g). Raw asbestos were
11 designed as chrysotile (CHR) or grinded chrysotile (CHRb), crocidolite (CRO) or grinded
12 crocidolite (CROb), amosite (AMO) or grinded amosite (AMOb). Error bars indicates
13 standard deviation over mean of triplicate experiments. Groups without significant
14 different iron amounts were indicated by a, b, and c.

15


A




B




C




D



E



F




5

6 **Figure 2:** Iron concentration measured in the supernatant after bacterial growth (B,D,
7 F) or in the presence of each bacterial strain's supernatant (A, C, E) after 3 renewal
8 cycles of 48 H with raw chrysotile (A, B), raw crocidolite (C, D) and raw amosite (E, F) at
9 30°C. The tested strains were the wild-type *Pseudomonas aeruginosa* ATCC 15691
10 (PAO1, red bars), pyochelin-deficient mutant (Δ PCH, green bars) and pyoverdine-
11 deficient mutant (Δ PVD, blue bars). Error bars indicates standard deviation over mean
12 of triplicate experiments.


13

14 **In color print**



1
2
3
4
5
6
7

Figure 3: STEM images of bacterial biofilm associated to crocidolite fibers (B) compared to control fibers (A). Crocidolite fibers were incubated with the wild-type *Pseudomonas aeruginosa* in succinate medium or succinate medium without bacteria during 48 h under shaking condition (220 rpm). Scale bar corresponds to 500 nm.



1
2
3 **Figure 4:** STEM images and STEM mappings of crocidolite fibers before contact (a and b),
4 after bacterial growth (c and d) and after incubation with bacterial supernatant (e and f) during
5 48 h under shaking conditions (220 rpm). Large images obtained from the combination of the
6 three distributions of Mg, Si, and Fe with analysis areas (a, c and e). Atomic ratios of Mg/Si
7 and Fe/Si (b, d and f). Mass percentage of iron, magnesium and silicium before and after
8 contact of raw crocidolite with *P. aeruginosa* PAO1 or bacterial supernatant (g)

9
10 **In color print**
11

1 **Table 1.** List and composition of asbestos used.
2

| Name | Composition | Source |
|-------------|----------------------------------------------|------------------------------------------------------------------|
| Chrysotile | $Mg_6Si_4O_{10}(OH)_8$ | Natural History Museum of Paris |
| Crocidolite | $Na_2(Fe^{3+})_2(Fe^{2+})_3Si_8O_{22}(OH)_2$ | mine South Africa « Wangu Hill, Kwagulu, province of Natal Woumo |
| Amosite | $(Fe, Mg)_7Si_8O_{22}(OH)_2$ | Penga mine- South Africa, province of Impopo |

3
4

1 **Table 2.** List of the strains used.

2


| Name | Relevant characteristics | Reference or source |
|-------------------------------------|---------------------------------|----------------------------|
| <i>P. aeruginosa</i> strains | | |
| PAO1 | Wild-type | ATCC15692 |
| PAO6297 | $\Delta pchBA$ | [32] |
| PAO6382 | $\Delta pvdF$ | [33] |

3

4

1 **Graphical Abstract**

2
3



4