

Effect of heat treatment on Pinus pinaster rosin: A study of physico chemical changes and influence on the quality of rosin linseed oil varnish

Manon Francès, Yanis Gardere, E. Duret, Léo Leroyer, Thomas Cabaret, M. Rubini, Arsène Bikoro Bi Athomo, Bertrand Charrier

▶ To cite this version:

Manon Francès, Yanis Gardere, E. Duret, Léo Leroyer, Thomas Cabaret, et al.. Effect of heat treatment on Pinus pinaster rosin: A study of physico chemical changes and influence on the quality of rosin linseed oil varnish. Industrial Crops and Products, 2020, 155, pp.112789 -. 10.1016/j.indcrop.2020.112789. hal-03492057

HAL Id: hal-03492057 https://hal.science/hal-03492057

Submitted on 7 Jan2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés. Version of Record: https://www.sciencedirect.com/science/article/pii/S0926669020307068 Manuscript_b09413b93eed54307ed78e18aa52afd0

1	Effect of heat treatment on Pinus pinaster rosin: a study of physico chemical changes and
2	influence on the quality of rosin linseed oil varnish
3	Frances, M. ^{a*} , Gardere, Y. ^a , Duret, E. ^a , Leroyer, L. ^a , Cabaret, T. ^a , Rubini, M. ^a , Bikoro Bi
4	Athomo, A. ^a , Charrier, B ^a
5	^a CNRS/ Univ Pau & Pays Adour, Institut des Sciences Analytiques et de Physico-Chimie pour
6	l'Environnement et les Matériaux, Xylomat, UMR5254, 40004, Mont de Marsan, France
7	Corresponding author: manon.mg.frances@gmail.com
8	Abstract:
9	The aim of this study was to get a better understanding of the formulation aspect of a new
10	linseed oil - rosin varnish inspired by the antique violin coating, using heat-treated and non-treated
11	rosin. To do so, the heat treatment effect on rosin was studied on both its thermal properties and some
12	of the varnish properties. The rosin without heat treatment was assigned as the reference. The
13	temperature treatments were: 180 °C, 200 °C and 250 °C. The thermal properties were studied using
14	TMA, DSC, ATG and HPLC. A change due to heat treatment was observed, especially on the
15	softening point and the glass transition, which increase with the temperature. Chemical changes were
16	observed, with the apparition of dehydrogenated and oxidised forms of abietane-based acid, which are
17	not present in the reference rosin. As expected, the amount of turpentine decreases with the heat
18	treatment. The varnish properties are also impacted, with a decrease of brightness and solvent
19	resistance with the temperature. A PCA was made in order to have a statistical analysis of the results.
20	Through this, a clear separation of the four groups was graphically observed, with different
21	representative variables. The variables' influence on each other was also clearly identified, as well as
22	the impact of the chemical changes on thermal and varnish properties.
23	Keywords: rosin, formulation, vegetable oil, maritime pine, varnish, heat treatment

25 1. Introduction

26 *Pinus pinaster*, also known as Maritime pine is present in vast areas of Italy, France, Portugal, Spain and North of Africa. The largest monospecific woodland in south-western Europe extends over 27 28 the Landes de Gascogne: a 1.5 million hectare maritime pine forest (Rosa et al., 2018). The maritime 29 pine is cultivated for its timber (Pinto et al., 2005; Riesco Muñoz et al., 2014). Historically, it was used to harvest resin (Soliño et al., 2018). Maritime pine contains more resin ducts than other conifers (Wu 30 and Hu, 1997), connected by anastomoses (Rodríguez-García et al., 2014). Conifers in the pine family 31 32 also have the ability to form new resin ducts following biotic and abiotic attacks (Krokene, 2015). The 33 resin is produced in epithelial cells, and accumulated in resin ducts (Wu and Hu, 1997). The harvest is 34 made by pine tapping, a process based on the defence system of the tree, which secretes resin as a 35 defensive response to external factors (Rodríguez-García et al., 2016). This defence mechanism can come into play as a response to phytopathogenes (Franceschi et al., 2005), abiotic stress (Blanche et 36 al., 1992), chemical stimuli (Moreira et al., 2009), or, in our case, mechanical wounding (Cheniclet, 37 38 1987). After distillation, resin is separated into a volatile fraction, the turpentine (30 %), and a solid residue, the rosin (70 %) (Hawley and Palmer, 1912). The rosin is a brittle, glassy solid, with a yellow-39 40 brown colour (Coppen and Hone, 1995).

41 Rosin composition has been investigated for several years. It contains 90 % of diterpenic 42 acids, and its empirical formula is $C_{20}H_{30}O_2$. The composition may vary depending on its source, species and geographical area. There are two main types of acids in the rosin, pimaric-like and abietic-43 44 like. The abietic-like includes: abietic, neoabietic, palustric, and dehydroabietic acid. The pimaric-like 45 includes: dextropimaric and isodextropimaric (Baldwin et al., 1958; Joye and Lawrence, 1967). The softening point has been determined with thermomechanical analysis (TMA) developed by Cabaret et 46 al., which could be more precise than the ASTM E28-14 standard, and is between 25 °C to 70 °C 47 48 (Cabaret et al., 2018). According to Gaillard et al. (2011), rosin does not have a precise glass transition 49 temperature, but a wide temperature range before reaching a liquid state. The thermal decomposition of rosin occurs in a temperature range from 190 °C to 310 °C (Narayanan et al., 2017). Rosin has 50 many applications such as adhesives (Wang et al., 2018), antibacterial polymer (Kanerva et al., 2019) 51 52 or packaging (Narayanan et al., 2017). It has been widely used from the 16th through to the early 19th century for varnish by violin makers (Echard and Malecki, 2014). There are numerous studies about
those varnishes (Chen, 1992; Echard et al., 2010; Invernizzi et al., 2016), which highlight a blend of
siccative oil, rosin and siccative additives (lead, aluminium, iron).

56 Previous studies have observed the proportion, preparation and molecular composition of these historical varnishes (Tirat et al., 2017, 2016), revealing the interaction between the triglycerides 57 from the linseed oil and the diterpenic acids ; they most probably react together to form hybrid species, 58 59 oligomeric diterpenes and/or hybrid glyceride-diterpene species. It is likely that the heat treatment is what causes the formation of acid species. The heat treatment of linseed oil has previously been 60 studied (Byrdwell and Neff, 1999): increasing the temperature results in a higher degree of oxidation 61 and increases the average molecular weight (Berg, 2002). The heat treatment has also been studied for 62 the rosin. The abietic based acids undergo isomerization, due to their two conjugated double bonds, 63 64 decomposition, dehydrogenation (Chen, 1992; Loeblich et al., 1955) and auto-oxidative polymerization during the heating (Artaki et al., 1992). Those modifications lead to the formation of 65 compounds such as 15-hydroxo-dehydroabietic acid, 7-oxo-15-hydroxy-dehydroabietic acid and 7-66 oxo-dehydroabietic acid (Cabaret et al., 2019; Scalarone et al., 2002). 67

68 The objective of this study is to characterize the rosin before and after high-temperature heat treatment (180 °C, 200 °C and 250 °C) with differential scanning calorimetry (DSC), 69 thermogravimetric analysis (TGA), TMA and high-performance liquid chromatography (HPLC), and 70 71 to qualify the consequences of those treatments in linseed oil – rosin varnishes. A principal component 72 analysis (PCA) was conducted, in order to correlate the rosin results with the varnishes. PCA is a 73 multivariate technique that aims to reduce the number of dimensions in a dataset (Wold et al., 1987). 74 The purpose is to obtain information in order to create a new varnish, inspired by the antique violin 75 coating and using a local resource for our research team localisation, the rosin.

- 76 2. Materials and methods
- 77 2.1 Raw materials

78 The rosin came from a batch obtained after distillation of one resin mixture from various maritime pine trees from the Landes forest, extracted with the Biogemme© eco-process. It was 79 80 furnished by Holiste, Biscarosse, France. This rosin is used raw as a reference. The distillation, in order to obtain pure rosin, was made by Biolandes, Le Sen, France, at low temperature and low 81 pressure; details of this process are confidential. The raw linseed oil, first pressing and 100 % from 82 linseed, was provided by Onyx, Roche-lez-Beaupré, France. Ôkhra company based in Roussillon, 83 84 France, supplied the umber powder, containing manganese dioxide and iron oxide, known as driers for 85 linseed oil. Indeed they promote peroxide decomposition and reduce the induction time (de Viguerie et al., 2016). 86

87 2.2 H

2.2 Heat treatment

The reference rosin (Holiste, Biscarosse, France) was used without heat treatment. The rosin degradation temperature range starts at 200 °C and ends around 300 °C (Artaki et al., 1992), therefore the heat treatment temperatures were chosen within that range. All the rosin samples were heated for 30 minutes with a stirring hot plate at 180 °C, 200 °C and 250 °C, corresponding respectively to the linseed oil temperature in the varnishes preparation, the onset temperature of rosin degradation and temperature where degradation occurs. It was decided to not test the 300 °C temperature, which is too close to the self-ignition temperature of the rosin, 390 °C (Carson and Mumford, 2002).

95 2.3 Varnishes preparation

All varnishes were prepared using the same protocol, to ensure reproducibility of the different steps. Linseed oil was first heated in a glass beaker at 180 °C for 220 minutes according to the recipe of the instrument maker Nicolas Gilles (Gilles, 2019). Umber powder was added as a siccative during the heating, at 0,2 % weight of the total varnish mass. After the heating time, the mixture was brought to room temperature. The rosin was grinded in a mortar before sifting at 800 μ m, and then added to the mixture with a 20/80 (rosin/linseed oil) w/w ratio at room temperature. The mixture was heated at 180 °C for a duration of 90 minutes under constant stirring. At the end, heating was cut and the varnish 103 was allowed to cool down to room temperature. The varnish was poured into a UV-protected vial and104 kept at room temperature.

105 2.4 Varnish application

Each varnish was applied with a brush on three maritime pine panels, and UV polymerized.
The panel dimensions were 150 x 74 x 18 mm. The UV lamp had a wavelength of 340 nm, and an
irradiance of 1,55W/m². Each layer of coating required 6 hours of UV exposition in order to
polymerize. Three layers were needed, in order to obtain a satisfying homogeneity. The three layers
gave a final film thickness between 150 and 200 μm.

111 2.5 Differential scanning calorimetry (DSC) analysis

Measurements were carried out on a DSC (TA Instruments, Q20) equipped with a rapid 112 cooling system. Individual samples of heat-treated rosin and the reference were weighed (~5 mg) in 113 114 standard aluminium pans (TA Instruments) and data acquisitions were carried out using the Universal Analysis 2000 program (TA Instruments). Samples were first dried using an isotherm at 105 °C for 1 115 minute followed by a cooling step at the rate of 10 °C/min. Then, samples were scanned under air 116 117 atmosphere between 20 °C and 110 °C at a heating rate of 10 °C/min. All experiments were repeated three times. The maximum temperature of 110 °C was chosen from the literature (Coppen and Hone, 118 119 1995; Gaillard et al., 2011). The experiment has been tested in a range from 5 °C to 200 °C, but no transition has been observed, as shown in Fig. 1. 120

121

Figure 1 : DSC thermogram of reference rosin in a range from 5 °C to 200 °C

122

2.6 Thermogravimetric analysis (TGA)

Thermal decomposition analysis of heat-treated rosin and the reference sample was performed by TGA (TA Instruments, Q20). Under flow of air at 60 ml/min, samples $(10.0 \pm 2.0 \text{ mg})$ of rosin were heated under temperature conditions ranging from 30 °C to 600 °C at a heating rate of 10 °C/min. An isotherm was kept for 20 min at 150 °C, in order to determine the turpentine amount in the rosin. All experiments were repeated three times.

128 2.7 Softening point measurement

129 According to ATSM E28-14, American standard for measuring this softening point, rosin is liquefied by heating before being cooled and solidified in a ring. This ring is placed in a beaker filled 130 131 with water, then a ball is placed on the solidified rosin, and the system is heated, until it liquefies. This causes the ball to fall through the rosin. The softening temperature is noted when the ball hits the 132 bottom of the beaker. However, this technique involves a first heat treatment of the rosin, to liquefy it 133 before measuring its softening point. Heat treatment has an influence on its softening properties. This 134 135 is why we opted to use a technique enhanced by Cabaret et al. (2018), where the softening point of the rosin was measured using TMA. Measurements were carried out using a TMA (Mettler Toledo, 136 SDTA840) and a standard probe. Samples with a thickness of 5 mm of heat-treated rosin and the 137 reference were prepared by breaking small pieces of hard rosin, without heating, and placed between 138 the probe and the support. A constant force of 0.02 N was applied and the sample was scanned at a 139 heating rate of 2 °C/min between 25 °C and 200 °C above the sample softening point. Thickness 140 141 measurements were performed each second with the shifting of TMA probe according to the thermal gradient. Thickness was measured each second and softening point temperature was determined at 100 142 143 µm, after the inflection point where the sample's height begins to quickly decrease due to the penetration of the probe. All experiments were repeated three times. 144

145 2.8 High-performance liquid chromatography (HPLC) analysis

All samples (1% w/v in methanol) were analysed by RP-HPLC-DAD (Ultimate 3000, Thermo Scientific) equipped with an Acclaim Polar Advantage II (3 mm x 150 mm, 3 μ m, Thermo Scientific), in methanol(A)/water(B) multi-gradient mode at 1 ml/min (injection volume 10 μ L). The gradient elution program was set as follows: 0-2 min.: (60%) A, 2-17 min.: (60-80%) A, 17-24 min. (80%) A, 24-35 min. (80-100%) A, 35-44 min. (100%) A. Then, the elution gradient was linearly ramped down to 60% A for 2 min. Finally, this gradient was maintained for 9 min in order to find the initial conditions of the column for the next injection. All experiments were repeated fifteen times.

153 2.9 Mechanical properties

154 2.9.1 Thickness

155 The thickness was measured in μm, using an ultrasonic coating thickness-measuring device156 (PosiTector 200). Three measurements were made on each panel.

157

2.9.2 Colour

The measurements were made using a spectrocoloremeter (X-rite, Ci62), according to the NF EN ISO 18314 standard. The colour was expressed using the CIEL*a*b* colour space, which expresses colour as three numerical values: L* for the lightness, a* for the green–red chromatic coordinate and b* for the blue–yellow chromatic coordinate. Three measurements were made on each panel.

163 2.9.3 Brightness

164 The brightness was measured at an angle of 60 °, using a glossmeter (Byk-Gardner, micro-tri-165 gloss), according to the NF EN ISO 2813 standard. Three measurements were made on each panel.

166 2.9.4 Adhesion

167 The measurements were carried out using a crosscut adhesion test kit (TQC), according to the 168 NF EN ISO 2409 standard. A grip with cutter was used to make two series of parallel cuts cross-169 angled with each other to obtain a pattern of 25 similar squares. The ruled area was evaluated after a 170 short treatment with adhesive tape, using a table chart from 0 to 5, 0 being the highest score (no 171 varnish removed from the substrate). Three measurements were made on each panel.

172

2.9.5 Solvent resistance

The solvent resistance was measured using a sodium hydroxide solution at 5 % mass fraction, according to the ISO 2812-4 standard. The panels were placed at a 30° angle from horizontal, and the solvent drops were applied every one or two seconds for 10 min through a burette. After the solvent application, the blistering was visually evaluated. Not according to the standard, it was decided to evaluate the colour and the brightness after the solvent application. Three measurement were made on each panel.

- 179
- 2.10 Principal Component Analysis (PCA) procedure

180 PCA helps to explain a data set with fewer linear combinations of the original variables, called principal components (PCs). The procedure is to find PCs that explain most of the variation in the 181 182 data. Extracted PCs are ordered in an increasing explained variance. PCs represent the linear combination of all variables included in the study. PCs are also called loadings because each original 183 variable is associated to weight (coefficient). All PCs are associated with the contribution of samples; 184 185 a score denotes this contribution. 186 A 12 x 17 matrix (where 12 is the number of samples, and 17 is the number of variables) was 187 used for the calculation. PCA on mean-scaled data was performed in R 3.6.0 (using RStudio Desktop 1.2.1335 interface) with FactoMineR (Lê et al., 2008) and Factoextra (Kassambara, 2017) packages. 188 189 The results of the analysis are presented in terms of Biplot. 3. Results and discussion 190 3.1 Thermal properties 191 192 3.1.1 Thermal degradation 193 The TGA thermograms of the reference and the heat-treated rosin are presented in Fig. 2. The raw rosin is used as a reference. 194 195 Figure 2 : TGA thermograms of rosin according to their heat treatment The weight loss at 150 °C corresponds to the turpentine fraction of the rosin, which will be 196 discussed in the chemical composition part of this paper. For all the samples, the main degradation 197 occurs at about 200 °C and finishes at about 350 °C, as observed by Kanerva et al. (2019). The final 198 mass loss observed with TGA for the reference and the heat-treated rosins are presented in Fig. 3. 199 200 Figure 3: Comparison of the final mass loss of rosin according to their heat treatment. The standard 201 deviation is calculated over 3 samples. 202 This final mass loss appears to be relatively unaffected by the heat treatment, which is 203 confirmed by the student test.

204	This observation is consistent with the mechanisms proposed by Artaki et al., (1992) at 250			
205	°C. In this study, this degradation observed at 250 °C corresponds to isomerization followed by			
206	dimerization, forming a mixture of dimeric diterpenes. In addition, under air, a mechanism of self-			
207	oxidation occurs through the formation of hydroperoxides, forming glycols, ketones and esters of			
208	varying molecular weights (Artaki et al., 1992). Finally, the degradation observed at 250 °C			
209	corresponds to the formation of new compounds through oxidation and isomerization, and not to the			
210	formation of small volatile molecules leading to a loss of mass. In our case the degradation caused by			
211	heat treatment (below 250 °C) does not lead to a different final mass loss, which is consistent with the			
212	study by Artaki et al., (1992). There is no relevant difference in the organic compounds/ashes ratio			
213	between the samples. The chemical composition will be checked with HPLC analysis.			
214	3.1.2 Softening point measurement			
215	The softening point is determined at 100 μ m after the bending point, which is when the sample			
216	thickness begins to shrink, due to the penetration of the TMA probe. Fig. 4 describes the thickness			
217	variation of all rosins, according to their heat treatment (raw for the reference, 180 °C, 200 °C and 250			
218	°C).			
219	Figure 4: Thickness variation against temperature for rosins according to their heat treatment			
220	The softening point temperatures, measured with TMA, of all rosins are shown in Fig.5.			
221 222	Figure 5: Comparison of the rosin softening point temperatures according to their heat treatment. The standard deviation is calculated over 3 samples.			
223				
224	The values are different to the values obtained by Coppen and Hone, using ASTM E28-14,			
225	which give softening points rather around 70 – 80 °C (Coppen and Hone, 1995). In addition, it appears			
226	that the softening temperature of the rosin increases with the treatment temperature, which is			
227	confirmed by the student test.			
228	Reference rosin (raw) has a significantly different softening point from thermally treated			

rosins. Heat treatment therefore increases the softening temperature of the rosin. This is consistent

with the observations of Cabaret et al. (2018), who showed that the rosin heated at 120 °C for 12 hours
might have a softening point 18 °C higher than that of the reference. This may be due to evaporation
of residual turpentine and/or chemical transformation of thermally treated rosin (with oxidation,
dehydrogenation and isomerization reactions). This will be checked with the turpentine amount
analysis by TGA and the composition analysis by HPLC.

235

3.1.3 Phase transition temperature measurement

Fig. 6 shows the DSC curves obtained for the reference and the heat treated rosin. A phase transition temperature is clearly observed between 45 and 60 °C according to their heat treatment.

238 Figure 6: DSC curves obtained for rosins according to their heat treatment

This transition had not previously been observed by Gaillard et al. (2011), because, according 239 to this study, the rosin is completely amorphous. In our experiments, the rosin is distilled and purified 240 with the patented process at low temperature and low pressure, which are not the same conditions as 241 Gaillard et al. (2011) experiments and can lead to a more homogeneous product. Its physico-chemical 242 properties can be different. Indeed, this transition has been observed by Cabaret et al. (2018) on 243 244 industrial rosin and acetone extractived rosin. This study shows that the transition phase temperature, comparable to glass transition according to Schilling (1989), can be observed when the rosin is 245 246 homogeneous.

247 The phase transition temperature of all rosins, reference and heat-treated, measured with DSC,248 are presented in Fig. 7.

Figure 7: Comparison of the rosin glass transition temperature according to their heat treatment. The
standard deviation is calculated over 3 samples.

According to the student test, all the phase transition temperatures, which can be compared to the glass transition temperature, are significantly different, except between the 200 °C and 250 °C heat-treated rosins. This confirms the previous results obtained on the softening point of the rosin: the heat treatment induces a softening, and thus a phase transition, at higher temperatures than for the reference. The following analysis of residual turpentine content and chemical composition may be used to validate the hypothesis of evaporation of residual turpentine, and/or a chemical transformation of the thermally treated rosin (always according to oxidation, dehydrogenation and isomerization mechanisms) leading to this phase transition to higher temperatures.

- 259 3.2 Chemical composition
- 260 3.2.1 Residual turpentine amount

The residual level of turpentine in the rosin was measured with TGA, where an isotherm at 261 262 150 °C was performed for 20 minutes to evaporate residual turpentine. As seen in Fig. 1, the weight loss at 150 °C corresponds to the residual turpentine. The turpentine starts boiling from 150 °C, due to 263 the boiling temperature of its major compounds: α-pinene between 154 °C and 159 °C and β-pinene 264 265 (between 156 °C and 166 °C) (Hawkins and Armstrong, 1954). Fig. 8 shows the amount of turpentine 266 in the rosin according to their heat treatment. Overall, all the rosin have a low turpentine amount, 267 under 3 %, and even lower with the increased heat treatment. However, these results show that the turpentine loss is not linear, the amount of turpentine being close between the heat-treated rosin. 268

Figure 8: Comparison of the turpentine amount in rosin according to their heat treatment. The standard deviation is calculated over 3 samples.

These results have been submitted to a student test, in order to evaluate the differences between them. According to this test, the raw rosin is significantly different from the heat-treated ones; the 180 °C heat-treated rosin is significantly different from the 250 °C heat-treated one, while the others heat-treated are not significantly different. Obviously, the residual turpentine is much lower after treatment at 180 °C and above, as its boiling point is between 150 °C and 180 °C. The small difference between 180, 200 and 250 °C can be explained by the difficulty to remove all the turpentine in the rosin (Cbaret et al., 2019).

The results obtained confirm the hypothesis of a lower level of turpentine for higher softening and phase transition temperatures. Glass transition temperature and softening point increase with heat treatment, and do not vary much for high processing temperatures, 200 °C and 250 °C. The opposite trend is observed with residual turpentine: it decreases with heat treatment, and does not vary much for high treatment temperatures. However, the residual turpentine amount of the 180 °C treated rosin is very close to the ones of the 200 and 250 °C treated rosins, whereas the phase transition temperatures of the 180 °C rosin is significantly different from the ones of the 200 and 250 °C treated rosins. Thus, the differences observed between the phase transition temperatures cannot be explained only by the evaporation of the turpentine. Indeed, heat treatment can also be affected by the chemical composition (Cabaret et al., 2018).

288

3.2.2 Abietane-based acids composition

All the rosin samples were analysed by HPLC, the raw rosin used as a reference, and the heattreated ones (at 180 °C, 200 °C and 250 °C). The chromatograms are presented in Fig. 9.

Figure 9: HPLC chromatograms at 254 nm wavelength absorption of rosins according to their heat

treatment. (1) 7-oxo-dehydroabietic acid (7–oxo–DHA), (2) Abietane-based dehydroabietic acid

293 (DHABA), (3) Dehydroabietic acid (DHA), (4) Palustric acid, (5) Abietic acid, (6) Neoabietic acid

Previous work by Cabaret et al., (2019) on rosin analysis by HPLC-MS, coupled with a comparison of UV profiles of compounds based on results from Kersten et al. (2007), allows the identification of the abietane-based acids and derivatives. Dehydroabietic acid (DHA) peak was assigned based on the study by Kersten et al. (2007). A second abietane-based dehydrogenic acid (DHABA) was also detected but could not be identified precisely. According to Cabaret et al. (2019) and (Pastorova et al., 1997), 7-oxo-dehydrobietic acid (7-oxo-DHA) was identified.

According to Ren et al. (2015), the hydroxyl group is formed first through the attack of
oxygen, resulting in the isomerization of the conjugated band. At the same time, the methylene is
converted to a hydroxyl intermediate by an oxygen atom.

In order to compare the different rosin samples, the surfaces of the different peaks, normalized
to 100, are calculated. With this technique, the concentration variation can be compared. The surfaces
are presented in table 1.

- Table 1: Comparison of abietane-based acids and derivatives contents in rosins according to their
 heat treatment. The standard deviation is calculated over 15 samples.
- 308 An apparition of dehydrogenated forms of abietane-based acids is noticed in heat-treated 309 rosins. For the DHA, this dehydrogenation leads to an aromatisation, and for the 7-oxo-DHA, it occurs 310 along with an oxidation. This has not been observed before, previous results presented by Cabaret et 311 al. (2018) only show heat-treated rosins, and the results presented by Kersten et al. (2006) show the 312 presence of DHA in reference rosin. Resin samples tested in Kersten et al. paper were obtained after 313 industrial distillation process during purification of Tall oil, which is a waste obtained from Kraft pulp. 314 This process might have been done at higher temperature than Biolandes process, and could be at the 315 origin of isomerization and degradation.

The presence of levopimaric acid was not observed. Classical acid portion of commercial pine oleoresin contains from 23 to 40 % levopimaric acid, which is completely isomerized to other resin acids during distillation (Loeblich et al., 1955). According to our study, this is probably due to the isomerization of levopimaric acid into palustric, abietic and neoabietic acids during the distillation process. The chromatogram obtained from levopimaric acid after heating at 155 °C for 3 hours by Loeblich et al. (1955) is presented in Fig. 10.

Figure 10: Chromatogram of levopimaric acid, heated at 155 °C for 3 hours, obtained by Loeblich, (1) palustric acid; (2) abietic acid; (3) neoabietic acid

The chromatogram closely resembles the one obtained in this study if we compare the reference and heat-treated rosins, with the same elution order. The palustric, abietic and neoabietic acids obtained here are therefore derived from the isomerization of levopimaric acid, which occurs during the hydrodistillation of the resin.

Cabaret et al., (2019) showed the presence of levopimaric, abietic and neoabietic acids in rosin obtained directly by heating the maritime pine resin at 60 °C and 90 °C, rosin that has not been hydrodistilled. In this study, the proportion of neoabietic acid is greater than the proportion of abietic and levopimaric acids, while palustric acid does not appear. We used a similar HPLC analysis program as was used by Cabaret et al. (2019). We were therefore able to compare the results. The hypothetical order of isomerization may be the following: levopimaric acid isomerises to abietic acid and neoabietic acid. At higher temperatures, that of hydrodistillation, levopimaric acid also isomerises to palustric acid, which, with neoabietic acid, isomerise in abietic acid, resulting in the disappearance of levopimaric acid and a higher proportion of abietic acid. The isomerisation pathways could be checked by comparing the spectra of pure palustric, abietic and neoabietic acids with the spectra of pure levopimaric acid heated at different temperatures.

These results also show that the Biogemme[®] hydrodistillation process, at low pressure and low
temperature, could have been done at a temperature higher than 90 °C.

The appearance of dehydrogenated and oxidized compounds of abietane-based acids, observed in thermally treated rosins, is associated with a decrease of abietane-based acids. Heat treatment can therefore cause dehydrogenation of the palustric, neoabietic and abietic acids in DHA and DHABA, lowering their proportions. Dehydrogenic acids also undergo oxidation, leading to the 7-oxo-DHA formation.

346 This analysis confirms the chemical transformation of rosin, which can affect phase transitions347 at higher temperatures observed in TMA and DSC.

- 348 3.3 Varnish properties
- 349 3.3.1 Physical properties

The film thickness, measured in the reference and the heat-treated rosins, is presented in table 2. The test is performed to ensure the homogeneity of the batch. According to the student test, the raw rosin is different from the heat-treated ones. It can be explained by the small standard deviation of this sample.

- Table 2 : Varnish colours according to the rosin heat treatment expressed using the CIELAB colour
 space. Three measurements were made on each of the three panels. The standard deviation is
 calculated over 9 measurements.
- 357 These results show that the film thickness is homogeneous with brush application.
- 358 The colours' measurements are presented in Fig. 11. No relevant difference is noticed, which 359 is confirmed by the student test.
- 360 *Figure 11: Varnish colours according to the rosin heat treatment expressed using the CIELAB colour*

361 space. Three measurements were made on each of the three panels. The standard deviation is
 362 calculated over 9 measurements.

363 Only one coordinate is different: the b* value is different for the varnish formulated if 364 compared with the reference. The varnishes formulated with the heat-treated rosins are more yellow, 365 which might be due to the rosin oxidation with heat treatment (observed with HPLC). Also, rosin is 366 known for having a yellowing effect (Domene-López et al., 2018).

- The brightness is presented in Fig. 12. It seems to decrease with the heat treatment, but, according to the student test, only the raw rosin is significantly different from the other ones. It means that in order to obtain a less brightening coating, rosin has to undergo heat treatment.
- 370 *Figure 12: Brightness variation at 60 ° for varnishes according to the rosin heat treatment. Three*
- 371 *measurements were made on each of the three panels. The standard deviation is calculated over 9*

measurements.

372

373

3.3.2. Mechanical properties

The adhesion performances are presented in Fig. 13. All varnishes present good adherence on wood, with no grade above 2. According to the student test, there is no significant difference between the samples.

- 377 Figure 13: Comparison of varnish adhesion on wood for varnishes according to the rosin heat treatment. Three measurements were made on each of the three panels. The standard deviation is 378 379

calculated over 9 measurements.

380 The solvent resistance, according to the standard, is evaluated with the apparition of blistering. 381 No blistering is noticed on the film, but a loss of brightness and a deepening is observed. The results 382 are presented in table 3.

Table 3: Comparison of brightness and colour loss after a solvent test for varnishes according to the 383 rosin heat treatment. Three measurements were made on each of the three panels. The standard 384 deviation is calculated over 9 measurements. 385

386 A noticeable loss of brightness and a change of colour are observed for every varnishes. For all the samples, the varnish is deeper, less green and less yellow. The difference in L* and a* is more 387 important for the heat-treated rosin, while the difference in b* and brightness is similar for all rosins. 388 389 These results show a lower solvent resistance for the heat-treated rosin, which may be due to a higher 390 solvent sensibility of the dehydrogenated and oxidized compounds of abietane-based acids.

391 3.4 PCA analysis

392 From thermal analysis, chemical analysis and varnish properties, and using the R Studio 393 software, a PCA was performed. The aim was to investigate some similarities and differences between 394 the samples, according to the rosin heat treatment, and the influence of the variables on each other.

PC1 and PC2 together represent 78 % of the total variability. The PC1 is mainly representative 395 (64,6%), and is based on the chemical differences in abietane-based acids and derivatives, the thermal 396 properties and some varnish properties (brightness, brightness loss, L* loss and b*). The PC2 is 397 representative of some colour characteristics (L*, a*). The representation of PC1 vs. PC2 shows the 398 variable position and their corresponding correlations. In fact, the variable position from one to 399 400 another can be correlated: their opposition means that these variables are inversely proportional.

The PCA biplot is presented in Fig. 14. The three representative values of the groups (nontreated rosin, 180 °C, 200 °C and 250 °C treated rosin) are represented in the same graphic as the variables.

404 Figure 14: Biplot: Projection of variables and samples onto the first two PCs. (1, 2, 3) for reference
405 rosin; (4, 5, 6), (7,8,9) and (10, 11, 12), respectively for 180 °C, 200 °C and 250 °C heat-treated rosin

The PC1 allows a good separation of the samples according to their heat treatment, with 64,6 % of the total variance: G1 (represented by the yellow point) is the raw rosin group, G2 (represented by the green point) is the 180 °C heat-treated rosin, G3 (represented by the blue point) is the 200 °C heat-treated rosin and G4 (represented by the deep blue point) is the 250 °C heat-treated rosin. This spatial distribution demonstrates the influence of the heat treatment on both the rosin properties and the varnish properties.

The first group (G1) is characterized by the presence of abietane-based acids without degradations, the varnish brightness and the high amount of turpentine left in the rosin. It is also characterized by a low softening point and a low glass transition temperature, along with a small amount of abietane-based acids with degradations. G2 is characterized by the same variables as G1, but less marked than G1. The characteristic variables of G3 are the softening point, the Tg and the presence of dehydrogenated and oxidized compounds of abietane-based acids. G4 has the same characteristic, but stronger than G3.

The PCA also shows the influence of the variables on each other. It is clear on the PC1 that the turpentine amount seems to have an impact on the glass transition and the softening point; when the amount of turpentine increases, the temperatures decrease. This allows a visual observation of the results obtained with the thermal analysis of the rosin. The dehydrogenated and oxidized form of abietic-based acid seems to have an influence on the brightness and the solvent resistance (brightness loss). Their presence causes a lower brightness, and a more important loss of brightness in the presence of solvent, which also allows a visual observation of the varnishes properties' results.

426 4. Conclusion

427 The heat treatment has an impact on thermal properties, as the softening point and a phase transition temperature, which can be compared to the glass transition temperature, increase with the 428 429 temperature. The turpentine amount, as expected, is lower when rosins are heated. The heat treatment 430 also causes the apparition of dehydrogenated and oxidised forms of abietane-based acid. For the first time, we have shown the presence of abietane-based acid only, without their degraded form in non-431 treated rosin, probably due to the innovative Biogemme[®] distillation process at low temperature. 432 433 However, the chemical composition changes could be further confirmed with elementary analysis for the C, O and H content. 434

This study shows the relevance of the rosin heat treatment for varnish formulation. The varnish films are less bright when formulated with heat-treated rosin. It can be interesting for the customer demand, which can change from a very bright to a natural aspect coating. However, the solvent resistance seems to decrease with the heat treatment, probably due to a higher sensibility of the dehydrogenated and oxidised forms of abietane-based acid to the sodium hydroxide solution.

The PCA allows us to have a spatial repartition of the samples groups, according to their results. In addition, some variables affect each other. Thanks to the PCA, the impact of the heat treatment on the thermal and the varnish properties, through the chemical composition change, can be observed visually.

444 From this study, a better understanding of the formulation aspect of bio-based varnishes with445 rosin can be expected.

446 Acknowledgements

We gratefully acknowledge the financial support from the Nouvelle Aquitaine region and the
Landes departmental council. This work was also funded by ANR-10-EQPX-16 XYLOFOREST
(Mont-de-Marsan). We gratefully acknowledge the support from our partner Holiste. We also
acknowledge Roxane Le Corre for the English editing.

451 Bibliography

- 452 Artaki, I., Ray, U., Gordon, H.M., Gervasio, M.S., 1992. Thermal degradation of rosin during high
 453 temperature solder reflow. Thermochimica acta 198, 7–20.
- Baldwin, D., Loeblich, V., Lawrence, R., 1958. Acidic Composition of Oleoresins and Rosins. Ind.
 Eng. Chem. Chem. Eng. Data Series 3, 342–346. https://doi.org/10.1021/i460004a036
- Berg, J.D.J. van den, 2002. Analytical chemical studies on traditional linseed oil paints, MolArt.
 FOM-Institute AMOLF.
- Blanche, C.A., Lorio, P.L., Sommers, R.A., Hodges, J.D., Nebeker, T.E., 1992. Seasonal cambial
 growth and development of loblolly pine: Xylem formation, inner bark chemistry, resin ducts, and
 resin flow. Forest Ecology and Management 49, 151–165. https://doi.org/10.1016/03781127(92)90167-8
- Byrdwell, W.C., Neff, W.E., 1999. Non-volatile products of triolein produced at frying temperatures
 characterized using liquid chromatography with online mass spectrometric detection. Journal of
 Chromatography A 852, 417–432. https://doi.org/10.1016/S0021-9673(99)00529-4
- Cabaret, T., Boulicaud, B., Chatet, E., Charrier, B., 2018. Study of rosin softening point through
 thermal treatment for a better understanding of maritime pine exudation. European Journal of Wood
 and Wood Products 76, 1453–1459. https://doi.org/10.1007/s00107-018-1339-3
- 468 Cabaret, T., Gardere, Y., Frances, M., Leroyer, L., Charrier, B., 2019. Measuring interactions between 469 rosin and turpentine during the drying process for a better understanding of exudation in maritime pine 470 wood used as outdoor siding. Industrial Crops and Products 130, 325-331. 471 https://doi.org/10.1016/j.indcrop.2018.12.080
- 472 Carson, P., Mumford, C., 2002. 6 Flammable chemicals, in: Carson, P., Mumford, C. (Eds.),
 473 Hazardous Chemicals Handbook (Second Edition). Butterworth-Heinemann, Oxford, pp. 178–227.
 474 https://doi.org/10.1016/B978-075064888-2/50007-4
- Chen, G.-F., 1992. Developments in the field of rosin chemistry and its implications in coatings.
 Progress in Organic Coatings 20, 139–167. https://doi.org/10.1016/0033-0655(92)80002-E

- 477 Cheniclet, C., 1987. Effects of Wounding and Fungus Inoculation on Terpene Producing Systems of
 478 Maritime Pine. J Exp Bot 38, 1557–1572. https://doi.org/10.1093/jxb/38.9.1557
- 479 Coppen, J.J.W., Hone, G.A., 1995. Gum naval stores, turpentine and rosin from pine resin. Food and
 480 Agriculture Organization of the United Nations 1–62.
- 481 de Viguerie, L., Payard, P.A., Portero, E., Walter, Ph., Cotte, M., 2016. The drying of linseed oil
- 482 investigated by Fourier transform infrared spectroscopy: Historical recipes and influence of lead
 483 compounds. Progress in Organic Coatings 93, 46–60. https://doi.org/10.1016/j.porgcoat.2015.12.010
- 484 Domene-López, D., M. M. Guillén, I. Martin-Gullon, J. C. García-Quesada, et M. G. Montalbán.
 485 2018. «Study of the Behavior of Biodegradable Starch/Polyvinyl Alcohol/Rosin Blends ».

Carbohydrate Polymers 202 (décembre): 299-305. https://doi.org/10.1016/j.carbpol.2018.08.137.

- 487 Echard, J.-P., Bertrand, L., von Bohlen, A., Le Hô, A.-S., Paris, C., Bellot-Gurlet, L., Soulier, B.,
- 488 Lattuati-Derieux, A., Thao, S., Robinet, L., Lavédrine, B., Vaiedelich, S., 2010. The Nature of the
- 489 Extraordinary Finish of Stradivari's Instruments. Angewandte Chemie International Edition 49, 197–
 490 201. https://doi.org/10.1002/anie.200905131
- 491 Echard, J.P., Malecki, V., 2014. Oil-Pinaceae resin varnish recipes in 15th-18th-century written
 492 sources. pp. 131–132.
- 493 Franceschi, V.R., Krokene, P., Christiansen, E., Krekling, T., 2005. Anatomical and chemical defenses
 494 of conifer bark against bark beetles and other pests Franceschi 2005 New Phytologist Wiley
 495 Online Library. New Phytol 367, 353–376.
- 496 Gaillard, Y., Mija, A., Burr, A., Darque-Ceretti, E., Felder, E., Sbirrazzuoli, N., 2011. Green material
- 497 composites from renewable resources: Polymorphic transitions and phase diagram of beeswax/rosin
- 498 resin. Thermochimica Acta 521, 90–97. https://doi.org/10.1016/j.tca.2011.04.010
- 499 Gilles, N., 2019. A method for cooking oil varnish. The Strad 130, 72–75.

- Hawkins, J.E., Armstrong, G.T., 1954. Physical and Thermodynamic Properties of Terpenes.1 III. The
 Vapor Pressures of α-Pinene and β-Pinene2. J. Am. Chem. Soc. 76, 3756–3758.
 https://doi.org/10.1021/ja01643a051
- Hawley, L.F., Palmer, R.C., 1912. Distillation of Resinous Wood by Saturated Steam. J. Ind. Eng.
 Chem. 4, 789–798. https://doi.org/10.1021/ie50047a003
- 505 Invernizzi, C., Daveri, A., Rovetta, T., Vagnini, M., Licchelli, M., Cacciatori, F., Malagodi, M., 2016.
- 506 A multi-analytical non-invasive approach to violin materials: The case of Antonio Stradivari "Hellier"
- 507 (1679). Microchemical Journal 124, 743–750. https://doi.org/10.1016/j.microc.2015.10.016
- Joye, N.M., Lawrence, R.V., 1967. Resin acid composition of pine oleoresins. J. Chem. Eng. Data 12,
 279–282. https://doi.org/10.1021/je60033a034
- 510 Kanerva, M., Puolakka, A., Takala, T.M., Elert, A.M., Mylläri, V., Jönkkäri, I., Sarlin, E., Seitsonen,
- J., Ruokolainen, J., Saris, P., Vuorinen, J., 2019. Antibacterial polymer fibres by rosin compounding
 and melt-spinning. Materials Today Communications 100527.
 https://doi.org/10.1016/j.mtcomm.2019.05.003
- Kassambara, A., 2017. Practical Guide To Principal Component Methods in R: PCA, M(CA), FAMD,
 MFA, HCPC, factoextra. STHDA.
- 516 Krokene, P., 2015. Conifer Defense and Resistance to Bark Beetles, in: Bark Beetles: Biology and
- 517 Ecology of Native and Invasive Species. Hofstetter RW, Vega FE, pp. 177–207.
- Lê, S., Josse, J., Husson, F., 2008. FactoMineR: An R Package for Multivariate Analysis. Journal of
 Statistical Software 25, 1–18. https://doi.org/10.18637/jss.v025.i01
- 520 Loeblich, V.M., Baldwin, D.E., O'Connor, R.T., Lawrence, R.V., 1955. Thermal Isomerization of
- 521 Levopimaric Acid. J. Am. Chem. Soc. 77, 6311–6313. https://doi.org/10.1021/ja01628a071
- 522 Moreira, X., Sampedro, L., Zas, R., 2009. Defensive responses of Pinus pinaster seedlings to
- 523 exogenous application of methyl jasmonate: Concentration effect and systemic response.
- 524 Environmental and Experimental Botany 67, 94–100. https://doi.org/10.1016/j.envexpbot.2009.05.015

- Narayanan, M., Loganathan, S., Valapa, R.B., Thomas, S., Varghese, T.O., 2017. UV protective
 poly(lactic acid)/rosin films for sustainable packaging. International Journal of Biological
 Macromolecules 99, 37–45. https://doi.org/10.1016/j.ijbiomac.2017.01.152
- Pastorova, I., van der Berg, K.J., Boon, J.J., Verhoeven, J.W., 1997. Analysis of oxidised diterpenoid
 acids using thermally assisted methylation with TMAH. Journal of Analytical and Applied Pyrolysis
 43, 41–57. https://doi.org/10.1016/S0165-2370(97)00058-2
- Pinto, I., Knapic, S., Pereira, H., Usenius, A., 2005. Simulated and realised industrial yields in sawing
 of maritime pine (Pinus pinaster Ait.). Holz als Roh- und Werkstoff 64, 30–36.
 https://doi.org/10.1007/s00107-005-0042-3
- Ren, Fan, Yan-Fei Zheng, Xiong-Min Liu, Xin-Yin Yue, Li Ma, Wei-Guang Li, Fang Lai, Jia-Ling
 Liu, et Wen-Long Guan. 2015. « An investigation of the oxidation mechanism of abietic acid using
 two-dimensional infrared correlation spectroscopy ». Journal of Molecular Structure 1084 (mars):
 236-43. https://doi.org/10.1016/j.molstruc.2014.12.055.
- Riesco Muñoz, G., Santaclara Estévez, Ó., Álvarez González, J.G., Merlo, E., 2014. Influence of
 provenance, silvicultural regime and tree shape on the quality of maritime pine (Pinus pinaster) timber.
 European Journal of Forest Research 133. https://doi.org/10.1007/s10342-014-0790-x
- 541 Rodríguez-García, A., López, R., Martín, J.A., Pinillos, F., Gil, L., 2014. Resin yield in Pinus pinaster
- is related to tree dendrometry, stand density and tapping-induced systemic changes in xylem anatomy.
- 543 Forest Ecology and Management 313, 47–54. https://doi.org/10.1016/j.foreco.2013.10.038
- 544 Rodríguez-García, A., Martín, J.A., López, R., Sanz, A., Gil, L., 2016. Effect of four tapping methods
- 545 on anatomical traits and resin yield in Maritime pine (Pinus pinaster Ait.). Industrial Crops and
- 546 Products 86, 143–154. https://doi.org/10.1016/j.indcrop.2016.03.033
- 547 Rosa, R., Soares, P., Tomé, M., 2018. Evaluating the Economic Potential of Uneven-aged Maritime
- 548 Pine Forests. Ecological Economics 143, 210–217. https://doi.org/10.1016/j.ecolecon.2017.07.009

- Scalarone, D., Lazzari, M., Chiantore, O., 2002. Ageing behaviour and pyrolytic characterisation of
 diterpenic resins used as art materials: colophony and Venice turpentine. Journal of Analytical and
- 551 Applied Pyrolysis 64, 345–361. https://doi.org/10.1016/S0165-2370(02)00046-3
- 552 Schilling, Michael R. 1989. « The glass transition of materials used in conservation ». Studies in
- 553 Conservation 34 (3): 110-16. https://doi.org/10.1179/sic.1989.34.3.110.
- 554 Soliño, M., Yu, T., Alía, R., Auñón, F., Bravo-Oviedo, A., Chambel, M.R., de Miguel, J., del Río, M.,
- 555 Justes, A., Martínez-Jauregui, M., Montero, G., Mutke, S., Ruiz-Peinado, R., García del Barrio, J.M.,
- 556 2018. Resin-tapped pine forests in Spain: Ecological diversity and economic valuation. Science of The
- 557 Total Environment 625, 1146–1155. https://doi.org/10.1016/j.scitotenv.2018.01.027
- 558 Tirat, S., Degano, I., Echard, J.-P., Lattuati-Derieux, A., Lluveras-Tenorio, A., Marie, A., Serfaty, S.,
- Le Huerou, J.-Y., 2016. Historical linseed oil/colophony varnishes formulations: Study of their molecular composition with micro-chemical chromatographic techniques. Microchemical Journal 126, 200–213. https://doi.org/10.1016/j.microc.2015.11.045
- Tirat, S., Echard, J.-P., Lattuati-Derieux, A., Le Huerou, J.-Y., Serfaty, S., 2017. Reconstructing
 historical recipes of linseed oil/colophony varnishes: Influence of preparation processes on application
 properties. Journal of Cultural Heritage 27, S34–S43. https://doi.org/10.1016/j.culher.2017.08.001
- Wang, J., Lu, C., Liu, Y., Wang, C., Chu, F., 2018. Preparation and characterization of natural rosin
 stabilized nanoparticles via miniemulsion polymerization and their pressure-sensitive adhesive
 applications. Industrial Crops and Products 124, 244–253.
 https://doi.org/10.1016/j.indcrop.2018.07.079
- Wold, S., Esbensen, K., Geladi, P., 1987. Principal component analysis. Chemometrics and Intelligent
 Laboratory Systems, Proceedings of the Multivariate Statistical Workshop for Geologists and
 Geochemists 2, 37–52. https://doi.org/10.1016/0169-7439(87)80084-9
- 572 Wu, H., Hu, Z., 1997. Comparative anatomy of resin ducts of the Pinaceae. Trees 11 132–143.
- 573

#	Molecule	Absorption max	Peak area	Peak area	Peak area	Peak area
		(nm)	ratio for	ration for	ration for	ration for
			Raw rosin	180 °C rosin	200 °C rosin	250 °C rosin
(1)	7-oxo-	255.6	0	1.6±0.4	2.0±1.1	6.5±4.6
	DHA					
(2)	DHABA	243.5	0	0.8±0.1	1.1±0.4	1.6±0.6
(3)	DHA	225.3/252/268	0	3.8±0.4	4.5±1.7	7.0±1.6
(4)	Palustric	268	11.4±1.8	9.9±1.8	9.5±2.0	9.0±2.5
(5)	Abietic	240.8	84.3±1.6	85.8±3.9	81.5±2.7	73.1±7.6
(6)	Neoabietic	252	4.1±2.3	5.0±0.8	3.4±0.8	1.1±1.4

 Table 1: Comparison of abietane based acids and derivatives contents in rosins according to their

 heat treatment. The standard deviation is calculated over 15 samples.

Table 2 : Varnish colours according to the rosin heat treatment expressed using the CIELAB colour space. Three measurements were made on each three panels. The standard deviation is calculated over 9 measurements.

Value	Raw	180 °C	200 °C	250 °C
L*	54.30±3.76	54.33±1.86	55.92±0.91	54.79±2.43
a*	17.26±2.85	16.78±1.04	16.07±0.71	16.81±1.17
b *	52.55±1.34	48.09±1.90	47.56±2.98	47.63±3.19

Table 3: Comparison of brightness and colour loss after a solvent test for varnishes according to the rosin heat treatment. Three measurements were made on each three panels. The standard deviation is calculated over 9 measurements.

Value	Raw	180 °C	200 °C	250 °C

L*	-7.3±2.4 %	-13.0±4.0 %	-15.1±0.6 %	-19.2±1.7 %
a*	+5.4±9.2 %	+9.8±4.3 %	+32.1±5.5 %	+15.0±5.9 %
b*	-26.9±1.1 %	-21.3±3.6 %	-19.3±2.1 %	-24.9±2.5 %
Brightness	-89.2±5.3 %	-92.2±7.2 %	-95.7±8.1 %	-96.2±16.1 %



Figure 1 : DSC thermogram of reference rosin in a range from 5 °C to 200 °C



Figure 2 : TGA thermograms of rosin according to their heat treatment



Figure 3: Comparison of the final mass loss of rosin according to their heat treatment. The standard deviation is calculated over 3 samples.



Figure 4: Thickness variation against temperature for rosins according to their heat treatment



Figure 5: Comparison of the rosin softening point temperature according to their heat treatment. The standard deviation is calculated over 3 samples.



Figure 6 : DSC curves obtained for rosins according to their heat treatment



Figure 7: Comparison of the rosin glass transition temperature according to their heat treatment. The

standard deviation is calculated over 3 samples.



Figure 8: Comparison of the turpentine amount in rosin according to their heat treatment. The standard deviation is calculated over 3 samples.



Figure 9: HPLC chromatograms at 254 nm wavelength absorption of rosins according to their heat treatment. (1) 7-oxo-dehydroabietic acid (7-oxo-DHA), (2) Abietane-based dehydroabietic acid (DHABA), (3) Dehydroabietic acid (DHA), (4) Palustric acid, (5) Abietic acid, (6) Neoabietic acid



Figure 10: Chromatogram of levopimaric acid, heated at 155 °C during 3 hours, obtains by Loeblich,

(1) palustric acid; (2) abietic acid; (3) neoabietic acid



Figure 11: Thickness variation for varnishes according to the rosin heat treatment. Three measurements were made on each three panels. The standard deviation is calculated over 9



measurements.

Figure 12: Brightness variation at 60 ° for varnishes according to the rosin heat treatment. Three measurements were made on each three panels. The standard deviation is calculated over 9

measurements.



Figure 13: Comparison of varnish adhesion on wood for varnishes according to the rosin heat treatment. Three measurements were made on each three panels. The standard deviation is calculated over 9 measurements.



Figure 14: Biplot : Projection of variables and samples onto the first two PCs. (1, 2, 3) for reference rosin; (4, 5, 6), (7,8,9) and (10, 11, 12), respectively for 180 °C, 200 °C and 250 °C heat-treated rosin

