



HAL
open science

Micropollutants removal from secondary-treated municipal wastewater using weak polyelectrolyte multilayer based nanofiltration membranes.

Seyed Mehran Abtahi, Shazia Ilyas, Claire Joannis-cassan, Claire Albasi,
Wiebe M. de Vos

► To cite this version:

Seyed Mehran Abtahi, Shazia Ilyas, Claire Joannis-cassan, Claire Albasi, Wiebe M. de Vos. Micropollutants removal from secondary-treated municipal wastewater using weak polyelectrolyte multilayer based nanofiltration membranes.. *Journal of Membrane Science*, 2018, 548, pp.654-666. 10.1016/j.memsci.2017.10.045 . hal-03510760

HAL Id: hal-03510760

<https://hal.science/hal-03510760>

Submitted on 4 Jan 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.






Open Archive TOULOUSE Archive Ouverte (OATAO)

OATAO is an open access repository that collects the work of some Toulouse researchers and makes it freely available over the web where possible.

This is an author's version published in : <http://oatao.univ-toulouse.fr/19778>

Official URL : <https://dx.doi.org/10.1016/j.memsci.2017.10.045>

To cite this version :

Abtahi, S. Mehran  and Ilyas, Shazia and Joannis Cassan, Claire  and Albasi, Claire  and De Vos, Wiebe M. *Micropollutants removal from secondary-treated municipal wastewater using weak polyelectrolyte multilayer based nanofiltration membranes.* (2018) *Journal of Membrane Science*, vol. 548. pp. 654-666. ISSN 0376-7388

Any correspondence concerning this service should be sent to the repository administrator :
tech-oatao@listes-diff.inp-toulouse.fr

Micropollutants removal from secondary-treated municipal wastewater using weak polyelectrolyte multilayer based nanofiltration membranes

S. Mehran Abtahi^{a,b}, Shazia Ilyas^{a,c}, Claire Joannis Cassan^b, Claire Albasi^b, Wiebe M. de Vos^{a,*}

^a Membrane Science and Technology, MESA + Institute for Nanotechnology, University of Twente, Faculty of Science and Technology, P.O. Box 217, 7500 AE Enschede, The Netherlands

^b Université de Toulouse, INPT, UPS, Laboratoire de Génie Chimique, 4 Allée Emile Monso, F31432 Toulouse, France

^c Urban Sector Planning & Management Services Unit. (Pvt.) Ltd. (The Urban Unit), 503-Shaheen Complex, Egerton Road, Lahore 54000, Pakistan

ARTICLE INFO

Keywords:

Polyelectrolyte multilayers
Micropollutants
Nanofiltration
Apparent rejection
Steady-state rejection

ABSTRACT

Nanofiltration (NF) is seen as a very promising technology to remove micropollutants (MPs) from wastewater. Unfortunately this process tends to produce a highly saline concentrate stream, as commercial NF membranes retain both the MPs and most of the ions. The high salinity makes subsequent degradation of the MPs in a bio-reactor very difficult. The main goal of this study is to prepare and study a NF membrane that combines a low salt rejection with a high MPs rejection for the treatment of secondary-treated municipal wastewater. This membrane was prepared using layer by layer (LbL) deposition of the weak polycation poly(allylamine hydrochloride) (PAH), and the weak polyanion poly(acrylic acid) (PAA), on the surface of a hollow fiber dense ultrafiltration (UF) membrane. The ionic strength of the coating solutions was varied and properties of the formed polyelectrolyte multilayers (PEMs), such as hydration, hydrophilicity, hydraulic resistance and ions retention were studied. Subsequently we tested the apparent and steady state rejection of MPs from synthetic wastewater under cross-flow conditions. The synthetic wastewater contained the MPs Diclofenac, Naproxen, Ibuprofen and 4n-Nonylphenol, all under relevant concentrations (0.5–40 µg/L, depending on the MP). PEMs prepared at lower ionic strength showed a lower hydration and consequently a better retention of MPs than PEMs prepared at higher ionic strengths. A strong relationship between the apparent rejection of MPs and their hydrophobicity was observed, likely due to adsorption of the more hydrophobic MPs to the membrane surface. Once saturated (steady state), the molecular size of the MPs showed the best correlation with their rejection, indicating rejection on the basis of size exclusion. In contrast to available commercial NF membranes with both high salt and MP rejection, we have prepared a unique membrane with a very low NaCl retention (around 17%) combined with a very promising removal of MPs, with Diclofenac, Naproxen, Ibuprofen and 4n-Nonylphenol being removed up to 77%, 56%, 44% and 70% respectively. This membrane would allow the treatment of secondary treated municipal wastewater, strongly reducing the load of MPs, without producing a highly saline concentrate stream.

1. Introduction

Over the last few years, a great concern has been highlighted regarding the occurrence of micropollutants (MPs) in aquatic resources and the subsequent effects on humans and the environment [1]. In addition to the 45 priority substances on the European Watch List (Directive, 2013) [2], an additional watch list of 10 priority substances that should be monitored within the European Union was recently included in Decision 495/2015/EU [3] indicating the growing attention to this issue. In this regard, effluents of wastewater treatment plants have been recognized as the main entry point of these compounds into the aquatic environment [4]. Conventional treatment methods do not

lead to sufficient removal of MPs, and adding additional steps during wastewater treatment is seen as the most promising way to reduce the release of these compounds into surface waters [5]. To date, identification of technically and economically feasible advanced wastewater treatment options for the elimination of MPs from secondary-treated effluent is ongoing. Adsorption processes, advanced oxidation processes (AOPs) and membrane filtration are important examples of such technologies. Among these options, listed in Table 1, membrane technologies such as nanofiltration (NF) and reverse osmosis (RO) have attracted a great interest because of high removal rates (> 90%) of low molecular weight MPs, excellent quality of treated effluent, modularity and the ability to integrate with other systems. On the other hand,

* Corresponding author.

E-mail address: w.m.devos@utwente.nl (W.M. de Vos).

Table 1
The most-frequently used treatment technologies for removal of MPs from secondary-treated municipal wastewater.

Category of tertiary treatment	Subcategory	Advantages	Disadvantages/limitations	References
Advanced oxidation processes (AOPs)	Ozonation	Remarkable capability for removing most of the pharmaceuticals and industrial chemicals It has been successfully applied in many full-scale applications in reasonable ozone dosages. This kind of system is attractive because it uses low-cost reagents, iron is abundant and a non toxic element and hydrogen peroxide is easy to handle and environmentally safe.	As O ₃ is a highly selective oxidant, ozonation often cannot ensure the effective removal of ozone-refractory compounds such as Ibuprofen. Ozonation produces carcinogenic bromate from bromide that exists in secondary-treated effluents.	[36] [36,37]
	Fenton oxidation		In this process, the low pH value often required in order to avoid iron precipitation that takes place at higher pH values. This process is not convenient for high volumes of wastewater in full-scale applications.	[2,38]
Adsorption processes	Heterogeneous photocatalysis with TiO ₂	The principle of this methodology involves the activation of a semiconductor (typically TiO ₂) due to its high stability, good performance and low cost by artificial or sunlight.	The need of post-separation and recovery of the catalyst particles from the reaction mixture in aqueous slurry systems can be problematic. The relatively narrow light-response range of TiO ₂ is one of the challenges in this process. This process is not convenient for high volumes of wastewater in full-scale applications.	[38]
	Photolysis under ultraviolet (UV) irradiation	Photo-sensitive compounds can be easily degraded with this method.	UV irradiation is a high-efficient process just for effluents containing photo-sensitive compounds. This process is not convenient for high volumes of wastewater in full-scale applications.	[38]
	Ultrasound irradiation (Sonolysis)	It is a relatively new process and therefore, has unsurprisingly received less attention than other AOPs. But it seems that this process is economically more cost-effective. It has been identified as powerful and easily adjustable technology to remove MPs.		The addition of H ₂ O ₂ to UV is more efficient in removing MPs than UV alone, but UV/H ₂ O ₂ is a viable solution for the transformation of organic MPs with low O ₃ and \cdot -OH reactivity. There are very few studies and consequently rare experience about sonolysis of the effluent MPs.
Membrane filtration	Adsorption processes with activated carbon	Large-scale trials have not only demonstrated excellent removal (> 80%) of a broad range of micropollutants, but also contributed to reducing the effluent toxicity.		
	RO and NF membranes	These processes have attracted a great interest because of higher removal rate of low molecular weight PSS, excellent quality of effluent, modularity and ability to integrate with other systems despite their fouling problems.	This process should be followed by a final polishing step (sand filtration or UF membranes) to retain adsorbed contaminants and spent activated carbon. So higher energy requirements of UF membrane and the relatively high carbon dosage (up to 20 mg/L) necessary to achieve the required MPs removal. In the case of "granular activated carbon", a regeneration process of the spent carbon is required, while spent "powdered activated carbon" must be incinerated or dumped after filtration process. High quantities of cations, anions, sulfate, MPs, etc. in the concentrate produced in NF and RO processes compel wastewater managers and decision makers to treat it with complicated processes specially in the case of full-scale applications. High energy consumption (about 4.7 and 3.4 kW h/m ³), high capital (334.3 and 338.2 \$/m ³ /d) and operational costs (0.72 and 0.57 \$/m ³) of RO and NF membranes, respectively, and their problematic fouling issues may preclude membrane treatment as an option.	[5] [6,40,41]

fouling is often a real problem for these membrane processes [6]. A lower energy consumption and higher permeate fluxes for NF membranes in comparison to RO membranes have encouraged the use of NF membranes for several commercial purposes, such as wastewater reclamation, water softening, and desalination [7,8]. Also for MPs removal, NF membranes are seen as a more cost effective alternative to RO membranes.

A major drawback of these pressurized membranes is the production of a waste stream (concentrate) which typically has a volume of up to 10–20% of the original wastewater volume [9]. This stream is rich in dissolved organic compounds, heavy metals and inorganic salts of Na^+ , Cl^- , Ca^{2+} , Mg^{2+} and SO_4^{2-} , and also contains the removed organic MPs [10]. Since the discharge of untreated concentrate poses a significant risk to the environment, increasing attention has been paid to this issue in recent years. Today, various methods exist for the disposal and management of concentrate produced from membrane plants such as discharge to surface water, wastewater treatment plants and deep wells, land application, and evaporation ponds. The removal of specific compounds from this unwanted stream may be performed by using activated sludge systems which are more cost-effective compared to other treatment options such as oxidation processes, adsorption or ion exchange [11–13]. The biological treatment of the concentrate stream strongly depends on its chemical composition which is often influenced by the membrane recovery rates (or expressed as the volume reduction factor) [11,14]. Azaïs et al. [14] investigated the chemical composition of the concentrate stream produced from NF90 membranes, treating secondary-treated wastewater, at different volume reduction factors (from 2 to 10). They reported the average composition of the NF concentrates: conductivity from 2 to 5.1 mS cm^{-1} , dissolved organic compound (DOC) from 12 to 48 mg L^{-1} , chemical oxygen demand (COD) from 49 to 180 mg L^{-1} , and MPs concentrations multiplied by a factor of 3–7 compared to those encountered in the secondary-treated wastewater. From this bibliographic review, there is still a lack of knowledge on the favorable concentration of MPs for their efficient biotic removal during the concentrate's biological treatment. Apart from that, the main limitation in biological treatment of the concentrate is its high salinity ($> 1\%$) which is harmful to the bacteria because the increased osmotic pressure damages bacterial cell walls (plasmolysis of the organisms at high salt concentrations) [9]. More information about detrimental levels of the salinity on the performance of activated sludge reactors is given in Section S1 in Supplementary data. Therefore, in the present work, we propose to make use of NF membranes with a much lower rejection of salts than most of the commercial NF membranes, with the aim to achieve easy and feasible biological treatment of the generated concentrate stream. For this purpose, one requires NF membranes with a low ion rejection ($< 30\%$) and a high rejection of MPs ($> 80\%$), a membrane that is currently not commercially available.

Recently, the development of better performing NF membranes has been an important on-going challenge, especially because a higher flux normally goes hand-in-hand with lower selectivity and vice versa. To achieve membranes with a high flux combined with a high selectivity, it is required to establish a thin and defectless separation membrane on top of a highly permeable and mechanically robust support [15]. To prepare such promising membranes, some techniques have been developed for membrane surface modification such as grafting and interfacial polymerization [16,17]. Since these processes are laborious, costly and rely on environmentally unfriendly solvents [18], the method chosen for this study is a polyelectrolyte layer by layer (LbL) deposition technique. In this approach, a substrate is alternatively exposed to polyanions and polycations to build polyelectrolyte multilayers (PEMs) of a controllable thickness [15]. Nowadays, the LbL adsorption of polyelectrolytes (PEs) is performed by some developed methods like dip-coating [19], spray coating [20] and spin coating [21] to make polyelectrolyte multilayer membranes. Indeed, PEM based membranes can be considered as functionalized membranes with a

strong potential for application in, for example, desalination [22], Heavy metals removal [23], alcohol/water separation [24], filtration of sludge supernatant [25] and recently in MPs removal [26,27]. In addition to the electrostatic interactions present in PEMs [28,29], other interactions such as hydrophobic interactions [30], hydrogen bonding [31] and chemical crosslinking [7] can play a role. As such, the choice of convenient PEs is the distinguished parameter that it affects all above-mentioned driving forces.

Apart from the choice of PEs, it has been demonstrated that multiple parameters such as pH, ionic strength, and charge density, can influence the LbL process and the resulting PEMs [32–34]. This versatility makes it possible to prepare PEM based membranes that are really optimized for a certain application. The application of PEMs-based membranes has been recently investigated in MPs removal by some researchers [26,27]. For the first time, Joris de Grooth et al. [26] obtained excellent retentions for both positively and negatively charged MPs in NF Membranes made by Polycation/Polyzwitterion/Polyanion Multilayers. Unfortunately, neutral and small micropollutants were hardly retained. Then, in the research of Ilyas et al. [27], a PEM based NF membrane made by LbL assembly of weak PEs was developed with interesting properties for the removal of MPs from wastewater effluents. The membrane combined a low ion rejection, with a good MP rejection (60–80%) even for small and neutral MPs, providing for the first time a membrane that could remove MPs without producing a highly saline waste stream. This membrane was only studied under ideal conditions and for unrealistically high MP concentrations (mg/mL). The performance under conditions relevant for wastewater treatment still needs to be studied.

In the present study, we aim to study the membrane developed by Ilyas et al. [27] under realistic conditions for municipal wastewater treatment, studying the ion rejection, and the rejection of relevant MPs within a complex water composition. Furthermore, we have continued to optimize the membrane performance by studying the impact of ionic strength on the properties of the formed PEMs in the case of salts and MPs retention. The polymers used here are two weak oppositely-charged PEs, with physical structures illustrated in Fig. 1, named Poly (allyl amine) hydrochloride (PAH) containing a primary amine ($-\text{NH}_3^+$) (weak cationic) and poly (acrylic acid) (PAA) with a weak anionic carboxylic acid group. The PEM based active separation layers were coated onto Hollow fiber dense UF membranes by LbL adsorption.

The removal of relevant MPs including three analgesic and anti-inflammatory pharmaceutical compounds (Diclofenac, Naproxen and Ibuprofen) and one endocrine disrupting compound (4n-Nonylphenol) from secondary-treated municipal wastewater was studied. The main objective of this study was to demonstrate the possibility to prepare LbL-made NF membranes with a high rejection of MPs and a low retention of salts from secondary-treated municipal wastewater. This strategy would lead to make membrane processes with a low-saline concentrate stream which is more convenient for the biological treatment in activated sludge systems.

2. Experimental

2.1. Chemicals

All chemicals used in this study including MPs (listed in Table 2








Fig. 1. Molecular structure of PAA and PAH used in this study [35].

Table 2
Physico-chemical characteristics of target MPs in this study [6,42,45,48,57–59].

Compound	CAS number	Formula	Molecular Weight (g mol ⁻¹)	Solubility in water at 25 °C (mg L ⁻¹)	Vapor pressure (mm Hg), at 25 °C	Boiling point (°C)	log K _{ow}	log D (pH:7)	pKa	Minimum Projection Area (Å ²)	Molar volume (cm ³ /mol)	Molecular dimension Length × Width × Height (nm)	Molecular structure
Diclofenac	15307-86-5	C ₁₄ H ₁₁ Cl ₂ NO ₂	296.15	2.4	1.59E-7	412 ± 45	4.548	1.77	4.18	43.3	182	0.829 × 0.354 × 0.767	
Naproxen	22204-53-1	C ₁₄ H ₁₄ O ₃	230.26	16	3.01E-7	404 ± 20	3.18	0.34	4.3	34.8	192.2	1.37 × 0.78 × 0.75	
Ibuprofen	15687-27-1	C ₁₃ H ₁₈ O ₂	206.28	21	1.39E-4	320 ± 11	3.97	0.77	4.47	35.4	200.3	1.39 × 0.73 × 0.55	
4n-Nonylphenol	104-40-5	C ₁₅ H ₂₄ O	220.35	6.35	8.53E-5	331 ± 11	6.142	6.14	10.15	NA	279.8	1.179 × 0.354 × 0.519	

NA: not available in literature.

with their physical and chemical properties), two weak PEs (PAH with $M_w = 15,000 \text{ g mol}^{-1}$ and PAA with $M_w = 15,000 \text{ g mol}^{-1}$), NaNO_3 as a background electrolyte, all salts (CaCl_2 , $\text{CaCl}_2 \cdot 2\text{H}_2\text{O}$, Na_2SO_4 , NaCl , K_2HPO_4 , $\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$), peptone, meat extract and urea) were obtained from Sigma–Aldrich. The concentration of PAH and PAA in PE solutions were always 100 mg L^{-1} with pH of 6 for both PEs and they were prepared in two ionic strengths of 5 and 50 mM NaNO_3 . By the way, for evaluating salt rejection, concentration of all salts in feed solution of all membranes were adjusted at 5 mM (CaCl_2 : 554.9, Na_2SO_4 : 710.2, and NaCl : 292.2 mg L^{-1}). Furthermore, Milli Q water (18.2 M $\Omega\text{-cm}$) was used to prepare PE and salts solutions, rinse and measure parameters including membranes permeability and resistance.

The hydrophobicity of MPs is expressed as the log D (logarithm of the octanol-water distribution coefficient), or the log K_{ow} (logarithm of the octanol-water partition coefficient). However, log D appears to be a better hydrophobicity indicator than log K_{ow} and can be used to evaluate the hydrophobicity of MPs at any pH value [42]. In this regard, compounds with log D > 2.6 are referred to as hydrophobic that prefer to accumulate in solid phases instead of being soluble in the aqueous phase, and hydrophilic when log D < 2.6 [43]. Hence, according to the values presented in Table 2 for log D, 4n-Nonylphenol is classified as hydrophobic, in contrast with the rest of MPs, and is therefore expected to adsorb to the surface of hydrophobic membrane surfaces by hydrophobic interactions.

Minimum projection area (MPA), calculated from the van der Waals radius, is defined as the smallest two-dimensional projection area of a three-dimensional molecule. By projecting the molecule on an arbitrary plane, two-dimensional projection area can be calculated and the process is repeated until the minimum of the projection area is obtained (Fig. 1S in Supplementary Data) [44,45].

2.2. Synthetic wastewater

Synthetic secondary-treated municipal wastewater was prepared according to the OECD protocol [46,47]. In order to make it, firstly, a mother stock solution was made in 1 L of tap water containing 160 mg peptone, 110 mg meat extract, 30 mg urea, 28 mg K_2HPO_4 , 7 mg NaCl , 4 mg $\text{CaCl}_2 \cdot 2\text{H}_2\text{O}$ and 2 mg $\text{MgSO}_4 \cdot 7\text{H}_2\text{O}$ [46,47]. Then the daughter stock solution was made in an effective volume of 5 L. This synthetic wastewater contained $50 \pm 2 \text{ mg L}^{-1}$ of COD, $10 \pm 1 \text{ mg L}^{-1}$ of total nitrogen (TN) and $1 \pm 0.1 \text{ mg P-PO}_4^{3-} \text{ L}^{-1}$. Moreover, daughter stock solutions of each target MP were prepared separately in Milli-Q water from their individual mother stock solutions, prepared in methanol at a concentration of 1 g L^{-1} . Regarding the review paper published by Luo et al. [48], and also on the basis of available data in literature about the concentration of target MPs in effluents of municipal wastewater treatment plants treated with conventional activated sludge systems (Fig. 2), final concentrations of Diclofenac, Naproxen, Ibuprofen and 4n-Nonylphenol in feed solution were considered 0.5, 2.5, 40 and $7 \mu\text{g L}^{-1}$, respectively. To avoid possible bacterial biodegradation and photodegradation, mother stock solutions of MPs were stored in amber glass bottles and kept in freezer ($-18 \text{ }^\circ\text{C}$) while synthetic wastewater and daughter stock solutions of MPs were prepared immediately before starting the filtration process in aluminum-wrapped glass containers.

2.3. COD, TN, and P-PO₄³⁻ measurements

Samples were firstly filtered through $0.45 \mu\text{m}$ glass fiber filters (Sartorius, Göttingen, Germany). Then, the analysis process were done using HACH LANGE kits for COD, TN, and P-PO_4^{3-} , along with DR3900 Benchtop VIS Spectrophotometer equipped with HT200S oven (HACH LANGE, Germany). These parameters were measured in duplicate and the average values were presented.




Fig. 2. Concentration range of target MPs in secondary-treated effluent of conventional wastewater treatment plants s found in literature (TS: This study, References: ^a [60], ^b [61], ^c [62], ^d [63], ^e [64], ^{f-g} [65], ^h [66], ⁱ [67], ^j [4], ^k [68], ^l [69], ^m [48], ^{n-o-p-q} [70], ^s [71], ^{t-u} [72], ^v [73], ^w [74], ^x [75], ^y [76], ^z [77]).

2.4. Membrane characteristics

Hollow fiber dense UF membranes (Hollow Fiber Silica (HFS)) with a molecular weight cutoff of 10 kDa and an inner diameter of 0.79 mm prepared from poly(ether sulfone) with a sulfonated poly(ether sulfone) separation layer (SPES) were kindly provided by Pentair X-Flow (The Netherlands). This membrane is designed for inside-out filtration. The presence of the anionic SO_3^- group on the sulfonated polymer backbone allows for a good adhesion of PEMs.

2.5. Preparation of PEMs via dip-coating

Dip-coating involves the sequential immersion of a given substrate into solutions with oppositely charged polyelectrolyte solutions, typically with one or more rinsing steps in between. By this simple procedure, transport of the polymer to the substrate surface is mainly based on diffusion. As we immerse the hollow fiber support membrane completely in the coating solution, PEs deposition is not limited to the inner surface of the membrane only and the whole porous structure can be coated by the PEs [49]. In this study, hollow fibers and silicon wafers were coated according to the protocol described by de Grooth et al. [50]. Considering the negatively charged surface of these membranes (zeta potential of -25 mV in 5 mM KCl [51]), the first applied polyelectrolyte should have an opposite charge, here PAH. In this study, we have used silicon wafers in order to follow the growth and thickness of adsorbed PEs which are difficult parameters to be monitored in coated HFS membranes.

Before coating, wetting of 20-cm hollow fibers were done in 15 wt% ethanol in water overnight. Then wet fibers were rinsed with deionized water three times followed by three times rinsing in the background electrolyte solution (NaNO_3). The used silica wafers were effectively cleaned by a 10-min plasma treatment using a low-pressure Plasma Etcher (Femto model) purchased from Diener Electronics, leading to a reproducible negative charge at the surface of all wafers.

Afterwards, fibers/wafers were completely immersed in a 0.1 g L^{-1} polycation solution (PAH) with a pH of 6 and ionic strengths of 5 or 50 mM NaNO_3 at room temperature. After 30 min, to remove polymer chains that are loosely attached to the pre-adsorbed polymer layer, fibers/wafers were rinsed in two separate solutions containing only NaNO_3 with an ionic strength similar to that of the coating solution for 15 min per solution. The rearrangement of the polymer chains that occurs during the rinsing step, leads to increased stability and improved thickness control [52]. Then to form the first bilayer of PAH/PAA, fibers/wafers were dipped for 30 min in 0.1 g L^{-1} polyanion solution (PAA) with pH of 6 and two ionic strengths of 5 or 50 mM NaNO_3 and

rinsed again in two separate background solutions exactly as before. This procedure was repeated up to the formation of 13 layers of PEs i.e. $(\text{PAH/PAA})_6\text{-PAH}$. After each step of coating, three samples of fibers/wafers were picked up for future experiments.

To avoid pore collapse, coated fibers were kept in glycerol/water (15 wt%/85 wt%) solution for at least 4 h and dried overnight under ambient conditions. These coated fibers were subsequently potted in single fiber plastic modules of 15 cm in length, with a hole in middle and two heads potted with an epoxy resin. Before filtration, these modules were put in deionized water overnight to help opening of blocked pores.

2.6. Spectroscopic ellipsometry (hydration measurement)

Ellipsometry is a very sensitive optical technique based on detecting the changes in polarization state of a light beam upon reflection from the sample of interest [53]. In the present work, dry and wet thicknesses of deposited multilayers on the surface of plasma-treated silicon wafers were measured using an in-situ Rotating Compensator Spectroscopic Ellipsometer (M-2000X, J. A. Woollam Co, Inc.) operated in a wavelength range from 370 to 920 nm at incident angles of 65° , 70° and 75° . Thickness measurements were calculated using the Cauchy model for ellipsometric parameters (ρ and Δ) and refractive index (n) was taken from independent measurements using a standard laboratory refractometer (Carl Zeiss). Finally, data obtained on three parts of each wafer were reported as a mean dry thickness \pm standard deviation [54], and subsequently hydration ratio (swelling degree) was determined using Eq. (1) by means of resulted wet thickness of multilayers [55].

$$\text{Hydration ratio} = \frac{d_{\text{swollen}} - d_{\text{dry}}}{d_{\text{dry}}} \quad (1)$$

Where, d_{swollen} is the wet thickness of multilayers measured in the presence of milli-Q water in nm, and d_{dry} is dry thickness of multilayers in nm.

2.7. Contact angle

In order to measure the hydrophilicity of coated fibers/wafers, optical contact angle measurements were performed on an OCA15 plus instrument (Dataphysics Inc.) using a sessile drop method. Sessile drops of $2 \mu\text{l}$ and $0.4 \mu\text{l}$ deionized water for coated wafers and fibers, respectively were used to measure the contact angle. The small droplets were essential to be able to obtain a reliable contact angle from the hollow fibers. The hollow fiber surface is curved, but for such a small




Fig. 3. Changes in hydraulic resistance of virgin and coated membrane ($\times 10^{14} \text{ m}^{-1}$) after deposition of each additional monolayer for PAH/PAA multilayers prepared in ionic strength of 50 mM NaNO_3 .

droplet the effect of curvature can be neglected when determining the contact angle. These measurements were carried out four times for each sample (at 20 °C), and the average and standard deviation are reported. The measurement was carried out five seconds after the bubble was placed on the surface of the wafers/fibers. We evaluated the hydrophilicity of coated wafers before and after immersion in the feed solution (synthetic wastewater containing target MPs) for 48 h, and coated fibers before and after filtration of the feed solution (see Section 2.8). Immersed silicon wafers were dried with nitrogen gas, and the fouled fibers were dried for 24 h at room temperature (20 °C) before the measurements.

2.8. Membrane performance

2.8.1. Water permeability & hydraulic resistance

To evaluate the water permeability and thereby the resistance of coated membranes, a lab-scale filtration system with dead-end mode was used. The pure water flux was measured at 20 °C with demineralized water at a trans-membrane pressure (TMP) of 1.5 bar (Eq. (2)). Then from the water flux, the membrane resistance was obtained using Eq. (3).

$$J = \frac{Q}{A_{\text{mem}}} \quad (2)$$

$$R = \frac{P}{\mu \times J} \quad (3)$$

Here, J is water flux in $\text{m}^3/\text{m}^2 \text{ s}$, Q is volume flow in m^3/s , A_{mem} is membrane area in m^2 , μ is the dynamic viscosity of the feed in Pa s, and P is the TMP in Pa. From each deposited layer of polymer, at least two modules were tested and the average of the permeability and resistance with standard deviation are reported.

2.8.2. Salts and MPs retention

For salts and MPs retention measurements, another lab-scale filtration set-up was used in a cross-flow mode at a TMP of 1.5 bar. The cross-flow velocity of the feed solution through the fibers was set at 4.5 m s^{-1} in order to reduce the effect of concentration polarization. This corresponds to a Reynolds number of approximately 3500, and is in the turbulent regime. We run the filtration set-up at extremely low recovery. That means that the concentration effect would be very small. In the case of wastewater filtration for MPs retention, membrane compaction was carried out at 1.5 bar for 2 h using demineralized water prior to feeding the filtration set-up with wastewater. Subsequently, permeate samples of the first 24 h of the filtration process were collected to measure the apparent rejection. Then a filtration

duration of 48 h was applied in order to provide sufficient membrane saturation to ensure steady state rejections, and a sample was taken after this time. Kimura et al., [56] observed quasi-saturation of the membranes after about a 20-h filtration of hydrophobic compounds at low concentration (~ 100 ppb). To avoid overestimation of compounds rejection, they proposed longer filtration times in order to reach adequate membrane saturation whenever low concentrations of solutes exists in the water.

Concentration values of all salts were measured with a Cond 3210 conductivity meter purchased from Wissenschaftlich-Technische Werkstätten GmbH. Each measurement was performed in triplet and the average of values with standard deviation is reported just for twelfth and thirteenth layers of polymer. Retention (Re) in % was calculated using Eq. (4).

$$\text{Re} = \left(1 - \frac{C_P}{C_F} \right) \times 100 \quad (4)$$

Where, C_P and C_F are solutes concentrations of permeate and feed solution, respectively.

For MPs analysis, samples of feed and permeate streams (duplicate samples) of the NF installation were shipped to the LaDrôme laboratory (in France) in a freeze box for analysis within 24 h under the analyzing license of COFRAC-ESSAIS. A multi detection procedure including Gas Chromatography (coupled with ECD/NPD mass spectrometry) and Liquid Chromatography (along with DAD, fluorescence, tandem mass spectrometry) was applied for all MPs with Limit of Quantification (LQ) of 0.01 $\mu\text{g}/\text{L}$ for Diclofenac, Naproxen and Ibuprofen, and 0.04 $\mu\text{g}/\text{L}$ for 4n-Nonylphenol. Then, as mentioned in Eq. (4), apparent (R_{app}) and steady-state rejection (R_{ste}) of MPs were determined.

3. Results and discussion

3.1. The hydraulic resistance of PEM based membranes

The hydraulic resistance of the PEM based membranes, prepared at an ionic strength of 50 mM NaNO_3 , were measured for each deposited layer to observe the transition from the pore dominated regime to the layer dominated regime [49]. As it can be seen in Fig. 3, the hydraulic resistance generally increases after an additional coating step, in line with the increasing PEM layer thickness. Initially, the smaller increment in hydraulic resistance from bare fiber until the fourth deposited layer (part a) indicates that firstly pores become narrower. Then, the much sharper increase is observed between layers 4–9 (part b), indicating the pores becoming fully filled with the PEM layer. After that, the resistance increases much slower again (part c), an increase simply related to the increasing thickness of the PEM coating. The sharp transition between layer 4 and 9 is a first clear indication of a transition from a pore dominated to a layer dominated regime. More evidence comes from the observed zig-zag behavior, which is related to the so-called odd-even effect. The final layer in a PEM can determine the degree of swelling of the whole layer, with PAH terminated layers being more swollen than PAA terminated layers. The change in swelling with different terminating layers leads to the zig-zag behavior. Initially, the resistance upon PAH adsorption (layer 3) shows a strong increase, which goes down when PAA is absorbed (layer 4). But for thicker layers (layer 12) PAA adsorption leads to an increase in resistance, while we see lower resistance for the 13th layer. This behavior (the flipping of the odd-even effect) also reflects a shift from the pore dominated regime to the layer dominated regime. In the pore dominated regime, the pores of the membrane are coated with the PEM, and an increase in swelling of that multilayer will result in a pore size decline and subsequently a reduced membrane permeability. While in the layer dominated regime, a dense layer is formed on top of the membrane and swelling of the layer leads to a more permeable layer and consequently a lower resistance [49]. From the observed behavior, we can be certain




Fig. 4. Comparison of ellipsometric dry thicknesses of each deposited layer in two ionic strengths of 5 and 50 mM NaNO₃.

that we are well within the layer dominated regime, and that any separation will be dominated by the PEM coating, rather than the original membrane pores.

3.2. The influence of ionic strength on the PEMs performance

To compare the properties of coated membranes at different ionic strengths, PEMs were also prepared at the lower ionic strength of 5 mM of NaNO₃. Lowering the ionic strength used for PEM preparation is known to lead to denser PEM layers, with better separation properties and lower permeabilities [50], but it has not been investigated for this type of polyelectrolyte system (PAH/PAA). Fig. 2S in Supplementary Data compares pure water permeabilities of the PEMs-based membranes made in this study with the common commercial UF, NF and RO membranes. In this figure, we show that permeability of our membranes is lower than UF and most of NF membranes, while it is mostly close to RO membranes. To compare the PEM growth under different conditions, ellipsometric thicknesses of PEMs on model surfaces along with hydraulic resistances of the prepared membranes were obtained.

Fig. 4 compares the dry thicknesses of adsorbed multilayers in two ionic strengths. After 13 layers, the PEM prepared at the lower ionic strength is about 2.3 times thinner than its counterpart. When polyelectrolyte assembly takes place at a low ionic strength, the polymer chains are more extended, resulting in a thinner film. Increasing the ionic strength results in the coiling of the chains, which become less extended but increase the volume of a multilayer [78]. The hydration of a PEM is a very important parameter to predict membrane performance, as it shows how open the layer structure is. The hydration ratio of PEMs consisting of 12 and 13 layers was determined from the measured wet and dry ellipsometric thicknesses as shown in Fig. 5. From this data, it is evident that PEMs prepared under lower ionic strength have a lower hydration, and therefore the layers will be expected to act as a denser membrane. This is also observed from the measured hydraulic resistance (Fig. 6). While the layers prepared under higher ionic strength are about 2.3 times thicker, the resistance is only 1.5 or 1.25 times higher. As the resistance linearly scales with the thickness of a layer, this must mean that the PEMs prepared at 5 mM are denser and are expected to have a better separation performance.

3.3. Contact angle of PEMs

In Fig. 3S in Supplementary Data, we clearly show variations in the water contact angle among both positively and negatively-charged PEMs with two ionic strengths of 5 and 50 mM NaNO₃. A decrease in




Fig. 5. Hydration, dry and wet thicknesses of membranes coated with (PAH/PAA)₆ and (PAH/PAA)₆-PAH multilayers in two ionic strengths of 5 and 50 mM NaNO₃.




Fig. 6. Hydraulic resistance of membranes ($\times 10^{14} \text{ m}^{-1}$) coated with (PAH/PAA)₆ and (PAH/PAA)₆-PAH multilayers in two ionic strengths of 5 and 50 mM NaNO₃.

contact angle was obtained after deposition of PEs (For instance $42.2 \pm 1.6^\circ$ and $42.4 \pm 1.5^\circ$ for silicon wafers and fibers, respectively coated with (PAH/PAA)₆ multilayers in 5 mM of NaNO₃) compared to bare HFS fiber that had a contact angle of $67.3 \pm 0.3^\circ$. This phenomenon indicates that multilayers adsorption imparts hydrophilicity to the membrane surface. This finding is in accordance with study performed

by Fadhillah et al., [35] who verified PSF membrane with PAH/PAA multilayers where the decrease in contact angle was resulted after 60 bilayers ($35.48 \pm 6.38^\circ$) compared to bare PSF substrate with a contact angle of 79.8° . Membranes with hydrophilic surfaces are less susceptible to fouling and their fouling is often reversible [79]. This is due to membrane hydration by water molecules which act as a barrier for potential foulants. Furthermore, these water soluble PEs form loops and tails which increase surface charge density. This rise in surface charge density contributes in the hydrophilicity of the membrane [80]. There was a small amount of increase in the hydrophilicity of coated silicon wafers after a 48-h immersion in synthetic wastewater containing target MPs. This reduction in contact angle did not change after re-immersing them in milli-Q water for another 48 h, indicating that this change is irreversible. In a similar trend, contact angles of coated fibers declined a little after filtration of feed solution e.g. contact angles of clean and fouled fibers were $42.4 \pm 1.5^\circ$ and $36.3 \pm 0.9^\circ$, respectively for (PAH/PAA)₆ multilayers coated with ionic strength of 5 mM NaNO₃. To the best of our knowledge, no literature data are available on contact angle changes after MPs rejection by NF membranes fabricated with PEMs, making comparison with the results of this study difficult.

3.4. Salts retention

PEM-based membranes, fabricated by the LbL assembly of PEs on hollow fiber support membranes, have been employed for ion rejection applications such as water softening or desalination [8]. In the category of NF membranes prepared with this method, membranes with high rejections of divalent ions and typically still significant rejections of monovalent ions have been studied [18]. Typically such membranes have two separation mechanisms (i) sieving in the case of species bigger than the membrane pore size and (ii) electric repulsion due to Donnan and dielectric effects in the case of charged species [81]. In the present work, the ion rejections were measured for three different ion pairs, namely NaCl, CaCl₂ and Na₂SO₄ at a concentration of 5 mM for all compounds. The results are presented in Fig. 7. For the both negatively and positively-charged membranes, the highest retention is obtained for the ion pair with the large SO₄²⁻ ion and a lower rejection is found for Ca²⁺ and Cl⁻ (the size order of the used ions is: SO₄²⁻ > Ca²⁺ > Cl⁻ > Na⁺ [82]). On the other side, a higher SO₄²⁻ rejection is seen in negatively-charged membranes compared to the PAH-terminated membranes. This trend is also observed in the case of Ca²⁺ rejection, but with a lower difference between PAA and PAH-terminated membranes. This behavior, next to the fact that a little difference is observed between the membranes prepared at two ionic strengths, indicates that size exclusion followed by charge repulsion are

the main mechanisms involved in salts retention by these membranes.

Fig. 7 also indicates that fibers coated with lower ionic strength have a somewhat higher salt rejection than membranes coated at higher ionic strength. For instance, Na₂SO₄ rejections of (PAH/PAA)₆ multilayers for ionic strengths of 5 and 50 mM NaNO₃ are $64.7 \pm 3.5\%$ and $59.0 \pm 0.9\%$, respectively. This behavior comes from this fact that PEMs prepared under lower ionic strength have a more compact structure (lower hydration ratio illustrated in Fig. 5) with less open multilayers leading to better retention. The most important result shown in this figure, however, is that we have prepared a NF membrane with a very low ionic rejection, similar to the results of Ilyas et al. [27]. As mentioned, a low ion rejection would be highly beneficial; as such membranes would not create a brine waste stream. Still the low ion rejection is only relevant, if the MPs rejection of these membranes under conditions relevant to wastewater treatment, is high enough.

3.5. MPs rejection

The apparent and steady-state retention of MPs from synthetic secondary-treated wastewater was examined under filtration circumstances similar to those for the salts rejection tests. Then, relationships between physicochemical properties of MPs and their rejections were evaluated.

3.5.1. Apparent MPs rejection

In Fig. 8a, we report on the apparent rejection of our four target MPs for PAA and PAH terminated PEM membranes, prepared at 5 and 50 mM NaNO₃. The apparent rejection of the hydrophobic 4n-Nonylphenol is the highest for all cases, followed by Diclofenac and then Ibuprofen and Naproxen. Of the membranes, the PAA terminated membranes perform better than the PAH terminated membranes. This effect was also observed by Ilyas et al. [27] and was attributed to PAA terminated layers being more dense in nature. Another way to densify the membrane is by lowering the ionic strength of preparation, as also discussed in Section 3.2. In apparent rejection, adsorption of MPs to the membrane can significantly affect the results. That means that affinity between the membrane and the MPs can be a crucial parameter. We investigated the connection between the rejection and some of the molecular properties of the MPs (Fig. 9 and Fig. 4S in Supplementary Data). In this matter, a linear increase ($R^2 = 0.9$) between hydrophobicity (log D) and apparent rejection of all MPs was observed (Fig. 9). Additionally, no strong relation was found between the apparent rejection of MPs and their correspondent molecular weight and molecular sizes (molecular volume and molar volume) (Fig. 4S in Supplementary Data). This gives a strong indication that affinity dominates the apparent rejection, with more hydrophobic MPs adsorbing more to the membrane surface. This can be due to the PEM layer, but more likely the adsorption takes place to the more hydrophobic PES support membrane.

3.5.2. Steady-state MPs rejection

In comparison with apparent rejection, the steady state rejections are lower for all investigated membranes (Fig. 8b). After reaching to steady-state condition, the membrane does not take up any MPs by adsorption, and other rejection mechanisms become dominant. This reduction is the most severe for the hydrophobic 4n-Nonylphenol (e.g. from $90.7 \pm 0.1\%$ to $70.1 \pm 2.3\%$ for 5 mM of NaNO₃ and (PAH/PAA)₆ multilayers), and is less notable for hydrophilic compounds. Consequently, in line with the findings of Yangali-Quintanilla et al. [59], we are not able to consider hydrophobic adsorption of MPs into the membrane surface as a long term rejection mechanism because diffusion through the membrane occurs over the time causing retention decedance after saturation of the membrane [59].

When comparing our prepared membranes, we again find that the membrane prepared at 5 mM and terminated with PAA outperforms the other membranes, although the effect is relatively small. The separation




Fig. 7. Single salt rejection of HFS membranes coated with (PAH/PAA)₆ and (PAH/PAA)₆-PAH multilayers in two ionic strengths under cross-flow filtration, at turbulent regime (Reynold number > 3500) and TMP of 1.5 bar.




Fig. 8. Apparent (a) and steady-state rejection (b) of MPs in membranes coated with (PAH/PAA)₆ and (PAH/PAA)₆-PAH multilayers (pH: 6/6 for both PEs) in two ionic strengths of 5 and 50 mM NaNO₃.

layer of this membrane is less hydrated compared to the others. In Fig. 8b we also show the rejection performance of the both (PAH/PAA)₆ and (PAH/PAA)₆-PAH multilayers prepared under two ionic strengths in accordance with those observed for the salt rejection. On one hand, the rejection performance of the membranes prepared at 5 mM NaNO₃ is still somewhat higher for all MPs as a result of lower hydration compared with its counterpart described in Section 3.2. For instance, rejection of Diclofenac for (PAH/PAA)₆ multilayers was $76.9 \pm 1.1\%$ versus $65.8 \pm 1.2\%$ for 5 and 50 mM NaNO₃, respectively. On the other side, in the case of the PAA-terminated PEMs, rejection mechanism of charge repulsion observed for negatively-charged MPs as though these negative-surface membranes showed about 32%, 24% and 20% of higher retention for Diclofenac, Naproxen and Ibuprofen, respectively than PAH-terminated PEMs for ionic strength of 5 mM NaNO₃. This evidence is what we saw in the case of SO₄²⁻ rejection by negatively-charged membrane. The higher rejection even also occurred for neutral 4n-Nonylphenol probably as a result of more-dense surface of PAA-terminated PEMs compared with PAH-terminated ones. As there is no charge involved in the rejection of 4n-Nonylphenol, we believe that its steady-state rejection is fundamentally based on size exclusion and still hydrophobic adsorption. Jermann et al., [83] indicated that Ibuprofen (up to 25%) and Estradiol (up to 80%) can be removed in hydrophobic UF membranes via adsorption onto membrane polymers, as well as interaction with natural organic matter in wastewater. Furthermore, it seems that long-shaped molecular geometry of 4n-Nonylphenol should be also taken into account in the retention adequacy since it can easily pass through the membrane's pores.

Relationship between steady-state rejection of MPs and their

relevant molecular weights (Fig. 10) represent that compounds of larger molecular weights are relatively better rejected even though the R-squared values of these linear curves are not gratifying. Meanwhile, as shown in Fig. 5S in Supplementary Data, parameters of log D, molecular and molar volume did not show striking correlation with steady-state rejection of all MPs. These results are in full agreement with the outcomes of Van der Bruggen et al. [84] who concluded that molecular weight can be a convenient representative of NF performance for retention of a series of organic molecules (molecular weight of 32–697 g mol⁻¹ and stokes diameter of 0.51–2.65 nm) compared with other molecular sizes.

In addition, as plotted in Fig. 11, we could also find a good correlation ($R^2 = 0.70$ – 0.97) between the steady-state rejection of charged MPs with their relevant MPA. Although the MPA was found as a better surrogate parameter in comparison to molecular weight, we do believe that much more research needs to be done to understand the MPs rejection by LbL-made NF membranes. In the case of commercial membranes, Fujioka et al. [85] reported that the rejection of charged MPs is high (over 90%) by hollow fiber cellulose triacetate RO membranes when the MPA of the compounds is over 35 Å² like this study. Conversely, there was not a strong correlation between the rejection of charged MPs and their MPA by the ceramic NF membranes in the observations of Fujioka et al. [44]. Kiso et al. [86], who investigated the effect of molecular shape on rejection of uncharged organic compounds, concluded that molecular width is a major factor controlling solute permeation in NF membranes. Similarly, Madsen and Sogaard [87] obtained the best relationships between the pesticides rejection by NF membranes and their molecular width. Hence, it seems that spatial




Fig. 9. The correlation between apparent rejection and hydrophobicity of MPs (Left and right figures are related to (PAH/PAA)₆ and (PAH/PAA)₆-PAH multilayers, respectively).




Fig. 10. The correlation between steady-state rejection and molecular weight of MPs (Left and right figures are related to (PAH/PAA)₆ and (PAH/PAA)₆-PAH multilayers, respectively).

dimensions that determine the movement and rotation of the molecules outperform the molecular weights in the rejection behavior of the membranes. Having a look at the 4n-Nonylphenol's molecular shape (Table 2) shows the long-shaped geometry of this molecule should be taken into account in the retention adequacy since it could easily pass through the membrane's pores.

3.5.3. Comparison of LbL-made NF membranes with commercial NF membranes in salts and MPs removal

When we now combine the data from Figs. 7 and 8b, we find that we have indeed prepared a membrane (PAA-terminated PEMs, prepared at 5 mM NaNO₃) with a very reasonable removal of MPs (around 45–80%) under relevant conditions for wastewater treatment, with and a very low ionic rejections (nearly 17% NaCl). It becomes clear how unique this membrane is when we compare our results to commercial NF membranes that have been applied to MPs removal. In Fig. 12, we compare the rejection of target MPs and NaCl simultaneously from commercial NF membranes found in literature and our best LbL-made NF membranes. More details about the type of feed, membrane and operational conditions are given in Table 1S in Supplementary Data. This data shows clearly that commercial NF membranes reject both MPs and salts to a great extent while the membranes prepared in this study rejected salts only slightly and MPs considerably. For example, commercial NF membranes could retain NaCl and Diclofenac up to 70–90% and 99–100%, respectively while these rejections have occurred by $16.8 \pm 1.6\%$ and $76.9 \pm 1.1\%$, respectively for our PEMs. Thus, a big advantage of our LbL-made NF membrane is that it could be used for MPs removal without producing a salty concentrate. Compared to the commercial membranes, that have been optimized towards high Donnan and Di-electric exclusion, we believe that size exclusion is the dominant mechanism for MP removal with our LbL based membranes.




Fig. 12. Simultaneous rejection of target MPs and NaCl using commercial NF membranes found in literature (Table 1S in Supplementary Data), and LbL-based NF membranes made with (PAH/PAA)₆ multilayers prepared in ionic strength of 5 mM NaNO₃.

Still, the exact separation mechanism will need to be studied in much more detail in the future. We strongly expect that with further optimization, for example by coating at even lower ionic strengths, that even higher MPs removals can be attained at still low NaCl rejections. This makes this type of membrane very interesting for use as a tertiary treatment step for wastewater treatment plants, of which the concentrate can be treated in a bioreactor as discussed in the introduction.




Fig. 11. The correlation between steady-state rejection and MPA (Å²) of charged MPs (Left and right figures are related to (PAH/PAA)₆ and (PAH/PAA)₆-PAH multilayers, respectively).

Moreover, as the salt balance of the effluent will not be changed dramatically after passing through these PEMs-based membranes, the effluent could be used for the irrigation of agricultural crops that are sensitive to salinity balance of the water used [88,89].

4. Conclusion

The scientific community is currently faced with the important challenge of MPs accumulation in aquatic environments. For this reason, various tertiary treatment methods are proposed to efficiently remove MPs from the wastewater effluent. In the present work, we provide further insights into the key parameters involved in apparent and steady-state rejections of MPs by NF membranes made with LbL adsorption of weak PEs on the surface of hollow fiber UF membrane. In addition, the effect of ionic strengths on the properties of PEMs was studied as this parameter determines the charge compensation of the PEs in the multilayer [49] and thereby the hydration and the effective pore size of the membrane. Here, we prove that PEMs prepared in lower ionic strength and terminated with PAA are more efficient in salts and MPs removal as they were found to be thinner and less open. We also demonstrate that it is possible to achieve good MPs rejections at realistic wastewater treatment conditions, combined with low ionic rejections. Lower rejection of salts will be much more favorable for biological treatment of the retentate stream. In addition, these membranes do not significantly disturb the salinity balance of the effluent, making the filtered effluent much more appropriate for use, for example, irrigation water. Considering these capabilities, low ion retentions and high MPs retentions would possibly enable these membranes to outperform currently available commercial NF membranes for MPs removal from municipals wastewater effluents.

Acknowledgments

The authors and persons involved in this project want to express their gratitude towards the R & D section of the Veolia Company especially Mr. Thierry Trotouin, and the European Commission – Education, Audiovisual and Culture Executive Agency (EACEA), for the PhD grants under the EUDIME Program (Doctoral contracts Nos. 2014-122 and 2011-0014).

Appendix A. Supplementary material

Supplementary data associated with this article can be found in the online version at <http://dx.doi.org/10.1016/j.memsci.2017.10.045>.

References

- [1] M.O. Barbosa, N.F.F. Moreira, A.R. Ribeiro, M.F.R. Pereira, Occurrence and Removal of Organic Micropollutants: An Overview of the Watch List of EU Decision 2015/495, 94, 2016. (<http://dx.doi.org/10.1016/j.watres.2016.02.047>).
- [2] A.R. Ribeiro, O.C. Nunes, M.F.R. Pereira, A.M.T. Silva, An overview on the advanced oxidation processes applied for the treatment of water pollutants defined in the recently launched Directive 2013/39/EU, *Environ. Int.* 75 (2015) 33–51, <http://dx.doi.org/10.1016/j.envint.2014.10.027>.
- [3] R. Mailler, J. Gasperi, Y. Coquet, A. Buleté, E. Vulliet, S. Deshayes, S. Zedek, C. Mirande-bret, Removal of a wide range of emerging pollutants from wastewater treatment plant discharges by micro-grain activated carbon in fluidized bed as tertiary treatment at large pilot scale, *Sci. Total Environ.* 542 (2016) 983–996, <http://dx.doi.org/10.1016/j.scitotenv.2015.10.153>.
- [4] J. Margot, C. Kienle, A. Magnet, M. Weil, L. Rossi, L. Felipe, D. Alencastro, C. Abegglen, D. Thonney, N. Chèvre, M. Schärer, D.A. Barry, Treatment of micropollutants in municipal wastewater: ozone or powdered activated carbon? *Sci. Total Environ.* 461–462 (2013) 480–498, <http://dx.doi.org/10.1016/j.scitotenv.2013.05.034>.
- [5] F. Bonvin, L. Jost, L. Randin, E. Bonvin, T. Kohn, Super-fine powdered activated carbon (SPAC) for efficient removal of micropollutants from wastewater treatment plant effluent, *Water Res.* 90 (2016) 90–99, <http://dx.doi.org/10.1016/j.watres.2015.12.001>.
- [6] M. Taheran, S.K. Brar, M. Verma, R.Y. Surampalli, T.C. Zhang, J.R. Valero, Membrane processes for removal of pharmaceutically active compounds (PhACs) from water and wastewaters, *Sci. Total Environ.* 547 (2016) 60–77, <http://dx.doi.org/10.1016/j.scitotenv.2015.12.139>.

- [7] L.Y. Ng, A.W. Mohammad, C.Y. Ng, A review on nanofiltration membrane fabrication and modification using polyelectrolytes: effective ways to develop membrane selective barriers and rejection capability, *Adv. Colloid Interface Sci.* 197–198 (2013) 85–107, <http://dx.doi.org/10.1016/j.cis.2013.04.004>.
- [8] O. Sanyal, Z. Liu, B.M. Meharg, W. Liao, I. Lee, Development of polyelectrolyte multilayer membranes to reduce the COD level of electrocoagulation treated high-strength wastewater, *J. Membr. Sci.* 496 (2015) 259–266, <http://dx.doi.org/10.1016/j.memsci.2015.09.011>.
- [9] A. Kemperman, H. Temmink, A. Zwijnenburg, C. Kappel, H.H. Rijnaarts, K. Nijmeijer, Impacts of NF concentrate recirculation on membrane performance in an integrated MBR and NF membrane process for wastewater treatment, *J. Membr. Sci.* 453 (2014) 359–368, <http://dx.doi.org/10.1016/j.memsci.2013.11.023>.
- [10] S. Jamil, S. Jeong, S. Vigneswaran, Application of pressure assisted forward osmosis for water purification and reuse of reverse osmosis concentrate from a water reclamation plant, *Sep. Purif. Technol.* 171 (2016) 182–190, <http://dx.doi.org/10.1016/j.seppur.2016.07.036>.
- [11] P. Chelme-ayala, D.W. Smith, M.G. El-din, Membrane concentrate management options: a comprehensive critical review, *Can. J. Civ. Eng.* 36 (2009) 1107–1119, <http://dx.doi.org/10.1139/L09-042>.
- [12] Z. Jeirani, A. Sadeghi, J. Soltan, B. Roshani, B. Rindall, Effectiveness of advanced oxidation processes for the removal of manganese and organic compounds in membrane concentrate, *Sep. Purif. Technol.* 149 (2015) 110–115, <http://dx.doi.org/10.1016/j.seppur.2015.05.009>.
- [13] P. Liu, H. Zhang, Y. Feng, F. Yang, J. Zhang, Removal of trace antibiotics from wastewater: a systematic study of nanofiltration combined with ozone-based advanced oxidation processes, *Chem. Eng. J.* 240 (2014) 211–220, <http://dx.doi.org/10.1016/j.cej.2013.11.057>.
- [14] A. Azais, J. Mendret, E. Petit, S. Brosillon, Influence of volumetric reduction factor during ozonation of nanofiltration concentrates for wastewater reuse, *Chemosphere* 165 (2016) 497–506, <http://dx.doi.org/10.1016/j.chemosphere.2016.09.071>.
- [15] N. Joseph, P. Ahmadiannamini, H. Richard, I.F.J. Vankelecom, Layer-by-layer preparation of polyelectrolyte multilayer membranes for separation polymer chemistry multilayer membranes for separation, *Polym. Chem.* (2013), <http://dx.doi.org/10.1039/c3py01262j>.
- [16] W.J. Lau, A.F. Ismail, Progress in interfacial polymerization technique on composite membrane preparation, in: *Proceedings of the 2nd International Conference on Environmental Engineering and Applications*, 2011, pp. 173–177.
- [17] A.W. Mohammad, Y.H. Teow, W.L. Ang, Y.T. Chung, D.L. Oatley-radcliffe, N. Hilal, Nanofiltration membranes review: recent advances and future prospects, *Desalination* 356 (2015) 226–254, <http://dx.doi.org/10.1016/j.desal.2014.10.043>.
- [18] R. Malaisamy, A. Talla-nwafo, K.L. Jones, Polyelectrolyte modification of nanofiltration membrane for selective removal of monovalent anions, *Sep. Purif. Technol.* 77 (2011) 367–374, <http://dx.doi.org/10.1016/j.seppur.2011.01.005>.
- [19] G. Decher, Fuzzy nanoassemblies: toward layered polymeric multicomposites, *Science* (80-) 277 (1997) 1232–1237, <http://dx.doi.org/10.1126/science.277.5330.1232>.
- [20] J.B. Schlenoff, S.T. Dubas, T. Farhat, Sprayed polyelectrolyte multilayers, *Langmuir* 16 (2000) 9968–9969, <http://dx.doi.org/10.1021/la001312i>.
- [21] J. Cho, C. K. H. J-D, K.-B. Lee, Fabrication of highly ordered multilayer films using a spin self-assembly method, *Adv. Mater.* 13 (2001) 1076–1078, [http://dx.doi.org/10.1002/1521-4095\(200107\)13:14<1076::AID-ADMA1076>3.0.CO;2-M](http://dx.doi.org/10.1002/1521-4095(200107)13:14<1076::AID-ADMA1076>3.0.CO;2-M).
- [22] L. Ouyang, R. Malaisamy, M.L. Bruening, Multilayer polyelectrolyte films as nanofiltration membranes for separating monovalent and divalent cations, *J. Membr. Sci.* 310 (2008) 76–84, <http://dx.doi.org/10.1016/j.memsci.2007.10.031>.
- [23] C. Magnenet, S. Lakard, C.C. Buron, B. Lakard, Functionalization of organic membranes by polyelectrolyte multilayer assemblies: application to the removal of copper ions from aqueous solutions, *J. Colloid Interface Sci.* 376 (2012) 202–208, <http://dx.doi.org/10.1016/j.jcis.2012.03.005>.
- [24] G. Zhang, W. Gu, S. Ji, Z. Liu, Y. Peng, Z. Wang, Preparation of polyelectrolyte multilayer membranes by dynamic layer-by-layer process for pervaporation separation of alcohol/water mixtures, *J. Membr. Sci.* 280 (2006) 727–733, <http://dx.doi.org/10.1016/j.memsci.2006.02.031>.
- [25] J. Kochan, T. Wintgens, J. Erik, T. Melin, Properties of polyethersulfone ultrafiltration membranes modified by polyelectrolytes, *Desalination* 250 (2010) 1008–1010, <http://dx.doi.org/10.1016/j.desal.2009.09.092>.
- [26] J. De Grooth, D.M. Reurink, J. Ploegmakers, W.M. De Vos, K. Nijmeijer, Charged micropollutant removal with hollow fiber nanofiltration membranes based on polycation/polyzwitterion/polyanion multilayers, *Appl. Mater. Interfaces* (2014), <http://dx.doi.org/10.1021/am504630a>.
- [27] S. Ilyas, S.M. Abtahi, N. Akkicil, H.D.W. Roesink, W.M. de Vos, Weak polyelectrolyte multilayers as tunable separation layers for micro-pollutant removal by hollow fiber nanofiltration membranes, *J. Membr. Sci.* 537 (2017) 220–228, <http://dx.doi.org/10.1016/j.memsci.2017.05.027>.
- [28] Z. Liu, Y. Shang, J. Feng, C. Peng, H. Liu, Y. Hu, Effect of hydrophilicity or hydrophobicity of polyelectrolyte on the interaction between polyelectrolyte and surfactants: molecular dynamics simulations, *J. Phys. Chem.* (2012), <http://dx.doi.org/10.1021/jp212089d>.
- [29] M. Schönhoff, N. Delorme, K. Glinel, M. Sch, V. Ball, A.R. Bausch, C. Dejognat, N. Delorme, K. Glinel, R. Steitz, Hydration and internal properties of polyelectrolyte multilayers hydration and internal properties of polyelectrolyte multilayers, *Colloids Surf. A Physicochem. Eng. Asp.* (2007), <http://dx.doi.org/10.1016/j.colsurfa.2007.02.054>.
- [30] M. Schonhoff, Self-assembled polyelectrolyte multilayers, *Curr. Opin. Colloid Interface Sci.* 8 (2003) 86–95, <http://dx.doi.org/10.1016/S1359-0294>.
- [31] I. Erel-unal, S.A. Sukhishvili, Hydrogen-bonded hybrid multilayers: film

- architecture controls release of macromolecules, *Macromolecules* 41 (2008) 8737–8744, <http://dx.doi.org/10.1021/ma8013564>.
- [32] D. Kovacevic, S. Borkovic, J. Pozar, The influence of ionic strength, electrolyte type and preparation procedure on formation of weak polyelectrolyte complexes, *Colloids Surf. A Physicochem. Eng. Asp.* 302 (2007) 107–112, <http://dx.doi.org/10.1016/j.colsurfa.2007.02.007>.
- [33] N. Wang, G. Zhang, S. Ji, Z. Qin, Z. Liu, The salt-, pH- and oxidant-responsive pervaporation behaviors of weak polyelectrolyte multilayer membranes, *J. Membr. Sci.* 354 (2010) 14–22, <http://dx.doi.org/10.1016/j.memsci.2010.03.002>.
- [34] K. Tang, N.A.M. Besseling, Formation of polyelectrolyte multilayers: ionic strengths and growth regimes, *Soft Matter* 12 (2016) 1032–1040, <http://dx.doi.org/10.1039/C5SM02118A>.
- [35] F. Fadhillah, S.M.J. Zaidi, Z. Khan, M.M. Khaled, F. Rahman, P.T. Hammond, Development of polyelectrolyte multilayer thin film composite membrane for water desalination application, *Desalination* 318 (2013) 19–24, <http://dx.doi.org/10.1016/j.desal.2013.03.011>.
- [36] W. Yao, X. Wang, H. Yang, G. Yu, S. Deng, J. Huang, B. Wang, Y. Wang, Removal of pharmaceuticals from secondary effluents by an electro-peroxide process, *Water Res.* 88 (2016) 826–835, <http://dx.doi.org/10.1016/j.watres.2015.11.024>.
- [37] Y. Lee, D. Gerrity, M. Lee, A.E. Bogeat, E. Salhi, S. Gamage, R.A. Trenholm, E.C. Wert, S.A. Snyder, U. Von Gunten, Prediction of micropollutant elimination during ozonation of municipal wastewater effluents: use of kinetic and water specific information, *Environ. Sci. Technol.* 47 (2013) 5872–5881, <http://dx.doi.org/10.1021/es400781r>.
- [38] V. Homem, L. Santos, Degradation and removal methods of antibiotics from aqueous matrices: a review, *J. Environ. Manag.* 92 (2011) 2304–2347, <http://dx.doi.org/10.1016/j.jenvman.2011.05.023>.
- [39] I. Michael, L. Rizzo, C.S. Mcardell, C.M. Manaia, C. Merlin, T. Schwartz, C. Dagot, D. Fatta-kassinos, Urban wastewater treatment plants as hotspots for the release of antibiotics in the environment: a review, *Water Res.* 47 (2012) 957–995, <http://dx.doi.org/10.1016/j.watres.2012.11.027>.
- [40] S.E.H. Comstock, T.H. Boyer, K.C. Graf, Treatment of nanofiltration and reverse osmosis concentrates: comparison of precipitative softening, coagulation, and anion exchange, *Water Res.* 45 (2011) 4855–4865, <http://dx.doi.org/10.1016/j.watres.2011.06.035>.
- [41] F. Elazhar, J. Touir, M. Elazhar, S. Belhamidi, N. El Harrak, A. Zdeg, M. Hafsi, M. Taky, A. Elmidaoui, J. Touir, M. Elazhar, S. Belhamidi, N. El Harrak, A. Zdeg, M. Hafsi, Techno-economic comparison of reverse osmosis and nanofiltration in desalination of a Moroccan brackish groundwater, *Desalin. Water Treat.* 3994 (2015), <http://dx.doi.org/10.1080/19443994.2014.959739>.
- [42] H.Q. Dang, W.E. Price, Factors governing the rejection of trace organic contaminants by nanofiltration and reverse osmosis membranes, *Desalination Water Treat.* 52 (2014) 589–599.
- [43] R.V. Linares, V. Yangali-quintanilla, Z. Li, G. Amy, Rejection of micropollutants by clean and fouled forward osmosis membrane, *Water Res.* 45 (2011) 6737–6744, <http://dx.doi.org/10.1016/j.watres.2011.10.037>.
- [44] T. Fujioka, S.J. Khan, J.A. McDonald, L.D. Nghiem, Nanofiltration of trace organic chemicals: a comparison between ceramic and polymeric membranes, *Sep. Purif. Technol.* 136 (2014) 258–264, <http://dx.doi.org/10.1016/j.seppur.2014.08.039>.
- [45] T. Fujioka, S.J. Khan, J.A. McDonald, L.D. Nghiem, Rejection of trace organic chemicals by a nanofiltration membrane: the role of molecular properties and effects of caustic cleaning, *Desalination* 368 (2015) 69–75, <http://dx.doi.org/10.1016/j.desal.2014.06.011>.
- [46] OECD Guideline for the Testing of Chemicals, Simulation Test – Aerobic Sewage Treatment, Organisation for Economic Co-operation and Development, Paris, 2001. (<http://dx.doi.org/10.1787/9789264067394-eng>).
- [47] C. Alcantara, R. Munoz, Z. Norvill, M. Plouviez, B. Guieysse, Nitrous oxide emissions from high rate algal ponds treating domestic wastewater, *Bioresour. Technol.* 177 (2015) 110–117, <http://dx.doi.org/10.1016/j.biortech.2014.10.134>.
- [48] Y. Luo, W. Guo, H. Hao, L. Duc, F. Ibney, J. Zhang, S. Liang, X.C. Wang, A review on the occurrence of micropollutants in the aquatic environment and their fate and removal during wastewater treatment, *Sci. Total Environ.* 473–474 (2014) 619–641, <http://dx.doi.org/10.1016/j.scitotenv.2013.12.065>.
- [49] J. de Groot, R. Oborny, J. Potreck, K. Nijmeijer, W.M. de Vos, The role of ionic strength and odd-even effects on the properties of polyelectrolyte multilayer nanofiltration membranes, *J. Membr. Sci.* 475 (2015) 311–319, <http://dx.doi.org/10.1016/j.memsci.2014.10.044>.
- [50] S. Ilyas, J. De Groot, K. Nijmeijer, W.M. De Vos, Multifunctional polyelectrolyte multilayers as nanofiltration membranes and as sacrificial layers for easy membrane cleaning, *J. Colloid Interface Sci.* 446 (2015) 386–393, <http://dx.doi.org/10.1016/j.jcis.2014.12.019>.
- [51] J. De Groot, M. Dong, W.M. De Vos, K. Nijmeijer, Building polyzwitterion-based multilayers for responsive membranes, *Langmuir* 30 (2014) 5152–5161, <http://dx.doi.org/10.1021/la500857b>.
- [52] I. Varga, E. Blomberg, Influence of salt and rinsing protocol on the structure of PAH/PSS polyelectrolyte multilayers, *Langmuir* 26 (2010) 17048–17057, <http://dx.doi.org/10.1021/la102351f>.
- [53] M. Elzbiaciak, M. Kolasinska, Z. Zapotoczny, R. Krastev, M. Nowakowska, P. Warszynski, Nonlinear growth of multilayer films formed from weak polyelectrolytes, *Colloids Surf. A Physicochem. Eng. Asp.* 343 (2009) 89–95, <http://dx.doi.org/10.1016/j.colsurfa.2009.01.034>.
- [54] X. Gong, C. Gao, Influence of salt on assembly and compression of PDADMAC/PSSMA polyelectrolyte multilayers, *Phys. Chem. Chem. Phys.* (2009) 11577–11586, <http://dx.doi.org/10.1039/b915335g>.
- [55] S. Dodoo, B.N. Balzer, T. Hugel, A. Laschewsky, R. Von Klitzing, S. Dodoo, B.N. Balzer, T. Hugel, A. Laschewsky, S. Dodoo, B.N. Balzer, T. Hugel, A. Laschewsky, R.V.O.N. Klitzing, Effect of ionic strength and layer number on swelling of polyelectrolyte multilayers in water vapour, *Soft Mater.* 4468 (2013), <http://dx.doi.org/10.1080/1539445X.2011.607203>.
- [56] K. Kimura, G. Amy, J. Drewes, Y. Watanabe, Adsorption of hydrophobic compounds onto NF/RO membranes: an artifact leading to overestimation of rejection, *J. Membr. Sci.* 221 (2003) 89–101, [http://dx.doi.org/10.1016/S0376-7388\(03\)00248-5](http://dx.doi.org/10.1016/S0376-7388(03)00248-5).
- [57] A.H.M.A. Sadmani, R.C. Andrews, D.M. Bagley, Rejection of pharmaceutically active and endocrine disrupting compounds by nanofiltration as a function of source water humic substances, *J. Water Process Eng.* 2 (2014) 63–70, <http://dx.doi.org/10.1016/j.jwpe.2014.05.004>.
- [58] A.R.D. Verliefde, E.R. Cornelissen, S.G.J. Heijman, I. Petrinic, T. Luxbacher, G.L. Amy, B. Van Der Bruggen, J.C. Van Dijk, Influence of membrane fouling by (pretreated) surface water on rejection of pharmaceutically active compounds (PhACs) by nanofiltration membranes, *J. Membr. Sci.* 330 (2009) 90–103, <http://dx.doi.org/10.1016/j.memsci.2008.12.039>.
- [59] V. Yangali-quintanilla, A. Sadmani, M. Mcconville, M. Kennedy, G. Amy, Rejection of pharmaceutically active compounds and endocrine disrupting compounds by clean and fouled nanofiltration membranes, *Water Res.* 43 (2009) 2349–2362, <http://dx.doi.org/10.1016/j.watres.2009.02.027>.
- [60] J.M. Choubert, L. Ribeiro, M. Euse, M. Coquery, C. Miegue, Fate of pharmaceuticals and personal care products in wastewater treatment plants – conception of a database and first results, *Environ. Pollut.* 157 (2009) 1721–1726, <http://dx.doi.org/10.1016/j.envpol.2008.11.045>.
- [61] T. Deblonde, C. Cossu-Jeguille, P. Hartemann, Emerging pollutants in wastewater: a review of the literature, *Int. J. Hyg. Environ. Health* 214 (2011) 442–448, <http://dx.doi.org/10.1016/j.ijheh.2011.08.002>.
- [62] E. Gracia-Ior, J.V. Sancho, R. Serrano, F. Hernández, Occurrence and removal of pharmaceuticals in wastewater treatment plants at the Spanish Mediterranean area of Valencia, *Chemosphere* 87 (2012) 453–462, <http://dx.doi.org/10.1016/j.chemosphere.2011.12.025>.
- [63] S. Kumar, H. Woo, J. Oh, H. Park, Occurrence and removal of antibiotics, hormones and several other pharmaceuticals in wastewater treatment plants of the largest industrial city of Korea, *Sci. Total Environ.* 409 (2011) 4351–4360, <http://dx.doi.org/10.1016/j.scitotenv.2011.07.015>.
- [64] N.K. Stamatidis, I.K. Konstantinou, Occurrence and removal of emerging pharmaceutical, personal care compounds and caffeine tracer in municipal sewage treatment plant in Western Greece, *J. Environ. Sci. Health* 48 (2013) 800–813, <http://dx.doi.org/10.1080/03601234.2013.781359>.
- [65] B. Kasprzyk-Hordern, R.M. Dinsdale, A.J. Guwy, The removal of pharmaceuticals, personal care products, endocrine disruptors and illicit drugs during wastewater treatment and its impact on the quality of receiving waters, *Water Res.* 43 (2009) 363–380, <http://dx.doi.org/10.1016/j.watres.2008.10.047>.
- [66] A. Perdigo, A. Petre, R. Rosal, A. Rodra, A. Agu, A.R. Ferna, Occurrence of emerging pollutants in urban wastewater and their removal through biological treatment followed by ozonation, *Water Res.* 44 (2010) 578–588, <http://dx.doi.org/10.1016/j.watres.2009.07.004>.
- [67] S. Comero, R. Loos, R. Carvalho, D.C. Antao, G. Locoro, S. Tavazzi, B. Paracchini, M. Ghiani, T. Lettieri, L. Blaha, B. Jarosova, S. Voorspoels, K. Servaes, P. Haglund, J. Fick, R.H. Lindberg, D. Schwesig, B.M. Gawlik, EU-wide monitoring survey on emerging polar organic contaminants in wastewater treatment plant effluents, *Water Res.* 7 (2013) 6475–6487, <http://dx.doi.org/10.1016/j.watres.2013.08.024>.
- [68] V.G. Samaras, A.S. Stasinakis, D. Mamais, N.S. Thomaidis, T.D. Lekkas, Fate of selected pharmaceuticals and synthetic endocrine disrupting compounds during wastewater treatment and sludge anaerobic digestion, *J. Hazard. Mater.* 244–245 (2013) 259–267, <http://dx.doi.org/10.1016/j.jhazmat.2012.11.039>.
- [69] S. Zorita, L. Mårtensson, L. Mathiasson, Occurrence and removal of pharmaceuticals in a municipal sewage treatment system in the south of Sweden, *Sci. Total Environ.* 407 (2009) 2760–2770, <http://dx.doi.org/10.1016/j.scitotenv.2008.12.030>.
- [70] J.L. Santos, I. Aparicio, M. Callejón, E. Alonso, Occurrence of pharmaceutically active compounds during 1-year period in wastewaters from four wastewater treatment plants in Seville (Spain), *J. Hazard. Mater.* 164 (2009) 1509–1516, <http://dx.doi.org/10.1016/j.jhazmat.2008.09.073>.
- [71] A. Huyard, M. Esperanza, A. Bruchet, Reduction of endocrine disruptor emissions in the environment: the benefit of wastewater treatment, *Water Res.* 43 (2009) 1565–1576, <http://dx.doi.org/10.1016/j.watres.2008.12.051>.
- [72] C. Höhne, W. Püttmann, Occurrence and temporal variations of the xenoestrogens bisphenol A, 4-tert-octylphenol, and tech. 4-nonylphenol in two German wastewater treatment plants, *Environ. Sci. Pollut. Res.* 15 (2008) 405–416, <http://dx.doi.org/10.1007/s11356-008-0007-2>.
- [73] P. Pothitou, D. Voutsas, Endocrine disrupting compounds in municipal and industrial wastewater treatment plants in Northern Greece, *Chemosphere* 73 (2008) 1716–1723, <http://dx.doi.org/10.1016/j.chemosphere.2008.09.037>.
- [74] O.O. Olujimi, O.S. Fatoki, A.P. Daso, O.S. Akinsoji, O.U. Oputu, O.S. Oluwafemi, S. P. Songca, Levels of Nonylphenol and Bisphenol A in wastewater treatment plant effluent, sewage sludge and leachates around Cape Town, South Africa, in: *Handb. Wastewater Treat.*, 2013 Nova Science Publishers, Inc., 2013, pp. 305–315.
- [75] K. Xia, H.L. Keller, J. Wagner, Occurrence, distribution, and fate of 4-nonylphenol in Kansas domestic wastewater treatment plants, *J. Contemp. Water Res. Educ.* 120 (2001) 41–48 <http://opensiuc.lib.siu.edu/jcwr/vol120/iss1/5/>.
- [76] Y. Nie, Z. Qiang, H. Zhang, W. Ben, Fate and seasonal variation of endocrine-disrupting chemicals in a sewage treatment plant with A/A/O process, *Sep. Purif. Technol.* 84 (2012) 9–15, <http://dx.doi.org/10.1016/j.seppur.2011.01.030>.
- [77] R. Céspedes, S. Lacorte, A. Ginebreda, D. Barceló, Occurrence and fate of alkylphenols and alkylphenol ethoxylates in sewage treatment plants and impact on receiving waters along the Ter River (Catalonia, NE Spain), *Environ. Pollut.* 153

- (2008) 384–392, <http://dx.doi.org/10.1016/j.envpol.2007.08.026>.
- [78] R.A. McAloney, M. Sinyor, V. Dudnik, M. Cynthia Goh, Atomic force microscopy studies of salt effects on polyelectrolyte multilayer film morphology, *Langmuir* 17 (2001) 6655–6663, <http://dx.doi.org/10.1021/la010136q>.
- [79] R. Kumar, A. Ismail, Fouling control on microfiltration/ultrafiltration membranes: effects of morphology, hydrophilicity, and charge, *J. Appl. Polym. Sci.* 1 (1–20) (2015) 42042, <http://dx.doi.org/10.1002/APP.42042>.
- [80] J. Saqib, I.H. Aljundi, Membrane fouling and modification using surface treatment and layer-by-layer assembly of polyelectrolytes: state-of-the-art review, *J. Water Process Eng.* 11 (2016) 68–87, <http://dx.doi.org/10.1016/j.jwpe.2016.03.009>.
- [81] J. Irigoyen, T. Laakso, N. Politakos, L. Dahne, A. Pihlajamäki, M. Mänttari, S.E. Moya, Design and performance evaluation of hybrid nanofiltration membranes based on multiwalled carbon nanotubes and polyelectrolyte multilayers for larger ion rejection and separation, *Macromol. Chem. Phys.* (2016) 804–811, <http://dx.doi.org/10.1002/macp.201500433>.
- [82] G. Bargeman, J.B. Westerink, C.F.H. Manuhutu, A. Kate, The effect of membrane characteristics on nanofiltration membrane performance during processing of practically saturated salt solutions, *J. Membr. Sci.* 485 (2015) 112–122, <http://dx.doi.org/10.1016/j.memsci.2015.03.039>.
- [83] D. Jermann, W. Pronk, M. Boller, A.I. Schäfer, The role of NOM fouling for the retention of estradiol and ibuprofen during ultrafiltration, *J. Membr. Sci.* 329 (2009) 75–84, <http://dx.doi.org/10.1016/j.memsci.2008.12.016>.
- [84] B. Van Der Bruggen, J. Schaep, D. Wilms, C. Vandecasteele, Influence of molecular size, polarity and charge on the retention of organic molecules by nanofiltration, *J. Membr. Sci.* 156 (1999) 29–41, [http://dx.doi.org/10.1016/S0376-7388\(98\)00326-3](http://dx.doi.org/10.1016/S0376-7388(98)00326-3).
- [85] T. Fujioka, S.J. Khan, J.A. McDonald, L.D. Nghiem, Rejection of trace organic chemicals by a hollow fibre cellulose triacetate reverse osmosis membrane, *Desalination* 368 (2015) 69–75, <http://dx.doi.org/10.1016/j.desal.2014.06.011>.
- [86] Y. Kiso, K. Muroshige, T. Oguchi, T. Yamada, M. Hhirose, T. Ohara, T. Shintani, Effect of molecular shape on rejection of uncharged organic compounds by nanofiltration membranes and on calculated pore radii, *J. Membr. Sci.* 358 (2010) 101–113, <http://dx.doi.org/10.1016/j.memsci.2010.04.034>.
- [87] H.T. Madsen, E.G. Søgaard, Applicability and modelling of nanofiltration and reverse osmosis for remediation of groundwater polluted with pesticides and pesticide transformation products, *Sep. Purif. Technol.* 125 (2014) 111–119, <http://dx.doi.org/10.1016/j.seppur.2014.01.038>.
- [88] R.D.H. Bugan, N.Z. Jovanovic, W.P. De Clercq, Quantifying the catchment salt balance: an important component of salinity assessments, *S. Afr. J. Sci.* 111 (2015) 1–8, <http://dx.doi.org/10.17159/sajs.2015/20140196>.
- [89] J.W. Kijne, *Water and Salinity Balances for Irrigated Agriculture in Pakistan*, 1996. (<http://dx.doi.org/10.3910/2009.006>).