



HAL
open science

Microwave-assisted synthesis of lanthanide coordination polymers with 2-bromobenzoic acid as ligand from hexa-lanthanide molecular precursors

Haiyun Yao, Guillaume Calvez, Carole Daiguebonne, Yan Suffren, Kevin Bernot, Olivier Guillou

► **To cite this version:**

Haiyun Yao, Guillaume Calvez, Carole Daiguebonne, Yan Suffren, Kevin Bernot, et al.. Microwave-assisted synthesis of lanthanide coordination polymers with 2-bromobenzoic acid as ligand from hexa-lanthanide molecular precursors. *Journal of Molecular Structure*, 2022, 1250, pp.131918. 10.1016/j.molstruc.2021.131918 . hal-03515035

HAL Id: hal-03515035

<https://hal.science/hal-03515035>

Submitted on 29 Mar 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial 4.0 International License

Microwave-assisted synthesis of lanthanide coordination polymers with 2-bromobenzoic acid as ligand from hexa-lanthanide molecular precursors

Haiyun Yao^{a,b}, Guillaume Calvez^{a,*}, Carole Daignebonne^a, Yan Suffren^a, Kevin Bernot^a and Olivier Guillou^{a,*}

^aUniv Rennes, INSA Rennes, CNRS UMR 6226 "Institut des Sciences Chimiques de Rennes", F-35708 Rennes, France

^bPresent address: School of Opto-electronic Engineering, Zaozhuang University, Zaozhuang 277160, China

*To whom correspondence should be addressed.

Highlights

- New lanthanide-based coordination polymers crystal structure
- Straight chains are obtained from octahedral hexa-lanthanide precursors
- Strong intermetallic energy transfers between lanthanide ions

ABSTRACT

Microwave-assisted reactions, between 2-bromobenzoic acid (2-bbH) and hexa-lanthanide molecular precursors of general chemical formula

$\text{Ln}_6(\mu_6\text{-O})(\mu_3\text{-OH})_8(\text{NO}_3)_6(\text{H}_2\text{O})_{12}\cdot 2\text{NO}_3\cdot 2\text{H}_2\text{O}$ ($[\text{Ln}_6]$), lead to iso-structural 1D coordination polymers of general chemical formula $[\text{Ln}(2\text{-bb})_3]_\infty$ with $\text{Ln} = \text{Eu}, \text{Tb}$ or Dy . These compounds crystallize in the monoclinic system, space group $P2_1/c$ ($n^\circ 14$), with the following cell parameters (for the Dy-derivative): $a = 12.3809(10) \text{ \AA}$, $b = 21.8653(16) \text{ \AA}$, $c = 7.9119(7) \text{ \AA}$, $\beta = 98.709(3)^\circ$, $V = 2117.2(3) \text{ \AA}^3$ and $Z = 4$. The influence of the hexa-nuclear precursors over the final coordination polymer is demonstrated. Indeed, while the hexa-nuclear complexes collapse during the synthetic process their progressive destruction affords a unique 1D coordination polymer that cannot be readily obtained otherwise. Additionally, some iso-structural hetero-lanthanide derivatives with general chemical formulas $[\text{Eu}_x\text{Tb}_{1-x}(2\text{-bb})_3]_\infty$ and $[\text{Y}_x\text{Tb}_{1-x}(2\text{-bb})_3]_\infty$ with $0 \leq x \leq 1$ have been prepared from the corresponding hexa-nuclear complexes $[\text{Eu}_6\text{Tb}_{6-6x}]$ and $[\text{Y}_6\text{Tb}_{6-6x}]$, respectively. Luminescent properties have been recorded and colorimetric coordinates have been calculated for all the compounds. These measurements indicate that the molecular chains host strong intermetallic energy transfers.

INTRODUCTION

Lanthanide based coordination polymers¹ have been widely studied in the past two decades because of their interesting porous,²⁻⁶ luminescent⁷⁻⁹ or magnetic¹⁰⁻¹³ properties, for instance. Indeed, because of the unique chemical and physical properties of the lanthanide ions,¹⁴⁻¹⁶ they can find their application in various technological fields¹⁷⁻¹⁹ such as molecular thermometry,²⁰⁻²⁵ chemical sensing,^{9, 26-28} light and display²⁹⁻³¹ or chemical tagging,³²⁻³⁶ for examples. Therefore, the quest for new compounds with enhanced optical properties is a continuous concern.³⁷ To achieve this objective one can play both with the nature of the ligand or with the metallic centers of the coordination polymers. The more common strategy

consists on modifying the ligand^{21-22, 38-45} but it is also possible to use polymetallic centers.^{18, 46-49} (i) In one hand, in recent years, it has been shown that the use of a ligand that induces a large distance between the molecular motifs is beneficial because it reduces intermetallic energy transfers⁵⁰⁻⁵¹ between neighboring molecular motifs.^{36, 52-54} Halogeno derivatives, for example, that can induce halogen bonds, have shown their efficiency.^{36, 52-53} (ii) In the other hand, it is possible to design coordination polymers in which the metallic centers are no longer single lanthanide ions but poly-lanthanide entities. Many beautiful such compounds have been reported so far⁵⁵ that sometimes present metallic centers with very high nuclearities.⁵⁶⁻⁵⁸ However, most of these compounds have been obtained via one-pot serendipitous syntheses. Actually, the only poly-lanthanide complexes usable as molecular precursors for the design of coordination polymers, to date, are the octahedral hexa-nuclear complexes first described by Giester *et al.*⁵⁹⁻⁶³ (Figure 1). Several coordination compounds have been obtained using these complexes as reactants.^{47, 64-67}




Figure 1. Left: Projection view of a hexa-nuclear molecular complex $Y_6(\mu_6-O)(\mu_3-OH)_8(NO_3)_6(H_2O)_{12} \cdot 2NO_3 \cdot 2H_2O$ ($[Y_6]$). Redrawn from reference 68. Right: Molecular view of 2-bromo-benzoate.

To the best of our knowledge, there is only one lanthanide coordination polymer based on 2-bbH reported so far: $[Eu(2-bb)_3 \cdot H_2O]_\infty$.⁶⁹ As expected, in this 1D crystal structure, the 2-bb⁻ ligands act both as antenna⁷⁰ and spacers.

Our group has developed the use of hexa-lanthanide complexes as molecular precursors for almost 20 years⁷¹⁻⁷² and, in this article, we describe the microwave-assisted synthesis, the crystal structure and the luminescent properties of new lanthanide coordination polymers obtained from 2-bromo-benzoic acid (2-bbH) and hexa-lanthanide complexes ([Ln₆]).

EXPERIMENTAL SECTION.

Synthesis of [Ln(2-bb)₃]_∞ with Ln = Eu, Tb or Dy.

2-bbH was purchased from TCI (>98%) and used without further purification. Lanthanide oxides were purchased from Ampère (4N) and used without further purification. Lanthanide nitrates and hexa-nuclear complexes [Ln₆] were prepared as previously described.^{68, 73}

5.10⁻³ mmol of hexa-lanthanide complexes ([Ln₆]) with Ln = Eu, Tb or Dy, 5.10⁻³ mmol of 2-bromobenzic acid (2-bbH) and 2 mL of acetonitrile were mixed under magnetic stirring in a 10 mL tube. The suspension was then microwave heated at 100°C (CEM Discover microwave heater; power setting 150 W; maximum pressure 2 bars) for 15 min. Then the mixture was filtered and allowed to cool down to room temperature. The resulting limpid solution was then left for several days at room temperature in a closed vessel. After a few days, single crystals appeared. They were collected, rinsed with acetonitrile and dried in air. Each batch produces only about 300 µg of single crystals which makes difficult some measurements. Iso-structurality of the samples was assumed on the basis of their powder X-ray diffraction diagrams and IR spectra. They were all similar and only those of the Tb-derivative are reported (Figures S1 and S2). Measurements have been made on crushed single crystals.

Single crystal X-ray diffraction.

The crystal structure has been solved on the basis of the dysprosium-derivative. Single crystals were mounted on a Bruker D8 Venture diffractometer. Crystal data collection were performed at 150 K with Mo K $_{\alpha}$ radiation ($\lambda = 0.70713 \text{ \AA}$). The crystal structure was solved, using SIR 97,⁷⁴ by direct methods. It was refined, using SHELX-2017⁷⁵⁻⁷⁶ with the aid of WINGX program.⁷⁷⁻⁷⁸ All non-hydrogen atoms were refined anisotropically. Hydrogen atoms were located at ideal positions. Absorption corrections were performed using the facilities of WINGX program.⁷⁹ There is some residual density near the Dy³⁺ ion. Selected crystal and final structure refinement data are gathered in Table 1. Full details of the crystal structure have been deposited with the Cambridge Crystallographic Data Centers under the depositary number CCDC-1871218.

Table 1. Crystallographic data for [Dy(2-bb)₃] $_{\infty}$.

Chemical formula	C ₂₁ H ₁₂ Br ₃ DyO ₆
System	Monoclinic
Space group (n ^o)	<i>P</i> 2 ₁ / <i>c</i> (n ^o 14)
Formula weight (g.mol ⁻¹)	762.51
<i>a</i> (Å)	12.3809(10)
<i>b</i> (Å)	21.8653(16)
<i>c</i> (Å)	7.9119(7)
β (°)	98.709(3)

$V (\text{\AA}^3)$	2117.2(3)
Z	4
$D_{calc} (\text{g}\cdot\text{cm}^{-3})$	2.392
$R (\%)$	4.26
$R_w (\%)$	11.27
GoF	1.067
CCDC number	1871218

Electronic microscopy and Energy Dispersive Spectroscopy (EDS).

EDS measurements have been performed with a Hitachi TM-1000, Tabletop Microscope version 02.11 (Hitachi High-Technologies, Corporation Tokyo Japan) with EDS analysis system (SwiftED-TM, Oxford Instruments Link INCA). Reproducibility of the elemental analyses has been checked by repeating the measurements several times. Results, expressed in atom percentages, are average values of different spots. These experiments support the homogeneity of the samples.

Optical measurements.

Solid-state emission and excitation spectra have been measured on a Horiba Jobin-Yvon Fluorolog III fluorescence spectrometer equipped with a Xe lamp 450 W, an UV-Vis photomultiplier (Hamamatsu R928, sensitivity 190 - 860 nm). The emission/excitation spectra recordings were realized on powder samples in 700 μL quartz cuvettes. The quantum yields were measured with the same device using an integrating sphere, extending its correction curve in the 290-330 nm range by measuring standards in this range (the Eu tris-dipicolinate in *tris* (tris(hydroxymethyl)aminomethane) buffer solution as proposed by Chauvin *et al*⁸⁰). The quantum yield was estimated measuring the ratio between absorbed photons around the excitation wavelength without and with the sample (the

difference between respectively L_a and L_c values for corresponding integrated spectra) and the emitted photons with and without the sample (the difference between respectively E_c and E_a values for corresponding integrated spectra). The lifetime values were measured with the same device, using a pulsed Xenon source and measuring the intensity emitted after increasing time delay. The decay time was then fitted using a mono-exponential decay function. Appropriate filters were used to remove the residual excitation laser light, the Rayleigh scattered light and associated harmonics from spectra. All spectra were corrected for the instrumental response function. Colorimetric coordinates have been calculated on the basis of the emission spectra.⁸¹⁻⁸²

RESULTS AND DISCUSSION.

Crystal structure of $[\text{Ln}(\text{2-bb})_3]_\infty$ with Ln = Eu, Tb or Dy.

Microwave-assisted reactions in acetonitrile between a hexa-lanthanide complex ($[\text{Ln}_6]$ with Ln = Eu, Tb or Dy) and 2-bromobenzoic acid lead to isostructural lanthanide coordination polymers with general chemical formula $[\text{Ln}(\text{2-bb})_3]_\infty$ with Ln = Eu, Tb or Dy. The crystal structure has been solved on the basis of the Dy-derivative. It can be described as the juxtaposition of almost linear molecular chains that spread parallel to the c -axis. The chain is situated at the c glide plane, which means it obeys sub-periodic rod group symmetry $pc11$ (No. R5).⁸³ Position of the Dy atom above the plane makes Dy...Dy distance a bit longer than half of the c axis: $3.9584(3) \text{ \AA}$ vs $3.9119(4) \text{ \AA} = c/2$.

There is only one Dy^{3+} ion in the asymmetric unit. It is eight coordinated by eight oxygen atoms from six different 2-bb⁻ ligands that form a bi-capped trigonal prism (Figure 2). There are three independent ligands in the asymmetric unit that present two different coordination modes: in the first one, the two oxygen atoms of the carboxylate function are monodentate while in the second one, one oxygen atom is monodentate and the second is

bidentate (Figure 2). There are three bridging ligands between two adjacent Dy³⁺ ions, which leads to a short intermetallic distance in the molecular chains: $d_{\text{Dy-Dy}} = 3.9584(3) \text{ \AA}$. This crystal structure presents a 1D inorganic sub-lattice (coordination polyhedrons share edges) which constitutes an asset as far as strong intermetallic energy transfers⁵²⁻⁵³ and high luminance are targeted.

It has been previously shown, that the octahedral complexes used as molecular precursors may present a structuring effect and may lead to crystal structures that cannot be obtained from simple mono-nuclear lanthanide salts.^{64-65, 84-85} This is, once more, the case here and despite several attempts, it has not been possible to obtain these compounds using other precursors. Moreover, the quasi-linearity of the molecular chains (Dy-Dy-Dy angle is 175.9(1)°) strongly suggests that the carboxylate functions of the ligands clip and connect neighboring lanthanide ions of hexa-nuclear complexes while nitrate ions, hydroxides and coordination water molecules are simultaneously removed (Scheme 1). This synthetic mechanism has already been proposed recently.⁸⁶





Figure 2. Neighborhood of the Dy³⁺ ion (top left), coordination modes of the 2-bb⁻ ligands (top right), triple Dy-Dy bridge (binding bonds are drawn in blue) (bottom left) and Dy³⁺ polyhedrons (bottom right) of $[\text{Dy}(\text{2-bb})_3]_\infty$.



Scheme 1. Schematic representation of the proposed synthetic mechanism: Carboxylate functions of 2-bb⁻ ligands connect (in red) neighboring atoms of a hexa-lanthanide complex while nitrates and hydroxides are removed (in blue). Then the linked ligands rotate because of π -stacking and halogen-bonds driving forces. Labile coordination water molecules of the starting complex (left) have been omitted for clarity.

The stability of the crystal packing is insured by π -stacking interactions (centroid-to-centroid distance of C16-C21 ring and its equivalent, by inversion at $(\frac{1}{2} \frac{1}{2} \frac{1}{2})$, is 3.676(3) Å) and halogen-bonds (the shortest distance between halogen atoms, 4.054(1) Å, is found for Br1...Br3 with the valence angle C17-Br3...Br1 equal to 89.6(2) $^\circ$) (Figure 3). It can be noticed that, in this crystal structure, there is no coordination or crystallization solvent molecule. This is an asset as far as strongly luminescent coordination polymers are targeted. Indeed it implies the absence of O-H or C-H vibrators in the vicinity of the lanthanide ions that are known for favoring non-radiative de-excitation of the lanthanide ions, especially of Eu³⁺ ions.⁸⁷ Intermetallic distances between lanthanide ions that belong to adjacent molecular chains are greater than 10 Å (Scheme 2) that is the threshold above which intermetallic energy transfers are expected to be less efficient.⁸⁷⁻⁸⁸ On a global point of view, there are four lanthanide ions closer than 10 Å from a given Dy³⁺ ions (Scheme 2).





Figure 3. Projection views along the a - (left) and c -axes (right) of an extended unit cell of $[\text{Dy}(\text{2-bb})_3]_\infty$. Halogen bonds and π -stacking interactions are drawn in brown and yellow dotted lines, respectively (right).



Scheme 2. Projection views along the a -axis (left) and along the c -axis (right) of the crystal packing of $[\text{Dy}(\text{2-bb})_3]_\infty$. A 10 Å radius gray sphere centered on a given Dy^{3+} ion is drawn.

Shortest intermetallic distances between Dy^{3+} ions that belong to different molecular chains are indicated. In a given molecular chain, shortest intermetallic distance is 3.9584(3) Å.

Luminescence properties of $[\text{Ln}(2\text{-bb})_3]_\infty$ with Ln = Eu, Tb or Dy.

Emission and excitation spectra of $[\text{Ln}(2\text{-bb})_3]_\infty$ with Ln = Eu or Tb have been recorded (Figure 4). Quantum yields and luminescence lifetimes have been measured and colorimetric coordinates calculated (Table 2). From Table 2, it can be noticed that overall quantum yields and luminescent lifetimes are sizeable and compare well with what is usually reported for lanthanide-based coordination polymers.⁵⁴ This may be related with the presence of an inorganic sub-lattice and with the absence of C-H or O-H vibrators in the vicinity of the lanthanide ions.⁸⁷ On the opposite, the luminescence of the Dy^{3+} -derivative is very weak and difficult to record with our setup.




Figure 4. Room temperature solid state excitation and emission spectra of $[\text{Tb}(2\text{-bb})_3]_\infty$ (left) and $[\text{Eu}(2\text{-bb})_3]_\infty$ (right).

Table 2. Quantum yields, luminescent lifetimes and colorimetric coordinates of [Tb(2-bb)₃]_∞ and [Eu(2-bb)₃]_∞.

	$Q_{Ln}^{Ligand} (\%)^\dagger$	$\tau (ms)^\dagger$	$Q_{Ln}^{Ln} (\%)^\ddagger$	Colorimetric coordinates [†]	
				x	y
[Tb(2-bb) ₃] _∞	35(3)	2.0(2)	-	0.328	0.570
[Eu(2-bb) ₃] _∞	11(1)	0.97(9)	32(3)	0.617	0.353

[†] $\lambda_{exc} = 295 \text{ nm}$

[‡] $\lambda_{exc} = 394 \text{ nm}$

Both excitation spectra show a broad excitation band centered at 295 nm that can be attributed to the ${}^3\pi^*/{}^1\pi^* \leftarrow {}^1\pi$ transition of the ligand and confirm an efficient antenna⁷⁰ effect toward both lanthanide ions. This efficiency (η_{sens}) has been estimated for the Eu³⁺-derivative according to the following relationship:⁸⁷

$$Q_{Eu}^{Ligand} = \eta_{sens} \cdot Q_{Eu}^{Eu} \quad (1)$$

where Q_{Eu}^{Ligand} and Q_{Eu}^{Eu} are the overall and intrinsic quantum yields, respectively. Q_{Eu}^{Eu} has been measured under 394 nm excitation wavelength that corresponds to the ${}^5L_6 \leftarrow {}^7F_0$ Eu³⁺ transition because this transition doesn't significantly overlap the ligand excitation band. This leads to a moderate value of $\eta_{sens} = 34.5 \%$. This moderate value is in agreement with the quite high intensity of the ${}^5L_6 \leftarrow {}^7F_0$ Eu³⁺ transition compared with the ${}^3\pi^*/{}^1\pi^* \leftarrow {}^1\pi$ transition. This feature can be related to the presence of a PET (Photo-induced Electron Transfer) effect that arises when a donor group (such as Br) is present near an easily reducible metallic ion (such as Eu³⁺).⁸⁹⁻⁹³

The emission spectrum of [Tb(2-bb)₃]_∞ shows the characteristic ${}^5D_4 \rightarrow {}^7F_{6-0}$ transitions⁹⁴ of the Tb³⁺ ion centered at 489, 544, 584, 621, 648, 669 and 681 nm,

respectively. It is dominated by the ${}^5D_4 \rightarrow {}^7F_5$ transition and therefore $[\text{Tb}(\text{2-bb})_3]_\infty$ exhibits green emission under UV excitation.

The emission spectrum of $[\text{Eu}(\text{2-bb})_3]_\infty$ shows the characteristic ${}^5D_0 \rightarrow {}^7F_{0-4}$ Eu^{3+} transitions⁹⁵ centered at 578, 593, 617, 649 and 689 nm, respectively. The ${}^5D_0 \rightarrow {}^7F_1$ transition dominates the emission spectrum and induces a red emission of $[\text{Eu}(\text{2-bb})_3]_\infty$ under UV excitation.

Luminescence properties of $[\text{Y}_x\text{Tb}_{1-x}(\text{2-bb})_3]_\infty$ and $[\text{Eu}_x\text{Tb}_{1-x}(\text{2-bb})_3]_\infty$ with $0.1 \leq x \leq 0.5$.

Isostructural hetero-lanthanide derivatives ($[\text{Y}_x\text{Tb}_{1-x}(\text{2-bb})_3]_\infty$ and $[\text{Eu}_x\text{Tb}_{1-x}(\text{2-bb})_3]_\infty$ with $0.1 \leq x \leq 0.5$) have been prepared from the corresponding hexa-lanthanide molecular precursors ($[\text{Y}_{6x}\text{Tb}_{6-6x}]$ and $[\text{Eu}_{6x}\text{Tb}_{6-6x}]$). Their isostructurality with $[\text{Eu}(\text{2-bb})_3]_\infty$ has been assumed on the basis of their powder X-ray diffraction diagrams and relative contents of the different lanthanide ions have been measured by EDS (Table S1). The x value has been limited to 0.5 because afterwards the $[\text{Y}_x\text{Tb}_{1-x}(\text{2-bb})_3]_\infty$ molecular alloys were no longer isostructural to $[\text{Dy}(\text{2-bb})_3]_\infty$ and because when x is greater than 0.5, the Tb^{3+} luminescence completely vanishes in the $[\text{Eu}_x\text{Tb}_{1-x}(\text{2-bb})_3]_\infty$ series.

Tb^{3+} overall quantum yields and luminescence lifetimes have been measured and colorimetric coordinates have been calculated for $[\text{Y}_x\text{Tb}_{1-x}(\text{2-bb})_3]_\infty$ with $0.1 \leq x \leq 0.5$ (Table 3). Emission spectra are reported in Figure S3.

Table 3. Overall quantum yield, luminescence lifetime and colorimetric coordinates for $[\text{Y}_x\text{Tb}_{1-x}(\text{2-bb})_3]_\infty$ with $0.1 \leq x \leq 0.5$.

x	$Q_{\text{Tb}}^{\text{Ligand}}$ (%)	τ_{Tb} (ms)	Colorimetric coordinates	
			x	y
0.1	42(4)	1.9(2)	0.354	0.566
0.15	50(5)	2.0(2)	0.349	0.570

0.3	74(5)	2.0(2)	0.337	0.577
0.5	29(3)	1.7(2)	0.350	0.570

$\lambda_{\text{exc}} = 295 \text{ nm}$

The measurements indicate that there is a sizeable concentration quenching effect in this system. Indeed, dilution of the optically active Tb^{3+} ion by the optically no-active Y^{3+} provokes an enhancement of the Tb^{3+} overall quantum yield even at low dilution rate ($x = 10\%$). The maximum overall quantum yield is observed for $x \approx 0.3$. Then the dilution effect does not compensate anymore the decrease of the number of optically active lanthanide ions.

Emission spectra of the corresponding $[\text{Eu}_x\text{Tb}_{1-x}(\text{2-bb})_3]_{\infty}$ compounds have been recorded (Figure 5), colorimetric coordinates have been calculated (Figure 6) and the Tb^{3+} and Eu^{3+} overall quantum yields and luminescence lifetimes have been measured (Table 4).




Figure 5. Room temperature solid-state emission spectra ($\lambda_{\text{exc}} = 295 \text{ nm}$) of $[\text{Eu}_x\text{Tb}_{1-x}(\text{2-bb})_3]_{\infty}$ with $0.1 \leq x \leq 0.5$.

These spectra strongly suggest that there are efficient Tb³⁺-to-Eu³⁺ intermetallic energy transfers. Indeed, the Tb³⁺ component rapidly decreases and almost completely vanishes for $x = 0.5$ while the Eu³⁺ component increases. This is in agreement with the evolutions *versus* x of the quantum yields and of the luminescence lifetimes that are observed (Table 4) and with the observed strong concentration quenching effect.⁹⁶

Table 4. Tb³⁺ and Eu³⁺ overall quantum yields and luminescence lifetimes for [Eu _{x} Tb _{$1-x$} (2-bb)₃]_∞ with $0.1 \leq x \leq 0.5$.

x	$Q_{\text{Tb}}^{\text{Ligand}}$ (%)	τ_{Tb} (ms)	$Q_{\text{Eu}}^{\text{Ligand}}$ (%)	τ_{Eu} (ms)	η_{ET} (%)
0.1	10(1)	0.6(1)	28(3)	1.8(2)	69
0.15	2.3(2)	0.2(1)	47(4)	2.0(2)	88
0.3	1.9(2)	0.2(2)	40(4)	1.6(2)	94
0.5	0.04(1)	0.12(2)	29(3)	1.3(1)	96

$\lambda_{\text{exc}} = 295 \text{ nm}$

The intermetallic energy transfers have been quantified by the following relationship:⁸⁷

$$\eta_{\text{ET}} = 1 - \frac{\tau_{\text{obs}}}{\tau_0} \quad (2.)$$

where τ_{obs} and τ_0 are the luminescent lifetimes of the Tb³⁺ in presence (Table 4) and in absence (Table 3) of an acceptor Eu³⁺ ion, respectively. These calculations confirm the efficiency of the Tb³⁺-to-Eu³⁺ intermetallic energy transfers (Figure 6).




Figure 6. Colorimetric coordinates of $[\text{Eu}_x\text{Tb}_{1-x}(\text{2-bb})_3]_\infty$ with $x = 0, 0.05, 0.1, 0.15, 0.3, 0.5$ and 1. Colorimetric coordinates have been calculated from emission spectra ($\lambda_{\text{exc}} = 295 \text{ nm}$).

CONCLUSIONS AND OUTLOOK.

In this article, we have structurally described a new series of 1D lanthanide coordination polymers obtained from hexa-lanthanide complexes by a microwave-assisted synthesis. These compounds cannot be obtained from simple mono-nuclear salts of lanthanide ions and a mechanism is proposed for explaining the synthetic process that leads from octahedral hexa-nuclear complexes to straight molecular chains. Although there are many “catena type” lanthanides containing coordination polymers reported to date, this one is special and can be called “hybrid inorganic chain”⁹⁷ because metal ions are linked by bridging oxygen atoms and the organic part is not involved in propagation of the chain. Luminescence properties of the Tb^{3+} - and Eu^{3+} -derivatives and of some hetero-lanthanide derivatives have been studied. This study suggests that the molecular chains host strong intermetallic energy transfers.

ACKNOWLEDGEMENTS.

The China Scholarship Council Ph.D. Program, a cooperation program with the French UT and INSA, is acknowledged for financial support. The CDIFX (X-ray diffraction center of Rennes) is acknowledged for single-crystal X-ray diffraction data collection.

SUPPORTING INFORMATION.

Experimental X-ray powder diffraction pattern of $[\text{Tb}(2\text{-bb})_3]_\infty$ and calculated from the crystal structure X-ray powder diffraction diagram of $[\text{Dy}(2\text{-bb})_3]_\infty$; IR spectrum of $[\text{Tb}(2\text{-bb})_3]_\infty$; Metallic relative contents in $[\text{Y}_x\text{Tb}_{1-x}(2\text{-bb})_3]_\infty$ and $[\text{Eu}_x\text{Tb}_{1-x}(2\text{-bb})_3]_\infty$ with $0.1 \leq x \leq 0.5$; Room temperature solid state emission spectra of $[\text{Y}_x\text{Tb}_{1-x}(2\text{-bb})_3]_\infty$ with $0.1 \leq x \leq 0.5$ ($\lambda_{\text{exc}} = 295 \text{ nm}$).

Credit Author statement

Haiyun Yao: Investigation. **Guillaume Calvez:** Supervision. **Carole Daiguebonne:** Supervision, Investigation. **Yan Suffren:** Validation. **Kevin Bernot:** Writing. **Olivier Guillou:** Writing, Review and Editing.

Declaration of interests

The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

REFERENCES.

1. E. W. Berg; A. Alam, Studies on coordination polymers. Part I : Coordination polymers of 8,8'-dihydroxy-5,5'-biquinolyl. *Anal. Chim. Acta* **1962**, *27*, 454-459.
2. A. Dimos; D. Tsaousis; A. Michaelies; S. Skoulika; S. Golhen; L. Ouahab; C. Didierjean; A. Aubry, Microporous rare earth coordination polymers : effect of lanthanide contraction on crystal architecture and porosity. *Chem. Mater.* **2002**, *14*, 2616-2622.
3. N. Kerbellec; C. Daiguebonne; K. Bernot; O. Guillou; X. Le Guillou, New lanthanide based coordination polymers with high potential porosity. *J. Alloys Compd.* **2008**, *451*, 377-383.
4. W.-X. Zhang; P.-Q. Liao; R.-B. Lin; Y.-S. Wei; M. H. Zeng; X.-M. Chen, Metal Cluster-Based Functional Porous Coordination Polymers. *Coord. Chem. Rev.* **2015**, *293-294*, 263-278.
5. S. Ma; D. Yuan; X. S. Wang; H. C. Zhou, microporous lanthanide MOF containing coordinatively linked interpenetration : syntheses, gas adsorption studies, thermal stability analysis and photoluminescence investigation. *Inorg. Chem.* **2009**, *48*, 2072-2077.
6. L. Z. Zhang; W. Gu; B. Li; X. Liu; D. Z. Liao, {[Nd4(ox)4(NO3)2(OH)2(H2O)2].5H2O } : a porous lanthanide based coordination polymer with a special luminescent properties *Inorg. Chem.* **2007**, *46*, 622-624.
7. J. C. G. Bünzli; S. V. Eliseeva, Intriguing aspect of lanthanide luminescence. *Chem. Sci.* **2013**, *4*, 1039-1049.
8. J. C. G. Bünzli, Rising stars in science and technology : Luminescent lanthanide materials. *Eur. J. Inorg. Chem.* **2017**, 5058-5063.
9. S. V. Eliseeva; J. C. G. Bünzli, Lanthanide luminescence for fonctionnal materials and bio-sciences. *Chem. Soc. Rev.* **2010**, *39*, 189-227.
10. R. Sessoli; K. Bernot, Lanthanides in extended molecular networks. In *Molecular magnetism*, Wiley-VCH Verlag GmbH & Co. KGaA: **2015**, p 89-124.
11. X. Yi; K. Bernot; F. Pointillart; G. Poneti; G. Calvez; C. Daiguebonne; O. Guillou; R. Sessoli, A Luminescent and Sublimable DyIII-Based Single-Molecule Magnet. *Chem. - Eur. J.* **2012**, *18*, 11379-11387.
12. L. Bogani; C. Sangregorio; R. Sessoli; D. Gatteschi, Molecular Engineering for Single-Chain-Magnet Behavior in a One-Dimensional Dysprosium-Nitronyl Nitroxide Compound. *Angew. Chem. Int. Ed.* **2005**, *44*, 5817-5821.
13. K. Bernot; C. Daiguebonne; G. Calvez; Y. Suffren; O. Guillou, A Journey in Lanthanide Coordination Chemistry: From Evaporable Dimers to Magnetic Materials and Luminescent Devices. *Accounts Chem. Res.* **2021**, *54*, 427-440.

14. J. C. G. Bünzli, Benefiting from the unique properties of lanthanide ions. *Accounts Chem. Res.* **2006**, *39*, 53-61.
15. J. D. Rinehart; J. R. Long, Exploiting single-ion anisotropy in the design of f-element single-molecule magnets. *Chem. Sci.* **2011**, *2*, 2078-2085.
16. D. G. Karraker, Coordination of trivalent lanthanide ions. *J. Chem. Educ.* **1970**, *47*, 424-430.
17. Y. Cui; B. Li; H. He; W. Zhou; B. Chen; G. Qian, Metal-organic frameworks as platforms for functional materials. *Accounts Chem. Res.* **2016**, *49*, 483-493.
18. D. Alezi; A. M. P. Peedikakkal; L. Weselinski; V. Guillermin; Y. Belmabkhout; A. J. Cairns; Z. Chen; L. Wojtas; M. Eddaoudi, Quest for highly connected metal-organic framework platforms : rare earth polynuclear clusters versatility meets net topology needs. *J. Am. Chem. Soc.* **2015**, *137*, 5421-5430.
19. D.-X. Xue; Y. Belmabkhout; O. Shekha; H. Jiang; K. Adil; A. J. Cairns; M. Eddaoudi, Tunable rare earth fcu-MOF platform : Access to adsorption kinetics driven gas/vapor separations via pore size contraction. *J. Am. Chem. Soc.* **2015**, *137*, 5034-5040.
20. V. Trannoy; A. N. C. Neto; D. S. C. Brites; L. D. Carlos; H. Serier-Brault, Engineering of mixed Eu³⁺/Tb³⁺ Metal-Organic Frameworks luminescent thermometers with tunable sensitivity. *Advanced Optical Materials* **2021**, 2001938.
21. J. Rocha; D. S. C. Brites; L. D. Carlos, Lanthanide organic framework luminescent thermometers. *Chem. - Eur. J.* **2016**, *22*, 14782-14795.
22. K.-M. Wang; L. Du; Y.-L. Ma; J.-S. Zhao; Q. Wang; T. Yan; Q.-H. Zhao, Multifunctional chemical sensors and luminescent thermometers based on lanthanide metal-organic framework materials. *Cryst. Eng. Comm.* **2016**, *18*, 2690-2700.
23. Y. Cui; W. Zou; R. Song; J. Yu; W. Zhang; Y. Yang; G. Qian, A ratiometric and colorimetric luminescent thermometer over a wide temperature range based on a lanthanide coordination polymer. *Chem. Comm.* **2014**, *50*, 719-721.
24. Y. Cui; H. Xu; Y. Yue; Z. Guo; J. Yu; Z. Chen; J. Gao; Y. Yang; G. Qian; B. Chen, A Luminescent mixed-lanthanide Metal-Organic Framework thermometer. *J. Am. Chem. Soc.* **2012**, *134*, 3979-3982.
25. A. Abdallah; S. Freslon; X. Fan; A. Rojo; C. Daiguebonne; Y. Suffren; K. Bernot; G. Calvez; T. Roisnel; O. Guillou, Lanthanide based coordination polymers with 1,4 carboxyphenylboronic ligand: multi emissive compounds for multi sensitive luminescent thermometric probes. *Inorg. Chem.* **2019**, *58*, 462-475.
26. J.-C. G. Bünzli, Lanthanide luminescence for biomedical analyses and imaging. *Chem. Rev.* **2010**, *111*, 2729-2755.
27. J. He, Xu, J. ; J. Yin; N. Li; X.-H. Bu, Recent advances in luminescent metal-organic frameworks for chemical sensors. *Sci China Mater* **2019**, *62*, 1655-1678.
28. Y. Ning; M. Zhu; J.-L. Zhang, Near-infrared (NIR) lanthanide molecular probes for bioimaging and biosensing. *Coord. Chem. Rev.* **2019**, 213028.
29. W. P. Lustig; J. Li, Luminescent metal organic frameworks and coordination polymers as alternative phosphors for energy efficient lighting devices. *Coord. Chem. Rev.* **2018**, *373*, 116-147.
30. L. L. da Luz; B. F. L. Viana; G. C. O. da Silva; C. C. Gatto; A. M. Fontes; M. Malta; I. T. Weber; M. O. Rodrigues; S. A. Junio, Controlling the energy transfer in lanthanide-organic frameworks for the production of white-light emitting materials. *Cryst. Eng. Comm.* **2014**, *16*, 6914-6918.
31. Q. Tang; S. Liu; Y. Liu; D. He; J. Miao; Y. Ji; Z. Zheng, Color tuning and white light emission via in situ doping of luminescent lanthanide metal-organic frameworks. *Inorg. Chem.* **2014**, *53*, 289-293.
32. O. Guillou; C. Daiguebonne; G. Calvez; K. Bernot, A long journey in lanthanide chemistry : from fundamental crystallography studies to commercial anti-counterfeiting taggants. *Accounts Chem. Res.* **2016**, *49*, 844-856.
33. J. Andres; R. D. Hersch; J. E. Moser; A. S. Chauvin, A new counterfeiting feature relying on invisible luminescent full color images printed with lanthanide-based Inks. *Adv. Func. Mater.* **2014**, *24*, 5029-5036.
34. K. A. White; D. A. Chengelis; K. A. Gogick; J. Stehman; N. L. Rosi; S. Petoud, Near infra-red luminescent lanthanide MOF barcodes. *J. Am. Chem. Soc.* **2009**, *131*, 18069-18071.

35. Z. Gao; B. Xu; T. Zhang; Z. Liu; W. Zhang; X. Sun; Y. Liu; X. Wang; Z. Wang; Y. Yan; F. Hu; X. Meng; Y. S. Zhao, Spatially responsive multicolor lanthanide-MOF heterostructures for covert photonic barcodes. *Angew. Chem. Int. Ed.* **2020**, *59*, 1-6.
36. A. M. Badiane; S. Freslon; C. Daiguebonne; Y. Suffren; K. Bernot; G. Calvez; K. Costuas; M. Camara; O. Guillou, Lanthanide based coordination polymers with a 4,5-dichlorophthalate ligand exhibiting highly tunable luminescence : Toward luminescent bar codes. *Inorg. Chem.* **2018**, *57*, 3399-3410.
37. J. C. G. Bünzli, On the design of highly luminescent lanthanide complexes. *Coord. Chem. Rev.* **2015**, *293-294*, 19-47.
38. J. Liu; A. Kaczmarek; R. Van Deun, Advances in tailoring luminescent rare-earth mixed inorganic materials. *Chem. Soc. Rev.* **2018**, *47*, 7225-7238.
39. Y. Han; P. Yan; J. Sun; G. An; X. Yao; Y. Li; G. Li, Luminescence and white-light emitting luminescent sensor of tetrafluoroterephthalatelanthanide metal-organic frameworks. *Dalton Trans.* **2017**, *46*, 4642-4653.
40. Y. Xiao; S.-H. Wang; F.-K. Zheng; M.-F. Wu; J. Xu; Z.-F. Liu; J. E. Chen; R.-W. Li; G.-C. Guo, Excitation wavelength-induced color tunable and white-light emissions in lanthanide(III) coordination polymers constructed by an environment-dependent luminescent tetrazolate-dicarboxylate ligand. *Cryst. Eng. Comm.* **2016**, *18*, 721-727.
41. Y. Cui; J. Zhang; B. Chen; G. Qian, Lanthanide Metal-Organic Frameworks for Luminescent Applications. *Handbook on the Physics and Chemistry of Rare Earths* **2016**, *50*, 243-268.
42. J.-F. Lecomte; L. Guénée; C. Beuchat; T. A. Wesolowski; P. Mukherjee; D. H. Waldeck; K. A. Gogick; S. Petoud; C. Piguet, Optimizing sensitization processes in dinuclear luminescent lanthanide oligomers : Selection of rigid aromatic spacers. *J. Am. Chem. Soc.* **2011**, *133*, 16219-16234.
43. X. Fan; S. Freslon; C. Daiguebonne; L. Le Polles; G. Calvez; K. Bernot; O. Guillou, A family of lanthanide based coordination polymers with boronic acid as ligand. *Inorg. Chem.* **2015**, *54*, 5534-5546.
44. Y. Luo; Y. Zheng; G. Calvez; S. Freslon; K. Bernot; C. Daiguebonne; T. Roisnel; O. Guillou, Synthesis, crystal structure and luminescent properties of new lanthanide-containing coordination polymers Involving 4,4'-oxy-bis-benzoate as Ligand. *Cryst. Eng. Comm.* **2013**, *15*, 706-720.
45. Y. Qiu; C. Daiguebonne; J. Liu; R. Zeng; N. Kerbellec; H. Deng; O. Guillou, Four three-dimensionnal lanthanide coordination polymers constructed from benzene-1,4-dioxyacetic acid. *Inorg. Chim. Acta* **2007**, *360*, 3265-3271.
46. V. Guillerme; L. Weselinski; Y. Belmabkhout; A. J. Cairns; V. D'Elia; L. Wojtas; K. Adil; M. Eddaoudi, Discovery and introduction of a (3,18)-connected net as an ideal blueprint for the design of metal-organic frameworks. *Nat. Chem.* **2014**, *6*, 673-680.
47. G. Calvez; C. Daiguebonne; O. Guillou, Unprecedented lanthanide containing coordination polymers constructed from hexanuclear molecular building blocks: $\{[Ln_6O(OH)_8](NO_3)_2(bdc)(Hbdc)_2, 2NO_3, H_2bdc]\}_n$. *Inorg. Chem.* **2011**, *50*, 2851-2858.
48. Z. Zheng, Cluster compounds of rare-earth elements. In *Handbook on the Physics and Chemistry of Rare Earths*, Gschneidner, K. A.; Bünzli, J. C. G.; Pecharsky, V. K., Eds. Elsevier: **2010**; Vol. 40, p 109-239.
49. X. J. Zheng; L. P. Jin; S. Gao, Synthesis and Characterization of two Novel Lanthanide Coordination polymers with an open framework Based on an Unprecedented $[Ln_7(\mu_3-OH)_8]^{13+}$ cluster. *Inorg. Chem.* **2004**, *43*, 1600-1602.
50. D. L. Dexter, A theory of sensitized luminescence in solids. *J. Chem. Phys.* **1953**, *21*, 836-850.
51. T. Förster, *Comparative effects of radiation*. John Wiley & Sons: New-York, **1960**.
52. Y. Pointel; Y. Suffren; C. Daiguebonne; F. Le Natur; S. Freslon; G. Calvez; K. Bernot; O. Guillou, Rational design of dual IR and visible highly luminescent light lanthanides based coordination polymers. *Inorg. Chem.* **2020**, *59*, 10673-10687.
53. Y. Pointel; F. Houard; Y. Suffren; C. Daiguebonne; F. Le Natur; S. Freslon; G. Calvez; K. Bernot; O. Guillou, High luminance of hetero lanthanide based molecular alloys by phase-induction strategy. *Inorg. Chem.* **2020**, *59*, 11028-11040.

54. I. Badiane; S. Freslon; Y. Suffren; C. Daiguebonne; G. Calvez; K. Bernot; M. Camara; O. Guillou, High britness and easy color modulation in lanthanide-based coordination polymers with 5-methoxyisophthalate as ligand: Toward emission colors additive strategy. *Cryst. Growth Des.* **2017**, *17*, 1224-1234.
55. G. Calvez; F. Le Natur; C. Daiguebonne; K. Bernot; Y. Suffren; O. Guillou, Lanthanide-based hexanuclear complexes and their use as molecular precursors. *Coord. Chem. Rev.* **2017**, *340*, 134-153.
56. Z. Zheng, Assembling lanthanide hydroxo clusters. *Chemtracts - Inorganic Chemistry* **2003**, *16*, 1-12.
57. Z. Zheng, Ligand-controlled self-assembly of polynuclear lanthanide-oxo/hydroxo complexes: from synthetic serendipity to rational supramolecular design. *Chem. Comm.* **2001**, 10.1039/b107971a, 2521-2529.
58. D. A. Galico; A. A. Kitos; J. Ovens; F. A. Sigoli; M. Murugesu, Untapped potentials of lanthanide-based molecular clusteraggregates: optical barcoding and white-light emission with nanosized $\{Ln_{20}\}$ compound. *Angew. Chem. Int. Ed.* **2021**, *60*, 6130-6136.
59. G. Giester; Z. Zak; P. Unfried, Syntheses and crystal structures of rare earth basic nitrates hydrates. *J. Alloys Compd.* **2009**, *481*, 116-128.
60. G. Giester; Z. Zak; P. Unfried, Syntheses and crystal structures of rare earth basic nitrates hydrates: Part III. $[Ln_6(\mu_6-O)(\mu_3-OH)_8(H_2O)_{12}(NO_3)_6](NO_3)_2 \cdot xH_2O$, Ln=Y, Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb, Lu; x=0;3, 4, 5, 6. *J. Alloys Compd.* **2009**, *481*, 116-128.
61. G. Giester; P. Unfried; Z. Zak, Syntheses and crystal structures of some new rare earth basic nitrates II : $[Ln_6O(OH)_8(H_2O)_{12}(NO_3)_6](NO_3)_2 \cdot xH_2O$, Ln=Sm, Dy, Er ; x(Sm)=6, x(Dy)=5, x(Er)=4. *J. Alloys Compd.* **1997**, *257*, 175-181.
62. C. L. Lengauer; G. Giester; P. Unfried, $Sm(OH)_2NO_3$: synthesis, characterization, powder diffraction data and structure refinement by Rietveld technique. *Powder Diffr.* **1994**, *9*, 115-118.
63. Z. Zak; P. Unfried; G. Giester, The structures of some rare earth basic nitrates $[Ln_6(\mu_6-O)(\mu_3-OH)_8(H_2O)_{12}(NO_3)_6](NO_3)_2 \cdot xH_2O$, Ln=Y, Gd, Yb ; x(Y, Yb)=4, x(Gd)=5. A novel rare earth metal cluster of the M_6X_8 type with interstitial O atom. *J. Alloys Compd.* **1994**, *205*, 235-242.
64. H. Yao; G. Calvez; C. Daiguebonne; K. Bernot; Y. Suffren; O. Guillou, Hetero-hexalanthanide complexes: A new synthetic strategy for molecular thermometric probes. *Inorg. Chem.* **2019**, *58*, 16180-16193.
65. H. Yao; G. Calvez; C. Daiguebonne; K. Bernot; Y. Suffren; M. Puget; C. Lescop; O. Guillou, Hexalanthanide complexes as molecular precursors: synthesis, crystal structure and luminescent and magnetic properties. *Inorg. Chem.* **2017**, *56*, 14632-14642.
66. F. Le Natur; G. Calvez; J. P. Guégan; L. Le Polles; X. Trivelli; K. Bernot; C. Daiguebonne; C. Neaime; K. Costuas; F. Grasset; O. Guillou, Characterization and luminescence properties of lanthanide based polynuclear complexes nanoaggregates. *Inorg. Chem.* **2015**, *54*, 6043-6054.
67. F. Le Natur; G. Calvez; C. Daiguebonne; O. Guillou; K. Bernot; J. Ledoux; L. Le Polles; C. Roiland, Coordination polymers based on hexanuclear rare earth complexes : Toward independant luminescence brightness and color emission. *Inorg. Chem.* **2013**, *52*, 6720-6730.
68. G. Calvez; C. Daiguebonne; O. Guillou; T. Pott; P. Méléard; F. Le Dret, Lanthanide-based hexanuclear complexes usable as molecular precursor for new hybrid materials : state of the art. *C. R. Chimie* **2010**, *13*, 715-730.
69. X.-S. Wu; Y.-B. Zhang; X. Li; P. Z. Li, Two 1-D europium coordination polymers: synthesis, crystal structure and fluorescence. *J. Coord. Chem.* **2009**, *62*, 797-807.
70. S. I. Weissman, Intramolecular energy transfer - The fluorescence of complexes of europium. *J. Chem Phys* **1942**, *10*, 214-217.
71. G. Calvez; O. Guillou; C. Daiguebonne; P.-E. Car; V. Guillerm; Y. Gérault; F. L. Dret; N. Mahé, Octahedral hexanuclear complexes involving light lanthanide ions. *Inorg. Chim. Acta* **2008**, *361*, 2349-2356.
72. N. Mahé; O. Guillou; C. Daiguebonne; Y. Gérault; A. Caneschi; C. Sangregorio; J. Y. Chane-Ching; P. E. Car; T. Roisnel, Polynuclear lanthanide hydroxo complexes : new chemical precursors for coordination polymers. *Inorg. Chem.* **2005**, *44*, 7743-7750.


73. J. F. Desreux, In *Lanthanide Probes in Life, Chemical and Earth Sciences*, Choppin, G. R.; Bünzli, J. C. G., Eds. Elsevier: Amsterdam, **1989**; Vol. Elsevier, p 43.
74. A. Altomare; M. C. Burla; M. Camalli; G. Cascarano; C. Giacovazzo; A. Guagliardi; A. G. G. Moliterni; G. Polidori; R. Spagna, SIR97: a new tool for crystal structure determination and refinement *J. Appl. Crystallogr.* **1999**, *32*, 115-119.
75. G. M. Sheldrick, A short history of SHELX. *Acta Crystallogr. A* **2008**, *64*, 112-122.
76. G. M. Sheldrick; T. R. Schneider, SHELXL : High-Resolution Refinement. *Macromol. Crystallogr. B* **1997**, 319-343.
77. L. J. Farrugia, WinGX suite for smallmolecule single-crystal crystallography. *J. Appl. Crystallogr.* **1999**, *32*, 837-838.
78. L. J. Farrugia, WinGX and ORTEP for Windows: an update. *J. Appl. Crystallogr.* **2012**, *45*, 849-854.
79. R. H. Blessing, An empirical correction for absorption anisotropy. *Acta Crystallogr.* **1995**, *A51*, 33-38.
80. A. S. Chauvin; F. Gumy; D. Imbert; J. C. G. Bünzli, Europium and terbium tris(dipicolinate) as secondary standards for quantum yield determination. *Spectrosc Lett* **2004**, *37*, 512-532.
81. G. Wyszecki, Colorimetry. In *Handbook of Optics*, Driscoll, W. G.; Vaughan, W., Eds. Mac Graw-Hill Book Company: New-York, **1978**, p 1-15.
82. CIE, *International Commission on Illumination - Technical report*. CIE: **1995**; Vol. 13-3, p 16.
83. V. Kopsky; D. B. Litvin, *INTERNATIONAL TABLES FOR CRYSTALLOGRAPHY. Volume E: SUBPERIODIC GROUPS*. John Wiley & sons, Ltd: **2010**; Vol. E.
84. O. Guillou; C. Daiguebonne; G. Calvez; F. Le Dret; P. E. Car, Structuring effect of $[\text{Ln}_6\text{O}(\text{OH})_8(\text{NO}_3)_6(\text{H}_2\text{O})_{12}]^{2+}$ entities. *J. Alloys Compd.* **2008**, *451*, 329-333.
85. G. Calvez; K. Bernot; O. Guillou; C. Daiguebonne; A. Caneschi; N. Mahé, Sterically-induced synthesis of 3d-4f one-dimensional compounds: a new route towards 3d-4f Single Chain Magnets. *Inorg. Chim. Acta* **2008**, *361*, 3997-4003.
86. H. Yao; G. Calvez; C. Daiguebonne; Y. Suffren; K. Bernot; O. Guillou, Hexa-nuclear molecular precursors as tools to design luminescent coordination polymers with lanthanide segregation. **2021**, 10.1021/acs.inorgchem.1c02662.
87. J. C. G. Bünzli; S. V. Eliseeva, Basics of lanthanide photophysics. In *Lanthanide Luminescence*, Hänninen, P.; Härmä, H., Eds. Springer Berlin Heidelberg: **2010**; Vol. 7, p 1-45.
88. C. Piguet; J. C. G. Bünzli; G. Bernardinelli; G. Hopfgatner; A. F. Williams, Self-assembly and photophysical properties of lanthanide dinuclear triple-helical complexes. *J. Am. Chem. Soc.* **1993**, *115*, 8197-8206.
89. L. Prodi; M. Maestri; R. Ziesel; V. Balzani, Luminescent Eu^{3+} , Tb^{3+} and Gd^{3+} complexes of a branched triazacyclononane ligand containing three 2,2'bipyridine units. *Inorg. Chem.* **1991**, *30*, 3798-3802.
90. S. Quici; M. Cavazzini; G. Marzanni; i. G. Accors; N. Armaroli; B. Ventura; F. Barigelletti, Visible and near-infrared luminescence from water soluble Lanthanide complexes. *Inorg. Chem.* **2005**, *44*, 529-537.
91. M. D. Ward, Transition metal sensitized near infrared luminescence from lanthanide in d-f heteronuclear arrays. *Coord. Chem. Rev.* **2007**, *251*, 1663-1677.
92. C. Galaup; J.-M. Couchet; S. Bedel; P. Tisnès; C. Picard, Direct access to terpyridine-containing polyazamacrocycles as photosensitizing ligands for Eu(III) luminescence in aqueous media. *J. Org. Chem.* **2005**, *70*, 2274-2284.
93. S. Freslon; Y. Luo; G. Calvez; C. Daiguebonne; O. Guillou; K. Bernot; V. Michel; X. Fan, Influence of photo-induced electron transfer on lanthanide-based coordination polymers luminescence : A comparison between two pseudo-isorecticular molecular networks. *Inorg. Chem.* **2014**, *53*, 1217-1228.
94. W. T. Carnall; P. R. Fields; K. Rajnak, Energy levels in the trivalent lanthanide ions. III. Tb^{3+} . *J. Chem. Phys.* **1968**, *49*, 4447-4450.

95. W. T. Carnall; P. R. Fields; K. Rajnak, Electronic energy levels of the trivalent lanthanide ions. IV. Eu^{3+} . *J. Chem. Phys.* **1968**, *49*, 4450-4455.
96. S. Freslon; Y. Luo; C. Daiguebonne; G. Calvez; K. Bernot; O. Guillou, Brightness and color tuning in a series of lanthanide-based coordination polymers with benzene 1,2,4,5-tetracarboxylic acid as ligand. *Inorg. Chem.* **2016**, *55*, 794-802.
97. A. K. Cheetham; C. N. R. Rao; R. K. Feller, Structural diversity and chemical trends in hybrid inorganic–organic framework materials. *Chem. Comm.* **2006**, 4780-4785.

Journal Pre-proof

TABLE OF CONTENT.

A new series of lanthanide coordination polymers obtained from hexa-lanthanide complexes by a microwave assisted synthesis with a strong intermetallic energy transfer.



Journal Pre-proof