



HAL
open science

Insight into the factors affecting the performances of a conventional GaAs solar cell operating at up to 200 °C

Paul Oublon, Alexandre Arnoult, Maxime Levillayer, Frédéric Martinez, Inès Massiot, S. Parola, Guilhem Almuneau, Yvan Cuminal, Rodolphe Vaillon

► To cite this version:

Paul Oublon, Alexandre Arnoult, Maxime Levillayer, Frédéric Martinez, Inès Massiot, et al.. Insight into the factors affecting the performances of a conventional GaAs solar cell operating at up to 200 °C. Journées Nationales du Photovoltaïque 2021, Nov 2021, Dourdan, France. hal-03515509

HAL Id: hal-03515509

<https://hal.science/hal-03515509>

Submitted on 26 Oct 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Insight into the factors affecting the performances of a conventional GaAs solar cell operating at up to 200 °C

Paul Oublou¹, Alexandre Arnoult², Maxime Levillayer², Frédéric Martinez¹, Inès Massiot²,
Stéphanie Parola¹, Guilhem Almuneau², Yvan Cuminal¹, Rodolphe Vaillon¹

¹IES, Univ Montpellier, CNRS, Montpellier, France

²LAAS-CNRS, Toulouse, France

In certain configurations, solar cells are operating under thermal stress, i.e. at temperatures far beyond those of the Standard Test Conditions (STC, 25 °C) [1]. In space for near-the-sun missions [2] or in terrestrial photovoltaic -thermal [3] or -thermoelectric [4] or -CSP [5] hybrid systems, cells can reach temperatures from 150 °C up to more than 400 °C. New methodologies aiming at designing, fabricating and characterizing such components are required. The main unknowns are the physical properties of the materials involved and the physical phenomena affecting the photovoltaic conversion performances of cells at such large temperatures.

To contribute to addressing these unknowns, our research work consists in analyzing the performances of conventional GaAs solar cells - optimized in the STC -, but operating under thermal stress (at up to 200 °C). Such cells are fabricated using solid source Molecular Beam Epitaxy and conventional clean room processes, and their performances are characterized by measuring the I-V curves in the dark and under illumination, the spectral response, and the reflectance of the cells as a function of temperature, from 25 to 200 °C.

Factors responsible for the expected degradation of performances with temperature are analyzed using TCAD 1D-simulations and pseudo-3D modeling [6]. The temperature sensitivity of carrier mobilities and contact resistances are examined by Hall effect and CTLM measurements (Figure 1). In particular, we show that the reliability of the methodology for characterizing the contacts is strongly dependent on the number and quality of the samples. Therefore, we propose a novel approach which eliminates some usual simplifying assumptions and considers the propagation of measurement errors by using a Monte Carlo technique (Figure 1-2).




Figure 1. CTLM measurement considering non-linear equations resolution and error propagation. Experimental data (circle) of CTLM measurement for Ti/Pt/Au on p-GaAs at 200 °C, and nonlinear extraction equation (red line). Error bars are not significant enough to be illustrated in the figure.




Figure 2. Comparison between experimental specific contact resistivity data (circle) for Ti/Pt/Au (20/30/200 nm) on p-GaAs ($N_d = 1 \times 10^{19} \text{ cm}^{-3}$) extracted from CTLM measurement and model (red line) with respect to the temperature. AuGeNi on p-GaAs was discarded after similar experiment because the specific contact resistance was too high and presents a lower stability to high temperature.

- [1] R. Vaillon et al., Solar cells operating under thermal stress, Cell Reports Physical Science, 2020.
- [2] E. López et al., Optimum single-gap solar cells for missions to Mercury, Journal of Spacecraft and Rockets, 2016.
- [3] C. Lamnatou et al., Photovoltaic/thermal systems based on concentrating and non-concentrating technologies: Working fluids at low, medium and high temperatures, Renewable and Sustainable Energy Reviews, 2021.
- [4] D. Narducci et al., Hybrid and Fully Thermoelectric Solar Harvesting, Springer, 2018.
- [5] J. Zeitouny et al., Assessing high-temperature photovoltaic performance for solar hybrid power plants, Solar Energy Materials and Solar Cells, 2018.
- [6] S. Parola et al., Improved efficiency of GaSb solar cells using an $\text{Al}_{0.50}\text{Ga}_{0.50}\text{As}_{0.04}\text{Sb}_{0.96}$ window layer, Solar Energy Materials and Solar Cells, 2019.

Acknowledgements

The work is supported by the program « Investments for the future » managed by the French National Research Agency (ANR) under contract ANR-10-LABX-22-01-SOLSTICE.