

In Situ Raman Spectroscopy Monitoring of Material Changes During Proton Irradiation

Aurélien Canizarès, Frédéric Foucher, Mickael Baqué, Jean-Pierre de Vera, Thierry Sauvage, Olivier Wendling, Aurelien Bellamy, Paul Sigot, Thomas Georgelin, Patrick Simon, et al.

▶ To cite this version:

Aurélien Canizarès, Frédéric Foucher, Mickael Baqué, Jean-Pierre de Vera, Thierry Sauvage, et al.. In Situ Raman Spectroscopy Monitoring of Material Changes During Proton Irradiation. Applied Spectroscopy, 2022, pp.000370282110629. 10.1177/00037028211062943 . hal-03560256

HAL Id: hal-03560256 https://hal.science/hal-03560256

Submitted on 12 Apr 2024 $\,$

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

In situ Raman spectroscopy monitoring of material changes during proton irradiation

Mickael Baqué¹, Frédéric Foucher², Aurélien Canizarès³, Jean-Pierre de Vera⁴, Thierry Sauvage³, Olivier Wendling³,

Aurélien Bellamy³, Paul Sigot³ Thomas Georgelin³, Frances Westall²,

¹German Aerospace Center (DLR), Institute of Planetary Research, Department of Planetary Laboratories,

Astrobiological Laboratories, Berlin, Germany

²CNRS, CBM, UPR 4301, rue Charles Sadron, CS80054, 45071 Orléans Cedex 2, France

³CNRS, CEMHTI UPR3079, Univ. Orléans, F-45071 Orléans, France

⁴German Aerospace Center (DLR), Space Operations and Astronaut Training, MUSC, Linder Höhe, Cologne,

Germany.

Introduction: Organic molecules are prime targets for the search for life on other planetary bodies in the Solar System. Understanding their preservation potential and detectability after ionic irradiation, with fluencies potentially representing those received for several millions to billions of years at Mars or in interplanetary space, is a crucial goal for astrobiology research (Hassler et al. 2014). Particles of different energies and fluencies can indeed induce breaking of molecular bonds, depolymerization, and temperature increase among others. However, materials can evolve rapidly after irradiation and the changes, between the irradiation chamber and the ex situ laboratory analysis conditions (and environment), are hard to predict and time and sample consuming. The possibility to monitor changes in the sample in situ in the chamber thus constitutes an important breakthrough for the domain. In order to be able to perform in situ characterization of organic molecules under ionic irradiation, a feasibility experiment was performed with polymer test samples to validate the optical configuration and the irradiation chamber geometry (Fig. 1). Indeed, polymers are known to be sensitive to proton irradiation and they usually give Raman spectra with high signal to noise ratio (Samuel 2020). We present here a Raman in situ investigation of the evolution of a series of polymers during proton irradiation, for which a new type of Raman optical probe was designed.

Material and methods: In order to demonstrate the relevance of the coupling, a series of commercial polymers has been analyzed: polyvinyl chloride (PVC), polyamide (PA), polyethylene (PET), polystyrene (PS), and polypropylene (PP). The experiments were carried out in the Micro-beam line vacuum chamber with a 2.8 MeV proton (H⁺) beam at the CEMHTI Pelletron facility (http://emir.in2p3.fr/CEMHTI), CNRS, Orléans (Fig. 1). Samples were irradiated using a flux of $5x10^{10}$ protons.cm⁻².s⁻¹ to obtain different fluence values from $5x10^{12}$ to $3x10^{14}$ protons.cm⁻². The probe is a 0.15 numerical aperture optic giving a 0.4 mm diameter spot size at the surface of the sample and a 1.5 mm depth of focus. The laser used was a 532 nm Excelsior Spectra Physics laser, and the spectrometer a Renishaw RA100 (1800 lines/mm grating, 250 mm focal length) with a spectral resolution 3.5-1.65 cm⁻¹. The samples were alternately moved from the irradiation position to the Raman analysis position using a x,y goniometer.




Fig. 1. Raman spectrometer probe interfaced with the Pelletron irradiation chamber, CEMHTI, CNRS, Orléans, France.

Summary: The coupling of particle irradiation with in situ Raman detection is particularly relevant for present and future missions to Mars like NASA Mars2020 and ESA/Roscosmos ExoMars2022 rovers carrying Raman instruments (Rull et al. 2017). Using a series of polymers as a proof of concept, we showed that the kinetics of alteration may vary drastically from one sample to another. Indeed, proton irradiation (with a final fluence of 3.10^{14} protons.cm⁻²) leads to an increase in the background level of the signal, potentially explained by the scission of the polymeric chains and by the atom displacements creating defects in the materials. Further improvements of the system are underway to reduce the Raman probe working distance, include a cooled sample holder, and allow for Raman mapping to apply to biomolecular samples of relevance for astrobiology.

Acknowledgment: The authors thank the French space agency Centre National d'Etudes Spatiales (CNES) for funding. MB acknowledges the support of the Deutsche Forschungsgemeinschaft (DFG) for the project "Raman Biosignatures for Astrobiology Research" (RaBioFAM; project number: 426601242). The authors thank Dr Guillaume Collet for the Nikon AZ100 observations.

References: Hassler D.M. et al. (2014) *Science*, 343(6169), 1244797.

Samuel A.Z. (2020) Spectrochim Acta, Part A, 224:117431.

Rull F. et al (2017) Astrobiology, 17(6-7):627-654.