

# Molecular study of waterproofing agents from the Zambratija wreck

Armelle Charrié-Duhaut

### ▶ To cite this version:

Armelle Charrié-Duhaut. Molecular study of waterproofing agents from the Zambratija wreck. I. Koncani Uhac; G. Boetto; M. Uhac. Zambratija, prehistoric sewn boat. Results of the archaeological research, analysis and study, Arheološki muzej Istre, 2019. hal-03565647

## HAL Id: hal-03565647 https://hal.science/hal-03565647

Submitted on 11 Feb2022

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

#### Molecular study of waterproofing agents from the Zambratija wreck

Armelle Charrié

To identify the nature of macro-residues of the protective coating used to waterproof the hull of the Zambratija boat, chemical analyses were undertaken. These analyses combine the techniques conventionally used for this type of organic material, namely infrared spectroscopy and gas chromatography coupled with mass spectrometry (GC-MS). This study was carried out on two samples described herein.

N° sample	Description	Observations
Z1	inner face of the	Light brown powder, almost
	axial element P2	completely soluble in
Z2	inner face of the plank P1	dichloromethane

#### Methodology

An account of the basic principles of the procedure used to study this type of archaeological material is reported in several publications (Charrié-Duhaut *et al.* 2009a; 2009b). The molecular approach is based on the identification of diagnostic biomarkers derived from naturally occurring organic substances. Biomarkers are compounds that have retained a carbon skeleton specific enough to be related to their biological precursor, thus enabling identification of the natural substances used. In case of alteration, it is possible to rely on specific degradation by-products (Burger *et al.* 2009).

At first, the samples were analysed by attenuated total reflection – Fourier-transform infrared spectroscopy (ATR – FTIR). The powder sample is directly deposited on the crystal. The device used was a Golden Gate spectrometer (Bruker) operating in mono-ATR mode (64 scans recorded). Then the samples were solubilized ultrasonically with a mixture of dichloromethane/methanol (1:1 v/v). The solution obtained is then silylated using BSTFA + TMSC (99:1). GC-MS analyses were carried out using a Focus Gas chromatograph interfaced with a ISQ mass detector (injector initial temperature: 35°C, HP-5 MS column, 30 m x 0.25 mm i.d., 0.1 µm film thickness, temperature program: 40°C (1 min), 40-100°C (10°C/min), 100-300°C (4°C/min), isothermal 300°C). Helium was used as carrier gas. Mass spectra were produced at 70eV, source 180°C, in full detection mode over 50-700 amu.

#### **Results and discussion**

The FTIR spectra of the two samples are similar. The stretching vibrations of the -CH<sub>2</sub> and -CH<sub>3</sub> groups (2956-2922-2869 cm<sup>-1</sup>), as well as their bending bands (1458-1384 cm<sup>-1</sup>), account for the hydrocarbon skeleton of the residue. However, the absence of carbonyl groups that are usually expressed by the vibrations of elongations at 1717 and 1701 cm<sup>-1</sup> and of aromatic rings at 1600 cm<sup>-1</sup> is noteworthy. The absorbance profiles seem different from that usually observed for a product derived from conifers, more specifically from the family of Pinaceae (Colombini *et al.* 2003; Izzo *et al.* 2013).

The GC-MS profiles of the two samples are again very similar. They are predominantly dominated by diterpenic compounds all derived from abietic and pimaric acid (Fig. 1). These derivatives are diagnostic of coniferous oils, resins, and tars (Bailly *et al.* 2013; Bailly 2015).

The presence of aromatic compounds (retene, tetrahydroretene, 19-norabiétatriene, 18norabietatriene for the main) indicates a product having undergone heating, and therefore probably pitch, tar obtained by heating coniferous wood (Fig. 2). Heating, however, remained moderate since the proportion of polyaromatic hydrocarbons remains low compared to acids. The predominance of dehydroabietic acid, the presence in significant amounts of abietic, pimaric, isopimaric acid indicates a low degree of alteration.

Bailly *et al.* (2016) described a series of alkyl guaiacyl dehydroabietates as novel markers of pitch. Such mixed esters between dehydroabietic acid and alkylmethoxyphenols were identified in the two samples. They are characterized by the fragments m/z 173 and 255 (characteristic of the "dehydroabietate" part) and a molecular mass of 436 u.m.a.

#### Conclusion

The molecular data clearly show that the two samples correspond to pitch, characterized by the identification of diterpenic structures related to abietic / pimaric acid and alkyl guaiacyl dehydroabietates.

#### **Captions and figures**

Fig. 1: Examples of diagnostic compounds of pitch.




Fig. 2: GC-MS profiles of samples Z1/8 and Z2

