



**HAL**  
open science

## Assessment of parameters variations for treatment of CO<sub>2</sub> laser carburizing over AISI 4340 steel

Renato Barros, Karl Delbé, Jean Denape, Humberto Rodrigues, Jorge Abdalla

### ► To cite this version:

Renato Barros, Karl Delbé, Jean Denape, Humberto Rodrigues, Jorge Abdalla. Assessment of parameters variations for treatment of CO<sub>2</sub> laser carburizing over AISI 4340 steel. Journées Internationales Francophones de Tribologie, May 2015, Nantes, France. pp.1-2. hal-03662179

**HAL Id: hal-03662179**

**<https://hal.science/hal-03662179>**

Submitted on 9 May 2022

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



## Open Archive TOULOUSE Archive Ouverte (OATAO)

OATAO is an open access repository that collects the work of Toulouse researchers and makes it freely available over the web where possible.

This is an author-deposited version published in : <http://oatao.univ-toulouse.fr/>  
Eprints ID : 15595

**To cite this version** : Barros, Renato and Delbé, Karl and Denape, Jean and Rodrigues, Humberto and Abdalla, Jorge *Assessment of parameters variations for treatment of CO2 laser carburizing over AISI 4340 steel*. (2015) In: Journées Internationales Francophones de Tribologie, 27 May 2015 - 29 May 2015 (Nantes, France). (Unpublished)

Any correspondence concerning this service should be sent to the repository administrator: [staff-oatao@listes-diff.inp-toulouse.fr](mailto:staff-oatao@listes-diff.inp-toulouse.fr)

## Assessment of parameters variations for treatment of CO<sub>2</sub> laser carburizing over AISI 4340 steel

Renato BARROS<sup>1\*</sup>, Karl DELBÉ<sup>2</sup>, Jean DENAPE<sup>2</sup>,  
Humberto RODRIGUES<sup>3</sup>, Jorge ABDALLA<sup>4</sup>

<sup>1</sup>FEG/UNESP – Faculdade de Engenharia de Guaratinguetá,  
Departamento de Materiais e Tecnologia, Guaratinguetá – Brazil

<sup>2</sup>INPT-ENIT/LGP – Ecole Nationale d'Ingénieurs de Tarbes,  
Laboratoire Génie de Production, Tarbes – France

<sup>3</sup>FATEC – Faculdade de Tecnologia e Ciências – Pindamonhangaba – Brazil

<sup>4</sup>IEAV/DCTA – Instituto de Estudos Avançados, Departamento de Ciência e Tecnologia  
Aeroespacial, Divisão de Fotônica EFO-O, São José dos Campos – Brazil

\*Correspondent author: greensleeves@uol.com.br - +33 05 62 44 27 53

Poster proposal

**Keywords:** AISI 4340 steel, surface treatments, laser carburizing, microscratch tests.

### Abstract

This study evaluated the best parameters for the carburizing treatment using a CO<sub>2</sub> laser of low power over an AISI 4340 steel previously subjected to heat treatments of quenching and tempering. The coating process used a liquid dispersion of carbon black in ethanol and carboxyl methylcellulose. The laser power was kept constant at 125 W and the resolution is 600 dots per inch. The variable parameter of CO<sub>2</sub> laser was the speed. Two speeds were selected for the coating preparation: 1200 and 2000 m/s. After treatment, metallographic preparation and optical microscopy observation were performed in addition to the evaluation of parameter variations through hardness measurements and microscratch tests.

Observations of polished cross sections show that treatment produce a multiphase region successively composed of a superficial coated zone (CZ) with a high content of carbon and iron (carburized layer), a zone of interaction (ZI) affected by carbon diffusion and a heat-affected zone (HAZ). The laser treatment performed at a speed of 1200 m/s provided a greater inhomogeneity for the CZ (Fig. 1a) than the treatment carried out at a speed of 2000 m/s (Fig. 1b). The carburized layer presents Vickers hardness values in the order of 800 HV, much higher than the metal base (MB), 300 HV and the HAZ, 500 HV.




Figure 1: Polished cross section of AISI 4340 steel substrate with a carburizing treatment using a CO<sub>2</sub> laser treated at 1200 m/s (a) and 2000 m/s (b), showing different layers of treated surface: Coated Zone (CZ), Zone of Interaction (ZI), Heat Affected Zone (HAZ) and Metal Base (MB).

The scratch tests were realized using a Vickers slider over a distance of 5 mm at a constant sliding speed of 30 mm/min. Three progressive loading conditions were carried out: from 0 to 5 N, from 0 to 10 N and finally, from 0 to 20 N.

Low friction coefficients close to 0.1 are recorded, independently of load, but treatments performed at higher laser speeds show a greater stability (Fig. 2). The groove width and depth as a function of load was measured with optical profilometry along the sliding distance, in order to detect the appearance of the substrate on the groove base.




Figure 2: Friction coefficient as a function of normal load for samples treated with a laser speed of 1200 m/s (a) and 2000 m/s (b)

Finally, optical observations of the tracks reveal the damage changes during the sliding. For similar tests, with the same progressive normal load, the dimensions of the wear track look bigger for a coating prepared at a speed of 1200 m/s than at 2000 m/s. Deformation of the coating is the main accommodation mechanism, whatever the loading level, indicating a lack of the coating adhesion (fig. 3).




Figure 3 : Comparison in detail between scratch morphologies after microscratch tests of the surfaces treated at speed of 1200 m/s (a) and 2000 m/s (b). Normal load is progressively increase from left to right.

Indeed, the laser speed of 2000 m/s provided the best results reached. This may be related to a better quality of coated zone, as a result of better carbon deposition on the surface.

## References

1. ABDALLA, A. J.; HASHIMOTO, T. M.; MOURA NETO, C.; PEREIRA, M. S.; SOUZA, N. S.; MENDES, F. A. Alterações nas propriedades mecânicas em aços 4340 e 300M através de tratamentos térmicos isotérmicos e intercríticos., *Congresso Anual da ABM*, 59, São Paulo, Anais. São Paulo: ABM, 2004.
2. REIS, J. L., Tratamento térmico superficial do aço AISI M2 via laser de CO<sub>2</sub>. 2009. 104f. *Tese de mestrado em Física e Química dos Materiais Aeroespaciais*, Instituto Tecnológico de Aeronáutica, São José dos Campos.