

# Exciton ionization induced by intersubband absorption in non-polar ZnO/ZnMgO quantum wells at room temperature

A Jollivet, P Quach, M Tchernycheva, R Ferreira, E Di Russo, L Rigutti, B Vinter, N Le Biavan, D Lefebvre, M Hugues, et al.

## ▶ To cite this version:

A Jollivet, P Quach, M Tchernycheva, R Ferreira, E Di Russo, et al.. Exciton ionization induced by intersubband absorption in non-polar ZnO/ZnMgO quantum wells at room temperature. Physical Review B, 2022, 105 (19), pp.195143. 10.1103/PhysRevB.105.195143. hal-03694675

# HAL Id: hal-03694675 https://hal.science/hal-03694675v1

Submitted on 13 Jun2022

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Exciton ionization induced by intersubband absorption

### in non-polar ZnO/ZnMgO quantum wells at room temperature.

A. Jollivet<sup>1</sup>, P. Quach<sup>1</sup>, M. Tchernycheva<sup>1</sup>, R. Ferreira<sup>2</sup>, E. Di Russo<sup>3</sup>, L. Rigutti<sup>3</sup>, B.
Vinter<sup>4</sup>, N. le Biavan<sup>4</sup>, D. Lefebvre<sup>4</sup>, M. Hugues<sup>4</sup>, J-M. Chauveau<sup>4</sup>, F. H. Julien<sup>1</sup>

<sup>1</sup> Centre de Nanosciences et de Nanotechnologies, CNRS, Université Paris-Saclay, 91120 Palaiseau, France.

<sup>2</sup> Laboratoire de Physique de l'Ecole Normale Supérieure, ENS, Université PSL, CNRS,

Sorbonne Université, Université de Paris, F-75005 Paris, France

<sup>3</sup> Normandie Univ., UNIROUEN, INSA Rouen, CNRS, Groupe de Physique des Matériaux, 76000 Rouen, France.

<sup>4</sup> Université Côte d'Azur, CNRS, CRHEA, Valbonne, France

Corresponding author: <a href="mailto:arnaud.jollivet@c2n.upsaclay.fr">arnaud.jollivet@c2n.upsaclay.fr</a>

#### Abstract:

We present a systematic investigation of intersubband transitions in non-intentionallydoped m-plane ZnO/ZnMgO quantum wells (QWs). The investigation is performed using photo-induced absorption spectroscopy at room temperature under optical pumping by a UV laser to generate electron-hole pairs. All samples exhibit TM-polarized intersubband-like absorption resonances. However, the peak transition energy is largely blue-shifted (> 100 meV) with expectations from electronic quantum confinement simulations. Based on calculations of the exciton binding energies, we attribute the photo-induced absorption at room temperature to the dissociation of hh<sub>1</sub>-e<sub>1</sub> excitons towards free-carriers in the e<sub>2</sub> state and not to hh<sub>1</sub>-e<sub>1</sub> to hh<sub>1</sub>-e<sub>2</sub> excitonic transitions induced by the intersubband absorption as previously stated by Olzakier et al. [Phys. Rev. Lett. **62**, 2997 (1989)]. This effect, which has never been observed before at room temperature in other III-V or IV-IV semiconductors, is a consequence of the huge binding energy of excitons in the ZnO material system, which is further enhanced in QWs due to the quantum confinement. This would pave way for a better understanding of semiconductors excitonic processes as well as for developing intersubband devices with blue-shifted operating range. Wide-gap semiconductors appear as promising materials in order to develop intersubband (ISB) devices in the whole infrared range. Especially ZnO/ZnMgO heterostructures has recently attracted renewed interest for far-infrared ISB devices. ISB absorption has initially been observed at room temperature in wurtzite polar ZnO materials grown along the c-axis [1, 2]. In addition, it was predicted that the large energy (72 meV) of longitudinal optical (LO)phonons in ZnO provides room for THz quantum cascade lasers (QCL) operating at recordhigh temperatures [3] much larger than that of the driving technology based on GaAs/AlGaAs THz QCLs [4]. Non-polar ZnO/(Zn,Mg)O quantum wells (QW) grown on m-plane ZnO substrates would be even better suited materials for quantum cascade devices, lasers or detectors, because of the absence of internal electric fields which greatly simplifies their design. ISB absorption in m-plane n-doped ZnO/ZnMgO QWs has been recently observed at mid-infrared wavelengths [5]. It was shown that the electron concentration in the ground state (3-8x10<sup>12</sup> cm<sup>-2</sup>) [6] leads to a significant blue-shift of the ISB transitions with respect to the values calculated for an unpopulated QW due to the depolarization shift which is a manifestation of the screening of the incoming radiation by the ISB plasmons [7]. Such effect was also observed in the first prototypes of non-polar ZnO/ZnMgO quantum cascade detectors operating at short infrared wavelengths up to room temperature [8].

In order to get rid of the depolarization effect one should investigate bare ISB transitions in undoped QWs. One solution is to make use of the photo-induced absorption (PIA) spectroscopic technique [9, 10]. The technique developed in the late 80's involves a chopped interband excitation at a photon energy above the QW band-gap to generate electron-hole pairs in their respective ground states and to probe the resulting infrared ISB absorption change using a lock-in amplifier. This differential technique, which allows probing absorption changes as low as 10<sup>-4</sup>-10<sup>-6</sup>, is applicable to both undoped and doped QWs. The typical photogenerated electron concentration, which depends on the pump intensity is in the range of

10<sup>9</sup>-10<sup>10</sup> cm<sup>-2</sup> [9, 10], which is well below the exciton Mott transition and is too low to provide any significant contribution of many-body effects such as the depolarization shift. In addition, PIA does not require a reference sample since the reference is provided by the sample transmission without excitation. PIA has been successfully applied to various material systems such as GaAs/AlGaAs, SiGe/Si, GaN/AlN QWs or InAs/GaAs quantum dots and InAs/AlInAs quantum dashes [9-14].

In the pioneering work of Olzsakier et al. on GaAs/AlGaAs QWs at cryogenic temperatures down to 2 K, PIA was ascribed to excitonic transitions from hh<sub>1</sub>-e<sub>1</sub> to hh<sub>1</sub>-e<sub>2</sub> induced by the ISB absorption. However, no estimation of the hh<sub>1</sub>-e<sub>2</sub> excitonic binding energy was provided [9]. Similar experiments performed on GaAs/AlGaAs QWs at room temperature did not reveal any excitonic effect because the binding energy of excitons is much lower than the thermal energy, i.e the PIA only involves free-carriers [10]. In turn, ZnO QWs appear as a model system to investigate the excitonic effects on photo-induced intersubband absorption at room temperature because of the huge binding energy of excitons in the ZnO material system (~60 meV in bulk ZnO). At room temperature, photoexcited carriers in ZnO QWs are bound by Coulomb interaction and only excitonic interband transitions are present.

In this paper, we have carried out a systematic investigation of ISB transitions in nonintentionally-doped m-plane ZnO/ZnMgO QWs using PIA spectroscopy at room temperature. A series of samples with various well thicknesses and an Mg concentration in the barriers around 40% has been grown by molecular beam epitaxy (MBE). In addition to PIA, the samples have been characterized by photoluminescence, X-ray diffraction (XRD), transmission electron microscopy (TEM) and atom probe tomography (APT). All samples exhibit TM-polarized ISB-like photo-induced absorption. However, the peak PIA ISB transition energy is blue-shifted by around 110-140 meV with respect to the value predicted by electron quantum confinement simulations. These simulations were performed using Nextnano software [15] by solving Schrödinger equation with a mass-effective model accounting for the uncertainty on the Mg content, QW thickness and the actual value of the conduction band (CB) offset. The parameters used in Nextnano software are reported in the supplemental [16] (also see Refs. [17–22]). This discrepancy can only be explained by excitonic effects. We have carried out extensive simulations of the  $hh_1$ - $e_1$  (X<sub>1</sub>) and  $hh_1$ - $e_2$  (X<sub>2</sub>) exciton binding energies following Ref [23]. The comparison with the measurements of the calculated intersubband energy corrected by the exciton binding energies shows that the observed PIA transitions cannot be attributed to X1 to X2 excitonic transitions induced by the ISB absorption as previously stated by Olzsakier et al. [9] and theoretically investigated by Sadeghi and Li [24]. In turn, a good agreement with the experimental results is observed when accounting only for the X<sub>1</sub> exciton binding energy. We therefore claim that the photoinduced intersubband absorption in ZnO/ZnMgO QWs arises from the X1 exciton ionization to free carriers in the e<sub>2</sub> state induced by the intersubband absorption. This effect, which has never been observed at room temperature in other III-V or IV-IV semiconductors, is again a consequence of the huge binding energy of excitons in the ZnO material system [25] which is further enhanced in QWs due to the quantum confinement [26-28].

The investigated samples were grown on 10x20 mm<sup>2</sup> m-oriented ZnO substrates (Crystec) by MBE. The substrates were annealed at 1065 °C under an oxygen (O) atmosphere to reveal atomic steps. The atomic O was provided by a plasma cell operating at 420 W, and the O flow was set to 0.3 sccm. The substrate temperature was set to 420 °C. The Zn and O fluxes were adjusted to be close to stoichiometry to limit defect concentrations with a growth rate of 170 nm/h. The structures consisted of a 150 nm ZnO buffer layer followed by 15-period ZnO/ZnMgO QWs with a nominal Mg concentration of 40% and a barrier thickness of 15 nm. The whole structure is non-intentionally doped. The nominal well thickness of the seven investigated samples labeled A to G is 2.2, 2.6, 3.0, 3.2, 3.4, 3.7 and 4 nm, respectively.

Figure 1 a) shows the photoluminescence (PL) spectra at room temperature of the samples. The peak at low (high) energy arises from the ZnO QWs (ZnMgO barrier). Figure 1 b) plots the QW peak PL energy versus the well thickness. As expected, the peak PL energy decreases with increasing well thicknesses. Based on the high-energy PL peak, the average Mg concentration is estimated to be in the range 39.1 to 40%.

TEM and APT measurements performed on samples A and G confirm that the actual well thickness is within  $\pm$  one monolayer (ML, 0.23 nm) close to the nominal thickness. However, the analysis reveals a coherent corrugation within the multiple QWs with V-grooves in the QW planes aligned along the c-axis. Such morphology has already been observed in m-plane ZnO/ZnMgO QWs linked to the different adatom diffusion along the c-axis and the a-axis [29]. In addition, APT reveals that the Mg concentration in each individual QW varies by  $\pm$  10% in absolute value with a maximum (minimum) value at the bottom (apex) of the V-grooves [30]. The structural characterizations of these samples were performed with another set of samples with similar features, more details may be found in Ref [30].

For PIA spectroscopic measurements, the samples were mechanically polished to form a multi-pass waveguide with two internal reflections and  $45^{\circ}$  angle facets. Interband excitation at 266 nm was provided by a Spectra-Physics Millenia visible laser frequency-doubled with a Wavetrain. The UV light was mechanically chopped at 1 kHz and focused at normal incidence onto the sample surface with a spot size of 2 mm. A liquid-nitrogen cooled HgCdTe detector was used to detect the infrared sample transmission change ( $\Delta$ T) along with a lock-in amplifier. Figure 2 shows PIA spectra of samples A, B and C for TM and TE polarized lights recorded with a Bruker Vertex 70 Fourier Transform Infrared spectrometer (FTIR) operated in a step-scan mode. The pump power was fixed at 100 mW. The differential absorption is divided by the transmission of the samples without UV illumination measured in the rapid-scan mode, in order to get rid of the spectral response of the optics and detector. As seen in

Fig. 2, the TE-polarized PIA spectra reveal a monotonous increase at low energy, which is attributed to free-carrier absorption probably in the ZnO substrate. In turn, the TM-polarized spectra show a sharp resonance. This is indeed expected from the ISB selection rules since only the TM component of the electric polarization couples to the ISB transition. A similar behavior, i.e. the presence of a TM-polarized ISB absorption, is observed for all investigated samples. These resonances are attributed to CB ISB transitions and not to valence band (VB) ISB transitions, reasons are explained in the supplemental.

In order to assess the effect of the corrugation on the confinement energies, we have prepared samples with opposite facets polished at 45° angle to allow infrared light propagation along either the c-axis or the a-axis. Figure 3 shows the TM- and TE-polarized PIA spectra of sample E at room-temperature for the two propagation directions. As seen, the TM-polarized absorption is peaked at 323 (317) meV for light propagating along the c (a) axis. The energy shift is only 6 meV which means that the corrugation in the QWs has little effect on the confinement energies, at least at room temperature. Besides experiments have been carried out by varying the UV pump power from 40 mW to 350 mW on sample E at room-temperature along the c and a axis, presented in figure 3. No measurable change of the TM-polarized ISB resonance peak energy and spectral shape has been observed in this power range, which confirms that the depolarization shift is negligible within our experimental conditions.

Table 1 summarizes the sample parameters as well as the energy, wavelength and full width at half maximum (FWHM) of the ISB resonance of all samples. As seen in Table 1, the transition energy red-shifts with increasing well thicknesses as expected from ISB transitions. The FWHM is around 51-54 meV for samples D to F but significantly increases when the well thickness decreases below 3.1 nm. Although one could suspect that for the thinner QWs the excited state gets closer to the continuum leading to the formation of a miniband and

resulting in extra broadening, NextNano [15] simulations assuming a CB band offset of 66.5% following Ref [31] show that the ZnMgO barriers are thick enough to prevent coupling between the QWs, therefore excluding the miniband effect. A more likely explanation is the delocalization of the e<sub>2</sub> envelope function linked to the its vicinity to the continuum and the enhanced sensitivity of the ISB transition energy to QW thickness and barrier Mg content fluctuations for the thinner QWs.

We have simulated the *bare* ISB transition energy, e<sub>21</sub>, assuming a Mg concentration in the barrier of 33, 40 and 48 %, respectively. Figure 4 shows the dependence of the calculated ISB transition energy on the well thickness. It also displays the experimental peak PIA energies. As seen in Fig.4, the evolution of the experimental PIA transition energy versus well thickness qualitatively follows that of the simulation results. However, the PIA energy exhibits a significant blue-shift of the order of 110-115 meV for samples C to G and 125-140 meV for the thinner samples A and B. Further simulations show that this discrepancy cannot be accounted for even by using unrealistic material parameters such as a very high Mg content or a lighter effective mass in ZnO. It should be noted that for previously studied heavily doped samples (i.e. with an electron concentration beyond the Mott transition), the measured PIA ISB transition energy coincided with the ISB energy extracted from standard FTIR spectroscopy, i.e. no blue shift was revealed [5]. This suggests that the observed blue-shift of the PIA-measured energies in undoped samples is linked to excitonic effects.

Effectively the binding energy of bulk ZnO excitons is around 60 meV at room temperature and is further enhanced in QW structures due to the quantum electron-hole confinement [25-27]. The binding energy for a 2 nm thick ZnO/ZnMgO QW was estimated to be 115 (87) meV for a Mg content of 27 % (12 %) [27] in agreement with calculations [26]. For the presently investigated samples, it is estimated to be in the range of 128-213 meV accounting for the actual Mg content. This means that the processes involved in PIA

spectroscopy of ZnO heterostructures fundamentally differ from other III-V or IV-IV semiconductors. At room temperature, photoexcited carriers in ZnO QWs are bound by Coulomb interaction and only excitonic interband transitions are present. So, the observed PIA transitions are ascribed to the excitonic transition from the  $X_1$  to  $X_2$  1s exciton states, implying the fundamental and first excited excitonic states, induced by the  $e_1-e_2$  ISB absorption. Such effect has already been theoretically predicted by Sadeghi and Lei [24].

We have calculated the binding energy of the  $X_1$  to  $X_2$  excitonic transitions with respect of the QW thickness based on Ref [23] and briefly described in the supplemental. Table II recasts the corresponding values versus well thickness. As expected, the binding energy of the  $X_1$  excitonic transition,  $\Delta_1$ , increases when the well thickness diminishes [26]. For the  $X_2$ excitonic transition, the binding energy,  $\Delta_2$ , is smaller than that of the  $X_1$  excitonic transition because of the largest delocalization of the  $e_2$  envelope function with respect to the  $e_1$ envelope function [9, 25] and gets maximum for 2.6 nm thick QWs.

The energy of the transition between  $X_1$ - $X_2$  1s excitonic transition is expressed as  $E_{X1-X2} = e_{21}+\Delta_1-\Delta_2$  corresponding to the sum of the  $e_1-e_2$  ISB energy and the difference in the binding energy between the  $X_1$  exciton and the  $X_2$  exciton. This results in a blue shift of the transition energy with respect to the bare ISB energy, as seen in Fig. 4 with the blue curve corresponding to the  $X_1$ - $X_2$  transition. However, the blue-shift is still insufficient to explain the observations. In turn, a good agreement with experiments is achieved when accounting only for the  $X_1$  binding energy correction ( $E = e_{21}+\Delta_1$ ) as observed with the red curve corresponding to the  $X_1$ - $e_2$  transition in Fig. 4. These reported results are different compared to a X1 to X2 1s excitonic transition as stated by Olzsakier et al. [9] and Sadeghi and Li [24]. Our results show that the underlying mechanism for the photo-induced absorption is the dissociation of the  $X_1$  exciton induced by the ISB absorption towards free-carriers in the  $e_2$  state, as pictured in Fig.5. More details involving transition selection rules can be found in

the supplemental. Finally, it should be noticed that such ISB induced excitonic effect has never been observed at room temperature in other semiconductor material systems because their exciton binding energy is too small with respect to the thermal energy.

In conclusion, we have performed a systematic study of intersubband absorption of nonintentionally-doped m-plane ZnO/ZnMgO QWs using photoinduced infrared absorption spectroscopy under irradiation by a UV laser. All samples exhibit intersubband-like absorption resonances. However, the peak transition energy is strongly blue-shifted with respect to simulations. We claim that the observed transitions, which have never been observed before, involve the dissociation of the  $h_1$ -e<sub>1</sub> exciton induced by the ISB absorption towards unbound electrons in the e<sub>2</sub> state and is supported by the resolution of the X1 and X2 exciton binding exciton.

A direct measurement of binding energies could be performed by monitoring the photoluminescence emission dynamics while an UV pump wavelength is tuned from band gap to higher energies [32]. This observation would allow a better understanding of transitions between excitonic states as well as the development of short-wavelength intersubband devices with near-infrared and even visible operating range. The high binding energies in 2D materials reaching ~ 600 meV [33] could be used to explore this phenomenon and unrevealed exotic excitonic transitions.

## Acknowledgments:

This work was supported by the European Union's Horizon 2020 Research and Innovation FET-Open Program under Grant Agreement No. 665107 (project ZOTERAC). Supplemental materials:

See Supplemental Material at [URL will be inserted by the production group] for parameters list of the mass-effective model for solving Schrödinger equation, the investigation of intersubband transitions in the valence band, the calculation procedure of excitonic binding energy, a study on the influence V-groove profile on quantum confinement and its implication on X1-X2 inter-exciton transitions and other transitions

#### **References**:

[1] M. Belmoubarik, K. Ohtaniand and H. Ohno, Intersubband transitions in ZnO multiple quantum wells. Appl. Phys. Lett. 92, 191906 (2008).

[2] K. Zhao, G. Chen, B. S. Li, and A. Shen, Mid-infrared intersubband absorptions in ZnO/ZnMgO multiple quantum wells. Appl. Phys. Lett. 104, 212104 (2014).

[3] E. Belotti, K. Driscoll, T. D. Moustatkas, and R. Paiella, "Monte Carlo simulation of terahertz quantum cascade laser structures based on wide-bandgap semiconductors", J. Appl. Phys. 105, 113103 (2009).

[4] S. Kumar, Q. Hu, and J. L. Reno, Appl. Phys. Lett. 94, 131105 (2009).

[5] N. Le Biavan, M. Hugues, M. Bajo, J. Tamayo-Arriola, A. Jollivet, D. Lefebvre, Y.

Cordier, B. Vinter, F.H. Julien, A. Hierro, J.-M. Chauveau, App. Phys. Lett. 111, 231903 (2017).

[6] M. Montes Bajo, J. Tamayo-Arriola, M. Hugues, J. M. Ulloa, N. Le Biavan, R. Peretti, F.

H. Julien, J. Faist, J.M. Chauveau, and A. Hierro, Phys. Rev. Applied, 10, 024005 (2018).

[7] S. J. Allen, D. C. Tsui, and B. Vinter, Solid State Commun. 20, 425 (1976).

[8] A. Jollivet, B. Hinkov, S. Pirotta, H. Hoang, S. Derelle, J. Jaeck, M. Tchernycheva, R.

Colombelli, A. Bousseksou, M. Hugues, N. Le Biavan, J. Tamayo-Arriola, M. Montes Bajo,

L. Rigutti, A. Hierro, G. Strasser, J.M. Chauveau, and F. H. Julien, Appl. Phys. Lett., 113, 251104 (2018).

[9] M. Olszakier, E. Ehrenfreund, E. Cohen, J. Bajaj, and J. Sullivan, Phys. Rev. Lett. 62, 2997 (1989).

[10] D. D. Yang, F. H. Julien, J.-M. Lourtioz, P. Boucaud, and R. Planel, IEEE Photon.Technol. Lett. 2, 398 (1990).

[11] P. Boucaud, L. Gao, Z. Moussa, F. Visocekas, F. H. Julien, J.-M. Lourtioz, I. Sagnes, Y.Campidelli, P.-A. Badoz, Appl. Phys. Lett. 67, 2948 (1995).

[12] M. Tchernycheva, L. Nevou, L. Doyennette, F. H. Julien, E. Warde, F.

Guillot, E. Monroy, E. Bellet-Amalric, T. Remmele, and M. Albrecht,

Phys. Rev. B 73, 125347 (2006).

[13] S. Sauvage, P. Boucaud, F.H. Julien, J.M. Gerard, J.Y. Marzin, Infrared spectroscopy of intraband transitions in self-organized InAs/GaAs quantum dots, J. Appl. Phys. 82, 3396 (1997).

[14] A. Weber, O. Gauthier-Lafaye, F.H. Julien, J. Brault, M. Gendry, Y. Désieres, T.Benyattou, Appl. Phys. Lett., 74, 413 (1999).

[15] Nextnano3 software, http://www.nextnano.de.

[16] See Supplemental Material at [URL will be inserted by the production group] for parameters list of the mass-effective model for solving Schrödinger equation, the investigation of intersubband transitions in the valence band, the calculation procedure of excitonic binding energy, a study on the influence V-groove profile on quantum confinement and its implication on X1-X2 inter-exciton transitions and other transitions.

[17] B. Laumer, F. Schuster, M. Stutzmann, A. Bergmaier, J. Appl. Phys. 113, 233512 (2013).

[18] S.-H. Jang and S. F. Chichibu, J. Appl. Phys. 112, 073503 (2012).

[19] J. Chen, W. Z. Shen, N. B. Chen, D. J. Qui, H. Z. Wu, J. Phys: Condens Matter 15, L475 (2003).

- [20] Y.-N. Xu et W. Y. Ching, PRB 43, 4461 (1991).
- [21] T. C. Damen, S. P. S. Porto, B. Tell, Phys. Rev. B 142, 570 (1966).
- [22] A.R. Denton and N.W Ashcroft, Phys. Rev. A 43 (6), 3161-3164 (1991).
- [23] R. P. Leavitt and J. W. Little, Phys. Rev. B 42 (18), 11774 (1990).
- [24] S.M. Sadeghi and W. Li, IEEE JQE 40, 343 (2004).
- [25] D. G. Thomas, J. Phys. Chem. Solids 15, 86 (1960).

- [26] G. Bastard, J. A. Brum, and R. Ferreira, J. of App. Phys. 72, 3218 (1992).
- [27] G. Coli, K. K. Bajaj, Appl. Phys. Lett. 78, 2861 (2001).
- [28] H. D. Sun, T. Makino, Y. Segawa, M. Kawasaki, A. Ohtomo, K. Tamura, H. Koinuma, J. of Appl. Phys. 91, 1993 (2002).
- [29] H. Matsui, N. Hasuike, H. Harima, and H. Tabata, J. Appl. Phys. 104,

094309 (2008).

[30] E. Di Russo, J. Houard, S. Moldovan, G. Da Costa, I. Blum, F. H. Julien, M.

Tchernycheva, J.M. Chauveau, M. Hugues, D. Blavette, L. Rigutti, Appl. Phys. Lett. 111,

032108 (2017).

[31] H. Yin, J. Chen, Y. Wang, J. Wang and H. Guo, Scientific Reports 7, 41567 (2017).

[32] A. Tzimis, A. V. Trifonov, G. Christmann, S. I. Tsintzos, Z. Hatzopoulos, I. V. Ignatiev, A. V. Kavokin, and P. G. Savvidis, Appl. Phys. Lett. **107**, 101101 (2015).

[33] T. Mueller, E. Malic, 2D Mater Appl 2, 29 (2018).

## **Table caption**

Table I: Sample parameters, energy, wavelength and full width at half maximum (FWHM) of the ISB resonance. The average Mg concentration is deduced from PL measurements. The well and barrier thicknesses are deduced from XRD and APT measurements.

Table II: Well thickness, binding energy of the  $hh_1$ - $e_1$  exciton ( $\Delta_1$ ) and of the  $hh_1$ - $e_2$  exciton ( $\Delta_2$ ).

| Table | I |
|-------|---|
|-------|---|

| Sample | Mg<br>(%) | Well thickness | Barrier thickness | ISB energy | ISB wavelength | FWHM  |
|--------|-----------|----------------|-------------------|------------|----------------|-------|
|        |           | (nm)           | (nm)              | (meV)      | (µm)           | (meV) |
| А      | 39.5      | 2.2            | 15.3              | 472        | 2.6            | 93    |
| В      | 40.0      | 2.6            | 15.0              | 428        | 2.9            | 78    |
| С      | 39.1      | 3.1            | 15.3              | 362        | 3.4            | 64    |
| D      | 39.9      | 3.2            | 15.2              | 345        | 3.6            | 54    |
| Е      | 39.6      | 3.4            | 15.2              | 323        | 3.8            | 53    |
| F      | 39.9      | 3.8            | 15.2              | 300        | 4.1            | 52    |
| G      | 39.6      | 4.0            | 14.9              | 282        | 4.4            | 51    |

## Table II

| Thickness | $\Delta_1$ | $\Delta_2$ |
|-----------|------------|------------|
| (nm)      | (meV)      | (meV)      |
| 2.2       | 108.4      | 77.0       |
| 2.6       | 104.5      | 81.6       |
| 3.1       | 99.8       | 81.1       |
| 3.2       | 98.9       | 80.7       |
| 3.4       | 97.0       | 79.8       |
| 3.8       | 93.8       | 77.8       |
| 4         | 92.4       | 76.8       |

### **Figure captions**:

Figure 1: a) photoluminescence spectra at room temperature of the samples. b) The red dots are peak PL energy of the ZnO QWs versus the well thickness, the red curve corresponds to the simulated gap energy.

Figure 2: PIA spectra of samples A (left), B (center) and C (right) at room temperature for TM and TE polarized light.

Figure 3: PIA spectra of sample E at room temperature for TM polarized light at different UV pump power 40 mW (black), 114 mW (red), 350 mW (blue) along (a) the c-axis and (b) the a-axis.

Figure 4: Calculated CB ISB energy versus well thickness for an Mg content in the barrier of 33% (orange curve), 40% (purple curve) and 48% (green curve). The full black squares are the experimental peak energies measured by PIA. The blue curve is the X1-X2 (hh<sub>1</sub>-e<sub>1</sub> to hh<sub>1</sub>-e<sub>2</sub>) excitonic transition energy for 40% Mg content, the blue filled area delimited by dots correspond to the X1-X2 transition error accounting for a  $\pm 1$  ML fluctuation of the well thickness. The red curve is the ISB energy corrected by the hh<sub>1</sub>-e<sub>1</sub> exciton binding energy, which corresponds to a transition X1-e2 implying a fundamental excitonic state and an excited e<sub>2</sub> state with unbound electrons and holes and the red filled area delimited by dots correspond to the X1-e2 transition error accounting for a  $\pm 1$  ML fluctuation of the well thickness.

Figure 5: Scheme of the  $X_1$  (hh<sub>1</sub>-e<sub>1</sub>) exciton ionization to free carriers in the e<sub>2</sub> state induced by the e<sub>1</sub>-e<sub>2</sub> intersubband absorption. The black curved lines represent the electronic states confined in a QW in the conduction and valence bands. The black dotted line is the Fermi energy. The orange dashed lines simulate the excitonic states. The blue full (hollow) dots correspond to electron (hole) particles, their electron-hole coulomb interaction, symbolized by the green dotted curve, forms an exciton quasiparticle represented by the green dot. The purple (red) arrows illustrate the electron excitation inducing the exciton generation (exciton ionization) by the ultraviolet pump (infrared probe).



















