



**Comment on the paper "Experimental investigation of
the Ni–V–W ternary phase diagram", Calphad:
Comput. Coupling Phase Diagrams Thermochem. 76
(2022) 102384**

Jean-Marc Joubert

► To cite this version:

Jean-Marc Joubert. Comment on the paper "Experimental investigation of the Ni–V–W ternary phase diagram", Calphad: Comput. Coupling Phase Diagrams Thermochem. 76 (2022) 102384. Calphad, 2022, 77, pp.102424. 10.1016/j.calphad.2022.102424 . hal-03747849

HAL Id: hal-03747849

<https://hal.science/hal-03747849>

Submitted on 8 Aug 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Comment on the paper "Experimental investigation of the Ni-V-W ternary phase diagram", Calphad: Comput. Coupling Phase Diagrams Thermochem. 76 (2022) 102384.

Jean-Marc Joubert
Univ Paris Est Creteil, CNRS, ICMPE, UMR 7182, 2 rue Henri
Dunant, 94320 Thiais, France

jean-marc.joubert@cnrs.fr

In a recent paper [1], Meifang Tang *et al.* report an investigation of the ternary Ni–V–W system. Though this is not the main subject of their paper, they mention results related to the binary Ni–W system that need to be commented.

In one ternary alloy (sample A13), they found a phase of measured composition $\text{Ni}_{50.33}\text{V}_{0.36}\text{W}_{49.31}$. This phase was identified as corresponding to the (slight) ternary extension of WNi binary phase. They therefore conclude on the existence of this phase in the binary Ni–W system. They also mention and take into account in the thermodynamic assessment the NiW_2 phase, though they do not provide any experimental result about this phase.

However, in a previous (not-cited) work, Cury *et al.* [2] had shown **that there is no compelling evidence for the existence of the two previously reported phases NiW and NiW_2 . Previous evidence is actually better interpreted in terms of the presence of the two ternary carbides $\text{Ni}_6\text{W}_6\text{C}$ and $\text{Ni}_2\text{W}_4\text{C}$ that would have been taken mistakenly for binary phases.** It was later shown that, similarly, the so-called FeW phase in the Fe–W system corresponds also probably to the ternary $\text{Fe}_6\text{W}_6\text{C}$ phase [3]. The results on Ni–W system have been confirmed since then by several authors, see *e.g.* [4–7]. In particular, in Ref. [6], Isomäki *et al.*, made a complete review (see references therein) and reach the same conclusions.

Any discussion is absent from the paper of Meifang Tang *et al.* to rebut the arguments developed in previous literature. The statement 'In their (Isomäki's) assessment, the WNi phase is considered to be metastable' is misleading. Contrary to what is suggested by the authors, the conclusions by Isomäki are not based on first-principles calculations but rather on a careful literature review. Their conclusion is that the so-called NiW does exist and is in fact a ternary carbide. This is not a question of 'metastability'.

The conclusions of Meifang Tang *et al.* are based on EDS analysis and an X-ray diffraction pattern. No analysis of the carbon content by EDS is provided to support the conclusion that the 'WNi' phase is truly an intermetallic compound. The diffraction pattern of sample A13 is shown with an indexation of WNi phase for phase 3. But, the crystal structure used for the indexation is not provided. It is supposed it comes from the old literature reporting the existence of this phase for which no crystal structure has ever been reported. A careful look shows that the diffraction lines of phase 3 can actually be very well indexed by the diffraction pattern simulated with the crystal structure of the ternary carbide $\text{Ni}_6\text{W}_6\text{C}$ [8] (Fig. 1). This diagram instead of being a proof of the existence of WNi turns to be a proof that the authors actually have a ternary carbide instead.

This clarification on the binary Ni–W system does not cast doubt on the rest of the study. This is a minor point in the publication of the ternary Ni–V–W system. It is however important to avoid introducing new confusions in the literature as far as the binary system is concerned. Note also that the same authors made the same **misinterpretation** of their results in the Ref. [9] on the Mo–Ni–W system.




Fig. 1. Diffraction pattern of sample A13 in Ref. [1] with superposition of the calculated pattern of $\text{Ni}_6\text{W}_6\text{C}$ [8] (black) and visible diffraction lines indexed by this carbide (red arrows).

References

- [1] Meifang Tang, Yong Du, Peng Zhou, Taibai Fu, Yuling Liu, B. Sundman, Experimental investigation of the Ni-V-W ternary phase diagram, *Calphad: Comput. Coupling Phase Diagrams Thermochem.* 76 (2022) 102384.
- [2] R. Cury, J.-M. Joubert, S. Tusseau-Nenez, E. Leroy, A. Allavena-Valette, On the existence and the crystal structure of Ni_4W , NiW and NiW_2 , *Intermetallics* 17 (2009) 174-178.
- [3] A. Antoni-Zdziobek, T. Commeau, J.-M. Joubert, Partial redetermination of the Fe-W phase diagram, *Metall. Mater. Trans. A* 44 (7) (2013) 2996-3003.
- [4] S. Inomata, M. Kajihara, Solid-state reactive diffusion between Ni and W, *J. Alloys Compd.* 509 (2011) 4958-4966.
- [5] C.J. Marvel, P.R. Cantwell, M.P. Harmer, The critical influence of carbon on the thermal stability of nanocrystalline Ni-W alloys, *Scr. Mater.* 96 (2015) 45-48.
- [6] I. Isomäki, M. Härmäläinen, M.H. Braga, M. Gasik, First principles, thermal stability and thermodynamic assessment of the binary Ni-W system, *Int. J. Mater. Res.* 108 (12) (2017) 1025-1035.
- [7] Lilong Zhu, Changdong Wei, Liang Jang, Zhanpeng Jin, Ji-Cheng Zhao, Experimental determination of the phase diagrams of the Co-Ni-X (X=W, Mo, Nb, Ta) ternary systems using diffusion multiples, *Intermetallics* 93 (2018) 20-29.
- [8] P. Ettmayer, R. Suchentrunk, Über die thermische Stabilität der Eta-Carbide, *Monatsh. Chem.* 101 (1970) 1098-1103.
- [9] Meifang Tang, Yong Du, Peng Zhou, Shimin Wang, Huaqing Zhang, Yinping Zeng, Shuhong Liu, Xueyuan Chai, Yingbiao Peng, Changjun Wu, Xuping Su, Zi-Kui Liu, Experimental phase diagram, thermodynamic modeling and solidified microstructure in the Mo-Ni-W ternary system, *Calphad: Comput. Coupling Phase Diagrams Thermochem.* 68 (2020) 101748.