



HAL
open science

Modeling of the morphic effect using a 1st-order transitional magneto-elastic energy

Julien Taurines, Boris Kolev, Rodrigue Desmorat, Olivier Hubert

► To cite this version:

Julien Taurines, Boris Kolev, Rodrigue Desmorat, Olivier Hubert. Modeling of the morphic effect using a 1st-order transitional magneto-elastic energy. 25th Soft Magnetic Materials conference 2022, May 2022, Grenoble, France. <hal-03773047>

HAL Id: hal-03773047

<https://hal.science/hal-03773047v1>

Submitted on 8 Sep 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire HAL, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



HAL Authorization

Modeling of the morphic effect using a 1st-order transitional magneto-elastic energy

J.Taurines^a, B.Kolev^a, R.Desmorat^a, O.Hubert^a

^aUniversité Paris-Saclay, ENS Paris-Saclay, CNRS, LMT, F-91190 Gif-sur-Yvette, France

The study takes place in the context of magneto-elastic coupling. A new magnetoelastic energy formulation is proposed at the magnetic domain scale in order to account for the non-linear and non-monotonous effect of stress on magnetization and magnetostriction. The model uses 1st order cubic/isotropic invariants and a transition function taking an equivalent stress as argument.

Keywords: magnetostriction, second-order effect, invariants

1 Introduction

Magnetostriction and Villari effect are two consequences of the magneto-elastic coupling [1]. In some materials such as Fe-3%Si, the mechanical loading has a non-monotonous influence on the magnetic behaviour (fig1). This second-order phenomenon is denoted as the morphic effect [2,3,4].

2 Former simulations and drawbacks

This phenomenon can be modeled by adding a quadratic term to the usual Gibbs magneto-elastic energy density $\Psi\mu\sigma$. This term can be formulated via a constitutive 6th order tensor [3] or via an equivalent polynomial formulation using polynomial invariants [4]. The main drawback of this formulation is that both magnetostriction strain and magnetic behaviour are not bounded with respect to the stress leading to strong divergences at high stress.

3 New first order transitional model

One way to avoid this problem is to use a transition function f (eq. 1) in the magnetoelastic free energy density allowing to switch from one linear energy formulation ψ_1 to another ψ'_1 (both functions of local stress σ and magnetization \mathbf{m}) This reflects a modification of the material constants c_{210} involved in eq. 2 (where ' indicates the deviatoric part of tensors). f takes as argument a magneto-elastic equivalent stress σ_{eq} (eq. 3 – M_s : saturation magnetization) [5].

$$\Psi\mu\sigma(\sigma, \mathbf{m}) = f(\sigma_{eq}) \cdot \psi_1(\sigma, \mathbf{m}) + (1-f(\sigma_{eq})) \cdot \psi'_1(\sigma, \mathbf{m}) \quad (1)$$

$$\psi_1(\sigma, \mathbf{m}) = c_{210} \cdot [(\mathbf{m} \otimes \mathbf{m})' : \sigma'] \quad (2)$$

$$\sigma_{eq} = 3/(2M_s^2) \cdot [(\mathbf{m} \otimes \mathbf{m})' : \sigma'] \quad (3)$$

The new formulation is introduced in a multiscale model. Figure 1 illustrates the way the new model respects the non-monotony of the magnetization, the change of sign of the magnetostriction and its saturation at high stress.




Figure 1 : Comparison between experimental magnetostriction (left) and transition model (right) for magnetization (up) and magnetostriction (down) as function of stress.

References

- [1] R. Bozorth. *Ferromagnetism*. D. Van Nostrand, 1951
- [2] W. P. Mason. *Physical Review*, 82(5):715–723, June 1951
- [3] O. Hubert. *Journal of Magnetism and Magnetic Materials*, 491:165564, Dec. 2019.
- [4] J. Taurines, M. Olive, R. Desmorat, O. Hubert, and B. Kolev. *Journal of Magnetism and Magnetic Materials*, page 167885, 2021.
- [5] O. Hubert and L. Daniel. *Journal of Magnetism and Magnetic Materials*, 323(13):1766–1781, 2011.