

# Stabilization of the epitaxial rhombohedral ferroelectric phase in ZrO 2 by surface energy

Ali El Boutaybi, Thomas Maroutian, Ludovic Largeau, Sylvia Matzen,

Philippe Lecoeur

# ► To cite this version:

Ali El Boutaybi, Thomas Maroutian, Ludovic Largeau, Sylvia Matzen, Philippe Lecoeur. Stabilization of the epitaxial rhombohedral ferroelectric phase in ZrO 2 by surface energy. Physical Review Materials, 2022, 6 (7), pp.074406. 10.1103/PhysRevMaterials.6.074406 . hal-03781535

# HAL Id: hal-03781535 https://hal.science/hal-03781535v1

Submitted on 20 Sep 2022

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Stabilization of the epitaxial rhombohedral ferroelectric phase in ZrO<sub>2</sub> by surface energy

Ali El Boutaybi, Thomas Maroutian, Ludovic Largeau, Sylvia Matzen, Philippe Lecoeur

Centre de Nanosciences et de Nanotechnologies, Universite Paris-Saclay, CNRS, Palaiseau, France

Contact: <u>ali.el-boutaybi@c2n.upsaclay.fr</u>

# Keywords

ab initio calculations, epitaxial growth, ferroelectrics, rhombohedral phase, Zirconia

# Abstract

Doped HfO<sub>2</sub> and HfO<sub>2</sub>-ZrO<sub>2</sub> compounds are gaining significant interest thanks to their ferroelectric properties in ultrathin films. Here, we show that ZrO<sub>2</sub> could be a new playground for doping and strain engineering to increase the thickness in epitaxial thin films. Based on surface energy considerations supported by *ab initio* calculations, we find that pure ZrO<sub>2</sub> exhibits a ferroelectric rhombohedral phase (r-phase, with R3m space group) more stable than for the HZO and pure HfO<sub>2</sub> cases. In particular, for a thickness up to 37 nm we experimentally evidence a single (111)-oriented r-phase in ZrO<sub>2</sub> films deposited on La<sub>2/3</sub>Sr<sub>1/3</sub>MnO<sub>3</sub>-buffered DyScO<sub>3</sub>(110) substrate. The formation of this r-phase is discussed and compared between HfO<sub>2</sub>, ZrO<sub>2</sub> and HZO, highlighting the role of surface energy.

Since the discovery of ferroelectricity in Si-doped hafnia in 2011 [1], hafnia-based thin films have been widely studied to stabilize the ferroelectric phase, and many polar phases have been suggested or experimentally proved. In polycrystalline thin films, the orthorhombic phase Pbc21 is usually reported [1][2]. Theoretically, two other polar phases were found for HfO<sub>2</sub>, an orthorhombic Pnm2<sub>1</sub> [3][4] and a rhombohedral R3 [5]. The main problem observed in polar orthorhombic is the necessity of a high number of applied electric field cycles (the so-called wake-up effect) to reach the ferroelectric state [6][7][8]. Moreover, two other issues that are often encountered in these polycrystalline films are the degradation of the ferroelectricity with the increase of film thickness, with a vanishing polarization above a thickness of about 20 nm [1][9][10], and the coexistence of non-polar phases such as monoclinic and tetragonal phases with the polar one [11][12]. Indeed, HfO2 as well as ZrO2 are well known for their structural and chemical similarity[13], and both of them can adopt a wide variety of crystal phases. In bulk form and at room temperature, the stable phase is monoclinic (m-phase,  $P2_1/c$ ). At high temperature, tetragonal phase (t-phase, P42/nmc) and cubic phase (c-phase, Fm3m) are observed for ZrO<sub>2</sub> and HfO<sub>2</sub> [14][15]. The non-centrosymmetric, ferroelectric orthorhombic Pbc2<sub>1</sub> phase (o-phase) can be obtained via transformation of the t-phase under stress [16] [17] [18], or under tensile strain [19]. On the other hand, in 2018, Wei et al. [20] demonstrated the rhombohedral symmetry with R3m space group (r-phase) for the first time in epitaxial Hf<sub>0.5</sub>Zr<sub>0.5</sub>O<sub>2</sub> (HZO) thin films under compressive strain on a La<sub>2/3</sub>Sr<sub>1/3</sub>MnO<sub>3</sub> (LSMO)-buffered SrTiO<sub>3</sub>(001) substrate (STO), and no wake-up effect was observed. Strain engineering is thus investigated to stabilize this r-phase on different substrates, such as recently demonstrated by Zheng et al. for HZO epitaxial films on ZnO [21].

The influence of surface energy on phase stability has been discussed in polycrystalline films through studies on grain size. It was shown that optimizing the latter could stabilize the orthorhombic Pbc2<sub>1</sub> ferroelectric phase in pure HfO<sub>2</sub> [22] and ZrO<sub>2</sub> [23], and that inserting different interlayers allowed the ferroelectricity to be maintained above 40 nm thickness in HZO [24][25]. Concerning bulk ceramics and polycrystalline films, it is known that for a grain diameter less than 30 nm, the ZrO<sub>2</sub> adopts the t-phase [26] [27], whereas the HfO<sub>2</sub> has a similar size effect at around 5 nm [11][28]. From this perspective, ZrO<sub>2</sub>-based epitaxial thin films are promising to increase both film thickness and grain size, which are usually critical for energy storage [29] and optical applications [30][31][32]. Mastering the surface energy balance during growth is thus identified as a critical issue to control the ferroelectric phases of hafnia and zirconia compounds [33][34]. However, very few data are available regarding actual surface energy were reported for the rhombohedral polar phase.

The rhombohedral phase in ZrO<sub>2</sub> or Partially Stabilized Zirconia (PSZ) has been known for more than two decades. Hasegawa. [36] reported a rhombohedral phase in the abraded surfaces of PSZ and fully stabilized zirconia (FSZ) powders; this phase was only observed in the surface layer under some stress, which can be introduced by polishing and grinding. It was therefore postulated that the rhombohedral phase could only exist in the presence of stress. Also, this rhombohedral phase has been reported as an intermediate phase during cubic and tetragonal–monoclinic transformation [37][38][39]. Nevertheless, in all these earlier studies, no electric properties were reported. R3m and R3 rhombohedral phases were evidenced in HZO epitaxial thin films [20][21][40], and recently, Silva *et al.* [41] reported the same r-phase in a 8 nm-thick ZrO<sub>2</sub> thin film deposited on Nb-STO(111). While this polar r-phase is promising for numerous applications based on ultrathin films [42][43][44][45], the issue of its poor thickness-dependent stability is still present when increasing the thickness above 10 nm. In this picture, we will show that rhombohedral ZrO<sub>2</sub> films are more stable at high thickness than HfO<sub>2</sub> and HZO

ones, and thus that ZrO<sub>2</sub>-rich compounds provide a novel playground for strain engineering and doping schemes towards outstanding ferroelectric properties.

In this letter, we first compare with the support of *ab initio* calculations the stability of the (111)oriented rhombohedral R3m phase between pure  $ZrO_2$ , HZO, and pure HfO<sub>2</sub>. We then study epitaxial  $ZrO_2$ , HZO, and HfO<sub>2</sub> thin films grown by pulsed laser deposition (PLD) on both (110)-oriented DyScO<sub>3</sub> (DSO) and (001)-oriented STO substrates, with LSMO buffer. Using X-ray diffraction (XRD), we evidence the presence of the r-phase in  $ZrO_2$  thin films, up to about 40 nm thickness, with a clear ferroelectric behavior without wake-up effect.

We performed density functional theory (DFT) calculations to investigate the (111)-oriented rhombohedral stability by employing Quantum Espresso (QE) package [46] with Perdew-Burke-Erzhenhoff (PBE) [47] generalized gradient approximation (GGA) (see supplemental material (SM) for more details [48]). First, we ran our calculations for m-, t-, o-, and r-phases of ZrO<sub>2</sub>, HZO, and HfO<sub>2</sub>. The energies of these phases are summarized in Table S1 with a comparison to literature data. Our results agree with previous calculations using different approaches and with the experimental results. For r-ZrO<sub>2</sub>, we obtained an energy of 140 meV/f.u with respect to the monoclinic energy, which is less than the 154 meV/f.u found for r-HfO<sub>2</sub>, in good agreement with Ref. [20]. In a second step, the calculations for different surface orientations were performed by constructing 4 layer-thick slabs separated by 15 Å of vacuum (more details in SM. [48]). It is known that the surfaces on each side of a slab may interact through long-range strain fields induced by ionic relaxations [49]. This effect depends somewhat on surface orientation and on the material; for metals, for example, the interlayer relaxations typically fall below the experimental threshold after 3-4 layers [50]. Orlando et al. [51] showed the same average value in the case of t-ZrO<sub>2</sub>. Thus, slabs of 4 layers were used for surface energy calculations (Figure S2) with a 5×5×1 k-point sampling in the surface Brillouin zone (SBZ) [52], and an energy cutoff of 60 Ry.



Figure 1. Surface energy of m- and r-phase of  $Hf_{1-x}Zr_xO_2$  (x=0, 0.25, 0.50, 0.75, and 1) shown in black and red respectively. The thickness up to which Gibbs energy of the R3m phase is lower than the one of the m-phase is shown in blue.

The surface energy in Joule per square meter is given in Table S2 and Figure 1 for (111)-oriented mand r-phases at different ratios of  $ZrO_2$  in  $Hf_{1-x}Zr_xO_2$  composition. The r-(111) showed the lowest surface energy compared to all other calculated surfaces of  $HfO_2$ ,  $ZrO_2$ , and HZO. As indicated in Figure 1, (111) m-phase increases in energy with increasing  $ZrO_2$  content, while the r-(111) phase decreases. This, in turn, increases the energy gap between the m-(111) and r-(111) surfaces, with this gap achieving his maximum in pure  $ZrO_2$ . In the literature, the role of the surface energy was not systematically explored in  $HfO_2$ -ZrO<sub>2</sub> epitaxial thin films, especially regarding the stabilization of the rhombohedral phase. In order to assess the relative stability of the m- and r-phases, taking into account the computed surface energies, we use a simple thermodynamic argument based on the Gibbs free energy [33], that was successfully applied to explain the stability of the orthorhombic polar phase in atomic layer deposited (ALD) thin films [11] [33]. Figure 1 shows (in blue) the thickness up to which the Gibbs free energy of the r-phase is lower than the one of the m-phase as a function of ZrO<sub>2</sub> content in Hf<sub>1-x</sub>Zr<sub>x</sub>O<sub>2</sub>. This estimated maximum thickness for the r-phase was calculated with an in-plane compressive strain of 1%, which is close to the estimated strain from our experimental results as shown below. The stability window of r-ZrO<sub>2</sub> is up to a thickness of 33 nm, while it is less than 4 nm in pure HfO<sub>2</sub>. For HZO, rhombohedral phase is stable up to a thickness of about 12 nm, in good agreement with previous results that reported a 10 nm maximum thickness in epitaxial HZO thin films [20]. The (111)-oriented HfO<sub>2</sub> R3m phase was discussed elsewhere [53] and found to be stable at a very low thickness (2 layers) compared to the (111)-orthorhombic and (111)-monoclinic. Thus, from our calculations, pure ZrO<sub>2</sub> epitaxial thin films are expected to be the most stable regarding the (111)-oriented R3m phase. This makes ZrO<sub>2</sub>-based thin films very promising to stabilize the rhombohedral polar phase at significantly higher thickness than reported for HZO.



Figure 2. Out-of-plane XRD  $\theta$ -2 $\theta$  scans of HZO, HfO<sub>2</sub>, and ZrO<sub>2</sub> films on LSMO-buffered 110-oriented DSO with thicknesses of 14 nm. Insert Figure shows  $\theta$ -2 $\theta$  of ZrO<sub>2</sub> at different thicknesses, and dashed lines show the 2 $\theta$  shift of the (111)-ZrO<sub>2</sub> diffraction peak.

In order to test our findings experimentally,  $ZrO_2$ ,  $HfO_2$ , and  $Hf_{0.5}Zr_{0.5}O_2$  films were grown by PLD on LSMO buffered DSO and STO substrates. The ferroelectric nature of  $ZrO_2$  and HZO was characterized through Positive Up Negative Down (PUND) measurements on capacitor devices with Pt top and LSMO bottom electrodes on DSO substrate (more details are given in SM. [48]). In 14 nmthick films, a remanent polarizations (2Pr) of 40  $\mu$ C/cm<sup>2</sup> and 41.5  $\mu$ C/cm<sup>2</sup> were measured for HZO and ZrO<sub>2</sub>, respectively (Figure S4). These results are comparable to the previously reported values in epitaxial HZO with the same range of thickness [20][54] [55]. At 37 nm thickness, a 2Pr of 22  $\mu$ C/cm<sup>2</sup> is measured for pure ZrO<sub>2</sub> (Figure S4c), hinting at a persistent ferroelectricity. Structural analyses were performed by XRD with Panalytical X'pert Pro diffractometer for out-ofplane  $\theta$ -2 $\theta$  scans (Figure 2) and Rigaku SmartLab diffractometer equipped with a rotating anode for in-plane measurements and pole figure (Figure 3). Figure 2 gives  $\theta$ -2 $\theta$  patterns of HZO, HfO<sub>2</sub>, and ZrO<sub>2</sub> films at a thickness of 14 nm. The highest peaks correspond to the (110)-oriented orthorhombic DSO substrate. At the right and close to the substrate peaks, are the LSMO peaks corresponding to (001) pseudo-cubic orientation. The thickness of LSMO is about 25 nm, measured by X-ray reflectivity. For  $2\theta$  between  $30.09^{\circ}$ - $30.27^{\circ}$ , is found the (111) peak of the HfO<sub>2</sub>, HZO, and ZrO<sub>2</sub> films. Note that, the diffracted peak around  $30^{\circ}$  is referred to the (111) orthorhombic Pbc2<sub>1</sub> in polycrystalline thin films [1], and even in some epitaxial thin films [54]. In the case of polycrystalline films this peak is usually found at a slightly higher 2 $\theta$  value (around 30.5°) compared to epitaxial thin films [10]. Here, the (111) diffracted peak will be ascribed to the rhombohedral phase, as demonstrated below through complimentary XRD analyses. In the case of pure HfO<sub>2</sub>, a peak at 20 around 28.3° is observed with higher intensity than r-(111); this peak corresponds to (111) m-phase [56]. This m-(111) peak decreases in intensity in HZO film and disappears in pure ZrO<sub>2</sub> film. The inset of Figure 2 shows the XRD data of pure ZrO<sub>2</sub> films at different thicknesses. The r-phase in the film appears compressively strained, as the (111) peak is shifted towards smaller angles for the thinner films, indicating that the out-of-plane parameter is expanded compared to the relaxed one at 41 nm. From this thicknessdependent shift, a compressive strain of around 1% was extracted [48]. Additionally, a diffraction peak at 34.6° attributed to m-(020) plane is observed in the 41 nm-thick ZrO<sub>2</sub> film [56], while no monoclinic phase is observed for thicknesses up to 37 nm. Noteworthy, an increase in compressive strain higher than 1% could increase the thickness of the pure r-ZrO<sub>2</sub> film much higher than 37 nm.

In line with our theoretical considerations, both our experimental composition and thickness series confirm that a polar (111)-oriented phase remains stable at high thickness upon increasing the  $ZrO_2$  content in HfO<sub>2</sub>-ZrO<sub>2</sub> compounds, allowing to reach a thickness close to 40 nm in pure ZrO<sub>2</sub> on DSO substrate. We now present the additional XRD measurements that unambiguously identify the rhombohedral phase in our ZrO<sub>2</sub> thin films, as previously reported for HZO films [20]. Note that due to the very low intensity of the r-phase related peak in our pure HfO<sub>2</sub> films (Figure 2, black), we could not perform a similar analysis for them.

Figure 3a shows a pole figure for a 14 nm-thick  $ZrO_2$  film on DSO substrate measured at  $2\theta = 30.19^\circ$ ; 12 radial peaks were found, corresponding to four variants of ZrO<sub>2</sub>. For one r-ZrO<sub>2</sub> variant, only three peaks are expected at a radial angle  $\chi = 71^{\circ}$  [48]. The three inclined planes diffract at a different angle than the (111) plane (surface plane of the thin film); which gives a multiplicity of 3:1, that is a feature of rhombohedral symmetry. Figure 3b shows  $\theta$ -2 $\theta$  scans for {-111} planes family of one rhombohedral variant (selected in red in pole figure) inclined relatively to the sample surface: A clear shift between these peaks collected at  $\chi \sim 71^{\circ}$  and the one corresponding to the (111) plane parallel to the surface is observed, confirming the rhombohedral symmetry [20]. The shift between the central peak and the inclined ones is around  $\Delta(2\theta) = 0.31^\circ$ , and the same shift was observed for the other variants (Figure S5). Importantly, with  $d_{hkl}$  the interplanar spacing of (hkl) planes, the  $d_{111}$ -  $d_{11-1}$  difference depends on the  $\alpha$  angle of the rhombohedral phase. An angle  $\alpha = 89.40^{\circ}$  was reported in HZO thin film with a thickness of 5.9 nm [40], and  $\alpha = 89.5^{\circ}$  in ZrO<sub>2</sub>-3% Y<sub>2</sub>O<sub>3</sub> powder [38], which give a  $\Delta(2\theta)$  between the r-(111) and r-{-111} planes of about 0.42° and 0.36°, respectively. According to the shift observed in Figure 3b, the estimated angle for 14 nm-thick pure  $ZrO_2$  r-phase is  $\alpha = 89.56^{\circ}$  with lattice parameters  $a = b = c \approx 5.089$ Å. The values of  $\alpha$  and of the corresponding out-of-plane d<sub>111</sub> at different thicknesses of ZrO<sub>2</sub> films are reported in Figure 3c. They exhibit a clear dependence on thickness, characteristic of the relaxation of an in-plane compressively strained r-phase: The angle  $\alpha$  increases

toward 90° and  $d_{111}$  decreases as the film thickness increases. This relaxation is consistent with the decrease of polarization measured in ZrO<sub>2</sub> films between 14 nm and 37 nm thickness (Figure S4). Indeed, compressive strain was shown to have a strong impact on the ferroelectric properties of the r-phase [20][40][53].



Figure 3. a) Pole figure around the (111) peak at  $2\theta = 30.19^{\circ}$  of a 14 nm-thick ZrO<sub>2</sub> film. The radial angle  $\chi$  varies between 0° and 90°, the azimuthal angle  $\varphi$  is in the 0°–360° range. b)  $\theta$ -2 $\theta$  scans of one r-variant (red circles in pole figure) revealing a  $\Delta(2\theta)$  shift of 0.31° between diffraction peaks corresponding to out-of-plane and 71°-inclined {111} planes. c) out-of-plane d<sub>111</sub> and rhombohedral angle  $\alpha$  at various thicknesses d) In-plane  $2\theta\chi/\varphi$  scan along <-11-2> DSO in-plane azimuthal direction. e) In-plane  $\varphi$ -scan around  $2\theta\chi$ =50.54°.

In order to get further insights into the epitaxial relationships of ZrO<sub>2</sub> films on LSMO-buffered DSO and STO, and to be more sensitive to the eventual presence of minority phases, we performed a series of in-plane XRD measurements. These in-plane measurements were done only for HZO (SM. [48]) and pure ZrO<sub>2</sub> films; as in pure HfO<sub>2</sub>, the dominant phase is monoclinic. First, we searched the (-11-2) plane of orthorhombic DSO (o-DSO) substrate that diffracts at around  $2\theta = 32.09^{\circ}$  (called  $2\theta \chi$  in in-plane geometry) by rotating the sample in-plane along the  $\varphi$  angle [57]. That allows to fix the offset between  $2\theta \chi$  and  $\varphi$ . Then, in-plane  $2\theta \chi/\varphi$  scans were performed along the azimuthal substrate directions, as given in Figure 3d. In addition to the substrate peaks, two other peaks are present at  $2\theta\chi$ = 50.54° and  $2\theta\chi$  = 95.57°, which correspond to the rhombohedral (20-2) and (22-4) planes, respectively. As the (22-4) plane is rotated by 30° relative to the (20-2) plane; in fact, from Figure 3d, two rhombohedral variants rotated by 90° against each other are observed (Figure S7c). In order to determine the in-plane symmetry of the  $ZrO_2$  phase, we performed in-plane  $\varphi$  scans with the detector fixed at  $2\theta\chi = 50.54^\circ$ . The  $\varphi$ -scan is shown in Figure 3e, revealing 12 peaks with a separation  $\Delta \varphi =$  $30^{\circ}$ , confirming the six-fold symmetry (hexagonal notation) of ZrO<sub>2</sub> thin film. The  $\varphi$ -scan for  $2\theta\chi$  = 95.57° and for the substrate are given in SM (Figure S6), also indicating a six-fold symmetry of the peak around 95.57°. Similar results were obtained for HZO thin film (Figure S7 in SM. [48]). Finally, we note that no LSMO peak was detected in the in-plane scans, neither on DSO nor on STO substrate, in agreement with a fully strained LSMO buffer layer [58].

Furthermore, growth of  $ZrO_2$  and HZO films on STO substrate were also tested and the same structural analyses as discussed for DSO substrate were performed. Interestingly, a tetragonal phase has been detected along the r-phase by in-plane measurements (Figure S9 and S10). The in-plane lattice parameters calculated from XRD for this phase are  $a = b \approx 5.088$  Å, close to the value reported for the relaxed t-ZrO<sub>2</sub> [59][60]. This t-phase was not observed on DSO substrate neither in out-of-plane nor in in-plane XRD scans, even at the highest studied thicknesses of ZrO<sub>2</sub> thin films (Figure 2), hinting at an effect of the different strain caused by DSO compared to STO substrate on t-phase stability.

In conclusion, the rhombohedral phase in  $HfO_2$ -Zr $O_2$  compounds was systematically studied using first-principles calculations and experiments. We evidenced the stability of (111) oriented r-phase in Zr $O_2$  up to the 30-40 nm thickness range from surface energy considerations, and demonstrated experimentally the stabilization of this pure rhombohedral phase in a 37 nm-thick Zr $O_2$  thin film deposited on LSMO buffered DSO (110) substrate, with a remanent polarization 2Pr of 22  $\mu$ C/cm<sup>2</sup>. On STO (001) substrate, a relaxed tetragonal phase was found to coexist with rhombohedral phase in HZO and pure Zr $O_2$  films. We believe that Zr $O_2$ -rich epitaxial thin films open new routes in terms of strain engineering and doping for optimized ferroelectric properties and thicknesses higher than the ones reported in this work.

Acknowledgements: This work has received support from the French national research agency (ANR) under project FOIST (N°ANR-18-CE24-0030), and from the French national network RENATECH for nanofabrication. The authors thank Michel Rerat (IPREM-Pau University, France) for helpful discussions on our *ab initio* calculations.

### References

- T. S. Böscke, J. Müller, D. Bräuhaus, U. Schröder, and U. Böttger, "Ferroelectricity in hafnium oxide thin films," *Appl. Phys. Lett.*, vol. 99, no. 10, 2011, doi: 10.1063/1.3634052.
- [2] S. J. Kim, J. Mohan, S. R. Summerfelt, and J. Kim, "Ferroelectric Hf0.5Zr0.5O2 Thin Films: A Review of Recent Advances," *Jom*, vol. 71, no. 1, pp. 246–255, 2019, doi: 10.1007/s11837-018-3140-5.
- [3] T. D. Huan, V. Sharma, G. A. Rossetti, and R. Ramprasad, "Pathways towards ferroelectricity in hafnia," *Phys. Rev. B Condens. Matter Mater. Phys.*, vol. 90, no. 6, pp. 1–5, 2014, doi: 10.1103/PhysRevB.90.064111.
- Y. Qi *et al.*, "Stabilization of Competing Ferroelectric Phases of HfO2 under Epitaxial Strain," *Phys. Rev. Lett.*, vol. 125, no. 25, p. 257603, 2020, doi: 10.1103/PhysRevLett.125.257603.
- [5] S. V. Barabash, "Prediction of new metastable HfO 2 phases: toward understanding ferro- and antiferroelectric films," *J. Comput. Electron.*, vol. 16, no. 4, pp. 1227–1235, 2017, doi: 10.1007/s10825-017-1077-5.
- [6] F. P. G. Fengler, M. Hoffmann, S. Slesazeck, T. Mikolajick, and U. Schroeder, "On the relationship between field cycling and imprint in ferroelectric Hf0.5Zr0.5O2," J. Appl. Phys., vol. 123, no. 20, pp. 0–8, 2018, doi: 10.1063/1.5026424.
- [7] M. Pešić *et al.*, "Physical Mechanisms behind the Field-Cycling Behavior of HfO2-Based Ferroelectric Capacitors," *Adv. Funct. Mater.*, vol. 26, no. 25, pp. 4601–4612, 2016, doi: 10.1002/adfm.201600590.
- [8] M. Lederer *et al.*, "On the Origin of Wake-Up and Antiferroelectric-Like Behavior in Ferroelectric Hafnium Oxide," *Phys. Status Solidi Rapid Res. Lett.*, vol. 15, no. 5, pp. 1–8, 2021, doi: 10.1002/pssr.202100086.
- [9] M. H. Park *et al.*, "Study on the degradation mechanism of the ferroelectric properties of thin Hf0.5Zr0.5O2 films on TiN and Ir electrodes," *Appl. Phys. Lett.*, vol. 105, no. 7, pp. 0–5, 2014, doi: 10.1063/1.4893376.
- [10] M. Hyuk Park, H. Joon Kim, Y. Jin Kim, W. Lee, T. Moon, and C. Seong Hwang, "Evolution of phases and ferroelectric properties of thin Hf 0.5Zr0.5O2 films according to the thickness and annealing temperature," *Appl. Phys. Lett.*, vol. 102, no. 24, pp. 0–5, 2013, doi: 10.1063/1.4811483.
- [11] M. H. Park *et al.*, "Surface and grain boundary energy as the key enabler of ferroelectricity in nanoscale hafnia-zirconia: A comparison of model and experiment," *Nanoscale*, vol. 9, no. 28, pp. 9973–9986, 2017, doi: 10.1039/c7nr02121f.
- [12] J. Müller *et al.*, "Ferroelectricity in yttrium-doped hafnium oxide," J. Appl. Phys., vol. 110, no. 11, pp. 1–6, 2011, doi: 10.1063/1.3667205.
- [13] R. RUH and P. W. R. CORFIELD, "Crystal Structure of Monoclinic Hafnia and Comparison with Monoclinic Zirconia," *J. Am. Ceram. Soc.*, vol. 53, no. 3, pp. 126–129, Mar. 1970, doi: https://doi.org/10.1111/j.1151-2916.1970.tb12052.x.
- [14] J. Wang, H. P. Li, and R. Stevens, "Hafnia and hafnia-toughened ceramics," J. Mater. Sci., vol. 27, no. 20, pp. 5397–5430, 1992, doi: 10.1007/BF00541601.
- [15] X. Luo, W. Zhou, S. V. Ushakov, A. Navrotsky, and A. A. Demkov, "Monoclinic to tetragonal transformations in hafnia and zirconia: A combined calorimetric and density functional study," *Phys. Rev. B - Condens. Matter Mater. Phys.*, vol. 80, no. 13, pp. 1–13, 2009, doi: 10.1103/PhysRevB.80.134119.
- [16] E. H. Kisi, "Influence of hydrostatic pressure on the t  $\rightarrow$  o transformation in Mg-PSZ studied by in situ neutron diffraction," *J. Am. Ceram. Soc.*, vol. 81, no. 3, pp. 741–745, 1998, doi: 10.1111/j.1151-2916.1998.tb02402.x.
- [17] A. H. Heuer *et al.*, "On the orthorhombic phase in ZrO2-based alloys," *J. Mater. Sci.*, vol. 24, no. 1, pp. 124–132, 1989, doi: 10.1007/BF00660943.
- [18] P. Fan *et al.*, "Origin of the Intrinsic Ferroelectricity of HfO2 from ab Initio Molecular Dynamics," *J. Phys. Chem. C*, vol. 123, no. 35, pp. 21743–21750, 2019, doi: 10.1021/acs.jpcc.9b04106.
- [19] S. J. Lee *et al.*, "Effect of ZrO2 interfacial layer on forming ferroelectric HfxZryOz on Si substrate," *AIP Adv.*, vol. 9, no. 12, 2019, doi: 10.1063/1.5124402.
- [20] Y. Wei *et al.*, "A rhombohedral ferroelectric phase in epitaxially strained Hf 0.5 Zr 0.5 O 2 thin films," *Nat. Mater.*, vol. 17, no. 12, pp. 1095–1100, 2018, doi: 10.1038/s41563-018-0196-0.
- [21] M. Zheng, Z. Yin, Y. Cheng, X. Zhang, J. Wu, and J. Qi, "Stabilization of thick, rhombohedral Hf 0.5 Zr 0.5 O 2 epilayer on c-plane ZnO," *Appl. Phys. Lett.*, vol. 119, no. 17, p. 172904, 2021, doi: 10.1063/5.0064113.
- [22] K. D. Kim *et al.*, "Ferroelectricity in undoped-HfO2 thin films induced by deposition temperature control during atomic layer deposition," *J. Mater. Chem. C*, vol. 4, no. 28, pp. 6864–6872, 2016, doi: 10.1039/c6tc02003h.
- [23] S. Starschich, T. Schenk, U. Schroeder, and U. Boettger, "Ferroelectric and piezoelectric properties of Hf1-xZrxO2 and pure ZrO2 films," *Appl. Phys. Lett.*, vol. 110, no. 18, pp. 2–7, 2017, doi: 10.1063/1.4983031.

- [24] S. Riedel, P. Polakowski, and J. Müller, "A thermally robust and thickness independent ferroelectric phase in laminated hafnium zirconium oxide," *AIP Adv.*, vol. 6, no. 9, 2016, doi: 10.1063/1.4964300.
- [25] H. J. Kim *et al.*, "Grain size engineering for ferroelectric Hf0.5Zr0.5O2 films by an insertion of Al2O3 interlayer," *Appl. Phys. Lett.*, vol. 105, no. 19, pp. 3–8, 2014, doi: 10.1063/1.4902072.
- [26] R. C. Garvie, "The occurrence of metastable tetragonal zirconia as a crystallite size effect," *J. Phys. Chem.*, vol. 69, no. 4, pp. 1238–1243, 1965, doi: 10.1021/j100888a024.
- [27] M. W. Pitcher *et al.*, "Energy crossovers in nanocrystalline zirconia," J. Am. Ceram. Soc., vol. 88, no. 1, pp. 160–167, 2005, doi: 10.1111/j.1551-2916.2004.00031.x.
- [28] M. Shandalov and P. C. McIntyre, "Size-dependent polymorphism in HfO2 nanotubes and nanoscale thin films," *J. Appl. Phys.*, vol. 106, no. 8, pp. 0–5, 2009, doi: 10.1063/1.3243077.
- [29] M. H. Park, H. J. Kim, Y. J. Kim, T. Moon, K. Do Kim, and C. S. Hwang, "Thin HfxZr1-xO2 films: A new lead-free system for electrostatic supercapacitors with large energy storage density and robust thermal stability," *Adv. Energy Mater.*, vol. 4, no. 16, pp. 1–7, 2014, doi: 10.1002/aenm.201400610.
- [30] D. K. Fork, F. Armani-Leplingard, and J. J. Kingston, "Optical Losses in Ferroelectric Oxide Thin Films: Is There Light at the end of the Tunnel?," *MRS Online Proc. Libr.*, vol. 361, no. 1, pp. 155–166, 1994, doi: 10.1557/PROC-361-155.
- [31] B. W. Wessels, "Ferroelectric oxide epitaxial thin films: Synthesis and non-linear optical properties," *J. Cryst. Growth*, vol. 195, no. 1–4, pp. 706–710, 1998, doi: 10.1016/S0022-0248(98)00697-6.
- [32] D. Sando, Y. Yang, C. Paillard, B. Dkhil, L. Bellaiche, and V. Nagarajan, "Epitaxial ferroelectric oxide thin films for optical applications," *Appl. Phys. Rev.*, vol. 5, no. 4, 2018, doi: 10.1063/1.5046559.
- [33] R. Materlik, C. Kunneth, and A. Kersch, "The origin of ferroelectricity in Hf1-xZrxO2: A computational investigation and a surface energy model," *J. Appl. Phys.*, vol. 117, no. 13, 2015, doi: 10.1063/1.4916707.
- [34] T. Mimura, T. Shimizu, and H. Funakubo, "Ferroelectricity in YO1.5-HfO2 films around 1 μ m in thickness," *Appl. Phys. Lett.*, vol. 115, no. 3, 2019, doi: 10.1063/1.5097880.
- [35] R. Batra, H. D. Tran, and R. Ramprasad, "Stabilization of metastable phases in hafnia owing to surface energy effects," *Appl. Phys. Lett.*, vol. 108, no. 17, pp. 106–110, 2016, doi: 10.1063/1.4947490.
- [36] H. Hasegawa, "Rhombohedral phase produced in abraded surfaces of partially stabilized zirconia (PSZ)," *J. Mater. Sci. Lett.*, vol. 2, no. 3, pp. 91–93, 1983, doi: 10.1007/BF00722220.
- [37] H. Hasegawa, T. Hioki, and O. Kamigaito, "Cubic-to-rhombohedral phase transformation in zirconia by ion implantation," *J. Mater. Sci. Lett.*, vol. 4, no. 9, pp. 1092–1094, 1985, doi: 10.1007/BF00720424.
- [38] O. N. Grigor'ev, G. S. Krivoshei, N. A. Stel'mashenko, V. I. Trefilov, and A. V Shevchenko, "Phase transformations during mechanical treatment and the properties of surface layers of a zirconium dioxide ceramic," *Sov. Powder Metall. Met. Ceram.*, vol. 30, no. 5, pp. 376–379, 1991, doi: 10.1007/BF00793662.
- [39] D. P. Burke and W. M. Rainforth, "Intermediate rhombohedral (r-ZrO2) phase formation at the surface of sintered Y-TZP's," J. Mater. Sci. Lett., vol. 16, no. 11, pp. 883–885, 1997, doi: 10.1023/A:1018571601638.
- [40] L. Bégon-Lours *et al.*, "Stabilization of phase-pure rhombohedral HfZr O4 in pulsed laser deposited thin films," *Phys. Rev. Mater.*, vol. 4, no. 4, pp. 1–6, 2020, doi: 10.1103/PhysRevMaterials.4.043401.
- [41] J. P. B. Silva *et al.*, "Wake-up Free Ferroelectric Rhombohedral Phase in Epitaxially Strained ZrO 2 Thin Films," ACS Appl. Mater. Interfaces, vol. 13, no. 43, pp. 51383–51392, 2021, doi: 10.1021/acsami.1c15875.
- [42] Y. Wei *et al.*, "Magnetic Tunnel Junctions Based on Ferroelectric Hf0.5Zr0.5 O2 Tunnel Barriers," *Phys. Rev. Appl.*, vol. 12, no. 3, p. 1, 2019, doi: 10.1103/PhysRevApplied.12.031001.
- [43] Y. Wei *et al.*, "Magneto-ionic control of spin polarization in multiferroic tunnel junctions," *npj Quantum Mater.*, vol. 4, no. 1, pp. 1–6, 2019, doi: 10.1038/s41535-019-0201-0.
- [44] B. Prasad, V. Thakare, A. Kalitsov, Z. Zhang, B. Terris, and R. Ramesh, "Large Tunnel Electroresistance with Ultrathin Hf0.5Zr0.5O2 Ferroelectric Tunnel Barriers," *Adv. Electron. Mater.*, vol. 7, no. 6, pp. 1–6, 2021, doi: 10.1002/aelm.202001074.
- [45] J. P. B. Silva, K. C. Sekhar, H. Pan, J. L. Macmanus-Driscoll, and M. Pereira, "Advances in Dielectric Thin Films for Energy Storage Applications, Revealing the Promise of Group IV Binary Oxides," ACS Energy Lett., vol. 6, pp. 2208–2217, 2021, doi: 10.1021/acsenergylett.1c00313.
- [46] P. Giannozzi *et al.*, "QUANTUM ESPRESSO: A modular and open-source software project for quantum simulations of materials," *J. Phys. Condens. Matter*, vol. 21, no. 39, 2009, doi: 10.1088/0953-8984/21/39/395502.

- [47] J. P. Perdew, K. Burke, and M. Ernzerhof, "Generalized gradient approximation made simple," *Phys. Rev. Lett.*, vol. 77, no. 18, pp. 3865–3868, 1996, doi: 10.1103/PhysRevLett.77.3865.
- [48] A. El Boutaybi, T. Maroutian, L. Largeau, S. Matzen, and P. Lecoeur, "Supplemental material," no. 1.
- [49] A. Christensen and E. A. Carter, "Phys.\_Rev.\_B\_1998\_Christensen," vol. 58, no. 12, pp. 1–15, 1998, [Online]. Available: papers2://publication/uuid/BC6EEC15-2082-4245-956E-813AB1175FCE.
- [50] T. Ning, Q. Yu, and Y. Ye, "Multilayer relaxation at the surface of fcc metals: Cu, Ag, Au, Ni, Pd, Pt, Al," *Surf. Sci.*, vol. 206, no. 1–2, 1988, doi: 10.1016/0039-6028(88)90008-8.
- [51] R. Orlando, C. Pisani, E. Ruiz, and P. Sautet, "Ab initio study of the bare and hydrated (001) surface of tetragonal zirconia," *Surf. Sci.*, vol. 275, no. 3, pp. 482–492, 1992, doi: 10.1016/0039-6028(92)90821-M.
- [52] W. Sun and G. Ceder, "Efficient creation and convergence of surface slabs," Surf. Sci., vol. 617, pp. 53–59, 2013, doi: 10.1016/j.susc.2013.05.016.
- [53] Y. Zhang, Q. Yang, L. Tao, E. Y. Tsymbal, and V. Alexandrov, "Effects of Strain and Film Thickness on the Stability of the Rhombohedral Phase of Hf O2," *Phys. Rev. Appl.*, vol. 14, no. 1, p. 1, 2020, doi: 10.1103/PhysRevApplied.14.014068.
- [54] J. Lyu, I. Fina, R. Solanas, J. Fontcuberta, and F. Sánchez, "Robust ferroelectricity in epitaxial Hf1/2Zr1/2O2 thin films," *Appl. Phys. Lett.*, vol. 113, no. 8, 2018, doi: 10.1063/1.5041715.
- [55] T. Song *et al.*, "Stabilization of the Ferroelectric Phase in Epitaxial Hf1- xZr xO2Enabling Coexistence of Ferroelectric and Enhanced Piezoelectric Properties," *ACS Appl. Electron. Mater.*, vol. 3, no. 5, pp. 2106–2113, 2021, doi: 10.1021/acsaelm.1c00122.
- [56] A. Gualtieri, P. Norby, J. Hanson, and J. Hriljac, "Rietveld Refinement using Synchrotron X-ray Powder Diffraction Data Collected in Transmission Geometry using an Imaging-Plate Detector: Application to Standard m-ZrO2," *J. Appl. Crystallogr.*, vol. 29 PART 6, pp. 707–713, 1996, doi: 10.1107/s0021889896008199.
- [57] R. P. Liferovich and R. H. Mitchell, "A structural study of ternary lanthanide orthoscandate perovskites," *J. Solid State Chem.*, vol. 177, no. 6, pp. 2188–2197, 2004, doi: 10.1016/j.jssc.2004.02.025.
- [58] M. Zahradník et al., "Electronic structure of La2/3Sr1/3MnO3: Interplay of oxygen octahedra rotations and epitaxial strain," Phys. Rev. B, vol. 99, no. 19, p. 195138, May 2019, doi: 10.1103/PhysRevB.99.195138.
- [59] C. J. Howard, E. H. Kisi, R. B. Roberts, and R. J. Hill, "Neutron Diffraction Studies of Phase Transformations between Tetragonal and Orthorhombic Zirconia in Magnesia Partially Stabilized Zirconia," J. Am. Ceram. Soc., vol. 73, no. 10, pp. 2828–2833, 1990, doi: 10.1111/j.1151-2916.1990.tb06682.x.
- [60] C. J. Howard, R. J. Hill, and B. E. Reichert, "Structures of ZrO2 polymorphs at room temperature by high □resolution neutron powder diffraction," *Acta Crystallogr. Sect. B*, vol. 44, no. 2, pp. 116–120, 1988, doi: 10.1107/S0108768187010279.

## Supplemental material

# Stabilization of the epitaxial rhombohedral ferroelectric phase in ZrO<sub>2</sub> by surface energy

Ali El Boutaybi, Thomas Maroutian, Ludovic Largeau, Sylvia Matzen, Philippe Lecoeur

Centre de Nanosciences et de Nanotechnologies, Université Paris-Saclay, CNRS, Palaiseau, France

Contact: ali.el-boutaybi@c2n.upsaclay.fr

### **DFT calculations**

We used the Quantum Espresso (QE) package for our first-principles calculations with a 12-atom cell for HfO<sub>2</sub> and ZrO<sub>2</sub> structures. We tested our calculation results by reproducing some of the previous results (Ref[1]), the calculations have been performed for orthorhombic Pbc2<sub>1</sub> (o-phase), monoclinic P2<sub>1</sub>/c (m-phase), tetragonal P4<sub>2</sub>/nmc (t-phase), and rhombohedral R3m (r-phase) (Figure S1). For R3m phase, we considered a 12-atom cell for HfO<sub>2</sub> with 3-fold-symmetry and we ran an optimization to find the positions of the 12 atoms corresponding to the minimum energy while keeping 3-fold symmetry. Then, we replaced some of the Hf atoms with Zr atoms, according to the targeted composition Hf<sub>1-x</sub>Zr<sub>x</sub>O<sub>2</sub> (x=0, 0.25, 0.5, 0.75, and 1). A cell optimization (lattice parameters and volume) of R3m phase was allowed for all compositions, with a fixed angle at 89.5° as given in Refs [2] [3].



Figure S1. Different phases of ZrO2. The tetragonal cubic face-centered is used in DFT calculation to facilitate the data comparison and for 111-oriented surface energy calculation (Table S2).

	Energy (meV)	Volume (Å)	a(Å)	b(Å)	c(Å)	Technique and Ref
m-HfO <sub>2</sub>	/	138	5.11	5.17	5.29	Exp[4]
	/	138.2	5.11	5.19	5.28	PBE*
	/	137.1	5.12	5.20	5.28	LDA[1]
	/	-	5.13	5.19	5.30	GGA[5]
t-HfO <sub>2</sub>	/		5.06	5.06	5.20	Exp[6]
	122	138.8	5.05	5.05	5.20	PBE*
	92	129.5	5.03	5.03	5.12	LDA[1]
						_
o-HfO <sub>2</sub>	/					Exp
	90	132.2	5.01	5.045	5.23	PBE*
	83.4	-	5.06	5.09	5.27	PBE[7]
	83	-	-	-	-	PBE[8]
	62	132.1	5.02	5.04	5.22	LDA[1]
r-HfO	154	132.3	5 097	5 097	5 097	PRF*
1-11102	154	-	5.09	5.09	5.09	PBEsol[9]
	150		5.07	5.07	5.07	1 DE301[7]
m-ZrO <sub>2</sub>	/	140.3	5.15	5.20	5.32	Exp[10]
	/	140.6	5.16	5.20	5.33	PBE*
	/	138.2	5.11	5.20	5.28	LDA[1]
	/	-	5.17	5.23	5.34	LDA[11]
t-ZrO <sub>2</sub>	/		5.11	5.11	5.27	Exp[12]
	90	138.8	5.10	5.10	5.26	PBE*
7.0	,		5.07	5.00	5.06	F [10]
$0-ZrO_2$	1		5.07	5.08	5.26	Exp[10]
	01	138.8	5.09	5.12	5.52	PBE*
r-7rO-	1	_	5 089	5 089	5 089	Evn**
1-2102	140	135.5	5.13	5.13	5.13	PBE*
	110	155.5	5.15	5.15	5.15	
m-HZO	/	139	5.14	5.19	5.32	PBE*
	/	137.6	5.11	5.18	5.28	LDA[1]
o-HZO			5.01	5.05	5.24	Exp[13]
	68	135.2	5.05	5.08	5.27	PBE*
	59	132.8	5.03	5.05	5.23	LDA[1]
r-HZO	152	-	5.09	5.09	5.09	Exp*
	152	133.5	5.11	5.11	5.11	PBE*

Table S1. Comparison of lattice constants a, b, and c in Å and total

energy difference  $\Delta U^{**}$  in meV/f.u. for HfO<sub>2</sub>, ZrO<sub>2</sub> and HZO.

\*This work, \*\*  $\Delta U$  is given with respect to the monoclinic phase (ground state)

-

- -

PBEsol[9]

-

154

 $\dagger$  These parameters are calculated from a 14-nm thick  $ZrO_2\,thin$  film.

Once these calculations were done for all the considered phases (Table S1), slabs of 4 layers and 48 atoms were created at fixed lattice parameters with different orientations, with a focus on (111)-orientation as it is the most present in our epitaxial thin films. The slab geometries of (111)-oriented rhombohedral and monoclinic phases are given in Figure S1. The slabs are with nonpolar surfaces for all investigated phases, comprised of an integer number of  $ZrO_2$  formula units.

The surface energy was computed following the relation (1) below, and the results are summarized in Table S2.

$$\gamma_{slab}^{\alpha}(t) = \frac{1}{2 A_{slab}^{\alpha}} \left[ E_{slab}^{\alpha}(t) - n E_{bulk}^{\alpha} \right]$$
(1)

Where  $E_{slab}^{\alpha}$  is the DFT energy of the slab with thickness t,  $A_{slab}^{\alpha}$  is the slab area, *n* is the total number of formula units, and  $E_{bulk}^{\alpha}$  is the bulk energy. The superscript  $\alpha$  denotes the phase.



Figure S2. Periodically repeated slab geometry with 48 atoms and convergence test with the number of slab layers for surface energy calculations of r-phase (a and c) and m-phase (b and d), respectively.

	This work	Literature	
m-HfO <sub>2</sub>			
001	1.82	1.55[14]	
111	1.26	1.25[14]	
t-HfO <sub>2</sub>			
001	1.26	1.21[14]	
111	1.25	1.12[14]	
o-HfO <sub>2</sub>			
111	1.6	-	
r-HfO <sub>2</sub>			
R3m 111	1.15	-	
m-ZrO <sub>2</sub>			
001	1.80	1.802[15]	
111	1.42	1.246[15]	
t-ZrO <sub>2</sub>			
001	1.19	1.57[15]	
111	1.21	1.24[15] Exp 1.23[16]	
o-ZrO <sub>2</sub>			
111	1.49	-	
r-ZrO <sub>2</sub>			
R3m 111	0.98	-	
m-HZO			
001	1.87	-	
111	1.31	-	
t-HZO			
001	1.25	-	
111	1.24	-	
o-HZO			
111	1.54	-	
r-HZO	-	-	
R3m 111	1.09	-	

Table S2. Surface energy for HfO<sub>2</sub>, ZrO<sub>2</sub>, and HZO in J/m<sup>2</sup>.

### **Thickness-dependent Gibbs free energy**

The calculated surface energies (Table S2) are integrated in a simple thermodynamic model (Ref [1]) to obtain a thickness-dependent Gibbs free energy for the (111)-oriented monoclinic, rhombohedral and orthorhombic phases. Note that the (111)-oriented o-phase is more stable than the m-phase below 20 nm thickness, but its Gibbs free energy is higher than the one of the r-phase (Figure S3, blue).

Gibbs free energy is calculated as follows [1][17]:

$$\mathbf{G} = \mathbf{F} + \gamma \mathbf{A} + \mathbf{V} \,\boldsymbol{\sigma}_{ii} \boldsymbol{\varepsilon}_{ii} \qquad \mathbf{i} = \mathbf{x}; \, \mathbf{y}; \, \mathbf{z}$$
(2)

Where  $\gamma$ , A, V,  $\sigma_i$ , and  $\varepsilon_i$  are surface energy, surface area, volume, stress tensor, and strain tensor, respectively. The Helmholtz free energy F for the monoclinic phase is taken as zero at 298.15 K. Then, multiplying the equation (2) by (1/V) will give G/V as a function of (1/t<sub>film</sub>), where t<sub>film</sub> is the film thickness (Figure S3). The compressive strain was estimated from the measured relaxation of the ZrO<sub>2</sub> films with increasing film thickness using the equations (3) and (4) [18].

$$\boldsymbol{\varepsilon}_{oop} = \frac{-2\nu}{1-\nu} \boldsymbol{\varepsilon}_{in} \tag{3}$$

Where  $\varepsilon_{oop}$ ,  $\varepsilon_{in}$ , and  $\nu$  are out-of-plane strain, in-plane strain, and Poisson coefficient, respectively. For a Poisson coefficient taken as 0.30 [19], then  $\varepsilon_{oop} \approx -\varepsilon_{in}$ . In-plane strain is thus estimated from  $\varepsilon_{oop}$ , calculated using the following equation:

$$\varepsilon_{oop} = \frac{c_{f} - c_{rf}}{c_{rf}} \tag{4}$$

Where  $c_f$  is the out-of-plane parameter of strained r-phase at 6 nm thickness ( $c_f = 2.98$  Å), and  $c_{rf}$  is the out-of-plane parameter of the relaxed r-phase at 41 nm thickness ( $c_{rf} = 2.95$  Å). Together with equation (3), this gives an estimated in-plane compressive strain of 1%. We used the out-of-plane parameter of the relaxed phase instead of the bulk phase, as no experimental data are available for bulk rhombohedral pure ZrO<sub>2</sub>.

Then, the elastic strain energy was calculated using this relation:

$$\sigma_i = \frac{E}{(1-2\nu)(1+\nu)} \left[ (1-\nu)\varepsilon_i + \nu \left(\varepsilon_j + \varepsilon_k\right) \right]$$
(5)

Where the elastic modulus E is taken as 180 GPa for all phases and compositions [20], and the i,j,k indexes stand successively for the x,y (in-plane) and z (out-of-plane) directions.



Figure S3. a) Gibbs free energy (with 1% compressive strain, see text) of m- and polar o-, and r-phases as a function of film thickness for an epitaxial  $ZrO_2$  film. b) Free energy F +  $\gamma$ A (without compressive strain) of r-phase compared to Gibbs energy (with strain) of m- and r-phase as a function of film thickness.

From Figure S3a, we observe that the Gibbs energy of rhombohedral (R3m) is lower than that of monoclinic phase when the thickness is less than 33 nm. Above this value, the monoclinic phase becomes more stable than the (111)-oriented rhombohedral. While the Gibbs energy of orthorhombic (Pbc2<sub>1</sub>) phase is lower than the one of monoclinic phase when the thickness is less than 19 nm, it is still higher than for the rhombohedral. Note that in this simple Gibbs energy picture, strain-free r-ZrO<sub>2</sub> is still the most stable phase up to about 25 nm (Figure S3b). Also, the surface energy difference between HZO, ZrO<sub>2</sub> and HfO<sub>2</sub> is enough to account for the experimentally observed hierarchy of r-phase stability in these compounds, without invoking grain boundaries or other interface effects.

### **Thin-film synthesis**

Thin films of ZrO<sub>2</sub>, HfO<sub>2</sub>, and HZO were grown by pulsed laser deposition (PLD) on LSMO-buffered DSO(110) and STO(001) substrates. A laser fluence of 1.2 J/cm<sup>2</sup> (wavelength of 248 nm), a repetition rate of 2 Hz, and growth temperature of 760 °C were used for all depositions. The oxygen pressure was 120 mTorr for LSMO and 75 mTorr for Hf<sub>1-x</sub>Zr<sub>x</sub>O<sub>2</sub> (x=0, 0.5, and 1) films, respectively. Right after growth, the films were cooled down to room temperature under an oxygen pressure of 300 Torr, at a rate of 10 °C/min.

#### **P-E characterization**

On top of  $Hf_{1-x}Zr_xO_2/LSMO/DSO$ , Platinum (Pt) top-electrode pads with square shapes ranging from 10x10 to  $200x200 \ \mu\text{m}^2$  were defined by photolithography. Two photolithography levels were used, one for SiN the second for Pt deposition (Figure S4d). Sputtering was used for SiN dielectric (Plassys MP800S) and Pt metal (Alliance Concept AC450) depositions. Pt/ZrO<sub>2</sub>/LSMO and Pt/HZO/LSMO capacitors were characterized using a ferroelectric tester (AiXACCT, TF analyzer 1000). The film ferroelectric response was obtained via Positive Up Negative Down (PUND) measurements, allowing for the switching current to be separated from other contributions (Figure S4).



Figure S4. a, b) Polarization–voltage hysteresis loops of 14 nm-thick ZrO<sub>2</sub> and HZO on DSO substrate. c) Polarization–voltage hysteresis curves of 37 nm-thick ZrO<sub>2</sub> film on DSO substrate. d) Schematic view of metal/film/metal capacitor configuration for P-E characterization.

### Structural characterization

Structure and epitaxial orientations of the thin films were characterized by X-ray diffraction (XRD). Panalytical X'pert Pro diffractometer was used for  $\theta$  -2 $\theta$  characterizations, while pole figures and  $\varphi$  scans (azimuthal angle) were obtained with a Rigaku SmartLab. Both diffractometers were operated in parallel beam configuration with monochromated Cu K $\alpha$ 1 radiation (wavelength of 1.54059Å).

### ZrO2 and HZO on DSO substrate



Figure S5. a) Rhombohedral phase with three planes in radial directions at  $\chi$  around 71° (red color). b) Pole figure around the (111) peak at  $2\theta = 30.19^{\circ}$  of a 14 nm-thick ZrO<sub>2</sub> film. The radial angle  $\chi$  varies between 0° and 90°, the azimuthal angle  $\varphi$  is in the 0°–360° range. c)  $\theta$ -2 $\theta$  scans of the 13 peaks observed in the pole figure revealing a  $\Delta(2\theta)$  shift of 0.31° between diffraction peaks corresponding to out-of-plane and 71°-inclined {111} planes.



Figure S6. a) In-plane  $\varphi$ -scan of {11-2} DSO substrate collected at  $2\theta\chi = 32.09^{\circ}$ . b) In-plane  $\varphi$ -scan of ZrO<sub>2</sub> film at  $2\theta\chi = 95.54^{\circ}$  corresponding to the peak observed in Figure 3a.

Figure S6a confirms the pseudo-cubic four-fold symmetry of the DSO substrate. Figure S6b confirms the six-fold symmetry of the peak around 95.54°; from this figure, four rhombohedral R3m variants are observed.

Figure S7 presents in-plane diffraction scans of HZO on DSO substrate. The tetragonal phase was not detected; only the rhombohedral phase is present. Two r-HZO variants are observed in Figure S7a as illustrated in Figure S7c.



Fig S7. a, b) In-plane  $2\theta\chi/\phi$  scan of HZO film of 14 nm thickness on DSO substrate. b) in-plane  $\phi$ -scan (0-180°) at  $2\theta = 50.53^{\circ}$  showing the hexagonal symmetry. c) Schematic top view of the parallel planes to (-11-2) of the DSO substrate showing two rhombohedral phases rotated by 90° relative to each other.





Figure S8. a) XRD structural characterization of 14 nm-thick ZrO<sub>2</sub> and HZO films on LSMO-buffered STO (001); b) AFM image of the ZrO<sub>2</sub> film with root mean square (RMS) roughness and c) height profile along the horizontal green line.

As shown in Figure S8, at 14 nm thickness a clear monoclinic peak around 28.3° is observed for HZO, while none is seen for ZrO<sub>2</sub>. The dashed line indicates the angle at which would be the tetragonal peak corresponding to the t-phase detected in in-plane measurements (Figures S9 and S10). The surface topography of ZrO<sub>2</sub> was characterized by atomic force microscopy (AFM, Innova from Bruker) in

contact mode. Representative 5 x 5  $\mu$ m<sup>2</sup> image and extracted height profile [21] are shown in Figure S8.



Figure S9. a) In-plane  $2\theta\chi/\phi$  scan along <110> of STO in-plane azimuthal direction. b) In-plane  $\phi$  –scan around  $2\theta\chi$ =50.67°. These measurements have been performed on the film of 14-thick ZrO<sub>2</sub> film (Figure S8).

In the case of  $ZrO_2$ , Figure S9b shows 12 peaks corresponding to four r-phase variants, but also reveals the four-fold symmetry of a tetragonal phase in the film. This t-phase  $ZrO_2$  is not detected in the out-of-plane 2 $\theta$  as illustrated in Figure S8, for the same  $ZrO_2$  film.



Figure S10. a, b) In-plane  $2\theta \chi/\phi$  of 14 nm thick HZO film along <110> and <100> STO azimuthal direction respectively. c) in-plane  $\phi$  -scan at  $2\theta \chi = 50.78^{\circ}$ . d) in-plane  $\phi$  -scan at  $2\theta \chi = 35.25^{\circ}$ .

Figure S10 shows in-plane diffraction of HZO thin film on STO (001), revealing the existence of two phases, rhombohedral (Figure S10c) and tetragonal (Figure S10d). The (100) plane of the tetragonal phase is rotated by 15° with respect to the (20-2) rhombohedral. Figure S10d confirms the four-fold symmetry of the (001)-oriented tetragonal phase. Again, the t-phase is only observed in this in-plane XRD and not in out-of-plane  $\theta$ -2 $\theta$  (figure S8a).



### Crystallographic alignment of r-phase on 4-fold symmetry layer

Figure S11. Possible crystallographic alignment of r-phase (3-fold symmetry) with respect to a buffer layer with 4-fold symmetry, inferred from our XRD data. The atoms at the top of the buffer and in the first layer of the rhombohedral phase are depicted in brown and blue, respectively. (a,b,c) are pseudo-cubic axes of buffer layer.

Here, we would like to present the possible alignment of the r-phase with respect to an underlining 4fold symmetry layer, termed buffer layer for simplicity (Figure S11). This layer could be the LSMO electrode, with or without intermixed Zr/Hf atoms as reported in Ref [22], or a fully strained t-phase as observed at the interface of HZO with LSMO [9]. Note that such an ultrathin t-phase, having the same in-plane lattice parameter as the substrate, cannot be detected by in-plane diffraction scans. Given the 4-fold symmetry of the substrate and the 3-fold symmetry of the r-phase film, the latter can have either 2 or 4 crystallographic variants [23][24]. From in-plane XRD data of Figure S7, S9, and S10, we conclude that the (20-2) rhombohedral plane ((220) in hexagonal notation) is parallel to the (110)-STO and DSO substrate ((-11-2) for DSO in orthorhombic representation). This alignment of the rhombohedral phase is depicted in Figure S11, with the long axis of the unit cell aligned along the [1-10] direction of the buffer. The same alignment is also possible in the [110] direction, giving another r-variant rotated by 90° with respect to the first one (Figure S7). For each of these two variants, another two possibilities arise from the two possible stackings in the ABC-type stacking sequence of r-phase planes in the growth direction (see Figure S2a). Finally, this gives 4 r-phase variants, as detected in the pole figure (Figure S5).

- [1] R. Materlik, C. Kunneth, and A. Kersch, "The origin of ferroelectricity in Hf1-xZrxO2: A computational investigation and a surface energy model," *J. Appl. Phys.*, vol. 117, no. 13, 2015, doi: 10.1063/1.4916707.
- [2] O. N. Grigor'ev, G. S. Krivoshei, N. A. Stel'mashenko, V. I. Trefilov, and A. V Shevchenko, "Phase transformations during mechanical treatment and the properties of surface layers of a zirconium dioxide ceramic," *Sov. Powder Metall. Met. Ceram.*, vol. 30, no. 5, pp. 376–379, 1991, doi: 10.1007/BF00793662.
- [3] L. Bégon-Lours *et al.*, "Stabilization of phase-pure rhombohedral HfZr O4 in pulsed laser deposited thin films," *Phys. Rev. Mater.*, vol. 4, no. 4, pp. 1–6, 2020, doi: 10.1103/PhysRevMaterials.4.043401.
- [4] R. RUH and P. W. R. CORFIELD, "Crystal Structure of Monoclinic Hafnia and Comparison with Monoclinic Zirconia," *J. Am. Ceram. Soc.*, vol. 53, no. 3, pp. 126–129, Mar. 1970, doi: https://doi.org/10.1111/j.1151-2916.1970.tb12052.x.
- [5] J. E. Jaffe, R. A. Bachorz, and M. Gutowski, "Low-temperature polymorphs of ZrO2 and HfO2: A density-functional theory study," *Phys. Rev. B Condens. Matter Mater. Phys.*, vol. 72, no. 14, pp. 1–9, 2005, doi: 10.1103/PhysRevB.72.144107.
- [6] I. MacLaren, T. Ras, M. MacKenzie, A. J. Craven, D. W. McComb, and S. De Gendt, "Texture, Twinning, and Metastable 'Tetragonal' Phase in Ultrathin Films of HfO[sub 2] on a Si Substrate," *J. Electrochem. Soc.*, vol. 156, no. 8, p. G103, 2009, doi: 10.1149/1.3141705.
- [7] R. Batra, T. D. Huan, J. L. Jones, G. Rossetti, and R. Ramprasad, "Factors Favoring Ferroelectricity in Hafnia: A First-Principles Computational Study," J. Phys. Chem. C, vol. 121, no. 8, pp. 4139–4145, 2017, doi: 10.1021/acs.jpcc.6b11972.
- [8] S. V. Barabash, "Prediction of new metastable HfO 2 phases: toward understanding ferro- and antiferroelectric films," *J. Comput. Electron.*, vol. 16, no. 4, pp. 1227–1235, 2017, doi: 10.1007/s10825-017-1077-5.
- [9] Y. Wei *et al.*, "A rhombohedral ferroelectric phase in epitaxially strained Hf 0.5 Zr 0.5 O 2 thin films," *Nat. Mater.*, vol. 17, no. 12, pp. 1095–1100, 2018, doi: 10.1038/s41563-018-0196-0.
- [10] E. H. Kisi and C. J. Howard, "Crystal structures of zirconia phases and their inter-relation," *Key Eng. Mater.*, vol. 154, no. 153–154, pp. 1–36, 1998, doi: 10.4028/www.scientific.net/kem.153-154.1.
- [11] J. E. Lowther, J. K. Dewhurst, J. M. Leger, and J. Haines, "Relative stability of ZrO2 and HfO2 structural phases," *Phys. Rev. B*, vol. 60, no. 21, pp. 14485–14488, 1999, doi: 10.1103/physrevb.60.14485.
- [12] G. Teufer, "The crystal structure of tetragonal ZrO2," *Acta Crystallogr.*, vol. 15, no. 11, pp. 1187–1187, 1962, doi: 10.1107/s0365110x62003114.
- [13] J. Müller *et al.*, "Ferroelectricity in simple binary ZrO 2 and HfO 2," *Nano Lett.*, vol. 12, no. 8, pp. 4318–4323, 2012, doi: 10.1021/nl302049k.
- [14] R. Batra, H. D. Tran, and R. Ramprasad, "Stabilization of metastable phases in hafnia owing to surface energy effects," *Appl. Phys. Lett.*, vol. 108, no. 17, pp. 106–110, 2016, doi: 10.1063/1.4947490.
- [15] A. Christensen and E. A. Carter, "Phys.\_Rev.\_B\_1998\_Christensen," vol. 58, no. 12, pp. 1–15, 1998, [Online]. Available: papers2://publication/uuid/BC6EEC15-2082-4245-956E-813AB1175FCE.
- [16] A. V. Radha, O. Bomati-Miguel, S. V. Ushakov, A. Navrotsky, and P. Tartaj, "Surface enthalpy, enthalpy of water adsorption, and phase stability in nanocrystalline monoclinic zirconia," *J. Am. Ceram. Soc.*, vol. 92, no. 1, pp. 133–140, 2009, doi: 10.1111/j.1551-2916.2008.02796.x.
- [17] Z. Zhang *et al.*, "Epitaxial Ferroelectric Hf0.5Zr0.5O2 with Metallic Pyrochlore Oxide Electrodes," *Adv. Mater.*, vol. 33, no. 10, pp. 1–10, 2021, doi: 10.1002/adma.202006089.
- [18] J. Y. Tsao, Materials Fundamentals of Molecular Beam Epitaxy. 1993.
- [19] K. Tapily, J. E. Jakes, D. Gu, H. Baumgart, and A. A. Elmustafa, "Nanomechanical study of amorphous and polycrystalline ALD HfO2 thin films," *Int. J. Surf. Sci. Eng.*, vol. 5, no. 2–3, pp. 193–204, Jan. 2011, doi: 10.1504/IJSURFSE.2011.041402.
- [20] A. Jayaraman, S. Y. Wang, S. K. Sharma, and L. C. Ming, "Pressure-induced phase transformations in HfO2 to 50 GPa studied by Raman spectroscopy," *Phys. Rev. B*, vol. 48, no. 13, pp. 9205–9211, Oct. 1993, doi: 10.1103/PhysRevB.48.9205.
- [21] I. Horcas, R. Fernández, J. M. Gómez-Rodríguez, J. Colchero, J. Gómez-Herrero, and A. M. Baro, "WSXM: A software for scanning probe microscopy and a tool for nanotechnology," *Rev. Sci. Instrum.*, vol. 78, no. 1, p. 13705, Jan. 2007, doi: 10.1063/1.2432410.
- [22] S. Estandía, T. Cao, R. Mishra, I. Fina, F. Sánchez, and J. Gazquez, "Insights into the atomic structure of the interface of ferroelectric Hf0.5Zr0.5 O2 grown epitaxially on La2/3Sr1/3Mn O3," *Phys. Rev. Mater.*, vol. 5, no. 7, pp. 1–9, 2021, doi: 10.1103/PhysRevMaterials.5.074410.
- [23] A. Yanase, Y. Segawa, M. Mihara, W. M. Tong, and R. S. Williams, "Heteroepitaxial growth of CuCl on MgO(001) substrates," *Surf. Sci.*, vol. 278, no. 1–2, 1992, doi: 10.1016/0039-6028(92)90569-R.
- [24] M. Grundmann, T. Böntgen, and M. Lorenz, "Occurrence of rotation domains in heteroepitaxy," *Phys. Rev. Lett.*, vol. 105, no. 14, pp. 1–4, 2010, doi: 10.1103/PhysRevLett.105.146102.