



HAL
open science

3D modeling of HTS tape stacks in superconducting magnetic bearings with real thickness

Asef Ghabeli, Francesco Grilli, Jens Hänisch, Günther Fuchs, Oliver de Haas,
Pengbo Zhou

► **To cite this version:**

Asef Ghabeli, Francesco Grilli, Jens Hänisch, Günther Fuchs, Oliver de Haas, et al.. 3D modeling of HTS tape stacks in superconducting magnetic bearings with real thickness. 8th International Workshop on Numerical Modelling of High Temperature Superconductors (HTS 2022), Kévin Berger (Université de Lorraine - GREEN), Jun 2022, Nancy, France. hal-03791509

HAL Id: hal-03791509

<https://hal.science/hal-03791509v1>

Submitted on 29 Sep 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

3D modeling of HTS tape stacks in superconducting magnetic bearings with real thickness

Asef Ghabeli, Francesco Grilli
and Jens Hänsch
*Institute for Technical Physics
Karlsruhe Institute of Technology
Karlsruhe, Germany
asef.ghabeli@kit.edu
francesco.grilli@kit.edu
jens.haenisch@kit.edu*

Günther Fuchs
and Oliver de Haas
*evico GmbH
Dresden, Germany
g.fuchs@evico.de
deHaas@evico.de*

Pengbo Zhou
¹*Institute for Technical Physics
Karlsruhe Institute of Technology
Karlsruhe, Germany*
²*Southwest Jiaotong University
Chengdu, China
pengbo.zhou@kit.edu*

Abstract—Superconducting magnetic bearings (SMBs) offer a passive and contactless technique for rotating machines and, as linear bearings, for superconducting maglev systems. Stacks of superconducting tapes have been recently used as an alternative to the bulk. Modeling has been employed as a cost-effective, fast and reliable tool for improving the performance of SMBs. 2D models have been extensively used in the past, due to offering much faster computations compared to 3D models. However, using the 3D models is sometimes inevitable, especially when the depth of the problem geometry is comparable to the width and height or when the magnet guideway or the passive component geometries are complicated or asymmetrical. In this study, we employ an energy minimization method called MEMEP 3D, developed in C++, for modeling the magnetization of the tape stacks in three dimensions in a reasonable time. This method is significantly faster and more efficient than the previously proposed 3D methods giving the opportunity to model tens of HTS tapes with their real thickness with consideration of $J_c(B, \theta)$ dependence.

Keywords—Tape Stacks, Magnetization of tape stacks, Numerical modeling, Superconducting magnetic bearing, Lorentz force calculation

I. INTRODUCTION

The passive superconducting levitation of superconducting magnetic bearings (SMBs) is very promising for the development of levitated trains [1]. The advantage is that the generated repulsive force between the magnet guideway and the superconducting part is mechanically stable without using any control system, unlike the repulsive force between two permanent magnets (PM).

Bulk superconductors have been mostly employed as the passive component in SMBs [2]–[5]. However, recently, stacks of superconductor tapes have been utilized as an alternative for the bulks offering better mechanical properties, better thermal conductivity and a simpler production process. [6]–[8].

Modeling is a cost-effective, fast and reliable tool to optimize or improve the performance of the SMBs. This issue has been investigated in several studies using numerical methods or a combination of analytical and numerical methods. For performing the optimization process, the problem should be solved in a reasonable time, which makes the 2D models a more popular option. However, using a 3D model is sometimes inevitable for the following reasons: when the depth of problem geometry is comparable to the width and height, the 2D model usually leads to a large errors. Moreover, when the magnet guideway or the passive component geometries are complicated or asymmetrical, the 2D model would be either incapable of simulating or subjected to a large error. A fast and efficient 3D model that can be solved in a reasonable time period can be the solution of the above mentioned issues.

There are several numerical models with the purpose of reproducing the performances of tape stacks or cables made of stacks such as 2D models in [9]–[16] and 3D models in [17]–[19]. The 2D models take advantage of several strategies to reduce the computational load such as homogenization, densification and multi-scaling. However, these strategies have been mostly implemented and verified on 2D models due to the very high aspect ratio of the HTS tape and enormous numbers of degrees of freedom in 3D models.

In this study, we employ an energy minimization method called minimum electromagnetic entropy production method in 3D (MEMEP 3D), implemented in C++, for solving the problem of magnetization of tape stacks in three dimensions. This method had been presented and verified by experiments and other methods in several works [18]–[22]. We develop this method to calculate the levitation force between magnet and tape stacks in field cooling (FC) and zero field cooling (ZFC) cases and compare the results with experimental data. We investigate the implementation of strategies such as homogenization and densification and study the possibility of implementing the real configuration of tape stacks including modeling of each individual HTS tape with its real thickness and $J_c(B, \theta)$ dependence of the HTS tape. The




Fig. 1. Schematic of the problem

TABLE I
PROBLEM PARAMETERS INCLUDING PM GEOMETRY AND MOVEMENT,
AND HTS STACKS OF TAPES CHARACTERISTICS

Permanent Magnet	Diameter	35 mm
	Height	20 mm
	Remanent flux density, B_r	1.22 T
Magnet displacement	$2 \text{ mm} < \Delta z < 52 \text{ mm}$	
	Movement speed	1 mm/s
2 Stacks of Tapes	Width	24 mm
	Depth	24 mm
	Height	10 mm
	Width	12 mm
HTS Tape	Thickness	76 μm
	Thickness of Superconducting layer	1 μm
	Tape Critical Current I_c	350 A
	Assumed n-value	25

non-superconducting layers in the stacks are modeled as a conducting material of very high resistivity.

II. PROBLEM DESCRIPTION

Fig. 1 shows the schematic of the problem and Table I lists the parameters related to PM geometry and movement as well as characteristics of the stacks. The passive part of the SMB is comprised of two parallel stacks of SuperOx tapes, each one containing 132 pieces of tapes.

The first investigated case is ZFC in which the magnet traverses the distance from $\Delta z = 52 \text{ mm}$, where the magnet is far enough from the stack so that the applied field is negligible, up to the distance of $\Delta z = 2 \text{ mm}$ and comes back to its initial position in a full cycle. The goal is to obtain the hysteresis force loop between stacks and PM. The force \mathbf{F} is defined as the Lorentz force due to interaction between the PM magnetic field and the screening current generated in the HTS stacks of tapes:

$$\mathbf{F} = \int_v \mathbf{J} \times \mathbf{B} dv \quad (1)$$

where v is the volume of the HTS domain, \mathbf{J} is the screening current in the HTS stacks, and \mathbf{B} is the magnetic field of PM.

III. MODELING RESULTS

As the first step, we use the homogenization process to obtain the force loop. Using homogenization, we transform the two parallel HTS tape stacks into a single homogeneous bulk. This is more convenient and faster in terms of computational speed. The calculation time is about one hour for one cycle.




Fig. 2. MEMEP 3D bulk homogenization modeling results against experiment for the ZFC case

Due to unavailable $J_c(B, \theta)$ data of the SuperOx tape at the present time, we use the trial-and-error process to find the two parameters of isotropic Kim-Anderson model for describing the dependence of the critical current density of the HTS tape to the magnetic field [23]. Figure 2 shows the MEMEP 3D bulk homogenization modeling result against the experimental data in the ZFC case. Good agreement between modeling and experiment can be observed. We expect even better agreement when the measured $J_c(B, \theta)$ data of the tape is used instead of the Kim-Anderson model for defining the $J_c(B, \theta)$ dependence of the HTS tape to the magnetic field.

ACKNOWLEDGMENT

The authors would like to acknowledge the financial support of the German Federal Ministry for Economic Affairs and Energy under BMWi contract no. ZIM KK5082301SH0.

REFERENCES

- [1] P. Bernstein and J. Noudem, "Superconducting magnetic levitation: principle, materials, physics and models," *Superconductor Science and Technology*, vol. 33, no. 3, p. 033001, 2020.
- [2] D. H. N. Dias, E. S. Motta, G. G. Sotelo, R. de Andrade, R. M. Stephan, L. Kuehn, O. de Haas, and L. Schultz, "Simulations and tests of superconducting linear bearings for a MAGLEV prototype," *IEEE transactions on applied superconductivity*, vol. 19, no. 3, pp. 2120–2123, 2009.
- [3] F. Werfel, U. Floegel-Delor, R. Rothfeld, T. Riedel, D. Wippich, B. Goebel, and P. Schirrmeister, "Bulk superconductors in mobile application," *Physics Procedia*, vol. 36, pp. 948–952, 2012.
- [4] L. Quéval, G. G. Sotelo, Y. Kharmiz, D. H. Dias, F. Sass, V. M. Zermeno, and R. Gottkehaskamp, "Optimization of the superconducting linear magnetic bearing of a maglev vehicle," *IEEE Transactions on Applied Superconductivity*, vol. 26, no. 3, pp. 1–5, 2016.
- [5] F. Werfel, U. Floegel-Delor, R. Rothfeld, T. Riedel, B. Goebel, D. Wippich, and P. Schirrmeister, "Superconductor bearings, flywheels and transportation," *Superconductor Science and Technology*, vol. 25, no. 1, p. 014007, 2011.
- [6] A. Patel, S. Hahn, J. Voccio, A. Baskys, S. Hopkins, and B. Glowacki, "Magnetic levitation using a stack of high temperature superconducting tape annuli," *Superconductor Science and Technology*, vol. 30, no. 2, p. 024007, 2016.
- [7] M. Osipov, A. Starikovskii, D. Abin, and I. Rudnev, "Influence of the critical current on the levitation force of stacks of coated conductor superconducting tapes," *Superconductor Science and Technology*, vol. 32, no. 5, p. 054003, 2019.
- [8] Z. Liu, W. Yang, L. Yu, Y. Ji, M. Bai, X. Li *et al.*, "Testing and comparison of levitation forces and rotational friction in different superconducting tape stacks," *Journal of Superconductivity and Novel Magnetism*, vol. 33, no. 10, pp. 3035–3041, 2020.

- [9] L. Quéval, V. M. Zermeño, and F. Grilli, "Numerical models for ac loss calculation in large-scale applications of HTS coated conductors," *Superconductor Science and Technology*, vol. 29, no. 2, p. 024007, 2016.
- [10] V. M. Zermeño, A. B. Abrahamsen, N. Mijatovic, B. B. Jensen, and M. P. Sørensen, "Calculation of alternating current losses in stacks and coils made of second generation high temperature superconducting tapes for large scale applications," *Journal of Applied Physics*, vol. 114, no. 17, p. 173901, 2013.
- [11] E. Berrospe-Juarez, F. Trillaud, V. M. Zermeño, and F. Grilli, "Advanced electromagnetic modeling of large-scale high-temperature superconductor systems based on H and T-A formulations," *Superconductor Science and Technology*, vol. 34, no. 4, p. 044002, 2021.
- [12] E. Berrospe-Juarez, V. M. Zermeño, F. Trillaud, and F. Grilli, "Iterative multi-scale method for estimation of hysteresis losses and current density in large-scale HTS systems," *Superconductor Science and Technology*, vol. 31, no. 9, p. 095002, 2018.
- [13] F. Sass, G. Sotelo, R. de Andrade Junior, and F. Sirois, "H-formulation for simulating levitation forces acting on HTS bulks and stacks of 2G coated conductors," *Superconductor Science and Technology*, vol. 28, no. 12, p. 125012, 2015.
- [14] F. Liang, S. Venuturumilli, H. Zhang, M. Zhang, J. Kvitkovic, S. Pamidi, Y. Wang, and W. Yuan, "A finite element model for simulating second generation high temperature superconducting coils/stacks with large number of turns," *Journal of Applied Physics*, vol. 122, no. 4, p. 043903, 2017.
- [15] S. Zou, V. M. Zermeño, and F. Grilli, "Simulation of stacks of high-temperature superconducting coated conductors magnetized by pulsed field magnetization using controlled magnetic density distribution coils," *IEEE Transactions on Applied Superconductivity*, vol. 26, no. 3, pp. 1–5, 2016.
- [16] K. Zhang, S. Hellmann, M. Calvi, and T. Schmidt, "Magnetization simulation of ReBCO tape stack with a large number of layers using the ANSYS A-V-A formulation," *IEEE Transactions on Applied Superconductivity*, vol. 30, no. 4, pp. 1–5, 2020.
- [17] V. M. Zermeño and F. Grilli, "3D modeling and simulation of 2G HTS stacks and coils," *Superconductor Science and Technology*, vol. 27, no. 4, p. 044025, 2014.
- [18] M. Kapolka, V. M. R. Zermeño, S. Zou, A. Morandi, P. L. Ribani, E. Pardo, and F. Grilli, "Three-dimensional modeling of the magnetization of superconducting rectangular-based bulks and tape stacks," *IEEE Transactions on Applied Superconductivity*, vol. 28, no. 8201206, 2018.
- [19] M. Kapolka, E. Pardo, F. Grilli, A. Baskys, V. Climente-Alarcon, A. Dadhich, and B. Glowacki, "Cross-field demagnetization of stacks of tapes: 3D modelling and measurements," *Supercond. Sci. Technol.*, vol. 33, no. 4, p. 044019, 2020.
- [20] E. Pardo, M. Kapolka, J. Kováč, J. Šouc, F. Grilli, and A. Piqué, "Three-dimensional modeling and measurement of coupling ac loss in soldered tapes and striated coated conductors," *IEEE Transactions on Applied Superconductivity*, vol. 26, no. 3, pp. 1–7, 2016.
- [21] E. Pardo and M. Kapolka, "3D computation of non-linear eddy currents: Variational method and superconducting cubic bulk," *Journal of Computational Physics*, vol. 344, pp. 339 – 363, 2017.
- [22] A. Ghabeli, E. Pardo, and M. Kapolka, "3D modeling of a superconducting dynamo-type flux pump," *Scientific Reports*, vol. 11, no. 1, pp. 1–12, 2021.
- [23] L. Quéval, K. Liu, W. Yang, V. M. Zermeño, and G. Ma, "Superconducting magnetic bearings simulation using an H-formulation finite element model," *Superconductor Science and Technology*, vol. 31, no. 8, p. 084001, 2018.