



**HAL**  
open science

# Complex refractive index determination of PTFE, TPX and polypropylene windows for TeraHertz broadband spectroscopy

J. Bichon, A. Pillet, A. Sklia, D. Petitprez, Romain Peretti, S. Eliet

► **To cite this version:**

J. Bichon, A. Pillet, A. Sklia, D. Petitprez, Romain Peretti, et al.. Complex refractive index determination of PTFE, TPX and polypropylene windows for TeraHertz broadband spectroscopy. 2022 47th International Conference on Infrared, Millimeter and Terahertz Waves (IRMMW-THz), Aug 2022, Delft, Netherlands. pp.1-2, 10.1109/IRMMW-THz50927.2022.9895520 . hal-03794330

**HAL Id: hal-03794330**

**<https://hal.science/hal-03794330>**

Submitted on 6 Oct 2022

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Complex refractive index determination of PTFE, TPX and polypropylene windows for TeraHertz broadband spectroscopy

J. Bichon<sup>1,2</sup>, A. Pillet<sup>1</sup>, A. Sklia<sup>1,3</sup>, D. Petitprez<sup>2</sup>, R. Peretti<sup>1</sup> and S. Eliet<sup>1</sup>

<sup>1</sup>Univ. Lille, CNRS, Centrale Lille, Univ. Polytechnique Hauts-de-France, UMR 8520 - IEMN, F-59000 Lille, France

<sup>2</sup>Univ. Lille, CNRS, UMR 8522 - PC2A - Physicochimie des Processus de Combustion et de l'Atmosphère, F-59000 Lille, France

<sup>3</sup>ENS Paris-Saclay, 91190 Gif-sur-Yvette, France

**Abstract**—We perform TeraHertz characterization of three low-loss polymer candidates, i.e. polytetrafluoroethylene, polymethylpentene, and polypropylene, to choose the material with the proper opto-mechanical properties for aerosol and gas broadband spectroscopy cell windows. Samples are analyzed with the TeraHertz time domain spectroscopy technique. Then, the time-traces are fitted with theoretical models and the real and imaginary parts of their complex refractive indices are extracted using the Fit@TDS algorithm developed by Photonic TeraHertz team members.

## I. INTRODUCTION

POLYMERS are valuable materials in research for their exceptional properties such as durability and resistance. They are, for instance, widely used in optical assemblies as lenses or windows due to their transparency in the visible and TeraHertz (THz) range. However, only few studies have calculated their complex refractive indices (CRI) and data from 3 to 10 THz is almost non-existent [1].


Broadband spectroscopy in the THz is of paramount importance in the study of aerosols and/or gases to understand current issues such as climate change [2] or disease diagnosis [3]. Nonetheless, the analytical equipment needs windows with opto-mechanical requirements (e.g. withstanding pressure, avoiding degassing and maximizing transmission). A complete optical characterization of the deployed materials in optical assemblies is therefore essential before taking measurements.

In this regard, three low-loss polymer candidates, i.e. polytetrafluoroethylene (PTFE – 2.5 mm thick), polymethylpentene (TPX – 2 mm) and polypropylene (PP – 50 microns), are analyzed with a TeraHertz Time Domain Spectrometer (THz-TDS – TDS Terasmart from Menlo systems, 90 fs/1.5μm laser; 850 ps delay line). In comparison with other techniques, THz-TDS has the advantage of measuring the time-dependent amplitude  $E(t)$  and hence simultaneously acquiring the amplitude and the phase. There is therefore no need of empirical models or Kramers-Kronig analysis to get the CRI [4].

The real and imaginary parts of the CRI are extracted from the time-traces and fitted with theoretical models using the Fit@TDS software developed by THz Photonic team members at IEMN [5]. For nonpolar polymers, the model used is the Lorentz oscillator. The fit is based on 4 parameters: the permittivity, and the resonance frequency, the linewidth, and the strength of the oscillator for each oscillator [6]. An extrapolation is carried out for PTFE (beyond 5 THz) and for PP (beyond 7.3 THz).


## II. RESULTS

The CRI of PTFE from 0.2 to 8 THz are reported in the figures below (Fig.1). The figures show a Lorentz-shaped resonant absorption at 0.91 THz with a linewidth of 0.12 THz above a broad band of higher frequency. Our results demonstrate a broad absorption band of small oscillator strength characteristic of low-loss polymers at 2.48 THz. These two resonances can be attributed to weak lattice modes. An intense Lorentz oscillator absorption peak is at 5.71 THz. This peak is found by extrapolation and corresponds to the twisting mode of  $CF_2$ . Previous studies indicate only a broad absorption band in the measured range and confirm the intense peak around 6 THz. These results go beyond previous reports by showing the presence of a weak absorption peak at 0.91 THz thanks to a better signal/noise ratio [7,8].




**Fig. 1.** The real (blue) and imaginary (red) parts of the CRI of PTFE from 0.2 to 8 THz on the left. On the right, a zoom between 0.2 and 4 THz. The results indicate 3 Lorentz oscillator resonance at 0.91, 2.48 and 5.71 THz. The extrapolation was performed in the range after the orange dotted line.

PP exhibits 3 Lorentzian shape absorption peaks at 2.32, 5.19 and 7.56 THz (Fig.2). Similarly, the two weak peaks can be assigned to lattice modes and the one at 7.56 THz is probably due to CH vibrations. A comparable conclusion was reached by reported findings regarding the frequencies of the resonances [9]. Although the intensity of the peak at 7.56 THz is clearly higher than that of the two other absorptions as in our case, the precision of the measurements in the literature does not allow to compare the intensities of the peaks.



**Fig. 2.** The real (blue) and imaginary (red) parts of the CRI of PP from 0.2 to 8.5 THz, showing 3 Lorentz shape resonance at 2.32, 5.19 and 7.56 THz. The extrapolation was performed in the range after the orange dotted line.

TPX has a wide absorption band at 3.56 THz of low oscillator strength due to lattice mode vibrations (Fig.3). The variations of the real and imaginary parts are of the order of  $10^{-3}$  in the measurement frequencies range. Furthermore, the TPX has no absorption peak from 0.2 to 5 THz that could interfere with measurements. Nevertheless, further studies should be carried out to study its behavior beyond 5 THz.



**Fig. 3.** The real (blue) and imaginary (red) parts of the CRI of TPX from 0.2 to 5 THz. TPX has a singular weak and broad absorption band at 3.56 THz with a linewidth of 38.3 THz.

### III. SUMMARY

This study adds to a corpus of research showing the dielectric properties of non-polar polymers in the THz range. Collectively, our results appear to be consistent with those in the literature. However, our measurements show a better resolution at low frequency and a better signal-to-noise ratio. Additionally, more than 8 THz is reached in some cases, while most studies have results that stop at around 3 THz. During the conference, an overview of the dielectric, optical and mechanical properties of the three materials will be provided during the conference to enable proper comparison and benchmark of the windows.

### IV. ACKNOWLEDGMENT

The authors gratefully acknowledge the financial support of the French National Research Agency (ANR-20-CE42-0002 STEPSON). The authors also appreciated the support by the CaPPA project (Chemical and Physical Properties of the Atmosphere) funded by the French National Research Agency (ANR) through the PIA (Programme d'Investissement d'Avenir) under contract « ANR-11-LABX-0005-01 ».

### REFERENCES

- [1] E. V. Fedulova, *et al*, "Studying of dielectric properties of polymers in the terahertz frequency range," Proc. SPIE 8337, Saratov Fall Meeting 2011: Optical Technologies in Biophysics and Medicine XIII, 83370I (28 February 2012).
- [2] J. Bichon, *et al*, "Complex refractive indices in the TeraHertz domain of samples from atmospheric aerosol sources", 46th International Conference on Infrared, Millimeter and Terahertz Waves (IRMMW-THz), Aug 2021, Chengdu, China. pp.1-2.
- [3] N.Rothbart, *et al*, « Analysis of Human Breath by Millimeter-Wave/TeraHertz Spectroscopy », Sensors (Basel, Switzerland) vol. 19,12,2719. 17 Jun. 2019.
- [4] H. Herbin *et al*, "New approach for the determination of aerosol refractive indices - Part I: Theoretical bases and numerical methodology", Journal of Quantitative Spectroscopy and Radiative Transfer 200, March 2017
- [5] R. Peretti, *et al*, "THz-TDS time-trace analysis for the extraction of material and metamaterial parameters", IEEE transactions on Terahertz Science and Technology, 9, 136, 2019. Software available on: <https://github.com/THzbiophotonics/Fit-TDS>
- [6] M. Lavancier, *et al*, "Retrieving permittivity model parameters for polarliquids and multilayer systems through THz-TDS time-trace data analysis", 44th International Conference on Infrared, Millimeter, and Terahertz Waves (IRMMW-THz), Sep 2019, Paris, France. pp.1-2.
- [7] P.D. Cunningham, *et al*, "Broadband terahertz characterization of the refractive index and absorption of some important polymeric and organic electro-optic materials", Journal of applied physics, 2011-02-22, Vol.109 (4), p.043505-043505-5.
- [8] F. D'Angelo *et al*, "Ultra-broadband THz time-domain spectroscopy of common polymers with THz air-photonics", Optics Express, 19 May 2014, Vol. 22, No. 10.
- [9] S. Ariyoshi, *et al*, "Broadband terahertz spectroscopy of cellulose nanofiber-reinforced polypropylenes", Materials Science and Engineering: B Volume 265, March 2021, 115000.