



HAL
open science

Study of the behavior of post installed fasteners in civil engineering structures of french nuclear installations

Aya Rima, Frederic Ragueneau, Cecile Oliver-Leblond, Thierry Guillet, Marie Helene Bonhomme, Georges Nahas

► To cite this version:

Aya Rima, Frederic Ragueneau, Cecile Oliver-Leblond, Thierry Guillet, Marie Helene Bonhomme, et al.. Study of the behavior of post installed fasteners in civil engineering structures of french nuclear installations. FIB International Conference on Concrete Sustainability, FIB, Nov 2021, Shangai, China. hal-03812712

HAL Id: hal-03812712

<https://hal.science/hal-03812712>

Submitted on 13 Oct 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

STUDY OF THE BEHAVIOR OF POST INSTALLED FASTENERS IN CIVIL ENGINEERING STRUCTURES OF FRENCH NUCLEAR INSTALLATIONS

Aya RIMA^{1,2,3}, Frédéric RAGUENEAU¹, Cécile OLIVER-LEBLOND¹, Thierry GUILLET², Marie-Hélène BONHOMME³, Georges NAHAS³

1. LMT (ENS Paris-Saclay), 61 avenue du Président Wilson, 94235 Cachan Cedex, France

2. Université Paris-Est, Centre Scientifique et Technique du Bâtiment (CSTB), 84 avenue Jean Jaurès, Champs-sur-Mame, 77447 Mame-la-Vallée Cedex 2, France

3. Institut de Radioprotection et de Sûreté Nucléaire (IRSN), 92262 Fontenay-aux-Roses Cedex, France

Corresponding author email: aya.rima@ens-paris-saclay.fr

Abstract

When it comes to providing connection between different components, post installed mechanical fasteners always offer a suitable solution. The level of performances of these fasteners is nevertheless a concern, due to the consequences it may cause if they were inappropriately chosen. In order to avoid unexpected low performance of the fasteners, it is important to have a good knowledge of the mechanical behavior of fasteners to guarantee the durability and the efficiency of the structure. This issue is for instance raised in the case of French nuclear power plants for which the decision to extend the duration life is at stake. In addition, except for newly installed anchors, most fasteners used in nuclear power plants have not been specifically qualified to demonstrate their capacity to support seismic loading. In recent years, CSTB (Centre Scientifique et Technique du Bâtiment) carried out experimental tests on fasteners used in nuclear power plant. The results showed that the shear capacity of these anchors subjected to seismic load is relatively lower with respect to a static loading, which highlighted a need to study in more details their behavior. It should be noted that this qualification was not requested when the fasteners were installed.

The scientific approach is to use two additional modeling to assess the fasteners behavior with seismic loading: At the fasteners scale, the concrete crack will be explicitly described by a discrete model and at the structure scale, a simplified model using generalized variables will be developed to represent the non-linear behavior of the fasteners. The parameters of this model will be defined by the discrete model. In this paper, only the part at the scale of the fasteners is presented.

In order to complete the experimental results, a numerical study is proposed in this paper to predict the behavior and the capacity of the fasteners under various loading. This study was done using a discrete element method, which allows to explicitly represent the cracks induced by the seismic event and the associated mechanisms (initiation, propagation, closure and unilateral effect, friction). After a brief description of the discrete model, the new meshing procedure, taking into account complex geometries, is presented. Then, numerical results obtained in 2D and 3D for static loads and carried out on headed stud are discussed. Finally, they are compared against experimental data. The discussion focuses on the capacity and the limitation of a 2D numerical model, to predict the behavior of fasteners and the necessity to move to a 3D modeling.

Keywords: Concrete, Fastening, Discrete model, Friction, Contact.

1. Introduction

In structural and construction applications in general, mechanical anchors are used to ensure the connection between different structural elements, allowing the transfer of external loads toward base materials.

Anchor systems are distinguished by two main factors. The first one is the installation method and the second is the way of transmission of external forces toward base material. Generally, Anchor systems are divided into two categories: cast in place and post-installed fasteners.

In order to extract the maximum potential and performance out of fastening elements, a deep knowledge of their behavior under static and dynamic loading is necessary.

Experimental tests and empirical formulas are used to give a clear understanding of anchors behavior. It is worth noting that these experiments do not question the physical state of these anchors or how they may adapt during loading.

Nowadays, numerical simulations have been frequently used in the field of fastening technology. Recently, they were even confirmed as a valuable complement for any experimental result. Moreover, simulations can offer a wide understanding and giving us a new perspective regarding the behavior of the studied material under different conditions. In addition, it can also reduce numbers, duration, and costs of experimental tests and help to estimate the seismic capacity of fasteners that couldn't be tested anymore

However, the behavior of fasteners is a very complex problem due to its non-linearity. That behavior can be affected by numerous factors (large deformations, the contact surface between the anchor and the base material, geometric non linearity...). Over the last few decades, numerical simulations have been conducted to study the behavior of fasteners under various types of loading for a better understanding of their failure mechanism. In this context, two-dimensional and three-dimensional model were used to solve anchors problems. The finite element method was the most employed method. This modeling aims to reproduce realistically the anchor-concrete behavior.

For example, (Ottosen, 1981) carried out some tests on a headed stud in order to determine the compressive strength of concrete using a nonlinear finite element method. (Cervenka and Pulk 1992) concentrated on the investigation of the behavior of headed anchors in concrete. In their research, they consider a perfect adhesion between anchors and concrete. In addition, (Long, 1996) evaluated the behavior of anchors by using commercial simulation software (ABAQUS). (Etze, 1997) studied the failure behavior of a pulled out anchor. the steel part was not modeled but it was replaced by an applied displacement at the upper surface of the anchor head. Furthermore, (Nienstedt and Mattner, 2001) used their own simulation tools to study the tensile behavior of mechanical fasteners. The investigation of the anchors performance under static and cyclic loads was conducted by (Boussa et al., 2007).

Nevertheless, most of these previous researches are based on a continuum mechanics that provides a global study without giving a fine description for the cracks process. For this reason, a discrete element model (DEM) is used instead of a finite element model (FEM) to represent a discontinuous material. For this purpose, DEAP (Discrete elements analysis program) is employed in this study to attain a clearer insight into the structural behavior. DEAP is a combination of a lattice model and a particular model. The lattice model has been proposed by (Hrennikof, 1941). The medium is represented by a group of beams or springs that can allow the transfer of force between the nodes. This model is unable to study the closure phenomena of cracks once they are opened.

Regarding the particular model, it was introduced by (Cundall, 1979) in order to study the behavior of granular materials. It discretizes the material to several particles and it models the interactions between particles.

In order to assess the behavior of these fasteners in seismic loading, the proposed scientific approach is to use two additional modeling: At the fasteners scale, the concrete crack will be explicitly described by a discrete model and at the structure scale, a simplified model using generalized variables will be developed to represent the non-linear behavior of the fasteners. The parameters of this model will be defined by the discrete model.

In this paper, the purpose is to demonstrate the capabilities of the beam-particular model (DEAP) for the analysis of the anchors behavior in the concrete during the setting and loading process.

The anchor and the concrete are presented through polygonal (polyhedral) particles in 2D (3D) linked together by beams that follow Euler-Bernoulli theory. Once two particles are not linked by a beam and are in contact, penetration and sliding are authorized between these two in order to represent the closure of cracks.

2. Model Description

DEAP is a particular discrete model originally developed by (Delaplace, 2008) and then extended by (Vassaux et al., 2015) and (Vassaux et al., 2016) to study the behavior of quasi-fragile materials, such as concrete. This discrete model represents a continuous medium by a finite number of rigid particles linked together through Euler-Bernoulli beams. Cohesion and contact efforts are the two types of interactions between the particles. The cohesive forces are provided by the set of beams joining the rigid particles by their centers.

These efforts take into account the cohesive behavior of the studied material. At this step, DEAP is similar to a lattice model. Then, the contact efforts are added to consider some mechanisms such as crack closure and aggregate interlocking. If two overlapping particles are not connected by a link or if the beam joining them initially was broken and removed during simulation, the particles will come in contact. Contact efforts, resulting from the penetration of these two particles and coulomb friction generated by the sliding caused between them, will be represented.

A brittle behavior is assigned to the set of beams used in the model. A breaking threshold P_{ij} is imposed and it depends on the axial strain and the flexion of the beam. When P_{ij} is reached, the breaking of the beam will be allowed (brittle fracture), it will be removed from the model and a microcrack will be formed on the common side of both particles previously connected by this beam. The breaking threshold used in DEAP is that proposed by (Herrmann and Roux, 1990) [eq. 1]:

$$P_{ij} = \left(\frac{\varepsilon_{ij}}{\varepsilon_{ij}^{cr}} \right)^2 + \left(\frac{|\theta_j - \theta_i|}{l_{ij}\theta_{ij}^{cr}} \right) \geq 1 \quad (1)$$

where ε_{ij}^{cr} and θ_{ij}^{cr} are the critical strain and the critical rotation of the beam i-j respectively.

Moreover, for a good representation of a quasi-brittle material such as concrete, a Weibull probability density function is introduced to the model to dissipate more energy and hence produce more microcracks in the material. More details are presented in (Delaplace, 2008), (Vassaux et al., 2015) and (Vassaux et al., 2016).




Figure 1. (a) Two cohesively linked particles (b) Rupture of link between the two particles (c) Two overlapping particles in contact

3. Mesh generation

For an anchor installed in concrete, a bad representation of the interface conducts to a bad behavior and performance. For this reason, the steel-concrete interface must be well reproduced to avoid the appearance of any frictional efforts much higher than the ones in the real case. In other words, on the macroscopic scale, two types of friction should be distinguished: Coulomb law friction and geometric friction related to roughness. The first type can be adjusted by modifying the parameters. In contrast, the friction associated with roughness completely depends on the geometric representation and it

cannot be modified. Hence, the need to generate correctly the contour of the surface.

For this purpose, a new meshing procedure has been developed and follows the VoroCrust method introduced by (Abdelkader et al., 2012). This surface meshing exhibits two initial steps: (1) The reconstruction of the surface bounding (2) the generation of random nodes within the contour. VoroCrust algorithm guarantees a good quality of meshing for the generation of a Voronoi mesh. Furthermore, ghost nodes, required for the meshing, located near the edges are generated automatically outside the geometry.

Meshing algorithm is the following:

1. Discretization and generation of a set of points P_i along the contour M of the geometry (fig. 2 (a)).
2. Definition of circles B_i centered at each sample P_i with a proper radius r_i (fig. 2(a)).
3. Definition of a set of points $U_i = UB_i$ (fig. 2(a)).
4. Random generation of points inside the geometry using the method Poisson Disk Sampling proposed by (Dunbar and Humphreys, 2006) (fig. 2(b)).
5. Delaunay triangulation calculation of the set of points (fig. 2(c)).
6. Computation of Voronoi polygons (fig. 2(d)).




Figure 2. (a) steps 1-2-3 (b) step 4 (c) step 5 (d) step 6

4. Numerical Simulation

The numerical simulation presented here was built using DEAP to model the pull-out behavior of a headed stud placed in the concrete. This simulation is performed assuming the plane constraints hypothesis.

At the anchor scale, discrete modeling is used to represent the degradation of the concrete. In the simulation, two distinct materials with different mechanical properties as well as different friction coefficients were taken into consideration (steel-steel, concrete-concrete, steel-concrete). Figure 3 shows the discrete model of the anchor system. A pull-out test applied to a headed stud of type M20*160 (20 mm in diameter and 160 mm in length) is investigated. The geometry is generated using the meshing procedure presented in section 3. Horizontal and vertical displacements are blocked at a distance equal to $2 \cdot h_{ef}$ from the center axis of anchor to represent the support installed above the concrete during the experimental tests.





Figure 3. Model of anchor system

4.1. Simulation results

Figure 4 illustrates the displacement field of the anchor subjected to an applied displacement greater than the recommended one during the pull-out process. A concrete cone failure is obtained numerically of dimensions very close to that of the experiment test (189*152*100 vs 185*161*100 mm³ respectively). On the other hand, quantitatively, the resistance obtained is very far from the real resistance of the anchor. This difference might be due to the inability of the plane constraints hypothesis to solve this type of problem.

4.2. Comparison with FE model (CAST3M)

This part aims to know whether to stay on DEAP2D or switch to a 3D version. For this purpose, a comparison was done in this section between DEAP and the finite element code CAST3M. The same geometry and the same boundary conditions were reproduced using CAST3M. Elastic behavior is assigned to anchor and damage model of (Mazars,1984) is adopted to concrete to take into account the degradation of the material and the development of micro-cracks. Three models have been studied: plane constraints simulations, axisymmetric simulations and three-dimensional model. In this study, adherence was applied between the screw head and the concrete. A spacing are assumed between the rod of the screw and the drilled hole. For the plane constraints simulation, the behavior and the maximal effort of the anchorage are very far from the experimental results. In contrast, in axisymmetric and three-dimensional simulations, the stiffness and the effort obtained numerically are close to that obtained experimentally with a concrete cone failure. Therefore, the hypothesis of plane constraints is not valid for studying anchor behavior. This result was expected given the symmetries of the problem. It is important to note that axisymmetric conditions can be used for this specific problem but the classical loadings undergone by an anchor do not necessarily present this symmetry (especially in the case of shear loading).



(a)



(b)

Figure 4. Concrete cone failure (a) DEAP (b) experimental tests




Figure 5. FE model for anchor system (a) in 2D (b) in 3D

5. Conclusions and perspectives

Good knowledge of the behavior of anchors installed in concrete is required for a safe design of anchors in structures. The two-dimensional modeling of an anchor system using a headed stud has been conducted under static tension loads. In this paper, a discrete model analysis is used for this aim. Experimental results carried out by the CSTB were chosen to be compared with the numerical simulation.

The following conclusions can be drawn from this study:

- The two-dimensional modeling based on the constraints plane hypothesis represents well the failure mechanisms. On the other side, it has a limitation on the prediction of the anchor's capacity.
- Axisymmetric simulations using a finite element program are compatible with the experimental tests. A concrete cone failure occurs and the model can reproduce the pull-out behavior of anchors. But those simulations are limited to specific cases.
- Concerning the three-dimensions, the results show compatibility with the experimental pull-out tests.

For this reason, a 3D version of DEAP will be developed in the future for a sound understanding of anchor applications under static and cyclic loads.

Reference

- A. Abdelkader, Ch. Bajaj, M. Ebeida, A. Mahmoud, S. Mitchell, J. Owens, and A. Rushdi. Sampling conditions for conforming voronoi meshing by the vorocrust algorithm, 2018.
- A. Delaplace. Modélisation discrète appliquée au comportement des matériaux et des structures. mémoire d'habilitation à diriger des recherches de l'école normale supérieure de cachan, 2008.
- A. Hrennikoff, Solution of problems of elasticity by the framework method, J. Appl. Mech. 8 (4) (1941) 169-175.
- D. Dunbar and G. Humphreys, A spatial data structure for fast Poisson-Disk-Sample generation, ACM Transactions on Graphics, Volume 25 Issue 3, July 2006, Pages 503-508.
- G. Etse. Finite element analysis of failure response behavior of anchor bolts in concrete. nuclear engineering and design 179, 245-252, 1998.
- H. Boussa, A. Si Chaib, H. Ung Quoc, G. Mounajednd C. La Borderie, Finite element modeling of anchor subjected to static and cyclic load, 2007.
- H.J. Herrmann and S. Roux. Statistical models for the fracture of disordered media. Elsevier, 1990.
- J. Nienstedt and R. Mattner. Three-dimensional modeling of anchoring systems in concrete, fracture mechanics of concrete structures, de borst et al, 2001 swets and zeitlinger, lisse, isbn 90 2651 825 0, 2001.
- J. Mazars, Application de la mécanique de l'endommagement au comportement non linéaire et à la rupture du béton de structure, PhD. Thesis, Paris VI University, 1984. 27.
- M. Vassaux. Comportement mécanique des matériaux quasi-fragiles sous sollicitations cycliques : de l'expérimentation numérique au calcul de structures, thèse de doctorat, ens cachan, 2015
- M. Vassaux, C. Oliver-Leblond, B. Richard, and F. Ragueneau. Beam-particle approach to model cracking and energy dissipation in concrete: Identification strategy and validation, cement and concrete composites 70 (2016) 1-14, 2016.
- N.S. Ottosen. Nonlinear finite element analysis of pull-out test. journal of the structural division, asce, 1981, vol. 107, n° 4, pp. 591-603, 1981.
- P.A. Cundall, O.D.L. Strack, A discrete numerical model for granular assemblies, Geotechnique 29 (1979) 47-60.
- S. Long. Validation de la modélisation par éléments finis en grandes déformations de l'ensemble "cheville-douille-béton". diplôme d'études approfondies de mécanique: Institut national des sciences appliquées de lyon, 1996. 95 p., 1996.
- V. Cervenka and R. Pulk. Computer models of concrete structures. structural engineering international 2/92, iabse, 1992, vol. 2, n° 2, pp. 103-107, 1992.